

BOND LAYER FOR SILICON-CONTAINING SUBSTRATES

TECHNICAL FIELD

[0001] The disclosure relates to coatings for superalloy substrates, ceramic substrates, or ceramic matrix composite substrates.

BACKGROUND

[0002] Components of high-temperature mechanical systems, such as, for example, gas-turbine engines, operate in severe environments. For example, the high-pressure turbine blades, vanes, blade tracks and blade shrouds exposed to hot gases in commercial aeronautical engines may experience metal surface temperatures of about 1000°C, with short-term peaks as high as 1100°C.

[0003] Components of high-temperature mechanical systems may include a Ni- or Co-based superalloy substrate, a ceramic substrate, or a ceramic matrix composite (CMC) substrate. Some ceramics or CMCs possess excellent high temperature mechanical, physical and chemical properties, and may allow gas turbine engines to operate at higher temperatures than gas turbine engines having superalloy components.

SUMMARY

[0004] The disclosure describes an article including a substrate and a coating that includes a bond layer comprising silicon metal (e.g., free silicon) and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride. The coating also may include an overlying layer including at least one oxide. Transition metal carbides, transition metal borides, and transition metal nitrides may have a different coefficient of thermal expansion than silicon metal. For example, transition metal carbides and transition metal borides may have CTEs between about 5 parts per million per degree Celsius (ppm/°C) and about 8 ppm/°C, and transition metal nitrides may have CTEs of about 9 ppm/°C. By mixing silicon metal and at least one of a transition metal carbide, a transition

metal boride, or a transition metal nitride, the CTE of the bond layer may be increased to more closely match the CTE of the substrate, the CTE of the overlying layer, or both.

[0005] In some examples, an article may include a substrate and a coating on the substrate. In accordance with some of these examples, the coating may include a bond layer and an overlying layer comprising at least one oxide. In some examples, the bond layer includes silicon metal and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride.

[0006] In some examples, a method may include forming a bond layer including silicon metal and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride on a substrate and forming an overlying layer comprising an oxide on the bond layer.

[0007] The details of one or more examples are set forth in the accompanying drawings and the description below. Other features, objects, and advantages will be apparent from the description and drawings, and from the claims.

BRIEF DESCRIPTION OF DRAWINGS

[0008] FIG. 1 is a conceptual and schematic diagram illustrating an example article including a substrate and a coating, which includes a bond layer and an overlying layer.

[0009] FIG. 2 is a flow diagram illustrating an example technique for forming article including a bond layer, which includes silicon metal and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride, and an overlying layer on the bond layer.

[0010] FIG. 3 is a flow diagram illustrating an example technique for forming bond layer using a slurry based processing technique followed by silicon melt infiltration.

DETAILED DESCRIPTION

[0011] The disclosure describes an article including a substrate and a coating that includes a bond layer including silicon metal (e.g., free silicon) and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride.

The coating also may include an overlying layer including at least one oxide. In some examples, ceramic or ceramic matrix composite (CMC) substrates may include silicon metal or a silicon-containing material, such as silicon carbide or silicon nitride. Substrates including silicon metal or a silicon-containing material may be vulnerable to chemical attack by species present in the cooling fluid, including impurities. For example, water vapor may chemically attack a ceramic or CMC substrate including silicon to form silicon hydroxide species at the temperatures experienced by the ceramic or CMC substrate and damage the ceramic or CMC substrate.

[0012] To reduce or substantially prevent damage to the ceramic or CMC substrate, the ceramic or CMC substrate may be coated with an environmental barrier coating (EBC), which reduces or substantially prevents recession of the CMC substrate by reaction with water vapor. In some examples, a bond layer is provided between the substrate and the EBC and may enhance adherence of the EBC to the substrate. Because the EBC may be permeable to some gaseous species (e.g., oxygen), the bond layer may include a material that forms a relatively stable oxide, such as silicon metal. To reduce stresses caused by differential thermal expansion and contraction during temperature changes, the ceramic or CMC substrate, the bond layer, and the EBC may have relatively similar coefficients of thermal expansion (CTE).

[0013] Silicon oxidizes to a stable silicon oxide and has a CTE that is relatively close to that of some EBCs (e.g., EBCs that include rare earth disilicate). The CTEs of silicon metal and rare earth disilicate are about 4 ppm/°C. However, some CMCs may have a CTE different than that of silicon metal. For example, SiC-SiC CMCs may have a CTE of between about 4.3 ppm/°C and about 5.5 ppm/°C. Similarly, EBCs that include rare earth monosilicates may have a CTE greater than about 6.0 ppm/°C. The difference in CTEs between the substrate and silicon metal and the EBC and silicon metal may lead to increased stress at the interfaces, which may lead to mechanical failure of the coating.

[0014] Transition metal carbides, transition metal borides, and transition metal nitrides may have a different CTE than silicon metal. For example, transition

metal carbides and transition metal borides may have CTEs between about 5 ppm/°C and about 8 ppm/°C, and transition metal nitrides may have CTEs of about 9 ppm/°C. By mixing silicon metal and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride, the CTE of the bond layer may be increased to more closely match the CTE of the substrate, the CTE of the overlying layer, or both. This may reduce stress at the interfaces between the substrate and the bond layer, between the bond layer and the overlying layer, or both, during thermal cycling of the article. In some examples, the addition of the transition metal carbide, the transition metal boride, the transition metal nitride, or combinations thereof may result in formation of a second phase within the bond layer, which may improve creep strength of the bond layer compared to a bond layer including a single phase.

[0015] Additionally or alternatively, the addition of the transition metal carbide, the transition metal boride, the transition metal nitride, or combinations thereof may improve oxidation resistant of the bond layer compared to a bond layer including only silicon metal. For example, the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride may be incorporated into the thermally grown silicon oxide, which may improve adherence of the thermally grown silicon oxide to the bond layer, decrease oxygen diffusivity through the thermally grown silicon oxide (which reduces the rate of oxidation of the remaining bond layer), or both.

[0016] FIG. 1 is a conceptual and schematic diagram illustrating an example article 10 including a substrate 12 and a coating 14, which includes a bond layer 16 and an overlying layer 18. Bond layer 16 may include a mixture of silicon metal and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride.

[0017] Substrate 12 may be a component of a high temperature mechanical system. For example, substrate 12 may be a blade track, an airfoil, a blade, a combustion chamber liner, or the like. In some examples, substrate 12 include a ceramic, a ceramic matrix composite (CMC), or a metal alloy that includes Si. In

some examples, substrate 12 may include a silicon based material, such as silicon based ceramic, a silicon based CMC, or a silicon based alloy.

[0018] In some examples in which substrate 12 includes a ceramic, the ceramic may be substantially homogeneous. In some examples, a substrate 12 that includes a ceramic includes, for example, a Si-containing ceramic, such as SiO₂, silicon carbide (SiC) or silicon nitride (Si₃N₄); Al₂O₃; aluminosilicate (e.g., Al₂SiO₅); or the like. In other examples, substrate 10 includes a metal alloy that includes Si, such as a molybdenum-silicon alloy (e.g., MoSi₂) or a niobium-silicon alloy (e.g., NbSi₂).

[0019] In examples in which substrate 12 includes a CMC, substrate 12 includes a matrix material and a reinforcement material. The matrix material includes a ceramic material, such as, for example, SiC, Si₃N₄, Al₂O₃, aluminosilicate, SiO₂, or the like. The CMC further includes a continuous or discontinuous reinforcement material. For example, the reinforcement material may include discontinuous whiskers, platelets, or particulates. As other examples, the reinforcement material may include a continuous monofilament or multifilament weave. In some examples, the reinforcement material may include SiC, Si₃N₄, Al₂O₃, aluminosilicate, SiO₂, or the like. In some examples, substrate 12 includes a SiC-SiC ceramic matrix composite.

[0020] Substrate 12 defines a surface 20 on which coating 14 is disposed. In the example illustrated in FIG. 1, coating 14 includes a bond layer 16 and an overlying layer 18.

[0021] Overlying layer 18 may include, for example, an environmental barrier coating (EBC), a thermal barrier coating (TBC), a calcia-magnesia-aluminosilicate (CMAS)-resistant layer, or the like. In some examples, a single overlying layer 18 may perform two or more of these functions. For example, an EBC may provide environmental protection, thermal protection, and CMAS-resistance to substrate 12. In some examples, instead of including a single overlying layer 18, article 10 may include a plurality of overlying layers, such as at least one EBC layer, at least one TBC layer, at least one CMAS-resistant layer, or combinations thereof.

[0022] An EBC layer may include at least one of a rare earth oxide, a rare earth silicate, an aluminosilicate, or an alkaline earth aluminosilicate. For example, an

EBC layer may include mullite, barium strontium aluminosilicate (BSAS), barium aluminosilicate (BAS), strontium aluminosilicate (SAS), at least one rare earth oxide, at least one rare earth monosilicate (RE_2SiO_5 , where RE is a rare earth element), at least one rare earth disilicate ($\text{RE}_2\text{Si}_2\text{O}_7$, where RE is a rare earth element), or combinations thereof. The rare earth element in the at least one rare earth oxide, the at least one rare earth monosilicate, or the at least one rare earth disilicate may include at least one of Lu (lutetium), Yb (ytterbium), Tm (thulium), Er (erbium), Ho (holmium), Dy (dysprosium), Tb (terbium), Gd (gadolinium), Eu (europium), Sm (samarium), Pm (promethium), Nd (neodymium), Pr (praseodymium), Ce (cerium), La (lanthanum), Y (yttrium), or Sc (scandium). In some examples, the at least one rare earth oxide includes an oxide of at least one of Yb, Y, Gd, or Er.

[0023] In some examples, an EBC layer may include at least one rare earth oxide and alumina, at least one rare earth oxide and silica, or at least one rare earth oxide, silica, and alumina. In some examples, an EBC layer may include an additive in addition to the primary constituents of the EBC layer. For example, an EBC layer may include at least one of TiO_2 , Ta_2O_5 , HfSiO_4 , an alkali metal oxide, or an alkali earth metal oxide. The additive may be added to the EBC layer to modify one or more desired properties of the EBC layer. For example, the additive components may increase or decrease the reaction rate of the EBC layer with CMAS, may modify the viscosity of the reaction product from the reaction of CMAS and the EBC layer, may increase adhesion of the EBC layer to bond layer 16, may increase or decrease the chemical stability of the EBC layer, or the like.

[0024] In some examples, the EBC layer may be substantially free (e.g., free or nearly free) of hafnia and/or zirconia. Zirconia and hafnia may be susceptible to chemical attack by CMAS, so an EBC layer substantially free of hafnia and/or zirconia may be more resistant to CMAS attack than an EBC layer that includes zirconia and/or hafnia.

[0025] In some examples, the EBC layer may have a dense microstructure, a columnar microstructure, or a combination of dense and columnar microstructures. A dense microstructure may be more effective in preventing the infiltration of CMAS and other environmental contaminants, while a columnar microstructure

may be more strain tolerant during thermal cycling. A combination of dense and columnar microstructures may be more effective in preventing the infiltration of CMAS or other environmental contaminants than a fully columnar microstructure while being more strain tolerant during thermal cycling than a fully dense microstructure. In some examples, an EBC layer with a dense microstructure may have a porosity of less than about 20 vol. %, such as less than about 15 vol. %, less than 10 vol. %, or less than about 5 vol. %, where porosity is measured as a percentage of pore volume divided by total volume of the EBC layer.

[0026] In some examples, overlying layer 18 may include a TBC layer. The TBC layer may include, for example, yttria-stabilized zirconia (YSZ), zirconia stabilized by a single or multiple rare earth oxides, hafnia stabilized by a single or multiple rare earth oxides, zirconia-rare earth oxide compounds, such as $\text{RE}_2\text{Zr}_2\text{O}_7$ (where RE is a rare earth element), and hafnia-rare earth oxide compounds, such as $\text{RE}_2\text{Hf}_2\text{O}_7$ (where RE is a rare earth element). As described above, the TBC layer may be used as a single overlying layer 18 or may be used in combination with at least one other layer, such as an EBC layer.

[0027] Bond layer 16 is between substrate 12 and overlying layer 18. Bond layer 16 may include silicon metal and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride. Bond layer 16 may include silicon metal and at least one transition metal carbide; silicon metal and at least one transition metal boride; silicon metal and at least one transition metal nitride; silicon metal, at least one transition metal carbide, and at least one transition metal boride; silicon metal, at least one transition metal carbide, and at least one transition metal nitride; silicon metal, at least one transition metal boride, and at least one transition metal nitride; or silicon metal, at least one transition metal carbide, at least one transition metal boride, and at least one transition metal nitride. The transition metal may include, for example, Cr, Mo, Nb, W, Ti, Ta, Hf, or Zr. The at least one transition metal carbide may include at least one of Cr_3C_2 , Cr_7C_3 , Cr_{23}C_6 , Mo_2C , NbC , WC , TaC , HfC , or ZrC . The at least one transition metal boride may include at least one of TaB , TaB_2 , TiB_2 , ZrB_2 , HfB , or HfB_2 . The at least one transition metal nitride may include at least one of TiN , ZrN , HfN , Mo_2N , or TaN .

[0028] In some examples, bond layer 16 may include between about 40 volume percent (vol. %) and about 99 vol. % silicon metal and a balance of the at least one of a transition metal carbide or a transition metal boride. For example, bond layer 16 may include between 1 vol. % and about 60 vol. % of the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride, and a balance silicon metal and any additional constituents (such as silicon carbide). In some examples, bond layer 16 may include between about 1 vol. % and about 30 vol. %, or between about 5 vol. % and about 20 vol. % of the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride, and a balance silicon metal and any additional constituents (such as silicon carbide). The particular composition ranges may vary based on the CTE of the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride. Table 1 illustrates a series of example amounts of transition metal carbide and transition metal boride based on use of a single transition metal carbide or boride, a Yb₂Si₂O₇ EBC and a SiC/SiC composite substrate.

Table 1

	<u>Example Upper</u> <u>Bound</u> (vol. %)	<u>Example Value</u> (vol. %)	<u>Example Lower</u> <u>Bound</u> (vol. %)
Mo ₂ C	31	13	2
NbC	21	9	1
TaC	24	10	1
HfC	24	10	2
ZrC	23	10	2
TaB	18	7	1
TiB ₂	17	7	1
ZrB ₂	21	9	1
TiN	21	9	1
Mo ₂ N	11	4.8	0.6
ZrN	22	9.4	1.3

[0029] At least some transition metal carbides, at least some transition metal borides, and at least some transition metal nitrides may possess a CTE higher than that of silicon metal and are refractory. For example, at least some transition metal carbides, at least some transition metal borides, and at least some transition metal nitrides have a melting point that is greater than about 2000°C or even greater than about 3000°C.

[0030] In some examples, addition of the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride may not decrease the melting point of bond layer 16 more than about 50°C when compared to a bond layer including substantially only silicon metal. In other words, addition of the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride may not decrease the melting point of bond layer 16 to lower than about 1354°C (the melting point of silicon metal is about 1414°C). Thus, addition of the at least one of a transition metal carbide, a transition metal boride, or at least one transition metal nitride to silicon metal may not substantially reduce the temperature capability of bond layer 16 compared to a bond layer including substantially only silicon metal.

[0031] Transition metal carbides, transition metal borides, and transition metal nitrides may have a different CTE than silicon metal. For example, transition metal carbides and transition metal borides may have CTEs between about 5 ppm/°C and about 8 ppm/°C. By mixing silicon metal and a transition metal carbide, a transition metal boride, or both, the CTE of bond layer 16 may be increased to more closely match the CTE of substrate 12, the CTE of overlying layer 18, or both. This may reduce stress at the interfaces between substrate 12 and bond layer 16, between bond layer 16 and overlying layer 18, or both, during thermal cycling of article 10.

[0032] Transition metal carbides and transition metal borides may have CTE's between about 5 ppm/°C and about 8 ppm/°C, and transition metal nitrides may have CTEs of about 9 ppm/°C. As a comparison, silicides and some oxides have CTEs that are higher, such as between about 9 ppm/°C and about 13 ppm/°C.

Because transition metal carbides and transition metal borides may have a lower CTE than some silicides or oxides, a bond layer 16 having a selected CTE may include a greater concentration of transition metal carbides or transition metal borides than a bond layer having the same CTE and a silicide additive. In some examples, bond layer 16 may include between about 1 volume percent and about 90 volume percent of the at least one of a transition metal boride, a transition metal carbide, or a transition metal nitride. A higher concentration of the at least one of a transition metal boride, a transition metal carbide, or a transition metal nitride may allow greater modification of properties (e.g., reactivity, incorporation of the at least one of a transition metal boride, a transition metal carbide, or a transition metal nitride into a thermal oxide layer formed on a surface of bond layer 16, or the like) of bond layer 16.

[0033] Additionally or alternatively, the addition of the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride may improve oxidation resistant of bond layer 16 compared to a bond layer including only silicon metal. For example, the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride may be incorporated into the thermally grown silicon oxide, which may improve adherence of the thermally grown silicon oxide to the bond layer, decrease oxygen diffusivity through the thermally grown silicon oxide (which reduces the rate of oxidation of the remaining bond layer), or both.

[0034] In some examples, the addition of the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride may result in formation of a second phase within bond layer 16 (in addition to a first phase including silicon metal). In some examples, the first phase including silicon metal may be a substantially continuous phase. In some examples, the second phase including the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride may include a discrete phase within the substantially continuous first phase. A bond layer 16 including a first phase and a second phase may possess improved creep strength compared to some bond layers including a single phase.

[0035] In some examples, bond layer 16 includes silicon metal and at least one transition metal carbide, and the at least one transition metal carbide may be carbon deficient. In other words, the at least one transition metal carbide may include less carbon than the stoichiometric ratio. This may increase the reactivity of the transition metal carbide with silicon metal. In some examples, the transition metal carbide may react with silicon metal to form a ternary carbide including the transition metal, silicon metal, and carbon.

[0036] Article 10 may be formed using one or more technique, such as slurry deposition, plasma spraying, physical vapor deposition (PVD), or chemical vapor deposition (CVD). FIG. 2 is a flow diagram illustrating an example technique for forming article 10 including bond layer 16, which includes silicon metal and at least one of a transition metal carbide and a transition metal boride. The technique of FIG. 2 will be described with concurrent reference to article 10 of FIG. 1, although the technique of FIG. 2 may be used to form different articles, and article 10 of FIG. 1 may be formed using a different technique.

[0037] The technique of FIG. 2 includes forming bond layer 16 on surface 20 of substrate 12 (32). In some examples, bond layer 16 may be deposited on surface 20 of substrate using plasma spraying, PVD, or CVD. In other examples, bond layer 16 may be formed on surface of substrate 12 (32) using a slurry-based colloidal processing technique followed by silicon melt infiltration. FIG. 3 is a flow diagram illustrating an example technique for forming bond layer 16 using a slurry-based colloidal processing technique followed by silicon melt infiltration.

[0038] The technique of FIG. 3 may include depositing a layer comprising a transition metal using a slurry based processing technique (42). In some examples, the slurry based processing technique may include tape casting. In tape casting, a slurry including the transition metal may be formed. The slurry may include a solvent (e.g., water, ethanol, isopropyl alcohol, methyl ethyl ketone, toluene, or the like) and transition metal particles. In some examples, the slurry additionally may include a binder (e.g. polyethylene glycol, acrylate co-polymers, latex co-polymers, polyvinyl pyrrolidone co-polymers, polyvinyl butyral, or the like), a dispersant (e.g., ammonium polyacrylate, polyvinyl butyral, a phosphate ester, polyethylene imine, BYK® 110 (available from Byk USA, Inc., Wallingford

Connecticut), or the like), or the like. The slurry then may be formed into a layer (a tape) on a liner and at least partially dried to remove at least some of the solvent. The resulting tape includes the transition metal and may be applied to a ceramic matrix composite or a ceramic matrix composite preform as part of forming bond layer 16 on surface 20 of substrate 12 (32).

[0039] In other examples, forming bond layer 16 on surface 20 of substrate 12 (32) may include depositing the transition metal from a slurry including a solvent and transition metal particles. In some examples, the slurry additionally may include a binder, a dispersant, or the like. The slurry may be applied on surface 20 of substrate 12 using, for example, spray coating, spin coating, dip coating, brushing, or the like.

[0040] In some examples, the slurry deposited on surface 20 of substrate 12 or used to form the tape may additionally include silicon carbide particles. The silicon carbide particles may affect the properties of bond layer 16. For example, the silicon carbide particles may modify oxidation resistance of bond layer 16, modify chemical resistance of bond layer 16, influence the CTE of bond layer 16, improve silicon melt infiltration into bond layer 16, or the like. In some examples, the slurry may include sufficient silicon carbide particles so that bond layer 16 includes between about 1 vol. % and about 40 vol. % silicon carbide, such as between about 1 vol. % and about 20 vol. % silicon carbide, or between about 5 vol. % and about 40 vol. % silicon carbide, or between about 5 vol. % and about 20 vol. % silicon carbide.

[0041] The size of the transition metal particles may be selected at least partially based on the size of particles that facilitate the subsequent reaction with a carbon or boron source to form the transition metal carbide, transition metal boride, or both. For example, larger transition metal particles may increase the time needed to substantially fully (e.g., fully or nearly fully) react the transition metal particles with the carbon or boron source to form the transition metal carbide, transition metal boride, or both throughout substantially the full volume of the particles. Conversely, small transition metal particles may decrease the time needed to substantially fully (e.g., fully or nearly fully) react the transition metal particles with the carbon or boron source to form the transition metal carbide, transition

metal boride, or both throughout substantially the full volume of the particles. In some examples, the transition metal particles may have a diameter between 1 μm and 20 μm , such as between about 1 μm and about 10 μm .

[0042] Regardless of whether the transition metal is applied to surface 20 using tape casting, slurry deposition, or another slurry-based colloidal processing technique, in some examples, the transition metal may be applied to a surface of a ceramic matrix composite preform. For example, a ceramic matrix composite preform may include a fibrous reinforcement infiltrated with a slurry including one or more constituents of the matrix material of the ceramic matrix composite. In some examples, the fibrous reinforcement may include silicon carbide (SiC) fibers and the slurry may include silicon carbide particles or a carbon source. The slurry may be infiltrated throughout pores defined between the fibrous reinforcement material, and may be dried or reacted to form a gel, which may help retain the one or more constituents of the matrix material within the ceramic matrix composite preform.

[0043] The technique of FIG. 3 also may include forming at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride by exposing the layer including the transition metal to a gaseous source of at least one of carbon, boron, or nitrogen (44). For example, to form a transition metal carbide, the layer including the transition metal may be heated and exposed to a gas including a carbon source, such as methane, carbon monoxide, or the like. The layer including the transition metal may be heated and exposed to the gas including the carbon source for a time sufficient to result in formation of transition metal carbide substantially throughout the transition metal particles and the layer.

[0044] Similarly, to form a transition metal boride, the layer including the transition metal may be heated and exposed to a gas including a boron source, such as gaseous boron trichloride, or the like. To form a transition metal nitride, the layer including the transition metal may be heated and exposed to a gas including a nitrogen source, such as nitrogen, gaseous ammonia, or the like. The layer including the transition metal may be heated and exposed to the gas including the boron source or the nitrogen source for a time sufficient to result in formation of

transition metal boride or transition metal nitride substantially throughout the transition metal particles and the layer. By forming the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride on the surface of the article by exposing a layer including a transition metal to at least one of a gaseous carbon source, a gaseous boron source, or a gaseous nitrogen source, in some examples, the resulting at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride may be substantially pure (e.g., pure or nearly pure).

[0045] After formation of at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride, the technique of FIG. 3 further includes infiltrating the porous substrate precursor and the porous layer including the at least one of the transition metal carbide, the transition metal boride, or the transition metal nitride with molten silicon metal or molten silicon alloy(46).

[0046] In other examples, rather than applying the transition metal in a layer from a slurry, borodizing, nitridizing, or carbonizing the transition metal, and melt infiltrating the layer with silicon metal, bond layer 16 may be formed by depositing the transition metal carbide, boride, or nitride and silicon metal from a slurry. The slurry may include particles of silicon metal or a silicon alloy and particles of at least one transition metal carbide, boride, or nitride. In some examples, the slurry additionally may include a binder, a dispersant, or the like, such as any of those described above. The slurry may be applied on surface 20 of substrate 12 using, for example, spray coating, spin coating, dip coating, brushing, or the like. The slurry then may be dried to remove excess solvent and sintered to form bond layer 16.

[0047] Returning to FIG. 2, the technique may additionally include forming overlying layer 18 on bond layer 16 (34). As described above, overlying layer 18 may include, for example, an EBC, CMAS-resistant layer, or the like. Overlying layer 18 may be formed using, for example, a thermal spraying technique, such as plasma spraying, CVD, PVD, electron beam PVD (EB-PVD), directed vapor deposition (DVD), a slurry-based coating technique, or the like.

[0048] Various examples have been described. These and other examples are within the scope of the following claims.

CLAIMS:

1. An article comprising:
a substrate; and
a coating on the substrate, wherein the coating comprises a bond layer and an overlying layer comprising at least one oxide, and wherein the bond layer comprises silicon and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride.
2. The article of claim 1, wherein the bond layer comprises silicon and at least one transition metal carbide.
3. The article of claim 2, wherein the at least one transition metal carbide comprises at least one of Cr_3C_2 , Cr_7C_3 , Cr_{23}C_6 , Mo_2C , NbC , WC , TaC , HfC , or ZrC .
4. The article of claim 1, wherein the bond layer comprises silicon and at least one transition metal boride.
5. The article of claim 4, wherein the at least one transition metal boride comprises at least one of TaB , TaB_2 , TiB_2 , ZrB_2 , HfB , HfB_2 .
6. The article of claim 1, wherein the bond layer comprises silicon and at least one transition metal nitride.
7. The article of claim 6, wherein the at least one transition metal nitride comprises at least one of TiN , ZrN , HfN , Mo_2N , or TaN .
8. The article of claim 1, wherein the bond layer comprises silicon, at least one transition metal carbide, and at least one transition metal boride.

9. The article of claim 8, wherein the at least one transition metal carbide comprises at least one of Cr_3C_2 , Cr_7C_3 , Cr_{23}C_6 , Mo_2C , NbC , WC , TaC , HfC , or ZrC , and wherein the at least one transition metal boride comprises at least one of TaB , TaB_2 , TiB_2 , ZrB_2 , HfB , HfB_2 .

10. The article of claim 1, wherein the bond layer comprises silicon, at least one transition metal carbide, and at least one transition metal nitride.

11. The article of claim 10, wherein the at least one transition metal carbide comprises at least one of Cr_3C_2 , Cr_7C_3 , Cr_{23}C_6 , Mo_2C , NbC , WC , TaC , HfC , or ZrC , and wherein the at least one transition metal nitride comprises at least one of TiN , ZrN , HfN , Mo_2N , or TaN .

12. The article of claim 1, wherein the bond layer comprises silicon, at least one transition metal boride, and at least one transition metal nitride.

13. The article of claim 12, wherein the at least one transition metal boride comprises at least one of TaB , TaB_2 , TiB_2 , ZrB_2 , HfB , HfB_2 , and wherein the at least one transition metal nitride comprises at least one of TiN , ZrN , HfN , Mo_2N , or TaN .

14. The article of claim 1, wherein the bond layer comprises silicon, at least one transition metal carbide, at least one transition metal boride, and at least one transition metal nitride.

15. The article of claim 14, wherein the at least one transition metal carbide comprises at least one of Cr_3C_2 , Cr_7C_3 , Cr_{23}C_6 , Mo_2C , NbC , WC , TaC , HfC , or ZrC , wherein the at least one transition metal boride comprises at least one of TaB , TaB_2 , TiB_2 , ZrB_2 , HfB , HfB_2 , and wherein the at least one transition metal nitride comprises at least one of TiN , ZrN , HfN , Mo_2N , or TaN .

16. The article of any one of claims 1 to 15, wherein the bond layer comprises between about 40 volume percent and about 99 volume percent silicon, and a balance of the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride.
17. The article of any one of claims 1 to 16, wherein the bond layer comprises a first phase comprising silicon and a second phase comprising the at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride.
18. The article of claim 17, wherein the first phase is a substantially continuous phase.
19. The article of any one of claims 1 to 18, wherein the overlying layer comprising at least one oxide comprises at least one of a rare earth oxide, a rare earth silicate, or an alkaline earth aluminosilicate.
20. The article of any one of claims 1 to 19, wherein the substrate comprises a silicon-based substrate.
21. The article of claim 20, wherein the substrate comprises silicon carbide.
22. The article of claim 21, wherein the substrate comprises a silicon carbide-silicon carbide ceramic matrix composite.
23. A method comprising:
forming a bond layer comprising silicon and at least one of a transition metal carbide, a transition metal boride, or a transition metal nitride on a substrate;
and
forming an overlying layer comprising an oxide on the bond layer.

24. The method of claim 23, wherein the bond layer comprises silicon and the transition metal carbide, and wherein forming the bond layer comprises:

depositing a layer comprising a transition metal from a slurry on a bulk surface of a porous substrate preform;

forming the transition metal carbide by exposing the layer including the transition metal to a carbon-containing gas to form a porous layer including the transition metal carbide; and

infiltrating the porous substrate preform and the porous layer including the transition metal carbide with molten silicon to form an article including a ceramic matrix composite substrate and the bond layer comprising silicon and the transition metal carbide.

25. The method of claim 24, wherein:

the transition metal comprises at least one of Cr, Mo, Nb, W, Ti, Ta, Hf, or Zr;

the carbon-containing gas comprises at least one of methane or carbon monoxide; and

the transition metal carbide comprises at least one of Cr_3C_2 , Cr_7C_3 , Cr_{23}C_6 , Mo_2C , NbC , WC , TaC , HfC , and ZrC .

26. The method of claim 23, wherein the bond layer comprises silicon and the transition metal boride, and wherein forming the bond layer comprises:

depositing a layer comprising a transition metal from a slurry on a bulk surface of a porous substrate preform;

forming the transition metal boride by exposing the layer including the transition metal to a boron-containing gas to form a porous layer including the transition metal boride; and

infiltrating the porous substrate preform and the porous layer including the transition metal boride with molten silicon to form an article including a ceramic matrix composite substrate and the bond layer comprising silicon and the transition metal boride.

27. The method of claim 26, wherein:
the transition metal comprises at least one of Ta, Ti, Zr, or Hf;
the boron-containing gas comprises boron trichloride; and
the transition metal boride comprises at least one of TaB, TaB₂, TiB₂, ZrB₂, HfB, or HfB₂.
28. The method of claim 23, wherein the bond layer comprises silicon and the transition metal nitride, and wherein forming the bond layer comprises:
depositing a layer comprising a transition metal from a slurry on a bulk surface of a porous substrate preform;
forming the transition metal nitride by exposing the layer including the transition metal to a nitrogen-containing gas to form a porous layer including the transition metal nitride; and
infiltrating the porous substrate preform and the porous layer including the transition metal nitride with molten silicon to form an article including a ceramic matrix composite substrate and the bond layer comprising silicon and the transition metal nitride.
29. The method of claim 26, wherein:
the transition metal comprises at least one of Ti, Zr, Hf, Mo, or Ta;
the nitrogen-containing gas comprises N₂ or ammonia; and
the transition metal nitride comprises at least one of TiN, ZrN, HfN, MoN, or TaN.
30. The method of any one of claims 24 to 29, wherein depositing the layer comprising the transition metal from the slurry comprises depositing a layer comprising a transition metal and silicon carbide from a slurry.
31. The method of claim 23, wherein forming the bond layer utilizes at least one of plasma spraying, physical vapor deposition, or chemical vapor deposition.