

ABSTRACT

Spherical silica particles excellent in fluidity, a resin composite composition containing the spherical silica particles, and a method of production of the same, that is, spherical silica particle
5 wherein, among the 1 μm or more and 30 μm or less particles detected by a Coulter counter, a number frequency of 3 μm or more particles is 300 ppm or more and 50000 ppm or less, a number frequency of 5 μm or more particles is 100 ppm or less, and a specific surface area by the BET method is 5.0 m^2/g or more and 20 m^2/g or less, a resin composite composition containing the spherical silica particles, and a method of production of the same.

10

[No figure]