

9

Description

Copending Applications

Copending EP—A1—0,143,342 and copending EP—A1—0,143,343, both filed on even date herewith, disclose and claim subject matter which is related to the present application.

Technical Field

The present invention relates to wear and corrosion resistant coatings and to a method for producing such coatings. More particularly, the invention relates to a new family of W-Co-Cr-C coatings having improved strength and wear resistance.

Background Art

Coatings of W-Co-Cr-C are used in those applications where both superior wear and corrosion resistance are required. A typical composition for these coatings comprises about 8 to 10 weight percent cobalt, about 3 to 4 weight percent chromium, about 4.5 to 5.5 weight percent carbon and the balance tungsten. These coatings can be successfully applied to various substrates, e.g., iron base alloy substrates, using known thermal spray techniques. Such techniques include, for example, detonation gun (D-Gun) deposition as disclosed in U.S. Patent Nos. 2,714,563 and 2,950,867, plasma arc spray as disclosed in U.S. Patent Nos. 2,858,411 and 3,016,447, and other so-called "high velocity" plasma or "hypersonic" combustion spray processes.

Although coatings of W-Co-Cr-C have been employed successfully in many industrial applications over the past decade or more, there is an ever increasing demand for even better coatings having superior strength and wear resistance.

It is also desirable to deposit these coatings at faster deposition rates than heretofore possible and thereby coat the substrates more economically. A problem with fast deposition rates, however, has been that high residual stresses tend to build up inside the coating. Unless the coating has sufficiently high strength to resist these stresses, the coating may crack and even spall.

In EP—A1—0,143,342, filed on even date herewith, there is disclosed a new family of W-Co-Cr-C coatings containing a high content of cobalt and having an improved strength. These coatings are ideally suited for use on gate valves, for example, in the petrochemical industry for handling highly corrosive fluids under high hydraulic pressures. Although these coatings are tough and strong enough to resist the high residual stresses that develop as a result of fast deposition rates, the wear resistance of the coatings is not better than that of conventional coatings.

As is generally known, coatings of W-Co-Cr-C derive their wear resistance from the presence of complex carbides of W, Co, and Cr. Corrosion resistance is derived, on the other hand, from the presence of chromium. The chromium content is

actually a compromise between that which is ordinarily required for corrosion resistance and that which interferes with or diminishes the wear and mechanical properties of the coating.

Summary of the Invention

It has now been surprisingly discovered in accordance with the present invention that, contrary to expectations, a higher chromium content can be employed if properly balanced with that of both carbon and cobalt to achieve improved coatings with low wear rates and capable of being deposited at much higher deposition rates without cracking or spalling.

A coating composition applied to a substrate by a thermal spray process in accordance with the present invention consists of from 4.0 to 10.5 weight percent cobalt, from 5.0 to 11.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

A method for coating a substrate wherein a powdered coating material is suspended within a high temperature, high velocity gaseous stream and heated to a temperature at least close to the melting point thereof, said gaseous stream being directed against a surface of said substrate to deposit said powdered coating material and form a coating thereon, in conformity with the present invention is characterized in that, a powdered coating material having a composition such that the coating deposited onto said substrate consists of from 4.0 to 10.5 weight percent cobalt, from 5.0 to 11.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities, is used.

A powdered coating composition for applying a high strength, wear and corrosion resistant coating onto a substrate by a thermal spray process, in accordance with the present invention consists of from 8.0 to 11.0 weight percent cobalt, from 8.0 to 11.0 weight percent chromium, from 4.0 to 5.5 weight percent carbon and the balance tungsten and incidental impurities.

Description of the Preferred Embodiments

The coatings of the present invention can be applied to a substrate using any conventional thermal spray technique. The preferred method of applying the coating is by detonation gun (D-Gun) deposition. A typical D-Gun consists essentially of a water-cooled barrel which is several 30 cm (feet) long with an inside diameter of about 25 mm (1 inch). In operation, a mixture of oxygen and a fuel gas, e.g., acetylene, in a specified ratio (usually about 1:1) is fed into the barrel along with a charge of powder to be coated. The gas is then ignited and the detonation wave accelerates the powder to about 730 m/s (2400 ft./sec.) while heating the powder close to or above its melting point. After the powder exits the barrel, a pulse of nitrogen purges the barrel and readies the system for the next detonation. The cycle is then repeated many times a second.

The D-Gun deposits a circle of coating on the

5

10

15

20

25

30

35

40

45

50

55

60

65

substrate with each detonation. The circles of coating are about 25 mm (1 inch) in diameter and a few microns (ten thousandths of an inch) thick. Each circle of coating is composed of many overlapping microscopic splats corresponding to the individual powder particles. The overlapping splats interlock and mechanically bond to each other and the substrate without substantially alloying at the interface thereof. The placement of the circles in the coating deposition are closely controlled to build-up a smooth coating of uniform thickness and to minimize substrate heating and residual stresses in the applied coating.

The powder used in producing the coating of the present invention is chosen to achieve the particular coating composition desired using a given set of deposition parameters. Preferably, the oxygen-fuel gas mixture ratio employed in the D-Gun process is maintained at about 1.0. It is also possible to use other operating conditions with a D-Gun and still obtain the desired coating composition if the powder composition is adjusted accordingly. Moreover, other powder compositions may be used with other thermal spray coating devices to compensate for changes in composition during deposition and obtain the desired coating composition of the present invention.

The powders used in the D-Gun for applying a coating according to the present invention are preferably cast and crushed powders. However, other forms of powder such as sintered powders can also be used. Generally, the size of the powders should be about 0.044 mm or smaller (-325 mesh). Powders produced by other methods of manufacture and with other size distributions may be used according to the present invention with other thermal spray disposition techniques if they are more suited to a particular spray device and/or size.

A typical powder composition for depositing a coating according to the present invention consists of from 8.0 to 11.0 weight percent cobalt, from 8.0 to 11.0 weight percent chromium, from 4.0 to 5.5 weight percent carbon and the balance tungsten and incidental impurities. Some of the carbon may be uncombined carbon, e.g., up to about 1.0 weight percent, which may be lost in the deposition process. The feed rate of both oxygen and fuel gas (e.g., acetylene) should be adjusted with this powder to provide an oxygen-fuel gas ratio of about 1.0. This is the same ratio that has been used to deposit conventional coatings of the prior art.

Alternatively, the coating of the present invention can be applied to a substrate by plasma arc spray or other thermal spray techniques. In the plasma arc spray process, an electric arc is established between a non-consumable electrode and a second non-consumable electrode spaced therefrom. A gas is passed in contact with the non-consumable electrode such that it contains the arc. The arc-containing gas is constricted by a nozzle and results in a high thermal content effluent. Powdered coating material is injected

into the high thermal content effluent nozzle and is deposited onto the surface to be coated. This process, which is described in U.S. Patent No. 2,858,411, supra, produces a deposited coating which is sound, dense and adherent to the substrate. The applied coating also consists of irregularly shaped microscopic splats or leaves which are interlocked and mechanically bonded to one another and also to the substrate.

In those cases where the plasma arc spray process is used to apply the coatings in the present invention, powders fed to the arc torch may have essentially the same composition as the applied coating itself. With some plasma arc or other thermal spray equipment, however, some change in composition is to be expected and, in such cases, the powder composition may be adjusted accordingly to achieve the coating composition of the present invention.

The coatings of the present invention may be applied to almost any type of substrate, e.g., metallic substrates such as iron or steel or non-metallic substrates such as carbon, graphite or polymers, for instance. Some examples of substrate material used in various environments and admirably suited as substrates for the coating of the present invention include, for example, steel, stainless steel, iron base alloys, nickel, nickel base alloys, cobalt, cobalt base alloys, chromium, chromium base alloys, titanium, titanium base alloys, aluminum, aluminum base alloys, copper, copper base alloys, refractory metals and refractory-metal base alloys.

Although the composition of the coatings of the present invention may vary within the ranges indicated above, the preferred coating composition consists of from 5.5 to 7.5 weight percent cobalt, from 5.5 to 7.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities. It is preferred in the practice of the present invention that the ratio of cobalt to chromium be about 1:1.

The microstructure of the coatings of the present invention are very complex and not completely understood. However, the major and some of the minor phases of both the powder and coating composition have been identified using essentially three techniques: (1) X-ray diffraction, (2) metallography, and (3) scanning electron microscopy (SEM). X-ray diffraction identifies the phases and gives an estimate of their volumetric amounts. However, some of the phases present in smaller amounts are not observed with X-ray diffraction. The following phases were identified with X-ray diffraction.

Powder

Major: W_2C

Minor: Hexagonal WC, CoW_3C

Coating

Major: W_2C

Minor: Cubic WC

11

Coatings of the present invention exhibit both improved strength and wear resistance as compared to conventional coating of the prior art. Because of their improved strength, they are ideally suited for use on gate valves employed in well service equipment for handling highly corrosive fluids (e.g., solutions containing chlorides, carbon monoxide, carbon dioxide, hydrogen sulfide, vanadium salts, etc.) under moderately high hydraulic pressures, typically about 69,000 kPa (10,000 psi), and temperatures above 93°C (200°F). In the past, conventional coatings failed under these conditions mostly due to their relatively low tensile strength.

The mechanisms of these failures is believed to be as follows: At high pressures and at sufficiently high temperatures, the pressurized fluid slowly diffuses through the thickness of the coating and accumulates within the porosity of the coating. During this phase, the coating is in compression and resists quite well the ambient pressure. After a certain time, the pressure within the porosity reaches a value equal to the ambient pressure, and the inward diffusion of fluid stops. As long as the pressure is maintained, the coating is not subjected to any unusual stresses.

Once the ambient pressure is released, however, the pressure within the porosity is no longer balanced by the ambient pressure. Before the pressurized fluid within the porosity has had time to diffuse out of the coating, the coating is stressed or loaded from within itself. If the internal specific load in the coating exceeds the fracture stress of the coating, the coating will fail outwardly from within the coating.

To satisfy the stringent requirements for gate valves subjected to high pressures and temperatures, it is imperative that stronger coatings be provided while still maintaining all of the normal requirements for gate valve coatings, such as wear and corrosion resistance.

Typically, coatings containing tungsten carbide, cobalt or nickel, and chromium have shown a low resistance to the type of failures described above and a low strength when loaded hydraulically in an outward direction from the interface. However, these coatings have shown a good resistance to wear and corrosion. On the other hand, coatings containing tungsten carbide and cobalt but devoid of any chromium have shown a good resistance to failure and a high strength when subjected to high internal pressures. Because of their lack of chromium, however, these coatings provide little or no resistance to corrosion. The addition of chromium to the coating may increase its resistance to corrosion but at the cost of lowering the strength of the coating to the point where the coating will fail when subjected to high internal pressures.

Coatings of the present invention represent a significant and unexpected improvement over the prior art. The coatings incorporate not only enough chromium to provide corrosion resistance but also enough cobalt, tungsten and carbon in appropriate relative proportions to provide a 50

percent improvement in toughness and strength over that of prior coatings while at the same time significantly increasing wear resistance. Although the exact reasons for improved strength and wear resistance are not clearly understood, it is believed that they result from a change in chemistry and accompanying phase changes in the coating.

In addition to improved strength and wear resistance, the present invention offers the advantage in that the coatings can be applied to a substrate at a faster deposition rate than heretofore possible without cracking or spalling. This is, of course, made possible by the fact that the coating of the present invention possesses sufficient strength to withstand the build-up of high residual stresses that result when the coating is deposited at high rates. The use of high deposition rates significantly reduces the cost of producing a coating since less equipment and operator time is required.

Another advantage of the present invention is that the coating exhibits a smooth "as-deposited" surface which requires less grinding to finish the coating as compared to the coatings of the prior art. Stated in other words, coatings of the present invention require less coating material to be deposited onto the substrate in order to achieve the same finish coating surface and thickness as that of prior coatings without, however, lowering the coatings requirements of resistance to abrasion and corrosion. Moreover, since less coating material needs to be deposited, the coating process is far more efficient and less costly than that of the prior art.

The following examples will serve to further illustrate the practice of the present invention.

Example I

Specimens of AISI 1018 steel were cleaned and prepared for coating as follows. The surface on one side of each specimen was ground smooth and parallel to the opposite side. The surface was then grit blasted with 0.25 mm (60 mesh) Al_2O_3 to a surface roughness of about 3 μm (120 micro-inch) RMS. Three specimens were set aside and prepared for hydraulic pressure test as follows. On the side to be coated, eight small holes, 0.51 mm (0.020 inch) in diameter, were drilled in the specimen substrate perpendicular to its surface to a depth of a few mm (few tenths of an inch). The holes were then enlarged so as to accommodate leak tight couplings. Piano wires, 0.51 mm (0.020 inch) in diameter, were then inserted through the couplings into the small holes and firmly secured so their ends were even and provided a smooth continuation with the surface to be coated. All the specimens were then coated according to the prior art using a detonation gun (D-Gun) and a sintered powder of the following composition: 10 weight percent Co, 4 weight percent Cr, 5.2 weight percent C, and the balance W. The size of the powders was about 0.044 mm or smaller (-325 mesh). Acetylene was used as the fuel-gas. The oxygen-fuel gas ratio was 0.98. The feed rate was 75 grams per min.

A chemical analysis of the coating showed the

following composition: 8 weight percent Co, 3.2 weight percent Cr, 4.7 weight percent C and the balance W. The chemical analysis was carried out principally by two methods. Carbon was analyzed by a combustion analysis technique using a Leco Carbon Analyzer and volumetric determination of gaseous output. Cobalt and chromium were analyzed by first fusing the sample in Na_2O_2 and separating the cobalt and chromium, then determining the amount of each potentiometrically.

The mechanical strength of the coating was determined by an hydraulic pressure test as follows. After coating the specimen prepared for this test in the manner described above, the piano wires were carefully removed providing cavities directly under the coating. By means of the couplings, the cavities were then connected to an hydraulic pressure system and the cavities filled with an hydraulic fluid. The fluid was then pressurized, loading the coating from the interface outward until failure of the coating occurred. Eight measurements were made on each coating and the average value defined as the failure pressure. The failure pressure was taken to be a measure of the coating's mechanical strength for the specific coating thickness. The failure pressures can then be used to rank different coatings of basically the same thickness. The failure pressures for the three coatings were 37,200 kPa (5,400 psi) at a thickness of 0.112 mm (0.0044 inch), 71,000 kPa (10,300 psi) at a thickness of 0.211 mm (0.0083 inch) and 91,000 kPa (13,200 psi) at 0.267 mm (0.0105 inch). Linear regression predicts a failure pressure of 57,200 kPa (8,300 psi) at 0.170 mm (0.0067 inch) thick coating.

Abrasive wear properties of the applied coating were also determined using the standard dry sand/rubber wheel abrasion test described in ASTM Standard G65-80, Procedure A. In this test, the coated specimens were loaded by means of a lever arm against a rotating wheel with a chlorobutyl rubber rim around the wheel. An abrasive (i.e., (0.21 mm to 0.30 mm) 50-70 mesh Ottawa Silica Sand) was introduced between the coating and the rubber wheel. The wheel was rotated in the direction of the abrasive flow. The test specimen was weighed before and after the test and its weight loss was recorded. Because of the wide differences in the densities of different materials tested, the mass loss is normally converted to volume loss to evaluate the relative ranking of materials. The average volume loss for the coated specimens tested (conventional W-Co-Cr-C coating) was 1.7 mm³ per 1,000 revolutions.

The hardness of the coatings was also measured by standard methods. The average hardness was found to be 1100 DPH₃₀₀.

Example II

Specimens of AISI 1018 steel, including one specimen for the hydraulic pressure test, were prepared in the same manner as described in Example I. The specimen surfaces were then coated using a D-Gun and a cast and crushed

powder of the following composition: 14.1 weight percent Co, 4.8 weight percent Cr, 3.2 weight percent C and the balance W. The powder size was 0.044 mm or smaller (-325 mesh). Acetylene was also used as the fuel gas. The oxygen-fuel gas ratio in the D-Gun was 0.98. The feed rate was 100 grams per minute.

A chemical analysis of the coating was performed using the same methods described in Example I. The analysis showed the following composition: 16.5 weight percent Co, 4.9 weight percent Cr, 3.7 weight percent C and the balance W.

The mechanical strength of the coating was determined using the same hydraulic pressure test. The failure pressure for this particular coating was 192,400 kPa (27,900 psi) at a thickness of 0.173 mm (0.0068 inch).

Abrasive wear tests were also carried out using the ASTM Standard G65-80, Procedure A. The average volume loss for the coated specimens was 1.8 mm³ per 1,000 revolutions.

The hardness of the coatings was also measured and found to be 1000 DPH₃₀₀.

This example illustrates a coating prepared according to EP-A1-0,143,342, supra, containing a high content of cobalt, i.e., 11.0 to 18.0 weight percent, and having an improved toughness and strength. The wear resistance of this particular coating is approximately equivalent to the coatings of the prior art as represented by Example I.

Example III

Specimens of AISI 1018 steel, including one specimen for the hydraulic pressure test, were prepared in the same manner as described in Example I. The specimen surfaces were then coated using a D-Gun and a cast and crushed powder of the following composition: 12.0 weight percent Co, 2.1 weight percent Cr, 4.9 weight percent C and the balance W. The powder size was 0.044 mm or smaller (-325 mesh). Acetylene was also used as the fuel gas. The oxygen-fuel gas ratio in the D-Gun was 0.98. The feed rate was 150 grams per minute.

A chemical analysis of the coating was performed using the same methods as described in Example I. The analysis showed the following composition: 17.9 weight percent Co, 2.8 weight percent Cr, 4.1 weight percent C and the balance W.

The same hydraulic pressure test was employed to determine the mechanical strength of the coating. The failure pressure for this particular coating was 182,700 kPa (26,500 psi) at a thickness of 0.170 mm (0.0067 inch).

Abrasive wear tests were also carried out using the ASTM Standard G65-80, Procedure A. The average volume loss for the specimens was 3.6 mm³ per 1000 revolutions.

The hardness of the coatings was also measured and found to be 1000 DPH₃₀₀.

This example also illustrates a coating prepared according to EP-A1-0,143,342, supra, having a

(12)

high strength, but in which the wear resistance was less than that of the prior art coating for Example I.

Example IV

Specimens of AISI 1018 steel, including one specimen for the hydraulic pressure test, were prepared in the same manner as described in Example I. The specimen surfaces were then coated using a D-Gun and a cast and crushed powder of the following composition: 9.6 weight percent Co, 9.5 weight percent Cr, 4.9 weight percent C and the balance W. The powder size was 0.044 mm or smaller (-325 mesh). Acetylene was also used as the fuel gas. The oxygen-fuel gas ratio in the D-Gun was 0.98. The feed rate was 150 grams per minute.

A chemical analysis of the coating was performed using the same methods as described in Example I. The analysis showed the following composition: 6.9 weight percent Co, 6.9 weight percent Cr, 4.2 weight percent C and the balance W.

The same hydraulic pressure test was employed to determine the mechanical strength of the coating. The failure pressure for this particular coating was 89,600 kPa (13,000 psi) at a thickness of 0.173 mm (0.0068 inch). This represents a 50 percent improvement in strength as compared to the coated specimen tested in Example I.

Abrasive wear tests were also carried out using the ASTM Standard G65-80, Procedure A. The average volume loss for the specimens was only 1.0 mm³ per 1000 revolutions.

The hardness of the coatings was also measured and found to be 1209 DPH₃₀₀.

This example illustrates a coating prepared according to the present invention having a moderately high strength and a superior wear resistance. The coating was applied at a fast deposition rate, i.e., 150 grams per minute, but no cracks or spalling occurred.

Example V

Specimens of AISI 1018 steel, including one specimen for the hydraulic pressure test, were prepared in the same manner as described in Example I. The specimen surfaces were then coated using a plasma spray torch and a conventional sintered powder of the following composition: 10 weight percent Co, 4 weight percent Cr, 5.2 weight percent C and the balance W. The powder size was 0.044 mm or smaller (-325 mesh).

A chemical analysis of the coating was performed using the same methods as described in Example I. The analysis showed the following composition: 9.2 weight percent Co, 3.5 weight percent Cr, 5.0 weight percent C and the balance W.

The same hydraulic pressure test was employed to determine the mechanical strength of the coating. The failure pressure for this particular coating was 66,200 kPa (9,600 psi) at a

thickness of 0.175 mm (0.0069 inch). Seven measurements were made on this coating instead of eight.

Abrasive wear tests were also carried out using the ASTM Standard G65-80, Procedure A. The average volume loss for the coated specimens was 9.3 mm³ per 1000 revolutions. The wear properties of this coating were poor even when compared against the wear properties of the conventional D-Gun coatings of Example I. This is to be expected in the case of plasma spray coatings which do not wear as well as D-Gun coatings.

The hardness of the coatings was also measured and found to be 687 DPH₃₀₀.

Example VI

Specimens of AISI 1018 steel, including the specimen for the hydraulic pressure test, were prepared in the same manner as described in Example I. The specimen surfaces were then coated using a plasma spray torch and a cast and crushed powder of the following composition: 9.6 weight percent Co, 9.5 weight percent Cr, 4.9 weight percent C and the balance W. This was the same powder composition used in preparing the coatings of Example IV. The powder size was also the same, i.e., 0.044 mm or smaller (-325 mesh).

A chemical analysis of the coating was performed using the same methods as described in Example I. The analysis showed the following composition: 8.7 weight percent Co, 8.1 weight percent Cr, 3.8 weight percent C and the balance W.

The same hydraulic pressure test was employed to determine the mechanical strength of the coating. The failure pressure for this particular coating was 64,100 kPa (9,300 psi) at a thickness of 0.163 mm (0.0064 inch).

Abrasive wear tests were also carried out using the ASTM Standard G65-80, Procedure A. The average volume loss for the coated specimen was 6.7 mm³ per 1000 revolutions. The wear rate for this coating was about one-third less than that for the plasma spray coating of the previous example using a conventional sintered powder.

The hardness of the coated specimen was also measured and found to be 775 DPH₃₀₀.

It will be seen from the foregoing that the present invention provides a new family of W-Co-Cr-C coatings having improved strength and superior wear resistance. The D-Gun coatings of this invention are capable of withstanding hydraulic pressures in excess of about 89,600 kPa (13,000 pounds per square inch) at a coating thickness of about 0.15 mm (0.006 inch) and exhibit a wear rate of only about 1.0 mm³ per 1000 revolutions. Even plasma coatings of this invention have lower wear rates than plasma coatings of the prior art. Moreover, the coatings can be applied at fast deposition rates without cracking or spalling.

Although the powder and coating compositions have been defined herein with certain specific ranges for each of the essential components, it

will be understood that minor amounts of various impurities may also be present. Iron is usually the principal impurity in the coating resulting from grinding operations and may be present in amounts up to about 1.5 and in some cases 2.0 weight percent of the composition.

Although the foregoing examples include only D-Gun and plasma spray coatings, it will be understood that other thermal spray techniques such as "high velocity" plasma, "hypersonic" combustion spray processes or various other detonation devices may be used to produce coatings of the present invention.

Claims

1. A coating composition applied to a substrate by a thermal spray process which consists of from 4.0 to 10.5 weight percent cobalt, from 5.0 to 11.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

2. A coating composition according to claim 1 consisting of from 5.5 to 7.5 weight percent cobalt, from 5.5 to 7.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

3. A coating composition according to claim 1 or 2 having a mechanical strength sufficient to withstand an hydraulic pressure in excess of about 90,000 kPa (13,000 pounds per square inch) at a coating thickness of about 0.15 mm (0.0060 inch).

4. A coating composition according to any one of claims 1 to 3 having a hardness value in excess of 1000 DPH₃₀₀.

5. A coating composition according to any one of claims 1 to 4 wherein the substrate is a metallic material selected from the group consisting of steel, stainless steel, iron base alloys, nickel, nickel base alloys, cobalt, cobalt base alloys, chromium, chromium base alloys, titanium, titanium base alloys, aluminum, aluminum base alloys, copper, copper base alloys, refractory metals, and refractory-metal base alloys.

6. A coating composition according to any one of claims 1 to 4 wherein the substrate is a non-metallic material selected from the group consisting of carbon, graphite and polymers.

7. A method for coating a substrate wherein a powdered coating material is suspended within a high temperature, high velocity gaseous stream and heated to a temperature at least close to the melting point thereof, said gaseous stream being directed against a surface of said substrate to deposit said powdered coating material and form a coating thereon, characterised in that, a powdered coating material having a composition such that the coating deposited onto said substrate consists of from 4.0 to 10.5 weight percent cobalt, from 5.0 to 11.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities, is used.

8. A method according to claim 7 wherein the powdered coating material has a composition

such that the coating deposited onto said substrate consists of from 5.5 to 7.5 weight percent cobalt, from 5.5 to 7.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

9. A method according to claim 7 or 8 wherein the powdered coating material is suspended within a high temperature, high velocity gaseous stream produced by a detonation device.

10. A method according to claim 9 wherein a mixture of oxygen and a fuel gas is fed to the barrel of a detonation gun along with the powdered coating material; and the oxygen and fuel gas mixture is ignited to produce a detonation wave along said barrel which accelerates said powdered coating material in said high temperature, high velocity gaseous stream.

11. A method according to claim 10 wherein the ratio of oxygen to fuel gas in said mixture is approximately 1.0.

12. A method according to any one of claims 7 to 11 wherein the powdered coating material has a composition consisting of from 8.0 to 11.0 weight percent cobalt, from 8.0 to 11.0 weight percent chromium, from 4.0 to 5.5 weight percent carbon and the balance tungsten and incidental impurities.

13. A method according to claim 7 or 8 wherein the powdered coating material is suspended within a high temperature, high velocity gaseous stream produced to plasma arc torch.

14. A method according to claim 13 wherein the powdered coating material has a composition which is substantially the same as the composition of said coating.

15. A powdered coating composition for applying a high strength, wear and corrosion resistant coating onto a substrate by a thermal spray process consisting of from 8.0 to 11.0 weight percent cobalt, from 8.0 to 11.0 weight percent chromium, from 4.0 to 5.5 weight percent carbon and the balance tungsten and incidental impurities.

16. A powdered coating composition according to claim 15 consisting of cast and crushed powder.

Patentansprüche

1. Auf ein Substrat durch einen thermischen Sprühprozeß aufgebraute Beschichtungszusammensetzung bestehend aus 4,0 bis 10,5 Gewichtsprozent Kobalt, 5,0 bis 11,5 Gewichtsprozent Chrom, 3,0 bis 5,0 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen.

2. Beschichtungszusammensetzung nach Anspruch 1 bestehend aus 5,5 bis 7,5 Gewichtsprozent Kobalt, 5,5 bis 7,5 Gewichtsprozent Chrom, 3,0 bis 5,0 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen.

3. Beschichtungszusammensetzung nach Anspruch 1 oder 2 mit einer ausreichenden mechanischen Festigkeit, um bei einer Beschichtungsdicke von etwa 0,15 mm (0,0060 inch) einem hydraulischen Druck von mehr als etwa 90.000

will be understood that minor amounts of various impurities may also be present. Iron is usually the principal impurity in the coating resulting from grinding operations and may be present in amounts up to about 1.5 and in some cases 2.0 weight percent of the composition.

Although the foregoing examples include only D-Gun and plasma spray coatings, it will be understood that other thermal spray techniques such as "high velocity" plasma, "hypersonic" combustion spray processes or various other detonation devices may be used to produce coatings of the present invention.

Claims

1. A coating composition applied to a substrate by a thermal spray process which consists of from 4.0 to 10.5 weight percent cobalt, from 5.0 to 11.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

2. A coating composition according to claim 1 consisting of from 5.5 to 7.5 weight percent cobalt, from 5.5 to 7.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

3. A coating composition according to claim 1 or 2 having a mechanical strength sufficient to withstand an hydraulic pressure in excess of about 90,000 kPa (13,000 pounds per square inch) at a coating thickness of about 0.15 mm (0.0060 inch).

4. A coating composition according to any one of claims 1 to 3 having a hardness value in excess of 1000 DPH₃₀₀.

5. A coating composition according to any one of claims 1 to 4 wherein the substrate is a metallic material selected from the group consisting of steel, stainless steel, iron base alloys, nickel, nickel base alloys, cobalt, cobalt base alloys, chromium, chromium base alloys, titanium, titanium base alloys, aluminum, aluminum base alloys, copper, copper base alloys, refractory metals, and refractory-metal base alloys.

6. A coating composition according to any one of claims 1 to 4 wherein the substrate is a non-metallic material selected from the group consisting of carbon, graphite and polymers.

7. A method for coating a substrate wherein a powdered coating material is suspended within a high temperature, high velocity gaseous stream and heated to a temperature at least close to the melting point thereof, said gaseous stream being directed against a surface of said substrate to deposit said powdered coating material and form a coating thereon, characterised in that, a powdered coating material having a composition such that the coating deposited onto said substrate consists of from 4.0 to 10.5 weight percent cobalt, from 5.0 to 11.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities, is used.

8. A method according to claim 7 wherein the powdered coating material has a composition

such that the coating deposited onto said substrate consists of from 5.5 to 7.5 weight percent cobalt, from 5.5 to 7.5 weight percent chromium, from 3.0 to 5.0 weight percent carbon and the balance tungsten and incidental impurities.

9. A method according to claim 7 or 8 wherein the powdered coating material is suspended within a high temperature, high velocity gaseous stream produced by a detonation device.

10. A method according to claim 9 wherein a mixture of oxygen and a fuel gas is fed to the barrel of a detonation gun along with the powdered coating material; and the oxygen and fuel gas mixture is ignited to produce a detonation wave along said barrel which accelerates said powdered coating material in said high temperature, high velocity gaseous stream.

11. A method according to claim 10 wherein the ratio of oxygen to fuel gas in said mixture is approximately 1.0.

12. A method according to any one of claims 7 to 11 wherein the powdered coating material has a composition consisting of from 8.0 to 11.0 weight percent cobalt, from 8.0 to 11.0 weight percent chromium, from 4.0 to 5.5 weight percent carbon and the balance tungsten and incidental impurities.

13. A method according to claim 7 or 8 wherein the powdered coating material is suspended within a high temperature, high velocity gaseous stream produced to plasma arc torch.

14. A method according to claim 13 wherein the powdered coating material has a composition which is substantially the same as the composition of said coating.

15. A powdered coating composition for applying a high strength, wear and corrosion resistant coating onto a substrate by a thermal spray process consisting of from 8.0 to 11.0 weight percent cobalt, from 8.0 to 11.0 weight percent chromium, from 4.0 to 5.5 weight percent carbon and the balance tungsten and incidental impurities.

16. A powdered coating composition according to claim 15 consisting of cast and crushed powder.

Patentansprüche

1. Auf ein Substrat durch einen thermischen Sprühprozeß aufgebraute Beschichtungszusammensetzung bestehend aus 4,0 bis 10,5 Gewichtsprozent Kobalt, 5,0 bis 11,5 Gewichtsprozent Chrom, 3,0 bis 5,0 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen.

2. Beschichtungszusammensetzung nach Anspruch 1 bestehend aus 5,5 bis 7,5 Gewichtsprozent Kobalt, 5,5 bis 7,5 Gewichtsprozent Chrom, 3,0 bis 5,0 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen.

3. Beschichtungszusammensetzung nach Anspruch 1 oder 2 mit einer ausreichenden mechanischen Festigkeit, um bei einer Beschichtungsdicke von etwa 0,15 mm (0,0060 inch) einem hydraulischen Druck von mehr als etwa 90.000



(15)

kPa (13.000 Pfund pro Quadratinch) zu widerstehen.

4. Beschichtungszusammensetzung nach einem der Ansprüche 1 bis 3 mit einem HärteWert von über 1000 DPH₃₀₀.

5. Beschichtungszusammensetzung nach einem der Ansprüche 1 bis 4, wobei das Substrat ein metallischer Werkstoff ist, der aus der aus rostfreiem Stahl, Eisenbasislegierungen, Nickel, Nickelbasislegierungen, Kobalt, Kobaltbasislegierungen, Chrom, Chrombasislegierungen, Titan, Titanbasislegierungen, Aluminium, Aluminiumbasislegierungen, Kupfer, Kupferbasislegierungen, feuerfesten Metallen und Feuerfestmetall-Basislegierungen bestehenden Gruppe ausgewählt ist.

6. Beschichtungszusammensetzung nach einem der Ansprüche 1 bis 4, wobei das Substrat ein nichtmetallischer Werkstoff ist, der aus der aus Kohlenstoff, Graphit und Polymeren bestehenden Gruppe ausgewählt ist.

7. Verfahren zum Beschichten eines Substrats, bei dem ein pulverförmiges Beschichtungsmaterial in einem Hochtemperatur-Hochgeschwindigkeits-Gasstrom suspendiert und auf eine mindestens nahe seinem Schmelzpunkt liegende Temperatur erhitzt wird, und der Gasstrom gegen eine Oberfläche des Substrats gerichtet wird, um das pulverförmige Beschichtungsmaterial abzulagern und auf der Oberfläche eine Beschichtung auszubilden, dadurch gekennzeichnet, daß ein pulverförmiges Beschichtungsmaterial solcher Zusammensetzung verwendet wird, daß die auf dem Substrat abgelagerte Beschichtung aus 4,0 bis 10,5 Gewichtsprozent Kobalt, 5,0 bis 11,5 Gewichtsprozent Chrom, 3,0 bis 5,0 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen, besteht.

8. Verfahren nach Anspruch 7, wobei das pulverförmige Beschichtungsmaterial eine solche Zusammensetzung hat, daß die auf dem Substrat abgelagerte Beschichtung aus 5,5 bis 7,5 Gewichtsprozent Kobalt, 5,5 bis 7,5 Gewichtsprozent Chrom, 3,0 bis 5,0 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen, besteht.

9. Verfahren nach Anspruch 7 oder 8, wobei das pulverförmige Beschichtungsmaterial in einem Hochtemperatur-Hochgeschwindigkeits-Gasstrom suspendiert wird, der mittels einer Detonationsvorrichtung erzeugt wird.

10. Verfahren nach Anspruch 9, wobei ein Gemisch aus Sauerstoff und einem Brenngas der Trommel einer Detonationspistole zusammen mit dem pulverförmigen Beschichtungsmaterial zugeführt wird und das Sauerstoff-Brenngas-Gemisch gezündet wird, um entlang der Trommel eine Detonationswelle zu erzeugen, welche das pulverförmige Beschichtungsmaterial in dem Hochtemperatur-Hochgeschwindigkeits-Gasstrom beschleunigt.

11. Verfahren nach Anspruch 10, wobei das Verhältnis von Sauerstoff zu Brenngas in dem Gemisch näherungsweise 1,0 beträgt.

12. Verfahren nach einem der Ansprüche 7 bis

11, wobei das pulverförmige Beschichtungsmaterial aus 8,0 bis 11,0 Gewichtsprozent Kobalt, 8,0 bis 11,0 Gewichtsprozent Chrom, 4,0 bis 5,5 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen, besteht.

13. Verfahren nach Anspruch 7 oder 8, wobei das pulverförmige Beschichtungsmaterial in einem mittels eines Plasmalichtbogens erzeugten Hochtemperatur-Hochgeschwindigkeit-Gasstrom suspendiert wird.

14. Verfahren nach Anspruch 13, wobei das pulverförmige Beschichtungsmaterial im wesentlichen die gleiche Zusammensetzung wie die Beschichtung hat.

15. Pulverförmige Beschichtungszusammensetzung zum Aufbringen einer hochfesten, verschleiß- und korrosionsbeständigen Beschichtung auf einem Substrat durch einen thermischen Sprühprozeß, bestehend aus 8,0 bis 11,0 Gewichtsprozent Kobalt, 8,0 bis 11,0 Gewichtsprozent Chrom, 4,0 bis 5,5 Gewichtsprozent Kohlenstoff, Rest Wolfram und beiläufige Verunreinigungen.

16. Pulverförmige Beschichtungszusammensetzung nach Anspruch 15 bestehend aus gegossenem und zerkleinertem Pulver.

Revendications

1. Composition de revêtement appliquée à un substrat par un procédé de projection thermique, qui est constituée de 4,0 à 10,5% en poids de cobalt, de 5,0 à 11,5% en poids de chrome, de 3,0 à 5,0% en poids de carbone et le reste de tungstène et d'impuretés accidentelles.

2. Composition de revêtement selon la revendication 1, constituée de 5,5 à 7,5% en poids de cobalt, de 5,5 à 7,5% en poids de chrome, de 3,0 à 5,0% en poids de carbone et le reste de tungstène et d'impuretés accidentelles.

3. Composition de revêtement selon la revendication 1 ou 2, ayant une solidité mécanique suffisante pour supporter une pression hydraulique supérieure à environ 90 000 kPa (13 000 pounds per square inch) à une épaisseur de revêtement d'environ 0,15 mm (0,0060 inch).

4. Composition de revêtement selon l'une quelconque des revendications 1 à 3, ayant une valeur de dureté supérieure à 1000 DPH₃₀₀.

5. Composition de revêtement selon l'une quelconque des revendications 1 à 4, dans laquelle le substrat est une matière métallique choisie dans le groupe constitué de l'acier, de l'acier inoxydable, d'alliages à base de fer, de nickel, d'alliages à base de nickel, de cobalt, d'alliages à base de cobalt, de chrome, d'alliages à base de chrome, de titane, d'alliages à base de titane, d'aluminium, d'alliages à base d'aluminium, de cuivre, d'alliages à base de cuivre, de métaux réfractaires et d'alliages à base de métaux réfractaires.

6. Composition de revêtement selon l'une quelconque des revendications 1 à 4, dans laquelle le substrat est une matière non métallique choisie dans le groupe constitué du carbone, du graphite et de polymères.



(16)

7. Procédé pour revêtir un substrat dans lequel une matière de revêtement en poudre est mise en suspension dans un courant gazeux à haute température, haute vitesse et chauffée à une température au moins proche de son point de fusion, ledit courant gazeux étant dirigé contre une surface dudit substrat pour y déposer ladite matière de revêtement en poudre et y former un revêtement, caractérisé en ce qu'une matière de revêtement en poudre ayant une composition telle que le revêtement déposé sur ledit substrat est constitué de 4,0 à 10,5% en poids de cobalt, de 5,0 à 11,5% en poids de chrome, de 3,0 à 5,0% en poids de carbone et le reste de tungstène et d'impuretés accidentelles, est utilisée.

8. Procédé selon la revendication 7, dans lequel la matière de revêtement en poudre possède une composition telle que le revêtement déposé sur ledit substrat est constitué de 5,5 à 7,5% en poids de cobalt, de 5,5 à 7,5% en poids de chrome, de 3,0 à 5,0% en poids de carbone et le reste de tungstène et d'impuretés accidentelles.

9. Procédé selon la revendication 7 ou 8, dans lequel la matière de revêtement en poudre est mise en suspension dans un courant gazeux à haute température, haute vitesse, produit par un dispositif à détonation.

10. Procédé selon la revendication 9, dans lequel un mélange d'oxygène et d'un gaz combustible alimente le canon d'un pistolet à détonation, en même temps que la matière de revêtement en poudre; et le mélange d'oxygène et de gaz combustible est allumé pour produire une onde détonante le long dudit canon, qui accélère

ladite matière de revêtement en poudre dans ledit courant gazeux à haute température, haute vitesse.

11. Procédé selon la revendication 10, dans lequel le rapport de l'oxygène au gaz combustible dans ledit mélange est d'environ 1,0.

12. Procédé selon l'une quelconque des revendications 7 à 11, dans lequel la matière de revêtement en poudre possède une composition constituée de 8,0 à 11,0% en poids de cobalt, 8,0 à 11,0% en poids de chrome, 4,0 à 5,5% en poids de carbone et le reste de tungstène et d'impuretés accidentelles.

13. Procédé selon la revendication 7 ou 8, dans lequel la matière de revêtement en poudre est mise en suspension dans un courant gazeux à haute température, haute vitesse produit par une torche à arc sous plasma.

14. Procédé selon la revendication 13, dans lequel la matière de revêtement en poudre possède une composition qui est sensiblement la même que la composition dudit revêtement.

15. Composition de revêtement en poudre pour l'application d'un revêtement à haute résistance, résistant à l'usure et à la corrosion, sur un substrat par un procédé de projection thermique, constituée de 8,0 à 11,0% en poids de cobalt, de 8,0 à 11,0% en poids de chrome, de 4,0 à 5,5% en poids de carbone et le reste de tungstène et d'impuretés accidentelles.

16. Composition de revêtement en poudre selon la revendication 15, constituée d'une poudre coulée et broyée.

