CLAIMS

1. A coating composition comprising:

a polyisocyanate component and a polyol component; and an organic solvent, wherein

the polyisocyanate component includes an aromatic ring-containing isocyanate,

the polyol component includes an acrylic polyol,

the acrylic polyol is a polymer of a monomer composition containing a hydroxyl group-containing polymerizable monomer and a carboxyl group-containing polymerizable monomer and containing no (meth)acrylonitrile,

the organic solvent contains an alkyl ester,

an equivalent ratio (NCO/OH) of isocyanate groups of the polyisocyanate component to hydroxyl groups of the polyol component is 1.2 or more and 6.5 or less,

a glass transition temperature of the acrylic polyol is -25°C or more and 80°C or less, and

a number average molecular weight of the acrylic polyol is 6000 or more and 50000 or less.

2. The coating composition according to claim 1, wherein

the aromatic ring-containing isocyanate includes a xylylene diisocyanate and/or a derivative of the xylylene diisocyanate.

3. The coating composition according to claim 1, wherein

the monomer composition includes an aromatic vinyl monomer.

4. The coating composition according to claim 1, wherein

an equivalent ratio (NCO/OH) of isocyanate groups of the polyisocyanate component to hydroxyl groups of the polyol component is 1.2 or more and 6.0 or less.

5. The coating composition according to claim 1, wherein

in the monomer composition, a mass ratio (carboxy group-containing monomer/hydroxyl group-containing monomer) of the carboxy group-containing monomer content to the hydroxyl group-containing monomer content is 0.03 or more and 0.1 or less.

6. The coating composition according to claim 1, wherein

a content ratio of the carboxy group-containing monomer is 0.1 parts by mass or more and 5.0 parts by mass or less with respect to 100 parts by mass of the total amount of the monomer composition.

7. A laminate comprising:

a resin film,

an inorganic thin film layer disposed on one side in a thickness direction of the resin film,

a polyurethane layer disposed on one side in the thickness direction of the inorganic thin film layer,

an adhesive layer disposed on one side in the thickness direction of the polyurethane layer, and

a sealant layer disposed on one side in the thickness direction of the adhesive layer, wherein

the polyurethane layer includes a cured product of the coating composition according to claim 1.

8. The laminate according to claim 7, wherein

the inorganic thin film layer includes aluminum oxide and/or silicon oxide.

9. The laminate according to claim 7, wherein

the resin film includes a polyester resin and/or a polyolefin resin.