

ARC DEPOSITION SOURCE HAVING A DEFINED ELECTRIC FIELD

The invention relates to an arc deposition device according to the preamble of claim 1. In the present description, an arc deposition device refers to a device with the aid of which an electric arc whose arc spot is on a cathode can be ignited under vacuum, wherein the material to be evaporated is made available by the cathode (= target) and the arc spot results in the evaporation of the target material.

Arc deposition sources are known in the state of the art. Snaper discloses in US3625848 a beam gun with a cathode and an anode that are arranged in such a manner that a spark discharge occurs between them. The cathode in this case is made of the material that is to be deposited. The anode described therein has a tapering geometry and is placed in the immediate vicinity of the cylindrical cathode. The arrangement according to this state of the art is shown in Figure 1. Magnetic means are not used in this arrangement. The movement of the arc spot on the target would thus be very slow by today's standards, although they were described at the time as being fast. A slow movement of the arc spot causes among other things an increased roughness of the layers produced by means of the arc deposition source.

By contrast, patent document US4 620 913 by Clark Bergman discloses a multi arc vacuum system in which magnetic means are used. This is an arc source with anode array, wherein the chamber or an electrically insulated introduced anode is used. The resulting disadvantage is that merely part of the magnetic fields exiting from the target lead into the anode. The advantage of the apparatus therein is a stable spark guiding, especially at low discharge currents. A current distribution between the chamber and the introduced anode is achieved by additionally supplying a positive voltage to the introduced anode.

There is therefore a need for an arc deposition source that makes it possible to produce layers with low surface roughness at a constantly high evaporation rate. It is the aim of the present invention to propose such an arc deposition source.

According to a first aspect of the present invention, there is provided an arc deposition device, comprising:

- a cathode comprising a surface with the material that is to be evaporated,
- magnetic means that lead to a magnetic field over the surface,
- an anode for absorbing the electrons that are extracted out of the cathode during the evaporation process,
- a voltage source for putting the anode at least partly at positive potential relative to the cathode,

characterized in that

the anode in the vicinity of the cathode is designed in such a way that the magnetic field lines that exit from the surface of the cathode hit the anode if they do not exit from the surface at a central area of the cathode, and in that in the central area measures have been taken that essentially prevent its erosion during operation of the deposition device.

According to a second aspect of the present invention, there is provided a vacuum treatment device with a vacuum chamber and a substrate holder and with an arc deposition device according to the first aspect.

The arc deposition source comprises a cathode (target), an anode and magnetic means that may enable the magnetic field lines to lead from the target surface to the anode in a short connection.

The anode is placed in the direct vicinity of the cathode so that the connection of the cathode with the anode may be ensured over magnetic field lines from any point of the target surface to be evaporated and which is subjected to erosion.

In this connection, the magnetic means are designed in such a way that the component parallel to the target surface is considerably larger than the component perpendicular to the target surface. Magnetic field forces of up to 500 Gauss can be used, i.e. considerably higher field forces than the magnetic field forces otherwise used in PVD technology.

The arc source thus described may exhibit, by comparison with the state of the art, higher coating rates with simultaneously very smooth layers.

The arc source can even be operated in vacuum, with a high spark speed being achieved. The arc source is then operated in metal mode. The metal ions thus generated, such as e.g. Cr^+ , Ti^+ , can arrive undisturbed onto the substrate and be used for the purpose of metal ion etching. Operation with low discharge current is possible.

By means of so-called "pre-biasing", it is possible with the anode to reliably adjust the ion energy.

The invention will now be explained by way of example and with the aid of the figures.

Figure 1 shows an arc deposition source according to the state of the art;

Figure 2 shows an arc deposition source according to the state of the art;

Figure 3 shows a first embodiment of an inventive arc deposition source;

Figure 4 shows a vacuum device with an inventive arc deposition source;

Figure 5 shows a vacuum device with an arc deposition source according to the state of the art;

Figure 6 shows the potential ratios with a device according to Figure 5;

Figure 7 shows the potential ratios with an inventive device according to Figure 4;

Figure 8 shows a further embodiment of the inventive vacuum device;

Figure 9 shows the potential ratios with an inventive device according to Figure 4;

Figure 10 shows a further embodiment of an inventive vacuum device;

Figure 11 shows the potential ratios with an inventive device according to Figure 4.

To gain a better understanding of the invention, the situation with arc sources according to the state of the art will be broadly discussed. Figure 2 shows an arc evaporation arrangement 201 with an anode 203 at a distance from the source cathode 209 according to the state of the art. The source cathode is cooled by means of a cooling device 211 and is connected with the negative pole 213 of a DC current supply. Behind the source cathode, magnetic means 215 are provided which ensure a magnetic field is generated above the target surface. An arc spot 205 releases a high current and thus a plurality of electrons in the evaporation chamber. The arc plasma is available as conductive medium. In the state of the art, since the anode 203 is not in the direct vicinity of the arc spot 205, the charged particles must cross the magnetic field on their way to the further removed anode. What is relevant is the movement of a charged particle with a charge q , mass m , speed v at the location r in an electric field $E(r)$ and a magnetic field $B(r)$. In this connection, various force components will be acting: for the movement parallel to the B field, a force proportional to qE will be acting; for the movement perpendicular to the magnetic field, the force proportional to $q(E_{\perp} + v_{\perp} \times B)$, will be acting, which results in a gyration movement which is however overlaid by an $E \times B$ drift. This leads to a "virtual" current path 207 as indicated in Figure 2. When travelling this path reminiscent of a spiral on its way to the remote anode 203, the working gas (e.g. Ar, N_2) present in the coating chamber is highly ionized. This results in the formation of gas ions, in a voltage increase of the discharge and in a jump of potential in front of the cathode. Furthermore, a reduction of the coating rate can be observed.

Figure 3 shows an embodiment of the inventive arc deposition source 301. This is only a variant given by way of example and can be achieved through very different executions. The cathode 309 consists of the material to be evaporated and is connected to the negative pole of a current source through the power connection. Through the magnetic means 305, a magnetic field is generated on the cathode surface that enables a fast movement of the spark.

The magnetic field lines that exit from the target surface are designed within a large portion of the area in such a way that they exhibit mainly components parallel to the surface of the cathode 309 and enable a short connection to the anode 303 extending in a ring-shape around the cathode edge. The arc deposition source represented in Figure 3 can however be executed both as an axially symmetrical circular cathode and as a rectangular cathode. Cathode areas in the center resp. along the middle line will always exhibit field lines running perpendicular to the target surface and should thus be excluded from the erosion. This can be achieved for example by means of a shutter or by means of a filled recess (both not represented). The magnetic field force in the area 6 amounts to 40 to 500 Gauss. A range between 60 and 100 Gauss has proved advantageous and between 200 and 500 Gauss particularly advantageous for especially smooth layer results. The inventive arrangement of the anode in combination with the magnetic field distribution enables operation with such high magnetic fields. The usual materials for mechanically resistant coatings, such as Ti, TiAl, AlCr, TiSi, Cr etc., can be used as target material of the cathode 309.

In an arc evaporation arrangement 301 according to Figure 3, the anode 303 in combination with the magnetic field generated by the magnetic means 305 is placed according to the invention in the vicinity of the cathode 309, so that the magnetic field lines enable the current path 307 in a direct line from the arc spot 315 to the anode 303. A drift as described above can essentially be avoided when the electric field runs essentially parallel to the magnetic field. In an advantageous embodiment of the present invention, the anode is designed in such a way that this is achieved at applied voltage and active magnetic field and nearly all or at least the majority of the magnetic field lines with the

exception of the central magnetic field lines lead to the anode. The path of the electrons is characterized by the Larmor radius and describes a gyration around the field line path. The gyration radius for an electron amounts for 10 Gauss to approx. 1mm and for 100 Gauss to approx. 0.1 mm. At the corresponding magnetic field forces, the path is thus well localized along the field line. The effect of such an arrangement is a reduction of the total discharge voltage and an increase of the coating rate. The working gas in the vicinity of the target is only negligibly ionized.

A possible advantageous use of the present invention is metal magnetron ion etching (MIE).

This is possible due to a further characteristic of the inventive arc deposition source. The characteristic consists in the possibility of a stable operation even without working gas under vacuum with pressures lower than $1\text{E-}03\text{Pa}$. The good electric connection of the arc spot 5 at the anode makes it possible for the electric conductivity of the metal plasma 8 to be sufficient to carry the current from the cathode to the anode 9. The metal steam from the arc source is singly and highly ionized to a high degree and can be accelerated through the bias voltage 12 onto the substrate 11. This enables a magnetron ion etching (MIE) to be effectively achieved. A corresponding MIE device 401 is shown in Figure 4: it comprises an arc deposition source 403 and a substrate holder 407 which are arranged in a vacuum chamber 405. The substrate holder, fitted with substrates to be etched (not represented) is set to negative potential by means of a voltage source 408, thus accelerating the positive ions generated at the arc deposition source towards the substrates.

It is noteworthy that the operation in vacuum can be maintained at very low current strengths: when selecting the parameter ranges for the above mentioned MIE process, it was surprising that even at very low discharge currents of the arc discharge, a stable process is possible. Due to the magnetic field lines, the potential of the anode is "carried over" up to shortly before the target surface, by means of which the current path can be maintained.

For aluminum, a stable process could be observed at current strengths down to just above 10A and for titanium at current strengths down to just above 40A. With the inventive arc deposition source, metal ion etching can also be performed in a stable manner with other materials, such as for example Cr, Nb, Ta and other metals with high ionization degree and high proportion of multiple ionization.

The inventive arc deposition source can be made with different arrays, which themselves are in turn inventive.

First, again for a better understanding, the situation will be sketched where an arc deposition source according to the state of the art is used. An arrangement according to the state of the art is accordingly represented in Figure 5.

In this context, the chamber wall of the vacuum chamber 505 forms the anode. The magnetic field lines that exit from the target have no direct connection with the anode. Figure 5 shows a coating device 501 with an arc deposition source 503 that is placed in a vacuum chamber 505, a substrate holder 507 being further placed in the vacuum chamber 505 and being capable of being set to negative voltage by means of a voltage source 508. Especially at high magnetic field forces, which have a positive impact on the layer roughness, the working gas (e.g. N_2) is strongly ionized and therefore the discharge voltage is increased resp. a drop of potential occurs in front of the target. Furthermore, the high electron temperature of the discharges (2eV-5eV) results in a distortion of the potential in front of the substrate, as sketched in Figure 6.

By contrast, an inventive embodiment has been outlined in Figure 4 and has been already explained to a large extent.

The cathode material evaporated with a high degree of ionization is accelerated through a bias voltage 408 onto the substrate. The electric system cathode 1 and anode 4 is executed floatingly relative to the chamber mass 10.

The plasma potential U_{plasma} in this embodiment is bound to the chamber wall.

The discharge current of the arc source flows from the cathode to the anode. The cathode voltage in this example of approx. -16 to -25V is formed against the anode 4. The substrate bias from the generator 408 accelerates ions from the plasma with a plasma potential U_{plasma} against the substrate. The behavior of the potential in front of the substrate is, as represented in Figure 7, no longer distorted, since the electron temperature of such a plasma is merely approx. 0.3eV to 1eV.

A further embodiment is shown in Figure 8, namely a coating device 801 with an arc deposition source 803 placed in a vacuum chamber 805, wherein a substrate holder 807, that can be set to a negative voltage by means of a voltage source 808, is further placed in the vacuum chamber. According to this embodiment, in contrast to Figure 4, the cathode of the floating cathode-anode system of Figure 4 is connected to the chamber mass (ground). The potentials are then shifted, as represented in Figure 9. The cathode potential is shifted towards the chamber mass. The arc discharge current runs from the cathode to the anode. The voltage generated by the voltage source (bias supply) 808 (in this example 40V) generates an acceleration of the ions with an additional proportion $U_{\text{bias}} + U_{\text{plasma}}$.

In Figure 8, the cathode is hot-wired with the chamber and is thus laid to the chamber mass. It is however also possible to connect the cathode and the chamber over a voltage source and thus achieve an additional shift of potential. It is thus possible to achieve a plasma potential, at least in front of the anode, that is strongly positive. This is shown in Figures 10 and 11.

Claims

1. Arc deposition device, comprising:
 - a cathode comprising a surface with the material that is to be evaporated,
 - magnetic means that lead to a magnetic field over the surface,
 - an anode for absorbing the electrons that are extracted out of the cathode during the evaporation process,
 - a voltage source for putting the anode at least partly at positive potential relative to the cathode,characterized in that
the anode in the vicinity of the cathode is designed in such a way that the magnetic field lines that exit from the surface of the cathode hit the anode if they do not exit from the surface at a central area of the cathode, and in that in the central area measures have been taken that essentially prevent its erosion during operation of the deposition device.
2. Arc deposition device according to claim 1, characterized in that the position and geometry of the anode in relation to the cathode are chosen in such a manner that the magnetic field lines hit the surface of the anode at an angle of over 45° and preferably essentially perpendicularly.
3. Arc deposition device according to claim 2, characterized in that the position and geometry of the anode in relation to the cathode are chosen in such a manner that the magnetic field lines and the electric field lines that hit the anode run essentially parallel to one another.
4. Arc deposition device according to claim 1, characterized in that the measures comprise a shutter in the central area of the cathode surface.
5. Vacuum treatment device with a vacuum chamber and a substrate holder and with an arc deposition device according to one of the preceding claims.

6. Vacuum treatment chamber according to claim 5, characterized in that the cathode of the arc deposition device is kept in relation to the vacuum chamber on one potential that is floating, at the same polarity or positive.

ARC DEPOSITION SOURCE HAVING A DEFINED ELECTRIC FIELD**Abstract**

The invention relates to an arc deposition device, comprising a cathode, an anode, as well as a voltage source for putting the anode at positive potential relative to the cathode. The device also comprises magnetic elements, which cause a magnetic field over the cathode surface, wherein the anode is arranged in the vicinity of the cathode in such a way that the magnetic field lines exiting from the cathode surface hit the anode.

TRANSLATION OF FIGURES

Figures 6, 7, 9, 11:

Kathode	cathode
Anode	anode
Substrat	substrate
Kammerwand	chamber wall