

PROCESS FOR INFLUENCING THE PROPERTIES OF COMBUSTION RESIDUE

The invention pertains to a process for influencing the properties of combustion residue from a combustion plant, especially a waste incinerator, in which the fuel is burned on a furnace grate and the unmelted and/or unsintered combustion residue which accumulates is returned to the combustion process. Most of the combustion residue originates from the ash content of the fuel and is obtained in the form of grate ash -- frequently referred to as slag -- in the deslagger. The residues can also include fly ash from the boiler or from the off-gas filtration unit. Grate ash can also contain metal, glass, and ceramic components.

A process of this type is known from DE 102 13 788.9 A1. In this process, combustion is regulated in such a way that a portion of the combustion residue melts and/or sinters in the combustion bed of the main combustion zone, whereas the unmelted and/or unsintered combustion residues are separated at the end of the combustion operation and returned to the combustion process.

It is also known from EP 0 862 019 B1 that flue dust can be metered into the high-temperature zone of the combustion furnace, where the temperature is above the melting or sintering temperature of the flue dust. The fly ash is metered in as a function of specific combustion conditions which promote the formation of toxic organic pollutants such as PCDD/PCDF and/or precursor compounds such the precursors of PCDD and PCDF.

These processes take no account of the fact that the return of the combustion residues can have a significant effect on the combustion process. Of particular importance in this regard are the percentage of combustion residue in the fuel mixture and the change in the

material composition of the combustion residue.

The return of combustion residue leads, for example, to an increase in the proportion of combustion residue in the fuel mixture and thus to a decrease in the temperature of the combustion bed. Because of the lower combustion bed temperature, the proportion of unmelted and/or unsintered components in the combustion residue increases even more. When these amounts are returned again in turn without regulation in accordance with DE 102 13 788.9 A1, for example, the temperature of the combustion bed will continue to drop, which will be disadvantageous.

The material composition of the combustion residue, furthermore, can also change as a result of its return. Unmelted and/or unsintered combustion residue in the form of fine slag fractions have, for example, higher calcium oxide contents and lower iron oxide contents than the average composition of the combustion residue. This means that the average lime content of the combustion residues can increase over time as a result of the return of fine slag fractions as done in accordance with DE 102 13 788.9 A1.

The melting and/or sintering process is determined

-- by the material composition of the fuel and of the returned combustion residue, this composition being in turn the crucial factor which determines the melting temperature and the reactivity during sintering reactions, and

-- by the combustion conditions, which are the deciding factor with respect to the combustion bed temperature and other essential combustion parameters. The amount of fuel mixture supplied; the point of introduction; the stoking by the grate; and the quantities of air, oxygen, and recycled off-gas and their temperatures determine the combustion conditions.

In the following, a distinction is made between "combustion conditions" and

"combustion parameters". Thus the combustion conditions are the settings which one is able to make or to influence directly by means of control devices. These include, for example, the quantity of fuel mixture supplied (fuel mixture = fuel + returned combustion residue), the point of introduction, and the rate and temperatures at which air, oxygen, and returned off-gas are supplied.

The combustion parameters are defined as the variables which cannot be set directly by means of control devices but rather which are the result of the combustion conditions. These include, for example, the temperature of the combustion bed, the temperature of the combustion chamber, the amount of steam produced, and the O₂ content in the off-gas. The composition of the fuel (calorific value, water content, ash content) is also considered a combustion parameter, because it cannot be directly influenced or controlled in the case of waste materials.

The task of the invention is to provide a process by means of which it can be guaranteed that essentially all of the solid combustion residue in the combustion bed is sintered and/or melted.

This task is accomplished according to the invention in a process according to the introductory clause of Claim 1 in that the melting and/or sintering processes in the combustion bed are regulated according to at least one of the following process steps:

- the residues are returned only as long as, and only in such an amount that, the changes thus caused in the essential combustion parameters remain within previously defined tolerance limits;

- the combustion conditions of the combustion process are changed in such a way as to counteract the changes in the combustion parameters produced by the return;

-- the material composition of the combustion residue is changed by the return of selected fractions of the combustion residue in such a way that the melting and/or sintering process of the combustion residue is influenced; and

-- the material composition of the combustion residue is changed by the addition of additives in such a way that the melting and/or sintering process of the combustion residue is influenced.

It is obvious that only a single one of the indicated process steps is sufficient to solve the problem described above. The larger the number of these process steps which are used jointly, the more favorable the combustion conditions and the larger the quantity of combustion residue which can be returned.

In an advantageous elaboration of the invention, the selected fractions of the combustion residue have a grain size of 2-10 mm.

In conjunction with the change in material composition, it is also possible to change the composition of the combustion bed on the grate in such a way that the melting and/or sintering processes are accelerated or proceed at lower temperatures. For this purpose, substances which have the effect of lowering the melting point can be mixed into the fuel or into the combustion residues to be returned. These can be silicate compounds such as boron silicate and similar compounds. In principle, therefore, any substance known to produce such effects can be used.

In an advantageous embodiment of the invention, scrap metal and especially scrap iron is used as an additive. This scrap can be recovered from the grate by known separation methods, or it can be obtained from an external source.

It is advantageous to grind up the scrap metal before it is added. The ground-up scrap

metal can have a grain size of 1-20 mm.

The combustion or partial combustion of this scrap leads to the formation of metal oxides and to the local release of large amounts of heat, which has an advantageous effect on the melting and sintering behavior. This is especially true when the basicity of the combustion residue is decreased as a result. The basicity can be defined in simplified form as:

$$B = (x_{\text{CaO}} + x_{\text{FeO}})/(x_{\text{SiO}_2} + x_{\text{Fe}_2\text{O}_3}),$$

where x stands for the molar fraction of the oxide component relative to an average composition of combustion residue. An especially preferred type of return is to meter the addition of scrap metal in such a way that the basicity B of the combustion residue is between 0.3 and 0.7. A preferred method of regulating the basicity of the combustion residue is to adjust the degree to which the scrap supplied or recycled as an additive is ground up. For example, the scrap metal can be ground up more finely when the basicity of the combustion residue is above a predetermined limit in the range of 0.3-0.7.

In another advantageous embodiment of the invention, the combustion residue can be returned directly to the combustion chamber. It is advantageous in this case for the combustion residue to be returned to the grate.

An especially preferred form of return is to return the combustion residue to the feeding disk. When this method is used, it is possible to determine very quickly how the combustion process is being affected, and at the same time this return method is advantageous because the temperatures on the feeding disk are not yet as high as they are in the primary combustion zone, as a result of which the device used to return the residue is not subjected to extreme temperature loads.

The combustion process can be influenced in an especially advantageous manner by

monitoring one of the essential combustion parameters, namely, the position of the burn-out zone. The feed of combustion residue should be reduced, for example, when the burn-out zone starts to migrate toward the discharge end of the grate as a result of a drop in the calorific value of the fuel/residue mixture present on the grate. Conversely, the amount of combustion residue being returned should be increased when the burn-out zone starts to migrate toward the feed end.

The expert can choose from among many different methods for changing and monitoring the essential combustion parameters.

One of the essential combustion conditions is the weight of fuel supplied per unit time. In addition to the weight of the fuel, essential combustion parameters include the calorific value of the fuel, its moisture content, and its ash content.

If the calorific value of the fuel drops, the amount of combustion residue supplied should be decreased and vice versa.

The moisture content of the fuel can be determined even before it reaches the combustion chamber by the use of a microwave detector, for example, installed in the area of the fuel loading or feed shaft. When the moisture content increases, the calorific value of the fuel decreases, even though its composition may otherwise remain the same, so that the amount of combustion residue supplied should be decreased -- and vice versa.

Other essential combustion parameters are the temperature of the combustion bed and the temperature distribution over the combustion bed. These combustion parameters can be monitored by means of an infrared camera, for example. Higher temperatures of the combustion bed make it possible to return larger amounts of combustion residue and vice versa.

Another essential combustion condition is the amount of combustion air, including the amounts of both the primary and the secondary combustion air as well as possibly the amount of returned off-gas.

Another essential combustion condition is the temperature of the combustion air, which is adjusted, for example, by means of an air preheater.

The combustion process can be strongly influenced by another essential combustion condition, namely, the oxygen content of the combustion air, because the control of the oxygen content exerts a significant effect on the primary combustion process and especially on the temperature of the combustion bed.

Another essential combustion condition is the point at which the combustion air is introduced. Especially sensitive control can be achieved here by dividing the grate both in the longitudinal direction and in the transverse direction into several under-grate blast zones, each of which is supplied with primary air and oxygen at specially calculated rates.

Other essential combustion conditions with which the combustion process can be influenced significantly are the stoking speed of the grate and the duration of the stoking. These two factors determine the rate at which the fuel is turned over within the combustion bed. Especially suitable for this purpose is a reciprocating grate slanted down toward the discharge end, where every other grate section is movable and the sections in between are stationary. With this design, the fuel is turned over continuously as it travels from the feed end to the discharge end, so that fuel components which were on the top of the fuel bed for a certain period of time wind up at the bottom, directly on the grate. Fuel which is already incandescent is thus mixed effectively with the freshly added fuel in the starting area, and the fuel in the areas farther down, toward the discharge end, is effectively aerated and loosened.

To establish arbitrary limits within which combustion residues are returned, it is possible to use the amount of heat released and the emission of pollutants, both of which will have an effect on the setting of these limits.

The invention is explained in greater detail below on the basis of a flow chart and an exemplary embodiment of an incinerator:

-- Figure 1 shows a flow chart of a basic process, and

-- Figure 2 shows a schematic diagram of an incinerator for implementing the process.

As shown in Figure 1, 1,000 kg of trash with an ash content of 220 kg is dumped onto a furnace grate and burned in such a way that 25-75% of the combustion residue obtained is already converted completely to sintered slag. The total weight of the combustion residue, including that which was previously returned, is 340 kg. Of this amount, 320 kg falls into a wet deslagger, is quenched there, and then discharged. 190 kg of completely sintered inert granulate and 30 kg of scrap iron are separated from this residue by a separation process, which comprises a sieving and possibly a washing step as well as a magnetic metal separation step. The granulate and some of the scrap iron are sent on to other recycling processes. The amount of scrap iron which is returned depends on the basicity of the combustion residue. In this example, 10 kg of scrap iron is returned, and 20 kg is sent for recycling. 110 kg of combustion residue which has not yet been sintered is sent back to the combustion process. 20 kg of fly ash leaves the combustion chamber with the off-gases. 50% of this ash is returned in the present example, and the other 50% is sent to a separate disposal process.

The incinerator illustrated schematically in Figure 2 comprises a feed shaft 1, into which the fuel is loaded, and a feeding disk 2 with a charging element 3, which conveys the fuel into the combustion chamber 4. 3a designates a variable drive device, which makes it

possible to regulate the rate at which the fuel is loaded as a function of a combustion parameter. Here the fuel, designated 5, drops onto a grate 6, which is designed as a reciprocating grate, and which executes stoking movements under the action of a drive unit 7. For this purpose, the drive unit 7 acts on the transmission element 8 to which every second grate section is connected, which means that a stationary grate section follows every movable grate section. An automatic controller 7a provides a variable drive so that the stoking speed can be adjusted as a function of other combustion parameters. In the case of the grate shown here, five different under-grate blast chambers 9a-9e are provided in a row in the longitudinal direction, each of which is also divided in the transverse direction, so that the quantity and distribution of the primary combustion air can be adapted to the specific requirements on the grate. The primary combustion air is supplied by a blower 10, indicated schematically, and the flow rate of the combustion air is regulated by valves (not shown) in the individual feed lines 11a-11e. The combustion air feed rate is controlled by means of an automatic controller 10a. The numbers 12 and 13 designate secondary air nozzles, which lead from feed lines 14 and 15, through which secondary air can be introduced into the combustion chamber 4.

At the bottom end of the grate, the slag and other combustion residues fall into a wet deslagger 16, from which they are sent to a separator 17. The unsintered or unmelted residual slag is then sent through a line 18 to the loading area above the feeding disk and mixed with the fuel, thus arriving back on the grate again. The separator, designated 17, is intended merely to symbolize in schematic fashion the separation process explained in conjunction with Figure 1. An infrared camera 19 monitors the combustion process on the grate 6. A central control unit 20 controls the various controllers, i.e., controller 3a which adjusts the feed rate, controller 7a for the stoking speed, controller 10a for the primary air feed rate, and controller

21a for the oxygen feed rate, which is supplied through a distributor 21 to the individual primary air chambers 9a-9e.

The system works in the following way:

As already described in conjunction with Figure 1, the goal of this process is to return unmelted or unsintered combustion residue to the combustion process. Thus, for example, an infrared camera 19 monitors the combustion bed and thus determines the distribution of the combustion mass and the temperature of the combustion bed. As a function of these combustion parameters, a central control unit 20 will tell the controller 3a, for example, how to adjust the amount of fuel being supplied. This central control unit can also tell the controller 10a how to change the feed rate of combustion air. Another possibility is for the central control unit 20 to tell the controller 7a how to change the stoking speed. A controller 21a, which is also commanded by the central control unit 20, adjusts the amount of oxygen being supplied to the individual under-grate blast chambers 9a-9e. In the exemplary embodiment shown here, of course, not all of the possible control options are shown schematically; on the contrary, only a few of the especially important control operations are shown, by means of which it is possible to control the combustion process in such a way that as much of the combustion residue as possible can be returned to the grate.

CLAIMS

1. Process for influencing the properties of combustion residue from a combustion plant, especially a waste incinerator, in which the fuel is burned on a grate and the accumulating unmelted and/or unsintered combustion residue is returned to the combustion process, characterized in that the melting and/or sintering processes in the combustion bed are regulated by means of at least one of the following process steps:

-- the residue is returned only as long as, and only in such an amount that, the changes thus caused in the essential combustion parameters remain within previously defined tolerance limits;

-- the combustion conditions of the combustion process are changed in such a way as to counteract the changes in the combustion parameters produced by the return;

-- the material composition of the combustion residue is changed by the return of selected fractions of the combustion residue in such a way that the melting and/or sintering process of the combustion residues is influenced; and

-- the material composition of the combustion residue is changed by the addition of additives in such a way that the melting and/or sintering process of the combustion residue is influenced.

2. Process according to Claim 1, characterized in that the selected fractions of the combustion residue have a grain size of 2-10 mm.

3. Process according to Claim 1 or Claim 2, characterized in that scrap metal and especially scrap iron is used as an additive.

4. Process according to Claim 3, characterized in that the scrap metal is ground up

before it is added.

5. Process according to Claim 4, characterized in that the ground-up scrap metal has a grain size of 1-20 mm.

6. Process according to one of Claims 1-5, characterized in that the combustion residue is returned directly to the combustion chamber.

7. Process according to Claim 6, characterized in that the combustion residue is returned to the grate.

8. Process according to Claim 6, characterized in that the combustion residue is returned to the feeding disk.

9. Process according to one of Claims 1-8, characterized in that an essential combustion parameter is the location of the burn-out zone.

10. Process according to one of Claims 1-8, characterized in that an essential combustion condition is the weight of fuel supplied per unit time.

11. Process according to one of Claims 1-8, characterized in that an essential combustion parameter is the calorific value of the fuel.

12. Process according to one of Claims 1-8, characterized in that an essential combustion parameter is the moisture content of the fuel.

13. Process according to one of Claims 1-8, characterized in that an essential combustion parameter is the temperature of the combustion bed and the temperature distribution over the combustion bed.

14. Process according to one of Claims 1-8, characterized in that an essential combustion condition is the feed rate of the combustion air.

15. Process according to one of Claims 1-8, characterized in that an essential

combustion condition is the temperature of the combustion air.

16. Process according to one of Claims 1-8, characterized in that an essential combustion condition is the oxygen content of the combustion air.

17. Process according to one of Claims 1-8, characterized in that an essential combustion condition is the point at which the combustion air is introduced.

18. Process according to one of Claims 1-8, characterized in that an essential combustion condition is the stoking speed, that is, the speed at which the fuel is turned over within the combustion bed.

19. Process according to one of Claims 1-8, characterized in that the tolerance limits are influenced by the release of heat.

20. Process according to one of Claims 1-8, characterized in that the tolerance limits are influenced by the emissions of pollutants.

21. Process according to one of Claims 1-8, characterized in that the quantity and type of additives or of the selectively returned fractions of combustion residue are selected as a function of the composition of the combustion residue.

22. Process according to one of Claims 1-8, characterized in that the quantity and type of additives or of the selectively returned fractions of combustion residue are selected as a function of the basicity of the combustion residue.

23. Process according to one of Claims 1-8, characterized in that the quantity of supplied scrap metal or of returned scrap metal separated from the grate ash is increased at a basicity above a selected tolerance limit in the range of 0.3-0.7, whereas the amount is decreased below this tolerance limit.