

22 Oct 04

2004062329

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
13 November 2003 (13.11.2003)

PCT

(10) International Publication Number
WO 03/093381 A1

(51) International Patent Classification⁷: C09D 167/06,
163/10, 175/14, B29C 63/34

(21) International Application Number: PCT/NL03/00321

(22) International Filing Date: 1 May 2003 (01.05.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
1020533 3 May 2002 (03.05.2002) NL

(71) Applicant (for all designated States except US): DSM IP
ASSETS B.V. [NL/NL]; Het Overloon 1, NL-6411 TE
Heerlen (NL).

(72) Inventor; and

(75) Inventor/Applicant (for US only): BESTEN DEN, Cor-
nelis [NL/NL]; Vackordestraat 90, NL-8081 TM Elburg
(NL).

(74) Agent: SCHMEETZ, Marcel, Max, Hubertina, Jo-
hanna; DSM Patents & Trademarks, P.O. Box 9, NL-6160
MA Geleen (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



162162



ACTION

WO 03/093381 A1

(54) Title: RESIN COMPOSITION FOR (RE)LINING OF PIPE SYSTEMS, ETC.

(57) Abstract: The invention relates to a curable resin composition for use in (re)lining containing a curable resin dissolved in a copolymerizable free monomer to which an initiator and optionally other additives have been added, the curable resin composition consisting of: (A) 30-70 wt.% of an unsaturated polyester resin, a vinyl ester resin, a vinyl ester urethane resin or a mixture of such resins, (B) 30-70 wt.% of a copolymerizable free monomer or a mixture thereof, it being understood that the wt.% of styrene and/or methyl methacrylate therein does not exceed 20 wt.%, and (C) 0.05-5 wt.% of an initiator, the total of the weight percentages of the components (A), (B) and (C) being 100. The invention similarly relates to the use of such a curable resin composition in flexible, sleeve-shaped objects for use in (re)lining, as well as a process for (re)lining a tube, tank or vessel with such a flexible, sleeve-shaped object.