

Description

This invention relates to oil soluble compositions useful as multifunctional viscosity index improver additives for oleaginous compositions, including lubricating oil compositions, and to concentrates containing said additives.

Nitrogen and ester containing lubricating oil multifunctional viscosity index improver, e.g., viscosity index improver-dispersant, additives have been widely used by the industry. Typically, these multifunctional viscosity index improvers are prepared from a long chain hydrocarbon polymer by reacting the polymer with an acid producing moiety such as acid or maleic anhydride to form the corresponding polymer which is substituted with succinic acid or anhydride groups. Ethylene-propylene has been widely used as the polymer of choice.

High molecular weight ethylene-propylene polymers and ethylene-propylene-diene terpolymers, having viscosity average molecular weights of from about 20,000 to 300,000, are generally produced employing Ziegler catalysts, generally VCl_4 or VOCl_3 with a halide source, such as organoaluminum halides and/or hydrogen halides. Such high molecular weight EP and EPDM polymers find use as viscosity index improvers. See, e.g., U.S. Patents 3,563,964; 3,697,429; 4,306,041; 4,540,753; 4,575,574; and 4,666,619.

The concept of derivatizing V.I. improving high molecular weight ethylene copolymers with acid or anhydride moieties such as maleic anhydride followed by reaction with an amine to form a multifunctional viscosity index improver, e.g., a viscosity index improver-dispersant, oil additive is known in the art as indicated by the following patents.

U.S. Patent 3,316,177 teaches ethylene copolymers of at least 50,000, such as ethylene-propylene, or ethylene-propylene-diene, which are heated to elevated temperatures in the presence of oxygen so as to oxidize the polymer and cause its reaction with maleic anhydride which is present during the oxidation. The resulting polymer can then be reacted with alkylene polyamines.

U.S. Patent 3,326,804 teaches reacting ethylene copolymers with oxygen or ozone, to form a hydroperoxidized polymer, which is grafted with maleic anhydride followed by reaction with polyalkylene polyamines. Preferred are ethylene-propylene copolymers, having M_v from 100,000 to 500,000, prepared by Ziegler type catalysts.

U.S. Patent 4,160,739 teaches an ethylene copolymer ($M_v = 10,000$ to $200,000$) which is grafted, using a free radical technique, with alternating maleic anhydride and a second polymerizable monomer such as methacrylic acid, which materials are reacted with an amine having a single primary, or a single secondary, amine group.

U.S. Patent 4,161,452 relates to graft copolymers wherein the backbone polymer is a polymeric hydrocarbon such as EP copolymer or EPDM ($M_v = 10,000$ to $200,000$) and the grafted units are the residues of an addition copolymerizable monomer system comprising, e.g., maleic anhydride, and at least one other addition monomer.

U.S. Patent 4,171,273 reacts an ethylene copolymer ($M_v = 10,000$ to $100,000$) with maleic anhydride in the presence of a free radical initiator and then with mixtures of C_4 to C_{12} n-alcohol and amine such as N-aminopropylmorpholine or dimethylamino propyl amine to form a V.I.-dispersant-pour depressant additive.

U.S. Patent 4,517,104 relates to EP and EPDM viscosity index improver-dispersant additives prepared from EP polymer ($M_n = 5000$ to $500,000$), by maleic anhydride grafting and reaction with polyamines.

The following references include disclosures of EP/EPDM polymers of M_n of 700/500,000, also prepared by conventional Ziegler catalysts.

U.S. Patent 4,089,794 teaches grafting the ethylene copolymer ($M_n = 700$ to $500,000$) with maleic anhydride using peroxide in a lubricating oil solution, wherein the grafting is preferably carried out under nitrogen, followed by reaction with polyamine.

U.S. Patent 4,137,185 teaches reacting C_1 to C_{30} monocarboxylic acid anhydrides, and dicarboxylic anhydrides, such as acetic anhydride, succinic anhydride, etc. with an ethylene copolymer ($M_n = 700$ to $500,000$) reacted with maleic anhydride and a polyalkylene polyamine to inhibit cross linking and viscosity increase due to further reaction of any primary amine groups which were initially unreacted.

U.S. Patent 4,144,181 is similar to 4,137,185 in that it teaches using a sulfonic acid to inactivate the remaining primary amine groups when a maleic anhydride grafted ethylene-propylene copolymer ($M_n = 700$ to $500,000$) is reacted with a polyamine.

U.S. Patent 4,219,432 teaches maleic anhydride grafted ethylene copolymer ($M_n = 700$ to $500,000$) reacted with a mixture of an amine having only one primary group together with a second amine having two or more primary groups.

Related disclosures of maleic anhydride grafted, aminated ethylene-propylene polymer viscosity improver-dispersant additives useful in lubricating oil compositions are contained in U.S. Patents 4,507,515;

4,557,847; 4,632,769; 4,693,838; and 4,707,285.

However, these conventional multifunctional viscosity index improvers derived from conventional ethylene alpha-olefin copolymers by such methods as free-radical initiated grafting require relatively harsh reaction conditions in order to graft the acid or anhydride moieties such as maleic anhydride onto the ethylene alpha-olefin copolymer backbone. This may result in economic disadvantages, the formation of deleterious or unwanted byproducts, and incomplete reaction of the ethylene alpha-olefin copolymer with the acid or anhydride moieties (low active ingredient - a.i.). The present invention, by utilizing an ethylene alpha-olefin copolymer having a high degree of terminal ethylenylidene unsaturation, remedies these disadvantages.

U.S. Patent 4,668,834 to Uniroyal Chemical discloses preparation (via certain metallocene and alumoxane catalyst systems) and composition of ethylene-alpha olefin copolymers and terpolymers having vinylidene-type terminal unsaturation, which are disclosed to be useful as intermediates in epoxy-grafted encapsulation compositions.

Japanese Published Patent Application 87-129,303A of Mitsui Petrochemical relates to narrow molecular weight distribution ($M_w/M_n < 2.5$) ethylene alpha-olefin copolymers containing 85-99 mol% ethylene, which are disclosed to be used for dispersing agents, modifiers or materials to produce toners. The copolymers (having crystallinity of from 5-85%) are prepared in the presence of a catalyst system comprising Zr compounds having at least one cycloalkadienyl group and alumoxane.

EP-A- 128,046 discloses (co)polyolefin reactor blends of polyethylene and ethylene/higher alphaolefin copolymers prepared by employing described dual-metallocene/alumoxane catalyst systems.

EP-A-129,368 discloses metallocene/alumoxane catalysts useful for the preparation of ethylene homopolymer and ethylene/higher alphaolefin copolymers.

EP-A-1-257,696 relates to a process for dimerising alphaolefins using a catalyst comprising certain metallocene/alumoxane systems.

WO 88/01626 relates to transition metal compound/alumoxane catalysts for polymerising alphaolefins.

GB-A-1,586,464 discloses multifunctional V.I. improver additives which are prepared by reacting high molecular weight, essentially saturated ethylene/propylene copolymers with an unsaturated carboxylic acid material, to attach carboxylic groups randomly along the polymer chain, followed by reaction with a polyamine or polyol, and then by repeated shearing action to reduce the molecular weight of the product to between 70,000 and 300,000.

Attention is directed to the following co-pending applications of the same priority date:

EP-A-440504 describes oleaginous compositions comprising V.I. improver additives comprising ethylene/alphaolefin copolymers having terminal vinylidene unsaturation.

EP-A-440505 describes high molecular weight (M_n 20,000+ - 500,000) V.I. improver additives for oleaginous compositions comprising ethylene/alphaolefin copolymers having terminal vinylidene unsaturation condensed with a hydroxyaromatic compound, an aldehyde and a nucleophilic reactant.

EP-A-440508 describes additives for oleaginous compositions comprising ethylene/alphaolefin copolymers having terminal vinylidene unsaturation substituted with an amine compound.

EP-A-440507 describes oleaginous compositions containing low molecular weight (300 - 20,000) dispersant comprising ethylene/alphaolefin copolymers having terminal vinylidene unsaturation condensed with a hydroxyaromatic compound, an aldehyde and a nucleophilic reactant.

SUMMARY OF THE INVENTION

The present invention is directed to an oil-soluble composition of matter useful as a multifunctional viscosity index improver (MFVI) oleaginous compositions additive comprising ethylene alpha-olefin inter-polymers of from 20,000 to 500,000 number average molecular weight terminally substituted with mono- or dicarboxylic acid producing moieties (preferably acid or anhydride moieties), wherein the ethylene alpha-olefin polymer group is a terminally unsaturated ethylene alpha-olefin polymer wherein the terminal unsaturation comprises ethenylidene unsaturation. The monocarboxylic acid and the dicarboxylic acid or anhydride substituted polymers of this invention are useful per se as additives for lubricating oils, fuel oils, fuels, etc. and can also be reacted with a nucleophilic reagent, such as amines, alcohols, amino alcohols and metal compounds, to form derivative products which are also useful lubricating oil, fuel oil, fuel, etc., additives, e.g., as viscosity index improvers-dispersants.

The materials of the invention are different from the conventional prior disclosure material because of their effectiveness and their ability to provide enhanced lubricating oil viscosity index improvement-dispersancy.

The process of this invention permits the preparation of lubricating oil multifunctional viscosity index improver additives which are characterized by a high active ingredient content (usually at least about 60 wt.%, and up to about 95 wt.%). In addition, the ethylene alpha-olefin polymers substituted by mono- and di-carboxylic acid producing moieties of this invention can be characterized by VR values (as hereinafter defined) of not greater than about 4.1, thereby providing advantageous viscosity modifying properties to the lubricating oils containing them. The present invention can produce such substituted polymers in a highly concentrated form as substantially halogen free materials, thereby reducing the corrosivity processing difficulties and environmental concerns which are associated with halogen-containing lubricating oil additives.

DETAILED DESCRIPTION OF THE INVENTION

PREPARATION OF ETHYLENE ALPHA-OLEFIN POLYMER

The polymers employed in this invention are polymers of ethylene and at least one alpha-olefin having the formula $H_2C=CHR^1$ wherein R^1 is straight chain or branched chain alkyl radical comprising 1 to 18 carbon atoms and wherein the polymer contains a high degree of terminal ethenylidene unsaturation. Preferably R^1 in the above formula is alkyl of from 1 to 8 carbon atoms, and more preferably is alkyl of from 1 to 2 carbon atoms. Therefore, useful comonomers with ethylene in this invention include propylene, 1-butene, hexene-1, octene-1, 4-methylpentene-1, decene-1, dodecene-1, tridecene-1, tetradecene-1, pentadecene-1, hexadecene-1, heptadecene-1, octadecene-1, nonadecene-1 and mixtures thereof (e.g., mixtures of propylene and 1-butene, and the like).

Exemplary of such polymers are ethylene-propylene copolymers, ethylene-butene-1 copolymers and the like. Preferred polymers are copolymers of ethylene and propylene and ethylene and butene-1.

The molar ethylene content of the polymers employed in this invention is preferably in the range of between 20 and 80 percent, and more preferably between 30 and 70 percent. When propylene and/or butene-1 are employed as comonomers(s) with ethylene, the ethylene content of such copolymers is most preferably between 45 and 65 percent, although higher or lower ethylene contents may be present.

The polymers employed in this invention generally possess a number average molecular weight of at least greater than 20,000, preferably at least 25,000, more preferably at least 30,000, and most preferably at least 35,000, or in some instances at least 40,000. Generally, the polymer should not exceed a number average molecular weight of about 500,000, preferably about 200,000, more preferably about 100,000, and most preferably about 50,000. The number average molecular weight for such polymers can be determined by several known techniques. A convenient method for such determination is by size exclusion chromatography (also known as gel permeation chromatography (GPC)) which additionally provides molecular weight distribution information, see W. W. Yau, J.J. Kirkland and D.D. Bly, "Modern Size Exclusion Liquid Chromatography", John Wiley and Sons, New York, 1979.

The polymers employed in this invention preferably exhibit a degree of crystallinity such that, when functionalized, they are readily soluble in mineral oils.

The polymers employed in this invention are further characterized in that up to about 95% and more of the polymer chains possess terminal ethenylidene-type unsaturation. Thus, one end of such polymers will be of the formula $POLY-C(T^1)=CH_2$ wherein T^1 is C_1 to C_{18} alkyl, preferably C_1 to C_8 alkyl, and more preferably C_1 to C_2 alkyl, (e.g., methyl or ethyl) and wherein POLY represents the polymer chain. The chain length of the T^1 alkyl group will vary depending on the comonomer(s) selected for use in the polymerization. A minor amount of the polymer chains can contain terminal ethenyl unsaturation, i.e. $POLY-CH=CH_2$, and a portion of the polymers can contain internal monounsaturations, e.g. $POLY-CH=CH(T^1)$, wherein T^1 is as defined above.

The polymers employed in this invention comprise polymer chains, at least about 30 percent of which possess terminal ethenylidene unsaturation. Preferably at least about 50 percent, more preferably at least about 60 percent, and most preferably at least about 75 percent (e.g. 75-98%), of such polymer chains exhibit terminal ethenylidene unsaturation. The percentage of polymer chains exhibiting terminal ethenylidene unsaturation may be determined by FTIR spectroscopic analysis, titration, or C^{13} NMR.

The polymers employed in this invention may generally be prepared substantially in accordance with the procedures described in U.S. Patent Nos. 4,752,597 and 4,871,705, in European Patent Publications 128,046, 129,368 and 0260999.

The polymers for use in the present invention can be prepared by polymerizing monomer mixtures comprising ethylene in combination with other monomers such as alpha-olefins having from 3 to 20 carbon atoms (and preferably from 3-4 carbon atoms, i.e., propylene, butene-1, and mixtures thereof) in the

presence of a catalyst system comprising at least one metallocene (e.g., a cyclopentadienyl-transition metal compound) and an alumoxane compound. The comonomer content can be controlled through the selection of the metallocene catalyst component and by controlling the partial pressure of the various monomers.


The catalysts employed in the production of the reactant polymers are organometallic coordination compounds which are cyclopentadienyl derivatives of a Group 4b metal of the Periodic Table of the Elements (56th Edition of Handbook of Chemistry and Physics, CRC Press (1975)) and include mono, di and tricyclopentadienyls and their derivatives of the transition metals. Particularly desirable are the metallocene of a Group 4b metal such as titanium, zirconium, and hafnium. The alumoxanes employed in forming the reaction product with the metallocenes are themselves the reaction products of an aluminum trialkyl with water.

In general, at least one metallocene compound is employed in the formation of the catalyst. As indicated, supra, metallocene is a metal derivative of a cyclopentadiene. The metallocenes usefully employed in accordance with this invention contain at least one cyclopentadiene ring. The metal is selected from the Group 4b preferably titanium, zirconium, and hafnium, and most preferably hafnium and zirconium. The cyclopentadienyl ring can be unsubstituted or contain one or more substituents (e.g., from 1 to 5 substituents) such as, for example, a hydrocarbyl substituent (e.g., up to 5 C₁ to C₅ hydrocarbyl substituents) or other substituents, e.g. such as, for example, a trialkyl silyl substituent. The metallocene can contain one, two, or three cyclopentadienyl rings; however, two rings are preferred.

Useful metallocenes can be represented by the general formulas:



wherein Cp is a cyclopentadienyl ring, M is a Group 4b transition metal, R is a hydrocarbyl group or hydrocarboxy group having from 1 to 20 carbon atoms, X is a halogen, and m is a whole number from 1 to 3, n is a whole number from 0 to 3, and q is a whole number from 0 to 3.



wherein (C₅R'_k) is a cyclopentadienyl or substituted cyclopentadienyl, each R' is the same or different and is hydrogen or a hydrocarbyl radical such as alkyl, alkenyl, aryl, alkylaryl, or arylalkyl radical containing from 1 to 20 carbon atoms, a silicon containing hydrocarbyl radical, or hydrocarbyl radicals wherein two carbon atoms are joined together to form a C₄-C₆ ring, R' is a C₁-C₄ alkylene radical, a dialkyl germanium or silicon, or a alkyl phosphine or amine radical bridging two (C₅R'_k) rings, Q is a hydrocarbyl radical such as aryl, alkyl, alkenyl, alkylaryl, or aryl alkyl radical having from 1-20 carbon atoms, hydrocarboxy radical having from 1-20 carbon atoms or halogen and can be the same or different from each other, Q' is an alkylidene radical having from 1 to about 20 carbon atoms, s is 0 or 1, g is 0, 1 or 2, s is 0 when g is 0, k is 4 when s is 1, and k is 5 when s is 0, and M is as defined above. Exemplary hydrocarbyl radicals are methyl, ethyl, propyl, butyl, amyl, isoamyl, hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl and the like. Exemplary silicon containing hydrocarbyl radicals are trimethylsilyl, triethylsilyl and triphenylsilyl. Exemplary halogen atoms include chlorine, bromine, fluorine and iodine and of these halogen atoms, chlorine is preferred. Exemplary hydrocarboxy radicals are methoxy ethoxy, butoxy, amyloxy and the like. Exemplary of the alkylidene radicals is methylidene, ethylidene and propylidene.

Illustrative examples of the metallocenes represented by formula I are dialkyl metallocenes such as bis(cyclopentadienyl)titanium dimethyl, bis(cyclopentadienyl)titanium diphenyl, bis(cyclopentadienyl)zirconium dimethyl, bis(cyclopentadienyl)zirconium diphenyl, bis(cyclopentadienyl)hafnium dimethyl and diphenyl, bis(cyclopentadienyl)titanium di-neopentyl, bis(cyclopentadienyl)zirconium di-neopentyl, bis(cyclopentadienyl)titanium dibenzyl, bis(cyclopentadienyl)zirconium dibenzyl, bis(cyclopentadienyl)vanadium dimethyl; the mono alkyl metallocenes such as bis(cyclopentadienyl)titanium methyl chloride, bis(cyclopentadienyl)titanium ethyl chloride bis(cyclopentadienyl)titanium phenyl chloride, bis(cyclopentadienyl)zirconium hydrochloride, bis(cyclopentadienyl)zirconium methyl chloride, bis(cyclopentadienyl)zirconium ethyl chloride, bis(cyclopentadienyl)zirconium phenyl chloride, bis(cyclopentadienyl)titanium methyl bromide, bis(cyclopentadienyl)titanium methyl iodide, bis(cyclopentadienyl)titanium ethyl bromide, bis(cyclopentadienyl)titanium ethyl iodide, bis(cyclopentadienyl)zirconium methyl bromide, bis(cyclopentadienyl)zirconium methyl iodide, bis(cyclopentadienyl)zirconium ethyl bromide, bis(cyclopentadienyl)zirconium ethyl iodide, bis(cyclopentadienyl)zirconium phenyl bromide, bis(cyclopentadienyl)zirconium phenyl iodide; the trialkyl

metallocenes such as cyclopentadienyltitanium trimethyl, cyclopentadienyl zirconium triphenyl, and cyclopentadienyl zirconium trineopentyl, cyclopentadienylzirconium trimethyl, cyclopentadienylhafnium triphenyl, cyclopentadienylhafnium trineopentyl, and cyclopentadienylhafnium trimethyl.

Illustrative examples of II and III metallocenes which can be usefully employed are monocyclopentadienyls titanocenes such as, pentamethylcyclopentadienyl titanium trichloride, pentaethylcyclopentadienyl titanium trichloride, bis(pentamethylcyclopentadienyl) titanium diphenyl, the carbene represented by the formula bis(cyclopentadienyl)titanium=CH₂ and derivatives of this reagent such as bis(cyclopentadienyl)-Ti=CH₂.Al(CH₃)₃, (Cp₂TiCH₂)₂, Cp₂TiCH₂CH(CH₃)CH₂, Cp₂Ti-CH₂CH₂CH₂; substituted bis(Cp)Ti(IV) compounds such as bis(indenyl) titanium diphenyl or dichloride, bis(methylcyclopentadienyl)titanium diphenyl or dihalides; dialkyl, trialkyl, tetra-alkyl and penta-alkyl cyclopentadienyl titanium compounds such as bis(1,2-dimethylcyclopentadienyl)titanium diphenyl or dichloride, bis(1,2-diethylcyclopentadienyl)titanium diphenyl or dichloride and other dihalide complexes; silicon, phosphine, amine or carbon bridged cyclopentadiene complexes, such as dimethylsilyldicyclopentadienyl titanium diphenyl or dichloride, methyl phosphine dicyclopentadienyl titanium diphenyl or dichloride, methylenedicyclopentadienyl titanium diphenyl or dichloride and other complexes described by formulae II and III.

Illustrative examples of the zirconocenes of Formula II and III which can be usefully employed are, pentamethylcyclopentadienyl zirconium trichloride, pentaethylcyclopentadienyl zirconium trichloride, the alkyl substituted cyclopentadienes, such as bis(ethylcyclopentadienyl)zirconium dimethyl, bis(betaphenylpropylcyclopentadienyl) zirconium dimethyl, bis(methylcyclopentadienyl)zirconium dimethyl, bis(n-butylcyclopentadienyl)zirconium dimethyl bis(cyclohexylmethylcyclopentadienyl)zirconium dimethyl bis(n-octylcyclopentadienyl)zirconium dimethyl, and haloalkyl and dihydride, and dihalide complexes of the above; dialkyl, trialkyl, tetra-alkyl, and penta-alkyl cyclopentadienes, such as bis(pentamethylcyclopentadienyl)zirconium diphenyl, bis(pentamethylcyclopentadienyl)zirconium dimethyl, bis(1,2-dimethylcyclopentadienyl)zirconium dimethyl and mono and dihalide and hydride complexes of the above; silicon, phosphorus, and carbon bridged cyclopentadiene complexes such as dimethylsilyldicyclopentadienyl zirconium dimethyl, methyl halide or dihalide, and methylene dicyclopentadienyl zirconium dimethyl, methyl halide, or dihalide. Mono, di and tri-silyl substituted cyclopentadienyl compounds such as bis(trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl bis(1,3-di-trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl and bis(1,2,4-tri-trimethylsilylcyclopentadienyl)zirconium dichloride and dimethyl. Carbenes represented by the formulae Cp₂Zr=CH₂P(C₆H₅)₂CH₃, and derivatives of these compounds such as Cp₂ZrCH₂CH(CH₃)CH₂.

Mixed cyclopentadienyl metallocene compounds such as cyclopentadienyl (pentamethyl cyclopentadienyl)zirconium dichloride, (1,3-di-trimethylsilylcyclopentadienyl) (pentamethylcyclopentadienyl) zirconium dichloride, and cyclopentadienyl(indenyl) zirconium dichloride can be employed.

Most preferably, the polymers used in this invention are substantially free of ethylene homopolymer.

Bis(cyclopentadienyl)hafnium dichloride, bis(cyclopentadienyl)hafnium; dimethyl, bis(cyclopentadienyl)-vanadium dichloride and the like are illustrative of other metallocenes.

Some preferred metallocenes are bis(cyclopentadienyl)zirconium; dimethyl, bis(cyclopentadienyl)-zirconium dichloride; bis(cyclopentadienyl)titanium dichloride; bis(methylcyclopentadienyl) zirconium dichloride; bis(methylcyclopentadienyl)titanium dichloride; bis(n-butylcyclopentadienyl)zirconium dichloride; dimethylsilyldicyclopentadienyl zirconium dichloride; bis(trimethylsilylcyclopentadienyl)zirconium dichloride; and dimethylsilyldicyclopentadienyl titanium dichloride; bis(indenyl)zirconium dichloride; bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; the racemic and/or meso isomer of 1,2-ethylene-bridged bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; the racemic and/or meso isomer of 1,1-dimethylsilyl-bridged bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride; and the racemic and/or meso isomer of 1,1-dimethylsilyl-bridged bis(methylcyclopentadienyl)zirconium dichloride.

The alumoxane compounds useful in the polymerization process may be cyclic or linear. Cyclic alumoxanes may be represented by the general formula (R-Al-O)_n while linear alumoxanes may be represented by the general formula R(R-Al-O)_{n'}AlR₂. In the general formula R is a C₁-C₅ alkyl group such as, for example, methyl, ethyl, propyl, butyl and pentyl, n is an integer of from 3 to 20, and n' is an integer from 1 to 20. Preferably, R is methyl and n and n' are 4-18. Generally, in the preparation of alumoxanes from, for example, aluminum trimethyl and water, a mixture of the linear and cyclic compounds is obtained.

The alumoxane can be prepared in various ways. Preferably, they are prepared by contacting water with a solution of aluminum trialkyl, such as, for examples, aluminum trimethyl, in a suitable organic solvent such as toluene or an aliphatic hydrocarbon. For example, the aluminum alkyl is treated with water in the form of a moist solvent. In an alternative method, the aluminum alkyl such as aluminum trimethyl can be desirably contacted with a hydrated salt such as hydrated copper sulfate or ferrous sulfate. Preferably, the alumoxane is prepared in the presence of a hydrated ferrous sulfate. The method comprises treating a

dilute solution of aluminum trimethyl in, for example, toluene, with ferrous sulfate represented by the general formula $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$. The ratio of ferrous sulfate to aluminum trimethyl is desirably about 1 mole of ferrous sulfate for 6 to 7 moles of aluminum trimethyl. The reaction is evidenced by the evolution of methane.

5 The mole ratio of aluminum in the alumoxane to total metal in the metallocenes which can be usefully employed can be in the range of 0.5:1 to 1000:1, and desirably 1:1 to 100:1. Preferably, the mole ratio will be in the range of 50:1 to 5:1 and most preferably 20:1 to 5:1.

The solvents used in the preparation of the catalyst system are inert hydrocarbons, in particular a hydrocarbon that is inert with respect to the catalyst system. Such solvents are well known and include, for
10 example, isobutane, butane, pentane, hexane, heptane, octane, cyclohexane, methylcyclohexane, toluene, xylene and the like.

Polymerization is generally conducted at temperatures ranging between 20° and 300°C, preferably between 30° and 200°C. Reaction time is not critical and may vary from several hours or more to several minutes or less, depending upon factors such as reaction temperature, the monomers to be copolymerized,
15 and the like. One of ordinary skill in the art may readily obtain the optimum reaction time for a given set of reaction parameters by routine experimentation.

The catalyst systems described herein are suitable for the polymerization of olefins in solution over a wide range of pressures. Preferably, the polymerization will be completed at a pressure of from 10 to 3,000 bar, and generally at a pressure within the range from 40 bar to 2,000 bar, and most preferably, the
20 polymerization will be completed at a pressure within the range from 50 bar to 1,500 bar.

After polymerization and, optionally, deactivation of the catalyst (e.g., by conventional techniques such as contacting the polymerization reaction medium with water or an alcohol, such as methanol, propanol, isopropanol, etc., or cooling or flashing the medium to terminate the polymerization reaction), the product polymer can be recovered by processes well known in the art. Any excess reactants may be flashed off
25 from the polymer.

The polymerization may be conducted employing liquid monomer, such as liquid propylene, or mixtures of liquid monomers (such as mixtures of liquid propylene and 1-butene), as the reaction medium. Alternatively, polymerization may be accomplished in the presence of a hydrocarbon inert to the polymerization such as butane, pentane, isopentane, hexane, isooctane, decane, toluene, xylene, and the like.

30 In those situations wherein the molecular weight of the polymer product that would be produced at a given set of operating conditions is higher than desired, any of the techniques known in the prior art for control of molecular weight, such as the use of hydrogen and/or polymerization temperature control, may be used in the process of this invention. If so desired, the polymerization may be carried out in the presence of hydrogen to lower the polymer molecular weight. Care should be taken to assure that terminal ethenylidene
35 unsaturation is not reduced to less than about 30 percent of the polymer chains.


However, the polymers are preferably formed in the substantial absence of added H_2 gas, that is, the absence of H_2 gas added in amounts effective to substantially reduce the polymer molecular weight. More preferably, the polymerizations will be conducted employing less than 5 wppm, and more preferably less than 1 wppm, of added H_2 gas, based on the moles of the ethylene monomer charged to the polymerization
40 zone.

When carrying out the polymerization in a batch-type fashion, the reaction diluent (if any), ethylene and alpha-olefin comonomer(s) are charged at appropriate ratios to a suitable reactor. Care must be taken that all ingredients are dry, with the reactants typically being passed through molecular sieves or other drying means prior to their introduction into the reactor. Subsequently, either the catalyst and then the cocatalyst,
45 or first the cocatalyst and then the catalyst are introduced while agitating the reaction mixture, thereby causing polymerization to commence. Alternatively, the catalyst and cocatalyst may be premixed in a solvent and then charged to the reactor. As polymer is being formed, additional monomers may be added to the reactor. Upon completion of the reaction, unreacted monomer and solvent are either flashed or distilled off, if necessary by vacuum, and the low molecular weight copolymer withdrawn from the reactor.

50 The polymerization may be conducted in a continuous manner by simultaneously feeding the reaction diluent (if employed), monomers, catalyst and cocatalyst to a reactor and withdrawing solvent, unreacted monomer and polymer from the reactor so as to allow a residence time of ingredients long enough for forming polymer of the desired molecular weight and separating the polymer from the reaction mixture.

PREPARATION OF ETHYLENE ALPHA-OLEFIN POLYMER SUBSTITUTED MONO- OR DICARBOXYLIC ACID MATERIAL

The ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material, i.e., acid, anhydride or acid ester of this invention, includes the reaction product of ethylene alpha-olefin polymer with a monounsaturated carboxylic reactant comprising at least one member selected from the group consisting of (i) monounsaturated C₄ to C₁₀ dicarboxylic acid wherein (a) the carboxyl groups are vicinyl, (i.e. located on adjacent carbon atoms) and (b) at least one, preferably both, of said adjacent carbon atoms are part of said mono unsaturation; (ii) derivatives of (i) such as anhydrides or C₁ to C₅ alcohol derived mono- or di-esters of (i); (iii) monounsaturated C₃ to C₁₀ monocarboxylic acid wherein the carbon-carbon double bond is allylic to the carboxy group, i.e. of the structure



and (iv) derivatives of (iii) such as C₁ to C₅ alcohol derived mono- or di-esters of (iii). Upon reaction with the polymer, the monounsaturations of the monounsaturated carboxylic reactant become saturated. Thus, for example, maleic anhydride becomes a polymer substituted succinic anhydride, and acrylic acid becomes a polymer substituted propionic acid.

Typically, from 0.7 to 4.0 (e.g., 0.8 to 2.6), preferably from 1.0 to 2.0, and most preferably from 1.1 to 1.7 moles of said monounsaturated carboxylic reactant are charged to the reactor per mole of polymer charged.

Normally, not all of the polymer reacts with the monounsaturated carboxylic reactant and the reaction mixture will contain unreacted polymer. The unreacted polymer is typically not removed from the reaction mixture (because such removal is difficult and would be commercially infeasible) and the product mixture, stripped of any monounsaturated carboxylic reactant may be employed for further reaction with the amine or alcohol as described hereinafter to make the dispersant.

Characterization of the average number of moles of monounsaturated carboxylic reactant which have reacted per mole of polymer charged to the reaction (whether it has undergone reaction or not) is defined herein as functionality. Said functionality is based upon (i) determination of the saponification number of the resulting product mixture using potassium hydroxide; and (ii) the number average molecular weight of the polymer charged, using techniques well known in the art. Functionality is defined solely with reference to the resulting product mixture. Although the amount of said reacted polymer contained in the resulting product mixture can be subsequently modified, i.e. increased or decreased by techniques known in the art, such modifications do not alter functionality as defined above. The terms ethylene-alpha-olefin polymer substituted monocarboxylic acid material and ethylene-alpha-olefin polymer substituted dicarboxylic acid material are intended to refer to the product mixture whether it has undergone such modification or not.

Accordingly, the functionality of the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid material will be typically at least about 0.5, preferably at least about 0.8, and most preferably at least about 0.9 and will vary typically from 0.5 to 2.8 (e.g., 0.6 to 2), preferably from 0.8 to 1.4, and most preferably from 0.9 to 1.3.

Exemplary of such monounsaturated carboxylic reactants are fumaric acid, itaconic acid, maleic acid, maleic anhydride, chloromaleic acid, chloromaleic anhydride, acrylic acid, methacrylic acid, crotonic acid, cinnamic acid, and lower alkyl (e.g., C₁ to C₄ alkyl) acid esters of the foregoing, e.g., methyl maleate, ethyl fumarate, methyl fumarate, etc.

The polymer can be reacted with the monounsaturated carboxylic reactant by a variety of methods. For example, the polymer can be first halogenated, chlorinated or brominated to 0.05 to 2 wt. %, preferably 0.1 to 1 wt. % chlorine, or bromine, based on the weight of polymer, by passing the chlorine or bromine through the polymer at a temperature of 60 to 250 °C, preferably 110 to 160 °C, e.g. 120 to 140 °C, for 0.5 to 10, preferably 1 to 7 hours. The halogenated polymer may then be reacted with sufficient monounsaturated carboxylic reactant at 100 to 250 °C, usually 180 ° to 235 °C, for 0.5 to 10, e.g. 3 to 8 hours, so the product obtained will contain the desired number of moles of the monounsaturated carboxylic reactant per mole of the halogenated polymer. Processes of this general type are taught in U.S. Patents 3,087,436; 3,172,892; 3,272,746 and others. Alternatively, the polymer and the monounsaturated carboxylic reactant are mixed and heated while adding chlorine to the hot material. Processes of this type are disclosed in U.S. Patents 3,215,707; 3,231,587; 3,912,764; 4,110,349; 4,234,435; and in U.K. 1,440,219.

While chlorination normally helps increase the reactivity of polyolefins with monounsaturated carboxylic reactant, it is not necessary with the present polymers due to their high terminal bond content and reactivity. Preferably, therefore, the polymer and the monounsaturated carboxylic reactant are contacted at elevated temperature to cause a thermal "ene" reaction to take place. Thermal "ene" reactions have been
 5 heretofore described in U.S. Patents 3,361,673 and 3,401,118, the disclosures of which are hereby incorporated by reference in their entirety. It has been surprisingly found that the ethylene alpha-olefin polymers used in this invention having terminal ethenylidene unsaturation readily undergo such thermal "ene" reactions under conditions in which the formation of sediment, or other by-products contributing to product haze, is greatly minimized or avoided altogether. The improved low sediment ene reaction product
 10 mixture is preferably formed using a polymer (more preferably, ethylene-propylene copolymers) having a number average molecular weight of from greater than 20,000 to 500,000, preferably from 25,000 to 200,000, more preferably from 30,000 to 100,000, and most preferably from 35,000 to 50,000, and a polydispersity of less than about 4, preferably less than about 3, e.g., from 1.1 to 3.5, most preferably from 1.2 to 3.

15 In this process, the selected polymer and monounsaturated carboxylic reactant are contacted for a time and under conditions effective to form the desired ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material. Generally, the polymer and monounsaturated carboxylic reactant will be contacted in a polymer to unsaturated carboxylic reactant mole ratio usually from 1:1 to 1:10, and preferably from 1:1 to 1:5, at an elevated temperature, generally from 120 to 260°C, preferably from 160 to 240°C.
 20 The reaction will be generally carried out, with stirring for a time of from 1 to 20 hours, preferably from 2 to 6 hours. The reaction is preferably conducted in the substantial absence of O₂ and water (to avoid competing side reactions), and to this end can be conducted in an atmosphere of dry N₂ gas or other gas inert under the reaction conditions. The reactants can be charged separately or together as a mixture to the reaction zone, and the reaction can be carried out continuously, semi-continuously or batchwise. Although
 25 not generally necessary, the reaction can be carried out in the presence of a liquid diluent or solvent, e.g., a hydrocarbon diluent such as mineral lubricating oil, toluene, xylene, dichlorobenzene and the like. The polymer substituted mono- or dicarboxylic acid material thus formed can be recovered from the liquid reaction mixture, e.g., after stripping the reaction mixture, if desired, with an inert gas such as N₂ to remove unreacted unsaturated carboxylic reactant.

30 The "ene" reaction product mixture thereby obtained has been surprisingly found to have a substantially reduced content of sediment or other solid by-products as impurities and can be employed, without filtering, centrifuging, clarification, phase separation or other conventional product purification treatments, as, e.g., an additive to lubricating oils or as intermediate in the preparation of derivative products for use in lubricating oils, as will be more completely described hereinafter.

35 The ene reaction product mixture is further improved by being substantially free of chlorine, that is, by having a chlorine content of less than about 25 ppm by weight, preferably less than about 10 ppm by weight.

A further advantage of the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material of the instant invention is that by conducting the reaction, i.e., "ene" reaction, of the ethylene alpha-olefin
 40 polymer and the monounsaturated carboxylic reactant in a solvent such as mineral oil, the resultant functionalized reaction product (containing the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material) is substantially free of by-product comprising solvent, e.g., oil, reacted with the monounsaturated carboxylic reactant, e.g., oil-succinic anhydride, which generally is formed when a free radical grafting process is conducted in a solvent such as oil.


45 The ene reaction product mixture comprising the desired ethylene-alpha-olefin substituted mono- or dicarboxylic acid material (e.g., ethylene-propylene polymer-substituted succinic anhydride) formed by the process of this invention will generally contain unreacted polymer, (that is, polymer which is unsubstituted by the mono- or dicarboxylic acid moiety), in a concentration of less than about 40 wt.% (e.g., from 5 to 35 wt.%), more preferably less than about 30 wt.% (e.g. from 10 to 25 wt.%).

50 It will be understood that the ethylene alpha-olefin polymers of this invention which are charged to the alkylation reaction zone can be charged alone or together with (e.g., in admixture with) other polyalkenes derived from alkenes having from 1 to 20 carbon atoms (butene, pentene, octene, decene, dodecene, tetradecene and the like) and homopolymers of C₃ to C₁₀, e.g., C₂ to C₅, monoolefins, and copolymers of C₂ to C₁₀, e.g., C₂ to C₅, monoolefins, said additional polymer having a number average molecular
 55 weight of at least about 900, and a molecular weight distribution of less than about 4.0, preferably less than about 3.0 (e.g. from 1.2 to 2.8). Preferred such additional olefin polymers comprise a major molar amount of C₂ to C₁₀, e.g. C₂ to C₅ monoolefin. Such olefins include ethylene, propylene, butylene, isobutylene, pentene, octene-1, styrene, etc. Exemplary of the additionally charged homopolymers is polypropylene,


polyisobutylene, and poly-n-butene the like as well as interpolymers of two or more of such olefins such as copolymers of: ethylene and propylene (prepared by conventional methods other than as described above for the preferred ethylene alpha-olefin copolymers employed in this invention, that is, ethylene-propylene copolymers which are substantially saturated, wherein less than about 10 wt. % of the polymer chains contain ethylenic unsaturation); butylene and isobutylene; propylene and isobutylene; etc. Other copolymers include those in which a minor molar amount of the copolymer monomers, e.g., 1 to 10 mole %, is a C₄ to C₁₈ non-conjugated diolefin, e.g., a copolymer of isobutylene and butadiene; or a copolymer of ethylene, propylene and 1,4-hexadiene; etc. An especially useful additional such polymer is polyisobutylene. Preferred are mixtures of such polyisobutylene with ethylene-propylene copolymers wherein at least 30 wt. % of the copolymer chains contain terminal ethenylidene monounsaturations as described above.

PREPARATION OF NUCLEOPHILICALLY-SUBSTITUTED DERIVATIVE PRODUCTS

The ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid materials, e.g., ethylene-propylene substituted carboxylic acids/ anhydrides/esters, of this invention, prepared as described above, can be contacted with a nucleophilic reactant, e.g., amines, alcohols, including polyols, amino-alcohols, reactive metal compounds, etc. to form the novel viscosity index improvers-dispersants of this invention. Amine compounds useful as nucleophilic reactants for reaction with the polymer substituted mono- or dicarboxylic acid materials include mono- and (preferably) polyamines, of about 2 to 60, preferably 2 to 40 (e.g. 3 to 20), total carbon atoms and about 1 to 12, preferably 3 to 12, and most preferably 3 to 9 nitrogen atoms in the molecule. These amines may be hydrocarbyl amines or may be hydrocarbyl amines including other groups, e.g., hydroxy groups, alkoxy groups, amide groups, nitriles, imidazoline groups, and the like. Hydroxy amines with 1 to 6 hydroxy groups, preferably 1 to 3 hydroxy groups are particularly useful. Preferred amines are those containing at least two reactive amino groups selected from primary amino groups, secondary amino groups and mixtures thereof. Preferred amines are aliphatic saturated amines, including those of the general formulas:



wherein R, R', R'' and R''' are independently selected from the group consisting of hydrogen; C₁ to C₂₅ straight or branched chain alkyl radicals; C₁ to C₁₂ alkoxy C₂ to C₆ alkylene radicals; C₂ to C₁₂ hydroxy amino alkylene radicals; and C₁ to C₁₂ alkylamino C₂ to C₆ alkylene radicals; and wherein R''' can additionally comprise a moiety of the formula:




wherein R' is as defined above, and wherein r and r' can be the same or a different number of from 2 to 6, preferably 2 to 4; and t and t' can be the same or different and are numbers of from 0 to 10, preferably 2 to 7, and most preferably about 3 to 7, with the proviso that the sum of t and t' is not greater than 15. To assure a facile reaction, it is preferred that R, R', R'', R''', r, r', t and t' be selected in a manner sufficient to provide the compounds of Formulas Va and Vb with typically at least one primary or secondary amine group, preferably at least two primary or secondary amine groups. This can be achieved by selecting at least one of said R, R', R'' or R''' groups to be hydrogen or by letting t in Formula Vb be at least one when R''' is H or when the VI moiety possesses a secondary amino group. The most preferred amine of the above formulas are represented by Formula Vb and contain at least two primary amine groups and at least one, and preferably at least three, secondary amine groups.

Examples of suitable amine compounds include: 1,2-diaminoethane; 1,3-diaminopropane; 1,4-diaminobutane; 1,6-diaminohexane; polyethylene amines such as diethylene triamine; triethylene tetramine;


tetraethylene pentamine; polypropylene amines such as 1,2-propylene diamine; di-(1,2-propylene)tri-amine; di-(1,3-propylene) triamine; N,N-dimethyl-1,3-diaminopropane; N,N-di-(2-aminoethyl) ethylene diamine; N,N-di(2-hydroxyethyl)-1,3-propylene diamine; 3-dodecyloxypropylamine; N-dodecyl-1,3-propane diamine; tris hydroxymethylaminomethane (THAM); diisopropanol amine; diethanol amine; triethanol amine; mono-, di-, and tri-tallow amines; amino morpholines such as N-(3-aminopropyl)morpholine; and mixtures thereof.

Other useful amine compounds include: alicyclic diamines such as 1,4-di(aminomethyl) cyclohexane, and heterocyclic nitrogen compounds such as imidazolines, and N-aminoalkyl piperazines of the general formula (VII):




wherein p_1 and p_2 are the same or different and are each integers of from 1 to 4, and n_1 , n_2 and n_3 are the same or different and are each integers of from 1 to 3. Non-limiting examples of such amines include 2-pentadecyl imidazoline; N-(2-aminoethyl) piperazine; etc. Commercial mixtures of amine compounds may advantageously be used. For example, one process for preparing alkylene amines involves the reaction of an alkylene dihalide (such as ethylene dichloride or propylene dichloride) with ammonia, which results in a complex mixture of alkylene amines wherein pairs of nitrogens are joined by alkylene groups, forming such compounds as diethylene triamine, triethylenetetramine, tetraethylene pentamine and isomeric piperazines. Low cost poly(ethyleneamines) compounds averaging about 5 to 7 nitrogen atoms per molecule are available commercially under trade names such as "Polyamine H", "Polyamine 400", "Dow Polyamine E-100", etc.

Useful amines also include polyoxyalkylene polyamines such as those of the formula (VIII):




where m has a value of about 3 to 70 and preferably 10 to 35; and the formula (IX):



where n''' has a value of about 1 to 40 with the provision that the sum of all the n''' values is from about 3 to about 70 and preferably from about 6 to about 35, and R^4 is a polyvalent saturated hydrocarbon radical of up to ten carbon atoms wherein the number of substituents on the R^4 group is represented by the value of "a", which is a number of from 3 to 6. The alkylene groups in either formula (VIII) or (IX) may be straight or branched chains containing about 2 to 7, and preferably about 2 to 4 carbon atoms.

The polyoxyalkylene polyamines of formulas (VIII) or (IX) above, preferably polyoxyalkylene diamines and polyoxyalkylene triamines, may have average molecular weights ranging from about 200 to about 4000 and preferably from about 400 to about 2000. The preferred polyoxyalkylene polyamines include the polyoxyethylene and polyoxypropylene diamines and the polyoxypropylene triamines having average molecular weights ranging from about 200 to 2000. The polyoxyalkylene polyamines are commercially available and may be obtained, for example, from the Jefferson Chemical Company, Inc. under the trade name "Jeffamines D-230, D-400, D-1000, D-2000, T-403", etc.

A particularly useful class of amines are the polyamido and related amines disclosed in U.S. Patent No. 4,857,217, which comprise reaction products of a polyamine and an alpha, beta unsaturated compound of the formula:



5

wherein X is sulfur or oxygen, Y is -OR⁸, -SR⁸, or -NR⁸(R⁹), and R⁵, R⁶, R⁷, R⁸ and R⁹ are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl. Any polyamine, whether aliphatic, cycloaliphatic, aromatic, heterocyclic, etc., can be employed provided it is capable of adding across the acrylic double bond and amidifying with for example the carbonyl group (-C(O)-) of the acrylate-type compound of formula X, or with the thiocarbonyl group (-C(S)-) of the thioacrylate-type compound of formula X.

When R⁵, R⁶, R⁷, R⁸ or R⁹ in Formula X are hydrocarbyl, these groups can comprise alkyl, cycloalkyl, aryl, alkaryl, aralkyl or heterocyclic, which can be substituted with groups which are substantially inert to any component of the reaction mixture under conditions selected for preparation of the amido-amine. Such substituent groups include hydroxy, halide (e. g., Cl, F, I, Br), -SH and alkylthio. When one or more of R⁵ through R⁹ are alkyl, such alkyl groups can be straight or branched chain, and will generally contain from 1 to 20, more usually from 1 to 10, and preferably from 1 to 4, carbon atoms. Illustrative of such alkyl groups are methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, dodecyl, tridecyl, hexadecyl, octadecyl and the like. When one or more of R⁵ through R⁹ are aryl, the aryl group will generally contain from 6 to 10 carbon atoms (e.g., phenyl, naphthyl).

When one or more of R⁵ through R⁹ are alkaryl, the alkaryl group will generally contain from about 7 to 20 carbon atoms, and preferably from 7 to 12 carbon atoms. Illustrative of such alkaryl groups are tolyl, m-ethyl-phenyl, o-ethyltolyl, and m-hexyltolyl. When one or more of R⁵ through R⁹ are aralkyl, the aryl component generally consists of phenyl or (C₁ to C₆) alkyl-substituted phenol and the alkyl component generally contains from 1 to 12 carbon atoms, and preferably from 1 to 6 carbon atoms. Examples of such aralkyl groups are benzyl, o-ethylbenzyl, and 4-isobutylbenzyl. When one or more of R⁵ and R⁹ are cycloalkyl, the cycloalkyl group will generally contain from 3 to 12 carbon atoms, and preferably from 3 to 6 carbon atoms. Illustrative of such cycloalkyl groups are cyclopropyl, cyclobutyl, cyclohexyl, cyclooctyl, and cyclododecyl. When one or more of R⁵ through R⁹ are heterocyclic, the heterocyclic group generally consists of a compound having at least one ring of 6 to 12 members in which one or more ring carbon atoms is replaced by oxygen or nitrogen. Examples of such heterocyclic groups are furyl, pyranyl, pyridyl, piperidyl, dioxanyl, tetrahydrofuryl, pyrazinyl and 1,4-oxazinyl.

The alpha, beta ethylenically unsaturated carboxylate compounds employed herein have the following formula:

35




40

wherein R⁵, R⁶, R⁷, and R⁸ are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of such alpha, beta-ethylenically unsaturated carboxylate compounds of formula XI are acrylic acid, methacrylic acid, the methyl, ethyl, isopropyl, n-butyl, and isobutyl esters of acrylic and methacrylic acids, 2-butenic acid, 2-hexenoic acid, 2-decenoic acid, 3-methyl-2-heptenoic acid, 3-methyl-2-butenic acid, 3-phenyl-2-propenoic acid, 3-cyclohexyl-2-butenic acid, 2-methyl-2-butenic acid, 2-propyl-2-propenoic acid, 2-isopropyl-2-hexenoic acid, 2,3-dimethyl-2-butenic acid, 3-cyclohexyl-2-methyl-2-pentenoic acid, 2-propenoic acid, methyl 2-propenoate, methyl 2-methyl 2-propenoate, methyl 2-butenate, ethyl 2-hexenoate, isopropyl 2-decenoate, phenyl 2-pentenoate, tertiary butyl 2-propenoate, octadecyl 2-propenoate, dodecyl 2-decenoate, cyclopropyl 2,3-dimethyl-2-butenate, methyl 3-phenyl-2-propenoate, and the like.

50

The alpha, beta ethylenically unsaturated carboxylate thioester compounds employed herein have the following formula:

55



wherein R^5 , R^6 , R^7 , and R^8 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of such alpha, beta-ethylenically unsaturated carboxylate thioesters of formula XII are methylmercapto 2-butenate, ethylmercapto 2-hexenoate, isopropylmercapto 2-decenoate, phenylmercapto 2-pentenoate, tertiary butylmercapto 2-propenoate, octadecylmercapto 2-propenoate, dodecylmercapto 2-decenoate, cyclopropylmercapto 2,3-dimethyl-2-butenate, methylmercapto 3-phenyl-2-propenoate, methylmercapto 2-propenoate, methylmercapto 2-methyl-2-propenoate, and the like.

The alpha, beta ethylenically unsaturated carboxamide compounds employed herein have the following formula:




wherein R^5 , R^6 , R^7 , R^8 and R^9 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of alpha, beta-ethylenically unsaturated carboxamides of formula XIII are 2-butenamide, 2-hexonamide, 2-decenamide, 3-methyl-2-heptenamide, 3-methyl-2-butenamide, 3-phenyl-2-propenamide, 3-cyclohexyl-2-butenamide, 2-methyl-2-butenamide, 2-propyl-2-propenamide, 2-isopropyl-2-hexenamide, 2,3-dimethyl-2-butenamide, 3-cyclohexyl-2-methyl-2-pentenamide, N-methyl 2-butenamide, N-methyl 2-butenamide, N,N-diethyl 2-hexenamide, N-isopropyl 2-decenamide, N-phenyl 2-pentenamide, N-tertiary butyl 2-propenamide, N-octadecyl 2-propenamide, N-N-didodecyl 2-decenamide, N-cyclopropyl 2,3-dimethyl-2-butenamide, N-methyl 3-phenyl-2-propenamide, 2-propenamide, 2-methyl-2-propenamide, 2-ethyl-2-propenamide and the like.

The alpha, beta ethylenically unsaturated thiocarboxylate compounds employed herein have the following formula:



wherein R^5 , R^6 , R^7 and R^8 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of alpha, beta-ethylenically unsaturated thiocarboxylate compounds of formula XIV are 2-butenethioic acid, 2-hexenethioic acid, 2-decenethioic acid, 3-methyl-2-heptenethioic acid, 3-methyl-2-butenethioic acid, 3-phenyl-2-propenethioic acid, 3-cyclohexyl-2-butenethioic acid, 2-methyl-2-butenethioic acid, 2-propyl-2-propenethioic acid, 2-isopropyl-2-hexenethioic acid, 2,3-dimethyl-2-butenethioic acid, 3-cyclohexyl-2-methyl-2-pentenethioic acid, 2-propenethioic acid, methyl 2-propenethioate, methyl 2-methyl 2-propenethioate, methyl 2-butenethioate, ethyl 2-hexenethioate, isopropyl 2-decenethioate, phenyl 2-pentenethioate, tertiary butyl 2-propenethioate, octadecyl 2-propenethioate, dodecyl 2-decenethioate, cyclopropyl 2,3-dimethyl-2-butenethioate, methyl 3-phenyl-2-propenethioate, and the like.

The alpha, beta ethylenically unsaturated dithioic acid and acid ester compounds employed herein have the following formula:



wherein R^5 , R^6 , R^7 , and R^8 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of alpha, beta-ethylenically unsaturated dithioic acids and acid esters of formula XV are 2-butenedithioic acid, 2-hexendithioic acid, 2-decendithioic acid, 3-methyl-2-heptendithioic acid, 3-methyl-2-butenedithioic acid, 3-phenyl-2-propendithioic acid, 3-cyclohexyl-2-butenedithioic acid, 2-methyl-2-butenedithioic acid, 2-propyl-2-propendithioic acid, 2-isopropyl-2-hexendithioic acid, 2,3-dimethyl-2-butenedithioic acid, 3-cyclohexyl-2-methyl-2-pentendithioic acid, 2-propendithioic acid, methyl 2-propendithioate, methyl 2-methyl 2-propendithioate, methyl 2-butenedithioate, ethyl 2-hexendithioate, isopropyl 2-decendithioate, phenyl 2-pentendithioate, tertiary butyl 2-propendithioate, octadecyl 2-propendithioate, dodecyl 2-decendithioate, cyclopropyl 2,3-dimethyl-2-butenedithioate, methyl 3-phenyl-2-propendithioate, and the like.

The alpha, beta ethylenically unsaturated thiocarboxamide compounds employed herein have the following formula:



wherein R^5 , R^6 , R^7 , R^8 and R^9 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl as defined above. Examples of alpha, beta-ethylenically unsaturated thiocarboxamides of formula XVI are 2-butenethioamide, 2-hexenethioamide, 2-decenethioamide, 3-methyl-2-heptenethioamide, 3-methyl-2-butenethioamide, 3-phenyl-2-propenethioamide, 3-cyclohexyl-2-butenethioamide, 2-methyl-2-butenethioamide, 2-propyl-2-propenethioamide, 2-isopropyl-2-hexenethioamide, 2,3-dimethyl-2-butenethioamide, 3-cyclohexyl-2-methyl-2-pentenethioamide, N-methyl 2-butenethioamide, N,N-diethyl 2-hexenethioamide, N-isopropyl 2-decenethioamide, N-phenyl 2-pentenethioamide, N-tertiary butyl 2-propenethioamide, N-octadecyl 2-propenethioamide, N-N-didodecyl 2-decenethioamide, N-cyclopropyl 2,3-dimethyl-2-butenethioamide, N-methyl 3-phenyl-2-propenethioamide, 2-propenethioamide, 2-methyl-2-propenethioamide, 2-ethyl-2-propenethioamide and the like.

Preferred compounds for reaction with the polyamines in accordance with this invention are lower alkyl esters of acrylic and (lower alkyl) substituted acrylic acid. Illustrative of such preferred compounds are compounds of the formula:



where R^7 is hydrogen or a C_1 to C_4 alkyl group, such as methyl, and R^8 is hydrogen or a C_1 to C_4 alkyl group, capable of being removed so as to form an amido group, for example, methyl, ethyl, propyl, isopropyl, butyl, sec-butyl, tert-butyl, aryl, hexyl, etc. In the preferred embodiments these compounds are acrylic and methacrylic esters such as methyl or ethyl acrylate, methyl or ethyl methacrylate. When the selected alpha, beta-unsaturated compound comprises a compound of formula X wherein X' is oxygen, the resulting reaction product with the polyamine contains at least one amido linkage ($-\text{C}(\text{O})\text{N}<$) and such materials are herein termed "amido-amines." Similarly, when the selected alpha, beta unsaturated compound of formula X comprises a compound wherein X' is sulfur, the resulting reaction product with the polyamine contains thioamide linkage ($-\text{C}(\text{S})\text{N}<$) and these materials are herein termed "thioamido-amines." For convenience, the following discussion is directed to the preparation and use of amido-amines, although it will be understood that such discussion is also applicable to the thioamido-amines.


The type of amido-amine formed varies with reaction conditions. For example, a more linear amido-amine is formed where substantially equimolar amounts of the unsaturated carboxylate and polyamine are reacted. The presence of excesses of the ethylenically unsaturated reactant of formula X tends to yield an amido-amine which is more cross-linked than that obtained where substantially equimolar amounts of reactants are employed. Where for economic or other reasons a cross-linked amido-amine using excess amine is desired, generally a molar excess of the ethylenically unsaturated reactant of about at least 10%, such as 10-300%, or greater, for example, 25-200%, is employed. For more efficient cross-linking an excess of carboxylated material should preferably be used since a cleaner reaction ensues. For example, a molar excess of about 10-100% or greater such as 10-50%, but preferably an excess of 30-50%, of the carboxylated material. Larger excess can be employed if desired.

In summary, without considering other factors, equimolar amounts of reactants tend to produce a more linear amido-amine whereas excess of the formula XII reactant tends to yield a more cross-linked amido-amine. It should be noted that the higher the polyamine (i.e., in greater the number of amino groups on the molecule) the greater the statistical probability of cross-linking since, for example, a tetraalkylenepentamine, such as tetraethylene pentamine



has more labile hydrogens than ethylene diamine.

These amido-amine adducts so formed are characterized by both amido and amino groups. In their simplest embodiments they may be represented by units of the following idealized formula (XVIII):



wherein the R^{10} s, which may be the same or different, are hydrogen or a substituted group, such as a hydrocarbon group, for example, alkyl, alkenyl, alkynyl, aryl, etc., and A is a moiety of the polyamine which, for example, may be aryl, cycloalkyl, alkyl, etc., and n_4 is an integer such as 1-10 or greater.

The above simplified formula represents a linear amido-amine polymer. However, cross-linked polymers may also be formed by employing certain conditions since the polymer has labile hydrogens which can further react with either the unsaturated moiety by adding across the double bond or by amidifying with a carboxylate group.

Preferably, however, the amido-amines employed in this invention are not cross-linked to any substantial degree, and more preferably are substantially linear.

Preferably, the polyamine reactant contains at least one primary amine (and more preferably from 2 to 4 primary amines) group per molecule, and the polyamine and the unsaturated reactant of formula X are contacted in an amount of from about 1 to 10, more preferably from about 2 to 6, and most preferably from about 3 to 5, equivalents of primary amino in the polyamine reactant per mole of the unsaturated reactant of formula X.


The reaction between the selected polyamine and acrylate-type compound is carried out at any suitable temperature. Temperatures up to the decomposition points of reactants and products can be employed. In practice, one generally carries out the reaction by heating the reactants below 100°C , such as $80-90^\circ\text{C}$, for a suitable period of time, such as a few hours. Where an acrylic-type ester is employed, the progress of the reaction can be judged by the removal of the alcohol in forming the amide. During the early part of the reaction alcohol is removed quite readily below 100°C in the case of low boiling alcohols such as methanol or ethanol. As the reaction slows, the temperature is raised to push the polymerization to completion and the temperature may be raised to 150°C toward the end of the reaction. Removal of alcohol is a convenient method of judging the progress and completion of the reaction which is generally continued until no more alcohol is evolved. Based on removal of alcohol, the yields are generally stoichiometric. In more difficult reactions, yield of at least 95% are generally obtained.

Similarly, it will be understood that the reaction of an ethylenically unsaturated carboxylate thioester of formula XII liberates the corresponding HSR^8 compound (e.g., H_2S when R^8 is hydrogen) as a by-product, and the reaction of an ethylenically unsaturated carboxamide of formula XIII liberates the corresponding $\text{HNR}^8(\text{R}^9)$ compound (e.g., ammonia when R^8 and R^9 are each hydrogen) as by-product.

The reaction time involved can vary widely depending on a wide variety of factors. For example, there is a relationship between time and temperature. In general, lower temperature demands longer times. Usually, reaction times of from about 2 to 30 hours, such as 5 to 25 hours, and preferably 3 to 10 hours will be employed.

Although one can employ a solvent, the reaction can be run without the use of any solvent. In fact, where a high degree of cross-linking is desired, it is preferably to avoid the use of a solvent and most particularly to avoid a polar solvent such as water. However, taking into consideration the effect of solvent on the reaction, where desired, any suitable solvent can be employed, whether organic or inorganic, polar or non-polar.

As an example of the amido-amine adducts, the reaction of tetraethylene pentamine (TEPA) with methyl methacrylate can be illustrated as follows:



PREPARATION OF THE VISCOSITY INDEX IMPROVER-DISPERSANT

15 The amine is readily reacted with the selected material, e.g., the ethylene-propylene copolymer substituted succinic anhydride, by reacting an oil solution containing 5 to 95 wt.% of the polymer substituted mono- or dicarboxylic acid material at 100 to 250 °C, preferably 125 to 175 °C, generally for 1 to 10, e.g., 2 to 6 hours until the desired amount of water is removed. The heating is preferably carried out to favor formation of imides or mixtures of imides and amides, rather than amides and salts.

20 Reaction ratios of polymer substituted mono- and dicarboxylic acid material to equivalents of amine as well as the other nucleophilic reactants described herein can vary considerably, depending on the reactants and type of bonds formed. When the polymer comprises a polymer substituted dicarboxylic acid material, containing dicarboxylic acid producing moieties derived from any of the above monounsaturated dicarboxylic acids, or anhydride or ester derivatives thereof, generally from 0.05 to 1.0, preferably from 0.1 to 0.6, e.g., 0.2 to 0.4, moles of dicarboxylic acid moiety content (e.g., grafted maleic anhydride content) is used, 25 per equivalent of nucleophilic reactant, e.g., amine. For example, about 0.8 mole of a pentamine (having two primary amino groups and 5 equivalents of nitrogen per molecule) is preferably used to convert into a mixture of amides and imides, the product formed by reacting one mole of polymer with sufficient maleic anhydride to add 1.6 moles of succinic anhydride groups per mole of polymer, i.e., preferably the pentamine is used in an amount sufficient to provide about 0.4 mole (that is 1.6/[0.8 x 5] mole) of succinic anhydride moiety per nitrogen equivalent of the amine. If an amido-amine, as above, is employed, generally 30 from 1 to 5, preferably from about 1.5 to 3 moles of dicarboxylic acid moiety content (e.g., grafted maleic anhydride content) is used per equivalent of amido-amine reactant, e.g., amine.

When the polymer comprises a polymer substituted monocarboxylic acid material, containing monocarboxylic acid producing moieties derived from any of the above monounsaturated monocarboxylic acids, or 35 ester derivatives thereof, generally from 0.05 to 1.0, preferably from about 0.1 to 0.6, e.g., 0.2 to 0.4, moles of monocarboxylic acid moiety content (e.g., grafted acrylic acid content) is used, per equivalent of nucleophilic reactant, e.g., amine. If an amido-amine, as above, is employed, generally from 1 to 5, preferably from 1.5 to 3 moles of monocarboxylic acid moiety content (e.g., grafted acrylic acid content) is used per equivalent of amido-amine reactant, e.g., amine.

40 An example of the reaction of an amido-amine reactant with a polymer mono- or dicarboxylic acid producing reactant is the reaction of ethylene-propylene copolymer substituted succinic anhydride (EPSA) with a polyamido-amine having two terminal -NH₂ groups, which can be illustrated as follows:

45

50

55

$$\text{O} \quad \text{R}^{10}$$
$$\parallel \quad |$$
$$-\text{C}(\text{CH}_2)_2\text{NH}-[\text{A}-\text{N}]_{n4}-\text{ANH}-$$

The ester viscosity index improver-dispersant may also be derived from unsaturated alcohols such as allyl alcohol, cinnamyl alcohol, propargyl alcohol, 1-cyclohexene-3-ol, and oleyl alcohol. Still other classes of the alcohols capable of yielding the esters of this invention comprise the ether-alcohols and amino-alcohols

including, for example, the oxy-alkylene, oxy-arylene-, amino-alkylene-, and amino-arylene-substituted alcohols having one or more oxy-alkylene, amino-alkylene or amino-arylene oxy-arylene radicals. They are exemplified by Cellosolve, Carbitol, N,N,N',N'-tetrahydroxy-trimethylene di-amine, and ether-alcohols having up to about 150 oxy-alkylene radicals in which the alkylene radical contains from 1 to about 8 carbon atoms.

The ester viscosity index improver-dispersant may be di-esters of succinic acids or acidic esters, i.e., partially esterified succinic acids; as well as partially esterified polyhydric alcohols or phenols, i.e., esters having free alcohols or phenolic hydroxyl radicals. Mixtures of the above illustrated esters likewise are contemplated within the scope of this invention.

The ester viscosity index improver-dispersant may be prepared by one of several known methods as illustrated for example in U.S. Patent 3,381,022. The ester viscosity index improver-dispersant may also be borated, similar to the nitrogen containing viscosity index improver-dispersants, as described above.

Hydroxyamines which can be reacted with the aforesaid ethylene alpha-olefin polymer substituted dicarboxylic acid material to form viscosity index improver-dispersants include 2-amino-1-butanol, 2-amino-2-methyl-1-propanol, p-(beta-hydroxyethyl)-aniline, 2-amino-1-propanol, 3-amino-1-propanol, 2-amino-2-methyl-1,3-propane-diol, 2-amino-2-ethyl-1,3-propanediol, N-(beta-hydroxypropyl)-N'-(beta-amino-ethyl)-piperazine, tris(hydroxymethyl) aminomethane (also known as trimethylolaminomethane), 2-amino-1-butanol, ethanolamine, beta-(beta-hydroxyethoxy)-ethylamine, and the like. Mixtures of these or similar amines can also be employed. The above description of nucleophilic reactants suitable for reaction with the ethylene alpha-olefin polymer substituted dicarboxylic acid or anhydride includes amines, alcohols, and compounds of mixed amine and hydroxy containing reactive functional groups, i.e., amino-alcohols.

Reactive metals or reactive metal compounds useful for reaction with the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention are those which will form carboxylic acid metal salts with the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention and those which will form metal-containing complexes with such dispersant derivative compositions produced by reacting the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials with amines and/or alcohols as discussed above. Reactive metal compounds useful for the formation of such complexes are disclosed in U.S. Patent 3,306,908. Complex-forming metal reactants include the nitrates, nitrites, halides, carboxylates, phosphates, phosphites, sulfates, sulfites, carbonates, borates, and oxides of cadmium as well as metals having atomic numbers from 24 to 30 (including chromium, manganese, iron, cobalt, nickel, copper and zinc). These metals are the so-called transition or coordination metals, i.e., they are capable of forming complexes by means of their secondary or coordination valence. Specific examples of the complex-forming metal compounds useful as the reactant in this invention are cobaltous nitrate, cobaltous oxide, cobaltic oxide, cobalt nitrite, cobaltic phosphate, cobaltous chloride, cobaltic chloride, cobaltous carbonate, chromous acetate, chromic acetate, chromic bromide, chromous chloride, chromic fluoride, chromous oxide, chromium dioxide, chromic oxide, chromic sulfite, chromous sulfate heptahydrate, chromic sulfate, chromic formate, chromic hexanoate, chromium oxychloride, chromic phosphite, manganous acetate, manganous benzoate, manganous carbonate, manganese dichloride, manganese trichloride, manganous citrate, manganous formate, manganous nitrate, manganous oxalate, manganese monoxide, manganese dioxide, manganese trioxide, manganese heptoxide, manganic phosphate, manganous pyrophosphosate, manganic metaphosphate, manganous hypophosphite, manganous valerate, ferrous acetate, ferric benzoate, ferrous bromide, ferrous carbonate, ferric formate, ferrous lactate, ferrous nitrate, ferrous oxide, ferric oxide, ferric hypophosphite, ferric sulfate, ferrous sulfite, ferric hydrosulfite, nickel dibromide, nickel dichloride, nickel nitrate, nickel dioleate, nickel stearate, nickel sulfite, cupric propionate, cupric acetate, cupric metaborate, cupric benzoate, cupric formate, cupric laurate, cupric nitrite, cupric oxychloride, cupric palmitate, cupric salicylate, zinc benzoate, zinc borate, zinc bromide, zinc chromate, zinc dichromate, zinc iodide, zinc lactate, zinc nitrate, zinc oxide, zinc stearate, zinc sulfite, cadmium benzoate, cadmium carbonate, cadmium butyrate, cadmium chloroacetate, cadmium, fumarate, cadmium nitrate, cadmium dihydrogenphosphate, cadmium sulfite, and cadmium oxide. Hydrates of the above compounds are especially convenient for use in the process of this invention.

U.S. Patent 3,306,908 is cited for its discussion of reactive metal compounds suitable for forming such complexes and its disclosure of processes for preparing the complexes. Basically, those processes are applicable to the viscosity index improver-dispersant derivative compositions of the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention with the amines as described above by substituting, or on an equivalent basis, the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention with the high molecular weight carboxylic acid acylating agents disclosed in U.S. Patent 3,306,908. The ratio of equivalents of the acylated amine thus produced and the complex-forming metal reactant remains the same as disclosed in 3,306,908.

U.S. Reissue Patent 26,433 discloses metals useful in preparing salts from the dispersant derivative compositions of the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention and amines as described hereinabove. Metal salts are prepared, according to this patent, from alkali metals, alkaline earth metals, zinc, cadmium, lead, cobalt and nickel. Examples of a reactive metal compound suitable for use herein are sodium oxide, sodium hydroxide, sodium carbonate, sodium methylate, sodium propylate, sodium pentylate, sodium phenoxide, potassium oxide, potassium hydroxide, potassium carbonate, potassium methylate, potassium pentylate, potassium phenoxide, lithium oxide, lithium hydroxide, lithium carbonate, lithium pentylate, calcium oxide, calcium hydroxide, calcium carbonate, calcium methylate, calcium ethylate, calcium propylate, calcium chloride, calcium fluoride, calcium pentylate, calcium phenoxide, calcium nitrate, barium oxide, barium hydroxide, barium carbonate, barium chloride, barium fluoride, barium methylate, barium propylate, barium pentylate, barium nitrate, magnesium oxide, magnesium hydroxide, magnesium carbonate, magnesium ethylate, magnesium propylate, magnesium chloride, magnesium bromide, barium, iodide, magnesium phenoxide, zinc oxide, zinc hydroxide, zinc carbonate, zinc methylate, zinc propylate, zinc pentylate, zinc chloride, zinc fluoride, zinc nitrate trihydrate, cadmium oxide, cadmium hydroxide, cadmium carbonate, cadmium methylate, cadmium propylate, cadmium chloride, cadmium bromide, cadmium fluoride, lead oxide, lead hydroxide, lead carbonate, lead ethylate, lead pentylate, lead chloride, lead fluoride, lead iodide, lead nitrate, nickel oxide, nickel hydroxide, nickel carbonate, nickel chloride, nickel bromide, nickel fluoride, nickel methylate, nickel pentylate, nickel nitrate hexahydrate, cobalt oxide, cobalt hydroxide, cobaltous bromide, cobaltous chloride, cobalt butylate, cobaltous nitrate hexahydrate, etc. The above metal compounds are merely illustrative of those useful in this invention and the invention is not to be considered as limited to such.

Again, in applying the teachings of this patent to the present invention, it is only necessary to substitute the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention on an equivalent weight basis for the high molecular weight carboxylic acylating agents of the reissue patent.

U.S. Patent 3,271,310 discloses the preparation of metal salt of high molecular weight carboxylic acid acylating agents, in particular alkenyl succinic acids. The metal salts disclosed therein are acid salts, neutral salts, and basic salts. Among the illustrative reactive metal compounds used to prepare the acidic, neutral and basic salts of the high molecular weight carboxylic acids disclosed in 3,271,310 are lithium oxide, lithium hydroxide, lithium carbonate, lithium pentylate, sodium oxide, sodium hydroxide, sodium carbonate, sodium methylate, sodium propylate, sodium phenoxide, potassium oxide, potassium hydroxide, potassium carbonate, potassium methylate, silver oxide, silver carbonate, magnesium oxide, magnesium hydroxide, magnesium carbonate, magnesium ethylate, magnesium propylate, magnesium phenoxide, calcium oxide, calcium hydroxide, calcium carbonate, calcium methylate, calcium propylate, calcium pentylate, zinc oxide, zinc hydroxide, zinc carbonate, zinc propylate, strontium oxide, strontium hydroxide, cadmium oxide, cadmium hydroxide, cadmium carbonate, cadmium ethylate, barium oxide, barium hydroxide, barium hydrate, barium carbonate, barium ethylate, barium pentylate, aluminum oxide, aluminum propylate, lead oxide, lead hydroxide, lead carbonate, tin oxide, tin butylate, cobalt oxide, cobalt hydroxide, cobalt carbonate, cobalt pentylate, nickel oxide, nickel hydroxide, and nickel carbonate. The present invention is not to be considered as limited to the use of the above metal compounds; they are presented merely to illustrate the metal compounds included within the invention.

As will be apparent, the processes of 3,271,310 are applicable to the polymer substituted materials of this invention merely by substituting on an equivalent weight basis, the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention for the high molecular weight carboxylic acids of the patent.

From the foregoing description, it is apparent that the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention can be reacted with any individual amine, alcohol, reactive metal, reactive metal compound or any combination of two or more of any of these; that is, for example, one or more amines, one or more alcohols, one or more reactive metals or reactive metal compounds, or a mixture of any of these. The mixture can be a mixture of two or more amines, a mixture of two or more alcohols, a mixture of two or more metals or reactive metal compounds, or a mixture of two or more components selected from amines and alcohols, from amines and reactive metals or reactive metal compounds, from alcohols and reactive metals compounds, or one or more components from each of the amines, alcohols, and reactive metal or reactive metal compounds. Furthermore, the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention can be reacted with the amines, alcohols, reactive metals, reactive metal compounds, or mixtures thereof, as described above, simultaneously (concurrently) or sequentially in any order of reaction.

Canadian Patent 956,397 discloses procedures for reacting the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention with amines, alcohols, reactive metal and

reactive metal compounds, or mixtures of these, sequentially and simultaneously. All that is required to apply the processes of that patent to this invention is to substitute, on an equivalent weight basis, the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention for the high molecular weight carboxylic acid acylating agents disclosed in that Canadian patent. Carboxylic acid derivatives of this invention prepared utilizing the processes disclosed in the Canadian patent constitute a preferred class of carboxylic acids or carboxylic acid derivative compositions. The following Patents are also cited, being counterparts of the cited Canadian patent, for the same reasons given for citing the Canadian patent: 3,836,469; 3,836,470; 3,836,471; 3,838,050; 3,838,052; 3,879,308; 3,957,854; 3,957,855. The Canadian patent and the U.S. patents are also cited to illustrate that the amount of polyoxyalkylene alcohol demulsifier utilized in preparing dispersant/detergents from the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention is normally quite small on an equivalent basis.

It is also pointed out that, among the more preferred carboxylic derivative compositions of this invention are those prepared according to the Canadian patent and corresponding U.S. patent and application identified above in which the polyoxyalkylene alcohol demulsifier has been omitted. In other words, a preferred class of carboxylic derivative compositions of this invention are the various reaction products of the high molecular weight carboxylic acid acylating agents of the Canadian patent with one or more amines, alcohols, and reactive metal compounds as disclosed therein differing only in that the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention are substituted on an equivalent weight basis and, further, that the polyoxyalkylene alcohol demulsifier reactant is omitted.

In addition, U.S. Patent 3,806,456 discloses processes useful in preparing products from the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention and polyoxyalkylene polyamines as described hereinbefore. Substitution of the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention for the high molecular weight carboxylic acid acylating agents disclosed in 3,806,456 on an equivalent weight basis produces compounds of similar utility further characterized by the desired viscosity index improving properties discussed hereinbefore.

U.S. Patent 3,576,743 discloses a process for preparing carboxylic derivative compositions from both polyhydric alcohols and amine; in particular, hydroxy-substituted primary amines. Again, substitution of the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention on an equivalent weight basis for the high molecular weight carboxylic acid acylating agents disclosed in 3,576,743 provides compositions having the desired dispersant/detergent compositions and the V.I. improving properties already discussed.

U.S. Patent 3,632,510 discloses processes for preparing mixed ester-metal salts. Mixed ester-metal salts derived from ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention, the alcohols, and the reactive metal compounds can be prepared by following the processes disclosed in 3,632,510 but substituting, on an equivalent weight basis, the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention for the high molecular weight carboxylic acid acylating agents of the patent. The carboxylic acid derivative compositions thus produced also represent a preferred aspect of this invention.

Finally, U.S. Patents 3,755,169; 3,804,763; 3,868,330; and 3,948,800 disclose how to prepare carboxylic acid derivative compositions. By following the teachings of these patents and substituting the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention for the high molecular weight carboxylic acid acylating agents of the patents, a wide range of carboxylic derivative compositions within the scope of the present invention can be prepared.

Reference to so many patents is done for the sake of brevity and because, it is felt, that the procedures necessary to prepare the carboxylic derivative compositions from the ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials and the amines, alcohols, and reactive metals and reactive metal compounds, as well as mixtures thereof, is well within the skill of the art, such that a detailed description herein is not necessary.

A preferred group of multifunctional viscosity index improvers, e.g., viscosity index improvers-dispersants, are those derived from ethylene-propylene copolymer substituted with succinic anhydride groups and reacted with polyethylene amines (referred to herein as "EPSA"), e.g., tetraethylene pentamine, pentaethylene hexamine, polyoxyethylene and polyoxypropylene amines, e.g., polyoxypropylene diamine, trimethylolaminomethane and pentaerythritol, and combinations thereof. One particularly preferred viscosity index improver-dispersant combination involves a combination of (A) ethylene-propylene copolymer substituted with succinic anhydride groups and reacted with (B) a hydroxy compound, e.g., pentaerythritol, (C) a polyoxyalkylene polyamine, e.g., polyoxypropylene diamine, and (D) a polyalkylene polyamine, e.g., polyethylene diamine and tetraethylene pentamine using about 0.3 to about 2 moles each of (B) and (D)

and about 0.3 to about 2 moles of (C) per mole of (A). Another preferred viscosity index improver-dispersant combination involves the combination of (A) ethylene-propylene copolymer succinic anhydride with (B) a polyalkylene polyamine, e.g., tetraethylene pentamine, and (C) a polyhydric alcohol or polyhydroxy-substituted aliphatic primary amine, e.g., pentaerythritol or trimethylolaminomethane.

5 Another embodiment of the instant invention is directed to a functionalized ethylene alpha-olefin polymer, i.e., ethylene alpha-olefin substituted mono- or dicarboxylic acid material, exhibiting viscosity index improving properties and enhanced dispersant efficacy. This embodiment, while generally applicable to all the polymers of the instant invention, is particularly useful with polymers having a number average molecular weight above about 50,000, i.e., from 50,000 to 400,000, preferably from 50,000 to 200,000, and
10 more preferably from 50,000 to 100,000.

In this embodiment an ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material is prepared substantially as described hereinafore. This ethylene alpha-olefin polymer substituted with mono- or dicarboxylic acid material is further substituted or reacted with additional mono- or dicarboxylic acid material. This further substitution or reaction of the ethylene alpha-olefin polymer may be carried out by
15 conventional and well-known means such as thermally or, more preferably, by use of a free-radical initiator such as peroxide. Such free-radical reaction or grafting is described, inter alia, in U.S. Patent Nos., 3,326,804; 4,089,794; 4,132,661; 4,171,273; 4,137,185; and 4,517,104.

The free radical reaction is preferably carried out using free radical initiators such as peroxides and hydroperoxides, and nitrile compounds, and preferably those which have a boiling point greater than about
20 100°C and which decompose thermally within the grafting temperature range to provide said free radicals. Representative of these free-radical initiators are azobutyro-nitrile, 2,5-dimethyl-hex-3-yne-2, 5-bis(tertiary-butyl peroxide) (sold as Luperso 130) or its hexane analogue, di-tertiary butyl peroxide and dicumyl peroxide. The initiator is generally used at a level of between about 0.005% and about 1%, based on the total weight of the polymer solution, and at temperatures of 150 to 220°C.

25 The monounsaturated carboxylic reactant, e.g., maleic anhydride, can be generally used in an amount ranging from 0.01% to 10%, preferably 0.1 to 2.0%, based on weight of the initial total solution. The aforesaid monounsaturated carboxylic reactant and free-radical initiator are generally used in a weight ratio of monounsaturated carboxylic reactant to free radical initiator of 1.0:1 to 30:1, preferably 3:1 to 6:1.

The reaction or grafting is preferably carried out in an inert atmosphere, such as that obtained by
30 nitrogen blanketing. While the grafting can be carried out in the presence of air, the yield of the desired graft polymer is generally thereby decreased as compared to grafting under an inert atmosphere substantially free of oxygen. The grafting time will usually range from 0.1 to 12 hours, preferably from 0.5 to 6 hours, more preferably 0.5 to 3 hours. The graft reaction will be usually carried out to at least approximately 4 times, preferably at least about 6 times the half-life of the free-radical initiator at the reaction temperature employed, e.g. with 2,5-dimethyl hex-3-yne-2, 5-bis(t-butyl peroxide) 2 hours at 160°C and one hour at
35 170°C, etc.

In the grafting process the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material, usually in solution, is first heated to grafting temperature and thereafter said monounsaturated carboxylic reactant and initiator are added with agitation, although they could have been added prior to
40 heating. When the reaction is complete, the excess monounsaturated carboxylic reactant can be eliminated by an inert gas purge, e.g. nitrogen sparging. Preferably the monounsaturated carboxylic reactant that is added is kept below its solubility limit in the polymer solution, e.g., below about 1 wt. %, preferably below 0.4 wt. % or less, of free maleic anhydride based on the total weight of polymer-solvent solution, e.g., ethylene-propylene substituted succinic anhydride/mineral lubricating oil solution. Continuous or periodic
45 addition of the monounsaturated carboxylic reactant along with an appropriate portion of initiator, during the course of the reaction, can be utilized to maintain the monounsaturated carboxylic above its solubility limits, while still obtaining the desired degree of total grafting.

In the grafting step the monounsaturated carboxylic reactant such as maleic anhydride may be grafted onto both the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material and the solvent
50 for the reaction. Many solvents such as dichlorobenzene are relatively inert and may be only slightly grafted, while mineral oil will tend to be more grafted. The exact split of graft between the substrates present depends upon the polymer and its reactivity, the reactivity and type of solvent, the concentration of the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material in the solvent, and also upon the maintenance of the monounsaturated carboxylic reactant in solution during the course of the
55 reaction and minimizing the presence of dispersed, but undissolved monounsaturated carboxylic reactant, e.g., the maleic anhydride. The undissolved monounsaturated carboxylic reactant appears to have an increased tendency to react to form oil insoluble materials as opposed to dissolved monounsaturated carboxylic reactant. The split between grafted solvent and grafted polymer may be measured empirically

from the infrared analyses of the product dialyzed into solvent and polymer fractions.

The grafting may be preferably carried out in a mineral lubricating oil which need not be removed after the grafting step but can be used as the solvent in the subsequent reaction of the grafted ethylene alpha-olefin substituted mono- or dicarboxylic acid material with the nucleophilic, e.g., amine, material and as a solvent for the end product to form the lubricating additive concentrate. The oil having attached grafted carboxyl groups, when reacted with the nucleophilic reactant such as amine will also be converted to the corresponding derivatives.

The solution grafting step when carried out in the presence of a high temperature decomposable peroxide can be accomplished without substantial degradation of the chain length (molecular weight) of the ethylene alpha-olefin polymer.

By using this further substitution or grafting functionalized ethylene alpha-olefin polymers having higher functionality (e.g., containing more mono- or dicarboxylic acid moieties, such as succinic anhydride, on the ethylene alpha-olefin backbone) can be obtained. Thus, for example, ethylene alpha-olefin polymers containing an average of from 0.5 to 2.5 carboxylic acid or anhydride groups, e.g., succinic anhydride groups, per 10,000 number average molecular weight segments of polymer can be obtained. Thus, for example, succinic anhydride substituted ethylene-propylene copolymer of M_n of about 50,000 containing an average number of succinic anhydride groups of from 2.5 to 12.5 can be obtained. These additional carboxylic acid or anhydride groups, e.g., succinic anhydride, will be present on the polymer backbone in addition to the terminal carboxylic acid or anhydride group which is grafted onto the polymers of the instant invention as described above.

These grafted ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid materials may then be reacted with the nucleophilic reactants, e.g., amine, as described hereinafore to form the nucleophilically substituted derivative products. When the nucleophilic reactant comprises amine, the resultant product will have a higher nitrogen content, since there are more carboxylic acid or anhydride moieties present on the polymer backbone with which the amines can react, thereby enhancing the dispersant efficacy of the product. Generally, amine substituted derivative products having a total nitrogen content of from 0.5 to 2 weight percent of higher can be prepared using this method.

In another embodiment of the instant invention the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material, e.g., ethylene propylene copolymer succinic anhydride, instead of being reacted in a reaction mixture containing said ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material and the nucleophilic reactant such as polyamine or polyol is reacted in a reaction mixture containing (i) a carboxylic acid component and said nucleophilic reactant such as polyamine or polyol, or (ii) the preformed reaction products, e.g., salts, imides, esters, amides, etc., of a carboxylic acid component and the nucleophilic reactant such as polyamine or polyol. Thus, for example a reaction mixture containing the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material, e.g., ethylene-propylene substituted succinic anhydride, and carboxylic acid component, e.g., polyisobutenyl substituted succinic anhydride, is prepared by admixing these two reactants, and the nucleophilic reactant such as polyamine is then introduced into this reaction mixture and the reaction is carried out as described hereinafter. Alternatively, the carboxylic acid component and nucleophilic reactant such as polyamine may be added substantially simultaneously to a reaction mixture containing the ethylene alpha-olefin polymer substituted mono- or dicarboxylic acid material.

This embodiment is particularly useful with the ethylene alpha-olefin substituted mono- or dicarboxylic acid material which is further substituted or grafted with additional monounsaturated carboxylic reactant.

CARBOXYLIC ACID COMPONENT

The carboxylic acid component includes: hydrocarbyl substituted dicarboxylic acid or anhydride, preferably succinic anhydride or acid, having 12 to 49 carbons, preferably 16 to 49 carbons in said hydrocarbyl group; long chain monocarboxylic acid of the formula $R'COOH$ where R' is a hydrocarbyl group of 50 to 400 carbons and long chain hydrocarbyl substituted dicarboxylic acid or anhydride, preferably succinic anhydride or acid, having an average number of carbon atoms of from 50 to 400 in said hydrocarbyl group. The preferred carboxylic acid component is the long chain hydrocarbyl substituted dicarboxylic acid or anhydride, preferably succinic acid or anhydride, having from 50 to 400 in said hydrocarbyl group. Said hydrocarbyl groups are essentially aliphatic and include alkenyl and alkyl groups. The longer chain acids and anhydrides are preferred, particularly when the reaction is carried out in lubricating oil.

The about C_{50} - C_{400} hydrocarbyl substituted dicarboxylic acid or anhydride includes the reaction product of the C_{50} - C_{400} hydrocarbon polymer, generally a polyolefin, with (i) monounsaturated C_4 to C_{10}

dicarboxylic acid wherein (a) the carboxyl groups are vicinyl, i.e., located on adjacent carbon atoms, and (b) at least one, preferably both, of said adjacent carbon atoms are part of said monounsaturations; or with (ii) derivatives of (i) such as anhydrides of (i). Upon reaction with the hydrocarbon polymer, the monounsaturations of the dicarboxylic acid, anhydride, etc. becomes saturated. Thus for example, maleic anhydride becomes a hydrocarbyl substituted succinic anhydride.

Typically, from 0.7 to 4.0 (e.g., 0.8 to 2.6), preferably from 1.0 to 2.0, and most preferably from 1.1 to 1.7 moles of said unsaturated C_4 to C_{10} dicarboxylic acid, anhydride or ester are charged to the reactor per mole of polyolefin charged.

Normally, not all of the polyolefin reacts with the unsaturated acid or derivative and the hydrocarbyl substituted dicarboxylic acid material will contain unreacted polyolefin. The unreacted polyolefin is typically not removed from the reaction mixture (because such removal is difficult and would be commercially infeasible) and the product mixture, stripped of any unreacted monounsaturated C_4 to C_{10} dicarboxylic acid or anhydride, is employed as the carboxylic acid component.

Characterization of the average number of moles of dicarboxylic acid or anhydride, which have reacted per mole of polyolefin charged to the reaction (whether it has undergone reaction or not) is defined herein as functionality. Said functionality is based upon (i) determination of the saponification number of the resulting product mixture using potassium hydroxide; and (ii) the number average molecular weight of the polymer charged, using techniques well known in the art. Functionality is defined solely with reference to the resulting product mixture. Although the amount of said reacted polyolefin contained in the resulting product mixture can be subsequently modified, i.e., increased or decreased by techniques known in the art, such modifications do not alter functionality as defined above. The term C_{50} - C_{400} hydrocarbyl substituted dicarboxylic acid material is intended to refer to the product mixture whether it has undergone such modification or not.

Accordingly, the functionality of the C_{50} - C_{400} hydrocarbyl substituted dicarboxylic acid material will be typically at least about 0.5, preferably at least about 0.8, and most preferably at least about 0.9 and will vary typically from 0.5 to 2.8 (e.g., 0.6 to 2), preferably from 0.8 to 1.4, and most preferably from 0.9 to 1.3.

Exemplary of such unsaturated dicarboxylic acids or anhydrides thereof are fumaric acid, itaconic acid, maleic acid, maleic anhydride, chloromaleic acid, chloromaleic anhydride, etc.

Preferred C_{50} to C_{400} olefin polymers, i.e., olefin polymers containing an average number of carbon atoms of from 50 to 400, for reaction with the unsaturated dicarboxylic acids or derivatives thereof are polymers comprising a major molar amount of C_2 to C_{10} , e.g., C_2 to C_5 monoolefin. Such olefins include ethylene, propylene, butylene, isobutylene, pentene, octene-1, styrene, etc. The polymers can be homopolymers such as polyisobutylene, as well as copolymers of two or more of such olefins such as copolymers of: ethylene and propylene; butylene and isobutylene; propylene and isobutylene; etc. Other copolymers include those in which a minor molar amount of the copolymer monomers, e.g., 1 to 10 mole %, is a C_4 to C_{18} non-conjugated diolefin, e.g., a copolymer of isobutylene and butadiene; or a copolymer of ethylene, propylene and 1,4-hexadiene; etc.

In some cases, the olefin polymer may be completely saturated, for example an ethylene-propylene copolymer made by a Ziegler-Natta synthesis using hydrogen as a moderator to control molecular weight.

The olefin polymers used will usually have number average molecular weights within the range of about 700 and about 6,000, more usually between about 800 and about 3000. Particularly useful olefin polymers have number average molecular weights within the range of about 900 and about 2500 with approximately one terminal double bond per polymer chain. An especially useful starting material is polyisobutylene. The number average molecular weight for such polymers can be determined by several known techniques. A convenient method for such determination is by gel permeation chromatography (GPC) which additionally provides molecular weight distribution information, see W. W. Yau, J. J. Kirkland and D. D. Bly, "Modern Size Exclusion Liquid Chromatography", John Wiley and Sons, New York, 1979.

Processes for reacting the about C_{50} to about C_{400} olefin polymer with the C_4 - C_{10} unsaturated dicarboxylic acid or anhydride are known in the art. For example, the olefin polymer and the dicarboxylic acid or derivative may be simply heated together as disclosed in U.S. Patents 3,361,673 and 3,401,118 to cause a thermal "ene" reaction to take place. Or, the olefin polymer can be first halogenated, for example, chlorinated or brominated to about 1 to 8 wt. %, preferably 3 to 7 wt. % chlorine, or bromine, based on the weight of polymer, by passing the chlorine or bromine through the polyolefin at a temperature of 60 to 250 °C, e.g. 120 to 160 °C, for 0.5 to 10, preferably 1 to 7 hours. The halogenated polymer may then be reacted with sufficient unsaturated acid or derivative at 100 to 250 °C, usually 180 to 235 °C, for 0.5 to 10, e.g. 3 to 8 hours, so the product obtained will contain the desired number of moles of the unsaturated acid or derivative per mole of the halogenated polymer. Processes of this general type are taught in U.S. Patents 3,087,936; 3,172,892; 3,272,746 and others.

Alternatively, the olefin polymer, and the unsaturated acid or derivative are mixed and heated while adding chlorine to the hot material. Processes of this type are disclosed in U.S. Patents 3,215,707; 3,231,587; 3,912,764; 4,110,349; and in U.K. 1,550,219.

By the use of halogen, 65 to 95 wt. % of the polyolefin, e.g. polyisobutylene will normally react with the dicarboxylic acid or derivative. Upon carrying out a thermal reaction without the use of halogen or a catalyst, then usually only 50 to 75 wt. % of the polyisobutylene will react. Chlorination helps increased the reactivity.

Particularly preferred as the acid component is polyisobutenyl succinic anhydride.

10 PREREACTIONED AMINE OR POLYOL-CARBOXYLIC ACID COMPONENT

The aforementioned nucleophilic reactant, preferably polyamine or polyol, and carboxylic acid component may be prereacted, with the acid moiety being generally attached to the polyamine or polyol through salt, imide, amide, amidine, ester or other linkages so that a primary amino group of the polyamine or a hydroxyl group of the polyol is still available for reaction with the acid or anhydride moieties of the grafted ethylene copolymer. A convenient source of these preacted materials are the well-known and generally commercially available lubricating oil dispersants, provided they retain primary amino groups or hydroxyl groups capable of further reaction with the grafted copolymer.

Usually these dispersants are made by condensing a hydrocarbyl substituted dicarboxylic acid or anhydride, preferably one having about 50 to 400 carbons in the hydrocarbyl substituent, such as these described hereinafter under "Carboxylic Acid Component", preferably a succinic acid producing material such as alkenyl succinic anhydride, with a polyamine or polyol, including those described above under "Polyamines" or "Polyols."

Monocarboxylic acid dispersants have been described in U.K. Patent Specification 983,040. There, polyamines are reacted with the high molecular weight mono carboxylic acid derived from a polyolefin, such as polyisobutylene, by oxidation with nitric acid or oxygen; or by addition of halogen to the polyolefin followed by hydrolyzing and oxidation; etc. Another method is taught in Belgian Patent 658,236, incorporated herein by reference where polyolefin, such as the polymers of C₂ to C₅ monoolefin, e.g., polypropylene or polyisobutylene, is halogenated, e.g., chlorinated, and then condensed with an alpha, beta-unsaturated, monocarboxylic acid of from 3 to 8, preferably 3 to 4, carbon atoms, e.g., acrylic acid, alpha-methyl-acrylic acid, i.e., 2-methyl propenoic acid, crotonic acid, etc., and then reacted with polyamine.

Formation of dicarboxylic acid dispersant by reaction of an amine with alkenyl succinic anhydride prepared from the reaction of a polyolefin or chlorinated polyolefin and maleic anhydride, etc., is well known in the art, as seen in U.S. Patent 3,272,746, incorporated herein by reference.

Most preferred are the lubricating oil dispersants made by reaction of the aforesaid alkylene polyamines previously described, with C₅₀-C₄₀₀ alkenyl succinic anhydrides described hereinafter.

Reaction, preferably amination and/or imidation of the carboxylic acid material is usefully done as a solution reaction with the acid material, usually polyisobutenylsuccinic anhydride, dissolved in a solvent such as mineral oil, to which the other reactant is added. The formation of the dispersants in high yield can be effected by adding from 0.5 to 3.3, preferably 0.7 to 1.3, most preferably about 1 to 1 molar proportions of the alkylene polyamine per molar proportion of alkenyl succinic anhydride to said solution and heating the mixture at 140°C to 165°C or higher until the appropriate amount of water of reaction is evolved. Typically the mineral oil solvent is adjusted so that it constitutes 50% by weight of the final acyl nitrogen compound solution.

45 REACTION OF ETHYLENE ALPHA-OLEFIN POLYMER SUBSTITUTED MONO- OR DICARBOXYLIC ACID MATERIAL AND CARBOXYLIC ACID COMPONENT WITH NUCLEOPHILIC REACTANT

The ethylene alpha-olefin substituted mono- or dicarboxylic acid material, preferably in solution generally equal to 5 to 30 wt. %, preferably 10 to 20 wt. % polymer in solution such as oil solution, and carboxylic acid component can be readily reacted with the nucleophilic reactant such as polyamine or polyol, or the ethylene alpha-olefin substituted mono- or dicarboxylic acid material can be readily reacted with pre-reacted nucleophilic reactant such as polyamine or polyol and carboxylic acid component by admixture and heating at a temperature of from 100°C. to 250°C., preferably from 150 to 200°C., for from 0.1 to 10 hours, usually 0.1 to about 2 hours. In the case of polyamines the heating is preferably carried out to favor formation of imides rather than amides and salts. Thus, imide formation will give a lower viscosity of the reaction mixture than amide formation and particularly lower than salt formation. This lower viscosity permits the utilization of a higher concentration of nitrogen containing ethylene alpha-olefin substituted

mono- or dicarboxylic acid material in the oleaginous composition. Removal of water, e.g., by N_2 stripping during slow addition of amine with stirring, assures completion of the imidation reaction. Reaction ratios can vary considerably, depending upon the reactants, amounts of excess, type of bonds formed, etc. Generally, the amount of polyamine used is an amount which is effective or sufficient to provide from 0.5 to 2.5, preferably from about 0.8 to 1.2 and more preferably from 0.9 to 1.0 equivalents of reactive primary amine moiety per acid equivalent of the acid moiety of the ethylene alpha-olefin substituted mono- or dicarboxylic acid material, e.g., succinic anhydride. If a polyol is used in place of the polyamine generally the amount of polyol reactant used is an amount which is effective or sufficient to provide from 0.5 to 2.5, preferably from 0.8 to 1.2, and more preferably from 0.9 to 1.0 equivalents of reactive hydroxyl moiety per acid equivalent of the acid moiety of the ethylene alpha-olefin substituted mono- or dicarboxylic acid material. The amount of carboxylic acid component used is generally from 0.5 to 4, preferably from 1.0 to 3 mole equivalents per mole equivalent of the acid moiety content, e.g., succinic anhydride content, of the ethylene alpha-olefin substituted mono- or dicarboxylic acid material.

Alternately, if pre-reacted polyamine and carboxylic acid component is used, such as a dispersant, sufficient dispersant is used to provide from 0.5 to 2.5 preferably from 0.8 to 1.2, and more preferably from 0.9 to 1.0 equivalents of reactive primary amine moiety per acid equivalent of the acid moiety of the ethylene alpha-olefin substituted mono-dicarboxylic acid material. Likewise, if pre-reacted polyol and carboxylic acid component is used, such as a dispersant, sufficient dispersant is used to provide from 0.5 to about 2.5, preferably from 0.8 to 1.2, and more preferably from 0.9 to 1.0 equivalents of reactive hydroxyl moiety per acid equivalent of the grafted dicarboxylic acid moiety of the ethylene alpha-olefin substituted mono- or dicarboxylic acid material.

Another aspect of this invention involves the post treatment of the nitrogen or ester containing dispersant materials. The process for post-treating said nitrogen or ester containing multifunctional viscosity index improver materials is analogous to the post-treating processes used with respect to derivatives of conventional ethylene copolymers of the prior art. Accordingly, the same reaction conditions, ratio of reactants and the like can be used.

The nitrogen-containing multifunctional viscosity index improver materials of the instant invention as described above are post-treated by contacting said nitrogen-containing multifunctional viscosity index improver materials with one or more post-treating reagents selected from the group consisting of boron oxide, boron oxidehydrate, boron halides, boron acids, esters of boron acids, carbon disulfide, sulfur, sulfur chlorides, alkenyl cyanides, aldehydes, ketones, urea, thio-urea, guanidine, dicyanodiamide, hydrocarbyl phosphates, hydrocarbyl phosphites, hydrocarbyl thiophosphates, hydrocarbyl thiophosphites, C_1 to C_{30} hydrocarbyl substituted succinic acids and anhydrides (e.g., succinic anhydride, dodecyl succinic anhydride and the like), maleic anhydride (or any of the above discussed monounsaturated carboxylic reactants useful in forming the ethylene-alpha-olefin polymer-substituted mono- and dicarboxylic acid materials employed in this invention), phosphorus sulfides, phosphorus oxides, phosphoric acid, hydrocarbyl thiocyanates, hydrocarbyl isocyanates, hydrocarbyl isothiocyanates, epoxides, episulfides, formaldehyde or formaldehyde-producing compounds plus phenols, and sulfur plus phenols. The same post-treating reagents are used with the multifunctional viscosity index improver materials prepared from a combination of polyamines and polyols. However, when the dispersant materials are derived from polyols, and that is, when they are esters, the post-treating reagents are usually selected from the group consisting of boron oxide, boron oxide hydrate, boron halides, boron acids, esters of boron acids, sulfur, sulfur chlorides, phosphorus sulfides, phosphorus oxides, epoxides, and episulfides.

For example, the nitrogen containing multifunctional viscosity index improvers can be treated with a boron compound selected from the class consisting of boron oxide, boron halides, boron acids and esters of boron acids in an amount to provide from 0.1 atomic proportion of boron for each mole of said nitrogen composition to 20 atomic proportions of boron for each atomic proportion of nitrogen of said nitrogen composition. Usefully the borated multifunctional viscosity index improvers of the invention contain from 0.05 to 2.0 wt. %, e.g. 0.05 to 0.7 wt. % boron based on the total weight of said borated nitrogen-containing multifunctional viscosity index improver compound. The boron, which appears to be in the product as dehydrated boric acid polymers (primarily $(HBO_2)_3$), is believed to attach to the multifunctional viscosity index improver as amine salts, e.g., the metaborate salt of said amine dispersants.

Treating is readily carried out by adding from 0.05 to 4, e.g. 1 to 3 wt. % (based on the weight of said nitrogen compound) of said boron compound, preferably boric acid which is most usually added as a slurry to said nitrogen compound and heating with stirring at from $135^\circ C.$ to $190^\circ C.$, e.g. $140-170^\circ C.$, for from 1 to 5 hours followed by nitrogen stripping at said temperature ranges. Or, the boron treatment can be carried out by adding boric acid to the hot reaction mixture of the dicarboxylic acid material and amine while removing water.


Since post-treating processes involving the use of these post-treating reagents is known insofar as application to reaction products of high molecular weight carboxylic acid acylating agents of the prior art and amines and/or alcohols, further descriptions of these processes herein is unnecessary. In order to apply the prior art processes to the compositions of this invention, all that is necessary is that reaction conditions, ratio of reactants, and the like as described in the prior art, be applied to the novel compositions of this invention. The following U.S. patents disclose post-treating processes and post-treating reagents applicable to the compositions of this invention: U.S. Pat. Nos. 3,087,936; 3,200,107; 3,254,025; 3,256,185; 3,278,550; 3,281,428; 3,282,955; 3,284,410; 3,338,832; 3,344,069; 3,366,569; 3,373,111; 3,367,943; 3,403,102; 3,428,561; 3,502,677; 3,513,093; 3,533,945; 3,541,012; 3,639,242; 3,708,522; 3,859,318; 3,865,813; 3,470,098; 3,369,021; 3,184,411; 3,185,645; 3,245,908; 3,245,909; 3,245,910; 3,573,205; 3,692,681; 3,749,695; 3,865,740; 3,954,639; 3,458,530; 3,390,086; 3,367,943; 3,185,704; 3,551,466; 3,415,750; 3,312,619; 3,280,034; 3,718,663; 3,652,616; UK Pat. No. 1,085,903; UK Pat. No. 1,162,436; U.S. Pat. No. 3,558,743.

The nitrogen and/or ester containing multifunctional viscosity index improver materials of this invention can also be treated with polymerizable lactones (such as epsilon-caprolactone) to form multifunctional viscosity index improver adducts having the moiety $-[C(O)(CH_2)_zO]_mH$, wherein z is a number of from 4 to 8 (e.g., 5 to 7) and m has an average value of from about 0 to 100 (e.g., 0.2 to 20). The multifunctional viscosity index improver of this invention can be post-treated with a C_5 to C_9 lactone, e.g., epsilon-caprolactone, by heating a mixture of the multifunctional viscosity index improver material and lactone in a reaction vessel in the absence of a solvent at a temperature of $50^\circ C$ to $200^\circ C$, more preferably from $75^\circ C$ to $180^\circ C$, and most preferably from $90^\circ C$ to $160^\circ C$, for a sufficient period of time to effect reaction. Optionally, a solvent for the lactone, multifunctional viscosity index improver material and/or the resulting adduct may be employed to control viscosity and/or the reaction rates.

In one preferred embodiment, the C_5 to C_9 lactone, e.g., epsilon-caprolactone, is reacted with a multifunctional viscosity index improver material in a 1:1 mole ratio of lactone to multifunctional viscosity index improver material. In practice, the ration of lactone to multifunctional viscosity index improver material may vary considerably as a means of controlling the length of the sequence of the lactone units in the adduct. For example, the mole ratio of the lactone to the multifunctional viscosity index improver material may vary from 10:1 to 0.1:1, more preferably from 5:1 to 0.2:1, and most preferably from 2:1 to 0.4:1. It is preferable to maintain the average degree of polymerization of the lactone monomer below 100, with a degree of polymerization on the order of from about 0.2 to 50 being preferred, and from 0.2 to 20 being more preferred. For optimum dispersant performance of the multifunctional viscosity index improver, e.g., viscosity index improver-dispersant, sequences of from about 1 to about 5 lactone units in a row are preferred.

Catalysts useful in the promotion of the lactone-multifunctional viscosity index improver material reactions are selected from the group consisting of stannous octanoate, stannous hexanoate, tetrabutyl titanate, a variety of organic based acid catalysts and amine catalysts, as described on page 266, and forward, in a book chapter authored by R.D. Lundberg and E. F. Cox, entitled "Kinetics and Mechanisms of Polymerization: Ring Opening Polymerization", edited by Frisch and Reegen, published by Marcel Dekker in 1969, wherein stannous octanoate is an especially preferred catalyst. The catalyst is added to the reaction mixture at a concentration level of about 50 to about 10,000 parts per weight of catalyst per one million parts of the total reaction mixture.

Exemplary of adducts formed by reaction of multifunctional viscosity index improver materials if this invention and epsilon-caprolactone are those adducts illustrated by the following equation:



20 wherein m and EP are as defined above.

Further aspects of the present invention reside in the formation of metal complexes of the novel multifunctional viscosity index improver additives prepared in accordance with this invention. Suitable metal complexes may be formed in accordance with known techniques of employing a reactive metal ion species during or after the formation of the present multifunctional viscosity index improver materials. Complex forming metal reactants include the metal nitrates, thiocyanates, halides, carboxylates, phosphates, thio-phosphates, sulfates, and borates of transition metals such as iron, cobalt, nickel, copper, chromium, manganese, molybdenum, tungsten, ruthenium, palladium, platinum, cadmium, lead, silver, mercury, antimony and the like.

As a further feature of the present invention, the (A) ethylene-alpha-olefin polymer substituted mono- and dicarboxylic acid materials of this invention can be admixed, prior to, after or during being contacted with the selected nucleophilic reagent, with (B) a conventional polyolefin-substituted mono- or dicarboxylic acid material derived from any of the polyolefins discussed above as being useful as a mixed charge with the ethylenically unsaturated ethylene-alpha-olefin polymers in the formation of the ethylene-alpha-olefin polymer substituted mono- and di-carboxylic acid materials of this invention. The ethylene-alpha-olefin polymer substituted mono- and di-carboxylic acid materials of this invention and the polyolefin-substituted mono- or dicarboxylic acid material will be generally admixed prior to contact with the selected nucleophilic reagent, e.g., alkylene polyamine. Such mixtures will generally employ a weight:weight ratio of ethylene-alpha-olefin polymer substituted mono- and di-carboxylic acid materials of this invention to polyolefin-substituted mono- or dicarboxylic acid material from 10:90 to 90:10, preferably from 20:80 to 80:20, and more preferably from 40:60 to 60:40. Especially preferred are mixtures of ethylene-propylene copolymer-substituted succinic anhydride materials of this invention and ethylene-propylene substituted succinic anhydride. The resulting mixtures can then be contacted for reaction with the selected nucleophilic reagent as described above for formation of multifunctional viscosity index improver materials. The resulting mixed materials can also be treated with any of the above-described post-treatment methods for incorporation of additional functional groups thereon, such as boron, hydroxy, ester, epoxy, lactone, sulfur, metals and the like, as discussed above.

The multifunctional viscosity index improvers of the present invention can be incorporated into a lubricating oil in any convenient way. Thus, these MFVIs can be added directly to the oil by dispersing or dissolving the same in the oil at the desired level of concentrations of the MFVI. Such blending into the additional lube oil can occur at room temperature or elevated temperatures. Alternatively, the multifunctional viscosity index improvers can be blended with a suitable oil-soluble solvent and base oil to form a concentrate, and then blending the concentrate with a lubricating oil basestock to obtain the final formulation.

The lubricating oil basestock for the multifunctional viscosity index improver typically is adapted to perform a selected function by the incorporation of additional additives therein to form lubricating oil compositions (i.e., formulations). Such multifunctional viscosity index improver concentrates will typically contain (on an active ingredient (A.I.) basis) from 5 to 60 wt.%, preferably from 10 to 60, and more preferably from 20 to 50 wt.% multifunctional viscosity index improver additive, and typically from 40 to 95

wt.%, preferably from 40 to 90, and more preferably from 50 to 80 wt.%, base oil, based on the concentrate weight.

LUBRICATING COMPOSITIONS

5

The additives of the present invention possess very good multifunctional viscosity index improver dispersant properties as measured herein in a wide variety of environments. Accordingly, the additive mixtures are used by incorporation and dissolution into an oleaginous material such as lubricating oils.

10 The additives of the present invention find their primary utility in lubricating oil compositions which employ a base oil in which the additives are dissolved or dispersed. Such base oils may be natural or synthetic. Base oils suitable for use in preparing the lubricating oil compositions of the present invention include those conventionally employed as crankcase lubricating oils for spark-ignited and compression-ignited internal combustion engines, such as automobile and truck engines, marine and railroad diesel engines, and the like. Advantageous results are also achieved by employing the additives of the present
15 invention in base oils conventionally employed in and/or adapted for use as power transmitting fluids, universal tractor fluids and hydraulic fluids, heavy duty hydraulic fluids, power steering fluids and the like. Gear lubricants, industrial oils, pump oils and other lubricating oil compositions can also benefit from the incorporation therein of the additive mixtures of the present invention.

20 These lubricating oil formulations conventionally contain several different types of additives that will supply the characteristics that are required in the formulations. Among these types of additives are included viscosity index improvers, antioxidants, corrosion inhibitors, detergents, dispersants, pour point depressants, antiwear agents, friction modifiers, and ashless dispersant (e.g., polyisobutenyl succinimides) and borated derivatives thereof, etc.

In the preparation of lubricating oil formulations it is common practice to introduce the additives in the
25 form of 10 to 80 wt. %, e.g., 20 to 80 wt. % active ingredient concentrates in hydrocarbon oil, e.g. mineral lubricating oil, or other suitable solvent. Usually these concentrates may be diluted with 3 to 100, e.g., 5 to 40 parts by weight of lubricating oil, per part by weight of the additive package, in forming finished lubricants, e.g. crankcase motor oils. The purpose of concentrates, of course, is to make the handling of the various materials less difficult and awkward as well as to facilitate solution or dispersion in the final blend.
30 Thus, a dispersant would be usually employed in the form of a 40 to 50 wt. % concentrate, for example, in a lubricating oil fraction.

The multifunctional viscosity index improver of the present invention will be generally used in admixture with a lube oil basestock, comprising an oil of lubricating viscosity, including natural and synthetic lubricating oils and mixtures thereof.

35 The amounts of the multifunctional viscosity index improvers, e.g., viscosity index improvers-dispersants, of the present invention present in oleaginous compositions such as lubricating oil compositions is at least a viscosity index improving effective amount, i.e., an amount effective to improve the viscosity index of the oleaginous material. In the particular case of a viscosity index improver-dispersant the amount present is a viscosity index improving and dispersant effective amount, i.e., an amount effective to improve the
40 viscosity index of the oleaginous material and to impart dispersancy properties to said composition. Generally, these amounts are usually from 0.01 to 20 wt. %, preferably from 0.05 to 12 wt. %, more preferably from 0.1 to 10 wt. %, and most preferably from 0.25 to 6 wt. %, of the total composition.

Natural oils include animal oils and vegetable oils (e.g., castor, lard oil) liquid petroleum oils and hydrorefined, solvent-treated or acid-treated mineral lubricating oils of the paraffinic, naphthenic and mixed
45 paraffinic-naphthenic types. Oils of lubricating viscosity derived from coal or shale are also useful base oils.

Alkylene oxide polymers and interpolymers and derivatives thereof where the terminal hydroxyl groups have been modified by esterification, etherification, etc., constitute another class of known synthetic lubricating oils. These are exemplified by polyoxyalkylene polymers prepared by polymerization of ethylene oxide or propylene oxide, the alkyl and aryl ethers of these polyoxyalkylene polymers (e.g., methyl-poly
50 isopropylene glycol ether having an average molecular weight of 1000, diphenyl ether of polyethylene glycol having a molecular weight of 500-1000, diethyl ether of polypropylene glycol having a molecular weight of 1000-1500); and mono- and polycarboxylic esters thereof, for example, the acetic acid esters, mixed C₃-C₈ fatty acid esters and C₁₃ Oxo acid diester of tetraethylene glycol.

Another suitable class of synthetic lubricating oils comprises the esters of dicarboxylic acids (e.g.,
55 phthalic acid, succinic acid, alkyl succinic acids and alkenyl succinic acids, maleic acid, azelaic acid, suberic acid, sebacic acid, fumaric acid, adipic acid, linoleic acid dimer, malonic acid, alkylmalonic acids, alkenyl malonic acids) with a variety of alcohols (e.g., butyl alcohol, hexyl alcohol, dodecyl alcohol, 2-ethylhexyl alcohol, ethylene glycol, diethylene glycol monoether, propylene glycol). Specific examples of

these esters include dibutyl adipate, di(2-ethylhexyl)sebacate, di-n-hexyl fumarate, dioctyl sebacate, diisooctyl azelate, diisodecyl azelate, dioctyl phthalate, didecyl phthalate, dieicosyl sebacate, the 2-ethylhexyl diester of linoleic acid dimer, and the complex ester formed by reacting one mole of sebacic acid with two moles of tetraethylene glycol and two moles of 2-ethylhexanoic acid.

5 Esters useful as synthetic oils also include those made from C_5 to C_{12} monocarboxylic acids and polyols and polyol ethers such as neopentyl glycol, trimethylolpropane, pentaerythritol, dipentaerythritol and tripentaerythritol.

Silicon-based oils such as the polyalkyl-, polyaryl-, polyalkoxy-, or polyaryloxysiloxane oils and silicate oils comprise another useful class of synthetic lubricants; they include tetraethyl silicate, tetraisopropyl
10 silicate, tetra-(2-ethylhexyl)silicate, tetra-(4-methyl-2-ethylhexyl)silicate, tetra-(p-tertbutylphenyl)silicate, hexa-(4-methyl-2-pentoxy)disiloxane, poly(methyl)siloxanes and poly(methylphenyl)siloxanes. Other synthetic lubricating oils include liquid esters of phosphorus-containing acids (e.g., tricresyl phosphate, trioctyl phosphate, diethyl ester of decylphosphonic acid) and polymeric tetrahydrofurans.

Unrefined, refined and rerefined oils can be used in the lubricants of the present invention. Unrefined
15 oils are those obtained directly from a natural or synthetic source without further purification treatment. For example, a shale oil, obtained directly from retorting operations, a petroleum oil obtained directly from distillation or ester oil obtained directly from an esterification process and used without further treatment would be an unrefined oil. Refined oils are similar to the unrefined oils except they have been further treated in one or more purification steps to improve one or more properties. Many such purification
20 techniques, such as distillation, solvent extraction, acid or base extraction, filtration and percolation are known to those skilled in the art. Rerefined oils are obtained by processes similar to those used to obtain refined oils applied to refined oils which have been already used in service. Such rerefined oils are also known as reclaimed or reprocessed oils and often are additionally processed by techniques for removal of spent additives and oil breakdown products.

25 Metal containing rust inhibitors and/or detergents are frequently used with multifunctional viscosity index improvers. Such detergents and rust inhibitors include the metal salts of sulphonic acids, alkyl phenols, sulphurized alkyl phenols, alkyl salicylates, naphthenates, and other oil soluble mono- and di-carboxylic acids. Highly basic, that is overbased metal salts which are frequently used as detergents appear particularly prone to interaction with the ashless dispersant. Usually these metal containing rust inhibitors
30 and detergents are used in lubricating oil in amounts of 0.01 to 10, e.g. 0.1 to 5 wt. %, based on the weight of the total lubricating composition. Marine diesel lubricating oils typically employ such metal-containing rust inhibitors and detergents in amounts of up to about 20 wt. %.

Highly basic alkaline earth metal sulfonates are frequently used as detergents. They are usually produced by heating a mixture comprising an oil-soluble sulfonate or alkaryl sulfonic acid, with an excess of
35 alkaline earth metal compound above that required for complete neutralization of any sulfonic acid present and thereafter forming a dispersed carbonate complex by reacting the excess metal with carbon dioxide to provide the desired overbasing. The sulfonic acids are typically obtained by the sulfonation of alkyl substituted aromatic hydrocarbons such as those obtained from the fractionation of petroleum by distillation and/or extraction or by the alkylation of aromatic hydrocarbons as for example those obtained by alkylating
40 benzene, toluene, xylene, naphthalene, diphenyl and the halogen derivatives such as chlorobenzene, chlorotoluene and chloronaphthalene. The alkylation may be carried out in the presence of a catalyst with alkylating agents having from 3 to more than 30 carbon atoms. For example haloparaffins, olefins obtained by dehydrogenation of paraffins, polyolefins produced from ethylene, propylene, etc. are all suitable. The alkaryl sulfonates usually contain from 9 to 70 or more carbon atoms, preferably from 16 to 50 carbon
45 atoms per alkyl substituted aromatic moiety.

The alkaline earth metal compounds which may be used in neutralizing these alkaryl sulfonic acids to provide the sulfonates includes the oxides and hydroxides, alkoxides, carbonates, carboxylate, sulfide, hydrosulfide, nitrate, borates and ethers of magnesium, calcium, and barium. Examples are calcium oxide, calcium hydroxide, magnesium acetate and magnesium borate. As noted, the alkaline earth metal compound
50 is used in excess of that required to complete neutralization of the alkaryl sulfonic acids. Generally, the amount ranges from 100 to 220%, although it is preferred to use at least 125%, of the stoichiometric amount of metal required for complete neutralization.

Various other preparations of basic alkaline earth metal alkaryl sulfonates are known, such as U.S. Patents 3,150,088 and 3,150,089 wherein overbasing is accomplished by hydrolysis of an alkoxide-carbonate complex with the alkaryl sulfonate in a hydrocarbon solvent-diluent oil.
55


A preferred alkaline earth sulfonate additive is magnesium alkyl aromatic sulfonate having a total base number ranging from 300 to 400 with the magnesium sulfonate content ranging from about 25 to about 32 wt. %, based upon the total weight of the additive system dispersed in mineral lubricating oil.

Neutral metal sulfonates are frequently used as rust inhibitors. Polyvalent metal alkyl salicylate and naphthenate materials are known additives for lubricating oil compositions to improve their high temperature performance and to counteract deposition of carbonaceous matter on pistons (U.S. Patent 2,744,069). An increase in reserve basicity of the polyvalent metal alkyl salicylates and naphthenates can be realized by utilizing alkaline earth metal, e.g. calcium, salts of mixtures of C_8 - C_{26} alkyl salicylates and phenates (see U.S. Patent 2,744,069) or polyvalent metal salts of alkyl salicylic acids, said acids obtained from the alkylation of phenols followed by phenation, carboxylation and hydrolysis (U.S. Patent 3,704,315) which could then be converted into highly basic salts by techniques generally known and used for such conversion. The reserve basicity of these metal-containing rust inhibitors is usefully at TBN levels of between 60 and 150. Included with the useful polyvalent metal salicylate and naphthenate materials are the methylene and sulfur bridged materials which are readily derived from alkyl substituted salicylic or naphthenic acids or mixtures of either or both with alkyl substituted phenols. Basic sulfurized salicylates and a method for their preparation is shown in U.S. Patent 3,595,791. Such materials include alkaline earth metal, particularly magnesium, calcium, strontium and barium salts of aromatic acids having the general formula:




where Ar is an aryl radical of 1 to 6 rings, R_1 is an alkyl group having from about 8 to 50 carbon atoms, preferably 12 to 30 carbon atoms (optimally about 12), X is a sulfur (-S-) or methylene (-CH₂-) bridge, y is a number from 0 to 4 and n is a number from 0 to 4.

Preparation of the overbased methylene bridged salicylate-phenate salt is readily carried out by conventional techniques such as by alkylation of a phenol followed by phenation, carboxylation, hydrolysis, methylene bridging a coupling agent such as an alkylene dihalide followed by salt formation concurrent with carbonation. An overbased calcium salt of a methylene bridged phenol-salicylic acid of the general formula (XXI):



with a TBN of 60 to 150 is highly useful in this invention.

The sulfurized metal phenates can be considered the "metal salt of a phenol sulfide" which thus refers to a metal salt whether neutral or basic, of a compound typified by the general formula (XXII):



where $x = 1$ or 2 , $n = 0, 1$ or 2 ; or a polymeric form of such a compound, where R is an alkyl radical, n and x are each integers from 1 to 4, and the average number of carbon atoms in all of the R groups is at least about 9 in order to ensure adequate solubility in oil. The individual R groups may each contain from 5 to 40, preferably 8 to 20, carbon atoms. The metal salt is prepared by reacting an alkyl phenol sulfide with a sufficient quantity of metal containing material to impart the desired alkalinity to the sulfurized metal phenate.

Regardless of the manner in which they are prepared, the sulfurized alkyl phenols which are useful generally contain from 2 to 14% by weight, preferably 4 to 12 wt. % sulfur based on the weight of sulfurized alkyl phenol.

The sulfurized alkyl phenol may be converted by reaction with a metal containing material including
 5 oxides, hydroxides and complexes in an amount sufficient to neutralize said phenol and, if desired, to overbase the product to a desired alkalinity by procedures well known in the art. Preferred is a process of neutralization utilizing a solution of metal in a glycol ether.

The neutral or normal sulfurized metal phenates are those in which the ratio of metal to phenol nucleus is about 1:2. The "overbased" or "basic" sulfurized metal phenates are sulfurized metal phenates wherein
 10 the ratio of metal to phenol is greater than that of stoichiometric, e.g. basic sulfurized metal dodecyl phenate has a metal content up to and greater than 100% in excess of the metal present in the corresponding normal sulfurized metal phenates wherein the excess metal is produced in oil-soluble or dispersible form (as by reaction with CO_2). The overbased sulfurized metal phenates desirably have a TBN value of at least 150, e.g. from 200 to 300.

15 Magnesium and calcium containing additives although beneficial in other respects can increase the tendency of the lubricating oil to oxidize. This is especially true of the highly basic sulphonates.

According to a preferred embodiment the invention therefore provides a crankcase lubricating composition also containing from 2 to 8000 parts per million of calcium or magnesium.

The magnesium and/or calcium is generally present as basic or neutral detergents such as the
 20 sulphonates and phenates, our preferred additives are the neutral or basic magnesium or calcium sulphonates. Preferably the oils contain from 500 to 5000 parts per million of calcium or magnesium. Basic magnesium and calcium sulphonates are preferred.

A particular advantage of the novel multifunctional viscosity index improvers of the present invention is, since they provide both viscosity index improvement and dispersancy, they can be used to form multi-
 25 grade automobile engine lubricating oils. The instant multifunctional viscosity index improvers can also be used in combination with index improvers or modifiers. Viscosity modifiers impart high and low temperature operability to the lubricating oil and permit it to remain relatively viscous at elevated temperatures and also exhibit acceptable viscosity or fluidity at low temperatures. Viscosity modifiers are generally high molecular weight hydrocarbon polymers including polyesters. The viscosity modifiers may also be derivatized to
 30 include other properties or functions, such as the addition of dispersancy properties. These oil soluble viscosity modifying polymers will generally have number average molecular weights of from 10^3 to 10^6 , preferably 10^4 to 10^6 , e.g., 20,000 to 250,000, as determined by gel permeation chromatography or osmometry.

Examples of suitable hydrocarbon polymers include homopolymers and copolymers of two or more
 35 monomers of C_2 to C_{30} , e.g. C_2 to C_8 olefins, including both alpha olefins and internal olefins, which may be straight or branched, aliphatic, aromatic, alkyl-aromatic, cycloaliphatic, etc. Frequently they will be of ethylene with C_3 to C_{30} olefins, particularly preferred being the copolymers of ethylene and propylene. Other polymers can be used such as polyisobutylenes, homopolymers and copolymers of C_6 and higher alpha olefins, atactic polypropylene, hydrogenated polymers and copolymers and terpolymers of styrene,
 40 e.g. with isoprene and/or butadiene and hydrogenated derivatives thereof. The polymer may be degraded in molecular weight, for example by mastication, extrusion, oxidation or thermal degradation, and it may be oxidized and contain oxygen. Also included are derivatized polymers such as post-grafted interpolymers of ethylene-propylene with an active monomer such as maleic anhydride which may be further reacted with an alcohol, or amine, e.g. an alkylene polyamine or hydroxy amine, e.g. see U.S. Patent Nos. 4,089,794;
 45 4,160,739; 4,137,185; or copolymers of ethylene and propylene reacted or grafted with nitrogen compounds such as shown in U.S. Patent nos. 4,068,056; 4,068,058; 4,146,489 and 4,149,984.

The preferred hydrocarbon polymers are ethylene copolymers containing from 15 to 90 wt. % ethylene, preferably 30 to 80 wt. % of ethylene and 10 to 85 wt. %, preferably 20 to 70 wt. % of one or more C_3 to C_{28} , preferably C_3 to C_{18} , more preferably C_3 to C_8 , alpha-olefins. While not essential, such copolymers
 50 preferably have a degree of crystallinity of less than 25 wt. %, as determined by X-ray and differential scanning calorimetry. Copolymers of ethylene and propylene are most preferred. Other alpha-olefins suitable in place of propylene to form the copolymer, or to be used in combination with ethylene and propylene, to form a terpolymer, tetrapolymer, etc., include 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, etc.; also branched chain alpha-olefins, such as 4-methyl-1-pentene, 4-methyl-
 55 1-hexene, 5-methylpentene-1, 4,4-dimethyl-1-pentene, and 6-methylheptene-1, etc., and mixtures thereof.

Terpolymers, tetrapolymers, etc., of ethylene, said C_3 - C_{28} alpha-olefin, and a non-conjugated diolefin or mixtures of such diolefins may also be used. The amount of the non-conjugated diolefin generally ranges from about 0.5 to 20 mole percent, preferably from about 1 to about 7 mole percent, based on the total

amount of ethylene and alpha-olefin present.

The polyester V.I. improvers are generally polymers of esters of ethylenically unsaturated C₃ to C₈ mono- and dicarboxylic acids such as methacrylic and acrylic acids, maleic acid, maleic anhydride, fumaric acid, etc.

5 Examples of unsaturated esters that may be used include those of aliphatic saturated mono alcohols of at least 1 carbon atom and preferably of from 12 to 20 carbon atoms, such as decyl acrylate, lauryl acrylate, stearyl acrylate, eicosanyl acrylate, docosanyl acrylate, decyl methacrylate, diamyl fumarate, lauryl methacrylate, cetyl methacrylate, stearyl methacrylate, and the like and mixtures thereof.

10 Other esters include the vinyl alcohol esters of C₂ to C₂₂ fatty or mono carboxylic acids, preferably saturated such as vinyl acetate, vinyl laurate, vinyl palmitate, vinyl stearate, vinyl oleate, and the like and mixtures thereof. Copolymers of vinyl alcohol esters with unsaturated acid esters such as the copolymer of vinyl acetate with dialkyl fumarates, can also be used.

15 The esters may be copolymerized with still other unsaturated monomers such as olefins, e.g. 0.2 to 5 moles of C₂ - C₂₀ aliphatic or aromatic olefin per mole of unsaturated ester, or per mole of unsaturated acid or anhydride followed by esterification. For example, copolymers of styrene with maleic anhydride esterified with alcohols and amines are known, e.g., see U.S. Patent 3,702,300.

Such ester polymers may be grafted with, or the ester copolymerized with, polymerizable unsaturated nitrogen-containing monomers to impart dispersancy to the V.I. improvers. Examples of suitable unsaturated nitrogen-containing monomers include those containing 4 to 20 carbon atoms such as amino substituted olefins as p-(beta-diethylaminoethyl)styrene; basic nitrogen-containing heterocycles carrying a polymeriza-
20 ble ethylenically unsaturated substituent, e.g. the vinyl pyridines and the vinyl alkyl pyridines such as 2-vinyl-5-ethyl pyridine, 2-methyl-5-vinyl pyridine, 2-vinyl-pyridine, 4-vinylpyridine, 3-vinyl-pyridine, 3-methyl-5-vinyl-pyridine, 4-methyl-2-vinyl-pyridine, 4-ethyl-2-vinyl-pyridine and 2-butyl-1-5-vinyl-pyridine and the like.


25 N-vinyl lactams are also suitable, e.g. N-vinyl pyrrolidones or N-vinyl piperidones.

The vinyl pyrrolidones are preferred and are exemplified by N-vinyl pyrrolidone, N-(1-methylvinyl) pyrrolidone, N-vinyl-5-methyl pyrrolidone, N-vinyl-3, 3-dimethylpyrrolidone, N-vinyl-5-ethyl pyrrolidone, etc.

30 Dihydrocarbyl dithiophosphate metal salts are frequently used as anti-wear agents and also provide antioxidant activity. The zinc salts are most commonly used in lubricating oil in amounts of 0.1 to 10, preferably 0.2 to 2 wt. %, based upon the total weight of the lubricating oil composition. They may be prepared in accordance with known techniques by first forming a dithiophosphoric acid, usually by reaction of an alcohol or a phenol with P₂S₅ and then neutralizing the dithiophosphoric acid with a suitable zinc compound.

35 Mixtures of alcohols may be used including mixtures of primary and secondary alcohols, secondary generally for imparting improved anti-wear properties, with primary giving improved thermal stability properties. Mixtures of the two are particularly useful. In general, any basic or neutral zinc compound could be used but the oxides, hydroxides and carbonates are most generally employed. Commercial additives frequently contain an excess of zinc due to use of an excess of the basic zinc compound in the neutralization reaction.

40 The zinc dihydrocarbyl dithiophosphates useful in the present invention are oil soluble salts of dihydrocarbyl esters of dithiophosphoric acids and may be represented by the following formula:



45 wherein R and R' may be the same or different hydrocarbyl radicals containing from 1 to 18, preferably 2 to 12 carbon atoms and including radicals such as alkyl, alkenyl, aryl, aralkyl, alkaryl and cycloaliphatic radicals. Particularly preferred as R and R' groups are alkyl groups of 2 to 8 carbon atoms. Thus, the
50 radicals may, for example, be ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec-butyl, amyl, n-hexyl, i-hexyl, n-octyl, decyl, dodecyl, octadecyl, 2-ethylhexyl, phenyl, butylphenyl, cyclohexyl, methylcyclopentyl, propenyl, butenyl etc. In order to obtain oil solubility, the total number of carbon atoms (i.e., R and R' in formula XXIII) in the dithiophosphoric acid will generally be about 5 or greater.

The antioxidants useful in this invention include oil soluble copper compounds. The copper may be blended into the oil as any suitable oil soluble copper compound. By oil soluble we mean the compound is oil soluble under normal blending conditions in the oil or additive package. The copper compound may be in the cuprous or cupric form. The copper may be in the form of the copper dihydrocarbyl thio- or dithio-phosphates wherein copper may be substituted for zinc in the compounds and reactions described above although one mole of cuprous or cupric oxide may be reacted with one or two moles of the dithiophosphoric acid, respectively. Alternatively the copper may be added as the copper salt of a synthetic or natural carboxylic acid. Examples include C_{10} to C_{18} fatty acids such as stearic or palmitic, but unsaturated acids such as oleic or branched carboxylic acids such as naphthenic acids of molecular weight from 200 to 500 or synthetic carboxylic acids are preferred because of the improved handling and solubility properties of the resulting copper carboxylates. Also useful are oil soluble copper dithiocarbamates of the general formula $(RR'NCSS)_nCu$, where n is 1 or 2 and R and R' are the same or different hydrocarbyl radicals containing from 1 to 18 and preferably 2 to 12 carbon atoms and including radicals such as alkyl, alkenyl, aryl, aralkyl, alkaryl and cycloaliphatic radicals. Particularly preferred as R and R' groups are alkyl groups of 2 to 8 carbon atoms. Thus, the radicals may, for example, be ethyl, n-propyl, i-propyl, n-butyl, i-butyl, sec-butyl, amyl, n-hexyl, i-hexyl, n-heptyl, n-octyl, decyl, dodecyl, octadecyl, 2-ethylhexyl, phenyl, butylphenyl, cyclohexyl, methylcyclopentyl, propenyl, butenyl, etc. In order to obtain oil solubility, the total number of carbon atoms (i.e., R and R') will generally be about 5 or greater. Copper sulphonates, phenates, and acetylacetonates may also be used.

Exemplary of useful copper compounds are copper (Cu^I and/or Cu^{II}) salts of alkenyl succinic acids or anhydrides. The salts themselves may be basic, neutral or acidic. They may be formed by reacting (a) any of the materials discussed above in the Ashless Dispersant section, which have at least one free carboxylic acid (or anhydride) group with (b) a reactive metal compound. Suitable acid (or anhydride) reactive metal compounds include those such as cupric or cuprous hydroxides, oxides, acetates, borates, and carbonates or basic copper carbonate.

Examples of the metal salts of this invention are Cu salts of polyisobutenyl succinic anhydride (hereinafter referred to as Cu-PIBSA), and Cu salts of polyisobutenyl succinic acid. Preferably, the selected metal employed is its divalent form, e.g., Cu^{+2} . The preferred substrates are polyalkenyl succinic acids in which the alkenyl group has a molecular weight greater than 700. The alkenyl group desirably has a M_n from 900 to 1400, and up to 2500, with a M_n of about 950 being most preferred. Especially preferred, of those listed above in the section on Dispersants, is polyisobutylene succinic acid (PIBSA). These materials may desirably be dissolved in a solvent, such as a mineral oil, and heated in the presence of a water solution (or slurry) of the metal bearing material. Heating may take place between 70° and $200^\circ C$. Temperatures of 110° to $140^\circ C$ are entirely adequate. It may be necessary, depending upon the salt produced, not to allow the reaction to remain at a temperature above about $140^\circ C$ for an extended period of time, e.g., longer than 5 hours, or decomposition of the salt may occur.

The copper antioxidants (e.g., Cu-PIBSA, Cu-oleate, or mixtures thereof) will be generally employed in an amount of from 50-500 ppm by weight of the metal, in the final lubricating composition.

The copper antioxidants used in this invention are inexpensive and are effective at low concentrations and therefore do not add substantially to the cost of the product. The results obtained are frequently better than those obtained with previously used antioxidants, which are expensive and used in higher concentrations. In the amounts employed, the copper compounds do not interfere with the performance of other components of the lubricating composition, in many instances, completely satisfactory results are obtained when the copper compound is the sole antioxidant in addition to the ZDDP. The copper compounds can be utilized to replace part or all of the need for supplementary antioxidants. Thus, for particularly severe conditions it may be desirable to include a supplementary, conventional antioxidant. However, the amounts of supplementary antioxidant required are small, far less than the amount required in the absence of the copper compound.

While any effective amount of the copper antioxidant can be incorporated into the lubricating oil composition, it is contemplated that such effective amounts be sufficient to provide said lube oil composition with an amount of the copper antioxidant of from 5 to 500 (more preferably 10 to 200, still more preferably 10 to 180, and most preferably 20 to 130 (e.g., 90 to 120)) part per million of added copper based on the weight of the lubricating oil composition. Of course, the preferred amount may depend amongst other factors on the quality of the basestock lubricating oil.

Corrosion inhibitors, also known as anti-corrosive agents, reduce the degradation of the metallic parts contacted by the lubricating oil composition. Illustrative of corrosion inhibitors are phosphosulfurized hydrocarbons and the products obtained by reaction of a phosphosulfurized hydrocarbon with an alkaline earth metal oxide or hydroxide, preferably in the presence of an alkylated phenol or of an alkylphenol

thioester, and also preferably in the presence of carbon dioxide. Phosphosulfurized hydrocarbons are prepared by reacting a suitable hydrocarbon such as a terpene, a heavy petroleum fraction of a C₂ to C₆ olefin polymer such as polyisobutylene, with from 5 to 30 weight percent of a sulfide of phosphorus for 1/2 to 15 hours, at a temperature in the range of 65° to 315°C. Neutralization of the phosphosulfurized hydrocarbon may be effected in the manner taught in U.S. Patent No. 1,969,324.

Oxidation inhibitors reduce the tendency of mineral oils to deteriorate in service which deterioration can be evidenced by the products of oxidation such as sludge and varnish-like deposits on the metal surfaces and by viscosity growth. Such oxidation inhibitors include alkaline earth metal salts of alkylphenolthioesters having preferably C₅ to C₁₂ alkyl side chains, calcium nonylphenol sulfide, barium t-octylphenyl sulfide, dioctylphenylamine, phenylalphanaphthylamine, phosphosulfurized or sulfurized hydrocarbons, etc.

Friction modifiers serve to impart the proper friction characteristics to lubricating oil compositions such as automatic transmission fluids.

Representative examples of suitable friction modifiers are found in U.S. Patent No. 3,933,659 which discloses fatty acid esters and amides; U.S. Patent No. 4,176,074 which describes molybdenum complexes of polyisobutenyl succinic anhydride-amino alkanols; U.S. Patent No. 4,105,571 which discloses glycerol esters of dimerized fatty acids; U.S. Patent No. 3,779,928 which discloses alkane phosphonic acid salts; U.S. Patent No. 3,778,375 which discloses reaction products of a phosphonate with an oleamide; U.S. Patent No. 3,852,205 which discloses S-carboxy-alkylene hydrocarbyl succinimide, S-carboxyalkylene hydrocarbyl succinamic acid and mixtures thereof; U.S. Patent No. 3,879,306 which discloses N-(hydroxyalkyl) alkenyl-succinamic acids or succinimides; U.S. Patent No. 3,932,290 which discloses reaction products of di-(lower alkyl) phosphites and epoxides; and U.S. Patent No. 4,028,258 which discloses the alkylene oxide adduct of phosphosulfurized N-(hydroxyalkyl) alkenyl succinimides. The disclosures of the above references are herein incorporated by reference. The most preferred friction modifiers are glycerol mono and dioleates, and succinate esters, or metal salts thereof, of hydrocarbyl substituted succinic acids or anhydrides and thiois alkanols such as described in U.S. Patent No. 4,344,853.

Pour point depressants lower the temperature at which the lubricating oil will flow or can be poured. Such depressants are well known. Typical of those additives which usefully optimize the low temperature fluidity of the fluid are C₈-C₁₈ dialkylfumarate vinyl acetate copolymers, polymethacrylates, and wax naphthalene.

Foam control can be provided by an antifoamant of the polysiloxane type, e.g. silicone oil and polydimethyl siloxane.

Organic, oil-soluble compounds useful as rust inhibitors in this invention comprise nonionic surfactants such as polyoxyalkylene polyols and esters thereof, and anionic surfactants such as salts of alkyl sulfonic acids. Such anti-rust compounds are known and can be made by conventional means. Nonionic surfactants, useful as anti-rust additives in the oleaginous compositions of this invention, usually owe their surfactant properties to a number of weak stabilizing groups such as ether linkages. Nonionic anti-rust agents containing ether linkages can be made by alkoxylating organic substrates containing active hydrogens with an excess of the lower alkylene oxides (such as ethylene and propylene oxides) until the desired number of alkoxy groups have been placed in the molecule.

The preferred rust inhibitors are polyoxyalkylene polyols and derivatives thereof. This class of materials are commercially available from various sources: Pluronic Polyols from Wyandotte Chemicals Corporation; Polyglycol 112-2, a liquid triol derived from ethylene oxide and propylene oxide available from Dow Chemical Co.; and Tergitol, dodecylphenyl or monophenyl polyethylene glycol ethers, and Ucon, polyalkylene glycols and derivatives, both available from Union Carbide Corp. These are but a few of the commercial products suitable as rust inhibitors in the improved composition of the present invention.

In addition to the polyols per se, the esters thereof obtained by reacting the polyols with various carboxylic acids are also suitable. Acids useful in preparing these esters are lauric acid, stearic acid, succinic acid, and alkyl- or alkenyl-substituted succinic acids wherein the alkyl- or alkenyl group contains up to about twenty carbon atoms.


The preferred polyols are prepared as block polymers. Thus, a hydroxy-substituted compound, R-(OH)_n (wherein n is 1 to 6, and R is the residue of a mono- or polyhydric alcohol, phenol, naphthol, etc.) is reacted with propylene oxide to form a hydrophobic base. This base is then reacted with ethylene oxide to provide a hydrophylic portion resulting in a molecule having both hydrophobic and hydrophylic portions. The relative sizes of these portions can be adjusted by regulating the ratio of reactants, time of reaction, etc., as is obvious to those skilled in the art. Thus it is within the skill of the art to prepare polyols whose molecules are characterized by hydrophobic and hydrophylic moieties which are present in a ratio rendering rust inhibitors suitable for use in any lubricant composition regardless of differences in the base oils and the presence of other additives.

If more oil-solubility is needed in a given lubricating composition, the hydrophobic portion can be increased and/or the hydrophylic portion decreased. If greater oil-in-water emulsion breaking ability is required, the hydrophylic and/or hydrophobic portions can be adjusted to accomplish this.


Compounds illustrative of $R-(OH)_n$ include alkylene polyols such as the alkylene glycols, alkylene triols, 5 alkylene tetrols, etc., such as ethylene glycol, propylene glycol, glycerol, pentaerythritol, sorbitol, mannitol, and the like. Aromatic hydroxy compounds such as alkylated mono- and polyhydric phenols and naphthols can also be used, e.g., heptylphenol, dodecylphenol, etc.

Other suitable demulsifiers include the esters disclosed in U.S. Patents 3,098,827 and 2,674,619.

The liquid polyols available from Wyandotte Chemical Co. under the name Pluronic Polyols and other 10 similar polyols are particularly well suited as rust inhibitors. These Pluronic Polyols correspond to the formula:



wherein x, y, and z are integers greater than 1 such that the $\text{CH}_2\text{CH}_2\text{O}-$ groups comprise from about 10% 20 to about 40% by weight of the total molecular weight of the glycol, the average molecule weight of said glycol being from about 1000 to 5000. These products are prepared by first condensing propylene oxide with propylene glycol to product the hydrophobic base



This condensation product is then treated with ethylene oxide to add hydrophylic portions to both ends of 30 the molecule. For best results, the ethylene oxide units should comprise from 10 to 40% by weight of the molecule. Those products wherein the molecular weight of the polyol is from 2500 to 4500 and the ethylene oxide units comprise from 10% to 15% by weight of the molecule are particularly suitable. The polyols having a molecular weight of about 4000 with about 10% attributable to $(\text{CH}_2\text{CH}_2\text{O})$ units are particularly 35 good. Also useful are alkoxyated fatty amines, amides, alcohols and the like, including such alkoxyated fatty acid derivatives treated with C_3 to C_{16} alkyl-substituted phenols (such as the mono- and di-heptyl, octyl, nonyl, decyl, undecyl, dodecyl and tridecyl phenols), as described in U.S. Patent 3,849,501, which is also hereby incorporated by reference in its entirety.

These compositions of our invention may also contain other additives such as those previously 40 described, and other metal containing additives, for example, those containing barium and sodium.

The lubricating composition of the present invention may also include copper lead bearing corrosion inhibitors. Typically such compounds are the thiadiazole polysulphides containing from 5 to 50 carbon atoms, their derivatives and polymers thereof. Preferred materials are the derivatives of 1,3,4-thiadiazoles such as those described in U.S. Patents 2,719,125; 2,719,126; and 3,087,932; especially preferred is the 45 compound 2,5 bis (t-octadithio)-1,3,4-thiadiazole commercially available as Amoco 150. Other similar materials also suitable are described in U.S. Patents 3,821,246; 3,903,537; 4,097,387; 4,107,059; 4,136,043; 4,188,299; and 4,193,882.

Other suitable additives are the thio and polythio sulphenamides of thiadiazoles such as those described in U.K. Patent Specification 1,560,830. When these compounds are included in the lubricating 50 composition, we prefer that they be present in an amount from 0.01 to 10, preferably 0.1 to 5.0 weight percent based on the weight of the composition.

Dispersants maintain oil insolubles, resulting from oxidation during use, in suspension in the fluid thus preventing slide glocculation and precipitation or deposition on metal parts. Suitable dispersants include high molecular weight alkyl succinimides, the reaction product of oil-soluble polyisobutylene succinic 55 anhydride with ethylene amines such as tetraethylene pentamine and borated salts thereof.

The ashless dispersants include the polyalkenyl or borated polyalkenyl succinimide where the alkenyl groups is derived from a C_3 - C_4 olefin, especially polyisobutenyl having a number average molecular weight of 700 to 5,000. Other well known dispersants include the oil soluble polyol esters of hydrocarbon

substituted succinic anhydride, e.g., polyisobutenyl succinic anhydride, and the oil soluble oxazoline and lactone oxazoline dispersants derived from hydrocarbon substituted succinic anhydride and disubstituted amino alcohols. Lubricating oils typically contain 0.5 to 5 wt. % of ashless dispersant.

Some of these numerous additives can provide a multiplicity of effects, e.g. a dispersant-oxidation inhibitor. This approach is well known and need not be further elaborated herein.

Compositions when containing these conventional additives are typically blended into the base oil in amounts effective to provide their normal attendant function. Representative effective amounts of such additives (as the respective active ingredients) in the fully formulated oil are illustrated as follows:

<u>Compositions</u>	<u>Wt. % A.I.</u> <u>(Preferred)</u>	<u>Wt. % A.I.</u> <u>(Broad)</u>
Viscosity Modifier	.01-4	0.01-12
Detergents	0.01-3	0.01-20
Corrosion Inhibitor	0.01-1.5	.01-5
Oxidation Inhibitor	0.01-1.5	.01-5
Dispersant	0.1-8	.1-20
Pour Point Depressant	0.01-1.5	.01-5
Anti-Foaming Agents	0.001-0.15	.001-3
Anti-Wear Agents	0.001-1.5	.001-5
Friction Modifiers	0.01-1.5	.01-5
Mineral Oil Base	Balance	Balance

When other additives are employed, it may be desirable, although not necessary, to prepare additive concentrates comprising concentrated solutions or dispersions of the novel multifunctional viscosity index improver of this invention (in concentrate amounts hereinabove described), together with one or more of said other additives (said concentrate when constituting an additive mixture being referred to herein as an additive-package) whereby several additives can be added simultaneously to the base oil to form the lubricating oil composition. Dissolution of the additive concentrate into the lubricating oil may be facilitated by solvents and by mixing accompanied with mild heating, but this is not essential. The concentrate or additive-package will typically be formulated to contain the additives in proper amounts to provide the desired concentration in the final formulation when the additive-package is combined with a predetermined amount of base lubricant. Thus, the multifunctional viscosity index improver of the present invention can be added to small amounts of base oil or other compatible solvents along with other desirable additives to form additive-packages containing active ingredients in collective amounts of typically from 2.5 to 90%, and preferably from 15 to 75%, and most preferably from 25 to 60% by weight additives in the appropriate proportions with the remainder being base oil.

The final formulations may employ typically about 10 wt. % of the additive-package with the remainder being base oil.

All of said weight percents expressed herein (unless otherwise indicated) are based on active ingredient (A.I.) content of the additive, and/or upon the total weight of any additive-package, or formulation which will be the sum of the A.I. weight of each additive plus the weight of total oil or diluent.

This invention will be further understood by reference to the following examples, wherein all parts are parts by weight, unless otherwise noted.

EXAMPLE 1 - PREPARATION OF ETHYLENE-PROPYLENE COPOLYMER

A clean, dry autoclave is flushed with propylene and a 4 ml. solution of methylalumoxane in toluene is added by syringe. The autoclave is then charged with 500 ml. of liquid propylene and brought to 50 °C for reaction. The pressure in the autoclave is then increased by 150 psi by addition of ethylene. One-half mg. of zirconocene (bis(n-butyl tetrahydroindenyl)zirconium dichloride) dissolved in 3 ml. of toluene is injected into the autoclave. Ethylene is supplied to maintain the initial total pressure in the autoclave. Reaction time

is 30 minutes. The monomers are flashed off, and the temperature is brought to 25°C. The polymer product, which has a number average molecular weight in the range of about 209,000, is recovered from the autoclave and is dried in a vacuum oven at 50°C overnight.

5 EXAMPLE 2 - PREPARATION OF ETHYLENE-PROPYLENE COPOLYMER SUBSTITUTED SUCCINIC ANHYDRIDE (EPSA)

10 Into a pressure reactor equipped with a stirrer and a thermocouple and heated by means of an electric heating mantle are charged under dry N₂ at atmospheric pressure 1.2 moles of pulverized maleic anhydride for every one mole of ethylene propylene copolymer, which copolymer is prepared substantially in accordance with the procedure of Example 1. The reaction mixture is heated to 70°C and the reactor is purged with dry N₂ by bubbling through the liquid reaction mass for 15 minutes. The purging is then ceased and the reactor temperature is raised to 220°C and is kept there under autogenous pressure for 4 hours while stirring. The liquid reaction mixture is then cooled to about 60°C, and transferred to a glass beaker. Dry gaseous nitrogen is passed through the liquid to strip off unreacted maleic anhydride at about 140°C. The resultant liquid product contains the EPSA and unreacted EP.

EXAMPLE 3 - PREPARATION OF EPSA-PAM

20 Succinic acid anhydride substituted ethylene-propylene copolymer which is prepared substantially in accordance with the procedure of Example 2 is dissolved in an equal amount by weight of a mineral oil, S150N. To the polymer (EPSA) solution is added a mixture of polyethylene polyamines having the average composition corresponding to tetraethylene pentamine and containing about 32.6 wt. % N (PAM), and the reaction mixture is heated to 140°C under nitrogen while stirring for about 2 to 4 hours. The molar ratio of total polymer to polyamine in terms of succinic acid equivalents to PAM which is charged is 2 to 1.

EXAMPLE 4

30 An SAE 10W40 formulation crankcase motor oil composition is prepared by dissolving sufficient EPSA-PAM which is prepared substantially in accordance with the procedure of Example 4 in mineral oil to provide a composition containing 1.3 wt. % (active ingredient) of said copolymer. The oil also contains 4.3 wt. % of a detergent inhibitor package of conventional additives.

The principles, preferred embodiments, and modes of operation of the present invention have been described in the foregoing specification. The invention which is intended to be protected herein, however, is not to be construed as limited to the particular forms disclosed, since these are to be regarded as illustrative rather than restrictive. Variations and changes may be made by those skilled in the art without departing from the spirit of the invention.

Claims

- 40 1. A composition useful as an oleaginous composition additive which comprises an ethylene alpha-olefin polymer substituted with at least one of C₃ to C₁₀ monounsaturated monocarboxylic acid producing moieties and C₄ to C₁₀ monounsaturated dicarboxylic acid producing moieties, said polymer comprising monomer units derived from ethylene and at least one alpha-olefin of the formula H₂C=CHR¹ wherein R¹ is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight of from greater than 20,000 to 500,000, and wherein an average of at least 30% of said polymer chains contain terminal ethenylidene unsaturation.
- 45 2. The composition of claim 1 wherein said polymer has a number average molecular weight is from 35,000 to 50,000.
- 50 3. The composition of claim 1 or claim 2 wherein said polymer has a molar ethylene content of from 45 to 65 percent.
- 55 4. A composition as claimed in any of claims 1 to 3 wherein R¹ is an alkyl group of from 1 to 2 carbon atoms, and wherein an average of at least 60% of said polymer chains contain terminal ethenylidene unsaturation.

is 30 minutes. The monomers are flashed off, and the temperature is brought to 25°C. The polymer product, which has a number average molecular weight in the range of about 209,000, is recovered from the autoclave and is dried in a vacuum oven at 50°C overnight.

5 EXAMPLE 2 - PREPARATION OF ETHYLENE-PROPYLENE COPOLYMER SUBSTITUTED SUCCINIC ANHYDRIDE (EPSA)

Into a pressure reactor equipped with a stirrer and a thermocouple and heated by means of an electric heating mantle are charged under dry N₂ at atmospheric pressure 1.2 moles of pulverized maleic anhydride
10 for every one mole of ethylene propylene copolymer, which copolymer is prepared substantially in accordance with the procedure of Example 1. The reaction mixture is heated to 70°C and the reactor is purged with dry N₂ by bubbling through the liquid reaction mass for 15 minutes. The purging is then ceased and the reactor temperature is raised to 220°C and is kept there under autogenous pressure for 4 hours while stirring. The liquid reaction mixture is then cooled to about 60°C, and transferred to a glass
15 beaker. Dry gaseous nitrogen is passed through the liquid to strip off unreacted maleic anhydride at about 140°C. The resultant liquid product contains the EPSA and unreacted EP.

EXAMPLE 3 - PREPARATION OF EPSA-PAM

20 Succinic acid anhydride substituted ethylene-propylene copolymer which is prepared substantially in accordance with the procedure of Example 2 is dissolved in an equal amount by weight of a mineral oil, S150N. To the polymer (EPSA) solution is added a mixture of polyethylene polyamines having the average composition corresponding to tetraethylene pentamine and containing about 32.6 wt. % N (PAM), and the reaction mixture is heated to 140°C under nitrogen while stirring for about 2 to 4 hours. The molar ratio of
25 total polymer to polyamine in terms of succinic acid equivalents to PAM which is charged is 2 to 1.

EXAMPLE 4

An SAE 10W40 formulation crankcase motor oil composition is prepared by dissolving sufficient EPSA-
30 PAM which is prepared substantially in accordance with the procedure of Example 4 in mineral oil to provide a composition containing 1.3 wt. % (active ingredient) of said copolymer. The oil also contains 4.3 wt. % of a detergent inhibitor package of conventional additives.

The principles, preferred embodiments, and modes of operation of the present invention have been described in the foregoing specification. The invention which is intended to be protected herein, however, is
35 not to be construed as limited to the particular forms disclosed, since these are to be regarded as illustrative rather than restrictive. Variations and changes may be made by those skilled in the art without departing from the spirit of the invention.

Claims


- 40
1. A composition useful as an oleaginous composition additive which comprises an ethylene alpha-olefin polymer substituted with at least one of C₃ to C₁₀ monounsaturated monocarboxylic acid producing moieties and C₄ to C₁₀ monounsaturated dicarboxylic acid producing moieties, said polymer comprising monomer units derived from ethylene and at least one alpha-olefin of the formula H₂C=CHR¹
45 wherein R¹ is an alkyl group of from 1 to 18 carbon atoms, and wherein said polymer has a number average molecular weight of from greater than 20,000 to 500,000, and wherein an average of at least 30% of said polymer chains contain terminal ethenylidene unsaturation.
 2. The composition of claim 1 wherein said polymer has a number average molecular weight is from
50 35,000 to 50,000.
 3. The composition of claim 1 or claim 2 wherein said polymer has a molar ethylene content of from 45 to 65 percent.
 - 55 4. A composition as claimed in any of claims 1 to 3 wherein R¹ is an alkyl group of from 1 to 2 carbon atoms, and wherein an average of at least 60% of said polymer chains contain terminal ethenylidene unsaturation.



5. The composition of any of claims 1 to 4 wherein said polymer comprises an ethylene-propylene copolymer.
6. The composition of any of claims 1 to 5 wherein said polymer is substantially halogen free.
7. The composition of any of claims 1 to 6 wherein said monounsaturated carboxylic acid producing moiety is derived from at least one monounsaturated carboxylic reactant selected from the group consisting of (i) monounsaturated C_4 to C_{10} dicarboxylic acids wherein (a) the carboxyl groups are attached to adjacent carbon atoms and (b) at least one of said adjacent carbon atoms are part of said mono unsaturation; (ii) anhydride or C_1 to C_5 alcohol derived mono- or di-ester derivatives of (i); (iii) monounsaturated C_3 to C_{10} monocarboxylic acids wherein the carbon-carbon double bond is allylic to the carboxy group; and (iv) C_1 to C_5 alcohol derived mono- or di-esters derivatives of (iii).
8. The composition of claim 7 wherein said monounsaturated carboxylic reactant comprises at least one of fumaric acid, itaconic acid, maleic acid, maleic anhydride, chloromaleic acid, chloromaleic anhydride, acrylic acid, methacrylic acid, crotonic acid, cinnamic acid, and lower alkyl acid esters of the foregoing acids.
9. The composition of any of claims 1 to 8 wherein said substituted polymer has a functionality of at least 0.8.
10. The composition of claim 9 wherein said substituted polymer has a functionality of from 0.5 to 2.8.
11. The composition of any of claims 1 to 10 wherein said substituted polymer contains less than 25 ppm by weight of chlorine.
12. The composition of claim 11 wherein said substituted polymer contains less than 10 ppm by weight of chlorine.
13. The composition of any of claims 1 to 12 wherein said composition contains less than 40 wt. % of said ethylene alpha-olefin polymer unsubstituted by said acid producing moieties.
14. A process for producing a composition useful as additive for oleaginous compositions which comprises contacting:
 - (a) an ethylene alpha-olefin polymer comprising monomer units derived from ethylene and at least one alpha-olefin of the formula $H_2C=CHR^1$ wherein R^1 is an alkyl group of from 1 to 18 carbon atoms, said polymer having a number average molecular weight of from greater than 20,000 to 500,000, and wherein an average of at least 30% of the polymer chains contain terminal ethenylidene unsaturation; with
 - (b) at least one monounsaturated carboxylic reactant selected from the group consisting of (i) monounsaturated C_4 to C_{10} dicarboxylic acids wherein (a) the carboxyl groups are attached to adjacent carbon atoms and (b) at least one of said adjacent carbon atoms are part of said monounsaturation; (ii) anhydride or C_1 to C_5 alcohol derived mono- or di-ester derivatives of (i); (iii) monounsaturated C_3 to C_{10} monocarboxylic acids wherein the carbon-carbon double bond is allylic to the carboxy group; and (iv) C_1 to C_5 alcohol derived mono- or di-esters derivatives of (iii) under conditions and for a time sufficient to form a product containing an ethylene alpha-olefin polymer substituted with said carboxylic acid moieties.
15. The process of claim 14 wherein said contacting is conducted at a temperature of from about 120 to 260 °C.
16. The process of claim 14 or claim 15 wherein said contacting is conducted for a time of from about 1 to 20 hours.
17. The process of any of claims 14 to 16 wherein said ethylene alpha-olefin polymer and said at least one monounsaturated carboxylic reactant are contacted in the presence of a lubricating oil solvent or diluent.



18. The process of any of claims 14 to 17 wherein said polymer is characterized by a polydispersity of from 1.2 to 3.0.
19. An oil soluble composition useful as a multifunctional viscosity index improver additive for oleaginous composition comprising adduct of:
- ethylene alpha-olefin polymer substituted with mono- or dicarboxylic acid producing moieties as defined in any of claims 1 to 13 or the product of any of claims 14 to 18 and
 - at least one nucleophilic reagent selected from amines, alcohols, metal reactants and mixtures thereof.
20. The composition of claim 19 wherein said acid producing moieties comprise succinic anhydride, succinic acid or propionic acid.
21. The composition of claim 19 or 20 wherein the nucleophilic reagent comprises an amine containing from 2 to 60 carbon atoms and from 1 to 12 nitrogen atoms per molecule.
22. The composition of claim 19 or 20 wherein said amine comprises a polyalkylenepolyamine wherein said alkylene group contains 2 to 60 carbons, preferably 2 to 40 carbons, and said polyalkylenepolyamine contains from 2 to 9 nitrogen atoms per molecule, preferably from 5 to 9 nitrogen atoms per molecule.
23. The composition of claim 22 wherein said amine comprises polyethylenepolyamine.
24. The composition of claim 19 or 20 wherein said nucleophilic reagent comprises an amido-amine or a thioamido-amine characterized by being a reaction product of at least a polyamine and an alpha, beta-unsaturated compound of the formula:



- wherein X is sulfur or oxygen, Y is $-\text{OR}^4$, $-\text{SR}^4$, or $-\text{NR}^4(\text{R}^5)$, and R^1 , R^2 , R^3 , R^4 and R^5 are the same or different and are hydrogen or substituted or unsubstituted hydrocarbyl.
25. The composition of claim 24, wherein the polyamine is as defined in claim 21 or 22.
26. The composition according to claim 25, wherein said polyamine comprises polyalkylenepolyamine wherein said alkylene groups contain 2 to 6 carbons and said polyalkylenepolyamine contains 5 to 9 nitrogen atoms per molecule, and said alpha, beta-unsaturated compound comprises at least one member selected from the group consisting of methyl acrylate, ethyl acrylate, propyl acrylate, butyl acrylate, methyl methacrylate, ethyl methacrylate, propyl methacrylate, and butyl methacrylate.
27. The composition according to claim 26 wherein said polyamine comprises polyethylenepolyamine or polypropyleneamine.
28. The composition of any of claims 24 to 27 wherein 1 to 5 moles of said acid producing moieties per primary nitrogen equivalent of said amido-amine are present in said reaction mixture.
29. The composition according to claim 28 wherein said polyamine contains an average of at least 2 primary nitrogen atoms per molecule, said X group is oxygen and said polyamine is contacted in an amount of from 3 to 5 equivalents of said polyamine (based on said primary amine content) per mole of said alpha, beta unsaturated compound.
30. A process for producing an oleaginous composition additive which comprises:



- (i) forming ethylene alpha-olefin substituted mono- or dicarboxylic acid material by a process as claimed in any of claims 14 to 18, and
 (ii) reacting said ethylene alpha-olefin substituted mono- or dicarboxylic acid material found in (i) with a nucleophilic reagent.

- 5 31. A process as claimed in claim 30, in which the nucleophilic reagent is as defined in any of claims 19 and 21 to 29.
- 10 32. An oil soluble composition useful as multifunctional viscosity index improver additive for oleaginous composition comprising reaction product of:
 (a) ethylene alpha-olefin polymer substituted with mono- or dicarboxylic acid producing moieties as defined in any of claims 1 to 13 or obtainable by the process of any of claims 14 to 18, and
 (b) hydrocarbyl substituted carboxylic acid producing material containing 1 to 2 carboxylic acid groups or anhydride group wherein said hydrocarbyl contains an average number of carbon atoms
 15 of from 12 to 400; and
 (c) at least one nucleophilic reagent selected from the group consisting of amines, alcohols, metal reactants, and mixtures thereof.
- 20 33. The composition according to claim 32 wherein in (b) said hydrocarbyl contains an average of from 50 to 400 carbon atoms.
34. The composition according to claim 32 or claim 33 wherein (b) is selected from the group consisting of hydrocarbyl substituted succinic anhydride, hydrocarbyl substituted succinic acid, and mixtures thereof.
- 25 35. The composition according to claim 34 wherein said hydrocarbyl is selected from polybutylene, polyisobutylene, and mixtures thereof.
36. The composition according to any of claims 32 to 35 wherein the nucleophilic reagent (c) is as defined in any of claims 21 to 29.
- 30 37. The use of a composition as claimed in any of claims 1 to 13, 19 to 29 and 32 to 36 as a multifunctional viscosity index improver.
- 35 38. A lubricating oil concentrate containing from 1 to 80 wt. %, preferably 20 to 60 wt. %, of the oil soluble composition as claimed in any of claims 1 to 13, 19 to 29 and 32 to 36.
39. A lubricating oil composition containing a viscosity index improving amount of the oil soluble composition as claimed in any of claims 1 to 13, 19 to 29 and 32 to 36.
- 40 40. A lubricating oil composition according to claim 39 containing from 0.01 to 20 wt. %, preferably 0.1 to 10 wt. %, of said oil soluble composition.

Patentansprüche


- 45 1. Zusammensetzung, die als Additiv für eine ölige Zusammensetzung brauchbar ist und ein Ethylen/ α -Olefin-Polymer umfaßt, das mit mindestens einem von monoungesättigte C_3 - C_{10} -Monocarbonsäure liefernden Resten und monoungesättigte C_4 - C_{10} -Dicarbonsäure liefernden Resten substituiert ist, wobei das Polymer Monoeinheiten umfaßt, die sich von Ethylen und mindestens einem α -Olefin der Formel $H_2C=CHR^1$ ableiten, in der R^1 eine Alkylgruppe mit 1 bis 18 Kohlenstoffatomen ist, das Polymer ein
 50 durchschnittliches zahlenmäßiges Molekulargewicht größer als 20 000 bis 500 000 aufweist und ein Durchschnitt von mindestens 30 % der Polymerketten endständige ethenylidenische Ungesättigtheit aufweist.
2. Zusammensetzung nach Anspruch 1, bei der das Polymer ein durchschnittliches zahlenmäßiges Molekulargewicht von 35 000 bis 50 000 aufweist.
- 55 3. Zusammensetzung nach Anspruch 1 oder Anspruch 2, bei der das Polymer einen molaren Ethylengehalt von 45 bis 65 % aufweist.



4. Zusammensetzung nach einem der Ansprüche 1 bis 3, bei der R¹ eine Alkylgruppe mit 1 bis 2 Kohlenstoffatomen ist und ein Durchschnitt von mindestens 60 % der Polymerketten endständige ethenylidenische Ungesättigtheit aufweist.
5. Zusammensetzung nach einem der Ansprüche 1 bis 4, bei der das Polymer ein Ethylen/Propylen-Copolymer umfaßt.
6. Zusammensetzung nach einem der Ansprüche 1 bis 5, bei der das Polymer im wesentlichen halogenfrei ist.
7. Zusammensetzung nach einem der Ansprüche 1 bis 6, bei der der monoungesättigte Carbonsäure produzierende Rest sich von mindestens einem monoungesättigten Carbonsäurereaktanten ableitet, der ausgewählt ist aus der Gruppe bestehend aus (i) monoungesättigten C₄-C₁₀-Dicarbonsäuren, bei denen (a) die Carboxylgruppen an benachbarten Kohlenstoffatomen gebunden sind und (b) mindestens eines der benachbarten Kohlenstoffatome Teil der Monoungesättigtheit ist, (ii) sich von Anhydrid oder C₁-C₅-Alkohol ableitenden Mono- oder Diesterderivaten von (i), (iii) monoungesättigten C₃-C₁₀-Monocarbonsäuren, bei denen die Kohlenstoff-Kohlenstoff-Doppelbindung zu der Carboxygruppe allylisch ist, und (iv) sich von C₁-C₅-Alkohol ableitenden Mono- oder Diesterderivaten von (iii).
8. Zusammensetzung nach Anspruch 7, bei der der monoungesättigte carboxylische Reaktant mindestens eine/einen von Fumarsäure, Itaconsäure, Maleinsäure, Maleinsäureanhydrid, Chlormaleinsäure, Chlormaleinsäureanhydrid, Acrylsäure, Methacrylsäure, Crotonsäure, Zimtsäure und niederen Alkylsäureestern der vorangegangenen Säuren umfaßt.
9. Zusammensetzung nach einem der Ansprüche 1 bis 8, bei der das substituierte Polymer eine Funktionalität von mindestens 0,8 aufweist.
10. Zusammensetzung nach Anspruch 9, bei der das substituierte Polymer eine Funktionalität von 0,5 bis 2,8 aufweist.
11. Zusammensetzung nach einem der Ansprüche 1 bis 10, bei der das substituierte Polymer bezogen auf das Gewicht weniger als 25 ppm an Chlor enthält.
12. Zusammensetzung nach Anspruch 11, bei der das substituierte Polymer bezogen auf das Gewicht weniger als 10 ppm an Chlor enthält.
13. Zusammensetzung nach einem der Ansprüche 1 bis 12, bei der die Zusammensetzung weniger als 40 Gew.-% des Ethylen/ α -Olefin-Polymers enthält, das nicht mit den säureproduzierenden Resten substituiert ist.
14. Verfahren zur Herstellung einer Zusammensetzung, die als Additiv für ölige Zusammensetzungen brauchbar ist, bei dem:
 - (a) ein Ethylen/ α -Olefin-Polymer, das Monomereinheiten umfaßt, die sich von Ethylen und mindestens einem α -Olefin der Formel H₂C=CHR¹ ableiten, in der R¹ eine Alkylgruppe mit 1 bis 18 Kohlenstoffatomen ist, wobei das Polymer ein durchschnittliches zahlenmäßiges Molekulargewicht größer als 20 000 bis 500 000 aufweist und ein Durchschnitt von mindestens 30 % der Polymerketten endständige ethenylidenische Ungesättigtheit aufweist, mit
 - (b) mindestens einem monoungesättigten carboxylischen Reaktanten ausgewählt aus der Gruppe bestehend aus (i) monoungesättigten C₄-C₁₀-Dicarbonsäuren, bei denen (a) die Carboxylgruppen an benachbarten Kohlenstoffatomen gebunden sind und (b) mindestens eines der benachbarten Kohlenstoffatome Teil der Monoungesättigtheit ist, (ii) sich von Anhydrid oder C₁-C₅-Alkohol ableitenden Mono- oder Diesterderivaten von (i), (iii) monoungesättigten C₃-C₁₀-Monocarbonsäuren, bei denen die Kohlenstoff-Kohlenstoff-Doppelbindung zu der Carboxygruppe allylisch ist, und (iv) sich von C₁-C₅-Alkohol ableitenden Mono- oder Diesterderivaten von (iii), unter Bedingungen und ausreichend lange kontaktiert wird, um ein Produkt zu bilden, daß ein Ethylen/ α -Olefin-Polymer enthält, das mit den Carbonsäureresten substituiert ist.



15. Verfahren nach Anspruch 14, bei dem die Kontaktierung bei einer Temperatur von etwa 120 bis 260 ° C durchgeführt wird.
16. Verfahren nach Anspruch 14 oder Anspruch 15, bei dem die Kontaktierung etwa 1 bis 20 Stunden lang durchgeführt wird.
17. Verfahren nach einem der Ansprüche 14 bis 16, bei dem das Ethylen/ α -Olefin-Polymer und der mindestens eine monounsättigte carboxylische Reaktant in Gegenwart eines Schmieröllösungsmittels oder -verdünnungsmittels kontaktiert werden.
18. Verfahren nach einem der Ansprüche 14 bis 17, bei dem das Polymer durch eine Polydispersität von 1,2 bis 3,0 gekennzeichnet ist.
19. Öllösliche Zusammensetzung, die als multifunktionelles Viskositätsindexverbessereradditiv für ölige Zusammensetzungen brauchbar ist und das Addukt von:
- (a) Ethylen/ α -Olefin-Polymer, das mit Mono- oder Dicarbonsäure produzierenden Resten wie definiert in einem der Ansprüche 1 bis 13 oder dem Produkt gemäß einem der Ansprüche 14 bis 18 substituiert ist, und
 - (b) mindestens einem nukleophilen Reagens ausgewählt aus Aminen, Alkoholen, Metallreaktanten und Mischungen derselben umfaßt.
20. Zusammensetzung nach Anspruch 19, bei der die säureproduzierenden Reste Bernsteinsäureanhydrid, Bernsteinsäure oder Propionsäure umfassen.
21. Zusammensetzung nach Anspruch 19 oder 20, bei der das nukleophile Reagens ein Amin umfaßt, das 2 bis 60 Kohlenstoffatome und 1 bis 12 Stickstoffatome pro Molekül enthält.
22. Zusammensetzung nach Anspruch 19 oder 20, bei der das Amin ein Polyalkylenpolyamin umfaßt, bei dem die Alkylengruppe 2 bis 60 Kohlenstoffatome, vorzugsweise 2 bis 40 Kohlenstoffatome enthält, wobei das Polyalkylenpolyamin 2 bis 9 Stickstoffatome pro Molekül und vorzugsweise 5 bis 9 Stickstoffatome pro Molekül enthält.
23. Zusammensetzung nach Ansprüche 22, bei der das Amin Polyethylenpolyamin umfaßt.
24. Zusammensetzung nach Anspruch 19 oder 20, bei der das nukleophile Reagens ein Amidoamin oder ein Thioamidoamin umfaßt, das dadurch gekennzeichnet ist, daß es ein Reaktionsprodukt von mindestens einem Polyamin und einer α,β -ungesättigten Verbindung Formel:



- ist, in der X Schwefel oder Sauerstoff ist, Y -OR⁴, -SR⁴ oder -NR⁴ (R⁵) ist und R¹, R², R³, R⁴ und R⁵ gleich oder verschieden und Wasserstoff, substituierter Kohlenwasserstoff oder unsubstituierter Kohlenwasserstoff sind.
25. Zusammensetzung nach Anspruch 24, bei der das Polyamin wie in Anspruch 21 oder 22 definiert ist.
26. Zusammensetzung nach Anspruch 25, bei der das Polyamin Polyalkylenpolyamin umfaßt, wobei die Alkylengruppen 2 bis 6 Kohlenstoffatome enthalten und das Polyalkylenpolyamin 5 bis 9 Stickstoffatome pro Molekül enthält, und die α,β -ungesättigte Verbindung mindestens eine Verbindung ausgewählt aus der Gruppe bestehend aus Methylacrylat, Ethylacrylat, Propylacrylat, Butylacrylat, Methylmethacrylat, Ethylmethacrylat, Propylmethacrylat und Butylmethacrylat umfaßt.
27. Zusammensetzung nach Anspruch 26, bei der das Polyamin Polyethylenpolyamin oder Polypropylenamin umfaßt.



28. Zusammensetzung nach einem der Ansprüche 24 bis 27, bei der in der Reaktionsmischung 1 bis 5 Mol der säureproduzierenden Reste pro primärem Stickstoffäquivalent des Amidoamins vorhanden sind.
29. Zusammensetzung nach Anspruch 28, bei der das Polyamin im Durchschnitt mindestens zwei primäre Stickstoffatome pro Molekül enthält, die X-Gruppe Sauerstoff ist und das Polyamin in einer Menge von 3 bis 5 Äquivalenten des Polyamins (bezogen auf den primären Amingehalt) pro Mol der α,β -ungesättigten Verbindung kontaktiert wird.
30. Verfahren zur Herstellung von Additiven für ölige Zusammensetzungen, bei dem:
- (i) mit Ethylen/ α -Olefin substituiertes Mono- oder Dicarbonsäurematerial nach einem Verfahren gemäß einem der Ansprüche 14 bis 18 gebildet wird und
 - (ii) das in (i) gebildete mit Ethylen/ α -Olefin substituierte Mono- oder Dicarbonsäurematerial mit einem nukleophilen Reagens umgesetzt wird.
31. Verfahren nach Anspruch 30, bei dem das nukleophile Reagens wie in einem der Ansprüche 19 und 21 bis 29 definiert ist.
32. Öllösliche Zusammensetzung, die als multifunktionelles Viskositätsindexverbessereradditiv für ölige Zusammensetzungen brauchbar ist und das Reaktionsprodukt von:
- (a) Ethylen/ α -Olefin-Polymer, das mit Mono- oder Dicarbonsäure produzierenden Resten substituiert ist, das wie in einem der Ansprüche 1 bis 13 definiert oder nach dem Verfahren gemäß einem der Ansprüche 14 bis 18 erhältlich ist,
 - (b) mit Kohlenwasserstoff substituierte Carbonsäure produzierendem Material, das 1 bis 2 Carbonsäuregruppen oder Carbonsäureanhydridgruppen enthält, wobei der Kohlenwasserstoff eine durchschnittliche Zahl von Kohlenstoffatomen von 12 bis 400 enthält, und
 - (c) mindestens einem nukleophilen Reagens ausgewählt aus der Gruppe bestehend aus Aminen, Alkoholen, Metallreaktanten und Mischungen derselben umfaßt.
33. Zusammensetzung nach Anspruch 32, bei der in (b) der Kohlenwasserstoff im Durchschnitt 50 bis 400 Kohlenstoffatome enthält.
34. Zusammensetzung nach Anspruch 32 oder Anspruch 33, bei der (b) ausgewählt ist aus der Gruppe bestehend aus mit Kohlenwasserstoff substituiertem Bernsteinsäureanhydrid, mit Kohlenwasserstoff substituiertes Bernsteinsäure und Mischungen derselben.
35. Zusammensetzung nach Anspruch 34, bei der der Kohlenwasserstoff ausgewählt ist aus Polybutylen, Polyisobutylen und Mischungen derselben.
36. Zusammensetzung nach einem der Ansprüche 32 bis 35, bei der das nukleophile Reagens (c) wie in einem der Ansprüche 21 bis 29 definiert ist.
37. Verwendung einer Zusammensetzung gemäß einem der Ansprüche 1 bis 13, 19 bis 29 und 32 bis 36 als multifunktionaler Viskositätsindexverbesserer.
38. Schmierölkonzentrat, das 1 bis 80 Gew.-%, vorzugsweise 20 bis 60 Gew.-% der öllöslichen Zusammensetzung gemäß einem der Ansprüche 1 bis 13, 19 bis 29 und 32 bis 36 enthält.
39. Schmierölszusammensetzung, die eine viskositätsindexverbessernde Menge der öllöslichen Zusammensetzung gemäß einem der Ansprüche 1 bis 13, 19 bis 29 und 32 bis 36 enthält.
40. Schmierölszusammensetzung nach Anspruch 39, die 0,01 bis 20 Gew.-%, vorzugsweise 0,1 bis 10 Gew.-% dieser öllöslichen Zusammensetzung enthält.

Revendications

1. Composition, utile comme additif pour une composition d'huile, qui comprend un polymère éthylène- α -oléfine substitué avec au moins un groupement choisi entre des groupements produisant des acides monocarboxyliques mono-insaturés en C_3 à C_{10} et des groupements produisant des acides



- dicarboxyliques mono-insaturés en C_4 à C_{10} , ledit polymère comprenant des motifs monomériques dérivés de l'éthylène et d'au moins une alpha-oléfine de formule $H_2C=CHR^1$ dans laquelle R^1 représente un groupe alkyle ayant 1 à 18 atomes de carbone, dans laquelle ledit polymère possède une moyenne numérique du poids moléculaire de plus de 20 000 à 500 000, et dans laquelle une
- 5 moyenne d'au moins 30 % des chaînes dudit polymère contient une insaturation éthénylidène terminale.
2. Composition suivant la revendication 1, dans laquelle le polymère possède une moyenne numérique du poids moléculaire de 35 000 à 50 000.
 - 10 3. Composition suivant la revendication 1 ou la revendication 2, dans laquelle le polymère possède une teneur molaire en éthylène de 45 à 65 %.
 - 15 4. Composition suivant l'une quelconque des revendications 1 à 3, dans laquelle R^1 représente un groupe alkyle ayant 1 ou 2 atomes de carbone, et dans laquelle une moyenne d'au moins 60 % des chaînes du polymère contient une insaturation éthénylidène terminale.
 - 20 5. Composition suivant l'une quelconque des revendications 1 à 4, dans laquelle le polymère comprend un copolymère éthylène-propylène.
 - 25 6. Composition suivant l'une quelconque des revendications 1 à 5, dans laquelle le polymère est pratiquement dépourvu d'halogène.
 - 30 7. Composition suivant l'une quelconque des revendications 1 à 6, dans laquelle le groupement produisant un acide carboxylique mono-insaturé est dérivé d'au moins un corps réactionnel carboxylique mono-insaturé choisi dans le groupe consistant en (i) des acides dicarboxyliques mono-insaturés en C_4 à C_{10} dans lesquels (a) les groupes carboxyle sont fixés à des atomes de carbone adjacents et (b) au moins un desdits atomes de carbone adjacents fait partie de ladite mono-insaturation ; (ii) des anhydrides ou dérivés consistant en mono- ou diesters d'un alcool en C_1 à C_5 et des acides (i) ; (iii) des acides monocarboxyliques mono-insaturés en C_3 à C_{10} dans lesquels la double liaison carbone-carbone est allylique par rapport au groupe carboxy ; et (iv) des dérivés consistant en mono- ou diesters d'un alcool en C_1 à C_5 et des acides (iii).
 - 35 8. Composition suivant la revendication 7, dans laquelle le corps réactionnel carboxylique mono-insaturé comprend au moins un acide choisi dans le groupe consistant en l'acide fumarique, l'acide itaconique, l'acide maléique, l'anhydride maléique, l'acide chloromaléique, l'anhydride chloromaléique, l'acide acrylique, l'acide méthacrylique, l'acide crotonique, l'acide cinnamique et des esters alkylés inférieurs des acides précités.
 - 40 9. Composition suivant l'une quelconque des revendications 1 à 8, dans laquelle le polymère substitué possède une fonctionnalité d'au moins 0,8.
 - 45 10. Composition suivant la revendication 9, dans laquelle le polymère substitué possède une fonctionnalité de 0,5 à 2,8.
 - 50 11. Composition suivant l'une quelconque des revendications 1 à 10, dans laquelle le polymère substitué contient moins de 25 ppm en poids de chlore.
 12. Composition suivant la revendication 11, dans laquelle le polymère substitué contient moins de 10 ppm en poids de chlore.
 13. Composition suivant l'une quelconque des revendications 1 à 12, qui contient moins de 40 % en poids du polymère éthylène-alpha-oléfine non substitué avec lesdits groupements engendrant un acide.
 - 55 14. Procédé de production d'une composition utile comme additif pour des compositions d'huiles, qui comprend la mise en contact :
 - (a) d'un polymère éthylène-alpha-oléfine comprenant des motifs monomériques dérivés de l'éthylène et d'au moins une alpha-oléfine de formule $H_2C=CHR^1$ dans laquelle R^1 représente un groupe



alkyle ayant 1 à 18 atomes de carbone, ledit polymère ayant une moyenne numérique du poids moléculaire de plus de 20 000 à 500 000, une moyenne d'au moins 30 % des chaînes du polymère contenant une insaturation éthénylidène terminale, avec

(b) au moins un corps réactionnel carboxylique mono-insaturé choisi dans le groupe consistant en (i) des acides dicarboxyliques en C₄ à C₁₀ mono-insaturés dans lesquels (a) les groupes carboxyle sont fixés à des atomes de carbone adjacents et (b) au moins un desdits atomes de carbone adjacents fait partie de ladite mono-insaturation ; (ii) des anhydrides ou dérivés consistant en mono- ou diesters d'un alcool en C₁ à C₅ et des acides (i) ; (iii) des acides monocarboxyliques mono-insaturés en C₃ à C₁₀ dans lesquels la double liaison carbone-carbone est allylique par rapport au groupe carboxy ; et (iv) des dérivés consistant en mono- ou diesters d'un alcool en C₁ à C₅ et des acides (iii), dans des conditions et pendant un temps suffisants pour former un produit contenant un polymère éthylène-alpha-oléfine substitué avec lesdits groupements acide carboxylique.

15. Procédé suivant la revendication 14, dans lequel la mise en contact est effectuée à une température d'environ 120 à 260 °C.

16. Procédé suivant la revendication 14 ou la revendication 15, dans lequel la mise en contact est effectuée pendant un temps d'environ 1 à 20 heures.

17. Procédé suivant l'une quelconque des revendications 14 à 16, dans lequel le polymère éthylène-alpha-oléfine et le corps réactionnel carboxylique mono-insaturé d'au moins un type sont mis en contact en présence d'un solvant ou diluant pour huile lubrifiante.

18. Procédé suivant l'une quelconque des revendications 14 à 17, dans lequel le polymère est caractérisé par une polydispersité de 1,2 à 3,0.

19. Composition soluble dans l'huile, utile comme additif multifonctionnel d'amélioration d'indice de viscosité pour une composition d'huile, comprenant le produit d'addition :

(a) d'un polymère éthylène-alpha-oléfine substitué avec des groupements produisant des acides mono- ou dicarboxyliques répondant à la définition suivant l'une quelconque des revendications 1 à 13 ou le produit suivant l'une quelconque des revendications 14 à 18, et
(b) d'au moins un corps réactionnel nucléophile choisi entre des amines, des alcools, des corps réactionnels métalliques et leurs mélanges.


20. Composition suivant la revendication 19, dans laquelle les groupements produisant des acides comprennent l'anhydride succinique, l'acide succinique ou l'acide propionique.

21. Composition suivant la revendication 19 ou 20, dans laquelle le réactif nucléophile comprend une amine contenant 2 à 60 atomes de carbone et 1 à 12 atomes d'azote par molécule.

22. Composition suivant la revendication 19 ou 20, dans laquelle l'amine comprend une polyalkylènepolyamine dans laquelle le groupe alkylène contient 2 à 60 atomes de carbone, de préférence 2 à 40 atomes de carbone, ladite polyalkylènepolyamine contenant 2 à 9 atomes d'azote par molécule, de préférence 5 à 9 atomes d'azote par molécule.

23. Composition suivant la revendication 22, dans laquelle l'amine comprend la polyéthylènepolyamine.

24. Composition suivant la revendication 19 ou 20, dans laquelle le corps réactionnel nucléophile comprend une amido-amine ou une thioamido-amine caractérisée en ce qu'elle consiste en un produit de réaction d'au moins une polyamine et d'un composé alpha, bêta-insaturé de formule :



dans laquelle X représente le soufre ou l'oxygène, Y représente un groupe -OR⁴, -SR⁴ ou -NR⁴(R⁵), et



R¹, R², R³, R⁴ et R⁵ sont identiques ou différents et représentent l'hydrogène ou des groupes hydrocarbyle substitués ou non substitués.

25. Composition suivant la revendication 24, dans laquelle la polyamine répond à la définition suivant la revendication 21 ou 22.
26. Composition suivant la revendication 25, dans laquelle la polyamine comprend une polyalkylènepolyamine dans laquelle les groupes alkylène contiennent 2 à 6 atomes de carbone, ladite polyalkylènepolyamine contenant 5 à 9 atomes d'azote par molécule, et le composé alpha, bêta-insaturé comprend au moins un membre du groupe consistant en l'acrylate de méthyle, l'acrylate d'éthyle, l'acrylate de propyle, l'acrylate de butyle, le méthacrylate de méthyle, le méthacrylate d'éthyle, le méthacrylate de propyle et le méthacrylate de butyle.
27. Composition suivant la revendication 26, dans laquelle la polyamine comprend la polyéthylènepolyamine ou la polypropylène-amine.
28. Composition suivant l'une quelconque des revendications 24 à 27, dans laquelle une quantité de 1 à 5 moles des groupements produisant un acide par équivalent d'azote primaire de ladite amino-amine est présente dans le mélange réactionnel.
29. Composition suivant la revendication 28, dans laquelle la polyamine contient une moyenne d'au moins 2 atomes d'azote primaires par molécule, le groupe X est l'oxygène et la polyamine est mise en contact en une quantité de 3 à 5 équivalents de ladite polyamine (sur la base de ladite teneur en amine primaire) par mole du composé alpha, bêta-insaturé.
30. Procédé de production d'un additif pour composition d'huile, qui comprend :
 - (i) la formation d'une matière du type acide mono- ou dicarboxylique substitué avec un polymère éthylène-alpha-oléfine par un procédé suivant l'une quelconque des revendications 14 à 18, et
 - (ii) la réaction de ladite matière du type acide mono- ou dicarboxylique substitué avec un polymère éthylène-alpha-oléfine de l'étape (i) avec un corps réactionnel nucléophile.
31. Procédé suivant la revendication 30, dans lequel le réactif nucléophile répond à la définition suivant l'une quelconque des revendications 19 et 21 à 29.
32. Composition, soluble dans l'huile, utile comme additif multifonctionnel d'amélioration d'indice de viscosité pour une composition d'huile, comprenant le produit de réaction :
 - (a) d'un polymère éthylène-alpha-oléfine substitué avec des groupements produisant des acides mono- ou dicarboxyliques suivant la définition figurant dans l'une quelconque des revendications 1 à 13 ou pouvant être obtenu par le procédé suivant l'une quelconque des revendications 14 à 18, et
 - (b) d'une matière produisant un acide carboxylique à substituant hydrocarbyle, contenant un ou deux groupes acide carboxylique ou groupes anhydride, dans laquelle ledit substituant hydrocarbyle contient un nombre moyen d'atomes de carbone de 12 à 400 ; et
 - (c) d'au moins un corps réactionnel nucléophile choisi dans le groupe consistant en amines, alcools, corps réactionnels métalliques et leurs mélanges.
33. Composition suivant la revendication 32, dans laquelle, dans l'étape (a), le substituant hydrocarbyle contient un nombre moyen de 50 à 400 atomes de carbone.
34. Composition suivant la revendication 32 ou la revendication 33, dans laquelle la matière de l'étape (b) est choisie dans le groupe consistant en un anhydride succinique à substituant hydrocarbyle, un acide succinique à substituant hydrocarbyle et leurs mélanges.
35. Composition suivant la revendication 34, dans laquelle le substituant hydrocarbyle est choisi entre le polybutylène, le polyisobutylène et leurs mélanges.
36. Composition suivant l'une quelconque des revendications 32 à 35, dans laquelle le corps réactionnel nucléophile (c) répond à la définition suivant l'une quelconque des revendications 21 à 29.



37. Utilisation d'une composition suivant l'une quelconque des revendications 1 à 13, 19 à 29 et 32 à 36 comme agent multifonctionnel d'amélioration d'indice de viscosité.

5 38. Concentré d'huile lubrifiante contenant 1 à 80 % en poids, de préférence 20 à 60 % en poids, de la composition soluble dans l'huile suivant l'une quelconque des revendications 1 à 13, 19 à 29 et 32 à 36.

10 39. Composition d'huile lubrifiante contenant une quantité, améliorant l'indice de viscosité, de la composition soluble dans l'huile suivant l'une quelconque des revendications 1 à 13, 19 à 29 et 32 à 36.

40. Composition d'huile lubrifiante suivant la revendication 39, contenant 0,01 à 20 % en poids, de préférence 0,1 à 10 % en poids de la composition soluble dans l'huile.

15

20

25

30

35

40

45

50

55

