

ABSTRACT

A glass substrate of the present invention has a glass composition in which specific content ranges of constituent components are satisfied, and in 5 mol%, the following condition: $\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{B}_2\text{O}_3$: 67 to 76% is satisfied, and the following ratios: $0.6 \leq \text{Li}_2\text{O}/(\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}) \leq 0.96$; and $0.78 \leq \text{MgO}/(\text{MgO} + \text{CaO} + \text{SrO} + \text{BaO} + \text{ZnO}) \leq 0.98$ are satisfied.