

ABSTRACT

Provided is a hardening accelerator for a hydraulic material, containing 20.0 to 80.0 mass% of calcium formate, 15.0 to 70.0 mass% of an inorganic calcium compound, and 0.5 to 30.0 mass% of an inorganic sulfate excluding calcium sulfate.