

07 MAY 2002

- 33 -

ELECTROCONDUCTIVE RESIN COMPOSITION

ABSTRACT OF THE DISCLOSURE

An electroconductive resin composition comprising, to 100 parts of a styrenic resin (A), about 5 to 50 parts by weight of a conductant (B) and about 11 to 44 parts by weight of an impact modifier (C) is prepared. The impact modifier (C) may be a styrenic thermoplastic elastomer (C₁), an olefinic thermoplastic elastomer (C₂), a polyester-series thermoplastic elastomer (C₃) and the like. The conductant (B) may be an electroconductive carbon black.

10 The resin composition is excellent in antistatic properties and has a surface resistivity of $1 \times 10^{11} \Omega/\square$ or less. A sheet or formed article made from the resin composition is suitable for use as a container or a packaging material for containing or carrying an electric component.



G00002



162162