




FLUORENYL-CONTAINING METALLOCENES FOR USE IN OLEFIN POLYMERIZATION

This invention relates to organometallic compounds. More specifically, this invention relates to organometallic compounds containing at least one benzofluorenyl ligand. In another aspect, this invention relates to polymerization catalyst systems which contain organometallic benzofluorenyl compounds. In still another aspect, this invention relates to a method for polymerizing olefins using such organometallic benzofluorenyl compounds and to the polymers resulting from such polymerizations.

Since the discovery of ferrocene in 1951, a number of metallocenes have been prepared by the combination of compounds having cyclopentadienyl structure with various transition metals. The term "cyclopentadienyl structure" as used herein refers to the following structure.



The term "cyclopentadiene-type compounds" as used herein refers to compounds containing the cyclopentadiene structure. Examples include unsubstituted cyclopentadiene, unsubstituted indene, unsubstituted fluorene, and substituted varieties of such compounds. Also included is tetrahydroindene.

CASE: 33271



- 2 -

Thus polycyclic cyclopentadiene compounds are included within the term.

Many cyclopentadiene-type metallocenes have been found useful in catalyst systems for the polymerization of olefins. It has been noted in the art that variations in the chemical structure of such cyclopentadienyl-type metallocenes can have significant effects upon the suitability of the metellocene as a polymerization catalyst. For example, the size of and substitutions on cyclopentadienyl-type ligands has been found to affect the activity of the catalyst, the stereoselectivity of the catalyst, the stability of the catalyst, and other properties of the resulting polymer; however, the effects of various substituents is still largely an empirical matter, that is, experiments must be conducted in order to determine just what effect a particular variation will have upon a particular type of cyclopentadienyl-type metallocene. Some examples of some cyclopentadienyl-type metellocenes are disclosed in U.S. Patent Nos. 4,530,914; 4,808,561; and 4,892,851.

While there are references in the prior art which have envisioned metallocenes containing fluorenyl groups, only a very limited number of fluorenyl-containing metallocenes have actually been prepared prior to the present invention. The Journal of Organometallic Chemistry, Vol. 113, pages 331-339 (1976), the disclosure of which is incorporated herein by reference, discloses preparing bis-fluorenyl zirconium dichloride and bis-fluorenyl zirconium dimethyl. U.S. Patent 4,892,851 and the New Journal of Chemistry, Vol. 14, pages 499-503, dated 1990, each disclose preparing a metallocene from the ligand 1-(cyclopentadienyl)-1-(fluorenyl)-1, 1-dimethylmethylene. The New Journal of Chemistry article also discloses preparing a similar compound in which the cyclopentadienyl radical has a methyl



- 3 -

substituent in the number 3 position. The term fluorenyl as used herein refers to 9-fluorenyl unless indicated otherwise.

The present invention provides certain new
5 benzofluorenyl-containing metallocenes. The invention also provides a method for preparing new benzofluorenyl-type metallocenes. The invention further provides polymerization catalysts employing benzofluorenyl-type metallocenes, processes for
10 polymerizing olefins using benzofluorenyl-type metallocene catalyst systems, and polymers produced using such benzofluorenyl-containing metallocene catalysts.

In accordance with the present invention,
15 there are provided new metallocenes of the formula $R''_x(FlR_n)(CpR_m)MeQ_k$ wherein Fl is a fluorenyl radical; Cp is a cyclopentadienyl, indenyl, tetrahydro indenyl, or fluorenyl radical; each R is the same or different and is a halide or an organo radical having 1 to 20
20 carbon atoms; R'' is a structural bridge linking (FlR_n) and (CpR_m) ; Me is metal selected from the group consisting of IVB, VB, and VIB metals of the Periodic Table; each Q is the same or different and is selected from the group consisting of hydrocarbyl or
25 hydrocarbyloxy radicals having 1 to 20 carbon atoms, hydrogen, and halogens, x is 1 or 0, k is a number sufficient to fill out the remaining valences of Me, n is a number in the range of 2 to 7, m is a number in the range of 0 to 7, further characterized by the fact
30 that in (FlR_n) two adjacent positions are substituted by four connected carbons to form a benzo substituent on the fluorenyl radical.

In accordance with the present invention there is provided a process for preparing the above
35 novel metallocenes which comprises reacting one mole of an alkali metal salt of a fluorenyl-containing compound of the formula FlR_nH and one mole of an alkali metal



- 4 -

salt of a cyclopentadienyl-containing compound of the formula CpR_mH or one mole of a dialkali metal salt of a bridged fluorenyl-containing compound of the formula $\text{R}''_x (\text{FlR}_n\text{H}) (\text{CpR}_m\text{H})$, with one mole of a transition metal compound of the formula MeQ_k , wherein Me, Q, k, Fl, Cp, R, m and n are the same as defined above except that x is only 1 when the bridged fluorenyl-containing compound is reacted.

In particular, there is provided a method for forming benzofluorenyl-containing metallocenes comprising reacting an alkali metal salt of the selected benzofluorenyl compound with a transition metal compound of the formula MeQ_k in the presence of a non-halogenated solvent for the benzofluorenyl salt which solvent is non-coordinating with respect to the transition metal compound.

In accordance with still another aspect of the present invention, there is provided a process for the polymerization of olefins comprising contacting said olefins under suitable reaction conditions with a catalyst system comprising a benzofluorenyl-containing metallocene as described above in combination with a suitable organoaluminum co-catalyst.

The present invention further provides the polymer products resulting from such polymerizations.

The novel metallocenes provided in accordance with the present invention fall into two broad general categories. One category involves metallocenes in which a benzofluorenyl radical, either substituted or unsubstituted, is bonded to another cyclopentadienyl-type radical by a bridging structure R'' and both the benzofluorenyl and the cyclopentadienyl radicals of that bridged ligand are bonded to the metal. These metallocenes are referred to herein as bridged metallocenes. The other category deals with metallocenes which are unbridged, that is the benzofluorenyl-containing ligand, either substituted or



unsubstituted, and the other cyclopentadienyl-type ligands that are bound to the metal are not bound to each other. These metallocenes are referred to as unbridged metallocenes.

5 The metal, Me is selected from the group IV, VB, or VIB metals of the Periodic Table. The currently preferred metals include titanium, zirconium, hafnium, chromium, and vanadium. The R" can be selected from any suitable bridging structure. Typical examples
10 include hydrocarbyl or heteroatom containing alkylene radicals containing 1 to 20 carbon atoms, especially 2 to 20 carbon atoms; germanium; silicon; phosphorus; boron; aluminum; tin; oxygen; nitrogen; and the like. The bridge can even be a cyclic hydrocarbyl structure.
15 Some examples include cyclopentylidene, adamantylidene, cyclohexenylidene, cyclohexylidene, indenylidene, and the like. The R" bridge when hydrocarbyl can be aromatic in nature, such as a phenyl-substituted alkylene. The currently most preferred bridges are
20 hydrocarbyl or heteroatom containing alkylene radicals having 1 to 20 carbon atoms. In an especially preferred embodiment k is equal to the valence of Me minus 2.

 The substituents R can be selected from a
25 wide range of substituents. In the preferred embodiments the substituents R are each independently selected from halides or hydrocarbyl radicals having 1 to 20 carbon atoms. In a particularly preferred
embodiment, the hydrocarbyl radicals R are alkyl, aryl, or arylalkyl radicals. More preferably the alkyl R
30 radicals have 1 to 5 carbon atoms. As noted above n is at least 2 so that at least two adjacent positions on F1 are connected by four carbons so that there is at least one benzo substituent at the 1,2; 2,3; 3,4; 5,6;
35 6,7; or 7,8 position of F1. It is also within the scope of the present invention for (F1R_n) to have more than one benzo group and for the benzo group or the



- 6 -

benzofluorenyl group to be substituted. The substituents on the benzo group can be the same as R, as defined above, but alkyl, aryl, and alkoxy substituents are particularly preferred.

5 Each Q is a hydrocarbyl radical such as, for example, aryl, alkyl, alkenyl, alkaryl, or arylalkyl radical having from 1 to 20 carbon atoms, hydrocarbyloxy radicals having 1 to 20 carbon atoms, hydrogen, or halogen. Exemplary Q hydrocarbyl radicals
10 include methyl, ethyl, propyl, butyl, amyl, isoamyl, hexyl, isobutyl, heptyl, octyl, nonyl, decyl, cetyl, 2-ethylhexyl, phenyl, and the like. Exemplary halogen atoms include chlorine, bromine, fluorine, and iodine, and of these halogen atoms, chlorine is currently the
15 most preferred. Exemplary hydrocarboxy radicals include methoxy, ethoxy, propoxy, butoxy, amyloxy, and the like.

 Illustrative, but non-limiting examples of unbridged metallocenes falling within the scope of the
20 above formula include bis(3,4-benzofluorenyl) zirconium dichloride, bis(1,2:7,8-dibenzofluorenyl) zirconium dimethyl, bis(2,3-benzofluorenyl) hafnium dichloride, bis(2,3:6,7-dibenzofluorenyl)zirconium dichloride, bis(2,5-dimethyl-7H-benzo (c) fluorenyl) zirconium
25 dichloride, bis(6-isopropyl-11H-benzo (b) fluorenyl) zirconium dichloride, bis(2,3-benzofluorenyl)hafnium dichloride, (cyclopentadienyl)(3,4-benzofluorenyl) zirconium dichloride, (cyclopentadienyl) (2,3:6,7-dibenzofluorenyl)zirconium dichloride, (pentamethyl
30 cyclopentadienyl) (2,3:6,7-dibenzofluorenyl) zirconium dichloride; bis(1-(cyclopentadienyl)-1,1-(dimethyl)-1-(3,4-benzofluorenyl) methane) zirconium dichloride, and the like.

 Illustrative, but non-limiting examples of
35 bridged metallocenes containing bridged benzofluorenyl ligands include for example 1-(cyclopentadienyl)-1-(3,4-benzofluorenyl)-1,1-(dimethyl)-methane zirconium



- 7 -

dichloride, 1,2-di(3,4-benzofluorenyl) ethane zirconium
 dichloride, 1,3-di(3,4-benzofluorenyl) propane
 zirconium dichloride, 1,2-di(2,3:6,7-
 dibenzofluorenyl)ethane hafnium dichloride, 1,3-di(2,3-
 5 benzofluorenyl) propane hafnium dichloride, 1-(3,4-
 benzofluorenyl)-2-(methyl)-2-(fluorenyl) ethane
 zirconium dichloride, dimethylsilyl di(2,3:6,7-
 dibenzofluorenyl) zirconium dichloride, dimethyl silyl
 (3,4:5,6-dibenzofluorenyl) (cyclopentadienyl) zirconium
 10 dichloride, 1,2-di(2,3-benzofluorenyl)ethane zirconium
 dichloride, 1,2-di(2,5-dimethyl-7H-benzofluorenyl)
 ethane hafnium dichloride, 1-(3,4-benzofluorenyl)-1-
 (cyclopentadienyl) methane zirconium dichloride, 1-
 (3,4-benzofluorenyl)-1-(cyclopentadienyl) methane
 15 hafnium dichloride, 1-(2,7-di-t-butylfluorenyl)-1-
 (2,3:6,7-dibenzofluorenyl) methane zirconium
 dichloride, 1-(3,4-benzofluorenyl)-2-(cyclopentadienyl)
 ethane zirconium dichloride, 1-(2,3:6,7-
 dibenzofluorenyl)-2-(3-methylcyclopentadienyl) ethane
 20 zirconium dichloride, 1(2,3 benzofluorenyl)-2-(indenyl)
 ethane zirconium dichloride, 1-(2,3-benzofluorenyl)-2-
 (indenyl) ethane hafnium dichloride, 1-(2,3-
 benzofluorenyl)-2-(methyl)-2-(indenyl) ethane zirconium
 dichloride, bis-(3,4-benzofluorenyl) methane vanadium
 25 dichloride, 1,2-di(3,4-benzofluorenyl) ethane vanadium
 dichloride, 1-(2,3-benzofluorenyl)-2-(methyl)-2-(3-
 methyl cyclopentadienyl) ethane zirconium dichloride,
 1-(2,3-benzofluorenyl)-2-(3,4-benzofluorenyl) ethane
 zirconium dichloride, (1-(2,7-di-t-butylfluorenyl)-2-
 30 (2,3:6,7-dibenzofluorenyl) ethane zirconium dichloride,
 1,2-di(2,3:6,7-dibenzofluorenyl) ethane zirconium
 dichloride, 1,2 di(3,4:5,6-dibenzofluorenyl) ethane
 zirconium dichloride, 1-(2,3-benzofluorenyl)-1-
 (cyclopentadienyl)-1,1-(dimethyl) methane zirconium
 35 dichloride, 1-(2,7-dimesitylfluorenyl)-1-(3,4-
 benzofluorenyl)-1,1-(dimethyl) methane zirconium
 dichloride, 1-(3,4-benzofluorenyl)-1-



- (cyclopentadienyl)-1,1-diphenylmethane zirconium dichloride, 1-(3,4:5,6-dibenzofluorenyl)-1-(cyclopentadienyl)-1,1-dimethyl methane zirconium dichloride, 1-(2,3-benzofluorenyl)-1-
- 5 (cyclopentadienyl) cyclopentane zirconium dichloride, 1-(3,4-benzofluorenyl)-1-(cyclopentadienyl) indanylidene zirconium dichloride, 1-(2,3-benzofluorenyl)-1-(cyclopentadienyl) cyclopentylidene zirconium dichloride, 1-(2,3-benzofluorenyl)-1-
- 10 (cyclopentadienyl) methane zirconium dichloride, 1-(1,2-benzofluorenyl)-1-(cyclopentadienyl)-1,1-dimethylmethane zirconium dichloride, and 1-(2,3:6, 7-dibenzofluorenyl)-1-(cyclopentadienyl)-1,1-diphenylmethane zirconium dichloride and the like.

- 15 A particularly preferred type of metallocene is a bridged metallocene containing at least one symmetrically substituted fluorenyl radical. The term symmetrically substituted as used herein refers to fluorenyl radicals having substituents on opposite
- 20 portions of the fluorenyl radical, such as for example 2,7-dialkylfluorenyl; 2,7-dicycloalkenylfluorenyl; 3,6-dialkylfluorenyl; 2,7-dihalo fluorenyl; 2,7-diarylfluorenyl; 1,8-dialkylfluorenyl; 4,5-dialkylfluorenyl; 2,7-diarylalkylfluorenyl; 2,3:6,7-
- 25 dibenzofluorenyl; 3,4:5,6-dibenzofluorenyl; and the like. Most preferably the substituents on the fluorenyl are the same. The currently preferred alkyl substituents have 1 to 20 carbon atoms, more preferably 1 to 6 carbon atoms, and most preferably 1 to 4 carbon
- 30 atoms. The currently most preferred halide substituents are chloride, iodide, and bromide. Examples of aryl substituents include those having 6 to 20 carbon atoms, with those having 6 to 10 carbon atoms generally more preferred. Likewise the arylalkyl
- 35 substituents can contain 7 to 20 carbon atoms, more commonly 7 to 10 carbon atoms. It should be recognized that in certain instances if the bridge and the



- 9 -

substituents on the (Fl_n) and/or (Cp_m) are particularly bulky it may be difficult to prepare the ligand, the dialkali metal salt, or the metallocene.

In accordance with a preferred embodiment of the invention, the metallocene consists essentially of (1-(3,4-benzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride, (1-(3,4-benzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride, (1-(2,3:6,7-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride, (1-(3,4:5,6-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride, or (1-(1,2:5,6-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride. By use of the term "consists essentially of" it is intended that the metallocene does not include any component which would have an adverse affect on the desired properties provided to the metallocene by the components recited after the expression.

The inventive metallocenes as well as related metallocenes can be prepared by reacting an alkali metal salt of the selected benzofluorenyl compounds with a suitable transition metal compound in a suitable solvent under suitable reaction conditions.

The bridged benzofluorenyl ligands can be prepared using procedures of the type taught in U.S. Patent No. 5,191,132 and the aforementioned U.S. Patent application Serial No. 08/064,630 and 07/984,054. Some methylene bridged benzofluorenyl ligands can be made by using 6 or 6,6 substituted fulvenes. Examples of fulvene reactions are disclosed in U.S. Patent No. 4,892,851 and in J. Organomet. Chem. 435, 299-310 (1992). In general the technique involves reacting an alkali metal salt of the selected benzofluorene compound with the selected fulvene type compound.



- 10 -

The 6,6-diphenyl fulvenes can be prepared by reacting a suitable aryl bromide, i.e. phenyl bromide, p-tolyl bromide, p-fluorophenyl bromide, or p-t-butylphenyl bromide, with magnesium to form a Grignard reagent. Then the dropwise addition of methyl formate and subsequent hydrolysis results in the formation of the diarylcarbinol. The diarylcarbinol can then be oxidized smoothly to give the corresponding substituted benzophenone, preferably using sulfuric acid and chromic acid. The resulting substituted benzophenone can then be reacted with cyclopentadiene in ethanol containing sodium ethoxide to yield the 6,6-substituted fulvene.

A variation of this technique involves the production of indanyl fulvene (which can also be called indanylidene fulvene) by reacting 1-indanone with cyclopentadiene in the presence of ethanol and sodium ethoxide. The indanyl fulvene is particularly useful in that it can be reacted with the alkali metal salt of a fluorene compound, i.e. a benzofluorene, to yield an indanyl bridged fluorenyl cyclopentadienyl compound. An example would be 1-(3,4 benzofluorenyl)-1-(cyclopentadienyl) indanylidene.

The benzofluorenyl compounds needed to make the ligands can be prepared using procedures generally known in the prior art. See for example U.S. Patent No. 3,615,412. Some particularly desirable techniques for forming certain of the benzofluorenyl compounds will be described in further detail in what follows.

The term transition metal compound as used herein includes compounds of the formula MeQ_k wherein Me, Q, and k are as defined above. Some non-limiting examples include zirconium tetrachloride, hafnium tetrachloride, titanium tetrachloride, cyclopentadienyl zirconium trichloride, fluorenyl cyclopentadienyl zirconium dichloride, 3-methylcyclopentadienyl zirconium trichloride, indenyl cyclopentadienyl



- 11 -


zirconium dichloride, 4-methyl fluorenyl zirconium trichloride, pentamethylcyclopentadienyl zirconium trichloride, and the like.

Inventive metallocenes in which Q is

- 5 hydrocarbyl or hydrocarbyloxy can be readily prepared by reacting the halide form of the metallocene with an alkali metal salt of the hydrocarbyl or hydrocarbyloxy radical under conditions as have been used in the past for forming such ligands in prior art metallocenes.
- 10 See, for example, the aforementioned J. Organomet. Chem. 113, 331-339 (1976). Another approach involves reacting a compound of the formula MeQ_k wherein at least one Q is hydrocarbyl or hydrocarbyloxy with the alkali metal salt of the bridged or unbridged
- 15 benzofluorenyl compound.

- One embodiment of the present invention involves carrying out the reaction of the benzofluorenyl-containing salt and the transition metal compound in the presence of a liquid diluent which is
- 20 non-halogenated and non-coordinating toward the transition metal compound. Examples of such suitable liquid include hydrocarbons such as toluene, pentane, or hexane as well as non-cyclic ether compounds such as diethylether. It has been found that the use of such
- 25 non-halogenated non-coordinating solvents generally allows one to obtain large amounts of substantially pure metallocenes and in a more stable form; and also often allows the reaction to be conducted under higher temperature conditions, than when dichloromethane is
- 30 used as the diluent. In an especially preferred embodiment the benzofluorenyl-containing salt used as a ligand is also prepared in a liquid diluent that is non-halogenated and non-coordinating toward the transition metal.

- 35 The formation of the alkali metal salt of the bridged or unbridged benzofluorenyl compound can be formed using generally any technique known in the art.



- 12 -

For example, such can be prepared by reacting an alkali metal alkyl with the cyclopentadienyl type compounds or the bridged compounds having two cyclopentadienyl-type radicals per molecule. The molar ratio of the alkali metal alkyl to the cyclopentadienyl type radicals present can vary, generally however, the ratio would be in the range of about 0.5/1 to about 1.5/1, still more preferably about 1/1. Typically, the alkali metal of the alkali metal alkyl would be selected from sodium, potassium, and lithium, and the alkyl group would have 1 to 8 carbon atoms, more preferably 1 to 4 carbon atoms. Preferably, if the benzofluorenyl salt is formed using tetrahydrofuran (THF) as the liquid solvent, the salt is isolated and substantially all of the THF is removed before the salt is contacted with the transition metal halide.

The molar ratio of the bridged or unbridged benzofluorenyl alkali metal compound to the transition metal compound can vary over a wide range depending upon the results desired. Typically, however, when an unbridged benzofluorenyl alkali metal compound is used, the molar ratio of the unbridged benzofluorenyl compound to the transition metal compound is in the range of from about 1 to 1 to about 2 to 1 and when a bridged benzofluorenyl alkali metal compound is used the molar ratio of the bridged benzofluorenyl alkali metal compound to the transition metal compound is about 1 to 1 when one desires a bridged metallocene and about 2 to 1 when one desires an unbridged metallocene.

The resulting metallocene can be recovered and purified using conventional techniques known in the art such as filtration, extraction, crystallization, and re-crystallization. It is generally desirable to recover the metallocene in a form that is free of any substantial amount of by-product impurities. Accordingly, recrystallization and fractional crystallization to obtain relatively pure metallocenes



- 13 -

is desirable. Dichloromethane has been found to be particularly useful for such recrystallizations. As a general rule, it has been found that the metallocenes based on unbridged fluorenyl compounds are less stable than the metallocene compounds formed from bridged fluorenyl compounds. Since the stability of the various metallocenes varies, it is generally desirable to use the metallocenes soon after their preparation or at least to store the metallocene under conditions favoring their stability. For example the metallocenes can generally be stored at low temperature, i.e. below 0°C. in the absence of oxygen or water.

The resulting benzofluorenyl-containing metallocenes can be used in combination with a suitable co-catalyst for the polymerization of olefins. In such processes the metallocene or the co-catalyst can be employed on a solid insoluble particulate support.

Examples of suitable co-catalysts include generally any of those organometallic co-catalysts which have in the past been employed in conjunction with transition metal-containing olefin polymerization catalysts. Some typical examples include organometallic compounds of metals of Groups IA, IIA, and IIIB of the Periodic Table. Examples of such compounds have included organometallic halide compounds, organometallic hydrides and even metal hydrides. Some specific examples include triethyl aluminum, tri-isobutyl aluminum, diethyl aluminum chloride, diethyl aluminum hydride, and the like. Other examples of known cocatalysts include the use of a stable non-coordinating counter anion technique such as disclosed in U.S. Patent 5,155,080, e.g. using triphenyl carbenium tetrakis(pentafluorophenyl)boronate. Another example would be the use of a mixture of trimethylaluminum and dimethylfluoroaluminum such as disclosed by Zambelli et al., Macromolecules, **22**, 2186 (1989). In such



- 14 -

processes the metallocene or the co-catalyst can be employed on a solid insoluble support.

The currently most preferred co-catalyst is an aluminoxane. Such compounds include those
5 oligomeric or polymeric compounds having repeating units of the formula



10 where R is an alkyl group generally having 1 to 5 carbon atoms. Aluminoxanes, also sometimes referred to as poly(hydrocarbyl aluminum oxides) are well known in the art and are generally prepared by reacting an organo aluminum compound with water. Such preparation
15 techniques are disclosed in U.S. 3,242,099 and 4,808,561. The currently preferred co-catalysts are prepared either from trimethylaluminum or triethylaluminum, sometimes referred to as poly(methyl aluminum oxide) and poly(ethyl aluminum oxide),
20 respectively. It is also within the scope of the invention to use an aluminoxane in combination with a trialkylaluminum, such as disclosed in U.S. Patent No. 4,794,096.

The fluorenyl-containing metallocenes in
25 combination with the aluminoxane co-catalyst can be used to polymerize olefins. Generally such polymerizations would be carried out in a homogeneous system in which the catalyst and co-catalyst were soluble; however, it is within the scope of the present
30 invention to carry out the polymerizations in the presence of supported forms of the catalyst and/or co-catalyst in a slurry or gas phase polymerization. It is within the scope of the invention to use a mixture of two or more fluorenyl-containing metallocenes or a
35 mixture of an inventive fluorenyl-containing metallocene with one or more other cyclopentadienyl-type metallocenes.

The fluorenyl-containing metallocenes when



- 15 -

used with aluminoxane are particularly useful for the polymerization of mono-unsaturated aliphatic alpha-olefins having 2 to 10 carbon atoms. Examples of such olefins include ethylene, propylene, butene-1, pentene-1, 3-methylbutene-1, hexene-1, 4-methylpentene-1, 3-ethylbutene-1, heptene-1, octene-1, decene-1, 4,4-dimethyl-1-pentene, 4,4-diethyl-1-hexene, 3,4-dimethyl-1-hexene, and the like and mixtures thereof. The catalysts are particularly useful for preparing copolymers of ethylene or propylene and generally a minor amount, i.e. about 20 to 10 mole percent, more commonly about 12 mole percent, still more typically less than about 10 mole percent, of a higher molecular weight olefin.

The polymerizations can be carried out under a wide range of conditions depending upon the particular metallocene employed, and the results desired. Examples of typical conditions under which the metallocenes can be used in the polymerization of olefins include conditions such as disclosed in U.S. Patents 3,242,099; 4,892,851; and 4,530,914. It is considered that generally any of the polymerization procedures used in the prior art with any transition metal-based catalyst systems can be employed with the present fluorenyl-containing metallocenes.

Generally the molar ratio of the aluminum in the aluminoxane to the transition metal in the metallocene would be in the range of about 0.1:1 to about 10^5 :1 and more preferably about 5:1 to about 10^4 :1. As a general rule, the polymerizations would be carried out in the presence of liquid diluents which do not have an adverse affect upon the catalyst system. Examples of such liquid diluents include propane, butane, isobutane, pentane, hexane, heptane, octane, cyclohexane, methylcyclohexane, toluene, xylene, and the like. The polymerization temperature can vary over a wide range, temperatures typically would be in the



- 16 -

range of about -60°C. to about 280°C., more preferably in the range of about 20°C. to about 160°C. Typically the pressure would be in the range of from about 1 to about 500 atmospheres or greater.

5 The polymers produced with this invention have a wide range of uses that will be apparent to those skilled in the art from the physical properties of the respective polymer.

10 A further understanding of the present invention, its various aspects, objects and advantages will be provided by the following examples.

15 In the following examples where information is given about the microstructure of polymers as determined by ¹³CNMR, the spectra were taken using standard accepted spectroscopy techniques. The polymer was dissolved in trichlorobenzene and the spectra was taken with respect to an internal standard relative to hexamethylsiloxane which has a known reference point relative to tetramethyl silane. From the observed
20 integrals of the relevant peaks, the details regarding the microstructure are calculated.

$$\text{Meso Content} = (\text{mm}) + 1/2 (\text{mr})$$

$$\text{Racemic Content} = (\text{rr}) + 1/2 (\text{mr})$$

$$\text{Isotacticity} = \% (\text{mm})$$

25 Heterotacticity = $\% (\text{mr})$

$$\text{Syndiotacticity} = \% (\text{rr})$$

$$\text{Randomness Index} = \frac{(\text{mr})100}{2(\text{m})(\text{r})}$$

30 Average Isotactic Block Length = $1 + \frac{2(\text{mm})}{(\text{mr})}$

$$\text{Average Syndiotactic Block Length} = 1 + \frac{2(\text{rr})}{(\text{mr})}$$

For more detail regarding the determination of these values, reference can be made to Chapter 3 of the
35 "Chain Structure and Conformation of Macromolecules" by Frank A. Bovey (Academic Press, 1982).



- 17 -

ExamplesExample ISynthesis of 3,4-benzofluorene

A. Grignard solution was prepared in a two liter two-necked flask from 13.6 g of magnesium powder, 1,000 ml of diethylether, and 123 g of distilled 1-bromo-2-methylnaphthalene. Then 0.5 g of $\text{Ni}(\text{TPP})_2\text{Cl}_2$ was added and 114 g of iodobenzene was added dropwise with stirring. The light brown suspension became hot and was heated for a further 10 hours under reflux. The resulting reaction product was hydrolyzed and then extracted with ether, dried and freed from the solvent. By vacuum distillation, an orange liquid was obtained which was determined to be 2-methyl-1-phenylnaphthalene.

Then 97.8 g of that product was combined with 81.9 g of N-bromosuccinimide and 4.2 g of α,α -azo bis isobutyronitrile in 300 ml of carbon tetrachloride and then heated under reflux for 8 hours. The resulting product is filtered off from the succinimide. Then after the solvent is removed in a vacuum, a pale yellow solid was obtained which was determined to be 2-bromomethyl-1-phenylnaphthalene.

Then 15.3 g of the 2-bromomethyl-1-phenylnaphthalene was heated with 23 g of calcium carbonate in a mixture consisting of 250 ml of an equal volume mixture of water and dioxane for 10 hours under reflux. The reaction mixture was carefully poured into diluted hydrochloric acid and then extracted with ether and dried and freed of solvent. The resulting product, 2-hydroxymethyl-1-phenylnaphthalene, in an amount of about 0.45 mol was dissolved in 200 ml of acetone and added dropwise to a hot suspension of 207 g of KMnO_4 , 280 ml of water, and 1000 ml of acetone. During the dropwise addition, the mixture boiled and was then heated for suspension was poured into a large glass beaker containing 1000 ml of water to dissolve the



- 18 -

magnesium dioxide by the portion-wise addition of dilute HCl and Na_2SO_3 . The product 1-phenylnaphthalene-2-carboxylic acid was isolated by extraction with ether together with extraction of the organic phase with aqueous carbonate solution. This carboxylic acid product was then reacted with polyphosphoric acid. Specifically, 250 g of polyphosphoric acid was heated to 100-120°C. in a 1000 ml flask. Then 23.9 g of the 1-phenylnaphthalene-2-carboxylic acid was added in portions and the mixture allowed to stand for 1 hour at that temperature. The mixture was then allowed to cool and diluted to 750 ml by the careful addition of ice water. The sticky crude product was extracted with hot toluene and washed with warm aqueous sodium bicarbonate solution. The organic phase was dried and filtered over silica gel. In a cooling cabinet, dark red crystals of the benzo(c) fluorenone separated from the deep red solution.

9.8 grams of the benzo(c) fluorenone were dissolved in 200 ml of tetrahydrofuran and hydrogenated in the presence of 0.5 g of a palladium carbon catalyst containing 10 wt% palladium under atmospheric pressure and room temperature. The resulting product was dried over Na_2SO_4 , the solvent removed and the residue extracted with pentane and filtered over silica gel. Colorless platelettes of 3,4-benzofluorene, also sometimes referred to as benzo(c) fluorene, were recovered.

Example II

Preparation of 1,2-di-(9-(3,4-benzofluorenyl)) ethane and Metallocene

3 grams of 3,4-benzofluorene was dissolved in 100 ml of ether and reacted with 8.7 ml of a 1.6 molar hexane solution of n-butyllithium. Then 0.6 ml of 1,2-dibromoethane was added to the orange solution after 3 hours and then the mixture was stirred for four more hours. Then a little water was added to carry out



hydrolysis, the solid product was filtered off, washed with water, and then with ether and pentane and then recrystallized from toluene. A mixture of the rac/meso isomers of bis 1,2-(3,4-benzofluorenyl) ethane was
5 obtained.


The isomeric mixture of the 1,2-ethylene bridged-bis 3,4-benzofluorene ligand was dissolved in diethyl ether and stirred with two molar equivalents of n-butyllithium for at least 8 hours at room temperature
10 then one molar equivalent of zirconium tetrachloride was added. The mixture was stirred for several more hours. The complex was extracted with dichloromethane and filtered over Na_2SO_4 . A solid precipitates out at about -25°C . to yield an approximately equal mixture of
15 the rac- and meso-forms of the 1,2-bis-(3,4-benzofluorenyl) ethane zirconium dichloride.

Example III

Ethylene Polymerization

Ethylene homopolymerization was carried out
20 using the metallocene of Example II. The polymerization was conducted in a 1-liter autoclave using 0.04 mg of the 1,2-di-(9-(3,4-benzofluorenyl)) ethane zirconium dichloride in 300 ml of hexane with 1 ml of a 30 wt% toluene solution of methylaluminumoxane.
25 After this, an ethylene pressure of 10 bar was applied and the reaction mixture stirred for 1 hour at 60°C . The recovered polymer was dried using a vacuum. A yield of 27.3 g of polymer was obtained. This translates to an activity of 4.2×10^5 g of
30 polyethylene/mol zirconium-hour.

A comparable polymerization was carried out employing the metallocene, 1,2-bis(fluorenyl) ethane zirconium dichloride, and the activity was only 5×10^4 g polyethylene/mol Z-Hr. It is theorized that perhaps
35 the benzo substituents keep the aluminosane counter ion away from the active site without hindering the monomer from coordination and insertion.



- 20 -

Example IV1-(3,4-benzofluorenyl)-1,1-dimethyl-1-(cyclopentadienyl) methane zirconium dichloride

5 of 3,4-benzofluorene in 100 ml of ether and then a molar equivalent of n-butyllithium in hexane was slowly added. The liquid was then stirred for several hours at room temperature. Then a molar equivalent quantity of 6,6-dimethylfulvene was added and stirring was
10 continued at room temperature. Decoloration of the solution occurred quickly. Then approximately 1 molar equivalent of n-butyllithium was added in order to transform any possible excess fulvene into a readily soluble colorless derivative. The mixture was then
15 stirred for further 30 minutes and then hydrolyzed with a little water. The resulting dimethylmethylen-bridged ligand was then isolated and purified by dissolving in a solvent, filtering over silica gel and crystallization.

20 Then 1 g of the bridged benzofluorenyl ligand was added to 30 ml of diethylether and stirred with exactly 2 molar equivalents of n-butyllithium for about 8 hours at room temperature. After the liquid became well colored, 1 molar equivalent of zirconium
25 tetrachloride was added and the mixture was stirred for several more hours. The resulting metallocene was then recovered and purified.

Example V1-(3,4 benzofluorenyl)-1,1 diphenyl-1-(cyclopentadienyl) methane zirconium dichloride

30 1-(3,4 benzofluorenyl)-1,1-diphenyl-1-(cyclopentadienyl) methane was prepared using a procedure similar to that used in Example IV but starting with 6,6-diphenylfulvene. In this preparation
35 it was necessary to stir the reaction mixture overnight to obtain the desired degree of reaction.

The resulting diphenylmethane bridged



- 21 -

benzofluorenyl ligand was then reacted with zirconium tetrachloride in the same manner as used in Example IV.

Example VI

Propylene Polymerization

5 The dimethyl methane bridged benzofluorenyl metallocene of Example IV was evaluated for the polymerization of propylene. Polymerization grade propylene was condensed into a 1-liter autoclave reactor. It was stirred for 15-30 min with 10 ml of a
10 30 wt% methylaluminoxane solution at 20°C. and then cooled down to a temperature in the range of 0 to -2°C. A catalyst solution was prepared by combining the metallocene of Example IV with 1 ml of a 30 wt% solution of methylaluminoxane in toluene. The catalyst
15 solution was forced into the cool stirred autoclave using argon pressure. The temperature was then brought to 60°C. and maintained at that temperature for 120 min and then the polymerization was terminated by draining the unconsumed propylene. The polymerization
20 demonstrated an activity of 34.9×10^3 kg of polypropylene per mol Zr-hr. The polymer had a nominal molecular weight of 37.5×10^3 g/mol. This was determined using a precision capillary viscometer in decolin at 135°C. For the determination, calibration
25 curves were available for three different polymer concentrations. From carbon ^{13}NMR it was determined that the polymer had a racemic content of 93.7, i.e. it would be viewed as a syndiotactic polymer.

Example VII

30 Bulk polymerization of propylene using the diphenyl methane bridged benzofluorenyl metallocene of Example V was carried out using the same technique as described in Example VI. This polymerization
35 demonstrated an activity of 42.9×10^3 kilograms of polypropylene/mol Zr-hr. The nominal molecular weight was 330×10^3 grams/mol. The presence of the phenyl groups appears to be effective in increasing the



- 22 -

molecular weight of the polymer without causing any significant reduction in the activity of the catalyst.

Example VIII

Propylene polymerization using the
5 metallocene of Example II, i.e. the bis(benzofluorenyl)
ethylene bridged zirconium dichloride, was carried out
using conditions substantially the same as those used
in Examples VI and VII. The resulting polypropylene
had an isotacticity of 34.3%, a heterotacticity of
10 39.7%, and a syndiotacticity of 25.9% as determined by
carbon ¹³NMR. The polymer had a melt flow of 204. The
molecular weight as determined by size exclusion
chromatography was 39,000. The nominal molecular
weight was 5,000.

C L A I M S

1. A metallocene of the formula $R^m_x(FlR_n)(CpR_m)MeQ_k$ wherein Fl is a fluorenyl radical, Cp is a cyclopentadienyl, indenyl, tetrahydroindenyl, or fluorenyl radical, each R is the same or different and is a halide or an organo radical having 1 to 20 carbon atoms, R^m is a structural bridge linking (FlR_n) and (CpR_m) , Me is a Group IVB, VB, or VIB metal of the Periodic Table, each Q is the same or different and is a hydrocarbyl or hydrocarbyloxy radical having 1 to 20 carbon atoms, hydrogen, or halogen, x is 0 or 1, k is a number sufficient to fill out the remaining valences of Me, n is a number in the range of 2 to 7, m is a number in the range of 0 to 7, wherein in (FlR_n) two adjacent positions are substituted by four connected carbons to form at least one benzo substituent.
2. A metallocene according to claim 1, wherein (FlR_n) is a substituted or unsubstituted 2,3-benzofluorenyl; 3,4-benzofluorenyl; 1,2-benzofluorenyl; 1,2:5,6-dibenzofluorenyl; 2,3:6,7-dibenzofluorenyl; 3,4:5,6-dibenzofluorenyl, or a 1,2:7,8-dibenzofluorenyl radical.
3. A metallocene according to claim 1 or 2, wherein (CpR_m) and (FlR_n) are the same.
4. A metallocene according to claim 1 or 2, wherein (CpR_m) and (FlR_n) are structurally different.
5. A metallocene according to claim 4, wherein (CpR_m) is a cyclopentadienyl, an indenyl, or an unsubstituted fluorenyl radical.
6. A metallocene according to claim 5, wherein (CpR_m) is an unsubstituted cyclopentadienyl radical.
7. A metallocene according to any one of claims 1-5, wherein m is a number in the range of 1 to 4.
8. A metallocene according to any one of the preceding claims, wherein n is greater than 2.
9. A metallocene according to any one of the preceding claims, wherein Me is Ti, Zr, or Hf.
10. A metallocene according to claim 9, wherein Me

CASE: 33271



is zirconium or hafnium, k is 2, and Q is a halogen.


11. A metallocene according to any one of the preceding claims, wherein each Q is a halogen atom, or a C₁ to C₁₀ alkyl or aryl group.

12. A metallocene according to any one of the preceding claims, wherein x is 1.

13. A metallocene according to claim 12, which comprises (1-(3,4-benzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride; (1-(2,3:6,7-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride; (1-(3,4-benzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride; (1-(2,3-benzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride; (1-(1,2-benzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride; (1-(3,4-benzofluorenyl)-1-pentamethyl cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride; (1-(2,3:6,7-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride; (1-(2,3-benzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride; (1-(1,2-benzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride; (1-(3,4-benzofluorenyl)-1-(cyclopentadienyl)-1-(phenyl) methane) zirconium dichloride; 1-(2,5-dimethyl-7 H benzo(c)fluorenyl)-1-(cyclopentadienyl)-1,1-dimethyl methane) zirconium dichloride; 1-(1,2-benzofluorenyl)-1-(cyclopentadienyl)-1-(phenyl) methane) zirconium dichloride; 1-(3,4-benzofluorenyl)-1-(fluorenyl)-1-(dimethyl methane) zirconium dichloride; 1-(3,4-benzofluorenyl)-1-(indenyl)-1-(phenyl methane) zirconium dichloride; 1-(3,4-benzofluorenyl)-1-(cyclopentadienyl)-1-(methyl methane) zirconium dichloride; 1-(2,3:6,7-dibenzofluorenyl)-1-(cyclopentadienyl)cyclopentane) zirconium dichloride; (1-(3,4-benzofluorenyl)-2-(indenyl) ethane) zirconium dichloride; (1,2-di(3,4:5,6-dibenzofluorenyl) ethane) zirconium dichloride; (1,2-di(3,4-benzofluorenyl) ethane) zirconium dichloride; and (1-(3,4-benzofluorenyl)-2-(cyclopentadienyl)-ethane) zirconium dichloride.



14. A metallocene according to claim 12, wherein R" is a hydrocarbyl ethylene radical of the formula



wherein each R' is the same or different and is hydrogen or a hydrocarbyl radical wherein at least one R' is hydrocarbyl.

15. A metallocene according to claim 14, wherein R' is hydrogen.
16. A metallocene according to claim 12, wherein R" is a hydrocarbyl group containing 2 to 20 carbon atoms.
17. A metallocene according to claim 14, wherein R" is a hydrocarbyl group containing 4 to 20 carbon atoms.
18. A metallocene according to claim 16, wherein R" is the divalent methylene radical --CR'₂--, wherein each R' is the same or different and is a methyl, a phenyl, or a hydrogen radical, with the further proviso that at least one R' is hydrocarbyl.
19. A metallocene according to claim 18, which consists essentially of (1-(3,4-benzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride, (1-(3,4-benzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride, (1-(2,3:6,7-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride, (1-(3,4:5,6-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(diphenyl) methane) zirconium dichloride, or (1-(1,2:5,6-dibenzofluorenyl)-1-cyclopentadienyl-1,1-(dimethyl) methane) zirconium dichloride.
20. A process for preparing a metallocene according to any one of the preceding claims, which comprises reacting one mole of an alkali metal salt of a fluorenyl-containing compound of the formula FlR_nH and one mole of an alkali metal salt of a cyclopentadienyl-containing compound of the formula CpR_mH or one mole of a dialkali metal salt of a bridged fluorenyl-containing compound of the formula R"_x(FlR_nH)(CpR_mH), with one mole of a transition metal compound of the formula MeQ_k, wherein Me, Q, k, Fl, Cp, R, m





- 26 -

and n are the same as defined above except that x is only 1 when the bridged fluorenyl-containing compound is reacted.

21. A process for polymerizing an olefin which comprises contacting said olefin under suitable polymerization conditions with a catalyst system comprising a metallocene according to any one of claims 1-19 or when made by a process according to claim 20, and a suitable cocatalyst.

22. A process according to claim 21, wherein said cocatalyst comprises an alkylaluminumoxane.

23. A process according to claim 21 or 22, wherein said metallocene consists essentially of an rac/meso mixture of (1,2-di(3,4-benzofluorenyl) ethane) zirconium dichloride.



* C L N S *