

DECORATING CONTAINERS

The present invention relates to methods of decorating containers by dye diffusion transfer, such as those described and claimed in co-pending UK patent application No. 8121726, filed on 14 July 1981. In such methods, for example, in respect of cylindrical metal containers, a flexible carrier printed with indicia in a sublimible dye, is applied over a coating receptive to such a dye on the cylindrical surface of the container and the carrier held in intimate contact with the coating whilst the container and carrier are heated, so that at least some of the dye migrates by sublimation to the coating. The carrier is then removed from the container.

In particular, a flexible paper carrier is applied over the receptive coating and held in position either directly or indirectly by means of an adhesive, the container and carrier then being heated whilst the carrier is in position at such a temperature and for such a time that the carrier freely shrinks into intimate contact with the coating, and at least some of the dye sublimates so as to transfer the indicia to the coating.

An important consequence of the use of an adhesive to hold the paper carrier in contact with the receptive coating is that the required intimate contact between carrier and coating is achieved by converting into a useful feature what may otherwise be a disadvantage, namely, the fact that the paper shrinks due to loss of moisture as a result of being heated to effect the dye transfer process. This results in considerably improved contact between the carrier and the coated container surface, as compared with previously proposed arrangements where the

contact relies on the external application of pressure whilst heating to effect dye transfer.

5 In the present invention the applicants have found that the intimacy of contact between the paper carrier and the receptive coating on the container body is of considerable importance in determining the quality of the transferred indicia, i.e. the closer the contact between the carrier and the receptive coating the sharper the definition of the transferred image.

10 The applicants have also found, to their surprise, that very close contact between the paper carrier and the receptive coating can be achieved by (1) a careful selection of the properties of the carrier material and (2) the orientation of the carrier with respect to the container.

15 Thus, according to the present invention there is provided a method of decorating containers including the steps of:

20 (a) applying a flexible paper carrier, printed with indicia in a sublimible dye, over a coating receptive to such dye on a surface of the container, by means of an adhesive such as to be removable without damage to the coating, and

25 (b) heating the container whilst the carrier is held to it, at such a temperature and for such a time that the carrier freely shrinks into intimate contact with the coating and at least some of the dye sublimes so as to transfer the indicia to the coating,

30 in which the paper carrier has a weight of 35-110 grams per square metre, an equilibrium moisture content of 2-15% when exposed to air with a relative humidity of 50%, and is applied to the coating on the surface of the container so that the

35

direction of grain of the paper is parallel to the axis of symmetry passing through the centre of the base of the container.

5 According to the present invention there is further provided a flexible paper carrier, having a longitudinal edge portion carrying an adhesive layer and another portion printed with indicia in a sublimable dye, for application over a coating receptive to such dye on a surface of a container, by
10 means of the adhesive layer such as to be removable without damage to the coating, and thereafter transfer printing by heating the container whilst the carrier is held to it, at such a temperature and for such a time that the carrier freely shrinks into
15 intimate contact with the coating and at least some of the dye sublimates so as to transfer the indicia to the coating, the paper carrier having a weight of 35-110 grams per square metre, an equilibrium moisture content of 2-15% when exposed to air with a relative
20 humidity of 50%, and a grain direction extending parallel to said longitudinal edge.

The expression "direction of grain of the paper" refers to the direction of the paper in which there is primarily a greater degree of alignment of
25 constituent fibres. The direction of grain is related to the direction of travel of a paper-making machine, which results in a relatively high ratio of orientation of fibres in the direction of the machine compared with fibres in the cross machine direction.

30 Preferably, the weight of the paper carrier is 50-100 grams per square metre and its equivalent moisture content 4-10% when exposed to air with a relative humidity of 50%. (BS 3433:1961).

35 Desirably, the thickness of the paper carrier is from 30 - 100 μ m.

5 It has also been found that the ratio of the dry tearing strength of the paper carrier in the cross grain direction to that in the machine grain direction is important in selecting paper for use as carrier material, and advantageously the ratio should lie in the range of 1.2 - 2.0. Preferably, the ratio should be in the range of 1.35 - 1.6. Tearing strength may be measured using an Elmendorf Tear Tester (BS 4468:1969).

10 The surface roughness of the paper carrier is also relevant to the practice of the present invention, since the smoother the paper surface, the closer the contact between the carrier and the container surface. The property may be measured by
15 the Bendtsen paper roughness test (BS 4420:1969) and desirably should fall in the range of 20-500 ml of air per minute, preferably 30-150 ml of air per minute.

By selecting a paper carrier possessing the

13 properties identified above and applying it to the
receptive coating of a container in the manner
described, it has been found that the carrier shrinks
on heating into very close contact with the coating
5 resulting in the transfer of indicia without any
noticeable loss of clarity or sharpness.

The carrier is applied over the receptive
coating by means of an adhesive, either in the manner
of a 360° wrap around label with a narrow overlapping
10 strip to which the adhesive is applied (i.e. the
adhesive may be present solely between the
overlapping strips, or between the overlapping strips
and between the underlying strip and the receptive
coating), or where there is no overlap, by the
15 application of adhesive to the undersurface of the
carrier, preferably in the form of two or more
adhesive strips parallel to the direction of grain of
the paper. In the latter circumstance the carrier
may cover only a portion of the receptive coating.

20 An adhesive may be applied over a greater
surface area of the carrier, but there must be
sufficient residual freedom of movement of the
carrier for it to shrink into intimate contact with
the receptive coating without splitting or tearing.
25 Thus, the primary purpose of the adhesive is to hold
the carrier in position on the receptive coating of
the container and to restrain its overall movement on
shrinkage so that it contracts into intimate contact
with the receptive coating. Adhesive substances
30 suitable for this purpose are described in
application No. 8121726.

The deliberate application of the carrier
in the manner proposed with its grain direction
parallel to the axis of symmetry passing through the
35 centre of the base of the container is in clear
contra-distinction to the teachings of the related

container labelling art, as evinced by, for example, Krones Manual of Labelling Technology, edited by H Kronseder, of Machininenfabrik, 8402 Neutraubling, Federal Republic of Germany (a leading reference book in the art) at pages 18 and 131, where it is made clear that the correct way to mount paper labels on containers is with the direction of grain of the paper perpendicular to the axis of symmetry of the container.

In an example of the present invention, which is not to be considered as limiting the invention in any way, a method and apparatus as exemplified in application No. 8121726 were used, in which the carrier was derived from a calendered, uncoated paper having the following properties:-

weight:	60 g/ m ² ;
moisture content:	7.5% at RH 50%
thickness:	52 µm;
dry tearing strength:	177 mN in grain direction,
	277 mN in cross direction;
dry tearing strength ratio:	1.56
surface roughness	125 ml of air/minute.

Wrap around carriers with printed indicia and an overlapping adhesive strip were then applied to cylindrical metal containers having a suitable receptive coating (as described in application No 8121726) in each of two ways - (1) with the grain direction of the carrier perpendicular to the axis of symmetry of the container, and (2) with the grain direction of the carrier parallel to the axis of symmetry of the container.

On heating to transfer the indicia it was noticed in the case of (1) above that the carrier wrinkled-up and became creased in various places on shrinking on to the receptive coating, but that the

carrier remained perfectly flat in respect of (2).
The failure of the carrier in (1) to shrink uniformly
and remain flat manifest itself in the subsequent
appearance of the transferred indicia when the
5 carrier was removed. Thus, in (1) the indicia lacked
clarity and sharpness and appeared dulled as if
slightly out of focus, whereas by comparison, in (2)
the indicia appeared sharp and clear and was judged
to be of considerable aesthetic attractiveness.

10 Two further important differences between
the traditional container labelling art and the
present invention and which further serve to
distinguish the invention are (1) the non-permanence
of the dye transfer carrier, i.e. it is intended to
15 be present on the container for only a relatively
short time, possibly only a few seconds, and (2) the
exposure of the carrier after its application to the
container to heat, to cause it to shrink.

20 Although the present invention has, for
convenience, been described with respect to
decorating metal containers, the invention is clearly
in no way limited thereto, since it is the presence
of a receptive coating on the surface of a container
that is relevant and not the nature of the material
25 of the container itself. Thus, containers comprising
non-metallic materials such as glass or plastics (for
example polyesters or polycarbonates) are also
envisaged.

CLAIMS

1. A method of decorating containers including the steps of:

(a) applying a flexible paper carrier, printed with indicia in a sublimible dye, over a coating receptive to such dye on a surface of the container, by means of an adhesive such as to be removable without damage to the coating, and

(b) heating the container whilst the carrier is held to it, at such a temperature and for such a time that the carrier freely shrinks into intimate contact with the coating and at least some of the dye sublimes so as to transfer the indicia to the coating,

in which the paper carrier has a weight of 35-110 grams per square metre, an equilibrium moisture content of 2-15% when exposed to air with a relative humidity of 50%, and is applied to the coating on the surface of the container so that the direction of grain of the paper is parallel to the axis of symmetry passing through the centre of the base of the container.

2. A method according to Claim 1 in which the paper carrier has a weight of 50-100 grams per square metre.

3. A method according to Claim 1 or Claim 2 in which the paper carrier has an equilibrium moisture content of 4-10% when exposed to air with a relative humidity of 50%.

4. A method according to any one of Claims 1-3 in which the thickness of the paper carrier is from 30-100 μ m.

5. A method according to any one of Claims 1-4 in which the ratio of the dry tearing strength of the paper carrier in the cross grain direction to that in



-8-

the machine grain direction lies in the range of 1.2 - 2.0.

6. A method according to any one of the preceding claims in which the surface roughness of the paper carrier lies in the range of 20-500 ml of air per minute.

7. A method according to any one of the preceding claims in which the container comprises a cylindrical metal can.

8. A method of decorating containers substantially as hereinbefore described with reference to the Example of the invention.

9. A container when decorated by a method according to any one of the preceding claims.



10. A flexible paper carrier, having a longitudinal edge portion carrying an adhesive layer and another portion printed with indicia in a sublimable dye, for application over a coating
5 receptive to such dye on a surface of a container, by means of the adhesive layer such as to be removable without damage to the coating, and thereafter transfer printing by heating the container whilst the carrier is held to it, at such a temperature and for
10 such a time that the carrier freely shrinks into intimate contact with the coating and at least some of the dye sublimates so as to transfer the indicia to the coating, the paper carrier having a weight of 35-110 grams per square metre, an equilibrium moisture
15 content of 2-15% when exposed to air with a relative humidity of 50%, and a grain direction extending parallel to said longitudinal edge.
11. A carrier according to Claim 10 in which the paper carrier has a weight of 50-100 grams per
20 square metre.
12. A carrier according to any one of Claims 10 or to Claim 11 in which the paper carrier has an equilibrium moisture content of 4-10% when exposed to air with a relative humidity of 50%.
- 25 13. A carrier according to any one of Claims 10 to 12 in which the thickness of the paper carrier is from 30-100 μm .
14. A carrier according to any one of Claims 10 to 12 in which the ratio of the dry tearing strength
30 of the paper carrier in the cross grain direction to that in the machine grain direction lies in the range of 1.2 - 2.0.
15. A carrier according to any one of Claims 10 to 14 in which the surface roughness of the paper
35 carrier lies in the range of 20-500 ml of air per



minute.

16. A flexible carrier according to Claim 7 or 10 substantially as herein described with reference to the Example of the invention.
