

This Sheet Has Been Replaced



CATALYST

THIS INVENTION relates to a catalyst. It relates in particular to a catalyst and catalyst system for use in the polymerization of olefins, to a method of making such a catalyst, and to a method of polymerization.

5 According to a first aspect of the invention, there is provided a method of making a catalyst suitable for the polymerization of olefins, which method comprises:

mixing an ether having a total number of carbon atoms equal to or greater than 8, with magnesium chloride, to
10 produce partially activated magnesium chloride;

mixing an alkyl aluminium with the partially activated magnesium chloride to form unwashed activated magnesium chloride;

washing the activated magnesium chloride with an inert
15 saturated hydrocarbon liquid, to obtain an activated magnesium chloride-containing slurry;

mixing a plurality of alcohols with the activated magnesium chloride-containing slurry to form an activated magnesium chloride/alcohol complex; and

20 mixing titanium tetrachloride with the activated magnesium chloride/alcohol complex, to form a magnesium chloride supported titanium catalyst.

Thus, the catalyst obtained by this method is a specific titanium catalyst supported on specifically activated
25 magnesium chloride. The magnesium chloride is hence a catalyst support. The ether and alkyl-aluminium compound



mixing steps constitute magnesium chloride support activation steps, while the alcohols and titanium chloride (TiCl_4) mixing steps constitute catalyst loading steps.

As is known, magnesium chloride forms five hydrates, namely
5 $\text{MgCl}_2 \cdot 12\text{H}_2\text{O}$, $\text{MgCl}_2 \cdot 8\text{H}_2\text{O}$, $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, $\text{MgCl}_2 \cdot 4\text{H}_2\text{O}$ and
 $\text{MgCl}_2 \cdot 2\text{H}_2\text{O}$. The most important of these from an application
or general use point of view is the hexahydrated form,
 $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, which is the general raw material used for
obtaining, by known methods, $\text{MgCl}_2 \cdot 2\text{H}_2\text{O}$. It is also known
10 that olefin polymerization processes are influenced
detrimentally by even minute amounts of water present in
the reaction medium or in a Ziegler-Natta catalyst used in
such processes. Attempts to use, in olefin polymerization,
known Ziegler-Natta catalysts based on magnesium chloride
15 and containing even a very low proportion of water, have
resulted in a decrease in the productivity of olefin
polymerization beyond an efficient or practical
application. Consequently, substantial effort is normally
required to render the hydrated support material completely
20 dry. All these methods are laborious and expensive. In
many cases, a drying agent is employed, and some of the
drying agent remains as a complex in the resultant
catalyst, with undesired consequences on the catalyst
performance.

25 It was surprisingly found that, with catalysts made
according to the method of the present invention, limited
amounts of water in the magnesium chloride can not only be
tolerated, but are in fact desirable for imparting
particular properties to the catalyst. The inventors have
30 discovered, surprisingly, that a certain amount of water
present in the initial support, if combined using the
specific method of catalyst preparation herein described,
imparts excellent application properties to the final
catalyst. Thus, according to the invention, the magnesium



chloride may be partially anhydriized. In other words, the magnesium chloride may have a water content of between 0,02 mole of water/ 1 mole of $MgCl_2$ and 2 moles of water/ 1 mole of $MgCl_2$, preferably between 0.08 mole of water/ 1 mole of $MgCl_2$ and 0.3 mole of water/ 1 mole of $MgCl_2$. This specified amount of water, by way of its distribution, participates in formation of the specific activated support. For low water content, known magnesium chloride anhydriization methods can be employed, except those where an anhydriization agent remains in the $MgCl_2$ after washing of the anhydriized magnesium chloride with an inert hydrocarbon liquid. In particular, anhydriization with organic acid esters should be avoided.

The terms "partially anhydriized" and "anhydrous", as used in respect of magnesium chloride refer to the hydration water limits given above. This precludes side interpretations such as that $MgCl_2 \cdot 2H_2O$ is an "anhydriized" product if compared with $MgCl_2 \cdot 6H_2O$, or that a 1,5% water containing magnesium chloride is considered "non anhydrous" when compared with a 0,1% water containing magnesium chloride". Thus, the partially anhydriized magnesium chloride may have a water content of 1,5%, or even 5%, on a mass basis.

The support activation steps are preferably effected under inert conditions, ie in a substantially oxygen and water free reaction environment. The reaction environment should also be substantially free of any reacting products other than the reactants used for each specific step of the catalyst preparation.

In the making or preparation of the catalyst according to the invention, the support activation constitutes a fundamental stage. Attempts to react $MgCl_2$ directly with $TiCl_4$ result in hardly any fixation of titanium taking

place, probably due to high crystal order, low surface area and low pore volume. Methods to decrease the crystallinity and increase the surface and pore volume of MgCl_2 in general, are known. However, when these methods were
5 employed instead of the catalyst support activation steps used in the present method, a totally different catalyst is obtained, with totally different performances. It was unexpectedly found that only when using the activation
10 procedure as herein described, is a new catalyst, with excellent performance, obtained in the final step.

The activation procedure thus comprises, as hereinbefore stated,

mixing the ether having a total number of carbon atoms equal to or greater than 8, with the magnesium chloride, to
15 produce the partially activated magnesium chloride;

mixing the alkyl aluminium with the partially activated magnesium chloride to form the unwashed activated magnesium chloride; and

washing the activated magnesium chloride with the
20 inert saturated hydrocarbon liquid, to obtain the activated magnesium chloride-containing slurry.

It was also surprisingly found that the desired effect is not achieved with any ether. Thus, the ether is selected from the range of ethers having a total carbon atom number
25 equal to or greater than 8. The ether may be a linear ether with a total number of carbon atoms between 8 and 16, and being of the type $\text{R}'\text{-O-R}''$ where $\text{R}'=\text{R}''$. Particularly, ethers with a total number of carbon atoms less than 8, are not suitable for the activation procedure hereinbefore
30 described. Moreover, mixtures of ethers each having a total carbon number equal to or greater than 8 can be used. The ether may be dibutyl ether or, preferably, dipentyl ether.



The molar ratio of partially anhydriized magnesium chloride to ether may be between 0,3:1 and 3:1. Preferably, the molar ratio of magnesium chloride to ether is between 1:1 and 2,5:1.

- 5 Typical alkyl aluminiums or alkyl-aluminium compounds that can be used are trialkyl-aluminium compounds expressed by the formula AlR_3 wherein R is an alkyl radical or alkyl component having 1 to 10 carbon atoms. Specific examples of suitable trialkyl-aluminium compounds which can be used are
- 10 tributyl aluminium, tri-isobutyl aluminium, trihexyl aluminium, and trioctyl aluminium. It was surprisingly found that only alkyl-aluminium compounds with no halogen content can be used, to achieve the control of the performances of the newly developed catalyst. The
- 15 preferred trialkyl-aluminium compound is triethyl-aluminium. The molar ratio of the alkyl-aluminium compound to the anhydrous magnesium chloride may be between 1:1 and 6:1. The preferred molar ratio of the alkyl-aluminium compound to the anhydrous magnesium chloride is 4:1 to 5:1.
- 20 However, it is an important feature not only of the activation step but also of the specific method of achieving the final complex catalyst that the alkyl aluminium compound be added in a specific amount to suit a specific performance target for the final catalyst.
- 25 In one embodiment of this step of the support activation, the molar ratio of the alkyl-aluminium compound to the magnesium chloride can be toward the bottom of the selected range. Thus, in this case, the main target of the alkyl-aluminium compound is the support activation and its
- 30 preparation for the fixation of the titanium compound. In this case, the proportions of the components may be selected to comply with formula (1):
- $$A > B + C + D \dots\dots\dots (1)$$
- where A represents the total moles of the alkyl-
- 35 aluminium compound used;



B represents the total moles of MgCl_2 used;
C represents the total moles of ether used;
D represents the total moles of water present,
being the sum of the water of hydration
5 associated with the MgCl_2 and any water traces in
a carrier liquid (when present) for the mixture
of ether and MgCl_2 , as hereinafter described.

10 In another embodiment of the support activation, the molar
ratio of the alkyl-aluminium compound to the magnesium
chloride can be towards the top of the selected range.
Then, additionally to the support activation and its
preparation for the fixation of the titanium compound, a
larger amount of alkyl remains available for the reduction
15 of Ti^{4+} . In this case, based on the total aluminium
content measured after washing the activated support with
the hydrocarbon carrier liquid, the total amount of the
alcohols used in the preparation of the activated
support/alcohol complex, and the composition of the alcohol
20 combination used, the level of the alkyl linked to the
aluminium in the activated support/alcohol complex obtained
in the next step of the catalyst preparation, can be
predicted. It is important to predict from this early
stage of the catalyst preparation some limits for the next
25 step of preparation. A catalyst more suitable for
copolymerization and terpolymerization may then be
obtained.

30 The mixing of the activators, ie the ether and the alkyl-
aluminium compound, can be performed in various ways with
the proviso that the ether is first mixed with the
magnesium chloride, whereafter the mixing of alkyl
aluminium compound takes place.

Thus, in one embodiment of the activation stage, the ether
can be added to the MgCl_2 in solid particulate form, and the



mixture stirred by mechanical means for a period of 10 minutes to 24 hours, preferably 1 hour to 12 hours. The temperature during the stirring can range between 40°C and 140°C. After said stirring, the mixture can then be
5 cooling down to a temperature below 20°C, whereafter the alkyl-aluminium compound can be added directly to the $MgCl_2$ treated with the ether, or after suspending the mixture in an inert hydrocarbon carrier liquid. The hydrocarbon carrier liquid is inert, ie it does not partake in the
10 activation reactions. It may be an aliphatic or cyclo-aliphatic liquid hydrocarbon, with hexane and heptane being preferred.

In another embodiment of the activation stage, the ether can be added to a suspension of the $MgCl_2$ in an inert
15 hydrocarbon liquid, and the mixture stirred by mechanical means for a period of 30 minutes to 24 hours, preferably 1 to 12 hours. The temperature of the mixture during the stirring may be between 40°C and the reflux temperature of the inert hydrocarbon liquid but should not exceed 140°C.
20 After cooling down the mixture to below 20°C under stirring, the alkyl-aluminium compound can be added directly to the mixture or admixed with an inert hydrocarbon liquid, with vigorous stirring. The hydrocarbon liquid is thus inert, ie it does not partake in
25 the activation reactions. It may be an aliphatic or cyclo-aliphatic liquid hydrocarbon, with hexane and heptane being preferred.

It was found that best results are obtained by effecting the addition of the alkyl-aluminium compound in drop-wise
30 fashion by making use of a pure alkyl aluminium compound in liquid form or using a solution of the alkyl-aluminium compound in an inert hydrocarbon liquid as described above. The manner of addition and the conditions selected for this step of the catalyst preparation are important to achieve



a high degree of activation of the activated support for further catalyst preparation.

5 The activated support-containing slurry is, as mentioned, washed with an inert saturated hydrocarbon liquid, such as hexane, before adding the alcohols thereto. The washing may be severe, eg repeated a number of times, typically 10-20 times. At this stage, the activated support should be checked for the absence of the initial ether employed in
10 the first step of the activation. The absence of the initially introduced ether is an important feature of the method of the invention.

The observable effect of each step of activation is the disordering of the magnesium chloride crystal structure and
15 an increase of surface area and of pore volume. However, a direct relationship between the performance of the resultant catalyst and the surface area, as determined by the BET method, was not observed. On the contrary, the inventors believe that the effect of the surface area on
20 the catalyst performance is of reduced importance. However, in contrast, it was found that the increase in pore volume enhances the performance of the resultant catalyst. It is believed that, as a result of the specific manner of activation, a specific level of surface defects
25 and crystal disorder is achieved regardless of the surface area, for each particular case selected from the multitude of possibilities provided by the established limits of the two steps of activation. However, it was, at the same time, surprisingly found that only by adhering to the
30 method described, is a suitable support for the preparation of the catalyst according to this invention obtained.

The next step of the catalyst preparation is, as mentioned, mixing a plurality of alcohols with the activated support-containing slurry to form a particularly activated
35 support/alcohol complex.



While the alcohols can be mixed separately with the slurry, they are preferably used as a multicomponent mixture. The alcohol mixture may thus be added to the slurry. A dicomponent, tri-component or a higher multicomponent alcohol mixture can thus be used. The Applicant has surprisingly found that particularly good results are obtained with a tri-component alcohol mixture.

The alcohol mixture addition may be effected under stirring. The stirring time may be between 1 minute and 10 hours, preferably between 5 minutes and 4 hours. The temperature range can be between 0°C and the lower of the boiling point of any one of the alcohols of the alcohol mixture or the solvent used in the activation step, more preferably between 0° and ambient temperature.

Each alcohol may have between 2 and 10 carbon atoms. The most preferred alcohols are those having the same number of carbon atoms as the monomers used in a method of polymerization thereof, wherein the catalyst, the product of this method of catalyst preparation, is also used. Preferred dicomponent alcohol mixtures are ethanol and propanol; ethanol and 1-butanol; ethanol and 1-pentanol; ethanol and 1-hexanol; ethanol and 1-heptanol and ethanol and 1-octanol. The molar proportion of the one alcohol to the other alcohol in the dicomponent mixture can vary widely, but is preferably about 1:1. Preferred tri-component or three component alcohol mixtures are ethanol, propanol and 1-butanol; ethanol, propanol and 1-pentanol; ethanol, propanol and 1-hexanol; ethanol, propanol and 1-heptanol; ethanol, propanol and 1-octanol; ethanol, 1-butanol and 1-pentanol; ethanol, 1-butanol and 1-hexanol; ethanol, 1-butanol and 1-heptanol; ethanol, 1-pentanol and 1-hexanol; ethanol, 1-pentanol and 1-heptanol; ethanol, 1-pentanol and 1-octanol; ethanol, 1-hexanol and 1-heptanol; ethanol, 1-hexanol and 1-octanol; ethanol 1-heptanol and 1-octanol. The molar proportions of



the respective alcohols in such tri-component mixtures can vary widely.

5 In general, the molar ratio of the alcohol mixture to the anhydrous magnesium chloride used initially, may be between 0,4:1 and 4:1, preferably between 0,8:1 and 2,5:1.

In one embodiment of the invention, the amounts of the alcohols used may be such that formula (2) is complied with:

10 $[A] < [Al]$ (2)
where [A] represents the total moles of alcohols added and [Al] is the measured moles of aluminium present in the activated magnesium chloride-containing slurry.

15 In another embodiment of the invention, the amounts of the alcohols used may be such that formula (3) is complied with:

$[A] < 2 [Al] / 3$ (3)
where [A] and [Al] are as hereinbefore defined.

20 In yet another embodiment of the invention, the amounts of the alcohols used may be such that formula (4) is complied with:

$[A] < [Al] / 3$ (4)
where [A] and [Al] are as hereinbefore defined.

25 Thus, from particular cases of any activated support/alcohol complex prepared according to this invention with the specific ability to reduce a part of the titanium tetrachloride subsequently added to Ti^{3+} and Ti^{2+} , a large range of new Ziegler-Natta type catalysts in accordance with the invention can be prepared.

30 The mixing of the titanium tetrachloride with the activated magnesium chloride/alcohol complex or activated support/alcohol complex, may be effected by adding the



titanium tetrachloride to the activated support/alcohol complex.

After the titanium chloride has been added, the resultant slurry may be stirred under reflux for a period of 10 minutes to 5 hours, preferably 1-2 hours. However the temperature can be lowered in increments of 1°C if desired, but the stirring time should then be increased, eg by around 5 minutes for each degree Celsius which the temperature is lowered. Thereafter the slurry is allowed to cool, eg for about 24 hours. The catalyst in the slurry is washed with an inert saturated hydrocarbon liquid, preferably the same hydrocarbon liquid as is used for washing the activated magnesium chloride. Preferably, this hydrocarbon liquid is hexane or heptane. The washing may be repeated a number of times, typically between 10 and 40 times, eg about 20 times.

The molar ratio of titanium chloride to magnesium chloride used initially, may be between about 1:2 and about 20:1, preferably between 2:1 and 10:1.

The final washing removes the inactive compounds formed during the complex reactions of the last two steps. It also removes any unreacted titanium tetrachloride and weakly bound titanium chlorides absorbed on the support surfaces and which apparently do not participate in the formation of active centres. The observable effect is an increase in the catalyst surface area and pore volume and an increase of activity per gram of titanium added. It was found that catalysts with different properties are obtained when different numbers of washing are employed.

The resultant catalyst is particularly suited for the polymerization of olefins, particularly when used as part of a catalyst system which includes also a suitable co-catalyst.



The invention accordingly extends also to a catalyst when obtained by the method of the first aspect of the invention.

5 The catalyst is thus obtained by following each step of the method of making the catalyst hereinbefore described. A large diversity of catalysts are obtainable due to the large number of different combinations of parameters that can be selected within the limits prescribed in each step, and each particular catalyst has a complex structure.

10 More particularly, the catalyst can be a catalyst selected from the catalyst range obtainable by the method of the first aspect of the invention, and having a total aluminium content between 0,1% and 6% (mass basis), a total magnesium content between 3% and 15% (mass basis), and a total
15 titanium content between 3 and 15% (mass basis), providing that the mass ratio of magnesium to titanium is below 3:1.

Thus, according to a second aspect of the invention, there is provided a magnesium chloride-supported titanium catalyst comprising magnesium chloride as a catalyst
20 support, titanium and aluminium, and having a total aluminium content between 0.1% and 6% (mass basis), a total magnesium content between 3% and 15% (mass basis), and a total titanium content between 3 and 15% (mass basis), with the mass ratio of magnesium to titanium being below 3:1.

25 More particularly, the catalyst may have a Ti^{3+} content of less than 50% of the total titanium present therein. In one embodiment, the sum of Ti^{3+} and Ti^{2+} may be less than 50% of the total titanium present therein. In another embodiment, the sum of Ti^{3+} and Ti^{2+} may be less than 10%
30 of the total titanium present therein. In an even more particular embodiment, the ratio of Ti^{3+} to Ti^{2+} in the catalyst may be greater than 5:1.



Further, according to a third aspect of the invention, there is provided a catalyst system which comprises
a catalyst as hereinbefore described; and
an aluminium compound as a co-catalyst.

5 The co-catalyst may be, or comprise, an organo-aluminium compound. Typical organo-aluminium compounds which can be used are compounds expressed by the formula AlR_mX_{3-m} wherein R is a hydrocarbon radical or component of 1 to 15 carbon atoms, X is a halogen atom, and m is a number
10 represented by $0 \leq m \leq 3$. Specific examples of suitable organo-aluminium compounds which can be used are trialkyl aluminium, trialkenyl aluminium, partially halogenated alkyl aluminium, alkyl aluminium sesquihalide and alkyl aluminium dihalide. Preferred organo-aluminium compounds
15 are an alkyl aluminium, and the most preferred of these is triethylaluminium. The atomic ratio of aluminium to titanium in the catalyst system may be between 0,1:1 and 15000:1, preferably between 1:1 and 7500:1.

20 The catalyst and catalyst system according to the invention have one or more application advantages which distinguish them further over known Ziegler-Natta catalysts.

The catalyst and the catalyst system according to the invention are characterized thereby that they have high catalytic activity, and that they do not have to be
25 extracted from the product following the polymerization. Thus, the catalyst or the catalyst system may have a productivity greater than 10000 grams of polymer/gram of catalyst. In other words, in the case where, for example, ethylene is reacted using the catalyst or the catalyst
30 system to obtain homopolymers, or when ethylene is copolymerized, using the catalyst or the catalyst system, with an olefin selected from the group of propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene and 1-decene, in either linear form or branched



form except isomers where the branch is attached to a carbon atom connected to another carbon atom by a double bond, a productivity greater than 10000 grams of polymer/gram of catalyst is obtained. In particular, the catalyst or the catalyst system may have a productivity greater than 30000 grams of polymer/gram of catalyst, or even greater than 100000 grams of polymer/gram of catalyst.

Similarly, in the case where, for example, terpolymerization is effected between ethylene, 1-pentene and a monomer selected from the olefin group of propylene, 1-butene, 1-hexene, 1-heptene, 1-octene, 1-nonene and 1-decene, in either linear form or branched form except isomers where the branch is attached to a carbon atom connected to another carbon atom by a double bond, and the catalyst or the catalyst system is used, a productivity greater than 10000 grams of terpolymer/gram of catalyst may be obtained.

In the case where, for example, terpolymerization is effected between ethylene, 1-pentene, and 1-hexene, and using the catalyst or the catalyst system, a productivity greater than 25 000 grams of terpolymer/gram of catalyst may be obtained.

The catalyst and the catalyst system according to the invention have a suitable rate of incorporation of alpha olefin during a copolymerization, a terpolymerization or a multiple polymerization of ethylene with the alpha olefin(s). The catalyst or catalyst system thus provides an easy way of controlling the density of the polymer, and thus implicitly controlling those properties which depends on the density of the polymer.

When used in a terpolymerization of a monomer feedstock comprising ethylene and two alpha olefins each having a total carbon number between 4 and 8 and whose total carbon



numbers differ by one, the catalyst may have the ability to incorporate in the terpolymer amounts of these monomers which differ less than 25% from the proportions of these monomers in the feedstock.

5 The catalyst and the catalyst system according to this invention may have a rate enhancement effect during copolymerization and terpolymerization under different process conditions rendering it suitable for particular high efficiency copolymerization and terpolymerization
10 processes.

The catalyst and catalyst system according to this invention are suitable for molecular weight control of the resulting polymer and to the use of hydrogen as regulating agent for the molecular weight of the polymer. The
15 molecular weights of the resultant polymers decrease with increasing catalyst and/or hydrogen concentration. Thus the application properties related to the molecular weight of the polymer can easily be controlled. The catalyst and catalyst system according to this invention may have a
20 polydispersity index below 4 when used in a copolymerization or terpolymerization of ethylene with alpha olefin(s).

Different catalysts of this invention, when prepared between the particular limits prescribed in each step can,
25 be used in a process for obtaining different molecular weight distribution of the resulting polymer. In one embodiment of this aspect of the invention, the molecular distribution is lower than 4.

The catalyst and catalyst system according to this
30 invention have a practical storage time under certain handling conditions. No practical decrease of activity was observed for a sample of the catalyst kept in a



conventional dry box under inert conditions at 15°C after one month storage time.

5 The catalyst and catalyst system according to this invention are suitable for restarting a slurry polymerization after a "freezing time" of up to 12 hours. "Freezing time" is defined as the time that has elapsed between an interruption of supplying monomers to the polymerization zone with a simultaneous drop of reaction temperature to ambient temperature, preferably 15°C and
10 reheating to the reaction temperature with the restart of the supply of the monomers, with the slurry being kept under stirring and no product being evacuated from the reaction zone during this time.

15 The combination of the advantages mentioned above make the catalyst and catalyst system according to this invention an improved catalyst and catalyst system for industrial applications compared to known Ziegler-Natta catalysts.

20 The various steps of the catalyst preparation are practical steps making the catalyst preparation suitable for industrial application. The most time consuming operation, ie the washing operation, is benefitted by the favourable sedimentation time of the catalyst. "Sedimentation time" is defined as the time required for 25ml of a stirred suspension of 0,5 grams of catalyst in n-heptane to settle down when transferred to a graduated
25 ampoule, with the time being measured at 20°C and from the moment of transfer of the suspension in the measuring ampoule up to the time when the solution above the sedimented catalyst is completely clear. Generally, it was
30 found that the activated supports have good sedimentation times, T_1 , of less than 20 minutes, while the final catalysts have good sedimentation times, T_2 , of less than 30 minutes. It was surprisingly found that excellent performances are obtained from those catalysts according to



this invention which have $T_1 < 10$ minutes and $T_2 < 20$ minutes, and particularly where $T_1 < 5$ minutes and $T_2 < 15$ minutes. It was also surprisingly found that catalysts according to this invention having a good balance between compactness of the finally prepared catalyst as determined by the sedimentation time and fragmentation during polymerization, also gave good performance during polymerizations using the catalysts.

According to a fourth aspect of the invention, there is provided a method of polymerization, which method comprises reacting at least one olefin in the presence of a catalyst, or a catalyst system, as hereinbefore described, thereby to obtain a polymer of the olefin.

The reaction may be effected in a single reaction zone, at a pressure between atmospheric pressure and 200kg/cm^2 , and at a reaction temperature between ambient and 120°C .

Suitable olefins are α -olefins having a total number of carbon atoms between 2 and 10, such as ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene or 1-decene, in either linear form or branched form except isomers where the branch is attached to a carbon atom connected by a double bond to another carbon atom.

In one embodiment of the method of polymerization, a single olefin may be homopolymerized in the presence of the catalyst or the catalyst system.

In another embodiment of the invention, at least two of the olefins may be reacted in the presence of the catalyst or the catalyst system, to obtain copolymers of the two olefins. A catalyst according to the invention and prepared by using a dicomponent alcohol mixture in the activated support/alcohol complex preparation step, may be



used. The two alcohols may have the same number of carbon atoms as the olefin used for the copolymerization. Preferred copolymers are copolymers of ethylene with a linear alpha olefin. Examples of such copolymers are copolymers of ethylene and propene; ethylene and 1-butene; ethylene and 1-pentene; ethylene and 1-hexene; ethylene and 1-heptene and ethylene and 1-octene.

In yet another embodiment of the invention, three of the olefins may be reacted in the presence of the catalyst or the catalyst system, to obtain terpolymers of the olefins. A catalyst according to the invention and prepared by using a tricomponent alcohol mixture in the activated support/alcohol complex preparation step, may be used. The three alcohols may have the same number of carbon atoms as the olefin used for the terpolymerization.

Preferred examples of such terpolymers are terpolymers of ethylene with 2 monomers selected from the olefin group of propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 1-nonene and 1-decene, in either linear form or branched form except isomers where the branch is attached to a carbon atom connected to another carbon atom by a double bond.

More preferred examples of such terpolymers are those which contain at least one linear alpha olefin. Examples of such terpolymers are terpolymers of ethylene, propylene and 1-butene; ethylene, propylene and 1-pentene; ethylene, propylene and 1-hexene; ethylene, propylene and 1-heptene; ethylene, propylene and 1-octene; ethylene, 1-butene and 1-pentene; ethylene, 1-butene and 1-hexene; ethylene, 1-butene and 1-heptene; ethylene, 1-butene and 1-octene; ethylene, 1-pentene and 1-hexene; ethylene, 1-pentene and 1-heptene; ethylene, 1-pentene and 1-octene; ethylene, 1-hexene and 1-heptene; ethylene, 1-hexene and 1-octene; ethylene, 1-heptene, and 1-octene.



The most preferred examples of ethylene containing terpolymers are terpolymers of ethylene with 1-pentene and a third olefin selected from the olefin group of propylene, 1-butene, 1-hexene, 1-heptene, 1-octene, 1-nonene and 1-decene, in either linear form or branched form except isomers where the branch is attached to a carbon atom connected to another carbon atom by a double bond.

The invention will now be described by way of the following non-limiting examples:

10 EXAMPLE 1

Catalyst (A) preparation.

In a 250ml flask equipped with a reflux condenser and stirring facilities, 2g of anhydrous magnesium chloride with a total water content of 5% (by mass) was suspended in 60ml highly purified hexane. The suspension temperature was raised to 45°C, whereafter 2ml of dibutyl ether was added to the flask and the mixture stirred for 3 hours. Thereafter, the heating was stopped, the heat of mixture allowed to dissipate, and the temperature allowed to drop to ambient temperature. 9g of triethyl aluminium ('TEA') was then added dropwise to avoid excessive heat build-up, and the resultant slurry allowed to cool to room temperature under stirring. The slurry was then subjected to twelve washings using 50ml hexane each time, to obtain an activated support-containing slurry.

To the activated support-containing slurry was added 2ml of a 2:1:1 molar mixture of ethanol, 1-butanol and 1-pentanol, and the slurry stirred for 3 hours at ambient temperature. 20ml of TiCl_4 was then added to the slurry, and the resultant mixture stirred under reflux for 2 hours. After cooling down, the slurry was subjected to ten washings using 50ml hexane each time. After the final washing the slurry concentration was adjusted, by hexane addition, to



0,01g magnesium chloride supported titanium catalyst/1ml slurry.

The catalyst had an aluminium content of 0,98% (mass basis), a magnesium content of 11,12% (mass basis) and a titanium content of 11.08% (mass basis). The catalyst had a BET surface area of 35,70m²/g and a pore volume of 0,1298cc/g.

EXAMPLE 2

Catalyst (B) preparation.

In a 250ml flask equipped with a reflux condenser and stirring facilities, 2g of anhydrous magnesium chloride with a total water content of 1,5% (mass basis) was suspended in 60ml highly purified hexane. After heating the suspension to 45°C, 2ml of dibutyl ether was then added to the flask, and the heating stopped. After the heating had been stopped, the mixture was stirred for 3 hours. 9g of triethyl aluminium ('TEA') was then added dropwise to avoid excessive heat build-up, and the resultant slurry allowed to cool to room temperature under stirring. The slurry was then subjected to twelve washings using 50ml hexane each time, to obtain an activated support-containing slurry.

To the activated support-containing slurry was added 2ml of a 3:1.5:1 molar mixture of ethanol : 1-pentanol : 1-hexanol mixture and the slurry stirred for 3 hours. 20ml of TiCl₄ was then added to the slurry, and the resultant mixture stirred under reflux for one hour. After cooling down, the slurry was subjected to ten washings using 50ml hexane each time. After the final washing the slurry concentration was adjusted, by hexane addition, to 0,01g magnesium chloride supported titanium catalyst/1ml slurry.

The catalyst had an aluminium content of 0,95% (mass basis), a magnesium content of 6,53% (mass basis) and a



titanium content of 12,15% (mass basis). The catalyst has a BET surface area of $159,21\text{m}^2/\text{g}$ and a pore volume of $0,3231\text{cc/g}$.

EXAMPLE 3

5 300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with agitation. The reactor was heated to 85°C , and 1ml of a 10wt percent solution of TEA was added thereto. 0,1ml of catalyst B was added to the reactor, and the mixture
10 stirred for five minutes after which the reactor was pressurised to 15 bar with ethylene and the reaction started. The reaction was continued for 60 minutes at constant pressure maintained by ethylene supply after which the ethylene supply was closed off and the reactor vented.
15 Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The slurry was filtered and washed with iso-propanol and acetone, and the resultant polymer dried for 24 hours under reduced pressure in a vacuum oven at 80°C . The dry polymer
20 in the form of a powder was weighed and 83g of polymer obtained. The activity of catalyst B was calculated as 83kg/g catalyst per hour.

EXAMPLE 4

25 300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with agitation. The reactor was heated to 85°C and 1ml of a 10wt percent solution of TEA was added thereto. 0,1ml of catalyst A was added to the reactor, and the mixture
30 stirred for five minutes after which the reactor was pressurised to 15 bar with ethylene and the reaction started. The reaction was continued for 60 minutes at constant pressure maintained by ethylene supply after which the ethylene supply was closed off and the reactor vented. Iso-propanol was added to deactivate the catalyst and the
35 reaction mixture allowed to cool to room temperature. The



slurry was filtered and washed with iso-propanol and acetone, and the resultant polymer dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The dry polymer in the form of a powder was weighed and 58,1g of polymer
5 obtained. The activity of catalyst A was calculated as 58,1kg/g catalyst per hour.

EXAMPLE 5

3000g of highly purified n-heptane was introduced into a 10 l stainless steel polymerisation vessel provided with
10 agitation. After thorough purging of the vessel with nitrogen, 15ml of triethylaluminium (10% solution in heptane) as a co-catalyst, and 5ml of catalyst B, were introduced into the vessel. The temperature was set at 85°C and after 10 minutes of stirring, 1300mg of hydrogen
15 were added. 1000g of ethylene, at a constant flow of 4g/minute, and 1200g of a 5:1 molar mixture of 1-pentene and 1-hexene at a constant flow of 4,8g/minute, were introduced into the vessel, with the flows being commenced simultaneously. In a next step, the polymerisation vessel
20 was depressurised and the catalyst decomposed with 1-propanol. The resultant terpolymer was then filtered and repeatedly washed with propanol, methanol and acetone. The terpolymer was dried in a vacuum oven at 70°C for 24 hours. The yield of the terpolymer was 1000g.

25 The composition of the terpolymer as measured by ^{13}C NMR was 3,0 molar % comonomer (sum of 1-pentene and 1-hexene) with the molar ratio of the incorporated 1-pentene:1-hexene being 5:1.

EXAMPLE 6

30 The polymerisation described in Example 5 was repeated, except that 1,2ml of catalyst A was used instead of catalyst B and 600g of a 5:1 mixture of 1-butene : 1-pentene instead of a mixture of 1-pentene : 1-hexene, at a constant flow of 2,4g/minute. 3000mg hydrogen were also



introduced. The yield of the terpolymer obtained was 290g. The composition of the terpolymer was 1,5 molar % (sum of 1-butene and 1-pentene) with the molar ratio of the incorporated 1-butene: 1-pentene being 5:1. The MFI of the
5 polymer was 3,5.

EXAMPLE 7

Catalyst (C) Preparation

In a 250ml flask equipped with a reflux condenser and stirring facilities, 2g of magnesium chloride with a total
10 water content of 1.5% (by mass) was suspended in 60ml highly purified hexane. 4ml of dipentyl ether was added to the flask, and the mixture stirred for 3 hours under reflux. Thereafter, the temperature was lowered to ambient temperature and 10g of triethyl aluminium ('TEA') was added
15 dropwise to avoid excessive heat build-up. The resultant slurry was allowed to cool to room temperature under stirring. The slurry was then subjected to twelve washings using 50ml hexane each time, to obtain an activated support-containing slurry.

20 To the activated support-containing slurry was added 2ml of a 1:1:1 molar mixture of ethanol, 1-butanol and 1-pentanol, and the slurry stirred for 3 hours at ambient temperature. 15ml of TiCl_4 was then added to the slurry, and the resultant mixture stirred under reflux for 2 hours. After
25 cooling down, the slurry was subjected to ten washings using 50ml hexane each time. After the final washing the slurry concentration was adjusted, by hexane addition, to 0,01g magnesium chloride supported titanium catalyst/1ml slurry.

30 The catalyst had an aluminium content of 1,1% (mass basis), a magnesium content of 12,93% (mass basis) and a titanium content of 7,04% (mass basis). The catalyst has a BET surface area of $112,39\text{m}^2/\text{g}$ and a pore volume of $0,4656\text{cc/g}$.



EXAMPLE 8

300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with agitation. The reactor was heated to 85°C and 1ml of a
5 10wt percent solution of TEA was added thereto. 0,1ml of catalyst C was added to the reactor, and the mixture stirred for five minutes after which the reactor was pressurised to 15 bar with ethylene and the reaction
10 started. The reaction was continued for 60 minutes at constant pressure maintained by ethylene supply after which the ethylene supply was closed off and the reactor vented. Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The
15 slurry was filtered and washed with iso-propanol and acetone, and the resultant polymer dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The dry polymer in the form of a powder was weighed and 120g of polymer obtained. The activity of catalyst C was calculated as 120kg/g catalyst per hour.

20 EXAMPLE 9

Catalyst C was kept in an Mbraun dry box for one month at ambient temperature and inert conditions. Example 8 was repeated using the same conditions and using catalyst C after one month storage time. An amount of 118g of polymer
25 were obtained. The activity of the catalyst after one month storage time was 118kg/g catalyst.

EXAMPLE 10

300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with
30 agitation. The reactor was heated to 85°C and 1ml of a 10wt percent solution of TEA was added thereto. 0,1ml of catalyst C was added thereto, and the mixture stirred for five minutes after which the reactor was pressurised to 15 bar with ethylene and the reaction started. The reaction
35 was continued for 30 minutes at constant pressure



maintained by ethylene supply after which the ethylene supply was stopped and the reactor cooled down to 15°C under stirring. After 6 hours the reactor was reheated and at 75°C the ethylene supply was restarted. The reaction
5 reached its previous conditions and was continued for another 30 minutes when the ethylene supply was stopped and the reactor cooled down and vented. Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The slurry was filtered and
10 washed with iso-propanol and acetone, and the resultant polymer dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The dry polymer in the form of a powder was weighed and 122g of polymer obtained.

EXAMPLE 11

15 Catalyst (D) Preparation

In a 250ml flask equipped with a reflux condenser and stirring facilities 2g of magnesium chloride with a total water content of 5% (by mass) was suspended in 60ml highly purified hexane. 2ml of dipentyl ether was added to the
20 flask and the mixture stirred for 3 hours under reflux. Thereafter, the temperature was lowered to ambient temperature and 12g of triethyl aluminium ('TEA') was added dropwise to avoid excessive heat build-up. The resultant slurry was allowed to cool to room temperature under
25 stirring. The slurry was then subjected to six washings using 50ml hexane each time, to obtain an activated support-containing slurry.

To the activated support-containing slurry was added 2,2ml of a 1:2 molar mixture of 1-butanol and 1-pentanol, and the
30 slurry stirred for 2 hours at reflux. 15ml of TiCl_4 was then added to the slurry, and the resultant mixture stirred under reflux for 2 hours. After cooling down, the slurry was subjected to six washing using 50ml hexane each time. After the final washing the slurry concentration was



adjusted, by hexane addition, to 0,01g magnesium chloride supported titanium catalyst/1ml slurry.

The catalyst had an aluminium content of 2,63% (mass basis), a magnesium content of 5,06% (mass basis) and a
5 titanium content of 8,82% (mass basis). The measured BET surface area was 20,52m²/g and the pore volume 0,071cc/g.

EXAMPLE 12

300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with
10 agitation. The reactor was heated to 85°C and 1ml of a 10wt percent solution of TEA was added thereto. 0,1ml of catalyst D was added to the reactor, and the mixture stirred for five minutes after which the reactor was
15 pressurised to 15 bar with ethylene and the reaction started. The reaction was continued for 60 minutes at constant pressure maintained by ethylene supply after which the ethylene supply was closed off and the reactor vented.
20 Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The slurry was filtered and washed with iso-propanol and acetone, and the resultant polymer dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The dry polymer in the form of a powder was weighed and 67,7g of polymer obtained. The activity of catalyst D was calculated as
25 67,7kg/g catalyst per hour.

EXAMPLE 13

3000g of highly purified n-heptane was introduced into a 10l stainless steel polymerisation vessel provided with
30 agitation. After thorough purging of the vessel with nitrogen, 150ml of triethylaluminium (10% solution in heptane) as a co-catalyst, and 5ml of catalyst D, were introduced into the vessel. The temperature was set at 85°C and after 10 minutes of stirring, 3000mg of hydrogen were added. 1000g of ethylene, at a constant flow of



4g/minute, and 1000g of a 1-butene at a constant flow of 4g/minute, were introduced into the vessel, with the flows being commenced simultaneously. In a next step, the polymerisation vessel was depressurised and the catalyst decomposed with 1-propanol. The resultant terpolymer was then filtered and repeatedly washed with propanol, methanol and acetone. The terpolymer was dried in a vacuum oven at 70°C for 24 hours. The yield of the terpolymer was 1000g.

The composition of the terpolymer as measured by ^{13}C NMR was 3,0 molar % of butene-1. The density of the copolymer was 0,9175.

EXAMPLE 14

3000g of highly purified n-heptane was introduced into a 10l stainless steel polymerisation vessel provided with agitation. After thorough purging of the vessel with nitrogen, 150ml of triethylaluminium (10% solution in heptane) as a co-catalyst, and 1ml of catalyst D, were introduced into the vessel. The temperature was set at 85°C and after 15 minutes of stirring, 3000mg of hydrogen were added. 1000g of ethylene, at a constant flow of 4g/minute, and 1000g of a mixture of 1-pentene and 1-hexene at a 1:9 ratio and at a constant flow of 4g/minute, were introduced into the vessel, with the flows being commenced simultaneously. In a next step, the polymerisation vessel was depressurised and the catalyst decomposed with 1-propanol. The resultant terpolymer was then filtered and repeatedly washed with propanol, methanol and acetone. The terpolymer was dried in a vacuum oven at 70°C for 24 hours. The yield of the terpolymer was 390g.

The composition of the terpolymer as measured by ^{13}C NMR was 0,9 molar % of a mixture of 1-hexene/1-pentene (with 1-pentene difficult detectable). The molecular data of the terpolymer have been measured: $M_w = 116836$; $M_z = 318748$; $M_n = 35623$ and polydispersity 3.279792.



EXAMPLE 15Catalyst (E) Preparation

In a 250ml flask equipped with a reflux condenser and stirring facilities 2g of anhydrous magnesium chloride with a total water content of 1,5% (by mass) was suspended in 60ml highly purified hexane. The temperature was raised to 45°C, and 2ml of dipentyl ether was then added to the flask and the mixture stirred for 3 hours. Thereafter, the heating was stopped, the heat of mixture allowed to dissipate, and the temperature allowed to drop to ambient temperature. 12g of triethyl aluminium ('TEA') was then added dropwise to avoid excessive heat build-up, and the resultant slurry allowed to cool to room temperature under stirring. The mixture was stirred at room temperature for another 8 hours. The slurry was then subjected to six washings using 50ml hexane each time, to obtain an activated support-containing slurry.

To the activated support-containing slurry was added 2ml of a 1:1 molar mixture of ethanol and 1-octanol, and the slurry stirred for 3 hours at ambient temperature. 20ml of TiCl_4 was then added to the slurry, and the resultant mixture stirred under reflux for 2 hours. After cooling down, the slurry was subjected to six washings using 50ml hexane each time. After the final washing the slurry concentration was adjusted, by hexane addition, to 0,01g magnesium chloride supported titanium catalyst/1ml slurry.

The catalyst had an aluminium content of 3,66% (mass basis), a magnesium content of 8,72% (mass basis) and a titanium content of 16,93% (mass basis). The Ti^{4+} was 91,65%; the Ti^{3+} was 8,21% and the Ti^{2+} was 0,095%.

EXAMPLE 16

300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with agitation. The reactor was heated to 85°C and 1ml of a



10wt percent solution of TEA was added thereto. 0,1ml of catalyst E was added to the reactor, and the mixture stirred for five minutes after which the reactor was pressurised to 15 bar with ethylene and the reaction started. The reaction was continued for 60 minutes at constant pressure maintained by ethylene supply after which the ethylene supply was closed off and the reactor vented. Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The slurry was filtered and washed with iso-propanol and acetone and the resultant polymer was dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The dry polymer in the form of a powder was weighed and 78g of polymer obtained. The activity of catalyst E was calculated as 78kg/g catalyst per hour.

EXAMPLE 17

300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with agitation. The reactor was heated to 85°C and 1ml of a 10wt percent solution of TEA was added thereto. 0,1ml of catalyst E was added to the reactor, and the mixture stirred for five minutes after which an 80g of ethylene were fed to the reactor at a flow of 4g/min. Concomitantly a feed of 4g/min of 80g of 1-octene was started. The reaction was continued for another 20 minutes under stirring and further cooled down under stirring to room temperature where the reactor was vented. Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The slurry was filtered and washed with iso-propanol and acetone, and the resultant polymer was dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The dry polymer in the form of a powder was weighed and 78g of polymer obtained.



EXAMPLE 18Catalyst (F) Preparation

5 To 4g of MgCl_2 , 4ml of di-n-butyl ether was added in a drybox and the suspension ground for 1 hour. It was then stirred for another 3 hours at 45°C and left to stand for 24 hours. A sample of the solid material had a BET surface area of $2.51 \text{ m}^2/\text{g}$, a pore volume of 0,0121cc/g and a measured sedimentation time of 5 minutes.

10 100ml of a 10% triethyl aluminium solution in heptane was added dropwise to this solid material and continuously stirred. After all the triethyl aluminium had been added, the suspension was stirred for a further 3 hours. The slurry was washed twelve times using 50ml heptane each time, and after the last washing, the heptane was allowed to evaporate. This powder had a BET surface area of $6.48 \text{ m}^2/\text{g}$, a pore volume of 0,0268cc/g and a measured sedimentation time of 5 minutes.

20 To the dry powder, 0,2ml ethanol, 0,37ml pentanol and 0,42ml hexanol were added. To the resulting lumpy solid, 20ml heptane were added and the material ground to a fine precipitate. 7ml TiCl_4 was slowly added to this suspension and refluxed under inert conditions for 60 minutes. After cooling the slurry was washed ten times using 200ml heptane each time. The concentration of the final slurry was adjusted to 0,01g/ml.

30 The final catalyst had a BET surface area of $38,9 \text{ m}^2/\text{g}$, a pore volume of 0,1cc/g and a measured sedimentation time of 15 minutes. Chemical analyses showed that the catalyst contained (on a mass basis) 0,1802 % Al, 11,4963 % Mg and 6,9060 % Ti. The Ti oxidation states were 0,688 % Ti^{2+} , 4,107 % Ti^{3+} and 95,205 % Ti^{4+} .



EXAMPLE 19

300ml of highly purified n-heptane was added to a 1l stainless steel reaction vessel (reactor) provided with agitation. The reactor was heated to 85°C and 1ml of a
5 10wt percent solution of TEA was added thereto. 0,1ml of catalyst F was added to the reactor, and the mixture stirred for five minutes after which the reactor was pressurised to 15 bar with ethylene and the reaction started. The reaction was continued for 60 minutes at
10 constant pressure maintained by ethylene supply after which the ethylene supply was closed off and the reactor vented. Iso-propanol was added to deactivate the catalyst and the reaction mixture allowed to cool to room temperature. The slurry was filtered and washed with iso-propanol and
15 acetone, and dried for 24 hours under reduced pressure in a vacuum oven at 80°C. The resultant dry polymer in the form of a powder was weighed and 14,4g of polymer obtained. The activity of catalyst F was calculated as 14,4kg/g catalyst per hour.

20 In the Examples, the following methods of analyses of the catalysts were used.

Al, Mg and Ti content was determined by Inductively Coupled Plasma (ICP);

Cl⁻ content was determined by Ion Chromatography;

25 The nature and concentration of organic species were determined by Gas Chromatography (GC) and Gel Chromatography coupled with Mass Spectrophotometry (GC/MS);

The sum of Ti²⁺ and Ti³⁺ was determined by UV/VIS absorbance of a 1,10-phenanthroline complex with Fe²⁺
30 obtained by reduction of Fe³⁺ in methanol;



Ti^{2+} was determined from the amount of H_2 evolved by reacting with protons formed when reacting the catalyst with methanol.

This Sheet Has Been Replaced



CLAIMS

1. A method of making a catalyst suitable for the polymerization of olefins, which method comprises
- 5 mixing an ether having a total number of carbon atoms equal to or greater than 8, with magnesium chloride, to produce partially activated magnesium chloride;
- mixing an alkyl aluminium with the partially activated magnesium chloride to form unwashed activated magnesium chloride;
- 10 washing the activated magnesium chloride with an inert saturated hydrocarbon liquid, to obtain an activated magnesium chloride-containing slurry;
- mixing a plurality of alcohols with the activated magnesium chloride-containing slurry to form an activated
- 15 magnesium chloride/alcohol complex; and
- mixing titanium tetrachloride with the activated magnesium chloride/alcohol complex, to form a magnesium chloride supported titanium catalyst.
2. A method according to Claim 1, wherein the
- 20 magnesium chloride is partially anhydriized, with the mixing of the ether with the partially anhydriized magnesium chloride being effected under inert conditions.
3. A method according to Claim 2, wherein the
- 25 partially anhydriized magnesium chloride has a water content of 0.02 to 2 moles of water per 1 mole of magnesium chloride.
4. A method according to Claim 2, wherein the partially anhydriized magnesium chloride has a water content of 1,5% (by mass).

This Sheet Has Been Replaced



5. A method according to Claim 2, wherein the partially anhydriized magnesium chloride has a water content of 5% (by mass).
6. A method according to any one of Claims 2 to 5 inclusive, wherein the ether is dipentyl ether.
7. A method according to any one of Claims 2 to 5 inclusive, wherein the ether is dibutyl ether.
8. A method according to any one of Claims 2 to 7 inclusive, wherein the magnesium chloride and the ether are used in such proportions that the molar ratio of magnesium chloride to ether is between 0,3:1 and 3:1, and wherein the mixing of the magnesium chloride with the ether is effected at a temperature between 40°C and 140°C.
9. A method according to any one of Claims 2 to 8 inclusive, wherein the alkyl aluminium, the magnesium chloride and the ether are used in such proportions that formula (1) is complied with:
- $$A > B + C + D \dots\dots\dots (1)$$
- where A represents the total moles of the alkyl aluminium used;
- B represents the total moles of magnesium chloride used;
- C represents the total moles of ether used; and
- D represents the total moles of water present, being the sum of the water of hydration associated with the magnesium chloride and any water traces in any carrier liquid used.
10. A method according to any one of Claims 1 to 9 inclusive, wherein the mixing of the alkyl aluminium with the partially activated magnesium chloride is effected by adding the alkyl aluminium dropwise to a solid mixture of





the magnesium chloride and the ether, while stirring the mixture.

11. A method according to any one of Claims 1 to 9 inclusive, wherein the mixing of the alkyl aluminium with the partially activated magnesium chloride is effected by adding the alkyl aluminium dropwise to a suspension or slurry of the magnesium chloride and the ether in an inert saturated hydrocarbon carrier liquid, while stirring the suspension.

12. A method according to any one of Claims 1 to 11 inclusive, wherein the amounts of the alcohols used are such that formula (2) is complied with:

$$[A] < [Al] \dots\dots\dots (2)$$

where [A] represents the total moles of alcohols used, and [Al] is the measured moles of aluminium present in the activated magnesium chloride-containing slurry.

13. A method according to any one of Claims 1 to 11 inclusive, wherein the amounts of the alcohols used are such that formula (3) is complied with:

$$[A] < 2 [Al]/3 \dots\dots\dots (3)$$

where [A] represents the total moles of alcohols used, and [Al] is the measured moles of aluminium present in the activated magnesium chloride-containing slurry.

14. A method according to any one of Claims 1 to 11 inclusive, wherein the amounts of the alcohols used are such that formula (4) is complied with:

$$[A] < [Al]/3 \dots\dots\dots (4)$$

where [A] represents the total moles of alcohols used, and [Al] is the measured moles of aluminium present in the activated magnesium chloride-containing slurry.

15. A method according to any one of Claims 1 to 14 inclusive, wherein the activated magnesium chloride has a





sedimentation time, T_1 , of less than 20 minutes, while the magnesium chloride supported titanium catalyst has a sedimentation time, T_2 , of less than 30 minutes.

16. A method according to Claim 15, wherein $T_1 < 10$
5 minutes and $T_2 < 20$ minutes.

17. A method according to Claim 16, wherein $T_1 < 5$
minutes and $T_2 < 15$ minutes.

18. A catalyst when prepared by a method according to
any one of the Claims 1 to 17 inclusive.

10 19. A magnesium chloride-supported titanium catalyst
comprising magnesium chloride as a catalyst support,
titanium and aluminium, and having a total aluminium
content between 0.1% and 6% (mass basis), a total magnesium
content between 3% and 15% (mass basis), and a total
15 titanium content between 3 and 15% (mass basis), with the
mass ratio of magnesium to titanium being below 3:1.

20. A magnesium chloride-supported titanium catalyst
comprising magnesium chloride as a catalyst support,
titanium and aluminium, and having a total aluminium
20 content between 0.1% and 6% (mass basis), a total magnesium
content between 3% and 15% (mass basis), and a total
titanium content between 3 and 15% (mass basis), with the
mass ratio of magnesium to titanium being below 3, when
prepared by a method according to any one of the Claims 1
25 to 17 inclusive.

21. A catalyst according to any one of Claims 18 to
20 inclusive, which has a Ti^{3+} content of less than 50%
based on the total titanium present therein.

This Sheet Has Been Replaced





22. A catalyst according to any one of Claims 18 to 20 inclusive, wherein the sum of Ti^{3+} and Ti^{2+} is less than 50% of the total titanium present therein.

5 23. A catalyst according to Claim 22, wherein the sum of Ti^{3+} and Ti^{2+} is less than 10% of the total titanium present therein.

24. A catalyst according to Claim 23, wherein the ratio of Ti^{3+} to Ti^{2+} is greater than 5:1.

10 25. A catalyst according to any one of Claims 18 to 24 inclusive, which has a productivity greater than 10000 grams of polymer/gram of catalyst.

26. A catalyst according to Claim 25, which has a productivity greater than 30000 grams of polymer/gram of catalyst.

15 27. A catalyst according to Claim 26, which has a productivity greater than 100000 grams of polymer/ gram of catalyst.

20 28. A catalyst according to any one of Claims 18 to 27 inclusive which, when used for terpolymerization of a monomer feedstock comprising ethylene and two alpha olefins each having a total carbon number between 4 and 8 and whose total carbon numbers differ by one, has the ability to incorporate in the terpolymer amounts of these monomers which differ less than 25% from the proportions of these
25 monomers in the feedstock.

29. A catalyst according to any one of Claims 18 to 28 inclusive, which gives a polydispersity index below 4 when used in a copolymerization or terpolymerization of ethylene with alpha olefin(s).





30. A catalyst system which comprises
a catalyst according to any one of Claims 18 to 29
inclusive; and
an aluminium compound, as a co-catalyst.
- 5 31. A catalyst system according to Claim 30, wherein
the co-catalyst is triethyl aluminium.
32. A catalyst system according to Claim 30 or Claim
31, which has a productivity greater than 10000 grams of
polymer/gram of catalyst.
- 10 33. A catalyst system according to any one of Claims
30 to 32 inclusive which, when used for terpolymerization
of a monomer feedstock comprising ethylene and two alpha
olefins each having a total carbon number between 4 and 8
and whose total carbon numbers differ by one, has the
15 ability to incorporate in the terpolymer amounts of these
monomers which differ less than 25% from the proportions of
these monomers in the feedstock.
34. A catalyst system according to any one of Claims
30 to 33 inclusive, which gives a polydispersity index
20 below 4 when used in a copolymerization or
terpolymerization of ethylene with alpha olefin(s).
35. A method of polymerization, which method
comprises reacting at least one olefin in the presence of
a catalyst according to any one of Claims 18 to 29
25 inclusive, or a catalyst system according to any one of
Claims 30 to 34 inclusive, thereby to obtain a polymer of
the olefin.
36. A method of polymerization according to Claim 35,
wherein the reaction is effected in a single reaction zone,
30 at a pressure between atmospheric pressure and 200kg/cm²,
and at a reaction temperature between ambient and 120°C.





39

37. A method of polymerization according to Claim 35 or Claim 36, wherein two olefins are reacted, as monomers, to produce a copolymer.
- 5 38. A method of polymerization according to Claim 37, wherein one of the monomers is ethylene.
39. A method of polymerization according to Claim 35 or Claim 36, wherein three olefins are reacted, as monomers, to produce a terpolymer.
- 10 40. A method of polymerization according to Claim 39, wherein one of the monomers is ethylene.
41. A method of polymerization according to Claim 40, wherein another of the monomers is 1-pentene.
42. A novel method of making a catalyst, substantially as described and exemplified herein.
- 15 43. A novel catalyst, substantially as described and exemplified herein.
44. A novel catalyst system, substantially as described and exemplified herein.
- 20 45. A novel method of polymerization, substantially as described and exemplified herein.

This Sheet Has Been Replaced

40
AMENDED CLAIMS

[received by the International Bureau on 11 November 1997 (11.11.97);
original claims 1-45 replaced by
new claims 1-54 (9 pages)]

1. A method of making a catalyst suitable for the polymerization of olefins, which method comprises
mixing an ether having a total number of carbon atoms
5 equal to or greater than 8, with magnesium chloride, to produce partially activated magnesium chloride;
mixing an alkyl aluminium with the partially activated magnesium chloride to form unwashed activated magnesium chloride;
10 washing the activated magnesium chloride with an inert saturated hydrocarbon liquid, to obtain an activated magnesium chloride-containing slurry;
mixing a plurality of alcohols with the activated magnesium chloride-containing slurry to form an activated
15 magnesium chloride/alcohol complex; and
mixing titanium tetrachloride with the activated magnesium chloride/alcohol complex, to form a magnesium chloride supported titanium catalyst.
2. A method according to Claim 1, wherein the
20 magnesium chloride is partially anhydriized, with the mixing of the ether with the partially anhydriized magnesium chloride being effected under inert conditions.
3. A method according to Claim 2, wherein the
partially anhydriized magnesium chloride has a water content
25 of 0.02 to 2 moles of water per 1 mole of magnesium chloride.
4. A method according to Claim 2, wherein the
partially anhydriized magnesium chloride has a water content of 1,5% (by mass).

This Sheet Has Been Replaced



5. A method according to Claim 2, wherein the partially anhydriized magnesium chloride has a water content of 5% (by mass).

5 6. A method according to any one of Claims 2 to 5 inclusive, wherein the ether is dipentyl ether.

7. A method according to any one of Claims 2 to 5 inclusive, wherein the ether is dibutyl ether.

10 8. A method according to any one of Claims 2 to 7 inclusive, wherein the magnesium chloride and the ether are used in such proportions that the molar ratio of magnesium chloride to ether is between 0,3:1 and 3:1.

15 9. A method according to any one of Claims 2 to 8 inclusive, wherein the mixing of the magnesium chloride with the ether is effected at a temperature between 40°C and 140°C.

10. A method according to any one of Claims 2 to 9 inclusive, wherein the alkyl aluminium, the magnesium chloride and the ether are used in such proportions that formula (1) is complied with:

20
$$A > B + C + D \dots\dots\dots (1)$$

where A represents the total moles of the alkyl aluminium used;

B represents the total moles of magnesium chloride used;

25 C represents the total moles of ether used; and
D represents the total moles of water present, being the sum of the water of hydration associated with the magnesium chloride and any water traces in any carrier liquid used.

30 11. A method according to any one of Claims 1 to 10 inclusive, wherein the mixing of the alkyl aluminium with





the partially activated magnesium chloride is effected by adding the alkyl aluminium dropwise to a solid mixture of the magnesium chloride and the ether, while stirring the mixture.

5 12. A method according to any one of Claims 1 to 10
 inclusive, wherein the mixing of the alkyl aluminium with
 the partially activated magnesium chloride is effected by
 adding the alkyl aluminium dropwise to a suspension or
10 slurry of the magnesium chloride and the ether in an inert
 saturated hydrocarbon carrier liquid, while stirring the
 suspension.

 13. A method according to any one of Claims 1 to 12
 inclusive, wherein the amounts of the alcohols used are
 such that formula (2) is complied with:

15 [A] < [Al] (2)

 where [A] represents the total moles of alcohols used, and
 [Al] is the measured moles of aluminium present in the
 activated magnesium chloride-containing slurry.

 14. A method according to any one of Claims 1 to 12
20 inclusive, wherein the amounts of the alcohols used are
 such that formula (3) is complied with:

 [A] < 2 [Al]/3 (3)

 where [A] represents the total moles of alcohols used, and
 [Al] is the measured moles of aluminium present in the
25 activated magnesium chloride-containing slurry.

 15. A method according to any one of Claims 1 to 12
 inclusive, wherein the amounts of the alcohols used are
 such that formula (4) is complied with:


 [A] < [Al]/3 (4)

30 where [A] represents the total moles of alcohols used, and
 [Al] is the measured moles of aluminium present in the
 activated magnesium chloride-containing slurry.





16. A method according to any one of Claims 1 to 15 inclusive, wherein the plurality of alcohols are used as a multicomponent alcohol mixture which is thus mixed with the activated magnesium-containing slurry.
- 5 17. A method according to any one of Claims 1 to 16 inclusive, wherein the activated magnesium chloride has a sedimentation time, T_1 , of less than 20 minutes, while the magnesium chloride supported titanium catalyst has a sedimentation time, T_2 , of less than 30 minutes.
- 10 18. A method according to Claim 17, wherein $T_1 < 10$ minutes and $T_2 < 20$ minutes.
19. A method according to Claim 18, wherein $T_1 < 5$ minutes and $T_2 < 15$ minutes.
- 15 20. A catalyst when prepared by a method according to any one of the Claims 1 to 19 inclusive.
21. A catalyst according to Claim 20, wherein the sum of Ti^{3+} and Ti^{2+} is less than 50% of the total titanium present therein.
- 20 22. A magnesium chloride-supported titanium catalyst comprising magnesium chloride as a catalyst support, titanium and aluminium, and having a total aluminium content between 0.1% and 6% (mass basis), a total magnesium content between 3% and 15% (mass basis), and a total titanium content between 3 and 15% (mass basis), and
- 25 wherein the sum of Ti^{3+} and Ti^{2+} is less than 50% of the total titanium present therein.
23. A magnesium chloride-supported titanium catalyst comprising magnesium chloride as a catalyst support, titanium and aluminium, and having a total aluminium





content between 0.1% and 6% (mass basis), a total magnesium content between 3% and 15% (mass basis), and a total titanium content between 3 and 15% (mass basis), when prepared by a method according to any one of the Claims 1 to 19 inclusive.

24. A catalyst according to Claim 23, wherein the sum of Ti^{3+} and Ti^{2+} is less than 50% of the total titanium present therein.

25. A catalyst according to any one of Claims 20 to 24 inclusive, wherein the mass ratio of magnesium to titanium therein is below 3:1.

26. A catalyst according to any one of Claims 21, 22, 24 and 25, wherein the sum of Ti^{3+} and Ti^{2+} is less than 10% of the total titanium present therein.

27. A catalyst according to Claim 26, wherein the ratio of Ti^{3+} to Ti^{2+} is greater than 5:1.

28. A catalyst according to any one of Claims 20 to 27 inclusive, which has a productivity greater than 10000 grams of polymer/gram of catalyst.

29. A catalyst according to Claim 28, which has a productivity greater than 30000 grams of polymer/gram of catalyst.

30. A catalyst according to Claim 29, which has a productivity greater than 100000 grams of polymer/gram of catalyst.

31. A catalyst according to any one of Claims 20 to 30 inclusive which, when used for terpolymerization of a monomer feedstock comprising ethylene and two alpha olefins each having a total carbon number between 4 and 8 and whose





total carbon numbers differ by one, has the ability to incorporate in the terpolymer amounts of these monomers which differ less than 25% from the proportions of these monomers in the feedstock.

- 5 32. A catalyst according to any one of Claims 20 to 31 inclusive, which gives a polydispersity index below 4 when used in a copolymerization or terpolymerization of ethylene with alpha olefin(s).
- 10 33. A catalyst according to any one of Claims 20 to 32 inclusive, which has a sedimentation time of less than 30 minutes.
34. A catalyst according to Claim 33, which has a sedimentation time of less than 20 minutes.
- 15 35. A catalyst according to Claim 34, which has a sedimentation time of less than 15 minutes.
36. A catalyst system which comprises
 a catalyst according to any one of Claims 20 to 35 inclusive; and
 an aluminium compound, as a co-catalyst.
- 20 37. A catalyst system according to Claim 36, wherein the co-catalyst is triethyl aluminium.
38. A catalyst system according to Claim 36 or Claim 37, which has a productivity greater than 10000 grams of polymer/gram of catalyst.
- 25 39. A catalyst system according to any one of Claims 36 to 38 inclusive which, when used for terpolymerization of a monomer feedstock comprising ethylene and two alpha olefins each having a total carbon number between 4 and 8 and whose total carbon numbers differ by one, has the





ability to incorporate in the terpolymer amounts of these monomers which differ less than 25% from the proportions of these monomers in the feedstock.

5 40. A catalyst system according to any one of Claims 36 to 39 inclusive, which gives a polydispersity index below 4 when used in a copolymerization or terpolymerization of ethylene with alpha olefin(s).

10 41. A method of polymerization, which method comprises reacting at least one olefin in the presence of a catalyst according to any one of Claims 20 to 35 inclusive, or a catalyst system according to any one of Claims 36 to 40 inclusive, thereby to obtain a polymer of the olefin.

15 42. A method of polymerization according to Claim 41, wherein the reaction is effected in a single reaction zone, at a pressure between atmospheric pressure and 200kg/cm², and at a reaction temperature between ambient and 120°C.

20 43. A method of polymerization according to Claim 41 or Claim 42, wherein two olefins are reacted, as monomers, to produce a copolymer.

 44. A method of polymerization according to Claim 43, wherein one of the monomers is ethylene.

25 45. A method of polymerization according to Claim 41 or Claim 42, wherein three olefins are reacted, as monomers, to produce a terpolymer.

 46. A method of polymerization according to Claim 45, wherein one of the monomers is ethylene.

 47. A method of polymerization according to Claim 46, wherein another of the monomers is 1-pentene.





48. A method of polymerization, which method comprises reacting a plurality of olefins, as monomers, in the presence of a magnesium chloride supported titanium catalyst obtained by mixing an ether having a total number
5 of carbon atoms equal to or greater than 8, with magnesium chloride, to produce partially activated magnesium chloride; mixing an alkyl aluminium with the partially activated magnesium chloride to form unwashed activated magnesium chloride; washing the activated magnesium
10 chloride with an inert saturated hydrocarbon liquid, to obtain an activated magnesium chloride-containing slurry; mixing the same number of alcohols as there are monomers and which alcohols have, respectively, the same number of carbon atoms as the respective monomers, with the activated
15 magnesium chloride-containing slurry to form an activated magnesium chloride/alcohol complex; and mixing titanium tetrachloride with the activated magnesium chloride/alcohol complex, to form the magnesium chloride supported catalyst, thereby to obtain a polymer of the olefins.

20 49. A method of polymerization according to Claim 48, wherein two olefins are reacted, as the monomers, to produce a copolymer, with two alcohols thus being mixed with the activated magnesium chloride-containing slurry, and with the alcohols being used in the form of a
25 dicomponent alcohol mixture.

50. A method of polymerization according to Claim 47, wherein three olefins are reacted, as the monomers, to produce a terpolymer, with three alcohols thus being mixed with the activated magnesium chloride-containing slurry,
30 and with the alcohols being used in the form of a tricomponent alcohol mixture.

51. A novel method of making a catalyst, substantially as described and exemplified herein.





WO 97/45460

PCT/GB97/01480

48

52. A novel catalyst, substantially as described and exemplified herein.

53. A novel catalyst system, substantially as described and exemplified herein.

5 54. A novel method of polymerization, substantially as described and exemplified herein.

This Sheet Has Been Replaced



AMENDED SHEET (ARTICLE 19)