

Description

The present invention relates to foamed particles of homopolymers and copolymers of propylene. Propylene polymers have excellent heat resistance, chemical resistance, and rigidity, and have further excellent properties which polystyrene and polyethylene do not have. Polystyrene and polyethylene are widely used as raw materials to make foamed substances in various fields, in which their properties are respectively exhibited. However, propylene-type polymers, although having the above-mentioned excellent properties, have not been fully utilized for making foamed particles.

We have therefore investigated raw materials for obtaining foamed substances which have a chemical resistance and flexibility substantially equal to those of foamed polyethylene, and further having high heat resistance which cannot be attained by polyethylene or polystyrene-type foamed substances, and methods for manufacturing foamed particles from such materials.

EP—A—0071981 describes particles of a polypropylene resin which have been foamed with a volatile blowing agent; the resin used can be, e.g. conventional propylene homopolymer or a random copolymer of propylene and ethylene, and is preferably cross-linked; such polymers have high stereo-regularity.

EP—A—0144039 was published on 12 June 1985, after the priority date of the present application and describes particles of a non-cross-linked polypropylene resin derived from a non-cross-linked random copolymer of propylene and an α -olefin having a heat of crystallisation of 5 to 15 cal/gram and having a high temperature peak in their differential scanning calorimetry curve.

Both type of prior particles are used by being heated in a mold to make foamed shaped articles. In the present invention, specific types of propylene resin are used which are different in crystal structure from those used previously.

By using propylene-type polymers as defined by the present invention, foamed particles in which the excellent properties of polypropylene are fully exhibited and which are satisfactory in blowing control are obtained.

The present invention is directed to foamed particles of propylene-type polymer of substantially non-crosslinked type, wherein specific propylene type polymer particles have a Melt Index (MI) of from 0.1 to 20 and are foamed with the use of an evaporation type blowing agent.

Foamed substances according to the present invention can be widely used in various fields by utilizing their excellent heat resistance, chemical resistance and impact resistance; that is, the foamed substances can be used as various materials such as, for example, heat insulating materials for steam pipes, etc. which require heat resistance, cushioning materials for various machines which have a risk of adhesion or flow-out of oil-like matter; and protective materials for various large-size machines.

Heretofore, it has been considered that cross-linking by electron beams or peroxide is indispensable for high-blowing of polypropylene in view of the known properties of foamed polyethylene. This is because, generally speaking, the melt viscoelasticity of polypropylene is considerably reduced at a temperature above its melting point, as is that of polyethylene, and there are difficulties in the control of the blowing since its ability to hold an evaporation-type blowing agent is lower than that of polystyrene.

Accordingly, the control of crosslinking is indispensable for blowing resins at a high temperature above the melting point of the resins by means of a decomposition type blowing agent such as azodicarbonamide.

Generally, when blowing is carried out with an evaporation-type blowing agent, the blowing is conducted at a temperature relatively lower than when using a decomposition type blowing agent, but the blowing ability is determined by the balance between the pressure of gas due to evaporation of the blowing agent and the visco-elasticity of the polymer being foamed.

Namely, if the viscoelasticity of the polymer is excessively low at its blowing temperature, the material cannot resist the gas pressure so that the blowing cannot be performed at a high multiplication factor since much of the blowing agent is lost, and also, coarse foam is produced. On the other hand, in the case of an excessive viscoelasticity, the amount of deformation of the resin is small so that blowing at a high multiplication factor also cannot be performed. In order to obtain separate foamed particles having a high blowing multiplication factor, the resin should have a suitable viscoelasticity at its blowing temperature. For ease of control of blowing, the temperature range in which a suitable viscoelasticity is exhibited should be wide.

We have therefore studied the blowing of propylene-type polymer particles with the use of evaporation type blowing agents, and have found that highly foamed substances can be obtained with a satisfactory controllability of blowing without any crosslinking being applied, by selecting initial polymers, referred to herein as base materials, which have suitable viscoelastic properties in the vicinity of the blowing temperature. Generally, since homopolypropylene has a high melting point of above 160°C, and also has a very high viscoelasticity in comparison with that of polyethylene at a temperature below the melting point, it is not so practical to blow this polymer at about its melting point since a considerably high pressure is necessary. Accordingly, in view of the above-mentioned consideration, the invention provides particles of a polymer which have been foamed with volatile blowing agent and are not cross-linked, characterised in that the polymer has a Melt Index of 0.1 to 20 and is of one of the following propylene polymers obtainable by polymerisation in a gaseous medium under conditions that the gas is not liquefied in the reaction:

(a) a soft polypropylene homopolymer having an <mmmm> partial rate (measured by ¹³C nuclear

magnetic resonance) of the stereo-regular central pentad chain of 45 to 85% and a fusion heat quantity of 21 to 92 joules per gram (5 to 22 calories per gram);

(b) a random copolymer of propylene and an α -olefin of 4 or more carbon atoms in amount of 7 to 30 mol % and optionally up to 5 mol % of ethylene, the proportion of copolymer which is soluble in xylene at 20°C being 15 to 60% by weight.

Thus when the above-mentioned polymer is selected for the base material particles and is foamed with the use of an evaporation type blowing agent, foamed particles having a high multiplication factor can be obtained without any crosslinking being applied. The material with less than 0.1 MI is low in blowability, and the material with larger than 20 MI is low in strength of the foamed substance. Therefore, these materials are not suitable as raw materials for the present invention. It is noted here that, with the soft homopolypropylene (a), the stereoregular pentad partial rate is measured by the method utilizing ^{13}C -NMR spectrum proposed by A. Zambelli et al, *Macromolecules*, Vol. 6, p. 925 (1973), and the <mmmm> pentad partial rate is a partial rate of monomeric unit which exists in the center of isotactic chain, or, in other words, the chain in which five propylene monomers are mesocoupled in series. The homopolypropylene having such a partial rate of less than 45% or a fusion heat quantity of less than 21 J/g (5 cal/g) does not exhibit the properties of polypropylene, substantially. Meanwhile, the one having a pentad partial rate of more than 85% or a fusion heat quantity of more than 92 J/g (22 cal/g) is nearly equal to normal homopolypropylene, so that it cannot be used as a base resin according to the present invention in view of the controllability of blowing. Next, in the copolymer corresponding to (b), an α -olefin having a carbon number of 4 or more is used, or, in addition to this, a slight amount of ethylene is also used as a comonomer. As the α -olefin having a carbon number of 4 or more, butene-1, pentene-1, hexene-1, 4-methylpentene-1 may be used solely or combined, with butene-1 being preferable. The content of the α -olefin in the copolymer is from 7 to 30 mol%, and preferably from 10 to 25 mol%. Below 7 mol% the softness of the base material is lost, so that it is not suitable for high-blowing, and above 30 mol% the powder characteristic upon copolymerization is deteriorated so that stable manufacture thereof becomes difficult.

The cold xylene-soluble matter (CXS) of propylene-copolymer used in the present invention is from 15 to 60 wt%, and preferably from 20 to 50 wt%. In the copolymer whose CXS is below 15 wt%, the softness of the copolymer deteriorates so that it is not suitable for high-blowing. The copolymer whose CXS is above 60 wt% does not exhibit, in the foamed substance, the characteristics which polypropylene normally has.

The propylene-type polymers used in the present invention are preferably manufactured by what is called a gas-phase polymerizing method.

Such a method is used because if a polymerizing method using an inert hydrocarbon as a solvent is used, a large amount of soluble polymers are produced, which is not only economically disadvantageous, but also produces no soft polymer which meets the requirements of the present invention. The polymerization may be effected with the use of a fluidized bed type reactor, a stirring type reactor, a fluidic type reactor provided with an agitator, etc.

The polymerization should be carried out under pressure and temperature conditions such that gas will not be liquified in the reactor and polymer particles will not be fused and aggregated into a mass, a particularly preferable condition being at a temperature of 40 to 100°C and at a pressure of 9.8 to 490×10^4 Pa (1 to 50 kg/cm² (G)). Catalyst systems used for the manufacturing of polymer used in present invention are catalysts for α -olefin stereoregular polymerization, such as, for example, a catalyst having, as a main component, TiCl_3 , $\text{TiCl}_3 \cdot 1/3\text{AlCl}_3$, or a catalyst consisting of a solid catalyst component such as, for example, a carrier carrying catalyst in which a Ti compound is carried by magnesium chloride, an organoaluminum catalyst, and a third component, as necessary, such as, for example, an electron donative chemical compound.

The catalyst components can be pre-treated with a small amount of an olefin in the presence of an organoaluminum compound or an electron donative chemical compound, and prepolymerized before copolymerization.

The evaporation type blowing agents used in the present invention include, for example, straight chain aliphatic hydrocarbons such as propane, butane or pentane, hexane, alicyclic hydrocarbons such as cyclobutane or cyclopentane; and halogenated hydrocarbons such as trichlorofluoromethane, dichlorodifluoromethane or dichlorotetrafluoroethane. These blowing agents are added in an amount of from 2 to 25 wt% with respect to the base material particles, although the amount may vary depending upon the kinds and blowing conditions of the agents used.

In order to add the blowing agent, (i) the base material particles can be put into a closed container into which the blowing agent is directly added so as to be impregnated into the particles; (ii) the particles can be dispersed in water within a closed container, and the blowing agent is press-charged thereinto with agitation; (iii) base material particles containing therein the blowing agent can be taken into a pressure-resistant container and blown by steam having a predetermined pressure; or (iv) the impregnation of the blowing agent is conducted at its blowing temperature in an aqueous suspension medium under agitation, and the base material particles are blown by the discharging pressure after completion of the impregnation.

In order to obtain foamed particles, in a foamed substance, which are uniform and fine in particle size, inorganic particles may be added to the polymer.

As inorganic substances having such a foam regulating effect, there may be used inorganic calcium salts such as calcium sulfate, calcium carbonate or calcium silicate, silica, magnesium silicate or active alumina. Additionally higher fatty acid metal salts such as calcium stearate may be used in a small amount.

Upon granulation of the base particles, 0.1 to 2 wt% of the foam regulating agent is desirably added and kneaded into the resin.

The present invention will now be illustrated by the following Examples.

In the Examples the melt index (MI), the fusion heat quantity (ΔH_m), the cold xylene-soluble matter (CXS) and the apparent density of the foamed substance mentioned were measured by the methods described below:

1) Melt index

Measurement was made in accordance with JIS K6785.

2) Fusion heat quantity (ΔH_m)

A sample weighing above 10 mg was disposed in a DSC sample chamber (DSC Model 2 manufactured by Perkins Elmer Co.), being held therein at 190°C for 10 minutes, and thereafter, after lowering the temperature at a rate of 5°C/min down to 30°C, the temperature was raised at a rate of 10°C/min. The fusion peak area of the sample upon raising of the temperature was compared with that of the indium standard sample (26.21 J/g=6.75 cal/g) to calculate the heat quantity.

3) Cold xylene-soluble matter (CXS)

After 1 g of polymer was dissolved in 200 ml boiling xylene, the solution was slowly cooled down to 50°C, and then, was poured into ice water while being stirred to be cooled down to 20°C. After being held for 3 hours at 20°C, precipitated polymer was filtered out. The xylene was evaporated from the filtrate, which was then dried under vacuum at 60°C, so that the polymer which is soluble in xylene at 20°C was recovered and weighed.

4) Pursuant to JIS K6767, the weight and volume of the foamed substance was measured.

5) The $\langle mmm \rangle$ partial rate was obtained from 100 MHz NMR.

Example 1

(1) Preparation of solid catalyst

After taking a solution consisting of 60 ml of titanium tetrachloride and 228 ml of n-heptane into an one liter volume flask purged with argon, an n-heptane solution (300 ml) of ethylaluminum sesquichloride (136.6 ml) was added dropwise thereto at a temperature of from -5 to -10°C over 2 hours. After completion of the dropwise addition, the solution was stirred at room temperature, (i.e., about 20-30°C) for 30 minutes, and was heat-treated at 80°C for one hour. After solid-liquid separation by leaving it at room temperature, the solid part was washed with 400 ml of n-heptane four times.

Next 580 ml of n-heptane and 5 ml of diethylaluminum chloride were filled into the flask, and maintained at 50°C. 32 g of propylene was gradually added at 50°C over 2 hours while being stirred, to be prepolymerized. After solid-liquid separation, the washing was repeated twice with the use of 400 ml of n-heptane. Then, 117 ml of n-butyl ether and 3.7 ml of tri-n-octyl aluminum were added under agitation into 392 ml of toluene filled in the flask and maintained at 85°C, to conduct reaction for 15 minutes. After reaction, a solution prepared by dissolving 15.5 g of iodine in 196 ml of toluene was added into the flask and reaction was carried out at 85°C for 45 minutes. After reaction, solid-liquid separation was conducted, washing was conducted once with the use of 500 ml of toluene, and then was repeated three times with 500 ml of n-heptane. Thereafter, by drying under reduced pressure, 90 g of a solid catalyst containing titanium trichloride was obtained. In this solid catalyst containing titanium trichloride, 65.2 wt% of titanium trichloride was contained.

(2) Polymerization

Polymerization was conducted with the use of a fluidized bed type reactor having an internal volume of 1 m³, provided with an agitator. At first, 60 kg of polypropylene particles for dispersing the catalyst were fed into the reactor, which was then purged with nitrogen and thereafter was supplied with propylene. The pressure was raised to 49.1×10⁴ Pa (5 kg/cm² (G)) with propylene, and circulating gas was fed at a flow rate of 80 m³/hr from the lower section of the reactor to maintain the polymer particles in a fluid condition, and then the catalysts indicated below were fed into the reactor. The catalyst components (b) and (c) were used in solutions obtained by diluting with heptane:

(a) solid catalyst containing therein titanium trichloride	21 g
(b) diethylaluminum chloride	112 g
(c) triethylaluminum	11 g
(d) methyl methacrylate	8 g

Then hydrogen and propylene were fed to obtain a hydrogen concentration of 1.7 vol%, and the pressure was raised to 9.807×10^3 Pa (10 kg/cm² (G)) while the temperature of the fluidized bed was adjusted to 65°C to initiate polymerization. During polymerization, the hydrogen concentration and pressure were maintained constant. When the bulk of the polymerization reached 75 kg, 60 kg of polymer particles were left in the reactor for the next dispersion of catalyst, and the remaining copolymer particles were poured into a stirring type mixing tank into which 210 g of propylene oxide and 100 g of methanol were added. Thereafter, treatment was made at 80°C for 30 minutes. Then the particles were dried, and a white powder-like polymer was obtained.

10 3) Method of manufacturing foamed particles

0.5 wt% of calcium silicate and 0.1 wt% of calcium stearate, as foam regulating agents, were added and kneaded into propylene homopolymer (MI=1.3) obtained in the step (2) and having an <mmmm> partial rate of 65% in stereoregular pentad partial rate by ¹³C-NMR spectrum and a fusion heat quantity of 42 J/g (10 cal/g), so as to be powdered to obtain polypropylene base material particles. 100 parts of base material particles, 300 parts of water, one part of a suspending agent, magnesium pyrophosphate, and 30 parts of n-butane were added into a pressure resistant container, and the system was maintained at 130°C, and was stirred for 2 hours. Leaving the system maintained at 130°C, one end of the container was opened so that uniform and fine particles were obtained. The apparent density of the foamed particles was 0.03 g/cm³.

20 Example 2

100 parts of base material particles, which were the same as described above Example 1, 300 parts of water, one part of a suspending agent, magnesium pyrophosphate, and 20 parts of n-butane were taken into a pressure resistant container, and were cooled down to room temperature after agitation at 60°C for 5 hr, to obtain foamable particles containing therein 14 wt% butane. These were heated by steam at 16.7×10^4 Pa (1.7 kg/cm² (G)) for 40 seconds, and uniform and fine foamed particles were obtained. The apparent density of the foamed particles was 0.05 g/cm³.

Comparison Examples 1 and 2

30 Base material particles were obtained by the same method as in Example 1, except that homopolypropylene (MI=2) having a cold xylene-soluble matter of 8% was used as the raw material polypropylene. The thus obtained base material particles were impregnated with n-butane at 90°C in the same manner as described in Example 2, to obtain foamable particles containing therein 7 wt% of butane. The particles were blown by steam at 16.7×10^4 Pa (1.7 kg/cm² (G)) and 36.3×10^4 Pa (3.7 kg/cm² (G)), respectively. However, the apparent density of the foamed particles were 0.67 g/cm³ and 0.33 g/cm³, respectively, which were very low, and therefore, foamed substances of high multiplication factor could not be obtained.

Comparison Example 3

40 As a raw material polypropylene, a homopolymer (MI=5) having an mmmm partial rate of 25 and a fusion heat quantity of 12.6 J/g (3 cal/g) was used, and the pressure of steam was set at 12.7×10^4 Pa (1.3 kg/cm² (G)). All other conditions were the same as those in Comparison Examples 1 and 2, so as to obtain foamed particles. The apparent density of the foamed particles was low, 0.10 g/cm³, and a foamed substance having a high multiplication factor could not be obtained.

45 The features of Examples 1 and 2 and the Comparison Examples 1 to 3 are shown in Table 1.

TABLE 1

	Example 1	Example 2	Comparison Example 1*	Comparison Example 2*	Comparison Example 3*
MI	1.3	1.3	2	2	5
<mmmm> Partial rate (%)	65	65	91	91	25
Fusion heat quantity (J/g) (cal/g)	41.8 10	41.8 10	109 26	109 26	12.5 3
Blowing agent impregnating temp. (°C)**	130	60	90	90	40
Blowing agent impregnating time (hr)	2	5	5	5	2
Blowing agent impregnating amount (wt%)	—	14	7	7	21
Steam pressure ($\text{Pa} \times 10^4$) (kg/cm^2 (G))	— —	16.7 1.7	16.7 1.7	36.3 3.7	12.7 1.3
Blowing by steam					
Blowing time (sec)	—	40	40	40	25
Apparent density of foamed particles (g/cm^3)	0.03	0.05	0.67	0.33	0.10
Shape of foamed particles	Uniform, fine	Uniform, fine	High density foams	High density foams	Coarse foams, large con- traction

*: Steam pressure alone was changed.

**: In the step of impregnating the blowing agent, 25 parts of n-butane as a blowing agent was used with respect to the base material particles.

Example 3

As a comonomer, butene-1 was used in the polymerization. A polymerizing reaction was carried out in the same method as described in Example 1, except that a mixed gas of propylene/butene-1 (volume ratio=60/40), instead of solely propylene, was fed into the polymerizing system. Propylene/butene-1 copolymer containing therein 16 mol% of butene-1 was obtained.

The MI of this copolymer was 2.0 and the cold xylene-soluble matter thereof was 42%.

The same foam regulating agent as described in Example 1 was added and kneaded into this copolymer and then used as base material particles. 100 parts of base material particles, 300 parts of water, one part of magnesium pyrophosphate, and 25 parts n-butane were taken into a pressure resistant container, and, after being stirred at 50°C for 3 hours, were cooled down to room temperature, whereby foamable particles containing therein 17 wt% of n-butane were obtained. The foamable particles were heated for 40 seconds by means of steam at 15.7×10^4 Pa (1.6 kg/cm² (G)), whereby uniformly and finely foamed particles having an apparent density of 0.05 g/cm³ were obtained.

Example 4

A polymerizing reaction was carried out in the same manner as described in Example 1, except that butene-1 and ethylene were used together as a copolymer and a mixed gas of propylene/butene-1/ethylene (volume ratio=55/38/7) was fed into a polymerizing system, whereby a propylene/butene-1/ethylene terpolymer containing 17 mol% of butene-1 and 2 mol% of ethylene was obtained. The MI of this terpolymer was 3.5, and the cold xylene-soluble matter thereof was 40%.

This terpolymer was granulated after the foam regulating agent was added thereto, as described in Example 1, so that base material particles were obtained. 100 parts of base material particles, 300 parts of water, one part of magnesium pyrophosphate, and 25 parts of n-butane were taken into a pressure-resistant container, were stirred at 60°C for 4 hours, and then were cooled down to room temperature, so that foamable particles containing therein 20 wt% of n-butane were obtained. The thus obtained foamable particles were heated for 30 seconds with the use of steam having a pressure of 14.7×10^4 Pa (1.5 kg/cm² (G)), so that uniformly and finely foamed particles were obtained. The apparent density of the foamed particles was 0.04 g/cm³.

Comparison Examples 4 to 7

In Example 3, the content of comonomer and the blowing condition were changed as indicated in Table 2.

The conditions used in Examples 3 and 4 and Comparison Examples 4 to 7 and the results obtained are shown in Table 2.

TABLE 2

	Example 3	Example 4	Comparison Example 4	Comparison Example 5	Comparison Example 6	Comparison Example 7
MI	2.0	3.5	2.0	1.6	36	0.05
Kind	Butene-1	Butene-1/ ethylene	Butene-1	Butene-1	Butene-1	Butene-1
Comonomer	16	17/2	41	1.7	15	11
Content (mol%)						
Cold xylene-soluble matter (wt%)	42	40	96	9	41	35
Blowing agent impregnating temp. (°C)**	50	60	40	90	60	90
Blowing agent impregnating time (hr)	3	4	2	4	4	4
Blowing agent impregnating amount (wt%)	17	20	23	10	18	14
Blowing by steam						
Steam pressure ($\text{Pa} \times 10^4$) (kg/cm^2 (G))	15.7 1.6	14.7 1.5	12.7 1.3	16.6 1.7	16.6 1.7	19.6 2.0
Blowing time (sec)	40	30	20	40	30	40
Apparent density of foamed particles (g/cm^3)	0.05	0.04	0.28	0.26	0.06	0.10
Shape of foamed particles	Uniform, fine	Uniform, fine	Coarse foams, large con- traction	High density foams	Fragile foams	High density foams

** : In the step of impregnating the blowing agent, 25 parts of n-butane as a blowing agent was used with respect to the base material particles.

Claims

1. Particles of a polymer which have been foamed with volatile blowing agent and are not cross-linked, characterised in that the polymer has a Melt Index of 0.1 to 20 and is one of the following propylene polymers obtainable by polymerisation in a gaseous medium under conditions that the gas is not liquefied in the reaction:
 - (a) a soft polypropylene homopolymer having an <mmmm> partial rate (measured by ^{13}C nuclear magnetic resonance) of the stereo-regular central pentad chain of 45 to 85% and a fusion heat quantity of 21 to 92 Joules per gram (5 to 22 calories per gram);
 - (b) a random copolymer of propylene and an α -olefin of 4 or more carbon atoms in amount of 7 to 30 mol% and optionally up to 5 mol% of ethylene, the proportion of copolymer which is soluble in xylene at 20°C being 15 to 60% by weight.
2. Foamed particles as claimed in Claim 1, wherein in the copolymer (b) the olefin is butene-1.
3. Foamed particles as claimed in Claim 1 or 2, wherein in the copolymer (b) the content of the olefin is 10 to 25 mol%.
4. Foamed particles as claimed in Claim 1, 2 or 3, wherein the polymerization was at a temperature of 40°C to 100°C and a pressure of 1 to 50 kg/cm² gauge.
5. Foamed particles as claimed in any preceding claim, wherein the amount of the volatile blowing agent used was 2 to 25 wt% of the polymer.

Patentansprüche

1. Teilchen eines Polymerisates, die mit einem flüchtigen Treibmittel geschäumt wurden und nicht vernetzt sind, dadurch gekennzeichnet, daß das Polymerisat einen Schmelzindex von 0,1 bis 20 aufweist und eines der folgenden Propylen-Polymerisate ist, die durch Polymerisation in einem gasförmigen Medium unter Bedingungen erhältlich sind, daß das Gas bei der Umsetzung nicht verflüssigt wird:
 - (a) ein weiches Polypropylen-Homopolymerisat mit einer <mmmm>-Teilrate (gemessen durch ^{13}C kernmagnetische Resonanz) der stereoregulären zentralen Pentade-Kette von 45 bis 85% und eine Schmelzwärme - Menge von 21 bis 92 Joules pro Gramm (5 bis 22 Kalorien pro Gramm);
 - (b) ein statistisches Copolymerisat von Propylen und einem α -Olefin mit vier oder mehr Kohlenstoffatomen in einer Menge von 7 bis 30 Mol-% und gegebenenfalls bis zu 5 Mol-% Äthylen, wobei der Anteil des Copolymerisates, der in Xylol bei 20°C löslich ist, 15 bis 60 Gew.-% beträgt.
2. Geschäumte Teilchen nach Anspruch 1, wobei in dem Copolymerisat (b) das Olefin Buten-1 ist.
3. Geschäumte Teilchen nach Anspruch 1 oder 2, wobei in dem Copolymerisat (b) der Gehalt an dem Olefin 10 bis 25 Mol-% beträgt.
4. Geschäumte Teilchen nach Anspruch 1, 2 oder 3, wobei die Polymerisation bei einer Temperatur von 40 bis 100°C und einem Überdruck von 1 bis 50 kg/cm² erfolgte.
5. Geschäumte Teilchen nach einem der vorangehenden Ansprüche, wobei die verwendete Menge des flüchtigen Treibmittels 2 bis 25 Gew.-% des Polymerisates betrug.

Revendications

1. Particules d'un polymère, qui ont été transformées en mousse avec un agent gonflant volatil et qui ne sont pas réticulées, caractérisées en ce que le polymère a un indice de fusion de 0,1 à 20 et est un des polymères de propylène ci-après pouvant être obtenus par polymérisation dans un milieu gazeux dans des conditions telles que le gaz ne soit pas liquéfié lors de la réaction:
 - (a) un homopolymère de polypropylène mou ayant un taux partiel [mmmm] (mesuré par résonance magnétique nucléaire ^{13}C) de la chaîne pentade centrale stéréorégulière de 45 à 85% et un degré de chaleur de fusion de 21 à 92 joules par g (5 à 22 calories/gramme);
 - (b) un copolymère statistique de propylène et d'une alpha-oléfine contenant 4 atomes de carbone ou plus, en une quantité de 7 à 30% molaires et éventuellement jusqu'à 5% molaires d'éthylène, la proportion du copolymère soluble dans le xylène à 20°C, étant de 15 à 60% en poids.
2. Particules transformées en mousse selon la revendication 1, caractérisées en ce que, dans le copolymère (b), l'oléfine est le butène-1.
3. Particules transformées en mousse selon la revendication 1 ou 2, caractérisées en ce que dans le copolymère (b), la teneur de l'oléfine est de 10 à 25% molaires.
4. Particules transformées en mousse selon la revendication 1, 2 ou 3, caractérisées en ce que la polymérisation a lieu à une température de 40 à 100°C et sous une pression de 1 à 50 kg/cm² manométrique.
5. Particules transformées en mousse selon l'une quelconque des revendications précédentes, caractérisées en ce que la quantité de l'agent gonflant volatil utilisé est de 2 à 25% en poids du polymère.

