

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 May 2005 (06.05.2005)

PCT

(10) International Publication Number
WO 2005/040301 A1

(51) International Patent Classification⁷: **C09K 7/02**

(21) International Application Number:
PCT/EP2004/011827

(22) International Filing Date: 15 October 2004 (15.10.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03078278.3 17 October 2003 (17.10.2003) EP

(71) Applicant (for all designated States except US): **AKZO NOBEL N.V.** [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **VAN DER HORST, Peter, Marten** [NL/NL]; Hagemanswei 92, NL-6843 XN Arnhem (NL).

(74) Agent: **SCHALKWIJK, Pieter, Cornelis**; Akzo Nobel N.V., Intellectual Property Department (Dept. AIP), P.O. Box 9300, NL-6800 SB Arnhem (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: USE OF CMC IN DRILLING FLUIDS

(57) Abstract: The invention relates to a water-based drilling fluid composition comprising a carboxymethyl cellulose (CMC), wherein the CMC is characterized by forming a gel at 25°C after high-shear dissolution in a 0.3 wt% aqueous sodium chloride solution, the final content of the CMC in the aqueous sodium chloride solution being 1 wt% for a CMC having a degree of polymerization (DP) of >4,000, 1.5 wt% for a CMC having a DP of >3,000-4,000, 2 wt% for a CMC having a DD of 1,500-3,000, and 4 wt% for a CMC having a DP of <1,500, the gel being a fluid having a storage modulus (G') which exceeds the loss modulus (G'') over the entire frequency region of 0.01-10 Hz when measured on an oscillatory rheometer operating at a strain of 0.2.



WO 2005/040301 A1