FIGURE 1




Acetaminophen 10%w/w, HPC-SL 2.5%w/w and Docusate Sodium 0.1%w/w NCD
LESR-1099-161 (sample 2)
NanoMill 01 + 10ml chamber. Milled for 90 mins @ 2500rpm
100x phase objective using immersion oil

FIGURE 2


Anetanthoplech 10%m:w. Plasdone K29/32 2.5%m:w and
Sodium Taurol Sulfide 0.1%w/w NCT
TKSR-1111-165
Nano Mill 01 .5ml chamber. Milled for 90 mins @ 3333rpm
100x phase objective using immersion oil