

LUBRICANT PRODUCTION BY HYDROISOMERIZATION OF SOLVENT
EXTRACTED FEEDSTOCKS

5 The present invention relates to a process for
the production of lubricants and more particularly,
to a process for the production of hydrocarbon
lubricants of high viscosity index.

10 Mineral oil lubricants are derived from various
crude oil stocks by a variety of refining processes
which are directed towards obtaining a lubricant base
stock of suitable boiling point, viscosity, viscosity
index (VI) and other characteristics. Generally, the
base stock will be produced from the crude oil by
distillation of the crude in atmospheric and vacuum
distillation towers, followed by the separation of
15 undesirable aromatic components and finally, by
dewaxing and various finishing steps. Because
aromatic components lead to high viscosity, poor
viscosity indices and poor oxidative stability, the
use of asphaltic type crudes is not preferred as the
20 yield of acceptable lube stocks will be extremely low
after the large quantities of aromatic components
contained in such crudes have been separated out;
paraffinic crude stocks will therefore be preferred
but aromatic separation procedures will still be
25 necessary in order to remove undesirable aromatic
components. In the case of the lubricant distillate
fractions, generally referred to as the neutrals,
e.g. heavy neutral, light neutral, etc., the
aromatics will be extracted by solvent extraction
30 using a solvent such as phenol, furfural or N-
methylpyrrolidone (NMP) or another material which is
selective for the extraction of the aromatic
components. If the lube stock is a residual lube
stock, the asphaltenes will first be removed in a
35 propane deasphalting step followed by solvent
extraction of residual aromatics to produce a lube

generally referred to as bright stock. In either case, however, a dewaxing step is normally necessary in order for the lubricant to have a satisfactorily low pour point and cloud point, so that it will not
5 solidify or precipitate the less soluble paraffinic components under the influence of low temperatures.

A number of dewaxing processes are known in the petroleum refining industry and of these, solvent dewaxing with solvents such as methylethylketone
10 (MEK) and liquid propane, has been the one which has achieved the widest use in the industry. Recently, however, proposals have been made for using catalytic dewaxing processes for the production of lubricating oil stocks and these processes possess a number of
15 advantages over the conventional solvent dewaxing procedures. The catalytic dewaxing processes which have been proposed are generally similar to those which have been proposed for dewaxing the middle distillate fractions such as heating oils, jet fuels
20 and kerosenes, of which a number have been disclosed in the literature, for example, in Oil and Gas Journal, January 6, 1975, pp. 69-73 and U.S. Patents Nos. RE 28,398, 3,956,102 and 4,100,056. Generally, these processes operate by selectively cracking the
25 longer chain end paraffins to produce lower molecular weight products which may then be removed by distillation from the higher boiling lube stock. The catalysts which have been proposed for this purpose have usually been zeolites which have a pore size
30 which admits the straight chain, waxy n-paraffins either alone or with only slightly branched chain paraffins but which exclude more highly branched materials and cycloaliphatics. Zeolites such as ZSM-5, ZSM-11, ZSM-12, ZSM-22, ZSM-23, ZSM-35 and ZSM-38
35 have been proposed for this purpose in dewaxing

processes, as described in U.S. Patent Nos.
3,894,938, 4,176,050, 4,181,598, 4,222,855, 4,229,282
and 4,247,388. A dewaxing process employing
synthetic offretite is described in U.S. Patent No.
5 4,259,174.

Although the catalytic dewaxing processes are
commercially attractive because they do not produce
quantities of solid paraffin wax which presently is
regarded as an undesirable, low value product, they
10 do have certain disadvantages and because of this,
certain proposals have been made for combining the
catalytic dewaxing processes with other processes in
order to produce lube stocks of satisfactory
properties. For example, U.S. Patent No. 4,181,598
15 discloses a method for producing a high quality lube
base stock by subjecting a waxy fraction to solvent
refining, followed by catalytic dewaxing over ZSM-5
with subsequent hydrotreatment of the product. U.S.
Patent No. 4,428,819 discloses a process for
20 improving the quality of catalytically dewaxed lube
stocks by subjecting the catalytically dewaxed oil to
a hydroisomerization process which removes residual
quantities of petrolatum wax which contribute to poor
performance in the Overnight Cloud Point test (ASTM
25 D2500-66). This process is intended to overcome one
disadvantage of the intermediate pore dewaxing
catalysts such as ZSM-5 which is that the normal
paraffins are cracked much faster than the slightly
branched chain paraffins and cycloparaffins so that,
30 although a satisfactory pour point is attained
(because the straight chain paraffins are removed)
residual quantities of branched chain paraffins and
cycloparaffins may be left in the oil, to contribute
to a poor performance in the Overnight Cloud Point
35 test when the oil is subjected to a relatively low

temperature for an extended period of time. During this time, the petrolatum wax which is made up of the less soluble slightly branched chain paraffins and cycloparaffins, nucleates and grows into wax crystals of a sufficient size to produce a perceptible haze. Although it would be possible to remove the petrolatum wax by operating the dewaxing process at a higher conversion so that these components were removed together with the straight chain paraffins, the yield loss which would result, has generally been considered unacceptable.

As mentioned above, the conventional catalytic dewaxing processes using intermediate pore size zeolites such as ZSM-5 operate by selectively cracking the waxy components of the feed. This results in a loss in yield since the components which are in the desired boiling range undergo a bulk conversion to lower boiling fractions which, although they may be useful in other products, must be removed from the lube stock. A notable advance in the processing of lube stocks is described in U.S. Patents Nos. 4,419,220 and 4,518,485, in which the waxy components of the feed, comprising straight chain and slightly branched chain paraffins, are removed by isomerization over a catalyst based on zeolite beta.

During the isomerization, the waxy components are converted to relatively less waxy isoparaffins and at the same time, the slightly branched chain paraffins undergo isomerization to more highly branched aliphatics. A measure of cracking does take place during the operation so that not only is the pour point reduced by reason of the isomerization but, in addition, the heavy ends undergo some cracking or hydrocracking to form liquid range

materials which contribute to a low viscosity product. The degree of cracking is, however, limited so as to maintain as much of the feedstock as possible in the desired boiling range. As mentioned
5 above, this process uses a catalyst which is based on zeolite beta, together with a suitable hydrogenation-dehydrogenation component which is typically a base metal or a noble metal, usually of group VIA or VIIIA of the Periodic Table of the Elements (the periodic
10 table used in this specification is the table approved by IUPAC), such as cobalt, molybdenum, nickel, tungsten, palladium or platinum. As described in U.S. 4,518,485, the isomerization dewaxing step may be preceded by a hydrotreating step
15 in order to remove heteroatom-containing impurities, which may be separated in an interstage separation process similar to that employed in two-stage hydrotreating-hydrocracking processes.

The zeolite beta dewaxing process has
20 significant advantages for dewaxing extremely waxy feeds, for example, Pacific and South-East Asian gas oils which may have upwards of 50 percent paraffins. Enhanced utilization of the properties of zeolite beta may, however, be secured by utilizing it in
25 combination with other processing steps. For example, European Patent Application Publication No. 225,053 (corresponding to U.S. Application Serial No. 793,937, filed 1 November 1985 and U.S. Pat. No. 4,919,788) utilizes an initial hydroisomerization
30 step using a zeolite beta catalyst followed by a selective dewaxing over ZSM-5 or ZSM-23 or even solvent dewaxing to produce a product of high V.I. and low pour point. The initial hydroisomerization effectively removes waxy components from the back end
35 of the feeds by isomerizing them to high V.I.

isoparaffins and the subsequent selective dewaxing step preferentially removes front end waxes to obtain the target pour point. Extremely waxy stocks such as slack wax and deoiled wax are of particular utility in this process, as described in U.S. Patent No. 4,975,177. Conventional high pressure hydroisomerization processes used in the production of very high V.I. lubes (120-145 V.I.) typically employ pressures over 1500 psig (about 10,440 kPa). See, for example, Developments in Lubrication PD19(2), 221-228 (Bull). Unlike these, the zeolite beta isomerization process operates well at low to moderate hydrogen pressures e.g. 300-1250 psig (about 2170-8720 kPa) and is therefore readily accommodated in existing low pressure refinery units e.g. Catalytic Hydrodesulfurization (CHD) units. In addition, the feed for the zeolite beta isomerization process may be obtained from various refinery streams including slack waxes and deoiled waxes as mentioned above as well as straight run gas oil (VGO) and deasphalted oil (DAO). The conventional high pressure process, however, usually employs wax feeds of specific character derived from aromatics extraction or hydrocracking of a crude prior to dewaxing.

Regardless of the nature of the feed, certain problems may arise. One is that a certain degree of cracking takes place during the isomerization process at the acidic sites on the zeolite beta catalyst. This cracking will cause dealkylation of some of the long chain alkyl substituted aromatic components so that cracking products including polycyclic aromatics within the lube boiling range but of extremely poor V.I. and oxidation stability are obtained. These components may adversely affect the properties of the

final lube product. In addition, a disparity between the pour point (ASTM D-97 or equivalent method e.g. Autopour) and cloud point (ASTM D-2500-66) may develop, as described above as a result of certain
5 waxes, primarily of a naphthenic character remaining in the oil after the isomerization-dewaxing step.

European Patent Application 0 464 547 discloses the preparation of high VI lubricants by treating a waxy feed which is hydrocracked to remove aromatic
10 components followed by hydroisomerization over a low acidity zeolite beta catalyst, e.g. Pt/zeolite beta which contains boron as a framework component to give a low alpha value. The removal of aromatics in the first step permits use of lower hydroisomerization
15 temperatures in the second step which limits 343°C+ (650°F+) conversion and enhances paraffin isomerization selectivity. However, it is necessary to further treat the hydroisomerized product by dewaxing, e.g., solvent dewaxing with
20 methylethylketone.

We have now devised a process for producing a high viscosity index (VI) lubricant from a hydrocarbon feed of mineral oil content having a paraffin content of at least 30 wt%, a nitrogen
25 content of at least 50 ppm, and an aromatics content of at least 10 wt% which comprises:

i) extracting the feed with a solvent which is selective for aromatics to provide an extracted feed containing greater than 40 wt% paraffins, less than
30 15 wt% aromatics, and less than 30 ppm nitrogen content, and

ii) hydroisomerizing the extracted feed with a low acidity zeolite beta catalyst having an alpha value of less than 15 and an inorganic oxide matrix

to provide a lubricant having a viscosity index of at least 110.

The present invention is of particular advantage in that it permits the preparation of high VI
5 lubricant from vacuum gas oils. Such feeds can include neutral gas oils, e.g., those having a boiling point range of 343 to 377°C (650 to 1250°F), preferably 399 to 565°C (750 to 1050°F). Waxy vacuum
10 gas oils which are treated by the extracting step i) exhibit characteristics similar to those of a heavy neutral slack wax feedstock, but with reduced aromatics content.

Figure 1 is a plot of 343°C+ (650°F+) lube yield (wt%) versus pour point (°F).

15 Feedstock

The feedstock for the present process may generally be characterized as a lube fraction prepared from a crude stock of suitable characteristics, e.g., by distillation in atmospheric
20 and vacuum towers. Such feedstocks have a paraffin content of at least 30 wt%, preferably at least 45 wt%, a nitrogen content of at least 50 ppm, preferably at least 100 ppm, and an aromatics content of at least 10 wt%, preferably at least 15 wt%.

25 Examples of such feedstocks include waxy gas oils, e.g., those having a boiling point range of 343 to 377°C (650 to 1250°F), preferably 399 TO 565°C (750 to 1050°F). Lubricant distillate fractions, generally referred to as the neutrals, e.g. heavy
30 neutral, light neutral, etc., contain aromatics which are extracted by solvent extraction using a solvent which is selective for the extraction of the aromatic components such as furfural, phenol or NMP. Other suitable feedstocks include fractionated visbreaker
35 343°C (650°F+) fraction from waxy resids, unconverted

343°C+ (650°F+) bottoms from FCC units processing waxy VGO or atmospheric resids.

5 Generally, the neutral stocks will have a viscosity in the range of 100 to 750 SUS (20 to 160 mm²/s) at 40°C (99°F) and in the case of a bright stock, the viscosity will generally be in the range of 1000 to 3000 SUS (210 to about 600 mm²/s) at 99°C (210°F).

10 The distillate (neutral) base stocks may generally be characterized as paraffinic in character, although they also contain naphthenes and aromatics and because of their paraffinic character, they are generally of fairly low viscosity and high viscosity index. The residual stocks such as bright
15 stock will be more aromatic in character and for this reason will generally have higher viscosities and lower viscosity indices. In general, the aromatic content of the stock will be in the range of 10 to 70 weight percent, usually 15 to 60 weight percent with
20 the residual stocks having the relatively higher aromatic contents, typically 20 to 70 weight percent, more commonly 30 to 60 weight percent and the distillate stocks having lower aromatic contents, for instance, 10 to 30 weight percent. Fractions in the
25 gas oil boiling range (315°C+(600°F+)) with an end point usually below about 565°C (about 1050°F) are a convenient feed because they can generally be treated by the present process to produce high quality lubes.

30 A typical highly paraffinic gas oil fraction which may be treated by the present process to form a high quality, high VI lube is a 345°-540°C (650°-1000°F) Minas gas oil. Highly paraffinic feeds such as this will generally have a pour point of at least 40°C; wax feeds such as slack wax will usually be
35 solid at ambient conditions.

Other high boiling fractions which may be used as feeds for the present process include synthetic lubricant fractions derived, for example, from shale oil by synthesis from natural gas, coal or other carbon sources.

The waxy feed may be hydrotreated before the hydroisomerization in order to remove heteroatom containing impurities and to hydrogenate at least some of the aromatics which may be present to form naphthenes. Inorganic nitrogen and sulfur formed during the hydrotreating may be removed by a conventional separation prior to the catalytic dewaxing. Conventional hydrotreating catalysts and conditions are suitably used as described in U.S. 4,919,788.

Aromatics Extraction

In the first step of the present process, the feed is subjected to extraction with a solvent which dissolves aromatics such as phenol, furfural or N-methylpyrrolidone (NMP), with furfural being especially preferred. Such extraction can be carried out in an extraction unit under suitable extraction conditions. Suitable extraction units include rotating disc contactors and packed beds. Preferably, the extraction is carried out in a continuous extraction unit having multiple stages, e.g. 3 to 10 stages, using 100 to 300 vol% of solvent, at temperatures ranging from 52 to 135°C (125 to 275°F), preferably 52 to 107°C (125 to 225°F).

The extraction may be carried out in a conventional manner with solvent:oil ratios and extraction temperatures and durations adjusted to achieve the desired degree of aromatics removal which is itself determined by the characteristics desired

in the final lube product, especially viscosity and oxidation stability.

5 The temperature and dosage of extraction solvent
in this step is controlled to provide high VI
products. Solvent:oil ratios of 1 to 5, preferably
1.5 to 2.5 (by weight), using furfural as the
solvent, are typical. The extracts provide a useful
source of sulfur-free or low-sulfur aromatic products
which can be recovered from the solvent by
10 conventional processing techniques such as
distillation.

 The solvent-free raffinate is thereafter passed
to the isomerization step of the present invention.

Isomerization

15 In the second step of the present process, the
raffinate of the first step is subjected to
isomerization over zeolite beta, a large pore,
siliceous zeolite catalyst. Although isomerization
does not require hydrogen for stoichiometric balance,
20 the presence of hydrogen is desirable in order to
promote certain steps in the isomerization mechanism
and also to maintain catalyst activity. Also,
because the isomerization steps entail hydrogenation
and dehydrogenation, the catalyst will contain a
25 hydrogenation-dehydrogenation component in addition
to the zeolite. A noble metal, preferably platinum
or palladium, is used to provide hydrogenation-
dehydrogenation functionality in the isomerization
catalyst in order to promote the desired
30 hydroisomerization reactions.

 The isomerization can be carried out in the
presence of hydrogen at a total pressure of at least
100 psig (740 kPa), preferably 200 to 1000 psig (1479
to 6991 kPa), at a temperature of 400 to 850°F (204
35 to 454°C), preferably 600 to 800°F (316 to 427°C).

The conversion to 650°F- (343°C-) product is generally not more than 70 weight percent, preferably not more than 50 weight percent, based on the feed to the isomerization step.

5 The isomerization catalyst comprises a noble metal/zeolite beta catalyst containing boron as a framework component of the zeolite, having an alpha value not greater than 15, preferably not greater than 10, and more preferably not greater than 5, said
10 alpha value being measured prior to incorporation of noble metal. The noble metal content ranges from 0.1 to 5 wt%, preferably from 0.5 to 2.0 weight percent based on the total weight of the catalyst.

15 Alpha value, or alpha number, of a zeolite is a measure of zeolite acidic functionality and is more fully described together with details of its measurement in U.S. Patent No. 4,016,218, J. Catalysis, 6, pp. 278-287 (1966) and J. Catalysis, 61, pp. 390-396 (1980). The experimental conditions
20 cited in the latter reference are used for characterizing the catalysts described herein. For present purposes, alpha is measured prior to incorporation of the hydrogenation/dehydrogenation component, of the zeolite, e.g., noble metal.

25 Noble metals, such as platinum and palladium, are employed in order to maximize the isomerization activity of the catalyst due to their strong hydrogenation function. Platinum may be incorporated into the catalyst by conventional techniques
30 including ion exchange with complex platinum cations such as platinum tetraammine or by impregnation with solutions of soluble platinum compounds, for example, with platinum tetraammine salts such as platinum tetraamminechloride. The catalyst may be subjected
35 to a final calcination under conventional conditions

in order to convert the noble metal to the oxide form and to confer the required mechanical strength on the catalyst. Prior to use the catalyst may be subjected to presulfiding, by established techniques.

5 In the isomerization step, conditions are optimized for hydroisomerization of the paraffins in the raffinate. For this purpose a low acidity catalyst with high isomerization selectivity is employed, and for this purpose, a low acidity zeolite
10 beta catalyst in which boron is present as a framework component of the zeolite beta has been found to give excellent results, particularly with respect to pour point and viscosity index. The boron is substituted for aluminum, preferably during
15 synthesis and thereby eliminates the acidity which would be associated with the tetrahedral aluminum.

 In addition to the hydrogenation component the hydroisomerization catalyst includes zeolite beta as an acidic (cracking) component. The pore structure
20 of zeolite beta gives it highly desirable selective properties. Zeolite beta is a known zeolite which is described in U.S. Patents Nos. 3,308,069 and RE 28,341, to which reference is made for further details of this zeolite, its preparation and
25 properties. The preferred forms of zeolite beta for use in the present process are the high silica forms, having a silica:alumina ratio of at least 30:1 and it has been found that ratios of at least 50:1 or even higher, for example, 100:1, 250:1, 500:1, may be used
30 to advantage because these forms of the zeolite are less active for cracking than the less highly siliceous forms so that the desired isomerization reactions are favored at the expense of cracking reactions which tend to effect a bulk conversion of
35 the feed, forming cracked products which are outside

the desired boiling range for lube components. Steamed zeolite beta with a higher silica:alumina ratio (framework) than the synthesized form of the zeolite is preferred. Suitable catalysts of this type used in the present process are described in U.S. Patents Nos. 4,419,220 and 4,518,485 and EP 225,053, to which reference is made for a more detailed description of these zeolite beta based catalysts. As mentioned in the two patents, the silica:alumina ratios referred to in this specification are the structural or framework ratios and the zeolite, whatever its type, may be incorporated into a matrix material such as clay, silica or a metal oxide such as alumina or silica alumina.

Zeolite beta is the preferred support since this zeolite has been shown to possess outstanding activity for paraffin isomerization, as disclosed in U.S. Patent 4,419,220, even in the presence of aromatics. The low acidity forms of zeolite beta may be obtained by synthesis of a highly siliceous form of the zeolite, e.g., with a silica-alumina ratio above 50:1, or, more readily, by steaming zeolites of lower silica-alumina ratio to the requisite acidity level. Another method is by replacement of a portion of the framework aluminum of the zeolite with another trivalent element such as boron which results in a lower intrinsic level of acid activity in the zeolite. The preferred zeolites of this type are those which contain framework boron, and normally at least 0.1 weight percent, preferably at least 0.5 weight percent, of framework boron is preferred in the zeolite. In zeolites of this type, the framework consists principally of silicon tetrahedrally coordinated and interconnected with oxygen bridges.

A minor amount of a trivalent element (alumina in the case of aluminosilicate zeolite beta) is usually also coordinated and forms part of the framework. The zeolite also contains material in the pores of the structure although these do not form part of the framework constituting the characteristic structure of the zeolite. The term "framework" boron is used here to distinguish between material in the framework of the zeolite which is evidenced by contributing ion exchange capacity to the zeolite, from material which is present in the pores and which has no effect on the total ion exchange capacity of the zeolite.

Methods for preparing high silica content zeolites containing framework boron are known and are described, for example, in U.S. Patent Nos. 4,269,813 and 4,672,049. As noted therein, the amount of boron contained in the zeolite may be varied by incorporating different amounts of borate ion in the zeolite forming solution, e.g., by the use of varying amounts of boric acid relative to the forces of silica and alumina. Reference is made to these disclosures for a description of the methods by which these zeolites may be made.

The zeolite framework will normally include some alumina and the silica:alumina ratio will usually be at least 30:1, in the as-synthesized conditions of the zeolite. A preferred zeolite beta catalyst is made by steaming an initial boron-containing zeolite containing at least 1 weight percent boron (as B_2O_3) to result in an ultimate alpha value no greater than about 10 and preferably no greater than 5.

The steaming conditions should be adjusted in order to attain the desired alpha value in the final catalyst and typically utilize atmospheres of 100 percent steam, at temperatures of from 800 to 1100°F

(427 to 595°C). Normally, the steaming will be carried out for about 12 to 48 hours, typically about 24 hours, in order to obtain the desired reduction in acidity. The use of steaming to reduce the acid activity of the zeolite has been found to be especially advantageous, giving results which are not achieved by the use of a zeolite which has the same acidity in its as-synthesized condition. It is believed that these results may be attributable to the presence of trivalent metals removed from the framework during the steaming operation which enhance the functioning of the zeolite in a manner which is not fully understood.

The zeolite will usually be composited with a matrix material to form the finished catalyst and for this purpose conventional non-acidic matrix materials such as alumina, silica-alumina and silica are suitable with preference given to silica as a non-acidic binder, although non-acidic aluminas such as alpha boehmite (alpha alumina monohydrate) may also be used, provided that they do not confer any substantial degree of acidic activity on the matrixed catalyst. The use of silica as a binder is preferred since alumina, even if non-acidic in character, may tend to react with the zeolite under hydrothermal reaction conditions to enhance its acidity. The zeolite is usually composited with the matrix in amounts from 80:20 to 20:80 by weight, typically from 80:20 to 50:50 zeolite:matrix. Compositing may be done by conventional means including mulling the materials together followed by extrusion or pelletizing into the desired finished catalyst particles. A preferred method for extruding the zeolite with silica as a binder is disclosed in U.S. Pat. 4,582,815. If the catalyst is to be steamed in

order to achieve the desired low acidity, it is performed after the catalyst has been formulated with the binder, as is conventional.

5 The isomerization process isomerizes the long
chain waxy paraffins in the raffinate to form iso-
paraffins which are less waxy in nature but which
possess a notably high viscosity index. At the same
time, the acidic function of the zeolite will promote
a certain degree of cracking or hydrocracking so that
10 some conversion to products outside the lube boiling
range will take place. This is not, however, totally
undesirable, because any aromatics still present
after the extraction step will tend to be removed by
hydrocracking, with consequent improvements in the
15 viscosity and VI of the product. The extent to which
cracking reactions and isomerization reactions will
predominate will depend on a number of factors,
principally the nature of the zeolite, its inherent
acidity, the severity of the reaction (temperature,
20 contact time) and, of course, the composition of the
feedstock. In general, cracking will be favored over
isomerization at higher severities (higher
temperature, longer contact time) and with more
highly acidic forms of the zeolite. Thus, a higher
25 zeolite silica:alumina ratio will generally favor
isomerization and therefore will normally be
preferred, except possibly to handle more aromatic or
nitrogen-rich feeds. The acidity of the zeolite may
also be controlled by exchange with alkali metal
30 cations, especially monovalent cations such as sodium
and divalent cations such as magnesium or calcium, in
order to control the extent to which isomerization
occurs relative to cracking. The extent to which
isomerization will be favored over cracking will also
35 depend upon the total conversion, itself a factor

dependent upon severity. At high conversions, typically over about 80 volume percent, isomerization may decrease fairly rapidly at the expense of cracking; in general, therefore, the total conversion
5 by all competing reactions should normally be kept below about 80 volume percent and usually below about 70 volume percent.

The relationships between cracking reactions and isomerization reactions for these zeolites are
10 described in some greater detail in U.S. Application Serial No. 379,423 and its counterpart EP 94,826, to which reference is made for such a description.

The selection of the metal hydrogenation-dehydrogenation component will also have a bearing on
15 the relative balance of reactions. The more highly active noble metals, especially platinum, promote hydrogenation-dehydrogenation reactions very readily and therefore tend to promote isomerization at the expense of cracking because paraffin isomerization by
20 a mechanism involving dehydrogenation to olefinic intermediates followed by hydrogenation to the isomer products. The less active base metals, by contrast, will tend to favor hydrocracking and therefore may commend themselves when it is known that cracking
25 reactions may be required to produce a product of the desired properties. Base metal combinations such as nickel-tungsten, cobalt-molybdenum or nickel-tungsten-molybdenum may be especially useful in these instances.

30 The hydroisomerization is carried out under conditions which promote the isomerization of the long chain, waxy paraffinic components to isoparaffins to increase the V.I. of the product. Generally, the conditions may be described as being
35 of elevated temperature and pressure. Temperatures

are normally from 400 to 850°F (204°C to 454°C), preferably 600 to 800°F (316 to 427°C). Because the use of lower temperatures tends to favor the desired isomerization reactions over the cracking reactions, the lower temperatures will generally be preferred although it should be remembered that since the degree of cracking which will to some extent inevitably take place will be dependent upon severity, a balance may be established between reaction temperature and average residence time in order to achieve an adequate rate of isomerization while minimizing cracking. Pressures may range up to high values, e.g. up to 25,000 kPa (3,600 psig), more usually in the range 4,000 to 10,000 kPa (565 to 1,435 psig). The possibility of using low hydrogen pressures, e.g., below about 1000 psig (about 7000 kPa) is a particularly advantageous feature of the present process. Space velocity (LHSV) is generally in the range of 0.1 to 10 hr.⁻¹, more usually 0.2 to 5 hr.⁻¹, say, 0.5 to 1.5 hr.⁻¹. The hydrogen:feed ratio is generally from 50 to 1,000 n.l.l.⁻¹ (about 280 to 5617 SCF/Bbl), preferably 200 to 400 n.l.l.⁻¹ (about 1125 to 2250 SCF/Bbl). Net hydrogen consumption will depend upon the course of the reaction, increasing with increasing hydrocracking and decreasing as isomerization (which is hydrogen-balanced) predominates. The net hydrogen consumption will typically be under 90 n.l.l.⁻¹ (500 SCF/Bbl) and about 40 n.l.l.⁻¹ (about 224 SCF/Bbl) with the feeds of relatively low aromatic content such as the paraffinic neutral (distillate) feeds and slack wax and frequently will be less, typically below 35 n.l.l.⁻¹ (about 197 SCF/Bbl); with feeds which contain higher amounts of aromatics higher net hydrogen consumptions should be anticipated,

typically in the range of 50-100 n.l.l.⁻¹ (about 280-560 SCF/Bbl), e.g. from 55-80 (about 310-450 SCF/Bbl). Process configuration will be as described in U.S. Patents Nos. 4,419,220 and 4,518,485, i.e.

5 with downflow trickle bed operation being preferred.

With highly paraffinic feeds of low aromatic content, it will be desirable to maximize isomerization over hydrocracking and therefore relatively low temperatures, e.g. from 250° to 400°C

10 (about 480° to 750°F) will be preferred together with relatively low severities, e.g. space velocities (LHSV) of about 1 to 5, and catalysts of relatively low acidity. As a general guide, the bulk conversion to products outside the lube boiling range will be at

15 least 10 weight percent and usually in the range 10 to 50 weight percent, depending upon the characteristics of the feed, the properties desired for the product and the desired product yield. With most feeds it will be found that there is an optimum

20 conversion for VI efficiency, or yield efficiency, that is, for maximum VI relative to yield or maximum yield and in most cases, this will be in the range of 10-50 weight percent conversion, more commonly 15-40 weight percent conversion.

25 Selection of the severity of the hydroisomerization step is an important part of the present process because it is not possible to remove the straight chain and slightly branched chain waxy components in a completely selective manner, while

30 retaining the desirable more highly branched chain components which contribute to high VI in the product. For this reason, the degree of dewaxing by isomerization which is achieved in the first step, is preferably limited so as to leave a residual quantity

of waxy components which may then be removed in the subsequent dewaxing (catalytic or solvent) step. The objective of maximizing the isoparaffinic content of the effluent from the catalytic dewaxing step so as to obtain the highest VI in the final product may be achieved by adjusting the severity of the initial dewaxing operation until the optimum conditions are reached for this objective. Further details of the hydroisomerization are found in Serial No. 793,937 and EP 225,053 to which reference is made for this purpose.

For upgrading a very waxy feedstock such as Minas VGO, the upstream furfural extraction and subsequent hydroisomerization with boron-containing zeolite beta isomerization catalyst results in high yields of a product of high viscosity index and adequate pour point without subsequent dewaxing and/or hydrofinishing. The use of low acidity zeolite beta results in a product of significantly higher viscosity index than a zeolite beta catalyst of higher acidity.

Although the product resulting from hydroisomerization can exhibit sufficiently low pour point and high viscosity index so that further processing is not required, subsequent dewaxing and hydrofinishing steps may be carried out as an option, depending on desired product specifications.

Dewaxing

Following the hydroisomerization the lube can be subjected to a dewaxing step which has two principal objectives. First, it will further reduce the pour point. Second, if a selective solvent dewaxing is used, a divergence between product pour point and cloud point can be avoided. Solvent dewaxing is therefore preferred for this step of the process and

may be carried out according to conventional prescriptions for achieving the desired product pour point e.g. solvent/oil ratio, chill temperature etc. Conventional solvents such as methyl ethyl ketone (MEK)/toluene mixtures may be used or autorefrigerants such as propane. It is, however, possible to use highly selective solvents such as those having at least 80 vol% MEK, e.g., 100% MEK, in the present process because with the highly paraffinic streams produced by the use of waxy feeds, the phase separations observed with less highly paraffinic materials have not been found to occur. This phenomenon may be occasioned by the relative absence of aromatics coupled with the relatively high proportion of iso-paraffins. The use of such highly selective solvent dewaxing procedures is desirable because of the highly favorable separation of the waxy components, which it achieves while, at the same time, leaving the high V.I. iso-paraffins in the oil. However, less selective solvent mixtures may be used if desired, for example, MEK/toluene with 60 to 80 percent (v/v) MEK. The wax separated in the solvent dewaxing may be recycled to the initial isomerization step for further improvement in product quality and process efficiency. Catalytic dewaxing may also be employed at this stage of the process, for example, using an intermediate pore size dewaxing catalyst such as ZSM-5, ZSM-11, ZSM-23, or ZSM-35 in any of the catalytic dewaxing processes disclosed in the patents identified above, to which reference is made for a description of such processes. Catalytic dewaxing over zeolite ZSM-23 or ZSM-35 is especially preferred, particularly for light lube stocks e.g. up to 43 mm²/s (200 SUS) light neutral because of the highly selective nature of the dewaxing with this

zeolite. Dewaxing with ZSM-23 is described in U.S. 4,222,855 to which reference is made for a disclosure of the process. Catalytic dewaxing is preferred when extremely low pour point ($<-20^{\circ}\text{F}$) lubricant products
5 are desired.

Dewaxing at this stage is carried out to reduce the pour point to the desired value, typically below 10°F (about -12°C) and usually lower e.g. 5°F (-15°C). Dewaxing severity will be adjusted according
10 to the desired pour point or other fluidity characteristic (cloud point, freeze point etc). Although increasing low pour points will result in lower yields as progressively more of the waxy paraffin content is removed in the processing.
15 However, the iso-paraffinic character of the oil produced by the initial hydroisomerization step results in higher yields at higher VI levels than would otherwise be achieved.

Hydrofinishing

20 After dewaxing, the oil can be hydrofinished to improve its lubricant quality by saturating residual lube boiling range olefins and removing color bodies and other sources of instability. If the hydrofinishing pressure is high enough, saturation of
25 residual aromatics may also take place. Hydrofinishing conditions may be conventional for lube hydrofinishing, typically at $400^{\circ}\text{--}700^{\circ}\text{F}$ (about $205^{\circ}\text{--}370^{\circ}\text{C}$), 400-5000 psig (about 2860-20,800 kPa), 0.1-5 LHSV, 500-10,000 SCF/Bbl H_2 :oil (about 90-1780
30 n.l.l. $^{-1}$ H_2 :oil). Catalysts typically comprise a metal hydrogenation component on an essentially non-acidic porous support such as alumina, silica or silica-alumina. The metal component is usually a base metal of Group VIA or VIIIA, or a combination of
35 such metals, such as nickel, cobalt, molybdenum,

cobalt-molybdenum or nickel-cobalt. Hydrofinishing catalysts of this type are conventional and readily available commercially. Hydrofinishing is particularly desirable after catalytic dewaxing by a shape-selective cracking process e.g. dewaxing over ZSM-5, because of the presence of lube range olefins in the dewaxed product which would otherwise lead to product instability.

The products of the present process are lubricants of high VI and low pour point and excellent oxidational stability, a combination of properties conferred by the presence of significant quantities of iso-paraffins coupled with relative freedom from aromatics. The use of the solvent extraction in combination with the subsequent isomerization dewaxing enables high VI to be coupled with low product pour point, as together with high efficiency in the process, either as to VI efficiency or yield efficiency.

EXAMPLES

The following examples are given in order to illustrate various aspects of the present process.

Example 1

A premium quality lube base stock was prepared from a waxy Minas vacuum gas oil whose composition is set out in Table 1 below.

Table 1

		<u>Minas Gas Oil</u>
5	Nominal boiling range, (399-566°C)	750°-1050°F
	API Gravity	31.5
	Sulfur, wt%	0.11
	Nitrogen, ppmw	550
	Composition, wt%	
10	Paraffins	52
	Naphthenes	25
	Aromatics	23

- 15 Minas 750-1050°F (399-566°C) boiling range VGO, having a pour point of +110°F (43°C) and containing about 52% wt. total paraffins (mainly n-paraffins), was treated in a continuous
- 20 furfural extraction unit (7 stages, 200 vol%, 255°F (124°C)). Under these furfural extraction conditions, this feedstock yielded about 69 vol%
- 25 Minas raffinate containing about 39.8 wt% entrained oil and very low heteroatom level (4 ppm N, 0.03 wt% S). The properties of the Minas raffinate resembled those of a typical Heavy Neutral slack wax feedstock (35 wt% oil, 59 ppm N, 0.12 wt% S).
- Table 2 below sets out the product properties of Minas VGO feedstock after furfural extraction with those of a conventional Heavy Neutral slack wax feedstock.

Table 2

	<u>Minas Gas Oil</u> <u>Raffinate</u>	<u>HN Slack Wax</u>
5	Nominal boiling range, 399-566°C (750-1050°F)	343-566°C (650-1050°F)
	API Gravity 36.0	36.0
	Sulfur, wt% 0.03	0.13
	Nitrogen, ppmw 4	59
10	Oil Content, wt% 39	36
	Composition, wt%	
	Paraffins 62	55
	Naphthenes 32	26
	Aromatics 6	19

15 A comparison of the Minas Gas Oil of Table 1 and its raffinate in Table 2 indicates that the furfural extraction step reduces significantly the heteroatom levels in the Minas VGO, concentrates the wax content and produces a Minas raffinate with product properties similar to those of a typical slack wax.

20 This Minas raffinate has higher paraffin content and much lower aromatic content even when compared with a slack wax (62 v. 55 wt% paraffins and 6 vs. 19 wt% aromatics).

Example 2(Comparative)

25 The Minas raffinate obtained from Example 1 was processed over a Pt/zeolite beta catalyst. The catalyst was an extrudate comprised of 65 wt% zeolite beta, 35 wt% alumina binder. Prior to 0.6 wt% Pt addition, the extrudate was steamed to lower its

30 acidity to about 55 alpha. Further properties of this catalyst as well as those of the Pt boron zeolite beta catalyst of Example 3 are set out below in Table 3.

Table 3
Catalyst Properties

	Pt/Beta/Al ₂ O ₃	Pt/B Beta/SiO ₂
Beta, wt%	65	65
5 Al ₂ O ₃ , wt%	35	-
SiO ₂ , wt%	-	35
Density, g/cc	0.53	0.55
Packed		
Pt, wt%	0.66	0.87
10 Alpha (w/o Pt)	55	4

The hydroisomerization evaluation was carried out in a fixed-bed unit under 2760 kPa (400 psig), 1 LHSV, 356 n.l.l.⁻¹ (2000 SCF/Bbl) H₂ circulation and in the temperature range of 740-770°F (393-410°C).

15 Under these process conditions, the 343°C+ (650°F+) boiling point conversion was in the range of 0-67 wt%. After vacuum distillation at 343°C (650°F) to remove converted products, certain portions of the 343°C+ (650°F+) fraction were subjected to a
20 conventional methyl ethyl ketone (MEK) dewaxing step to produce a lube fraction using 100% MEK at -25°F (-32°C) to obtain a +20°F (-6°C) pour point product in 28-56% yield.

Table 4 shows the relationship of 343°C+
25 (650°F+) conversion with lube production from the waxy Minas raffinate. The results show that this waxy Minas raffinate provides about 51.1 wt% lube yield with a maximum 111 VI at 32.8 wt% 343°C+
(650°F+) conversion by upgrading over Pt zeolite
30 beta/MEK dewaxing combination.

Table 4

**Upgrading Minas Raffinate Feedstock Using the Combination Fufural
Extraction/Pt Zeolite Beta/MEK Dewaxing**

5		Minas Raffinate	Pt Zeolite Beta					
	RxR Temp. °C(°F)	Feed	393(740)	396(745)	399(750)	403(758)	405(761)	410(770)
	343°C(650°F) Conv., wt%	--	22.4	32.8	38.3	48.9	53.5	67.7
	Overall MEK Lube Yield, wt%	45.0	56.1	51.1	47.0	45.6	40.1	28.6
10	<u>Lube Properties</u>							
	Pour Point, °C(°F)	-1(+30)	-7(+20)	-7(+20)	-12(+10)	-12(+10)	-12(+10)	-18(0)
	KV @ 40°C, mm ² /s	49.51	35.13	32.27	31.89	31.50	32.65	35.82
	@ 100°C, mm ² /s	7.031	5.870	5.557	5.551	5.421	5.485	5.561
	VI	98	109	111	109	107	103	89
15	VI corrected to -7°C(20°F) Pour Point	96	109	111	111	109	105	93



This Sheet Has Been Replaced

Example 3

A second portion of the Minas raffinate obtained from Example 1 was processed over a Pt boron-containing zeolite beta catalyst in place of the conventional zeolite beta as in Example 2. The catalyst was an extrudate comprised of 65 wt% zeolite beta, 35 wt% SiO_2 and contained 0.87 wt% Pt. Properties of the catalyst are set out in Table 3 above. The catalyst had very low acidity as indicated by a low alpha measurement of 5 (taken prior to Pt addition).

The hydroisomerization evaluation was carried out in a fixed-bed unit at 2760 kPa (400 psig), 0.5-1.0 LHSV, 356 n.l.l.⁻¹ (2000 SCF/Bbl) H_2 circulation and in the temperature range of 765-780°F (407-416°C). Under these process conditions, with the 343°C+ (650°F+) boiling point conversion at 27.3 wt%, the Pt boron zeolite beta produced directly a 20°F (-6°C) pour lube base stock without subsequent MEK dewaxing as shown in the Figure. Samples of the hydroisomerization product were subsequently treated by MEK dewaxing under the same conditions set out in Example 2. The combination with MEK dewaxing further increases the VI potential to at least 130 VI, as shown in Table 5 below, at very low conversion of 343°C (650°F+) product (10.1 wt%).

Table 5

Direct Upgrading Minas Raffinate over Pt Boron-Containing Zeolite Beta

		<u>Minas Raffinate</u>	<u>Pt Boron-Zeolite Beta</u>				
5	RxR Temp. °C(°F)	--	407(765)	404(759)	399(750)	412(774)	415(779)
	LHSV, hr ⁻¹	--	1.0	1.0	06.4	1.0	1.0
	650°F+ Conv., wt%	--	21.2	23.1	27.3	27.5	45.6
<u>650°F+ Properties</u>							
10	H, wt%	14.85	14.49	14.46	14.51	14.32	14.53
	S, wt%	0.030	0.010	0.005	0.002	0.005	0.002
	Pour Point, °C(°F)	43(+110)	10(+50)	4.4(+40)	-7(+20)	1.7(+35)	-26(-15)
	KV @ 40°C, mm ² /s	--	21.68	20.34	25.00	24.12	24.19
	100°C, mm ² /s	4.991	4.570	4.363	4.783	4.909	4.624
VI		--	128	125	120	122	107

This Sheet Has Been Replaced



Table 6 compares the performance of low acidity Pt boron zeolite beta with the higher acidity Pt/zeolite beta of Example 2. The results indicate that the low acidity Pt boron-containing zeolite beta not only increases the VI potential by at least 20 VI numbers from 111 to 130 VI, but also improves significantly the lube yield from 56.1 to 89.9 wt% as compared to the higher acidity Pt/zeolite beta. The higher paraffin content (64-66 wt%) in the lube produced from the Pt boron zeolite beta reflects its improved hydroisomerization selectivity.

Table 6

The Comparison of Pt Boron Zeolite Beta Versus Pt Zeolite Beta
for Upgrading Minas Raffinate Feedstock

		<u>Pt Zeolite Beta</u>		<u>Pt Boron Zeolite Beta</u>		
5	MEK Dewaxing	Yes	Yes	Yes	Yes	No
	343°C(650°F+) Conv., wt%	22.4	32.8	10.1	16.1	27.3
	Overall Lube Yield, wt%	56.1	51.1	89.9	75.6	72.7
<u>Lube Properties</u>						
10	Pour Point, °C(°F)	-7(+20)	-7(+20)	-7(+20)	-9(+15)	-7(+20)
	KV @ 40°C, mm²/s	35.13	32.27	21.89	23.43	24.12
	@ 100°C, mm²/s	5.870	5.577	4.621	4.776	4.783
VI		109	111	130	127	120
<u>Composition, wt%</u>						
15	Paraffins	49.2	47.5	65.2	64.8	65.3
	Mono-Napthenes	12.0	11.5	7.2	7.3	5.5
	Poly-Napthenes	26.2	28.3	17.2	15.1	16.8
	Aromatics	12.6	12.7	10.3	12.8	12.4

This Sheet Has Been Replaced





Claims:

1. A process for producing a high viscosity index (VI) lubricant from a hydrocarbon feed of mineral oil content having a paraffin content of at least 30 wt%, an aromatics content of at least 10 wt%, and a nitrogen content of at least 50 ppm, which process comprises:
 - i) extracting the feed with a solvent which is selective for aromatics to provide an extracted feed containing greater than 40 wt% paraffins, less than 15 wt% aromatics, and less than 30 ppm nitrogen content, and
 - ii) hydroisomerizing the extracted feed with a low acidity zeolite beta catalyst having an alpha value less than 15 and an inorganic oxide matrix to provide a lubricant having a viscosity index of at least 110.
2. The process according to claim 1 in which the hydroisomerizing is carried out at a temperature from 204° to 454°C, a total pressure of at least 690 kPa gauge and a space velocity of 0.1 to 10 LHSV, and the catalyst has an alpha value of less than 10.
3. The process according to claim 2 in which the zeolite beta catalyst comprises noble metal on zeolite beta.
4. The process according to claim 3 in which the noble metal is selected from palladium and platinum.



5. The process according to claim 1 in which the hydroisomerizing is carried out at a temperature from 316 to 427°C, a total pressure from 1380 to 6900 kPa gauge and a space velocity of 0.5 to 1.5 LHSV, and said catalyst has an alpha value of less than 5.

6. The process according to claim 1 in which the zeolite beta catalyst comprises a silica matrix.

7. The process according to claim 1 in which the solvent selective for aromatics is selected from the group consisting of furfural, N-methylpyrrolidone, and phenol.

8. The process of claim 1 which further comprises:

iii) solvent dewaxing the hydroisomerized lubricant to reduce its pour point.

9. The process according to claim 8 in which the dewaxing solvent comprises at least 80 vol. percent methyl ethyl ketone.

10. The process of claim 1 which further comprises:

iii) catalytic dewaxing the hydroisomerized lubricant by paraffin cracking to reduce its pour point.

11. The process according to claim 1 in which the product lubricant has a VI of at least 110 and a pour point not higher than -7°C.



12. The process according to claim 1 in which the hydrocarbon feed is a neutral lubricant distillate.

- 5 13. A process for producing a high viscosity index (VI) lubricant from a hydrocarbon feed of mineral oil content having a paraffin content of at least 30 wt%, a nitrogen content of at least 50 ppm, and an aromatics content of at least 10 wt% which consists essentially of:
- 10 i) extracting said feed with a solvent which is selective for aromatics to provide an extracted feed containing greater than 40 wt% paraffins, less than 15 wt% aromatics, and less than 30 ppm nitrogen content, and
- 15 ii) hydroisomerizing the extracted feed with a low acidity zeolite beta catalyst containing zeolite beta comprising boron as a framework component and an inorganic oxide matrix to provide a lubricant having a viscosity index of at least 110.
- 20 14. The process according to claim 13 in which the hydroisomerizing is carried out at a temperature from 204°C to 454°C, a pressure from 1380 to 10340 kPa and a space velocity of 0.1 to 10 LHSV, and said zeolite beta catalyst comprises platinum on zeolite
- 25 beta and said catalyst has an alpha value of less than 10.

15. The process according to claim 13 in which the solvent selective for aromatics is selected from furfural, N-methyl-pyrrolidone, and phenol.



-36-

16. The process according to claim 13 in which the lubricant is produced with a hydrogen consumption of not more than 80 n.l.l^{-1} in step (ii) of the process.

5 17. The process according to claim 13 in which the zeolite beta catalyst comprises platinum on zeolite beta.

10 18. The process according to claim 13 in which the zeolite beta catalyst comprises palladium on zeolite beta.

19. The process according to claim 13 in which the zeolite beta catalyst comprises a silica matrix.

15 20. The process according to claim 13 in which the hydrocarbon feed is a neutral lubricant distillate.