

Strained-Channel Transistor and Methods of Manufacture

TECHNICAL FIELD

[0001] The present invention relates generally to semiconductor devices and more particularly to a strained channel transistor and methods of manufacturing the same.

BACKGROUND

[0002] Size reduction of metal-oxide-semiconductor field-effect transistors (MOSFET), including reduction of the gate length and gate oxide thickness, has enabled the continued improvement in speed performance, density, and cost per unit function of integrated circuits over the past few decades.

[0003] To enhance transistor performance further, strain may be introduced in the transistor channel for improving carrier mobilities. Therefore, strain-induced mobility enhancement is another way to improve transistor performance in addition to device scaling. There are several existing approaches of introducing strain in the transistor channel region.

[0004] In one conventional approach, as described in a paper by J. Welser et al., published at the December 1992 International Electron Devices Meeting held in San Francisco, CA, pp. 1000-1002 and incorporated herein by reference, a relaxed silicon germanium (SiGe) buffer layer is provided beneath the channel region. Figure 1a shows such an approach. Referring to Figure 1a, a semiconductor device 100 includes a strained silicon layer 110 formed over and abutting a relaxed SiGe layer 112, which is formed over and abutting a graded SiGe buffer layer 114. The graded SiGe buffer layer 114 is formed over and abutting a silicon substrate 116.

[0005] The relaxed SiGe layer 112 has a larger lattice constant compared to relaxed Si, and the thin layer of epitaxial Si 110 grown on the relaxed SiGe 112 will have its lattice stretched in the lateral direction, i.e., it will be under biaxial tensile strain. This result is illustrated in Figures 1b and 1c. Therefore, a transistor 118 formed on the epitaxial strained silicon layer 110 will have a channel region 120 that is under biaxial tensile strain. In this approach, the relaxed SiGe buffer layer 112 can be thought of as a stressor that introduces strain in the channel region 120. The stressor, in this case, is placed below the transistor channel region 120.

[0006] Significant mobility enhancement has been reported for both electrons and holes in bulk transistors using a silicon channel under biaxial tensile strain. In the abovementioned approach, the epitaxial silicon layer is strained before the formation of the transistor. But there are concerns about the strain relaxation upon subsequent CMOS processing where high temperatures are used. In addition, this approach is very expensive since a SiGe buffer layer with thickness in the order of micrometers has to be grown. Numerous dislocations in the relaxed SiGe buffer layer exist and some of these dislocations propagate to the strained silicon layer, resulting in a substrate with high defect density. Thus, this approach has limitations that are related to cost and fundamental material properties.

[0007] In another approach, strain in the channel is introduced after the transistor is formed. In this approach, a high stress film 132 is formed over a completed transistor structure 130 formed in a silicon substrate 136, as shown in Figure 2. The high stress film or stressor 132 exerts significant influence on the channel 134, modifying the silicon lattice spacing in the channel region, and thus introducing strain in the channel region. In this case, the stressor 132 is placed above the completed transistor structure. This scheme is described in detail in a paper by A. Shimizu et al., entitled "Local mechanical stress control (LMC): a new technique for CMOS

performance enhancement," published in pp. 433-436 of the Digest of Technical Papers of the 2001 International Electron Device Meeting, which is incorporated herein by reference.

[0008] The strain contributed by the high stress film is believed to be uniaxial in nature with a direction parallel to the source-to-drain direction. However, uniaxial tensile strain degrades the hole mobility while uniaxial compressive strain degrades the electron mobility. Ion implantation of germanium can be used to selectively relax the strain so that the hole or electron mobility is not degraded, but this is difficult to implement due to the close proximity of the n and p-channel transistors.

[0009] On the other hand, strain is known to be also introduced in the channel region by the formation of the isolation structure, such as the shallow trench isolation structure. While there is much prior art related to the formation and improvement of the isolation structure, e.g., U.S. Patent No. 6,046,487, U.S. Patent No. 5,763,315, and U.S. Patent No. 5,447,884, this prior art has not addressed the separate optimization of strain for the n-channel and p-channel transistors. That is, the same isolation structure is used for all transistors, whether n-channel or p-channel transistors.

[0010] For example, Figure 3a shows a transistor 140 formed in an active region isolated by shallow trench isolation (STI) regions 142. The STI regions 142 exert compressive stress on the active region, and the channel region 144 of the transistor 140 is therefore under compressive stress. While compressive stress in the channel region 144 improves the mobility of holes, it degrades the mobility of electrons. Therefore, the STI of Figure 3a improves the performance of p-channel transistors while degrading the performance of n-channel transistors.

[0011] In Figure 3b, another prior art trench isolation structure is shown where a nitride liner 146 is formed over an oxide liner 148. The nitride liner 146 acts as an oxidation mask,

preventing further oxidation of the trench sidewalls. The nitride liner 146 minimizes confined volume expansion when the isolation trench is filled with oxide 150 and, therefore, reduces any compressive stress in the surrounding active region.

SUMMARY OF THE INVENTION

[0012] Aspects of this invention address the drawbacks of the prior art by optimizing the isolation structure induced strain for n-channel and p-channel transistors separately. For example, n-channel and p-channel transistors are each provided with strained channel regions. In particular, embodiments of the invention teach a structure and method of engineering the strain in the channel of the transistor by engineering the isolation structure to improve the performance of both the n-channel and p-channel transistors.

[0013] In one embodiment, a semiconductor device includes a region of semiconductor material with first and second isolation trenches formed therein. The first isolation trench is lined with a first material having a low oxygen diffusion rate and is filled with an insulating material. The second isolation trench is not lined with the first material but is filled with an insulating material. A first transistor is formed adjacent the first isolation region and a second transistor formed adjacent the second isolation region.

[0014] Several embodiments are provided. For example, the first material can be a nitride layer. The second trench can be lined with a nitride layer that has been modified, e.g., implanted with ions or removed. In another example, the first material can be an oxynitride (an nitrated oxide). In the case, the second trenches can be lined with an oxide liner or no liner at all, as examples.

[0015] Several methods of fabricating devices of various embodiments are also provided. For example, a plurality of trenches are formed in a semiconductor region, e.g., substrate or layer over a substrate. Each trench is lined with a liner. The liner can then be modified in some but not all of the plurality of trenches. Each trench would then be filled with an insulating material.

[0016] The foregoing has outlined rather broadly the features and technical advantages of the present invention in order that the detailed description of the invention that follows may be better understood. Additional features and advantages of the invention will be described hereinafter which form the subject of the claims of the invention. It should be appreciated by those skilled in the art that the conception and specific embodiment disclosed may be readily utilized as a basis for modifying or designing other structures or processes for carrying out the same purposes of the present invention. It should also be realized by those skilled in the art that such equivalent constructions do not depart from the spirit and scope of the invention as set forth in the appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

[0017] For a more complete understanding of the present invention, and the advantages thereof, reference is now made to the following descriptions taken in conjunction with the accompanying drawing, in which:

[0018] Figure 1a shows a conventional strained silicon transistor with a relaxed SiGe layer as a stressor to induce strain in the top epitaxial strained silicon layer;

[0019] Figures 1b and 1c illustrate the origin of strain in the Si/SiGe heterostructure.

[0020] Figure 2 illustrates another way of introducing strain in the channel is by using a high stress film as a stressor.

[0021] Figures 3a and 3b show conventional semiconductor devices with isolation structures;

[0022] Figures 4a and 4b illustrate two embodiment structures of the present invention;

[0023] Figures 4c-4e show plan views of embodiments of the present invention;

[0024] Figures 5a-5f illustrate an embodiment method of the present invention;

[0025] Figures 6a and 6b illustrate methods of forming transistors, which can apply to any of the methods of the present invention;

[0026] Figures 7a-7d illustrate an embodiment method of the present invention;

[0027] Figures 8a-8f illustrate an embodiment method of the present invention;

[0028] Figures 9a-9b show an alternate embodiment of present invention; and

[0029] Figure 10 shows a second alternate embodiment of the present invention.

DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[0030] The making and using of the presently preferred embodiments are discussed in detail below. It should be appreciated, however, that the present invention provides many applicable inventive concepts that can be embodied in a wide variety of specific contexts. The specific embodiments discussed are merely illustrative of specific ways to make and use the invention, and do not limit the scope of the invention.

[0031] The preferred embodiment of the present invention relates to the field of semiconductor devices, and more specifically, to the manufacture of strained n-channel and p-channel field effect transistors with enhanced performance using separately optimized isolation regions.

[0032] Figures 4a and 4b show the concept of separately optimizing the isolation structures for different active regions and the structural embodiments of the embodiments of the present invention. Referring now to Figure 4a, a semiconductor substrate 210 is provided in which active regions 212a, 212b and 212c, collectively 212, are defined by isolation structures 214a, 214b, 214c and 214d, collectively 214. The isolation structures 214 are preferably trench isolation structures, and more preferably shallow trench isolation (STI) structures. It is noted that the isolation structures 214 are shown in cross-section and that certain ones of these structures can be portions of the same, e.g., annular, isolation structure.

[0033] At least two types of trench isolation structures may be provided. These types of isolation structures 214 differ in the nature of stress, e.g., compressive stress or tensile stress, in which they exert on the active regions 212. As shown in Figures 4a and 4b, a first active region 212a is surrounded by a first isolation structure 214a/b (including isolation structures 214a and

214b). Due to the nature and design of the first isolation structure 214a/b, the first active region 212a will be under tensile stress or under little or no stress.

[0034] An example of such a first isolation 214a/b structure is a shallow trench isolation (STI) with a silicon oxide liner 216 underlying a silicon nitride liner 218. The first isolation structure 212 also includes a trench filling material 220 such as chemical-vapor-deposited (CVD) silicon oxide (e.g., SiO_2). The trench filling material 220 may also be a combination of materials, such as CVD silicon oxide and CVD poly-silicon. The depth d of the isolation structure may be in the range of about 200 to about 6000 angstroms.

[0035] The silicon nitride liner 218 in the first isolation structure helps to reduce the in-plane compressive stress in the active region 212 due to a number of reasons. Firstly, the silicon nitride liner 218 restricts further oxidation of the trench sidewall after the formation of the silicon oxide liner 216, thus restricting volume expansion of the isolation structure 214. The silicon nitride liner 216 is able to restrict oxidation of the trench sidewall because of the low diffusion rate of oxygen through silicon nitride. It is understood that another material with low oxygen diffusion rate, e.g., silicon oxynitride (SiO_xN_y), may be used in place of the silicon nitride liner to achieve the same effect.

[0036] Volume expansion of an isolation structure that surrounds an active area compresses the sandwiched active region and, therefore, results in an in-plane compressive stress in that active region. By reducing the volume expansion, the in-plane compressive stress in the channel region can be reduced significantly. Secondly, a silicon nitride liner film usually has an associated intrinsic tensile stress. Since the silicon nitride liner film is itself under tensile stress, it exerts a vertical compressive stress on the trench sidewall surfaces. This results in a vertical compressive strain and an in-plane tensile strain in the active region. Therefore, if the magnitude

of the intrinsic tensile stress in the silicon nitride liner is large, the first isolation structure may result in the introduction of an in-plane tensile stress in the active region.

[0037] As shown in Figures 4a and 4b, a second isolation structure 214c/d is employed to define a second active region 212c, which will be provided with in-plane compressive strain. In a first embodiment, as shown in Figure 4a, the second isolation structure 214c/d is a trench isolation structure with a silicon oxide liner 216 underlying an ion-implanted silicon nitride liner 222. The ion implantation introduces defects into the silicon nitride liner film 222 and causes it to lose or degrades its ability to block oxygen diffusion. Therefore, it is possible for oxygen to diffuse through silicon nitride 222 and result in further oxidation of the trench sidewall, causing volume expansion in a confined space, and therefore introducing in-plane compressive stress in the second active region.

[0038] The in-plane compressive stress results in an in-plane compressive strain in the crystal lattice of the material comprising the second active region 212c. It is desired that this in-plane compressive strain is not cancelled by an in-plane tensile strain component. By design, ion implantation of the silicon nitride liner 222 also additionally removes the intrinsic stress in the silicon nitride film 222. Examples of ion implant species that may be used to reduce the stress in the silicon nitride liner 222 are silicon ions and germanium ions. Other implantation ions such as silicon, germanium, nitrogen, helium, neon, argon, and xenon and combinations thereof could alternatively be used. In other words, silicon or germanium ions implanted into the silicon nitride liner 222 film will release or reduce the intrinsic stress in the film. By reducing the stress in the silicon nitride liner film 222, the silicon nitride liner 222 will not stress the sidewall surface of the second active region 212c and contribute an in-plane tensile strain component to cancel the desired in-plane compressive strain in the second active region 212c.

[0039] In a second embodiment, as shown in Figure 4b, the second isolation structure 214c/d is a conventional trench isolation structure with a silicon oxide liner (not shown) and with no silicon nitride liner. The second isolation structure resembles the isolation structure of Figure 3a and therefore results in an in-plane compressive strain in the second active region.

[0040] According to the preferred embodiment of the present invention, the first and second active regions 212a and 212c are provided on the same semiconductor substrate 210. By having the flexibility of providing active regions with different strain conditions, it is therefore possible to optimize the performance of n-channel and p-channel transistors by the choice and use of the appropriate strain conditions in the active regions. For example, n-channel transistors (not shown in Figure 4) may be formed on the first active region 212a with tensile strain in their source-to-drain direction to improve their drive current performance. In another example, p-channel transistors (not shown in Figure 4) may be formed on the second active region 212c with compressive strain in their source-to-drain direction to improve their drive current performance. While not ideal, it is also understood that p-channel transistors can be formed in first active region 212a and n-channel transistors in second active region 212c.

[0041] Figure 4c shows a top view of an n-channel transistor 236 formed in an active region surrounded by the first isolation structure 216/218/220. It is known that tensile strain in the source-to-drain direction (x-direction) or in a perpendicular direction (y-direction) improves the electron mobility. The channel region (below gate 246) of the n-channel transistor of Figure 4c has tensile strain in both the x and y directions.

[0042] Figure 4d shows a top view of a p-channel transistor 238 formed in an active region surrounded by the second isolation structure 220. In this case, compressive strain exists in the

source-to-drain direction (x-direction) and in a perpendicular direction (y-direction). This configuration improves the hole mobility.

[0043] Another preferred embodiment is shown in Figure 4e. In this case, a p-channel transistor 238 is formed in an active region sandwiched by the first isolation structure 262 in the y-direction and sandwiched by the second isolation 264 in the x-direction. Here, the first isolation structure 262 and the second isolation structure 264 are formed in different portions of a single annular trench. The p-channel transistor of Figure 4e has a channel region that is under compressive strain in the x-direction and tensile strain in the y-direction. This configuration is beneficial for hole mobility. However, it is understood that the isolation structure surrounding the active region of a p-channel transistor may be completely formed by a second isolation structure, so that there is compressive strain in both the x and y directions.

[0044] The semiconductor substrate 210 may be comprised of an elemental semiconductor such as silicon or germanium, an alloy semiconductor such as silicon-germanium, or a compound semiconductor such as gallium arsenide or indium phosphide. The semiconductor substrate 210 may also be a layered substrate, for example, comprising of a silicon layer on a silicon-germanium layer on a silicon substrate. In another example, the semiconductor substrate may be a silicon-on-insulator substrate. The magnitude of tensile or compressive strain in the channel may range from about 0.1% to about 4%. In the preferred embodiment, the strain magnitude is about 1% to about 4%.

[0045] A transistor or transistors or other element (not shown) can be formed in active area 212b. Active region 212b is expected to experience compressive stress on one side and tensile stress on the other side. Therefore, active region 212b is expected to be under a stress that is intermediate between that experienced by active region 212a and 212c.

[0046] Several methods for the manufacture of the abovementioned structures will next be described.

[0047] The first embodiment method provides a process flow for forming active regions with different strain conditions. For the purpose of illustrating the first method embodiment, a silicon nitride liner overlying a silicon oxide liner is used. It is understood that another material with a low oxygen diffusion rate can be used in place of silicon nitride.

[0048] Referring now to Figure 5a, a semiconductor substrate 210 is used as the starting material. This semiconductor substrate 210 may comprise an elemental semiconductor such as silicon or germanium, an alloy semiconductor such as silicon-germanium, or a compound semiconductor such as gallium arsenide or indium phosphide. The semiconductor substrate 210 may also be a layered substrate, for example, comprising of a silicon layer on a silicon-germanium layer on a silicon substrate. In another example, the semiconductor substrate may be a silicon-on-insulator substrate. In the preferred embodiment, the semiconductor substrate 210 is a monocrystalline silicon substrate.

[0049] In Figure 5b, a first patterned mask 230 is formed on the semiconductor substrate 210 and trenches 232 are etched. The first patterned mask 230 may comprise any masking material commonly used in the art, e.g. silicon oxide, silicon nitride, or a silicon nitride on silicon oxide stack. The first patterned mask 230 is preferably a silicon nitride on silicon oxide stack.

[0050] The trench 232 may be etched by anisotropic plasma etching. If the semiconductor substrate is a silicon substrate, the anisotropic plasma etching may employ a plasma with fluorine chemistry, e.g., containing chemical species such as CF_4 .

[0051] Next, as shown in Figure 5c, an oxide liner 216 is formed in the trenches 232. The oxide liner 216 may be formed by a thermal oxidation step, e.g., using temperatures ranging from about 600 degrees Celsius to about 1000 degrees Celsius and an oxidizing ambient containing species such as oxygen and water. Alternatively, the oxide liner 216 could be deposited, e.g., by chemical vapor deposition.

[0052] A silicon nitride liner 218 is also conformally formed, e.g., by chemical vapor deposition. The chemical vapor deposition step may use precursor gases such as ammonia and silane. As discussed above, other materials can be alternatively, or additionally, used for the liner 218.

[0053] Referring next to Figure 5d, a second patterned mask 234 is used to cover selected regions, including the first active region 212a and at least a portion of adjacent trenches 232a and 232b. The second patterned mask 234 preferably comprises a photoresist such as any photoresist known in the art. Figure 10 shows an embodiment where the mask 234 is patterned to cover a portion of a trench 232.

[0054] An ion implantation is then performed to alter the characteristics of the silicon nitride liner 218 in selected regions thus forming liner 222. The ion implanted silicon nitride liners 222 may, for example, be in the isolation structures surrounding the second active region 212c. The ion implantation process may be a conventional beam-line ion implantation process, a plasma immersion ion implantation (PIII), or any other ion implantation process known and used in the art. The dose of the ion implantation may be in the range of about $1\text{E}13$ to about $1\text{E}16$ ions per square centimeter and the energy may be in the range of about 10 eV to about 100 keV.

[0055] After the ion implantation process, the properties of the silicon nitride liner 222 will be altered such that its oxygen diffusion rate is faster and/or its intrinsic stress is reduced. In

addition, portions of the silicon nitride 222 may be sputtered so that the implanted silicon nitride liner 222 may have a smaller thickness compared to the unimplanted silicon nitride liner 218 that is protected by the second patterned mask 234.

[0056] Referring now to Figure 5e, the second patterned mask 234 may be removed after the ion implantation process step (or after the sputtering process if such process is used). A trench filling material 220, preferably silicon oxide, is filled into the trenches 232. It is understood that the trench filling material 220 may in fact be a combination of trench filling materials, such as a combination of CVD silicon oxide and CVD poly-silicon. A chemical mechanical polishing or etch-back step is then performed to planarize the surface of the wafer to give the cross-section as shown in Figure 5e.

[0057] The first patterned mask 230 can then be removed. In the preferred embodiment, the first patterned mask 230 comprises a silicon nitride on a silicon oxide stack, and it may be removed by an etch in hot phosphoric acid followed by an etch in dilute hydrofluoric acid. This gives the cross-section shown in Figure 5f.

[0058] Transistors 236 and 238 can then be formed in the first and second active regions 212a and 212c of Figure 5f, as shown in Figures 6a and 6b. For example, n-channel transistors 236 can be formed in the first active region 212a and p-channel transistors 238 can be formed in the second active region 212c, as shown in Figure 6a. In forming the transistors, n-type doped and/or p-type doped wells (not shown) are formed in the active regions for p-channel and n-channel transistors, respectively. Depending on the conductivity of the substrate 210, one of the wells may be eliminated.

[0059] This is followed by gate dielectric 244 formation. The gate dielectric 244 may be formed by thermal oxidation, thermal oxidation followed by nitridation, chemical vapor

deposition, sputtering, or other techniques known and used in the art for forming transistor gate dielectrics. The gate dielectric may comprise a conventional material such as silicon dioxide or silicon oxynitride with a thickness preferably ranging from about 3 angstroms to about 100 angstroms, preferably about 10 angstroms or less. The gate dielectric 244 may also comprise a high permittivity (high-k) material such as aluminum oxide (Al_2O_3), hafnium oxide (HfO_2), zirconium oxide (ZrO_2), hafnium oxynitride (HfON), hafnium silicate (HfSiO_4), zirconium silicate (ZrSiO_4), lanthanum oxide (La_2O_3) with an equivalent oxide thickness of about 3 angstroms to about 100 angstroms.

[0060] Next, the gate electrode 246 material is deposited. The gate electrode 246 material may be polycrystalline-silicon (poly-Si), poly-crystalline silicon-germanium (poly-SiGe), a refractory metal such as molybdenum and tungsten, compounds such as titanium nitride, or other conducting materials. Implants known as workfunction implants may be introduced in the gate electrode 246 material to alter the workfunction of the electrode. A gate mask (not shown) is deposited over the gate electrode material and patterned to define the gate electrode 246. The underlying gate electrode 246 material is then etched to form the gate electrode 246. The gate electrode 246 is electrically isolated from the channel region 248 by the gate dielectric 244. In the preferred embodiment, the gate electrode 246 material is poly-Si and the gate oxide 244 is silicon oxynitride. In the preferred embodiment, a plasma etch using chlorine and bromine chemistry may be used to etch the gate electrode 246 material with a high etch selectivity with respect to the gate dielectric 244.

[0061] After the definition of the gate electrode 246, the gate mask can be removed. The source and drain extension regions 250 are formed next. This may be achieved by ion implantation, plasma immersion ion implantation (PIII), or other techniques known and used in

the art. Next, a spacer 252 is formed on the sidewalls of the gate electrode 246 by deposition and selective etching of the spacer material. The spacer material may comprise of a dielectric material such as silicon nitride or silicon dioxide.

[0062] The dopants in the source/drain regions 254 may be introduced by ion implantation, PIII, gas or solid source diffusion, or any other techniques known and used in the art. Any implant damage or amorphization can be annealed through subsequent exposure to elevated temperatures. The resistance of the source and drain can also be reduced by strapping the source/drain 254 with a conductive material (not shown). The conductive material can be formed using a self-aligned silicide, also known as salicide, process, or other metal deposition process. The conductive material may be formed on the source and drain regions (as well as the gate electrode 246). Passivation, contact etch, metallization are then performed to complete the device.

[0063] Furthermore, the separately optimized isolation structures of the present invention may be combined with other means of introducing strain in the transistor channel. As illustrated in Figure 6b, a high stress film 260, i.e., a stressor, may be formed selectively over the n-channel transistor 236 in the first active region 212a to enhance the tensile strain in the channel region to improve electron mobility. The high stress film may be a high stress silicon nitride film deposited by plasma-enhanced chemical vapor deposition (PECVD) with an intrinsic stress of larger than about 500 mega-pascals (MPa), and more typically between about 500 MPa and about 1500 MPa. The high stress film or the stressor 260 further increases the tensile strain component in the lattice of the n-channel transistor 236 channel region 248 to further improve the electron mobility.

[0064] A second embodiment method provides another process flow for forming active regions with different strain conditions. The second method embodiment is identical to the first method embodiment in the first few process steps as illustrated in Figure 5a to Figure 5c. To describe the second method embodiment, we begin with the structure of Figure 5c, as illustrated in Figure 7a.

[0065] As shown in Figure 7b, a second patterned mask 234 is used to cover selected regions, including the first active region 212a. The second patterned mask 234 preferably comprises a photoresist. The silicon nitride liner 218 is then removed in regions not covered by the second patterned mask 234. The removal of the silicon nitride liner may be accomplished by etching in a hot phosphoric acid, for example. The second patterned mask 234 may then be removed. Once again, Figure 10 shows an embodiment where the mask 234 protects only a portion of a trench 232.

[0066] A trench filling material 220, preferably silicon oxide, is filled into the trenches. A chemical mechanical polishing or etch back step is then performed to planarize the surface of the wafer to give the cross-section as shown in Figure 7c. The first patterned mask 230 can then be removed. In the preferred embodiment, the first patterned mask 230 comprises a silicon nitride on a silicon oxide stack, and it may be removed by an etch in hot phosphoric acid followed by an etch in dilute hydrofluoric acid. This gives the cross-section as shown in Figure 7d.

[0067] Transistors (not shown in Figure 7d; see e.g., Figure 6b) may then be formed in the first and second active regions 212a and 212c. For example, n-channel transistors may be formed in the first active region 212a and p-channel transistors may be formed in the second active region 212c. The methods of forming the transistors have been described in the first method embodiment and will not be repeated here.

[0068] In the third embodiment method, another process flow is provided for forming active regions with different strain conditions. The starting material is a semiconductor substrate as shown in Figure 8a. Trenches 232 are formed in the semiconductor substrate 210 using a first mask 230, as shown in Figure 8b. A liner oxide 216, such as thermally grown silicon oxide, is then formed on at least the sidewalls of the trenches, as shown in Figure 8c. It is understood that the liner oxide may also be formed by deposition techniques.

[0069] A second patterned mask 235 is formed to cover the second active region 212c, while exposing the first active region 212a, as shown in Figure 8d. The mask 235 may cover all or a portion of the trenches 232. Liner oxide 216 not covered by the second patterned mask may be nitrided. The nitridation process forms a nitrided liner 217 and may include an ion implantation of nitrogen containing species, an anneal in a nitrogen-containing ambient, or exposure to nitrogen containing plasma. This step forms the barrier that will prevent diffusion of oxygen into active area 212a during filling of the trench.

[0070] The second patterned mask 235 is then removed. A chemical mechanical polishing step is then performed to planarize the surface of the wafer to give the cross-section as shown in Figure 8e. The first patterned mask 230 can then be removed. This gives the cross-section as shown in Figure 8f. Transistors (see Figures 6a and 6b) may then be formed in the first and second active regions 212a and 212c of Figure 8f. For example, n-channel transistors may be formed in the first active region and p-channel transistors may be formed in the second active region. The methods of forming the transistors have been described in the first method embodiment.

[0071] Figures 9a and 9b are provided to illustrate that the present invention can be utilized with an SOI substrate. In such a device, an insulating layer 211 is formed over substrate 209.

The active regions 212 can then be formed in a semiconductor layer, e.g., epitaxially grown silicon, that overlies insulating layer 211. Any of the embodiments described above can be formed in a SOI device.

[0072] The SOI embodiments, as exemplified by Figures 9a and 9b, can include strained channel regions, where the strain is enhanced by other techniques. For example, a silicon-germanium layer (not shown) can be included between the insulating layer 211 and the active semiconductor layer 210. This additional layer can cause additional stress. Other techniques could also be utilized.

[0073] Figure 10 illustrates an alternate embodiment. In this embodiment, the techniques described herein are used in a portion of a given trench. For example, Figure 10 shows an embodiment similar to that of Figure 4b. In this case, a nitride liner 218 is formed in each of the trenches and then selectively removed. Referring to Figure 10, the active region 212a is adjacent isolation regions 214a and 214b. Each portion of isolation region 214a/b that is adjacent active area 212a includes a nitride liner. On the other hand, each portion of isolation region 214b/c that is adjacent active region 212b includes no nitride liner. This is accomplished by having the nitride liner 218 formed along one but not both sidewalls of the trench of isolation region 214b. In this manner, active region 212a is under tensile stress and active region 212b is under compressive stress.

[0074] This concept can be utilized with any of the embodiments discussed herein. For example, if an angled implant is used, it is possible to perform an implant such that the nitride liner on one side of the trench is implanted while the nitride liner on the opposing side of the trench is not implanted.

[0075] Although particular embodiments of the invention have been described in detail, it is understood that the invention is not limited correspondingly in scope, but includes all changes, modifications, and equivalents coming within the spirit and terms of the claims appended hereto. Accordingly, the specification and figures are to be regarded in an illustrative rather than a restrictive sense.

WHAT IS CLAIMED IS:

- 1 1. A semiconductor device comprising:
2 a region of semiconductor material;
3 a first isolation trench formed in the region of semiconductor material, the first isolation
4 trench being lined with a first material, the first material being material having a low oxygen
5 diffusion rate, the first isolation trench further being filled with an insulating material;
6 a second isolation trench formed in the region of semiconductor material, the second
7 isolation trench not being lined with the first material, the second isolation trench further being
8 filled with an insulating material;
9 a first transistor formed adjacent the first isolation region; and
10 a second transistor formed adjacent the second isolation region.
- 1 2. The device of claim 1 wherein the second isolation trench is lined with a second material,
2 the second material being different than the first material.
- 1 3. The device of claim 1 wherein the second isolation trench is filled with the insulating
2 material without any liner of a material different than that of the insulating material.
- 1 4. The device of claim 1 wherein the first transistor comprises a transistor of a first
2 conductivity type and the second transistor comprises a transistor of a second conductivity type
3 different than the first conductivity type.
- 1 5. The device of claim 4 wherein the first conductivity type comprises n-type and the
2 second conductivity type comprises p-type.
- 1 6. The device of claim 1 wherein the first isolation trench is lined with a nitride liner.

1 7. The device of claim 6 wherein the second isolation trench is lined with an implanted
2 nitride liner.

1 8. The device of claim 6 wherein second isolation trench is lined with an oxide liner.

1 9. The device of claim 1 wherein the first isolation trench is lined with a nitrided oxide
2 liner.

1 10. The device of claim 9 wherein the second isolation trench is lined with an oxide liner.

1 11. A semiconductor device comprising:
2 a region of semiconductor material;
3 a first active area disposed in a first portion of the semiconductor material;
4 a first isolation region disposed adjacent the first active area, the first isolation region
5 imposing a first type of strain on the first active area;
6 a second active area disposed in a second portion of the semiconductor material; and
7 a second isolation region disposed adjacent the second active area, wherein the second
8 isolation region does not impose the first type of strain on the first active area.

1 12. The device of claim 11 wherein the second isolation region imposes a second type of
2 stress on the second active area.

1 13. The structure of claim 11 wherein the first type of strain comprises an in-plane tensile
2 strain and the second type of strain comprises an in-plane compressive strain.

1 14. The structure of claim 13 wherein the in-plane tensile strain has a magnitude of between
2 about 0.1% and about 2%.

1 15. The structure of claim 14 wherein the in-plane compressive strain has a magnitude of
2 between about 0.1% and about 2%.

1 16. The device of claim 11 wherein the second type of strain comprises substantially no
2 strain.

1 17. The device of claim 11 wherein the first isolation region includes an oxygen resistant
2 liner.

- 1 18. The device of claim 17 wherein the first isolation region includes a nitride liner.
- 1 19. The device of claim 18 wherein the second isolation region does not include a nitride
2 liner.
- 1 20. The device of claim 17 wherein the second isolation region includes a nitride liner that
2 has been implanted with selected ions.
- 1 21. The device of claim 17 wherein the first isolation region includes a nitrided oxide liner.
- 1 22. The device of claim 11 and further comprising an n-channel transistor formed in the first
2 active region and a p-channel transistor formed in the second active region.
- 1 23. The structure of claim 22 and further comprising a tensile stress-inducing, silicon nitride
2 film overlying the n-channel transistor.
- 1 24. The device of claim 11 wherein the first isolation region comprises an oxide liner
2 underlying a silicon nitride liner and wherein the second isolation region comprises an oxide
3 liner underlying an implanted silicon nitride liner.
- 1 25. The device of claim 11 wherein the first and second isolation regions further include a
2 trench filling material.
- 1 26. The structure of claim 25 wherein the trench filling material comprises silicon oxide.
- 1 27. The structure of claim 26 wherein the trench filling material comprises silicon oxide and
2 poly-crystalline silicon.

1 28. The device of claim 11 wherein the region of semiconductor material comprises an upper
2 portion of a silicon substrate.

1 29. The device of claim 11 wherein the region of semiconductor material comprises a silicon
2 layer overlying a silicon germanium layer.

1 30. The device of claim 11 wherein the region of semiconductor material comprises a silicon
2 layer overlying an insulating layer such that the device comprises a silicon-on-insulator device.

1 31. The device of claim 11 wherein the first and second isolation regions comprise shallow
2 trench isolation regions.

1 32. A semiconductor structure comprising:

2 a semiconductor substrate;

3 a first active region disposed in a first portion of the semiconductor substrate, the first
4 active region located between a pair of first isolation regions, each of the first isolation regions
5 including a silicon nitride liner;

6 a second active region disposed in a second portion of the semiconductor substrate, the
7 second active region located between a pair of second isolation regions, each of the second
8 isolation regions including an implanted silicon nitride liner.

1 33. The device of claim 32 and further comprising at least one n-channel transistor formed in
2 the first active region and at least one p-channel transistors formed in the second active region.

1 34. The structure of claim 33 and further comprising a tensile stress silicon nitride film
2 overlying the n-channel transistor.

1 35. The device of claim 32 wherein the first isolation region further comprises an oxide liner
2 underlying the silicon nitride liner and the second isolation region further comprises an oxide
3 liner underlying the implanted silicon nitride liner.

1 36. The device of claim 32 wherein the first and second isolation regions further comprise a
2 trench filling material.

1 37. The structure of claim 36 wherein the trench filling material comprises silicon oxide.

1 38. The structure of claim 37 wherein the trench filling material comprises silicon oxide and
2 poly-crystalline silicon.

- 1 39. The device of claim 32 wherein the first active region experiences an in-plane tensile
2 strain and the second active region experiences an in-plane compressive strain.
- 1 40. The structure of claim 38 wherein the in-plane tensile strain has a magnitude of between
2 about 0.1% and about 2%.
- 1 41. The structure of claim 38 wherein the in-plane compressive strain has a magnitude of
2 between about 0.1% and about 2%.
- 1 42. The device of claim 32 wherein the semiconductor substrate comprises an elemental
2 semiconductor, an alloy semiconductor, or a compound semiconductor.
- 1 43. The structure of claim 42 wherein the semiconductor substrate is a silicon substrate.
- 1 44. The device of claim 32 wherein the semiconductor substrate comprises a silicon layer
2 overlying a silicon germanium layer.
- 1 45. The device of claim 32 wherein the semiconductor substrate comprises a silicon-on-
2 insulator.
- 1 46. The device of claim 32 wherein the isolation regions are shallow trench isolation regions.

- 1 47. A semiconductor structure comprising:
2 a semiconductor substrate;
3 a first active region with an in-plane tensile strain in a first portion of the semiconductor
4 substrate, the first active region located between a pair of first isolation regions, wherein each of
5 the first isolation regions include a silicon nitride liner;
6 a second active region with an in-plane compressive strain in a second portion of the
7 semiconductor substrate, the second active region located between a pair of second isolation
8 regions, wherein the second isolation regions do not include a silicon nitride liner.
- 1 48. The structure of claim 47, further comprising n-channel transistors formed in the first
2 active region and p-channel transistors formed in the second active region.
- 1 49. The structure of claim 47, wherein the first isolation region further comprises of an oxide
2 liner underlying the silicon nitride liner.
- 1 50. The structure of claim 47, wherein the first and second isolation regions further include a
2 trench filling material.
- 1 51. The structure of claim 50 wherein the trench filling material comprises silicon oxide.
- 1 52. The structure of claim 51 wherein the trench filling material comprises silicon oxide and
2 poly-crystalline silicon.
- 1 53. The structure of claim 48, further comprising a tensile stress silicon nitride film overlying
2 the n-channel transistor.

1 54. The structure of claim 47 wherein the in-plane compressive strain has a magnitude of
2 between about 0.1% and about 2%.

1 55. The structure of claim 47 wherein the in-plane tensile strain has a magnitude of between
2 about 0.1% and about 2%.

1 56. The structure of claim 47 wherein the semiconductor substrate comprises an elemental
2 semiconductor, an alloy semiconductor, or a compound semiconductor.

1 57. The structure of claim 56 wherein the semiconductor substrate is a silicon substrate.

1 58. The structure of claim 47 wherein the semiconductor substrate comprises a silicon layer
2 overlying a silicon germanium layer.

1 59. The structure of claim 47 wherein the semiconductor substrate is a silicon-on-insulator
2 substrate.

1 60. The structure of claim 47 wherein the isolation regions are shallow trench isolation
2 regions with a depth of about 200 to about 6000 angstroms.

- 1 61. A method of forming a semiconductor structure, the method comprising:
2 providing a semiconductor substrate;
3 forming trenches in the semiconductor substrate;
4 forming a silicon nitride liner layer overlying a silicon oxide liner layer in the trenches;
5 implanting ions into the silicon nitride liner in selected trenches; and
6 filling the trenches with a trench filling material.
- 1 62. The method of claim 61 wherein the ions are selected from the group consisting of
2 silicon, germanium, nitrogen, helium, neon, argon, and xenon, and combinations thereof.
- 1 63. The method of claim 61 wherein a first active region is located adjacent a trench with a
2 silicon nitride liner, and a second active region is located adjacent a trench with an implanted
3 silicon nitride liner, the method further comprising:
4 forming an n-channel transistor in the first active region; and
5 forming a p-channel transistor in the second active region.
- 1 64. The method of claim 63 and further comprising forming a high stress film over one of the
2 n-channel transistor or the p-channel transistor.
- 1 65. The method of claim 64 wherein the high stress film is formed over the n-channel
2 transistor and wherein the high stress film comprises a silicon nitride film with intrinsic tensile
3 stress.
- 1 66. The method of claim 64 wherein the high stress film is formed by plasma-enhanced
2 chemical vapor deposition.

1 67. The method of claim 61 wherein the semiconductor substrate comprises an elemental
2 semiconductor, an alloy semiconductor, or a compound semiconductor.

1 68. The method of claim 67 wherein the semiconductor substrate is a silicon substrate.

1 69. The method of claim 61 wherein the semiconductor substrate comprises a silicon layer
2 overlying a silicon germanium layer.

1 70. The method of claim 61 wherein the semiconductor substrate is a silicon-on-insulator
2 substrate.

1 71. The method of claim 61 wherein the trenches are formed by anisotropic plasma etching
2 and the depth of the trenches is in the range of about 200 to about 6000 angstroms.

1 72. The method of claim 61 wherein the silicon nitride liner layer is formed by chemical
2 vapor deposition.

- 1 73. A method of forming a semiconductor structure, the method comprising:
2 providing a semiconductor substrate;
3 forming a plurality of trenches in the semiconductor substrate;
4 forming silicon nitride liner layer overlying a silicon oxide liner layer in the trenches;
5 removing the silicon nitride liner in some but not all of the plurality of the trenches; and
6 filling each trench in the plurality of trenches with a trench filling material.
- 1 74. The method of claim 73 wherein a first active region is formed between a pair of trenches
2 with a silicon nitride liner, and a second active region is formed between a pair of trenches
3 without a silicon nitride liner.
- 1 75. The method of claim 74 and further comprising forming an n-channel transistor in the
2 first active region and forming a p-channel transistor in the second active region.
- 1 76. The method of claim 75 and further comprising forming a high stress film over the n-
2 channel transistor or the p-channel transistor.
- 1 77. The method of claim 76 wherein the high stress film is formed over the n-channel
2 transistor and wherein the high stress film comprises a silicon nitride film with intrinsic tensile
3 stress.
- 1 78. The method of claim 76 wherein the high stress film is formed by plasma-enhanced
2 chemical vapor deposition.
- 1 79. The method of claim 73 wherein the semiconductor substrate comprises a silicon
2 substrate.

1 80. The method of claim 73 wherein the semiconductor substrate comprises a silicon layer
2 overlying a silicon germanium layer.

1 81. The method of claim 73 wherein the semiconductor substrate comprises a silicon-on-
2 insulator substrate.

1 82. The method of claim 73 wherein the trenches are formed by anisotropic plasma etching
2 and the depth of the trenches is in the range of about 200 to about 6000 angstroms.

1 83. The method of claim 73 wherein the silicon nitride liner layer is formed by chemical
2 vapor deposition.

- 1 84. A method of forming a semiconductor structure, the method comprising:
2 providing a semiconductor substrate;
3 forming trenches in the semiconductor substrate;
4 forming an oxide liner in the trenches;
5 nitriding the oxide liner in selected ones of the trenches but not nitriding the oxide liner in
6 unselected ones of the trenches; and
7 filling the selected and the unselected ones of the trenches with a trench filling material.
- 1 85. The method of claim 84 wherein a first active region is located adjacent a trench with a
2 nitrided oxide liner, and a second active region is located adjacent a trench with an oxide liner,
3 the method further comprising:
4 forming an n-channel transistor in the first active region; and
5 forming a p-channel transistor in the second active region.
- 1 86. The method of claim 85 and further comprising forming a high stress film over one of the
2 n-channel transistor or the p-channel transistor.
- 1 87. The method of claim 86 wherein the high stress film is formed over the n-channel
2 transistor and wherein the high stress film comprises a silicon nitride film with intrinsic tensile
3 stress.
- 1 88. The method of claim 86 wherein the high stress film is formed by plasma-enhanced
2 chemical vapor deposition.
- 1 89. The method of claim 84 wherein the semiconductor substrate comprises a silicon
2 substrate.

- 1 90. The method of claim 84 wherein the semiconductor substrate comprises a silicon layer
2 overlying a silicon germanium layer.
- 1 91. The method of claim 84 wherein the semiconductor substrate comprises a silicon-on-
2 insulator substrate.
- 1 92. The method of claim 84 wherein the trenches are formed by anisotropic plasma etching
2 and the depth of the trenches is in the range of about 200 to about 6000 angstroms.
- 1 93. The method of claim 84 wherein the oxide liner is formed by thermal oxidation of a
2 surface within the trench.
- 1 94. The method of claim 84 wherein nitriding the oxide liner comprises implanting a nitrogen
2 containing species.
- 1 95. The method of claim 84 wherein nitriding the oxide liner comprises exposing the oxide
2 liner to a nitrogen-containing plasma.
- 1 96. The method of claim 84 wherein nitriding the oxide liner comprises annealing the oxide
2 liner in a nitrogen-containing ambient.

1 97. A method of forming a semiconductor device, the method comprising:

2 forming a plurality of trenches in a semiconductor region;

3 lining each trench in the plurality of trenches with a liner;

4 modifying the liner in some but not all of the plurality of trenches;

5 filling each trench in the plurality of trenches with an insulating material.

1 98. The method of claim 97 wherein filling each trench comprises filling each trench with an
2 oxide.

1 99. The method of claim 97 wherein lining each trench comprises lining each trench in the
2 plurality of trenches with a nitride liner.

1 100. The method of claim 99 wherein modifying the liner comprises implanting ions into the
2 liner.

1 101. The method of claim 100 wherein the ions are selected from the group consisting of
2 silicon, germanium, nitrogen, helium, neon, argon, and xenon, and combinations thereof.

1 102. The method of claim 97 wherein modifying the liner comprises removing the liner from
2 some but not all of the plurality of trenches.

1 103. The method of claim 97 wherein lining each trench comprises lining each trench with an
2 oxide liner.

1 104. The method of claim 103 wherein modifying the liner comprises nitriding some but not
2 all of the oxide liners.

1 105. The method of claim 97 wherein a first active region is located adjacent a trench with a
2 modified liner, and a second active region is located adjacent a trench with an unmodified liner,
3 the method further comprising:

4 forming an n-channel transistor in the first active region; and
5 forming a p-channel transistor in the second active region.

1 106. The method of claim 97 wherein a first active region is located adjacent a trench with a
2 modified liner, and a second active region is located adjacent a trench with an unmodified liner,
3 the method further comprising:

4 forming an p-channel transistor in the first active region; and
5 forming a n-channel transistor in the second active region.