

LOW PRESSURE PROCESS FOR SYNTHESIS OF $\text{Pt}(\text{PF}_3)_4$ INVOLVING A SOLUBLE INTERMEDIATE AND STORAGE OF OBTAINED $\text{Pt}(\text{PF}_3)_4$

Cross Reference to Related Applications

[0001] This application claims the benefit of priority under 35 U.S.C. § 119 (a) and (b) to US Patent Application No. 17/546,169, filed December 9, 2021, the entire contents of which are incorporated herein by reference.

Technical Field

[0002] The present invention relates to synthesis and storage of $\text{Pt}(\text{PF}_3)_4$ used as a precursor in film forming compositions. $\text{Pt}(\text{PF}_3)_4$ is synthesized from a platinum compound selected from $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) or $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ (Hal = F, Cl, Br or I; $x = 1, 2$), a metal powder and PF_3 at low pressure in an anhydrous solvent capable of dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, a reaction intermediate, wherein $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ may be formed from $\text{Pt}(\text{Hal})_2$ and PF_3 . The obtained $\text{Pt}(\text{PF}_3)_4$ is then stored under air and moisture free conditions at room temperature in apparatus and ampoules fabricated from metal such as stainless steel and preferably having a passivated or electro-polished inner surface.

Background


[0003] Chemical vapor deposition (CVD) and atomic layer deposition (ALD) methods are gaining significant attentions for fabrication of catalysts and batteries at industrial scales. A proper precursor for a high throughout-put industrial process should have a high vapor pressure at ideally room temperature, to ensure a maximum dosage in the shortest time and at temperatures that do not compromise the precursor stability. Platinum is widely employed as catalyst and a wide variety of materials containing platinum on support are available to the date. Nonetheless, the processes applying deposition of platinum from the vapor phase are rare due to lack of proper platinum precursors.

[0004] For instance, platinum hexafluoride (PtF_6 , CAS # 13693-05-5), a solid at room temperature, although being volatile at room temperature, is rarely applied as deposition precursor due to very strong oxidizing nature and correspondingly very strong etching properties. A widely cited for deposition processes $(\text{MeCp})\text{PtMe}_3$ (CAS # 94442-22-5) has 1 Torr vapor pressure at 69°C, but start gradually decomposing at 50°C (Journal of Vacuum Science & Technology, B: Microelectronics and Nanometer Structures (1990), 8(6), 1826-9), precluding utilization of the given compound for the high throughout-put process.


[0005] Complex $\text{Pt}(\text{PF}_3)_4$ (CAS # 19529-53-4) is a volatile liquid at room temperature with the vapor pressure 36 Torr at room temperature (R.D. Sanner et al., Report (1989), (UCRL-53937;

Order No. DE90000902)), almost ideal potential precursor for Pt deposition from the vapor phase. However, the compound has a very limited commercial availability. The reason for non-scalability may be technical difficulties associated with the synthesis of $\text{Pt}(\text{PF}_3)_4$, almost ideal potential precursor for Pt deposition from the vapor phase. However, the compound has a very limited commercial availability (only from one supplier in Japan [Japan Advanced Chemicals, in gram scale) and so far no suitable ALD process has been reported using this chemical. The reason for non-scalability may be technical difficulties associated with the synthesis of $\text{Pt}(\text{PF}_3)_4$ at gram scale level and even more difficult in manners that could be scaled up industrially with acceptable yield and realistic operating conditions.

[0006] The original synthesis of $\text{Pt}(\text{PF}_3)_4$ in gram scale and yield 70-80% was performed by reaction (1) at 100-150 atm. PF_3 and 100°C applying "fine and oxide free copper powder" (Angew. Chem. Int. Ed. 1965, 4, 521). The synthesis recipe is only one sentence in reference and later references applying the same method, without any details on reaction and equipment. This reaction requires applying PF_3 gas onto a mixture of two solids (PtCl_2 and Cu powder) at high pressure and is barely scalable for the skilled-in-the-art chemists.



Notable that the reaction of PtCl_2 and PF_3 (2) at 60-80°C and under the undisclosed pressure afforded $\text{Pt}(\text{PF}_3)_4$ only in 1% yield (Inorg. Nucl. Chem. Letters, Vol. 4, pp. 275-278, 1968). Such low yield makes this approach impossible to implement for industrial applications.





The flow reaction (3) from the same starting compounds under the undisclosed pressure produced only donor – acceptor adducts (Inorg. Nucl. Chem. Letters, Vol. 4, pp. 275-278, 1968).



[0007] Compounds $\text{PtCl}_2(\text{PF}_3)_2$ and $[\text{PtCl}_2(\text{PF}_3)]_2$ were synthesized from solid PtCl_2 and PF_3 gas (J. Chatt, A.A. Williams, J. Chem. Soc. [London] 1951, 3061). Solid compounds may react with PF_3 under the undisclosed "higher" pressure forming $\text{Pt}(\text{PF}_3)_4$, according to one sentence on page 200 of Zeitschrift fur Anorganische und Allgemeine Chemie, Band 364, 1969, p192-208. One may assume that the "higher pressure" is 40-150 atm since this range is reported in Zeitschrift fur Anorganische und Allgemeine Chemie, Band 364, 1969, p192-208 for synthesis of $\text{Pt}(\text{PF}_3)_4$. Compound $\text{PtCl}_2(\text{PF}_3)_2$ is soluble in a polar solvent CDCl_3 and its NMR was reported by J. Chem. Res., Syn., 1981, 2, 38. Solubility of $\text{PtCl}_2(\text{PF}_3)_2$ in benzene was reported to be "low" and the molar concentrations were 0.005 – 0.01M and melting point of $\text{PtCl}_2(\text{PF}_3)_2$ is 118.3°C by J. Chem. Soc. [London] 1951, 3061. FTIR spectra of $\text{PtCl}_2(\text{PF}_3)_2$ is disclosed in Journal of Chemical Research, Synopses (1981), (2), 37.



[0008] Alternatively, preparation of $\text{Pt}(\text{PF}_3)_4$ achieved in a rarely available rotating autoclave in gram scale by reaction (4) under 40 atm of PF_3 with the 95% yield (Zeitschrift fur

Anorganische und Allgemeine Chemie. Band 364. 1969, 192-208).





[0009] It is notable that the reaction without copper (5) produces PF_3Cl_2 , which complicates purification of $\text{Pt}(\text{PF}_3)_4$ due to comparable volatility (Zeitschrift für Anorganische und Allgemeine Chemie. Band 364. 1969, 192-208). Although addition of copper reduces amount of PF_3Cl_2 , this implies that reactions (4) and (5) may afford impure $\text{Pt}(\text{PF}_3)_4$, which does not meet the quality standards for CVD and ALD precursors. Noteworthy, reaction (4) also requires mixing two solids and contacting them with PF_3 gas, raising already mentioned scalability concerns. The reaction of PtCl_4 with excess PF_3 makes the scale-up even less realistic.

[0010] RU 2478576C2 discloses a two-step process under 2-6.3 MPa (19.7-62.2 atm) of PF_3 (6a and 6b), where CuO is reduced in the same autoclave prior to introduction of K_2PtCl_6 and PF_3 .



[0011] RU 2201463C1, US 7044995B2, Terekhov et al. (Terekhov et al., International Symposium on Recycling of Metals and Engineered Materials, Proceedings, 4th, Oct. 22-25, 2000, pp. 487-491) and Kovtun et al. (Publications of the Australasian Institute of Mining and Metallurgy (2002), 2/2002, 367-372) disclose a platinum extraction from ore by interaction of "PGM matte" or "raw material" with PF_3 gas forming a volatile $\text{Pt}(\text{PF}_3)_4$. The raw materials were assumed to contain Pt metal and interact with PF_3 by (7d). However, Pt and PF_3 afforded platinum compound F_3PPt as first reported in 1891 (H. Moissan, Bull. Soc. Chim. France 5, 454 (1891)) and this compound was considered to be analogous to $(\text{PCl}_3)\text{PtCl}_2$.



[0012] In addition, according to Chem. Ber. 101, 138 -142 (1968), Pt metal does not react with PF_3 at any conditions. US 7044995 B2 discloses that finely dispersed Pt metal (platinum black, particles sizes < 20 μm) does not react with PF_3 and only "activated" Pt metal obtained by the multi-step procedure (7a-7c) and applying the reduction with hydrogen under the ultrasonic irradiation in step (7c) could react with PF_3 .

[0013] Solvent effect may be negative for reaction starting from PtCl_2 , because according to Zhurnal Neorganicheskoi Khimii (1970), 15(9), 2445-8, in contrast to the neat reaction of $\text{PtCl}_2 + \text{I}_2 = \text{PtCl}_2\text{I}_2$, reaction of these reagents in organic solvents gave various products but not PtCl_2I_2 . Several classes of solvents react with PF_3 , PtCl_2 , and reduced Pt species, and hence may not be used for synthesis of $\text{Pt}(\text{PF}_3)_4$. These classes of the solvents include primary

amines, since they react with PF_3 producing RNHPF_2 , $(\text{RNH})_2\text{PF}_2\text{H}$, and $(\text{RNH})_2\text{PF}$ (See J. Chem. Soc. A (1970), (11), 1935-8). Tertiary amines, e.g. NMe_3 , NEt_3 are forming adducts with PF_3 (See Inorganic Chemistry (1963), 2, 384-8). Alcohols and PF_3 form organic phosphites (See Transactions of the Illinois State Academy of Science (1936), 29 (No. 2), 89-91). General patterns of reactivity of $\text{P}(\text{Hal})_3$ ($\text{Hal} = \text{Cl}, \text{Br}$) toward alcohols are well documented. Dienes, olefins, unsaturated aldehydes, ketones reacts with PF_3 forming addition compounds as was shown for PCl_3 and PBr_3 in (See Uspekhi Khimii (1968), 37(5), 745-77). Acetone reacts with PF_3 and Pt(II) compounds (See Zhurnal Obshchei Khimii (1975), 45(3), 512-18; Inorganica Chimica Acta (1997), 264(1-2), 297-303). Halocarbons may react with Pt compounds under reaction conditions via oxidative addition as was shown in selected examples in Organometallics (2019), 38(10), 2273; Organometallics 2009, 28, 1358–1368; and Organometallics (1987), 6(12), 2548; oxidative addition of alkyl and aryl halides to platinum complexes is well documented reaction.

[0014] In conclusion, the existing synthesis approaches for $\text{Pt}(\text{PF}_3)_4$ strongly depend on the reaction conditions, while changing in conditions may significantly reduce the yield of $\text{Pt}(\text{PF}_3)_4$ or afford different products indicating a lack of robustness of the process, and no synthesis process has been reported so far requiring a PF_3 pressure inferior to 3 MPa (29.6 atm, 420 psig) as claimed in RU 2478576C2. Most of syntheses require special equipment or conditions not commonly available for scaling of processes to large scale, such as high pressure autoclaves. In particular, the existing methods are lacking of technical details and a purity of $\text{Pt}(\text{PF}_3)_4$ has not been reported in any references. Further, all the disclosed methods are essentially dry approaches which also present significant challenges for scale-up to industrial scale.

[0015] Numeral references for catalytic transformation of hydrocarbons by platinum compounds exist, such as, Journal of the American Chemical Society (2002), 124(42), 12550-12556. A catalytic activity of Pt compounds was illustrated for model systems $\text{Pt}_4(\text{PF}_3)_8$ - saturated and aromatic cyclic hydrocarbons in Jackson et al., J. Am. Chem. Soc. 1997, 119, 7567-7572. Namely small platinum clusters generated from $\text{Pt}_4(\text{PF}_3)_8$ react with a variety of saturated and aromatic cyclic hydrocarbons (cyclohexane, benzene, toluene). Jackson et al. illuminate a catalytic and dehydrogenation behavior of platinum. Hence one may assume that introduction of a hydrocarbon solvent in the reaction system followed by heating could lead to a mixture of products due to various catalytic reactions and may be considered as not favorable idea for selective synthesis of $\text{Pt}(\text{PF}_3)_4$. Owing to these reasons, $\text{Pt}(\text{PF}_3)_4$ was never synthesized and operated in organic solvents and only anhydrous HF and SO_2 were applied as solvents to study $\text{Pt}(\text{PF}_3)_4$ chemistry (Dreus et al., Chem. Eur. J. 2008, 14, 4280 – 4286).

[0016] It would be a significant advancement to provide a method capable of a scale up production of $\text{Pt}(\text{PF}_3)_4$ in a high yield, since up to date a potentially ideal $\text{Pt}(\text{PF}_3)_4$ precursor has not applied only due to absence of scalable method.

Summary

[0017] Disclosed is a method for synthesizing $\text{Pt}(\text{PF}_3)_4$ (CAS # 19529-53-4), the method comprising the steps of:

dissolving a platinum compound having a general formula, $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, in an anhydrous solvent forming a $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution, wherein Hal = F, Cl, Br or I, $x = 1, 2$;

adding a metal powder and excess amount of PF_3 into the $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution; and forming $\text{Pt}(\text{PF}_3)_4$ through a reaction between $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, PF_3 and the metal powder under a reaction condition. The disclosed methods may include one or more of the following aspects:

- the reaction condition including a reaction temperature ranging from approximately -120-200°C;
- the reaction condition including a reaction temperature ranging from approximately 30-200°C;
- the reaction condition including a reaction temperature ranging from room temperature to approximately 180°C;
- the reaction condition including a reaction temperature ranging from room temperature to approximately 130°C;
- the reaction condition including a reaction temperature ranging from approximately 80-130°C;
- the reaction condition including a reaction pressure ranging from approximately 10 psig to approximately 3000 psig;
- the reaction condition including a reaction pressure ranging from approximately 20 psig to approximately 1000 psig;
- the reaction condition including a reaction pressure ranging from approximately 20 to approximately 300 psig;
- the reaction condition including a reaction pressure below approximately 300 psig;
- the anhydrous solvent having a boiling point higher than 150°C;
- the anhydrous solvent having a boiling point higher than 200°C;
- the metal powder being a copper, zinc or aluminum powder;
- the metal powder being a copper powder;
- the metal powder being a zinc powder;
- the metal powder being an aluminum powder;
- the metal powder having an electrode potential lower than that of Pt;
- the metal powder not interacting with PF_3 and not forming complexes with PF_3 under the reaction conditions;

- the metal powder having a proper particle size range allowing it to stay in a powder form during the reaction process;
- the metal powder having a particle size ranging from 200 – 900 microns;
- the metal powder having a particle size ranging from 300 – 500 microns;
- further comprising the step of
 - synthesizing the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) that includes the steps of:
 - dispersing a platinum precursor having a general formula, $\text{Pt}(\text{Hal})_2$, into the anhydrous solvent forming a suspension of $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ;
 - introducing PF_3 into the suspension of $\text{Pt}(\text{Hal})_2$; and
 - forming the solution of the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) in the anhydrous solvent therefrom through a reaction of PF_3 and $\text{Pt}(\text{Hal})_2$;
- the platinum precursor $\text{Pt}(\text{Hal})_2$ being anhydrous;
- the platinum precursor $\text{Pt}(\text{Hal})_2$ being PtCl_2 ;
- the platinum precursor $\text{Pt}(\text{Hal})_2$ being anhydrous PtCl_2 ;
- the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , $x = 1, 2$) being anhydrous;
- the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , $x = 1, 2$) being $\text{PtCl}_2(\text{PF}_3)_2$;
- the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , $x = 1, 2$) being anhydrous $\text{PtCl}_2(\text{PF}_3)_2$;
- further comprising the steps of:
 - purifying $\text{Pt}(\text{PF}_3)_4$ in a trap made of metal under air and moisture free conditions; and
 - storing the purified $\text{Pt}(\text{PF}_3)_4$ under air and moisture free conditions in a container made of the metal,
- wherein the step of storing includes the steps of
 - removing moisture from the inner surface of the container; and
 - electro-polishing the inner surface of the container, or
 - passivating the container with PF_3 before introducing the purified $\text{Pt}(\text{PF}_3)_4$;
- the metal for the trap being selected from carbon steel, stainless steel, or stainless steel 316 alloy, respectively;
- the metal for the container being selected from carbon steel, stainless steel, or stainless steel 316 alloy, respectively;
- the anhydrous solvent being a hydrocarbon solvent;
- the hydrocarbon solvent being selected from an oxyhydrocarbon solvent having a general formula $(\text{C}_n\text{H}_{2n+1})_2\text{O}$ ($n \geq 1$) and $\text{H}_3\text{C}(\text{O}(\text{CH}_2)_2)_n\text{OCH}_3$ ($n \geq 1$);
- the hydrocarbon solvent being selected from an arene solvent having a general formula $(\text{C}_n\text{H}_{2n+1})_x\text{C}_6\text{H}_{6-x}$ ($x \geq 1, n \geq 1$);

- the hydrocarbon solvent being selected from an alkane solvent having a general formula C_nH_{2n+2} ($n \geq 1$);
- the anhydrous solvent being a dried alkane solvent selected from decane, di-, tri-, tetra-, penta- and hexadecane, the like;
- the anhydrous solvent being a dried arene solvent selected from xylene, mesithylene, cymene, pentylbenzene, diisopropylbenzene, diisobutylbenzene, or the like;
- the anhydrous solvent being a dried ether solvent selected from dibutyl ether, dihexyl ether, dioctyl ether, dimethyl ether of diethylene glycol, triethylene glycol dimethyl ether, tetraethylene glycol dimethyl ether or the like;
- the anhydrous solvent being an arene solvent selected from xylene, mesithylene, cymene, pentylbenzene, diisopropylbenzene, diisobutylbenzene or the like;
- the dried ether solvent being preferably dibutyl ether, dihexyl ether, dioctyl ether, triethylene glycol dimethyl ether, tetraethylene glycol dimethyl ether;
- the dried arene solvent being preferably xylene, mesithylene, cymene, pentylbenzene, diisopropylbenzene, diisobutylbenzene;
- the dried alkane solvent being preferably di-, tri-, tetra-, penta- and hexadecane as well as a mixture of alkanes known as a mineral oil;
- the anhydrous solvent being capable of dissolving the reaction intermediate;
- the anhydrous solvent being capable of dissolving $Pt(Hal)_2(PF_3)_x$ ($Hal = F, Cl, Br$ or $I, x = 1, 2$);
- the anhydrous solvent being capable of dissolving $PtCl_2(PF_3)_2$;
- the anhydrous solvent not reacting with $Pt(PF_3)_4$;
- the anhydrous solvent not reacting with $Pt(Hal)_2$ ($Hal = F, Cl, Br$ or I);
- the anhydrous solvent not reacting with $PtCl_2$;
- the anhydrous solvent being xylene;
- the anhydrous solvent being hexadecane;
- a yield of $Pt(PF_3)_4$ being in a range of approximately 70-99.9%;
- a yield of $Pt(PF_3)_4$ being in a range of approximately 70-95%;
- a yield of $Pt(PF_3)_4$ being in a range of approximately 70-93%;
- a purity of $Pt(PF_3)_4$ being more than 99% by weight;
- a purity of $Pt(PF_3)_4$ being more than 99.5% by weight;
- a purity of $Pt(PF_3)_4$ being approximately 90-99.9% by weight;
- a purity of $Pt(PF_3)_4$ being approximately 99.0-99.9% by weight;
- a purity of $Pt(PF_3)_4$ being approximately 99.5-99.9% by weight; and
- the formed $Pt(PF_3)_4$ being scalable to large industrial scale.

[0018] Also, disclosed is a method for manufacture and storage of $Pt(PF_3)_4$ (CAS # 19529-53-

4), the method comprising the steps of:

- a) forming a suspension of a platinum precursor $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , and a metal powder in an anhydrous solvent;
- b) introducing excess amount of PF_3 into the suspension of $\text{Pt}(\text{Hal})_2$ and the metal powder;
- c) forming a soluble reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ in the anhydrous solvent through a reaction of PF_3 and $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$, under a low pressure condition;
- d) forming $\text{Pt}(\text{PF}_3)_4$ from a reaction between $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, the metal powder and PF_3 in the anhydrous solvent;
- e) purifying $\text{Pt}(\text{PF}_3)_4$ under air and moisture free conditions in a trap made of metal; and
- f) storing the purified $\text{Pt}(\text{PF}_3)_4$ under the air and moisture free conditions in a container made of the metal. The disclosed method may include one or more of the following aspects:

- the platinum precursor $\text{Pt}(\text{Hal})_2$ being PtCl_2 ;
- the anhydrous solvent having a boiling point higher than 150°C ;
- the anhydrous solvent having a boiling point higher than 200°C ;
- the anhydrous solvent being a hydrocarbon solvent selected from an oxyhydrocarbon solvent having a general formula $(\text{C}_n\text{H}_{2n+1})_2\text{O}$ ($n \geq 1$) and $\text{H}_3\text{C}(\text{O}(\text{CH}_2)_2)_n\text{OCH}_3$ ($n \geq 1$), an arene solvent having a general formula $(\text{C}_n\text{H}_{2n+1})_x\text{C}_6\text{H}_{6-x}$ ($x \geq 1, n \geq 1$) or an alkane solvent having a general formula $\text{C}_n\text{H}_{2n+2}$ ($n \geq 1$);
- the anhydrous solvent being xylene or hexadecane;
- the anhydrous solvent being capable of dissolving the reaction intermediate;
- the anhydrous solvent being capable of dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , $x = 1, 2$);
- the anhydrous solvent being capable of dissolving $\text{PtCl}_2(\text{PF}_3)_2$;
- the anhydrous solvent not reacting with $\text{Pt}(\text{PF}_3)_4$;
- the anhydrous solvent not reacting with $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I);
- the anhydrous solvent not reacting with PtCl_2 ;
- a reaction temperature ranging from approximately 30 - 200°C ;
- a reaction temperature ranging from approximately 80 - 130°C ;
- the low pressure condition being a pressure below about 300 psig;
- the low pressure condition being a pressure ranging from approximately 20 to 300 psig;
- the metal powder being a copper, zinc or aluminum powder;
- the metal powder being a copper powder;

- the metal powder having an electrode potential lower than that of Pt;
- the metal powder not interacting with PF_3 and not forming complexes with PF_3 under the reaction conditions;
- the metal powder having a proper particle size range allowing it to stay in a powder form during the reaction process;
- the metal powder having a particle size ranging from 200 – 900 microns;
- the metal powder having a particle size ranging from 300 – 500 microns;
- a yield of $\text{Pt}(\text{PF}_3)_4$ being in the range of approximately 70-99.9%;
- a yield of $\text{Pt}(\text{PF}_3)_4$ being in a range of approximately 70-95%;
- a yield of $\text{Pt}(\text{PF}_3)_4$ being in a range of approximately 70-93%;
- a purity of $\text{Pt}(\text{PF}_3)_4$ being approximately 90-99.9 wt.% after purification;
- a purity of $\text{Pt}(\text{PF}_3)_4$ being 99.0-99.9 wt.% after purification;
- the metal for the trap and the metal for the container being selected from carbon steel, stainless steel, or stainless steel 316 alloy, respectively; and
- further comprising the steps of:
 - electro-polishing the inner surface of the container, or
 - passivating the container with PF_3 before introducing of the purified $\text{Pt}(\text{PF}_3)_4$.

[0019] Also, disclosed is a method for manufacture and storage of $\text{Pt}(\text{PF}_3)_4$ (CAS # 19529-53-4), the method comprising the steps of:

- a) forming a suspension of a platinum precursor $\text{Pt}(\text{Cl})_2$ in an anhydrous solvent selected from xylene or hexadecane;
- b) introducing excess amount of PF_3 into the suspension of $\text{Pt}(\text{Cl})_2$ to form a solution of $\text{Pt}(\text{Cl})_2(\text{PF}_3)_x$ ($x = 1, 2$) in the anhydrous solvent therefrom through a reaction of PF_3 and $\text{Pt}(\text{Cl})_2$;
- c) adding a copper powder into the solution of $\text{Pt}(\text{Cl})_2(\text{PF}_3)_x$ ($x = 1, 2$);
- d) forming $\text{Pt}(\text{PF}_3)_4$ from a reaction between the copper powder, PF_3 and $\text{Pt}(\text{Cl})_2(\text{PF}_3)_x$ in the anhydrous solvent in a reaction temperature ranging from 30-200°C and a reduced PF_3 pressure ranging from 20 to 300 psig;
- e) purifying $\text{Pt}(\text{PF}_3)_4$ under air and moisture free conditions in a trap made of stainless steel; and
- f) storing the purified $\text{Pt}(\text{PF}_3)_4$ under the air and moisture free conditions in a container made of the stainless steel, wherein the inner surface of the container is electro-polished or passivated with PF_3 . The disclosed method may include one or more of the following aspects:
 - the copper powder having a particle size ranging from 200 – 900 microns; and
 - the copper powder having a particle size ranging from 300 – 500 microns.

Notation and Nomenclature

[0020] The following detailed description and claims utilize a number of abbreviations, symbols, and terms, which are generally well known in the art. While definitions are typically provided with the first instance of each acronym, such as, stainless steel (SS). Certain abbreviations, symbols, and terms are used throughout the following description and claims, and include the followings.

[0021] The following detailed description and claims utilize a number of abbreviations, symbols, and terms, which are generally well known in the art.

[0022] As used herein, the indefinite article "a" or "an" means one or more.

[0023] As used herein, "about" or "around" or "approximately" in the text or in a claim means $\pm 10\%$ of the value stated.

[0024] As used herein, "room temperature" in the text or in a claim means from approximately 18°C to approximately 25°C.

[0025] As used herein, "atmospheric pressure" in the text or in a claim means approximately 1 atm.

[0026] The standard abbreviations of the elements from the periodic table of elements are used herein. It should be understood that elements may be referred to by these abbreviation (e.g., Si refers to silicon, N refers to nitrogen, O refers to oxygen, C refers to carbon, H refers to hydrogen, Hal refers to halogens, which are F, Cl, Br, I).

[0027] The unique CAS registry numbers (i.e., "CAS") assigned by the Chemical Abstract Service are provided to identify the specific molecules disclosed.

[0028] As used herein, the term "hydrocarbon" refers to a saturated or unsaturated function group containing exclusively carbon and hydrogen atoms.

[0029] As used herein, the term "low pressure", "low reaction pressure" or "low PF₃ pressure" refers to a pressure below 300 psig or below 20 atm. The same applies to "reduced pressure" that refers to a pressure reduced or lowered to below 300 psig or 20 atm. In some cases, "low pressure", "low reaction pressure" or "low PF₃ pressure" may refer to a pressure range ranging from 20 psig to 300 psig.

[0030] Ranges may be expressed herein as from about one particular value, and/or to about another particular value. When such a range is expressed, it is to be understood that another embodiment is from the one particular value and/or to the other particular value, along with all combinations within said range. Any and all ranges recited herein are inclusive of their endpoints (i.e., x= 1 to 4 or x ranges from 1 to 4 includes x= 1, x=4, and x=any number in between), irrespective of whether the term "inclusively" is used.

[0031] Reference herein to "one embodiment" or "an embodiment" means that a particular feature, structure, or characteristic described in connection with the embodiment may be included in at least one embodiment of the invention. The appearances of the phrase "in one

embodiment" in various places in the specification are not necessarily all referring to the same embodiment, nor are separate or alternative embodiments necessarily mutually exclusive of other embodiments. The same applies to the term "implementation."

[0032] As used in this application, the word "exemplary" is used herein to mean serving as an example, instance, or illustration. Any aspect or design described herein as "exemplary" is not necessarily to be construed as preferred or advantageous over other aspects or designs. Rather, use of the word exemplary is intended to present concepts in a concrete fashion.

[0033] Additionally, the term "or" is intended to mean an inclusive "or" rather than an exclusive "or". That is, unless specified otherwise, or clear from context, "X employs A or B" is intended to mean any of the natural inclusive permutations. That is, if X employs A; X employs B; or X employs both A and B, then "X employs A or B" is satisfied under any of the foregoing instances. In addition, the articles "a" and "an" as used in this application and the appended claims should generally be construed to mean "one or more" unless specified otherwise or clear from context to be directed to a singular form.

Brief Description of the Drawings

[0034] The foregoing and various other aspects, features, and advantages of the present invention, as well as the invention itself, may be more fully appreciated with reference to the following detailed description of the invention when considered in connection with the following drawings. The drawings are presented for the purpose of illustration only and are not intended to be limiting of the invention, in which:

FIG. 1 is a block diagram of exemplary disclosed system of synthesizing $\text{Pt}(\text{PF}_3)_4$;

FIG. 2a is a flowchart of an exemplary disclosed process of synthesizing $\text{Pt}(\text{PF}_3)_4$ starting with $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I);

FIG. 2b is a flowchart of an exemplary disclosed process of synthesizing $\text{Pt}(\text{PF}_3)_4$ starting with $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ (x = 1, 2; Hal = F, Cl, Br or I);

FIG. 3 is ^{19}F NMR spectra of $\text{PtCl}_2(\text{PF}_3)_2$ crystals and supernatant hexadecane solution of reaction mixture stopped on the stage $\text{PtCl}_2(\text{PF}_3)_2$; and

FIG. 4 is a graph for the $\text{Pt}(\text{PF}_3)_4$ assay and relative amount of impurities over time in an electro-polished stainless-steel miniature canister at room temperature.

Description of Preferred Embodiments

[0035] Disclosed are methods for synthesis, producing, manufacture and storage of $\text{Pt}(\text{PF}_3)_4$ (CAS # 19529-53-4). The disclosed methods are capable of a scale up production of $\text{Pt}(\text{PF}_3)_4$ in a high yield and the produced $\text{Pt}(\text{PF}_3)_4$ may be used as a precursor for Pt-containing film deposition in microelectronic devices or in catalytic industries.

[0036] The disclosed synthesis methods may be a 2-steps wet synthesis of $\text{Pt}(\text{PF}_3)_4$ using

insoluble platinum compound $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) and a soluble reaction intermediate, a platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$), which includes formation of the soluble reaction intermediate from the insoluble $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) suspension in low pressure conditions and a reaction of the soluble intermediate with a metal powder and a co-reactant, such as PF_3 , to form $\text{Pt}(\text{PF}_3)_4$.

[0037] Alternatively, since the soluble intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) can be isolated and purified, the disclosed synthesis methods may be a 1-step wet synthesis of $\text{Pt}(\text{PF}_3)_4$ using the soluble $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) to react with a metal powder and a co-reactant, such as PF_3 , to form $\text{Pt}(\text{PF}_3)_4$ under certain reaction conditions. Preferably, $\text{Hal} = \text{Cl}$. Preferably, a metal powder is a copper powder.

[0038] Furthermore, the disclosed are robust, high yield and scalable syntheses of $\text{Pt}(\text{PF}_3)_4$, which may proceed under a low pressure and may be performed in common reactors or apparatus. More specifically, $\text{Pt}(\text{PF}_3)_4$ may be synthesized from a platinum compound selected from $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) or $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$), with PF_3 and a metal powder, such as a copper powder, under a low PF_3 pressure, in an anhydrous solvent. The metal powder may have a particle size ranging from approximately 200-900 microns, preferably from approximately 300-500 microns. The anhydrous solvent may be capable of dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$), a reaction intermediate, in which $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) may form from $\text{Pt}(\text{Hal})_2$ and PF_3 under the certain reaction conditions, such as under a low pressure condition. Herein, the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) can be isolated and purified for using as a reactant or a starting material for synthesis of $\text{Pt}(\text{PF}_3)_4$. A yield of $\text{Pt}(\text{PF}_3)_4$ using the disclosed synthesis methods may be in a range of approximately 70-99.9%. The disclosed also includes purification processes of the product $\text{Pt}(\text{PF}_3)_4$ through metal traps and storage conditions of the purified $\text{Pt}(\text{PF}_3)_4$ in a vessel. $\text{Pt}(\text{PF}_3)_4$ may be stored under air and moisture free conditions in apparatus and ampoules fabricated from stainless steel and preferably having a passivated or electro-polished inner surface. $\text{Pt}(\text{PF}_3)_4$ may be stored in a metal vessel at room temperature without changing of its purity, such as a stainless steel vessel and an inner surface passivated or electro-polished stainless steel vessel.

[0039] As described above, the absence of scalable method in the art may be because commonly available reactors for pilot plant syntheses and high volume manufactures are not designed to operate under a high pressure and not designed for efficient stirring (mixing) of air sensitive solids. Namely, commercially available (e.g. from High Pressure Equipment Company) reactors capable of operation under a high pressure about 100 atm do not have a stirring capability, which is essential for reaction to proceed. In addition, commercially available reactors (e.g. from Buchiglas USA) are difficult to cool down to even dry ice temperature necessary to condense PF_3 in the reactor. Stirring of solids could be improved to some extent

using a specially designed stirring shafts, but would not solve a parasitic reaction, such as PtCl_2/Cu , which leads to platinum metal and reduces the yield of $\text{Pt}(\text{PF}_3)_4$. In addition, impurities are difficult to remove, requiring expensive and uncertain additional purification steps.

[0040] The disclosed methods for a robust, high yield and scalable synthesis of $\text{Pt}(\text{PF}_3)_4$ may proceed under a low PF_3 pressure, e.g., below 20 atm, and may be performed on commonly used commercially available reactors. The disclosed method is a significant advancement in the art to provide a method capable of producing a scale-up production of $\text{Pt}(\text{PF}_3)_4$ with a high yield, since up to date a potentially ideal $\text{Pt}(\text{PF}_3)_4$ precursor has not applied only due to the absence of a scalable synthesis method. The reason of the absence of the scalable synthesis method is that commonly used commercially available reactors for pilot plant syntheses and high volume manufacture are not designed for operation under a high pressure (e.g., 30 atm or higher) and not designed for efficient stirring (mixing) of air sensitive solids, as stated above.

[0041] The disclosed methods may have proven for the first time that reaction aimed for synthesis of $\text{Pt}(\text{PF}_3)_4$ with $\text{PtCl}_2 + \text{PF}_3 + \text{Cu}$ in a solvent goes through the sufficiently soluble intermediate $\text{PtCl}_2(\text{PF}_3)_2$ at reaction conditions (e.g., low pressure from 20 to 300 psig and temperature from 80 to 130°C), when starting materials $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) is PtCl_2 and the metal powder is a Cu powder. A common knowledge is that solubility of inorganic compound such as $\text{PtCl}_2(\text{PF}_3)_2$ is lower in saturated hydrocarbon solvent than in arene solvent benzene and hence counting on solubility in hydrocarbon solvent hexadecane is counterintuitive as well as counting on reaction with such low solubility even in an arene solvent.

[0042] $\text{Pt}(\text{PF}_3)_4$ was normally prepared from PtCl_2 , K_2PtCl_6 and K_2PtCl_6 according to the prior art, while K_2PtCl_6 is required to lower PF_3 pressure. Both PtCl_2 and K_2PtCl_6 are insoluble in the disclosed solvents (e.g., arenes, saturated hydrocarbons). As shown in the examples and comparative examples that follow, the solvent effects are not similar for platinum starting compounds, e.g. for PtCl_2 (Example 1, Table 1, comparative example 1) and for K_2PtCl_6 (Example 7, Table 5). While addition of the disclosed solvent (e.g., xylene, hexadecane) is beneficial for reaction starting from PtCl_2 , the neat reaction without solvent with starting compound K_2PtCl_6 :



has a higher yield of $\text{Pt}(\text{PF}_3)_4$ than the reaction starting from K_2PtCl_6 in the solvent hexadecane, showing that the solvent benefit is beneficial to certain Pt precursors such as PtCl_2 , PtF_2 , PtI_2 , PtBr_2 or the like. Hence using solvent for the synthesis of $\text{Pt}(\text{PF}_3)_4$ from $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) is novel.

[0043] FIG. 1 is a block diagram of an exemplary disclosed solid-gas $\text{PtCl}_2 + \text{PF}_3 + \text{Cu}$ system for synthesis of $\text{Pt}(\text{PF}_3)_4$. As shown, at first, a metal powder, such as Cu powder 11 is added to reactor 16 through line 101. Anhydrous solvents are used as solvent 14 in the disclosed process. The applied solvents for solvent 14 may have moisture from 0 to 50 ppm, preferably

from 0 to 10 ppm of moisture, more preferably 0 to 1 ppm of moisture. Solvent **14** may be dried by contacting with a drying agent selected from 3 Å or 4 Å molecular sieves or an activated alumina through drying process **104**. Drying process **104** could be done at a temperature range from 10 - 50°C, preferably at room temperature, within 0.5 hours to 20 hours. In some embodiments, drying process **104** may be achieved by keeping the solvent with the molecular sieves in container **15** or by passing through a column (not shown) with a drying agent in drying process **104**. The moisture content in container **15** after drying may be determined by Karl Fischer titration or any other suitable analysis. Solvent **14** may be a commercially available solvent and may be degassed by applying vacuum-inert gas cycles or by passing the inert gas with less than 0.5 ppm of O₂ and moisture before contacting with the drying agent. Solvent or anhydrous solvent **14** may be stored in container **15** or directed to reactor **16** via line **105** right after drying process **104**. Container **15** with the dried anhydrous solvent **14** could be stored before the next step, or transported to other place where reactor **16** is located.

[0044] Afterward, PtCl₂ **12** is charged into reactor **16** under an inert atmosphere (e.g., nitrogen, argon, helium) by any suitable means, e.g. applying solid addition funnel **102**. PtCl₂ **12** may be anhydrous PtCl₂. In the following, PF₃ **13** is charged into reactor **16** via addition line **103** by pressure difference, while reactor **16** may be pre-vacuumed and heated, or at room temperature and pre-vacuumed, or containing PF₃ at a certain pressure and temperature. Reactor **16** may be vacuumed up to 0.1-50 Torr, preferably up to 0.1-2 Torr to remove the inert gas selected from nitrogen, argon, helium, before addition of PF₃. Absence of the non-condensable gas (nitrogen, argon, helium) in reactor **16** will make distillation of the product Pt(PF₃)₄ more efficient. Alternatively, PF₃ added to reactor **16** may contain 1 atm of nitrogen, argon or helium at room temperature. The addition of PF₃ **13** in reactor **16** creates a PF₃ pressure from 20 psig to 300 psig in reactor **16**. PF₃ may be added by portions or continuously during the process. The value of the PF₃ pressure depends on the pressure rating of the applied reactor and may be added by portions or continuously during the process and recycled after the process.

[0045] Reactor **16** may be a typical vessel with means of agitation, temperature and pressure controls and reaction monitoring, applied to synthesis and purification of Pt(PF₃)₄. Reactor **16** has a cooling and heating device that is maintained at a temperature ranging from approximately -120°C to approximately 200°C, preferably from room temperature to 180°C, more preferably from room temperature to 130°C, and the corresponding pressure from approximately 10 psig to approximately 3000 psig, preferably from approximately 20 psig to approximately 1000 psig, more preferable from approximately 20 psig to approximately 300 psig. Reactor **16** is connected to an empty vessel serving as ballast and has a vent to vent the reaction content if over pressurized. Reactor **16** is connected to a nitrogen and vacuum line (not

shown) and a PF_3 scrubber (not shown) as well as traps **18** and **20** for collection of the product $\text{Pt}(\text{PF}_3)_4$ through line **107** and recycling unreacted PF_3 through line **110**.

[0046] Solvent **14** may include various organic solvents. In some embodiments, solvent **14** may be a dried alkane solvent selected from decane, di-, tri-, tetra-, penta- or hexadecane. In this case, Cu powder **11**, anhydrous PtCl_2 **12**, and dried alkane solvent **14** are loaded in reactor **16** forming a suspension. The starting amount of PtCl_2 solid in solvent **14** is from 1% to 50%, preferably from 5% to 40%, more preferably from 20% to 30%. The molar ratio of the PtCl_2 **12** to Cu powder **11** is from 1:2 to 1:20, preferably from 1:6 to 1:10. That is, the molar ratio of the Pt to Cu is from 1:2 to 1:20, preferably from 1:6 to 1:10. Reactor **16** is vacuumed to 0.1-50 Torr, preferably to 0.2-5 Torr prior to introducing of PF_3 **13**.

[0047] Alternatively, solvent **14** may be a dried arene solvent selected from xylene, mesitylene, cymene, pentylbenzene, diisopropylbenzene, or diisobutylbenzene. In this case, Cu powder **11**, anhydrous PtCl_2 **12**, and dried arene solvent **14** are loaded in reactor **16**. The starting amount of PtCl_2 solid in solvent is from 1% to 50% preferably from 10 to 40%, more preferably from 20% to 30%. The molar ratio of the PtCl_2 to Cu is from 1:2 to 1:20, preferably from 1:6 to 1:10. That is, the molar ratio of the Pt to Cu is from 1:2 to 1:20, preferably from 1:6 to 1:10. Reactor **16** is vacuumed to 0.1-50 Torr, preferably to 0.2-5 Torr prior to introducing of PF_3 **13**.

[0048] Alternatively, solvent **14** may be a dried ether solvent selected from dibutyl ether, dihexyl ether, dioctyl ether, dimethyl ether of diethylene glycol, triethylene glycol dimethyl ether, tetraethylene glycol dimethyl ether. In this case, Cu powder **11**, anhydrous PtCl_2 **12**, and dried ether solvent **14** are loaded in reactor **16**. The starting amount of PtCl_2 solid in solvent is from 1% to 50% preferably from 10 to 40%, more preferably from 20% to 30%. The molar ratio of the PtCl_2 to Cu is from 1:2 to 1:20, preferably from 1:6 to 1:10. That is, the molar ratio of the Pt to Cu is from 1:2 to 1:20, preferably from 1:6 to 1:10. Reactor **16** is vacuumed to 0.1-50 Torr, preferably to 0.2-5 Torr prior to introducing of PF_3 **13**.

[0049] After introducing PF_3 **13** into reactor **16**, a reaction mixture initially is a suspension of PtCl_2 **12** and Cu powder **11** in solvent **14** under the pressure of PF_3 **13**. Then heating reactor **16** with stirring the reaction mixture, $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) are formed in a temperature range from 20 to 120°C, preferably in a temperature range from 90-120°C. The reaction may be stopped after 20-80 minutes of heating with stirring in above preferred temperature ranges and $\text{PtCl}_2(\text{PF}_3)_2$ may be isolated from the solvent, reaction byproducts, residual PF_3 , etc. Compounds $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) are soluble in solvent **14** that may be proven by means of NMR spectroscopy, as shown in FIG. 3. The reaction continues in reactor **16** under the pressure of PF_3 while PF_3 and $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) are dissolved in the solvent and react with copper powder **11**. During the course of reaction, PF_3 **13** is consumed. PF_3 **13** could be added by portions in reactor **16** or continuously maintain a constant selected pressure. When all starting

and intermediate platinum compounds are consumed, the pressure in reactor 16 becomes constant at a given temperature.

[0050] The reaction time may be in the range of 1 hour to 24 hours, preferably from 4 hours to 8 hours. The degree of conversion may be monitored by a consumption rate of PF_3 and pressure change in reactor 16 through in-situ Raman spectroscopy or any other suitable technique.

[0051] In some embodiments, the reaction in reactor 16 occurs in hexadecane, under 20 to 50 psig of PF_3 , at the temperatures 100 to 125°C and finished in 6 hours. Alternatively, in some embodiments, the reaction in reactor 16 occurs in xylenes, under 20 to 40 psig of PF_3 , at the temperatures from 100 to 125°C and finished in 5 hours.

[0052] After the reaction finishes, the reaction mixture is cooled to 20 to 65°C, preferably 30 to 45°C. The remaining gases consisting of PF_3 , $\text{Pt}(\text{PF}_3)_4$ and solvent are directed to pre-vacuumed trap 17 maintained in a temperature ranging from -196°C to -160°C. PF_3 (melting point -151.5°C, boiling point -101.9°C) and $\text{Pt}(\text{PF}_3)_4$ (melting point -15°C) and the solvent are condensed in pre-vacuumed trap 17. At the end of $\text{Pt}(\text{PF}_3)_4$ condensation in pre-vacuumed trap 17, vacuum may be applied in periods to remove the residual gases such as nitrogen, argon, helium, to create a vacuum in the range of 0.1 to 50 Torr, preferably 0.2 to 2 Torr in order to facilitate the distillation of remaining $\text{Pt}(\text{PF}_3)_4$ from reactor 16 in pre-vacuumed trap 17. Pre-vacuumed trap 17, $\text{Pt}(\text{PF}_3)_4$ trap 18 and PF_3 trap 20 are pre-vacuumed to 0.01 – 10 Torr, preferably to 0.1-1 Torr before condensing the reaction products including $\text{Pt}(\text{PF}_3)_4$ and PF_3 .

[0053] Alternatively to the procedure described above, after the reaction finishes, the reaction mixture is cooled down to 20-65°C, preferably to 30-45°C and a portion of gases containing PF_3 , $\text{Pt}(\text{PF}_3)_4$ and solvent is directed to pre-vacuumed trap 17 through line 106 maintained in a temperature ranging from -60 to -80°C. PF_3 is not condensed, while $\text{Pt}(\text{PF}_3)_4$ and solvent are condensed in pre-vacuumed trap 17. After $\text{Pt}(\text{PF}_3)_4$ and solvent are condensed in pre-vacuumed trap 17, the non-condensed PF_3 is directed by pressure difference from pre-vacuumed trap 17 to PF_3 trap 20 maintained in a temperature ranging from -160 to -196°C, then the next portion of gases containing PF_3 , $\text{Pt}(\text{PF}_3)_4$ and solvent is directed in pre-vacuumed trap 17 from reactor 16 and the cycle continues until all PF_3 is condensed in PF_3 trap 20 and all $\text{Pt}(\text{PF}_3)_4$ is condensed in pre-vacuumed trap 17.

[0054] The condensation of gaseous products is preferably done by steps, as described above, where a continuous process is disclosed, since even with the efficient engineering and cooling of pre-vacuumed trap 17 with dry ice-isopropanol (-79°C), the continuous flow of gases from reactor 16 will result in bypassing 108 of 20-60% of $\text{Pt}(\text{PF}_3)_4$ in PF_3 trap 20 leading to an additional steps (not shown) to recover all $\text{Pt}(\text{PF}_3)_4$ from PF_3 trap 20. The additional steps may include warming up trap 20 above the boiling point of PF_3 (-102°C), commonly to -79°C (dry ice

cooling) and capture all PF_3 in a first separate trap (not shown) cooled with liquid nitrogen. After all PF_3 is captured, trap 20 is warmed up to room temperature and $\text{Pt}(\text{PF}_3)_4$ is captured in a second separate trap (not shown). The captured PF_3 in the first separate trap may be recycled to PF_3 13 through line 110 for synthesis in reactor 16. Pre-vacuumed trap 17, $\text{Pt}(\text{PF}_3)_4$ trap 18 and PF_3 trap 20 and all connecting lines are fabricated from or made of metal, where the metal material is preferably carbon steel, stainless steel and stainless steel alloy. In some embodiments, pre-vacuumed trap 17, $\text{Pt}(\text{PF}_3)_4$ trap 18 and PF_3 trap 20 and all connecting lines are made of stainless steel. All traps may have a passivated or electro-polished inner surface.

[0055] $\text{Pt}(\text{PF}_3)_4$ is separated from PF_3 by fractional distillation under air and moisture free conditions. After collection of volatile species, pre-vacuumed trap 17 is warmed to a temperature ranging from -20 to -90°C , preferably from -60 to -80°C and PF_3 is distilled in PF_3 trap 20 maintained in a temperature ranging from -160 to -196°C . PF_3 in PF_3 trap 20 may be stored, moved to a different location or recycled as PF_3 13 for next synthesis.

[0056] $\text{Pt}(\text{PF}_3)_4$ contaminated with the solvent, reaction byproducts such as solid copper chlorides is remaining in pre-vacuumed trap 17 after PF_3 uptake. $\text{Pt}(\text{PF}_3)_4$ in pre-vacuumed trap 17 has purity 90-99% and contain 0.1-5% of PF_3 and 0.1-10% of solvent and 0.1-1% of other impurities preferably being phosphorus oxofluorides and solid copper chlorides. $\text{Pt}(\text{PF}_3)_4$ and solvent, solids are separated if a mixture is kept in a temperature ranging from 10 to 40°C , preferably at room temperature and a receiver is kept in a temperature ranging from -50 to -196°C , while the apparatus and the receiver may be pre-vacuumed before the distillation and the pressure during the distillation is 0.01 Torr to 760 Torr, preferably from 0.1 Torr to 5 Torr. More specifically, $\text{Pt}(\text{PF}_3)_4$ collected in pre-vacuumed trap 17 is purified by distillation in $\text{Pt}(\text{PF}_3)_4$ trap 18. In one embodiment, pre-vacuumed trap 17 containing $\text{Pt}(\text{PF}_3)_4$ after PF_3 uptake is warmed to 0 to 40°C , preferably to room temperature and $\text{Pt}(\text{PF}_3)_4$ is distilled in pre-vacuumed trap 17 at a pressure from 0.01-50 Torr, preferably 0.1-2 Torr, while $\text{Pt}(\text{PF}_3)_4$ trap 18 kept in a temperature ranging from -15 to -196°C .

[0057] $\text{Pt}(\text{PF}_3)_4$ collected in $\text{Pt}(\text{PF}_3)_4$ trap 18 has a purity of 70-99.9% w/w, preferably 80-99.9% w/w, more preferably 90-99.9% w/w, even more preferably 95-99.9% w/w, even more preferably 99.0-99.99% w/w after purification. Preferably, $\text{Pt}(\text{PF}_3)_4$ collected has a purity of 99.50-99.99% w/w and contains 0-0.5% of PF_3 , 0.01-0.5% of other impurities, such as phosphorus oxofluorides, thermal decomposition products such as $\text{Pt}_4(\text{PF}_3)_8$ and 0-0.5% of residual solvent. Purity of $\text{Pt}(\text{PF}_3)_4$ determined by ^1H , ^{19}F , ^{31}P , ^{195}Pt NMR, FTIR, and Raman spectroscopy.

[0058] The purified $\text{Pt}(\text{PF}_3)_4$ may have an impurity of from approximately 0 wt.% to approximately 0.1 wt.% of PF_3 , preferably from approximately 0 wt.% to approximately 0.05 wt.% of PF_3 . The purified $\text{Pt}(\text{PF}_3)_4$ may have between approximately 0 wt.% to approximately 1

wt.% of phosphorus fluorides and oxofluorides including PF_3 , POF_3 , $(\text{HO})\text{POF}_2$, $(\text{HO})_2\text{POF}$, preferably between approximately 0 wt.% to approximately 0.05 wt.%. The purified $\text{Pt}(\text{PF}_3)_4$ may have between 0 wt.% to approximately 0.1 wt.% platinum compounds other than $\text{Pt}(\text{PF}_3)_4$. Preferably, approximately 0 wt.% to approximately 0.05 wt.% of platinum compounds other than $\text{Pt}(\text{PF}_3)_4$. The total concentration of $\text{Pt}(\text{Hal})_2$, $\text{Pt}_4(\text{PF}_3)_8$, $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , $x = 1, 2$) in $\text{Pt}(\text{PF}_3)_4$ may be from approximately 0 wt.% to approximately 0.1 wt.%, preferably from approximately 0 wt.% to approximately 0.05 wt.% after purification. Furthermore, the purified $\text{Pt}(\text{PF}_3)_4$ may have between 0.1 ppmw to 1000 ppmw of solvent utilized for synthesis, preferably from approximately 0 ppmw to 200 ppmw of solvent, more preferably from 0 ppmw to 50 ppmw of solvent, even more preferably from 0 ppmw to 20 ppmw of solvent. Moreover, the purified $\text{Pt}(\text{PF}_3)_4$ may have from approximately 0 ppmw to approximately 100 ppmw of hydrogen fluoride, from 0 ppmw to approximately 50 ppmw of hydrogen chloride. In addition, the purified $\text{Pt}(\text{PF}_3)_4$ may have between approximately 0 ppb to 10 ppm of trace metals, such as iron, nickel, manganese, cobalt, copper, etc. The residual PF_3 is recycled for synthesis of $\text{Pt}(\text{PF}_3)_4$.

[0059] In some embodiments, in order to determine the amount of organic compounds in $\text{Pt}(\text{PF}_3)_4$, the internal standard, such as Me_4Si , may be used. In some embodiments, the sample preparation may involve absorbing the organic solvent with the proper adsorbent such as C_6 derivatized silica gel.

[0060] In some embodiments, $\text{Pt}(\text{PF}_3)_4$ trap **18** may include two subsequent traps, e.g., trap **18a** and trap **18b** (not shown) for distillations to achieve the desired purity of $\text{Pt}(\text{PF}_3)_4$. After purification, $\text{Pt}(\text{PF}_3)_4$ may be stored in $\text{Pt}(\text{PF}_3)_4$ trap **18** prior to packaging in metal ampoule **19** for shipment, deposition or storage. Alternatively, $\text{Pt}(\text{PF}_3)_4$ may be stored in metal ampoule **19** after packaging **109**. Metal ampoule **19** may be a metal container/vessel that is made of made of a metal, such as stainless steel, carbon steel, and stainless steel 316 alloy. The inner surface of metal ampoule **19** may be passivated with PF_3 or electro-polished.

[0061] The moisture from the surface of metal $\text{Pt}(\text{PF}_3)_4$ trap **18**, metal ampoule **19** may be removed by heating under vacuum at approximately 100 to 170°C before introducing $\text{Pt}(\text{PF}_3)_4$ into metal $\text{Pt}(\text{PF}_3)_4$ trap **18** and metal ampoule **19**. Alternatively, the moisture from the surface of metal $\text{Pt}(\text{PF}_3)_4$ trap **18**, metal ampoule **19** may be removed by passivating the trap vessels with PF_3 before introducing $\text{Pt}(\text{PF}_3)_4$ into metal $\text{Pt}(\text{PF}_3)_4$ trap **18** and metal ampoule **19**.

[0062] The purified $\text{Pt}(\text{PF}_3)_4$ may be stored in metal $\text{Pt}(\text{PF}_3)_4$ trap **18**, metal ampoule **19** in the temperature range -80 to 60°C, preferably from 10 to 40°C, more preferably from 20 to 25°C. The disclosed methods include storing $\text{Pt}(\text{PF}_3)_4$ in a metal container, such as a stainless steel, carbon steel, and stainless steel 316 alloy container. The inner surface of the metal container may be passivated with PF_3 or electro-polished. Here the stainless-steel container may be a stainless steel single-ended miniature sample cylinder or an electro-polished stainless-steel

miniature canister. In one exemplary embodiment, the purified $\text{Pt}(\text{PF}_3)_4$ was stored in a stainless steel single-ended miniature sample cylinder at room temperature for 2 months without change of $\text{Pt}(\text{PF}_3)_4$ purity. Alternatively, the purified $\text{Pt}(\text{PF}_3)_4$ was stored in an electro-polished stainless-steel miniature canister at room temperature for 2 months without change of $\text{Pt}(\text{PF}_3)_4$ purity.

[0063] The disclosed methods may be represented by a step process through a soluble intermediate, $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x=1, 2$; $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I), as shown in FIG. 2a, a so-called solid-gas, $\text{Pt}(\text{Hal})_2\text{--M--PF}_3$, synthesis process in solution. Here HAL is F, Cl, Br or I, preferably Hal is Cl; M is metal (such as Cu), then a $\text{Pt}(\text{Hal})_2\text{--M--PF}_3$ synthesis process becomes a $\text{PtCl}_2\text{--Cu--PF}_3$ synthesis process. The disclosed method produces $\text{Pt}(\text{PF}_3)_4$ in a high yield (i.e., 70 to 99.9%) with a high purity (i.e., more than 99%, preferably more than 99.99%) and allows storage and delivery of the highly pure $\text{Pt}(\text{PF}_3)_4$ without degrading the purity. Using a hydrocarbon solvent is advantageous of the disclosed solid-gas, $\text{PtCl}_2\text{--Cu--PF}_3$, reaction process, in which the solvent is capable of dissolving the reaction intermediate (e.g., a platinum complex $\text{PtCl}_2(\text{PF}_3)_2$) formed from insoluble starting materials, solid platinum compound PtCl_2 and PF_3 gas, under proper reaction conditions, and does not react with $\text{Pt}(\text{PF}_3)_4$. Utilization of such solvent allows obtaining $\text{Pt}(\text{PF}_3)_4$ in a high yield, at a shorter time, under low PF_3 pressure. Due to the lower pressure of PF_3 in the disclosed synthesized method of $\text{Pt}(\text{PF}_3)_4$, cooling the reactor to condense PF_3 is eliminated and reactors with lower pressure rating could be used. As a result, commonly available equipment and reactors could be utilized for the disclosed synthesis method of $\text{Pt}(\text{PF}_3)_4$. This results in a $\text{Pt}(\text{PF}_3)_4$ synthesis process that is scalable to large industrial scale, with limited required equipment complexity due to its lower pressure requirement. The reaction conditions here include reaction temperature, reaction pressure and so on.

[0064] With the disclosed synthesis methods, the problem of low, moderate and irreproducible yield in the solid-gas reactions as well as a high pressure of PF_3 required for synthesis of $\text{Pt}(\text{PF}_3)_4$ is solved by addition of the disclosed solvent in the $\text{PtCl}_2\text{--Cu--PF}_3$ reaction system. Addition of solvent allows a synthesis of $\text{Pt}(\text{PF}_3)_4$ under a low PF_3 pressure, in a shorter time, with the reproducible high yield (Table 1, Examples #1 to #4). The reason for improvement in the synthesis process is solubility of $\text{PtCl}_2(\text{PF}_3)_2$ obtained in situ from PtCl_2 and PF_3 under the low pressure reaction conditions. It is a common knowledge that solution–solid reactions are much more efficient than the reaction between two different solids and gas. The addition of the solvent makes the solid-gas, $\text{PtCl}_2\text{--Cu--PF}_3$, reaction system change to a solution–solid reaction that is much more efficient. Although application of solvent in synthesis is a common practice, it is not obvious solution for the given reaction systems due to applied reaction conditions, a high reactivity of PF_3 as well as rich platinum coordination and catalytic chemistry in the organic solvents, and could even be argued against.

[0065] The addition of the solvent in the solid-gas $\text{Pt}(\text{Hal})_2\text{--M--PF}_3$ synthesis system solves

the problems of the low, moderate and irreproducible yield in the solid-gas reactions (see the comparative Example 1 below) and a high pressure of PF_3 (50 – 150 Atm) required for synthesis of $\text{Pt}(\text{PF}_3)_4$. The addition of the solvent allows a synthesis of $\text{Pt}(\text{PF}_3)_4$ under a low PF_3 pressure, in a shorter time, with the reproducible high yield, see Examples 2 to 4 that follow. The reason for the yield improvement is solubility of the reaction intermediate $\text{PtCl}_2(\text{PF}_3)_2$ obtained in situ from PtCl_2 and PF_3 under certain reaction conditions (FIG. 3). Once more, it is known that solution-solid reactions are much more efficient than the reaction between two different solids and gas. In the Examples 2 to 4 that follow, the addition of the solvent in the $\text{PtCl}_2\text{--Cu--PF}_3$ synthesis system allowed synthesis of $\text{Pt}(\text{PF}_3)_4$ under a 10 to 50 psig of PF_3 pressure, in a 5 to 6 hours with a reproducible high yield (also see Example 1) because a solid–gas, $\text{PtCl}_2\text{--Cu--PF}_3$ synthesis system, becomes a solution–solid reaction. As a result, commonly available equipment and reactors could be utilized for the disclosed synthesis processes of $\text{Pt}(\text{PF}_3)_4$.

[0066] Suitable solvents should be “inert” toward starting compounds and intermediates and product $\text{Pt}(\text{PF}_3)_4$ and not react with the starting compounds and the intermediates and the product $\text{Pt}(\text{PF}_3)_4$ under the reaction conditions. In other words, the suitable solvents should not be catalytically transformed by the starting compounds, intermediates and product $\text{Pt}(\text{PF}_3)_4$ under the reaction conditions and the solvent should not transform starting compounds and products in to other compounds. The suitable solvent should only dissolve at least one intermediate in the reaction to get the solution-solid reaction, which is much more efficient, reproducible and therefore scalable than the reaction between two different solids and gas. The suitable solvents should be able to dissolve at least one platinum containing reaction intermediate such as $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, wherein Hal = F, Cl, Br or I; $x = 1, 2$, obtained in situ from $\text{Pt}(\text{Hal})_2$ and PF_3 under the reaction conditions.

[0067] The platinum precursor may form the soluble reaction intermediate in the solvent under certain reaction conditions, otherwise addition of solvent will result in a lower yield of $\text{Pt}(\text{PF}_3)_4$ compared to the reaction without the solvent, see the Comparative Example 1 (b)), where the yield of $\text{Pt}(\text{PF}_3)_4$ is 60% in a solid-gas reaction and Example 7 (#9), where the yield of $\text{Pt}(\text{PF}_3)_4$ is 26% for the reaction in hexadecane under the same pressure and temperature. The disclosed platinum precursor $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) are forming soluble intermediates and hence they are suitable for the disclosed synthesis process.

[0068] The suitable solvents used herein may be selected from ether, arene or alkane solvents. The preferred boiling point (BP) of the solvent may be more than 150°C, preferably more than 200°C. This is necessary for an efficient separation of the solvent and the product $\text{Pt}(\text{PF}_3)_4$ since the calculated boiling point of $\text{Pt}(\text{PF}_3)_4$ is ~77°C calculated from the equation $\log P = 10.34 - 2610/T$ (P in Torr, T in Kelvin) from “Vapor Pressure Measurements of Volatile Transition-Metal Complexes”, by R.D. Sanner, J. H. Satcher, Jr., Report (1989), UCRL-53937.

For example, hexadecane (BP: 285°C, melting point (MP): 18°C and vapor pressure (VP): 0.07 Torr at 20°C), p-cymene (BP: 177°C, MP: -68°C and VP: 1 Torr at 20°C) and dihexyl ether (BP: 223°C, MP: -43°C and VP: 0.05 Torr at 20°C), triethylene glycol dimethyl ether (BP: 216°C, MP: -45°C and VP: 0.025 Torr at 20°C), tetraethylene glycol dimethyl ether (BP: 275°C, MP: -30°C and VP: 0.001 Torr at 20°C) may be suitable for using as a solvent in the disclosed $\text{Pt}(\text{Hal})_2\text{-M-PF}_3$ synthesis system.

[0069] In one embodiment, the intermediate $\text{PtCl}_2(\text{PF}_3)_2$ was isolated from the reaction of PtCl_2 and PF_3 in hexadecane, identity confirmed by analysis. $\text{PtCl}_2(\text{PF}_3)_2$ further reacted with copper and PF_3 under the conditions disclosed in #5 in Table 1 producing $\text{Pt}(\text{PF}_3)_4$.

[0070] Anhydrous solvents have to be applied for synthesis of $\text{Pt}(\text{PF}_3)_4$ because PF_3 , PtCl_2 , $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) and $\text{Pt}(\text{PF}_3)_4$ react with moisture. The reactions with moisture result in side products such as HCl, HF, and/or phosphorus oxofluorides, fluorophosphoric acids, which contaminate the product $\text{Pt}(\text{PF}_3)_4$. For example, HF may form SiF_4 when $\text{Pt}(\text{PF}_3)_4$ is placed in any vessels made from glass. To prevent the formation of contaminants, the commercially available solvent may be dried by contacting with the drying agent.

[0071] FIG. 2a is a flowchart of the disclosed $\text{Pt}(\text{Hal})_2\text{-M-PF}_3$ synthesis process for synthesis of $\text{Pt}(\text{PF}_3)_4$ starting with $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I). Starting materials include $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) and metal powder (M) and PF_3 . In a reaction temperature ranging from 20-180°C, $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) and the metal powder may not be soluble. For example, PtCl_2 is not soluble at a reaction temperature ranging from 20-180°C. First, at step 202, a suspension of the starting materials $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) and a metal powder is formed in an anhydrous solvent by dispersing $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) and the metal powder to the anhydrous solvent. Afterward, excess PF_3 gas is introduced into the suspension of $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) and the metal powder. Here, preferably, $\text{Hal} = \text{Cl}$, then $\text{Pt}(\text{Hal})_2$ is PtCl_2 . Preferably, the metal powder is a Cu powder.

[0072] $\text{Pt}(\text{Hal})_2$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) is anhydrous and suspended in the anhydrous solvent. A solvent is dried by a drying agent to form the anhydrous solvent that is used to mix with the starting materials anhydrous $\text{Pt}(\text{Hal})_2$ and metal powder. The solvent or anhydrous solvent may be a hydrocarbon solvent, such as an oxyhydrocarbon solvent, having a general formula $(\text{C}_n\text{H}_{2n+1})_2\text{O}$ and $\text{H}_3\text{C}(\text{O}(\text{CH}_2)_2)_n\text{OCH}_3$ ($n \geq 1$), an arene solvent having a general formula $(\text{C}_n\text{H}_{2n+1})_x\text{C}_6\text{H}_{5-x}$ ($x \geq 1, n \geq 1$) or an alkane solvent having a general formula $\text{C}_n\text{H}_{2n+2}$ ($n \geq 1$). The anhydrous solvent suitable for using in the disclosed methods may be a dried alkane solvent selected from decane, di-, tri-, tetra-, penta- and hexadecane, the like; a dried arene solvent selected from xylene, mesitylene, cymene, pentylbenzene, diisopropylbenzene, diisobutylbenzene, or the like; a dried ether solvent selected from dibutyl ether, dihexyl ether, dioctyl ether, dimethyl ether of diethylene glycol, triethylene glycol dimethyl ether, tetraethylene

glycol dimethyl ether or the like; or an arene solvent selected from xylene, mesithylene, cymene, pentylbenzene, diisopropylbenzene, diisobutylbenzene or the like; or combinations thereof. The ether solvent is preferably dibutyl ether, dihexyl ether, dioctyl ether, triethylene glycol dimethyl ether, tetraethylene glycol dimethyl ether. The arene solvent is preferably xylene, mesithylene, cymene, pentylbenzene, diisopropylbenzene, diisobutylbenzene. The alkane solvent is preferably di-, tri-, tetra, penta- and hexadecane as well as a mixture of alkanes known as a mineral oil. The anhydrous solvent used in the disclosed methods may be xylene or hexadecane.

[0073] In some embodiments, the solvent or anhydrous solvent may be xylene or hexadecane. The drying agent may be 3 Å or 4 Å molecular sieves. $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I), the metal powder and excess PF_3 in the anhydrous solvent may form a soluble reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; Hal = F, Cl, Br or I) at step **204**. The solvent or the anhydrous solvent used herein has to be able to dissolve $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; Hal = F, Cl, Br or I), a soluble reaction intermediate. Here excess PF_3 may be added into the suspension of $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) and the metal powder. Thus, the soluble reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; Hal = F, Cl, Br or I) may be formed from $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) and excess PF_3 at a temperature, for example, between 80°C to 130°C and a low pressure, for example, between 20 psig to 300 psig. $\text{Pt}(\text{Hal})_2$ (Hal = F, Cl, Br or I) reacts with excess PF_3 may produce a solution of the reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; Hal = F, Cl, Br or I) in the anhydrous solvent since the solvent is selected to be able to dissolve the intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; Hal = F, Cl, Br or I). At step **206**, the solution of the reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; Hal = F, Cl, Br or I) may react with the metal powder and PF_3 gas (e.g., when Hal = Cl, the metal powder is a Cu powder, $\text{PtCl}_2(\text{PF}_3)_2 + 2\text{Cu} + 3\text{PF}_3 = 2\text{CuCl} + \text{Pt}(\text{PF}_3)_4$) to form $\text{Pt}(\text{PF}_3)_4$. At this step, excess of PF_3 is used. Then, at step **208**, the produced $\text{Pt}(\text{PF}_3)_4$ is separated and purified from unreacted starting materials, the solvent and reaction byproducts such as copper halides (e.g., CuCl, CuCl_2) and their complexes with PF_3 . The separation and purification steps may be performed in a pre-vacuumed trap and/or a metal trap to remove residual PF_3 and the solvent and the reaction byproducts, as shown in **FIG. 1**. The residual PF_3 may be recycled to be used as the starting material. The metal traps may be made of a metal, such as stainless steel, carbon steel, and stainless steel 316 alloy. The purified product $\text{Pt}(\text{PF}_3)_4$ is then stored in a metal ampoule or vessel or container at step **210**. The storage metal ampoule or vessel or container may be made of a metal, such as stainless steel, carbon steel, and stainless steel 316 alloy. Alternatively, the storage ampoule or vessel or container may be made of plastic. The inner surface of the ampoule or vessel or container may be passivated with PF_3 or electro-polished.

[0074] In the disclosed methods, the anhydrous solvents have to be applied for synthesis of $\text{Pt}(\text{PF}_3)_4$ because PF_3 , PtCl_2 , $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) and $\text{Pt}(\text{PF}_3)_4$ react with moisture. To prevent

the formation of contaminants, the commercially available solvent may be dried by contacting with the drying agent selected from 3 Å or 4 Å molecular sieves or activated alumina. Solvent drying processes may be achieved by contacting the solvent and the drying agent, which may be achieved in a static process or in a flow process. Before the drying step, the commercially available solvent may be degassed by passing an inert gas or by applying vacuum-inert gas cycles, where the vacuum is in the range 0.1 Torr to 100 Torr, preferably 0.5-10 Torr and the inert gas is selected from N₂, Ar or He containing less than 1 ppm of oxygen and moisture. Alternatively, the commercially available solvent dried with the drying agent without degassing.

[0075] The disclosed synthesis methods provide practical/scalable synthesis methods of Pt(PF₃)₄, through tuning and optimizing reaction conditions that favor the product Pt(PF₃)₄ in a high yield and minimize effects of side reactions. The disclosed synthesis methods may be carried out in a standard high pressure reactor, e.g., reactors from Parr Instrument Company Series 4520, 4530, 4540, 4540 rated from 1900 to 5000 psig; in pressure rated glass reactors, e.g., in Series 5100 Glass Reactors from Parr Instrument Company rated up to 150 psig; or in lab and pilot pressure reactors from Büchiglas and equipped with standard stirrers and heaters.

[0076] In some embodiments, the disclosed synthesis methods for synthesis, purification and storage of Pt(PF₃)₄ may comprise the following steps:

- a) drying a solvent;
- b) dispersing a platinum compound having a general formula Pt(Hal)₂ (Hal = Cl, Br, I), such as PtCl₂, and a metallic powder having certain particle sizes such as a metallic copper powder, into the dried or anhydrate solvent in a flow reactor, forming a mixture or a suspension of Pt(Hal)₂ (Hal = Cl, Br, I) and the metallic copper powder;
- c) adding excess amount of PF₃ to the mixture or the suspension;
- d) stirring a reaction mixture formed in the step c) under a required temperature and a required PF₃ pressure (i.e., low PF₃ pressure) that lead to the following reactions and products:
 - a. formation of PtCl₂(PF₃)_x (x = 1, 2);
 - b. solution of PtCl₂(PF₃)_x in the dried solvent; and
 - c. reaction of PtCl₂(PF₃)_x and PF₃ with the metallic copper powder to form a product Pt(PF₃)₄;
- e) purifying the product Pt(PF₃)₄ through distilling volatile species from the reaction mixture into a separate trap that allows:
 - i. separating unreacted starting material(s), byproducts, solvent; and
 - ii. separating of the product Pt(PF₃)₄ from unreacted PF₃.
- f) purifying the crude Pt(PF₃)₄ by distillation;
- g) recycling the unreacted PF₃ to the step c); and
- h) storing the purified product Pt(PF₃)₄ in a metal ampoule or container made of a

metal, such as stainless steel, carbon steel, and stainless steel 316 alloy and the inner surface of the metal ampoule or container is passivated by PF_3 or electro-polished.

[0077] Alternatively, the disclosed methods for synthesizing $\text{Pt}(\text{PF}_3)_4$ with a platinum compound $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I comprise the following steps:

- dispersing the platinum compound $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I into an anhydrous solvent forming a suspension of $\text{Pt}(\text{Hal})_2$;
- introducing excess amount of PF_3 into the suspension of $\text{Pt}(\text{Hal})_2$;
- forming a solution of the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ in the anhydrous solvent therefrom through a reaction of PF_3 and $\text{Pt}(\text{Hal})_2$;
- adding a metal powder having certain particle sizes and additional excess amount of PF_3 into the $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution; and
- forming $\text{Pt}(\text{PF}_3)_4$ through a reaction between $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, PF_3 and the metal powder under a reaction condition.

[0078] In this case, $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ is a reaction intermediate synthesized by excess amount of PF_3 with the suspension of $\text{Pt}(\text{Hal})_2$ in an anhydrous solvent. Once again, using solvent for the synthesis of $\text{Pt}(\text{PF}_3)_4$ appears novel. To our best knowledge, $\text{Pt}(\text{PF}_3)_4$ was never synthesized from any platinum compound including the reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) in a solvent.

[0079] Alternatively, the disclosed methods for synthesizing $\text{Pt}(\text{PF}_3)_4$ with a platinum compound $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , comprise the following steps:

- providing a metal powder having certain particle sizes;
- providing PF_3 gas;
- synthesizing $\text{Pt}(\text{PF}_3)_4$ from the metal powder, PF_3 and the platinum compound $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , in an anhydrous solvent capable of dissolving at least one platinum containing reaction intermediate $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$), which is formed from the platinum precursor $\text{Pt}(\text{Hal})_2$ and PF_3 under reaction conditions, such as a low pressure from 20 psig to 300 psig and a temperature ranging from 80°C to 130°C ; and
- purifying and storing $\text{Pt}(\text{PF}_3)_4$ at an air and moisture free condition in apparatus and ampoules fabricated from metal or plastic.

[0080] Alternatively, the disclosed method for synthesis of $\text{Pt}(\text{PF}_3)_4$ with a platinum compound $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I comprises the following steps:

- a) drying a solvent with a drying agent to form an anhydrous solvent;
- b) adding a metal powder having certain particle sizes, a platinum compound having a general formula $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , and excess amount of PF_3 to the anhydrous solvent to form $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, where $x = 1, 2$, wherein the anhydrous solvent is capable of dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$;

- c) synthesizing $\text{Pt}(\text{PF}_3)_4$ by the reaction of the metal powder, PF_3 , and $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ in the anhydrous solvent; and
- d) purifying the synthesized $\text{Pt}(\text{PF}_3)_4$ and storing the purified $\text{Pt}(\text{PF}_3)_4$ under air and moisture free conditions in apparatus and ampoules fabricated from metal or plastic, such as stainless steel or plastic.

[0081] Here the plastic may be selected from polyethylene, polypropylene, styrene, teflon, polytetrafluoroethylene (PTFE), perfluoroalkoxy alkane (PFA).

[0082] As describe above, the reaction intermediates $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) are soluble in hydrocarbon solvents and can be isolated and purified. Synthesis of $\text{Pt}(\text{PF}_3)_4$ may be start with the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$). FIG. 2b is a flowchart of an exemplary process of synthesizing $\text{Pt}(\text{PF}_3)_4$ starting with $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I). As shown, at step 302, a $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) solution is formed by dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) into an anhydrate solvent. Preferably, Hal is Cl , $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ is $\text{PtCl}_2(\text{PF}_3)_x$. Then at step 304, a metal powder having certain particle sizes is introduced into the $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) solution and forms a suspension. Preferably, the metal powder is a Cu powder having certain particle sizes. Afterwards, excess PF_3 gas is introduced into the suspension at step 306. Then, $\text{Pt}(\text{PF}_3)_4$ is formed under low pressure by reacting $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($x = 1, 2$; $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I) with the metal powder and PF_3 at step 308. At this step, excess of PF_3 is used. Then, at step 310, the produced $\text{Pt}(\text{PF}_3)_4$ is separated and purified from unreacted starting materials, the solvent and reaction byproducts such as copper halides (e.g., CuCl , CuCl_2) and their complexes with PF_3 . The separation and purification steps may be performed in a pre-vacuumed trap and/or a metal trap to remove residual PF_3 and the solvent and the reaction byproducts, as shown in FIG. 1. The residual PF_3 may be recycled to be used as the starting material. The metal traps may be made of a metal, such as stainless steel, carbon steel, and stainless steel 316 alloy. The purified product $\text{Pt}(\text{PF}_3)_4$ is then stored in a metal ampoule or vessel or container at step 312. The storage metal ampoule or vessel or container may be made of a metal, such as stainless steel, carbon steel, and stainless steel 316 alloy. Alternatively, the storage ampoule or vessel or container may be made of plastic. The inner surface of the ampoule or vessel or container may be passivated with PF_3 or electro-polished.

[0083] The disclosed methods for synthesizing $\text{Pt}(\text{PF}_3)_4$ with a platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$, comprise the following steps:

- dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) in an anhydrous solvent forming a $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution;
- adding a metal powder having certain particle sizes and excess amount of PF_3 into the $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution; and
- forming $\text{Pt}(\text{PF}_3)_4$ through a reaction between $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, PF_3 and metal powder

under a reaction condition of a low pressure ranging from 20 psig to 300 psig and a temperature ranging from 80°C to 130°C.

[0084] Alternatively, the disclosed methods for synthesizing $\text{Pt}(\text{PF}_3)_4$ with a platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, wherein Hal = F, Cl, Br or I; $x = 1, 2$, comprise the following steps:

- a) drying a solvent with a drying agent to form an anhydrous solvent;
- b) adding the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, wherein Hal = F, Cl, Br or I; $x = 1, 2$, a metal powder having certain particle sizes and excess amount of PF_3 to the anhydrous solvent to synthesize $\text{Pt}(\text{PF}_3)_4$, wherein the anhydrous solvent is capable of dissolving $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$; and
- c) purifying the synthesized $\text{Pt}(\text{PF}_3)_4$ and storing the purified $\text{Pt}(\text{PF}_3)_4$ under air and moisture free conditions in apparatus and ampoules fabricated from metal or plastic, such as stainless steel.

[0085] Here the plastic may be selected from polyethylene, polypropylene, styrene, teflon, polytetrafluoroethylene (PTFE), perfluoroalkoxy alkane (PFA). The metal may be selected from selected from carbon steel, stainless steel, or stainless steel 316 alloy. The metal powder may be a Cu, Zn or Al powder, or the like.

[0086] The disclosed also include the purity of the product $\text{Pt}(\text{PF}_3)_4$ and storage vessels for the product $\text{Pt}(\text{PF}_3)_4$. The product $\text{Pt}(\text{PF}_3)_4$ may be stored in stainless steel and electro-polished stainless steel vessels at room temperature without changing of purity. The disclosed methods for synthesis of $\text{Pt}(\text{PF}_3)_4$ further comprise the steps of purifying the synthesized $\text{Pt}(\text{PF}_3)_4$:

- distilling the synthesized $\text{Pt}(\text{PF}_3)_4$ in a metal trap to remove the solvent and by-products, forming a by-product removal $\text{Pt}(\text{PF}_3)_4$;
- distilling the by-product removal $\text{Pt}(\text{PF}_3)_4$ in a metal vessel to remove the solvent and residual PF_3 , forming a purified $\text{Pt}(\text{PF}_3)_4$; and
- optionally, recycling the residual PF_3 for synthesizing $\text{Pt}(\text{PF}_3)_4$.

[0087] The disclosed methods for synthesizing $\text{Pt}(\text{PF}_3)_4$ further comprise the steps of storing the purified $\text{Pt}(\text{PF}_3)_4$:

- storing the purified $\text{Pt}(\text{PF}_3)_4$ in a metal (e.g., stainless steel) vessel or an inner surface passivated or electro-polished metal (e.g., stainless steel) vessel at room temperature.

[0088] Here, the purity of the purified $\text{Pt}(\text{PF}_3)_4$ stored in the metal vessels or an inner surface passivated or electro-polished metal vessels may not change and remains constant. The vessel fabricated from carbon steel, stainless steel, and stainless steel 316 alloy. The metal vessel may have electro-polished inner surface. Alternatively, $\text{Pt}(\text{PF}_3)_4$ may be stored in a plastic vessel. The plastic material may be polyethylene, polypropylene, styrene, teflon, polytetrafluoroethylene (PTFE), perfluoroalkoxy alkane (PFA).

[0089] The metal powder used in the disclosed methods consists of a metal having an

electrode potential lower than that of platinum, not interacting with PF_3 and not forming complexes with PF_3 under the reaction conditions and having a proper particle size range allowing it to stay in a powder form during the reaction process.

[0090] The metal powder preferably is a copper, zinc, aluminum powder, or the like. Any metal and its halide not interacting with PF_3 and not forming complexes with PF_3 under the reaction conditions and having the electrode potential lower than that of platinum (+1.2) may be used herein. For example, Cu (+0.34), Pb (-0.13), Sn (-0.14), Cd (-0.40), Zn (-0.76) and their halides do not interact with PF_3 under the reaction conditions and do not form complexes with PF_3 , which may be used as the metal powder.

Examples

[0091] The following non-limiting examples are provided to further illustrate embodiments of the invention. However, the examples are not intended to be all-inclusive and are not intended to limit the scope of the inventions described herein.

Experimental Procedures

[0092] Reaction mixtures, starting materials, solvents and products may be analyzed by any suitable means, such as by gas chromatography, NMR, Raman, FTIR spectroscopy using part of the stream or aliquots. All measurements were performed for samples in the closed containers, suitable tubes, or ampoules without any contact with atmosphere containing oxygen and moisture. Liquid nitrogen, nitrogen gas of high purity with less than 0.1 ppm of O_2 and water.

[0093] Reagents: Potassium Hexachloroplatinate (IV) (K_2PtCl_6 , Pt Assay $40.1 \pm 0.7\%$, CAS: 16921-30-5) was from Colonial Metals, Inc.; Platinum(II) chloride (PtCl_2 , Pt Assay $73.3 \pm 1.0\%$, CAS: 10025-65-7) was from Colonial Metals, Inc. Three types of copper powder, one was (99.999%) 100 mesh (100 mesh = $149 \mu\text{m}$) from Strem Chemicals Inc.; another one was $< 425 \mu\text{m}$, 99.5% from Sigma-Aldrich; another one was $< 45 \mu\text{m}$, 99.99% from Sigma-Aldrich. Phosphorus(III) fluoride (PF_3 , CAS: 7783-55-3) was from Advance Research Chemicals, Inc. Molecular sieves, 3 Å, beads, 4-8 mesh (Sigma-Aldrich), were regenerated either in dry nitrogen stream at temperatures 300-350°C or under vacuum at temperatures 300-350°C and operated under nitrogen atmosphere with less than 0.5 ppm of O_2 and moisture after regeneration. Solvents xylenes and hexadecane were from Sigma-Aldrich degassed and dried over 3 Å molecular sieves. The reactor was loaded with platinum compound and copper powders under nitrogen atmosphere with less than 0.5 ppm of O_2 and water.

Example 1. Synthesis of $\text{Pt}(\text{PF}_3)_4$ in high pressure reactor with hexadecane solvent.

[0094] Referring to Table 1 below, amounts of PtCl_2 , Cu, hexadecane are loaded in a reactor from Parr Instrument Company (Series 4540, 600 mL rated for 5000 psig) in a glove box. The

reactor transferred and connected to the vacuum line, vacuumed below 0.3 Torr and the required amount of PF_3 introduced in the reactor below -79°C (# 1-3) or at room temperature (# 6). Then the reactor warmed to room temperature, stirring started, and then the temperature in reactor increased to 105°C and the reaction mixture stirred under PF_3 pressure. In reaction #6, PF_3 is added in the reactor by portions during the reaction to maintain pressure in the range 100 - 200 psig. The pressure decrease observed in all reactions during the first 6 hours at 105°C and then the pressure stabilized indicating that the reaction may take approximately 6 hours. The pressure in reactor monitored during several more hours, then the reactor content cooled to $35 - 45^\circ\text{C}$ and the portion of gases (about 25 - 35%) directed in pre vacuumed trap (0.44 L, material stainless steel) cooled with the dry ice – isopropanol mixture. In reaction #6, all pressure released in the trap. The reactor closed, trap kept for about 10 min and then the non-condensable gas directed in the second trap cooled with liquid nitrogen (6L, material Aluminum). Transfer lines and valves were warmed if cooled below 0°C with the passing gas. After condensation of PF_3 portion in 6 L Al trap, vacuum applied to 6L Al trap to get the pressure in trap below 1 Torr. Operation repeated until all PF_3 and $\text{Pt}(\text{PF}_3)_4$ were stripped from the reactor and collected in two different traps. Then the trap with $\text{Pt}(\text{PF}_3)_4$ was reconnected to a separate pre-vacuumed vessel (0.4 L, electropolished stainless steel). The parent trap with $\text{Pt}(\text{PF}_3)_4$ warmed to room temperature, while a receiving vessel cooled with liquid nitrogen and all $\text{Pt}(\text{PF}_3)_4$ distilled in the receiving vessel under a static vacuum. After distillation, the receiving vessel warmed to room temperature and the residual PF_3 released through the scrubber. Yield of $\text{Pt}(\text{PF}_3)_4$ is in **Table 1** below.

Table 1

#	PtCl_2 (g)	Solvent	(mL)	PF_3 (psig) at 105°C	Yield of $\text{Pt}(\text{PF}_3)_4$ (% g)	Reactor
1	25.7	Hexadecane	100	2250-2350	93% (49.3 g)	SS Steel
2	40.3	Hexadecane	150	2150-2350	88% (73.5 g)	SS Steel
3	51.0	Hexadecane	129	2300-2500	86% (90.0 g)	SS Steel
4	8.75	Hexadecane	40	20-50	79% (14.3 g)	Glass
5	2.19	Xylene	18.5	20-40	95% (4.3 g)	Glass
6*	50	Hexadecane	200	100-200	90% (94 g)	SS Steel

*Reaction 6 is prophetic.

SS Steel reactor = high pressure reactor from Parr Instrument Company (Series 4540, 600 mL).
Glass reactor = 150mL HW Pressure Glass Vessel from Chemglass Life Sciences, part number CG-1880-31. The glass vessel is equipped with the thermocouple and pressure gauge.

[0095] Purity of $\text{Pt}(\text{PF}_3)_4$ is more than 99% in all experiments according to ^1H , ^{19}F NMR. For

example, reaction #1, ^{19}F NMR of neat product (σ CFCl_3 , ppm): -11.5 (m, $J(\text{P-F}) = 1302$ Hz, 99.63%, $\text{Pt}(\text{PF}_3)_4$), -34.4 (d, $J(\text{P-F}) = 1402$ Hz, 0.05%, PF_3), -81.58 (0.19%, fluorophosphoric acid, not assigned), -92.4 (d, $J(\text{P-F}) = 2035$ Hz, 0.12%, POF_3). ^1H NMR of neat product (σ SiMe_4 , ppm): 0.90 and 1.32 (hexadecane), 13.1 (s, fluorophosphoric acid). Determination of hexadecane by ^1H NMR. Taken 0.18 g of purified product from reaction #1 and mixed with in 0.77 g of C_6D_6 containing 0.03% (0.23 mg, 0.0026 mmol of SiMe_4). ^1H NMR of solution (σ SiMe_4 , ppm): 0.00 (s, 97.7 mol.%, SiMe_4), 1.32 (2.3 mol.%, hexadecane), 7.16 (s, fluorophosphoric acid, relative intensity not measured since C_6D_6 not dried from moisture). If to recalculate mol% to wt.%, and count that solution contains 0.23 mg TMS, then the total amount of hexadecane in $\text{Pt}(\text{PF}_3)_4$ sample is 0.014 mg corresponding to 79 ppm in $\text{Pt}(\text{PF}_3)_4$ from reaction #1.

[0096] Additional trap to trap distillation afford $\text{Pt}(\text{PF}_3)_4$ with purity 99.79%. ^{19}F NMR of neat sample measured in glass ampoule (σ CFCl_3 , ppm): -11.5 (m, $J(\text{P-F}) = 1302$ Hz, 99.79%, $\text{Pt}(\text{PF}_3)_4$), -88.20 (d, $J(\text{P-F}) = 975$ Hz, 0.19%, $(\text{HO})\text{POF}_2$), -92.4 (d, $J(\text{P-F}) = 2035$ Hz, 0.01%, POF_3), -166.1 (s, 0.02%, SiF_4). ^1H NMR of neat sample (σ SiMe_4 , ppm): 0.90 and 1.32 (hexadecane, rel. int. 28%), 12.94 (s, $(\text{HO})\text{POF}_2$, rel. int. 72%). The resonances of hexadecane were below the limit of detection for solution of 0.07 g of sample in 0.78 g of C_6D_6 containing 0.03% of SiMe_4 . Hence the total amount of hexadecane is less than 80 ppm. FTIR. [liquid $\text{Pt}(\text{PF}_3)_4$ on Golden Gate™ probe, resolution 4 cm^{-1}]: 882, 827, 496 cm^{-1} .

Example 2. Synthesis of $\text{Pt}(\text{PF}_3)_4$ with isolation of $\text{PtCl}_2(\text{PF}_3)_2$ and hexadecane solvent.

a) Synthesis of $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) in hexadecane.

[0097] PtCl_2 (1.9 g, 7.1 mmol), hexadecane (15.8 g, 20.4 mL) loaded in the 150mL pressure glass ampoule (Chemglass Life Sciences, part number CG-1880-31) equipped with a stirring bar, thermocouple, pressure gauge. The ampoule connected to a vacuum line and cylinder with PF_3 . The ampoule with the starting materials vacuumed to around 0.2 Torr to remove nitrogen, then 35 psig of PF_3 added and the suspension heated under stirring. The content stirred for 4 hours in the temperature range 100-120°C under 20-35 psig of PF_3 , where PF_3 added by portions when the pressure was approaching to 20 psig. During the reaction, initially insoluble in hexadecane PtCl_2 fully reacted with PF_3 and formed soluble in hexadecane compounds, which partially sublimed on the colder parts of apparatus as colorless crystals. After 4 hours, the heating stopped, reaction mixture cooled to room temperature, PF_3 condensed back in the cylinder and a portion of crystals separated from solution and analyzed; the portion of supernatant hexadecane solution also analyzed by ^{19}F NMR. ^{19}F NMR of crystals dissolved in pure, anhydrous hexadecane (σ CFCl_3 , ppm): -36.4 (m, $J(\text{Pt-F}) = 628$ Hz, $J(\text{P-F}) = 1320$ Hz, $\text{PtCl}_2(\text{PF}_3)_2$). ^{19}F NMR of hexadecane supernatant solution (σ CFCl_3 , ppm): -32.5 (d, $J(\text{P-F}) = 1405$ Hz, PF_3), -36.4 (m, $J(\text{Pt-F}) = 622$ Hz, $J(\text{P-F}) = 1318$ Hz, $\text{PtCl}_2(\text{PF}_3)_2$). FTIR of crystals (neat solid on Golden Gate™ probe, resolution 4 cm^{-1}): 417 (sh, w), 447 (sh, w), 461 (m), 483

(s), 507 (s), 518 (s), 531 (m), 551 (s), 901 (vs), 907 (sh), 933 (vs), 961 (s), 969 (w), 974 (m), 985 (w) DSC of crystals: 19.0°C (phase transition), 72.5°C (phase transition), 118.3°C (melting point).

b) Synthesis of $\text{Pt}(\text{PF}_3)_4$ from $\text{PtCl}_2(\text{PF}_3)_x$ ($x = 1, 2$) in hexadecane.

[0098] The colorless crystals from a) placed in a supernatant hexane solution, copper added (2.22 g, 34.9 mmol) and the ampoule (150mL HW Pressure Glass Vessel) connected to a vacuum line and a cylinder with PF_3 . The ampoule with the starting materials briefly vacuumed to about 2 Torr to remove nitrogen, then 40 psig of PF_3 added and the suspension heated in the temperature range 100-130°C under stirring for 4 hours. The reaction is under 20-40 psig of PF_3 , where PF_3 added by portions when the pressure was approaching to 20 psig. After 4 hours heating stopped, the reaction mixture cooled to 35°C and $\text{Pt}(\text{PF}_3)_4$, PF_3 , some solvent condensed in the trap (made from stainless steel) cooled with liquid nitrogen under the static vacuum. $\text{Pt}(\text{PF}_3)_4$ purified from PF_3 and residual hexadecane by trap to trap distillation. Yield of $\text{Pt}(\text{PF}_3)_4$ is 1.25 g (32%, low yield since part of $\text{PtCl}_2(\text{PF}_3)_2$ and supernatant solution used for analyses in a)). ^{19}F NMR of neat product $\text{Pt}(\text{PF}_3)_4$ (σ CFCl_3 , ppm): -11.5 (m, $J(\text{P-F}) = 1301$ Hz, $\text{Pt}(\text{PF}_3)_4$). ^1H NMR of neat product (σ SiMe_4 , ppm): 0.23 (t, $J = 6.1$ Hz, 71.7 mol.%, Me_2SiF_2), 0.90 and 1.32 (28.3 mol.%, hexadecane).

Example 3. Synthesis of $\text{Pt}(\text{PF}_3)_4$ in glass ampoule with hexadecane solvent.

[0099] PtCl_2 (8.75 g, 32.9 mmol), Cu (18.25 g, 287.2 mmol), hexadecane (30.95 g, 40 mL) loaded in an ampoule (150mL HW Pressure Glass Vessel from Chemglass Life Sciences, part number CG-1880-31) equipped with a stirring bar, thermocouple, pressure gauge. The ampoule connected to a vacuum line and cylinder with PF_3 . The ampoule with the starting materials vacuumed to about 0.2 Torr to remove nitrogen, then 40 psig of PF_3 added and the content heated under stirring. The content stirred for 5.5 hours in the temperature range 110-120°C under 20-50 psig of PF_3 , where PF_3 added by portions when the pressure was approaching to 20 psig. During the reaction, crystals of $\text{PtCl}_2(\text{PF}_3)_2$ formed and then consumed and at the end of reaction the reaction mixture contained two non-miscible liquids. After 5 hours 30 min heating stopped, the reaction mixture cooled to 41°C and $\text{Pt}(\text{PF}_3)_4$, PF_3 , some solvent condensed in the trap (made from stainless steel) cooled with liquid nitrogen under the static vacuum. $\text{Pt}(\text{PF}_3)_4$ purified from PF_3 and residual hexadecane by trap to trap distillation. Yield of $\text{Pt}(\text{PF}_3)_4$ is 79% (14.2 g). ^{19}F NMR of neat sample (σ CFCl_3 , ppm): -11.5 (m, $J(\text{P-F}) = 1301$ Hz, 99.40%, $\text{Pt}(\text{PF}_3)_4$), -34.4 (d, $J(\text{P-F}) = 1402$ Hz, 0.36%, PF_3), -92.4 (d, $J(\text{P-F}) = 2035$ Hz, 0.23%, POF_3), -166.0 (s, 0.007%, SiF_4). ^1H NMR of neat sample (σ SiMe_4 , ppm): 0.23 (t, $J = 6.1$ Hz, 67.4 mol.%, Me_2SiF_2), 0.90 and 1.32 (6.9 mol.%, hexadecane), 1.45 (d, $J = 6.1$ Hz, 25.8 mol.%, $\text{P}(\text{O}^i\text{Pr})_3$).

Determination of the organic content by ^1H NMR. The intensities of the resonances of organic compounds were below the limit of detection for solution of 0.09 g of $\text{Pt}(\text{PF}_3)_4$ sample dissolved in 0.76 g of C_6D_6 containing 0.03% (0.228 mg, 0.0026 mmol of SiMe_4). Hence the total amount of organic compounds is less than 80 ppm in $\text{Pt}(\text{PF}_3)_4$.

Example 4. Synthesis of $\text{Pt}(\text{PF}_3)_4$ in glass ampoule applying xylene solvent.

[00100] PtCl_2 (2.19 g, 8.2 mmol), Cu (4.69 g, 73.8 mmol), xylenes (16.1 g) loaded in a 150mL pressure glass ampoule (Chemglass Life Sciences, part number CG-1880-31) equipped with a stirring bar, thermocouple, pressure gauge. The ampoule connected to a vacuum line and a cylinder with PF_3 . The ampoule with the starting materials briefly vacuumed to around 3 Torr to remove nitrogen, then 40 psig of PF_3 added and the content heated under stirring. The content stirred for 4.5 hours in the temperature range 100-120°C under 20-40 psig of PF_3 , where PF_3 added by portions when the pressure was approaching to 20 psig. During the reaction, crystals of $\text{PtCl}_2(\text{PF}_3)_2$ formed and then consumed and at the end of reaction the reaction mixture contained two non-miscible liquids. After 4 hours 30 min heating stopped, the reaction mixture cooled to 38°C and $\text{Pt}(\text{PF}_3)_4$, PF_3 , some solvent condensed in the trap (made from stainless steel) cooled with liquid nitrogen under the static vacuum. $\text{Pt}(\text{PF}_3)_4$ purified from PF_3 and residual solvent xylene by trap to trap distillation. Yield of $\text{Pt}(\text{PF}_3)_4$ is 95% (4.3 g). ^{19}F NMR of neat sample (σ CFCI_3 , ppm): -11.5 (m, $J(\text{P-F}) = 1301$ Hz, 99.58%, $\text{Pt}(\text{PF}_3)_4$), -34.4 (d, $J(\text{P-F}) = 1402$ Hz, 0.39%, PF_3), -92.4 (d, $J(\text{P-F}) = 2035$ Hz, 0.03%, POF_3), -166.0 (s, 0.01%, SiF_4). % are from integration. ^1H NMR of neat sample (σ SiMe_4 , ppm): 0.12 (t, $J = 6.1$ Hz, 0.7 mol.%, Me_2SiF_2), 1.11 (t) and 2.56 (q) (18.8 mol.%, $\text{Et-C}_6\text{H}_5$), 2.05 (s) and 2.14 (s) (79.4 mol.%, xylenes), 6.97 (m, aromatic protons), 12.46 (br, 1.0 mol.%, fluorophosphoric acid). Determination of the residual solvent by ^1H NMR. Taken 0.088 g of $\text{Pt}(\text{PF}_3)_4$ sample dissolved in 0.80 g of C_6D_6 containing 0.03% (0.24 mg, 0.0027 mmol of SiMe_4). ^1H NMR (σ SiMe_4 , ppm): 0.00 (s, 6.28 mol.%, SiMe_4), 1.07 (t) and 2.39 (q) (18.64 mol.%, $\text{Et-C}_6\text{H}_5$), 2.02 (s, 11.41 mol.%, xylene), 2.14 (s, 63.67 mol.%, xylene), 6.97 (m, aromatic protons). If to recalculate mol% to wt.%, and count that solution contains 0.24 mg TMS, then the total amount of organic compounds is 4.27 mg corresponding to 4.85 wt.% in 88 mg of $\text{Pt}(\text{PF}_3)_4$ sample.

Example 5. $\text{Pt}(\text{PF}_3)_4$ Shelf Life

[0101] A shelf life study was performed during 12 weeks at room temperature. $\text{Pt}(\text{PF}_3)_4$ obtained in syntheses described in examples 3 and 4 and was stored at room temperature in a 316 alloy Single-Ended Miniature Sample Cylinder, volume 50 cm^3 with the blind cap attached and in electro-polished Stainless-Steel Miniature Canister ($V = 400$ cm^3) with the blind cap attached. Both containers were vacuum baked at approximately 150°C and 30 - 50 mTorr before

introducing $\text{Pt}(\text{PF}_3)_4$. ^{19}F and ^1H NMR spectra were measured for the neat liquid $\text{Pt}(\text{PF}_3)_4$ every 2 weeks, monitored $\text{Pt}(\text{PF}_3)_4$ assay and relative amount of impurities from ^{19}F and ^1H NMR spectra. The results of shelf life study are in Table 2.

Table 2

Package (Room Temperature)	Material	$\text{Pt}(\text{PF}_3)_4$ load (g)	$\text{Pt}(\text{PF}_3)_4$ assay*	Impurities	Hexadecane
50 mL	316 SS	45	99.74±0.06 %	0.26±0.06 %	Not quantified (< 10 ppm)
400 mL	Electro- polished SS	160	99.77±0.02 %	0.22±0.03 %	9.6±0.5 ppm

* Starting amount on day 1.

[0102] $\text{Pt}(\text{PF}_3)_4$ assay and relative amount of impurities is nearly similar in all experiments within 12 weeks. The deviation is higher for 316 SS steel ampoule. These results demonstrate the stability of $\text{Pt}(\text{PF}_3)_4$ over time. FIG. 4 is a graph for the $\text{Pt}(\text{PF}_3)_4$ assay and relative amount of impurities over time in a 400 mL electro-polished stainless-steel miniature canister at room temperature. The disclosed $\text{Pt}(\text{PF}_3)_4$ is aimed to use as a precursor for Pt-containing films in microelectronic devices or in catalyst industries.

Comparative Example 1. Synthesis of $\text{Pt}(\text{PF}_3)_4$ starting from K_2PtCl_6 using the recipes from Angew. Chem. Int. Ed. 1965, 4, 521 and RU2478576C2

[0103] Syntheses of $\text{Pt}(\text{PF}_3)_4$ according to the recipes from Angew. Chem. Int. Ed. 1965, 4, 521 and RU2478576C2 are shown in Table 3 below. The experiments are conducted with a commercially available high pressure reactor from Parr Instrument Company (Series 4540, 600 mL rated for 5000 psig equipped with the standard impeller in experiments #10 and #12 and with the U-type anchor stirrer designed for an efficient stirring of solids in b). The process of RU2478576C2 utilizes pure hydrogen and a step of drying after reduction, which requires costly safety equipment and a long time, if removal of water from the system is ever possible by scaling. As shown in Table 3, #10 was done with the copper powder Cu of 149 μm size (copper powder packed by vendor under argon and utilized as). #11 and #12 were done with the copper powder Cu of 425 μm size (99.5% from Sigma-Aldrich). Synthesis of $\text{Pt}(\text{PF}_3)_4$ starting from PtCl_2 (#12, Table 3) performed according to [Angew. Chem. Int. Ed. 1965, 4, 521] was done with, where Cu prepared from Copper powder of < 425 μm size (99.5% from Sigma-Aldrich). $\text{Pt}(\text{PF}_3)_4$ (in # 10-12) is forming in low to moderate yields.

[0104] Referring to Table 3, comparative examples performed on commercially available standard equipment, amounts of the starting materials K_2PtCl_6 , PtCl_2 , Cu were loaded in a

reactor in a glove box with < 0.5 ppm of oxygen and moisture. The reactor sealed, connected to the vacuum line, vacuumed below 0.2 Torr, cooled below -79°C and the required amount of PF₃ introduced in reactions #10 to #12 at low temperature with stirring. Then the reactor warmed to room temperature and further to 105 -130°C and the content stirred under PF₃ pressure for 24 hours. Then reactor content cooled to 35 - 45°C and the portion of gases (about 25 - 35%) directed in pre vacuumed trap (0.44 L, material stainless steel) cooled with the dry ice – isopropanol mixture. The reactor closed, trap kept for about 10 min and then the non-condensable gas directed in the second trap cooled with liquid nitrogen (6 L, material Aluminum). Transfer lines and valves were warmed if cooled below 0°C with the passing gas. After condensation of PF₃ portion in 6 L Al trap, vacuum applied to 6L Al trap to get the pressure in trap below 1 Torr. Operation repeated until all PF₃ and Pt(PF₃)₄ were stripped from the reactor and collected in two different traps. Then the trap with Pt(PF₃)₄ was reconnected to a separate pre-vacuumed vessel (50 mL, stainless steel). The parent trap with Pt(PF₃)₄ warmed to room temperature, while a receiving vessel cooled with liquid nitrogen and all Pt(PF₃)₄ distilled in the receiving vessel under a static vacuum. After distillation, the receiving vessel warmed to room temperature and the residual PF₃ released through the scrubber. Yield of Pt(PF₃)₄ for each experiment shows a low to moderate yield, although RU2478576C2 claimed 60-95% yield. The low to moderate yield of Pt(PF₃)₄ obtained from RU2478576C2 recipe might be because of a lack of solvent. Purity of Pt(PF₃)₄ is more than 97.9% in all experiments according to ¹H, ¹⁹F NMR. As example, ¹⁹F NMR of neat product from experiment b) (σ CFCI₃, ppm): -11.5 (m, J(P-F) = 1302 Hz, 97.9%, Pt(PF₃)₄), -34.4 (d, J(P-F) = 1402 Hz, 0.2%, PF₃), -92.4 (d, J(P-F) = 2035 Hz, 2.0%, POF₃).

Table 3

#	Pt reagent (g)	Cu powder size (μm)	PF ₃ pressure (psig)	Yield of Pt(PF ₃) ₄ (% , g)	Observations
10	29.3 [K ₂ PtCl ₆]	149	1552	1%, 0.5 g	Solid baked in one block, no stirring
11	54.1 [K ₂ PtCl ₆]	425	2940	60%, 36.2 g	Anchor stirrer. K ₂ PtCl ₆ partially sublimed on colder parts of reactor and did not react further.
12	26.9 [PtCl ₂]	425	2350	20%, 11.1 g	Standard impeller. Poor mixing.

Example 6. Synthesis of Pt(PF₃)₄ starting from K₂PtCl₆ in high pressure reactor with hexadecane solvent.

[0105] K_2PtCl_6 (79.5 g, 0.16 mol), Cu (120.6 g, 1.9 mol), hexadecane (100 g) are loaded in a reactor (Parr Instrument Company, Series 4540, 600 mL rated for 5000 psig) in glove box. The reactor transferred and connected to the vacuum line, vacuumed below 0.3 Torr and cooled below -79°C and 387 g (4.4 mol) of PF_3 introduced in the reactor. Then the reactor warmed to room temperature, stirring started, the reactor further warmed to 120°C and the content stirred under PF_3 pressure for 22 hours. Then reactor content cooled to $35 - 45^\circ\text{C}$ and the portion of gases (about 25 - 35%) directed in pre vacuumed trap (0.44 L, material stainless steel) cooled with the dry ice – isopropanol mixture. The reactor closed, trap kept for about 10 min and then the non-condensable gas directed in the second trap cooled with liquid nitrogen (6L, material Aluminum). Transfer lines and valves were warmed if cooled below 0°C with the passing gas. After condensation of PF_3 portion in 6 L Al trap, vacuum applied to 6L Al trap to get the pressure in trap below 1 Torr. Operation repeated until all PF_3 and $Pt(PF_3)_4$ were stripped from the reactor and collected in two different traps. Then the trap with $Pt(PF_3)_4$ was reconnected to a separate pre-vacuumed vessel (50 mL, stainless steel). The parent trap with $Pt(PF_3)_4$ warmed to room temperature, while a receiving vessel cooled with liquid nitrogen and all $Pt(PF_3)_4$ distilled in the receiving vessel under a static vacuum. After distillation, the receiving vessel warmed to room temperature and the residual PF_3 released through the scrubber. Yield of $Pt(PF_3)_4$ is 23.2 g, 25.9% from K_2PtCl_6 . See Table 4, which lists the yields of $Pt(PF_3)_4$ starting from K_2PtCl_6 , in the two reactions of this Example and the above Comparative Example 1. #13 is from the above Comparative Example 1 #11 and #14 was the result of this Example. Both reactions are at the same temperature and PF_3 pressure. Assay of $Pt(PF_3)_4$ by integration of ^{19}F NMR spectrum is 99.48%. ^{19}F NMR of neat product from experiment b) (σ CFCl_3 , ppm): -11.5 (m, $J(\text{P-F}) = 1302$ Hz, 99.48%, $Pt(PF_3)_4$), -34.4 (d, $J(\text{P-F}) = 1402$ Hz, 0.3%, PF_3), -92.4 (d, $J(\text{P-F}) = 2035$ Hz, 0.2%, POF_3).

Table 4

#	K_2PtCl_6 (g)	Hexadecane	Yield of $Pt(PF_3)_4$
13	54.1	-	60% (36.2 g)
14	79.5	120 mL	26% (23.2 g)

[0106] The reason of the low yields of using $PtCl_2$ in Table 3 may be due to inefficient mixing of components, coating of metal with the metal chloride during the reaction and other factors accompanying the reaction starting from two different solids and gas. The solution may be to shift from a solid gas-system to the solution-solid system to have a better mixing of components and more efficient interaction of components dissolved in the liquid phase with the suspended metal powder. However, no solution-solid system have been reported thus far because of the

expectation that solvent will undergo catalytic reaction with Pt precursor or intermediate.

[0107] Although the subject matter described herein may be described in the context of illustrative implementations to process one or more computing application features/operations for a computing application having user-interactive components the subject matter is not limited to these particular embodiments. Rather, the techniques described herein may be applied to any suitable type of user-interactive component execution management methods, systems, platforms, and/or apparatus.

[0108] It will be understood that many additional changes in the details, materials, steps, and arrangement of parts, which have been herein described and illustrated in order to explain the nature of the invention, may be made by those skilled in the art within the principle and scope of the invention as expressed in the appended claims. Thus, the present invention is not intended to be limited to the specific embodiments in the examples given above and/or the attached drawings.

[0109] While embodiments of this invention have been shown and described, modifications thereof may be made by one skilled in the art without departing from the spirit or teaching of this invention. The embodiments described herein are exemplary only and not limiting. Many variations and modifications of the composition and method are possible and within the scope of the invention. Accordingly, the scope of protection is not limited to the embodiments described herein, but is only limited by the claims which follow, the scope of which shall include all equivalents of the subject matter of the claims.

List of Drawing Symbols

11	Cu powder
12	PtCl ₂
13	PF ₃
14	solvent
15	container
16	reactor
17	pre-vacuumed trap
18	Pt(PF ₃) ₄ trap
19	metal ampoule
20	PF ₃ trap
101	line
102	addition funnel
103	addition line
104	drying process

105 line
106 line
107 line
108 bypassing
109 packaging
110 line

What is claimed is:

1. A method for synthesizing $\text{Pt}(\text{PF}_3)_4$ (CAS # 19529-53-4), the method comprising the steps of:
 - dissolving a platinum compound having a general formula, $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, in an anhydrous solvent forming a $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I , $x = 1, 2$;
 - adding a metal powder and excess amount of PF_3 into the $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ solution; and
 - forming $\text{Pt}(\text{PF}_3)_4$ through a reaction between $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$, PF_3 and the metal powder under a reaction condition.
2. The method of claim 1, wherein the reaction condition includes a reaction temperature ranging from approximately from 30 to 200°C.
3. The method of claim 1, wherein the reaction condition includes a reaction pressure below approximately 300 psig.
4. The method of claim 1, wherein the anhydrous solvent has a boiling point higher than 150°C.
5. The method of claim 1, wherein the metal powder is a copper, zinc or aluminum powder.
6. The method of claim 1, wherein the metal powder has a particle size ranging from 200 – 900 microns.
7. The method of claim 1, further comprising the step of synthesizing the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$), wherein the synthesizing step comprises the steps of:
 - dispersing a platinum precursor having a general formula, $\text{Pt}(\text{Hal})_2$, into the anhydrous solvent forming a suspension of $\text{Pt}(\text{Hal})_2$, wherein $\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ;
 - introducing PF_3 into the suspension of $\text{Pt}(\text{Hal})_2$; and
 - forming the solution of the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$ ($\text{Hal} = \text{F}, \text{Cl}, \text{Br}$ or I ; $x = 1, 2$) in the anhydrous solvent through a reaction of PF_3 and $\text{Pt}(\text{Hal})_2$.
8. The method of claim 7, wherein the platinum precursor $\text{Pt}(\text{Hal})_2$ is anhydrous.
9. The method of any one of claims 1 to 8, wherein the platinum compound $\text{Pt}(\text{Hal})_2(\text{PF}_3)_x$

(Hal = F, Cl, Br or I, x = 1, 2) is anhydrous.

10. The method of any one of claims 1 to 8, wherein the anhydrous solvent is a hydrocarbon solvent selected from an oxyhydrocarbon solvent having a general formula $(C_nH_{2n+1})_2O$ ($n \geq 1$) and $H_3C(O(CH_2)_nOCH_3$ ($n \geq 1$), an arene solvent having a general formula $(C_nH_{2n+1})_xC_6H_{6-x}$ ($x \geq 1, n \geq 1$) or an alkane solvent having a general formula C_nH_{2n+2} ($n \geq 1$).

11. The method of any one of claims 1 to 8, wherein a yield of $Pt(PF_3)_4$ is in a range of approximately 70-99.9%.

12. The method of any one of claims 1 to 8, wherein a purity of $Pt(PF_3)_4$ is approximately 90-99.9 wt. % after purification.

13. A method for synthesis and storage of $Pt(PF_3)_4$ (CAS # 19529-53-4), the method comprising the steps of:

- a) forming a suspension of a platinum precursor $Pt(Hal)_2$, wherein Hal = F, Cl, Br or I, and a metal powder in an anhydrous solvent;
- b) introducing excess amount of PF_3 into the suspension of $Pt(Hal)_2$ and the metal powder;
- c) forming a soluble reaction intermediate $Pt(Hal)_2(PF_3)_x$ in the anhydrous solvent through a reaction between PF_3 and $Pt(Hal)_2$, wherein Hal = F, Cl, Br or I; $x = 1, 2$, under a low pressure condition;
- d) forming $Pt(PF_3)_4$ from a reaction between $Pt(Hal)_2(PF_3)_x$, the metal powder and PF_3 in the anhydrous solvent;
- e) purifying $Pt(PF_3)_4$ under air and moisture free conditions in a trap made of metal; and
- f) storing the purified $Pt(PF_3)_4$ under the air and moisture free conditions in a container made of the metal.

14. The method of claim 13, wherein the platinum precursor $Pt(Hal)_2$ is anhydrous $PtCl_2$.

15. The method of claim 13, wherein the anhydrous solvent has a boiling point higher than 150°C.

16. The method of any one of claims 13 to 15, wherein a reaction temperature ranges from approximately 30-200°C.

17. The method of any one of claims 13 to 15, wherein the low pressure condition is a pressure below approximately 300 psig.
18. The method of any one of claims 13 to 15, wherein a purity of $\text{Pt}(\text{PF}_3)_4$ is approximately 90-99.9 wt.% after purification.
19. A method for manufacture and storage of $\text{Pt}(\text{PF}_3)_4$ (CAS # 19529-53-4), the method comprising the steps of:
- a) forming a suspension of a platinum precursor $\text{Pt}(\text{Cl})_2$ in an anhydrous solvent selected from xylene or hexadecane;
 - b) introducing excess amount of PF_3 into the suspension of $\text{Pt}(\text{Cl})_2$ to form a solution of $\text{Pt}(\text{Cl})_2(\text{PF}_3)_x$ ($x = 1, 2$) in the anhydrous solvent through a reaction between PF_3 and $\text{Pt}(\text{Cl})_2$;
 - c) adding a copper powder into the solution of $\text{Pt}(\text{Cl})_2(\text{PF}_3)_x$ ($x = 1, 2$);
 - d) forming $\text{Pt}(\text{PF}_3)_4$ from a reaction between the copper powder, PF_3 and $\text{Pt}(\text{Cl})_2(\text{PF}_3)_x$ in the anhydrous solvent in a reduced PF_3 pressure ranging from 20 to 300 psig and a reaction temperature ranging from 30-200°C;
 - e) purifying $\text{Pt}(\text{PF}_3)_4$ under air and moisture free conditions in a trap made of stainless steel; and
 - f) storing the purified $\text{Pt}(\text{PF}_3)_4$ under the air and moisture free conditions in a container made of the stainless steel, wherein the inner surface of the container is electro-polished or passivated with PF_3 .
20. The method of claim 19, wherein the copper powder has a particle size ranging from 200 – 900 microns.