

-1-

REPLACED SHEETS		SG
☒	Description : paged1.... to paged ...14....	
☒	Claim(s) : paged ...17.... to paged ...19....	
☒	Drawing(s) : paged ...1/1t. to paged ...17/1t....	
☒	Abstract : paged ...19.... to paged-	
DATE OF RECEIPT		

Ref. 01-8285

SULFUR REDUCTION IN FCC GASOLINE

Inventors: R. F. Wormsbecher
G. Kim

This Sheet Has Been Replaced



1-10200000

The present invention relates to catalytic cracking, and more specifically to catalytic cracking compositions and processes that may be used to catalytically convert high molecular weight feedstocks into valuable lower molecular weight products having reduced sulfur content.

It is generally known that catalytic cracking catalysts which comprise zeolites such as synthetic faujasite, zeolite Beta, and ZSM-5 dispersed in an inorganic oxide matrix such as silica/alumina hydrogel, sols and clay may be used to economically convert heavy hydrocarbon feedstocks such as gas-oils and/or resid into gasoline and diesel fuel.

More recently it has been disclosed that the addition of SOx reduction "additives" such as alumina, magnesium aluminate (spinel) to cracking catalyst compositions will improve the overall performance of the catalyst, particularly when used to process feedstocks that contain significant quantities of sulfur.

Canadian patent 1,117,511 describes FCC catalysts which contain free alumina hydrate, particularly alpha-alumina hydrate (boehmite) which may be used to catalytically crack hydrocarbons that contain sulfur.

U.S. Patent 4,010,116 discloses FCC catalysts which contain pseudo-boehmite aluminas that may contain crystalline trihydrate components such as bayerite and gibbsite.

While it is recognized that additives including aluminas and spinels may be added to catalytic cracking catalysts to reduce SOx emissions during the oxidation and regeneration of FCC catalyst, the industry has not developed catalytic cracking catalyst



compositions that reduce the sulfur level of cracked products such as gasoline and diesel fuel

5 It is therefore an object to provide improved FCC catalysts and additives which possess the ability to reduce the sulfur content of cracked products.

10 It is another object of the present invention to provide improved catalytic cracking compositions, additives and processes for converting sulfur-containing hydrocarbon feedstocks to low sulfur gasoline and diesel fuel.

15 It is yet a further object to provide a particulate FCC catalyst additive composition that may be blended with conventional zeolite-containing catalysts to reduce the sulfur content of cracked products.

20 These and additional objects of the invention will become readily apparent to one skilled-in-the-art from the following detailed description, specific examples, and drawings, wherein Figures 1-18 are graphic representations of Conversion vs. Gasoline sulfur content data, which illustrates the sulfur reduction capability of catalysts/additives of our invention.

25 Broadly, our invention contemplates zeolite catalytic cracking catalyst compositions and additives that contain a Lewis acid supported upon alumina and the use thereof to process hydrocarbon feedstocks.

30 More specifically, we have discovered that cracking catalyst compositions which contain from about 1 to 50 weight percent of a Lewis acid such as a compound of Ni, Cu, Zn, Ag, Cd, In, Sn, Hg, Tl, Pb, Bi, B, Al (other than Al_2O_3) & Ga supported on alumina may be used to obtain gasoline fractions that have low sulfur content.



In particular, we have found that if a composition which comprises from about 1 to 50 weight percent of a Lewis acid supported on alumina is added to conventional particulate zeolite containing fluid catalytic cracking (FCC) catalysts as either an integral catalyst matrix component or as a separate particulate additive having the same particle size as the conventional FCC catalyst, the catalysts may be used in the catalytic cracking of high molecular weight sulfur containing hydrocarbons feedstocks such as gas-oil, residual oil fractions and mixtures thereof to produce products such as gasoline and diesel fuel that have significantly reduced sulfur content.

Furthermore, the surface area of the Lewis acid on alumina should be as high as possible to facilitate the interaction of the sulfur species in the hydrocarbon feedstock. In other words, the dispersion of the Lewis acid on the support should be as high as possible. Therefore, compounds which can stabilize the alumina support surface area can be incorporated in the support, such as lanthana, or baria. Silica, which is also known to stabilize the surface area of alumina is detrimental to this invention.

While the mechanism by which the Lewis acid-containing alumina removes the sulfur components normally present in cracked hydrocarbon products is not precisely understood, it is believed that the Lewis Base (basic) sulfur species produced in the cracking of sulfur-containing hydrocarbons, such as gas-oil, interact with the Lewis acid on alumina by absorption or chemical reaction.

In other words, during the catalytic cracking of a sulfur-containing gas-oil at 500 to 550°C sulfur



species are produced in the gasoline boiling range from the cracking reaction. These species are thiophene, C₁ to C₄ alkylthiophenes, tetrahydrothiophene, and propyl to hexyl mercaptans, which all have boiling points in the gasoline range. These species are Lewis bases and can interact with the Lewis acid-containing alumina. One such interaction would be adsorption of the sulfur Lewis base species to the Lewis acid-containing alumina in the riser/reactor side of the FCCU. The adsorbed species on the Lewis acid-containing alumina could then be oxidized free of the sulfur Lewis base species in the regenerator side of the FCCU, enabling more sulfur species to be adsorbed in the riser/reactor side. Another interaction would be the adsorption of the sulfur Lewis base on the Lewis acid-containing alumina, followed by cracking reactions in the riser/reactor side of the FCCU. The most likely products from these reactions would be hydrogen sulfide and hydrocarbons free of sulfur.

As shown in the examples, this invention selectively removes those sulfur species from the gasoline, such as thiophene, methylthiophenes, ethylthiophenes, propylthiophenes, and tetrahydrothiophene.

The Lewis acid-containing alumina component is prepared by reacting/impregnating an alumina substrate, which in itself has Lewis acid properties, having a surface area of about 30 to 400 m²/g, with a "second" Lewis acid component selected from the group consisting of elements/compounds selected from the group consisting of Ni, Cu, Zn, Ag, Cd, In, Sn, Hg, Tl, Pb, Bi, B, Al (not Al₂O₃), Ga and mixtures thereof.



The preferred "desulfurizing" compositions of our invention contain from about 1 to 50 weight percent and preferably 10 to 40 weight percent of the second Lewis acid component, expressed as the oxide, and the
5 balance alumina (Al_2O_3).

Our Lewis acid desulfurization compositions are prepared by incorporating an alumina support having a particle size of 1 to 150 $\text{m}\mu$ with a salt solution of the second Lewis acid component. Typically, aqueous
10 solutions which contain from about 10 to 20 weight percent of the Lewis acid metal salt compound, preferably the nitrates, chlorides and sulfates are used to impregnate the alumina to incipient wetness, i.e. fill the water pore volume.

15 The impregnated alumina is then dried at 100 to 150°C and heated (calcined) at 200 to 850°C to remove the anionic component, such as chloride, nitrate, or sulfate, thereby yielding a particulate desulfurization composition which may be added to
20 commercial zeolite-containing "cracking" catalyst either as a component of the catalyst particulate, or as a separate particulate additive.

The hydrothermal stability of alumina substrate can be improved by stabilizing alumina with
25 approximately 5 to 30 weight percent La_2O_3 . This can be achieved either by incipient-wetness impregnation of alumina particles with an aqueous solution of lanthanum or lanthanum-rich rare earth salt solution, followed by drying and calcination, or by co-
30 precipitating well-mixed hydrous oxides of both lanthanum and aluminum, followed by washing, drying, and calcination.

Dispersion of the key Lewis acid component can be improved by including a precursor of this ingredient



in the co-precipitation of well-mixed hydrous oxides of aluminum and lanthanum. For example, a key Lewis acid such as ZnO can be well-dispersed on lanthana-stabilized alumina by a co-precipitation reaction as follows: two feedstreams are simultaneously fed into a mix-pump, one acidic stream containing a mixed aqueous solution of Zn, La (or La/Nd or La-rich rare earth) salts along with an acid as needed, the other a basic solution containing a sodium aluminate solution and sodium hydroxide as needed, maintaining approximately 8 to 9.5 pH at the mix-pump outlet. After dewatering, milling, and homogenization, the resulting slurry is spray dried, washed, dried, and calcined at approximately 500° to 700°C to obtain attrition resistant particles compatible with FCC catalysts.

Catalysts which may be improved by the addition of our Lewis acid compositions typically comprise crystalline alumino-silicate zeolites such as synthetic faujasite i.e. type Y zeolite, type X zeolite, Zeolite Beta, ZSM-5, as well as heat treated (calcined) and/or rare-earth exchanged derivatives thereof dispersed in an inorganic oxide matrix. Zeolites which are particularly suited include calcined rare-earth exchanged type Y zeolite (CREY), the preparation of which is disclosed in US patent 3,402,996, ultrastable type Y zeolite (USY) as disclosed in US patent 3,293,192, as well as various partially exchanged type Y zeolites as disclosed in US patents 3,607,043 and 3,676,368. The catalysts may also contain molecular sieves such as SAPO and ALPO as disclosed in US patent 4,764,269. Typical catalyst compositions will include from about 5 to 50 weight percent molecular sieve, about 1 to 50 weight percent Lewis acid alumina dispersed in the catalyst

This Sheet Has Been Replaced



particles, and the balance will comprise an inorganic oxide matrix which comprises binders and additives such as silica, silica alumina and alumina gels and sols as well as clay such as kaolin. Procedures that
5 may be used to prepare FCC catalysts of the invention are disclosed in US 3,957,689, 4,126,579, 4,226,743, 4,458,023 and Canadian patent 967,136.

The desulfurizing Lewis acid additive/catalyst compositions of the present invention possess the
10 following characteristics: A surface area of 30 to 400 m²/g as determined by BET; a bulk density of 0.4 to 0.9 g/cc; an attrition resistance of 1 to 20 DI (Davison Index) as described as follows: A 7 g sample
15 of catalyst is screened to remove particles in the 0 to 20 micron size range. The particles above 20 microns are then subjected to a 5 hour test in the standard Roller Particle Size Analyzer using a 0.07
20 inch jet and 1 inch I.D. U-Tube as supplied by American Instrument Company, Silver Spring, Md. An air flow of 21 liters per minute is used. The Davison Index is calculated as follows:

$$\text{Davison Index} = \frac{\text{Wt. 0-20 micron material formed during test} \times 100}{\text{Wt. original 20 + micron fraction;}}$$

The hydrocarbon feedstocks that are used typically
25 contain from about 0.1 to 2.5 weight percent, and as much as 4 weight percent sulfur. These feedstocks include gas-oils which have a boiling range of from about 340 to 565°C as well as residual feedstocks and mixtures thereof.

30 The catalytic cracking process is conducted in conventional FCC units wherein reaction temperatures that range of from about 400 to 700°C and regeneration



temperatures from about 500 to 850°C are utilized. The catalyst, i.e. inventory, is circulated through the unit in a continuous reaction/regeneration process during which the sulfur content of cracked gasoline and diesel fuel fraction is reduced by 5 to 100 percent.

Having described the basic aspects of the invention, the following examples are given to illustrate specific embodiments in which Table I shows the conditions of the microactivity testing of the examples of the invention, and Table II shows the feedstock properties of the feedstock used in the testing; and Table III shows the conditions of the circulating riser/regenerator pilot unit. All of the cracked products were analyzed for sulfur using capillary gas chromatography with an atomic emission detector, as described in Albro et al (accepted for publication in Journal of High Resolution Chromatography).

Example 1

An alumina substrate having a surface area of 350 m²/g, a water pore volume of 1 cc/g (SRA alumina as supplied by Grace-Davison) was impregnated with Ni to a level 10% by weight Ni as follows: 48.3 g of Ni(NO₃)₂·6 H₂O was dissolved into 100 ml H₂O. 100 g of dry SRA powder was impregnated with the above Ni(NO₃)₂·6 H₂O solution. The impregnated powder was dried overnight at 110°C, then heat treated at 815°C for 4 hours. The material was then screened to obtain a fraction having a particle size range of 20 to 100 microns. The sized material was then steamed for 4 hours at 815°C with 100% H₂O vapor to obtain a sample having a surface area of 106 m²/g, and an X-ray



diffraction pattern which identified the presence of $\text{Ni}(\text{AlO}_2)_2$.

Example 2

5 A sample which comprised 10 weight percent Cu on alumina was prepared using the general procedure of Example 1, except that the $\text{Ni}(\text{NO}_3)_2 \cdot 6 \text{H}_2\text{O}$ in the impregnating solution was replaced with 38.6 g of Cu $(\text{NO}_3)_2 \cdot 2.5 \text{H}_2\text{O}$. The surface area of the material was 70 m^2/g and the X-ray diffraction pattern identified
10 the presence of $\text{Cu}(\text{AlO}_2)_2$.

Example 3

FCC catalyst samples were prepared by blending 3 weight percent of the samples of Examples 1 and 2 with XP-750, a commercial cracking catalyst obtained from
15 Grace-Davison. The mixture was tested by MAT (ASTM procedure D-3907), as well as 100% XP-750 and the gasoline analyzed for sulfur. Figure 1 shows the sulfur content of the full range gasoline, T90 + 380°F, endpoint = 430°F, versus conversion. Figure 2
20 shows the sulfur content of cut gasoline, T90 = 300°F, endpoint = 340°F versus conversion. As shown in both figures, the sulfur content of the blends with the examples is significantly reduced.

Example 4

25 A sample which contained 10 weight percent Zn was prepared by the procedure of Example 1 except that the $\text{Ni}(\text{NO}_3)_2 \cdot 6 \text{H}_2\text{O}$ in the impregnating solution was replaced with 49.4 g of $\text{Zn}(\text{NO}_3)_2 \cdot 6 \text{H}_2\text{O}$. The surface area of the material was 142 m^2/g and the X-ray pattern
30 identified $\text{Zn}(\text{AlO}_2)_2$.




A blend of 3% by weight with steamed XP-750 was MAT tested as in Example 3. Figure 3 shows the sulfur content of the full range gasoline, and Figure 4 shows the cut gasoline, versus conversion. As seen in these figures, the use of Example 3 significantly reduces the sulfur content of the gasolines.

Example 5

This example shows that the alumina support must be free of SiO_2 . The incipient wetness of Grace-Davison SRS alumina, which contains 6% SiO_2 was determined to be 0.9 mls $\text{H}_2\text{O}/\text{g}$ SRS. 45.49 g of $\text{Zn}(\text{NO}_3)_2 \cdot 6 \text{H}_2\text{O}$ was dissolved into 237 mls H_2O . 263.04 g of SRS alumina (TV = 31.57%) was impregnated with the above solution. The sample was dried overnight at 110°C, then calcined for 2 hours at 800°C. The surface area of the material was 176 m^2/g . A blend containing 5 weight percent of the calcined sample and 95 weight percent steamed (1500°F, 100% H_2O , 4 hours) XP-750 was prepared and tested by MAT, using 100% XP-750 as the base case. Figure 5 shows the sulfur content of the full range gasoline, and Figure 6 shows the sulfur content of the cut gasoline at $T_{90} = 300^\circ\text{F}$, versus conversion. As shown when silica is present in the alumina support, the performance of the invention is degraded.

Example 6

A catalyst composition consisting of zinc oxide/lanthana-neodymia/alumina was prepared by coprecipitation as follows: an acidic solution containing 68.88 g of ZnO and 34.44 g of $(\text{La}/\text{Nd})_2\text{O}_3$ was prepared from their nitrates along with 9.6 g of straight nitric acid, and was diluted with DI-water to



98.4 ml. A dilute sodium aluminate solution containing 68.88 g Al_2O_3 was also readied by diluting 340.99 g of plant-made solution with DI-water to 984 ml. These two solutions were fed into a beaker with
5 400 g of DI-water at 38-43°C, at an equal rate of 40 ml/min., with good agitation. Feeding another feedstream of 16% sodium hydroxide solution directly into the beaker, pH of the resulting slurry of mixed hydrous oxide was maintained at 8.5-8.7 while
10 maintaining the slurry at 38 -43°C through the runoff. After 15 min. aging under this condition, pH of the slurry was raised to 9.0 with dilute sodium hydroxide, and the slurry was dewatered immediately using a Buchner funnel. The filtercake was then washed three
15 times with 1.7 liters of 80°C DI-water. The resulting filtercake was dried overnight in 115°C oven, crushed, and sifted. Particles of 80 - 200 meshes were air calcined for 2 hours at 704°C. The resulting material was 74 m^2/g BET (N_2) surface area, and had the
20 following composition (weight %): 40.72% ZnO , 0.05% Na_2O , 16.24% La_2O_3 , 1.89% Nd_2O_3 , 18.18% total RE_2O_3 , 0.15% SO_4 , and 40.81% Al_2O_3 . Powder X-ray diffraction scan largely exhibited a pattern characteristic of ZnO and the presence of La_2O_3 . This example was then
25 blended sith steamed XP-750 and MAT tested as in the previous examples. Figures 7 and 8 show the full range and cut gasoline sulfur levels for the blend with Example 6 and neat XP-750. As seen, a reduction in the sulfur content of the gasolines is achieved.

30

Example 7

This example shows the utility of this invention in circulating FCC riser/regenerator pilot unit testing. 15 kg of Davison SRA alumina was slurried in



H₂O to nominally 20% solids. The slurry was peptized with 35% HCl using 0.15 mols HCl/mole of Al₂O₃ in the slurry. The slurry was then sand milled, and peptized again with 0.1 moles HCl/mole of Al₂O₃. The slurry was then spray dried. 2 kg of the spray dried alumina was calcined for 2 hours at 538°C to remove moisture and HCl. 100 g of the above material was impregnated with 45.49 g of Zn (NO₃)₂·6 H₂O dissolved in 100 g H₂O. This impregnation was repeated 13 times, then combined, making Example 7. The combined materials were calcined for 3 hrs at 704°C to pre-treat the materials for testing.

A charge of 2300 g of XP-750 was loaded into the Davison Circulating Riser (DCR) and a yield curve at various conversions was run. 255.5 g of pretreated Example 7 was then added to the inventory of the DCR to give a nominal blend of 10% of Example 7 with 90% of XP-750. Another yield curve was run by varying the conversion. The gasolines from the riser testing were analyzed for sulfur in a similar fashion to the previous MAT studies. Figures 9 and 10 show the full range and cut gasolines for neat XP-750 and the 10% blend with Example 7. Again, a clear reduction in the sulfur content of the gasolines is observed with this invention in riser/regenerator pilot unit testing. To further illustrate the effectiveness of this invention Figures 11 - 18 show the concentrations of the individual classes of sulfur species in the gasoline fraction from the pilot unit testing. These classes are, respectively, the C₃ to C₆ mercaptans, thiophene, methylthiophenes, tetrahydrothiophene, C₂ alkyl thiophenes, C₃ alkyl thiophenes, C₄ alkyl thiophenes, and benzothiophene. In all cases, a reduction of the concentrations of the compounds is observed.



Furthermore, an increase in gasoline yield, which would account for the reduction in concentration in a simple way was not observed.

TABLE I

5 Conditions for Microactivity Testing (MAT)

Temperature, °F	980		
nominal catalyst charge, gr.	5		
cat to oil weight ratios	2	3	4
WHSV, hr ⁻¹	60	40	30

This Sheet Has Been Replaced



TABLE II

Feed Properties

	°API	27.8
	Anline Point, °F	187
5	Sulfur, wt.%	0.474
	Total Nitrogen, wt.%	0.07
	Basic Nitrogen, wt.%	0.02
	Conradson Carbon, wt.%	0.16
10	Ni, ppm	0.14
	V, ppm	0.1
	FE, ppm	0.4
	Cu, ppm	<0.1
	Simulated Distillation, vol. % °F	
15	IBP	338
	5	444
	10	486
	20	549
	30	603
	40	640
20	50	694
	60	734
	70	786
	80	840
	90	910
25	95	961
	FBP	1065
	K factor	11.68

This Sheet Has Been Replaced



TABLE III

Testing Conditions of the Davison Circulating Riser
(DCR) FCC Pilot Plant

Adiabatic Operating Mode

5	Riser Outlet Temperature	-	970°F
	Feed Preheat Temperature	-	250 - 750°F
	Regenerator Temperature	-	1300°F
	Reactor Pressure	-	25 psig

Catalyst Deactivation of the XP-750:

10	4 hrs./1500°F/100% 0 psig Steam Fluid Bed Steaming
----	---

This Sheet Has Been Replaced





WHAT IS CLAIMED IS:

- 1 1. A catalytic cracking catalyst composition
which comprises a molecular sieve dispersed in an
3 inorganic oxide matrix as a separate component, and a
Lewis acid supported on alumina.
- 1 2. The composition of claim 1 wherein the
separate component comprises from about 1 to 50 weight
3 percent of a Lewis acid selected from the group
comprising elements and compounds of Ni, Cu, Zn, Ag,
5 Cd, Iu, Su, Hg, Tl, Pb, Bi, B, Al (other than Al_2O_3)
and Ga supported on alumina.
- 1 3. The composition of claim 1 wherein said
component is included as a separate particulate
3 additive.
- 1 4. The composition of claim 1 wherein said
component is included in said matrix.
- 1 5. The composition of claim 1 which contains from
about 1 to 50 weight percent of said component.
- 1 6. The composition of claim 1 which contains from
about 1 to 50 weight percent of said component, from
3 about 5 to 50 weight percent synthetic faujasite, from
about 10 to 60 weight percent clay, and from about 10
5 to 30 weight percent of an inorganic oxide binder
selected from the group consisting of silica, alumina
7 and silica-alumina, hydrogels and sols.
- 1 7. The composition of claim 1 wherein the alumina
has a surface area of 30 to 400 m^2/g .





- 1 8. The composition of claim 1 wherein the alumina
is lanthana stabilized.
- 1 9. The composition of claim 1 wherein said Lewis
acid is Zn.
- 1 10. A composition for reducing the sulfur level
of catalytically cracked hydrocarbons comprising a
3 Lewis acid supported on alumina.
- 1 11. The composition of claim 10 wherein the
alumina is lanthana stabilized.
- 1 12. The composition of claim 8 wherein the
composition has a particle size of about 20 to 140 μm ,
3 a DI of 1 to 20, and a bulk density of 0.4 to 0.9.
- 1 13. A method for the catalytic cracking of
sulfur-containing hydrocarbons which comprises
3 reacting a hydrocarbon feedstock with the catalyst of
claim 1 and removing gasoline fractions having a
5 reduced sulfur content.
- 1 14. The method of claim 13 wherein said feedstock
contains in excess of up to about 4 weight percent S.

