

**REFLOW OVEN AND METHODS OF
TREATING SURFACES OF THE REFLOW OVEN**

BACKGROUND OF THE DISCLOSURE

5

1. Field of the Disclosure

This application relates generally to the surface mount of electronic components onto a printed circuit board by employing a reflow process, and more particularly to a reflow soldering oven that is designed to heat the printed circuit board during the reflow process.

10

2. Discussion of Related Art

In the fabrication of printed circuit boards, electronic components are often surface mounted to a bare board by a process known as “reflow soldering.” In a typical reflow soldering process, a pattern of solder paste is deposited onto the circuit board, and the leads of one or more electronic component are inserted into the deposited solder paste. The circuit board is then passed through an oven where the solder paste is reflowed (i.e., heated to a melt or reflow temperature) in the heated zones and then cooled in a cooling zone to electrically and mechanically connect the leads of the electronic component to the circuit board. The term “circuit board” or “printed circuit board,” as used herein, includes any type of substrate assembly of electronic components, including, for example, wafer substrates.

15

20

As stated above, present day reflow ovens have heating and cooling chambers. To achieve a consistent reflow process profile, flux needs to be extracted and collected away from the heating/cooling chambers. To achieve flux removal, there are two types of reflow ovens – air reflow ovens and inert atmosphere reflow ovens. With the air reflow ovens, flux is extracted by an exhaust system. With the inert atmosphere reflow ovens, a flux management system is used to extract flux from the heating/cooling chambers.

25

Both flux removal systems suffer from well-known shortcomings. With both systems, flux continues to deposit onto the inner walls of the heating/cooling chambers. Over time, the flux collected on the chamber walls create problems during production as excess flux may drip back onto actual production printed circuit boards,

30

thereby potentially contaminating or otherwise compromising the attachment of components onto the printed circuit boards.

With current production requirements, it is desired to continuously operate fabrication equipment, including reflow ovens. Thus, when contemplating scheduled maintenance of the fabrication equipment, it is further desirable to keep down-time as short as possible. During such scheduled maintenance, the removal of flux on chamber walls is generally not addressed. Thus, ongoing flux contamination exposed to the printed circuit boards being produced would remain. Over time, excess flux may also cause premature failures of components of the reflow oven, including blowers designed to facilitate air circulation within the reflow oven chamber.

SUMMARY OF THE DISCLOSURE

An aspect of the disclosure is directed to a reflow oven of the type used to join electronic components to a substrate. In one embodiment, the reflow oven comprises a chamber housing including surfaces that are in contact with heated air mixed with contaminants, including flux, and an intermediate layer selectively applied to the surfaces of the chamber housing. Embodiments of the reflow oven may include fabricating the intermediate layer with a foam material. In one embodiment, the foam material includes foaming polymers, e.g., epoxy, polyurethane, polyester, and silicone. In another embodiment, the intermediate layer includes a non-foam material including non-foaming polymers, e.g., polytetrafluoroethylene and polyimide. The intermediate layer may include a film or foil applied to the surfaces of the chamber housing with an adhesive.

Another aspect of the disclosure is directed to a method of treating surfaces of a reflow oven exposed to contaminants, including flux. In one embodiment, the method comprises selectively applying an intermediate layer on the surfaces of the reflow oven. In some embodiments, the intermediate layer is applied by spraying, or by applying a light pressure when adhering a film or a foil with adhesive. Embodiments of the method may further include operating the reflow oven such that contaminants, including flux, adhere to the intermediate layer, and removing the intermediate layer from the surfaces of the reflow oven. In one embodiment, removing the intermediate layer from the surfaces of the reflow oven includes peeling the intermediate layer from the surfaces. In a particular embodiment, the peeling may be achieved by using a device to peel the intermediate layer from the surfaces. The

device may include a putty knife. The method of removing the intermediate layer from the surfaces of the reflow oven may include applying a chemical to the intermediate layer and wiping off or peeling the intermediate layer from the surfaces.

The method further may comprise, after removing the intermediate layer,
5 applying a new intermediate layer on the surfaces of the reflow oven. Applying the intermediate layer on the surfaces of the reflow oven includes spraying or brushing the intermediate layer.

BRIEF DESCRIPTION OF THE DRAWINGS

10 The accompanying drawings are not intended to be drawn to scale. In the drawings, each identical or nearly identical component that is illustrated in various figures is represented by a like numeral. For purposes of clarity, not every component may be labeled in every drawing. In the drawings:

FIG. 1 is a schematic view of a reflow soldering oven of an embodiment of the
15 disclosure;

FIG. 2 is a perspective view of a reflow oven chamber of the reflow soldering oven;

FIG. 3 is a schematic cross-sectional view of an interior of the reflow oven chamber; and

20 FIG. 4 is an enlarged cross-sectional view of a wall of the reflow oven chamber.

DETAILED DESCRIPTION OF THE DISCLOSURE

For the purposes of illustration only, and not to limit the generality, the present
25 disclosure will now be described in detail with reference to the accompanying figures. This disclosure is not limited in its application to the details of construction and the arrangement of components set forth in the following description or illustrated in the drawings. The principles set forth in this disclosure are capable of other embodiments and of being practiced or carried out in various ways. Also the phraseology and
30 terminology used herein is for the purpose of description and should not be regarded as limiting. The use of “including,” “comprising,” “having,” “containing,” “involving,” and variations thereof herein, is meant to encompass the items listed thereafter and equivalents thereof as well as additional items.

Solder paste is routinely used in the assembly of printed circuit boards, where the solder paste is used to join electronic components to the circuit board. Solder paste includes solder for joint formation and flux for preparing metal surfaces for solder attachment. The solder paste may be deposited onto the metal surfaces (e.g.,
5 electronic pads) provided on the circuit board by using any number of application methods. In one example, a stencil printer may employ a squeegee to force the solder paste through a metallic stencil laid over an exposed circuit board surface. In another example, a dispenser may dispense solder paste material onto specific areas of the circuit board. Leads of an electronic component are aligned with and impressed into
10 the solder deposits to form the assembly. In reflow soldering processes, the solder is then heated to a temperature sufficient to melt the solder and cooled to permanently couple the electronic component, both electrically and mechanically, to the circuit board. The solder typically includes an alloy having a melting temperature lower than that of the metal surfaces to be joined. The temperature also must be sufficiently low
15 so as to not cause damage to the electronic component. In certain embodiments, the solder may be a tin-lead alloy. However, solders employing lead-free materials may also be used.

In the solder, the flux typically includes a vehicle, solvent, activators and other additives. The vehicle is a solid or nonvolatile liquid that coats the surface to be
20 soldered and can include rosin, resins, glycols, polyglycols, polyglycol surfactants, and glycerine. The solvent, which evaporates during the pre-heat and soldering process, serves to dissolve the vehicle activators, and other additives. Examples of typical solvents include alcohols, glycols, glycol esters and/or glycol ethers and water. The activator enhances the removal of metal oxide from the surfaces to be soldered.
25 Common activators include amine hydrochlorides, dicarboxylic acids, such as adipic or succinic acid, and organic acids, such as citric, malic or abietic acid. Other flux additives can include surfactants, viscosity modifiers and additives for providing low slump or good tack characteristics for holding the components in place before reflow.

One embodiment of a reflow soldering apparatus for soldering the circuit
30 board assembly is shown in FIG. 1. Such apparatus are sometimes referred to as reflow ovens or reflow soldering ovens in the art of printed circuit board fabrication and assembly. The reflow soldering oven, generally indicated at 10 in FIG. 1, includes a reflow oven chamber 12 in the form of a thermally insulated tunnel defining a passage for pre-heating, reflowing and then cooling solder on a circuit

board passing therethrough. The reflow oven chamber 12 extends across a plurality of heating zones, including, in one example, three pre-heat zones 14, 16, 18 followed by three soak zones 20, 22, 24, each zone comprising top and bottom heaters 26, 28, respectively. The soak zones 20, 22, 24 are followed by four spike zones 30, 32, 34, 36, for example, which likewise include heaters 26, 28. And finally, three cooling zones 38, 40, 42 follow the spike zones 30, 32, 34, 36.

A circuit board assembly 44, including deposited solder paste and electronic components, is passed (e.g., left-to-right in FIG. 1) through each zone of the thermally insulated reflow oven chamber 12 on a fixed-speed conveyor, indicated by dashed lines at 46 in FIG. 1, thereby enabling controlled and gradual pre-heat, reflow and post-reflow cooling of the circuit board assembly. In the preliminary pre-heat zones 14, 16, 18, the board is heated from ambient temperature up to the flux activation temperature, which may range between about 130 °C and about 150 °C for lead-based solders and higher for lead-free solders.

In the soak zones 20, 22, 24, variations in temperature across the circuit board assembly are stabilized and time is provided for the activated flux to clean the component leads, electronic pads and solder powder before reflow. Additionally, VOCs in the flux are vaporized. The temperature in the soak zones 20, 22, 24 is typically about 140 °C to about 160 °C for lead-based solders and higher for lead-free solders. In certain embodiments, the circuit board assembly may spend about thirty to about forty-five seconds passing through the soak zones 20, 22, 24.

In the spike zones 30, 32, 34, 36, the temperature quickly increases to a temperature above the melting point of the solder to reflow the solder. The melting point for eutectic or near-eutectic tin-lead solder is about 183 °C, with the reflow spike being typically set about 25 °C to about 50 °C above the melting point to overcome a pasty range of molten solder. For lead-based solders, a typical maximum temperature in the spike zones is in the range of about 200 °C to about 220 °C. Temperatures above about 225 °C may cause baking of the flux, damage to the components and/or sacrifice joint integrity. Temperatures below about 200 °C may prevent the joints from fully reflowing. In one embodiment, the circuit board assembly is typically maintained at a temperature within the spike zones 30, 32, 34, 36 above the reflow temperature for about one minute.

Next, in the cooling zones 38, 40, 42, the temperature drops below the reflow temperature, and the circuit board assembly is cooled sufficiently to solidify the joints

and thereby preserve joint integrity before the circuit board assembly leaves the reflow oven chamber 12.

5 A flux extraction/filtration system (not shown) may be provided to remove contaminant materials from the gas generated by the reflow soldering oven 10. In one embodiment, an input gas duct may be connected to or between selected zones to provide fluid communication from the reflow oven chamber 12 to the flux extraction/filtration system. An output gas duct may be connected to or between the selected zones to provide fluid communication from the flux extraction/filtration system back to the reflow oven chamber 12. In operation, a vapor stream is
10 withdrawn from the reflow oven chamber 12 through the input gas duct, through the system, then through the output gas duct and back to the reflow oven chamber. Similar constructions of input gas ducts, systems and output gas ducts may be likewise positioned to withdraw vapor streams from or between other zones of the reflow soldering oven 10.

15 Turning now to FIG. 2, the several zones (e.g., pre-heat zones 14, 16, 18, soak zones 20, 22, 24, and/or spike zones 30, 32, 34, 36) including heaters 26, 28 of the reflow oven include a reflow oven chamber assembly, which is generally indicated at 50. In the shown embodiment, the reflow oven chamber assembly 50 may embody one or more zones. It should be noted that the reflow oven chamber assembly 50 may
20 be configured to have any suitable number of zones needed or required within the reflow soldering oven. Also, it should be noted that FIG. 2 illustrates the upper reflow oven chamber assembly 50. A similar lower reflow oven chamber assembly may be provided in addition to or in lieu of the upper reflow oven chamber assembly to deliver heated air from below the printed circuit board as the board travels through
25 the reflow oven.

Referring to FIGS. 2 and 3, the reflow oven chamber assembly 50 includes a rectangular-shaped chamber housing generally indicated at 52 having a top 54, two relatively longer sides 56, 58, two relatively shorter ends 60, 62, and a bottom, which functions as a diffuser plate 64. In one embodiment, the chamber housing 52 is
30 fabricated from stainless steel. An air blower device 66 is provided on the top 54 of the chamber housing 52 to direct air from an inlet 68 provided in the top 54 of the chamber housing 52 to the reflow oven chamber 12. Air is exhausted out of plenums 70, 72 provided along respective sides 56, 58 of the chamber housing 52 toward an outlet 74, which is also provided in the top 54 of the chamber housing 52. The

chamber housing 52 is configured to enclose and mount the components of the reflow oven chamber assembly 50, and is further configured to be suitably secured within the reflow oven chamber 12 of the reflow soldering oven 10.

5 The diffuser plate 64 distributes air from the reflow oven chamber assembly 50 to the reflow oven chamber 12. In a certain embodiment, the diffuser plate 64 consists of 192 holes in a staggered pattern to provide consistent, uniform airflow to the printed circuit board 44. These holes are stamped from sheet metal material such that they form a converging nozzle that results in a uniform airstream. The arrangement is such that airflow through the reflow oven chamber assembly 50
10 generated by the air blower device 66 with air entering the inlet 68 and exiting the diffuser plate 64. Specifically, air enters the inlet 68 as illustrated by arrows A and exits through the outlet 74 as illustrated by arrows B through the plenums 70, 72.

The surfaces of the chamber housing 52, including the diffuser plate 64 and the plenums 70, 72, may be treated with an intermediate layer of removable material
15 to enable the easy removal of flux and other contaminants that build up over time on these surfaces. Specifically, the intermediate layer is applied by any suitable method during a maintenance procedure to the clean the stainless steel surfaces of the chamber housing 52. As flux builds up over time, the coating of intermediate layer is removed along with the built-up flux and associated contaminants. Thus, the easy
20 removal of the intermediate layer and flux reduces the flux clean-up process significantly and eliminates flux contamination during production. Following the removal of the intermediate layer and flux contaminants, a new intermediate layer is applied or coated on the chamber walls, including the diffuser plate 64, during the maintenance procedure.

25 FIG. 4 illustrates a chamber wall 78 having a surface 80 with an intermediate layer or coating 82 applied to the surface of the chamber wall. As shown, over time, flux 84 builds up on the intermediate layer 82, and requires removal for the reasons described above. One manner in which the intermediate layer 82 is removed from the surface 80 of the chamber wall 78 is by using a device 86 to peel the intermediate
30 layer from the chamber wall. The intermediate layer 82, while adhering to the surface 80 of the chamber wall 78, is sufficiently removable to be easily peeled away from the chamber wall with the device 86.

It should be understood that the provision of an intermediate layer 82 may be applied to reflow ovens having air or inert atmospheres and to reflow ovens having

flux management systems. Thus, use of the term “air” herein is meant to include any gas within the reflow oven chamber, whether inert or not inert.

In certain embodiments, the intermediate layer exhibits the following properties: good adhesion to stainless steel; capable of withstanding a general
5 operating temperature within the reflow oven chamber 12 of 400 °C, with high oven temperatures nearing 600 °C; easily removable from stainless steel; and easily disposable. For example, in one embodiment, the intermediate layer material is a foam material, selected from foaming polymers including epoxy, polyurethane, polyester, and silicone. In another embodiment, the intermediate layer material is a
10 non-foam material, selected from non-foaming polymers including polytetrafluoroethylene (“PTFE”) and polyimide. In yet another example, the intermediate layer may be a non-foam material that can be transformed into a foam material by adding a chemical or foaming agent.

Methods of applying the intermediate layer include, and are not limited to,
15 spraying and brushing the material onto the surfaces requiring coating. For example, any suitable spraying method may be employed, e.g., by a pressurized can. The spraying or brushing may be achieved either manually or automatically.

During a maintenance operation, in addition to other maintenance procedures, surfaces of the chamber housing may be accessible for cleaning. In one embodiment,
20 the intermediate coating enables the surfaces to be peeled away from the surfaces of the chamber housing by hand or by using any suitable instrument, e.g., a device similar to a putty knife. The intermediate layer is designed to attract flux contaminants, while enabling the easy release of contaminant-exposed coating. Other methods may be used to remove the contaminated intermediate layer, such as wiping,
25 brushing, and the like. Still further other methods may be used to remove the contaminated intermediate layer, such as an application of one or more chemicals onto the intermediate layer to break down the intermediate layer.

Having thus described several aspects of at least one embodiment of this disclosure, it is to be appreciated various alterations, modifications, and
30 improvements will readily occur to those skilled in the art. Such alterations, modifications, and improvements are intended to be part of this disclosure, and are intended to be within the spirit and scope of the disclosure. Accordingly, the foregoing description and drawings are by way of example only.

For example, other intermediate layer materials may be selected for application on surfaces of the reflow oven chamber. For example, the intermediate layer material may be a polyphenol, an oil/lubricant, films, liners, performs, foils (e.g., aluminum foil), porous coatings, inorganic “friable” coatings, and removable
5 panels (e.g., glass and stainless steel panels) and/or sheets (plastic or metal) that are adhered to the surfaces of the reflow oven chamber with adhesive, which is removable from the surfaces by peeling, wiping or any other suitable removal method.

What is claimed is:

Claims

1. A reflow oven of the type used to join electronic components to a substrate, the reflow oven comprising:

a chamber housing including an intermediate layer selectively applied to surfaces of the chamber housing in such a way that the intermediate layer is in contact with heated air mixed with contaminants, including flux, the intermediate layer including a film or foil applied to the surfaces of the chamber housing with an adhesive.

2. The reflow oven of claim 1, wherein the adhesive includes one of silicone and other high-temperature materials.

3. A method of treating surfaces of a reflow oven exposed to contaminants, including flux, the method comprising:

selectively applying an intermediate layer on the surfaces of the reflow oven;
operating the reflow oven such that contaminants, including flux, adhere to the intermediate layer; and
removing the intermediate layer from the surfaces of the reflow oven.

4. The method of claim 3, wherein removing the intermediate layer from the surfaces of the reflow oven includes peeling the intermediate layer away from the surfaces of the reflow oven.

5. The method of claim 4, wherein peeling the intermediate layer away from the surfaces of the reflow oven involves using a device.

6. The method of claim 5, wherein the device includes a putty knife.

7. The method of claim 3, wherein removing the intermediate layer from the surfaces of the reflow oven includes applying a chemical to the intermediate layer and wiping off or peeling the intermediate layer away from the surfaces of the reflow oven.

8. The method of claim 3, further comprising, after removing the intermediate layer, applying a new intermediate layer on the surfaces of the reflow oven.

9. The method of claim 3, wherein applying the intermediate layer on the surfaces of the reflow oven includes spraying the intermediate layer.

10. The method of claim 3, wherein applying the intermediate layer on the surfaces of the reflow oven includes applying a light pressure to a film or a foil with adhesive.

11. The method of claim 3, wherein applying the intermediate layer on the surfaces of the reflow oven includes brushing the intermediate layer.

12. The method of claim 3, wherein the intermediate layer includes foaming and non-foaming materials.

13. The method of claim 12, wherein the foaming and non-foaming materials include foaming and non-foaming polymers.

14. The method of claim 13, wherein the polymers include one of epoxy, polyurethane, polyester, silicone, fluoropolymer and polyimide.