



159159



G00002

SPECIFICATION

A PROCESS FOR INHIBITING POLYMERIZATION OF AN AROMATIC VINYL COMPOUND

Technical Field

The present invention relates to a process for inhibiting polymerization of an aromatic vinyl compound or of a process fluid containing it during the stage of producing, purifying, storing or transporting it.

Background Art

Among aromatic vinyl compounds, especially styrene is an industrially very important compound as raw material for preparing polystyrene, synthetic rubber, ABS resin, etc. and has been industrially manufactured in a large amount.

In general, an aromatic vinyl compound is extremely susceptible to polymerization so that it undergoes easily polymerization under an influence of the heat generated during its preparation or purification step, thereby causing lowering in the yield of the monomeric aromatic vinyl compound and further the formation of fouling in the facilities involved to induce trouble in operating the facilities. As the countermeasure taken hitherto, a process wherein certain polymerization inhibitor is added to process fluid containing an aromatic vinyl compound has been proposed and practically carried out. For example, there have been proposed a process employing phenols, nitrosophenols and/or nitrophenols (Japanese Patent Application Laid-Open No. Sho 63-316745), one employing piperidine-1-oxyls (Japanese Patent Application Laid-Open No. Hei 1-165534), one employing nitrophenols together with piperidineoxyls

(Japanese Patent Application Laid-Open No. Hei 6-166636), one employing an alkylsulfonic acid and dialkylhydroxylamine in combination (U.S. Patent No. 4,654,450 specification), one employing phosphoric acid ester and an alkylsulfonic acid in combination (U.S. Patent No. 4,425,223 specification), one adding phenol-, amine- and/or nitroso-related polymerization inhibitors together with a sulfonic acid compound such as dodecylbenzenesulfonic acid or the like and its salt in order to suppress an increase in viscosity in an olefin preparation process (Japanese Patent Application Laid-Open No. Hei 7-166152), and one adding a quinone-, hydroquinone- or nitroso-related polymerization inhibitor, or an amine related polymerization inhibitor such as phenylenediamine together with a sulfonic acid compound such as dodecylbenzenesulfonic acid or the like and its salt for preventing formation of fouling in step treating a vinyl compound (Japanese Patent Application Laid-Open No. Hei 8-34748). Among them, especially 2, 4-dinitrophenol (DNP) and 2, 4-dinitro-6-methylphenol, 2, 4 dinitro-6-sec-butylphenol (DNBP) which are nitrophenol compounds have been often used as the polymerization inhibitors for the aromatic vinyl compound. However, these chemical agents have characteristic property that their inhibitory power toward the polymerization reaction decreases gradually and a strict care is needed in handling them because they belong to toxic substances. Accordingly there has been strongly desired a process which is capable of maintaining polymerization-inhibiting effect by these chemical agents and reducing the amount used of them.


Disclosure of the Invention

So, an object of the present invention is to provide a process for inhibiting polymerization of an aromatic vinyl compound in the stage


of producing, purifying, storing or transporting the aromatic vinyl compound which is capable of efficiently inhibiting the polymerization not only in an initial stage but also over a long term and which is excellent in handling.

As a result of having in detail studied about the characteristic property based on the polymerization reaction of a vinyl compound, the present inventors have found that by employing specific nitrophenol compound and sulfonic acid compound in combination there can be obtained surprisingly high synergistic action that can be unexpected from the effect obtained when each of them was used singly, and have completed the present invention.

That is, the invention involving in claim 1 is a process for inhibiting polymerization of an aromatic vinyl compound which is characterized by adding (A) 2-nitrophenol compound represented by the general formula (I) together with (B) sulfonic acid compound represented by the general formula (II) to said aromatic vinyl compound during the stage of producing, purifying, storing or transporting the aromatic vinyl compound



wherein A, B, C and D represent independently hydrogen, a nitro group, a carboxyl group, a hydroxyl group, a straight or branched chain alkyl group having 1-12 carbon atoms.



wherein R represents a hydroxyl group, a straight or branched chain alkyl group having 1-32 carbon atoms, an alkylphenyl or an alkylnaphthyl group each having at least one straight or branched chain alkyl group having 1-32 carbon atoms.

The invention involving in claim 2 is the process for inhibiting polymerization of an aromatic vinyl compound as claimed in claim 1 wherein 2-nitrophenol compound represented by the general formula (I) is at least one member selected from the group consisting of 2, 4-dinitrophenol, 2, 6-dinitrophenol, 2, 4-dinitro-6-methylphenol, 2, 6-dinitro-4-methylphenol, 2, 4-dinitro-6-*sec*-butylphenol and 2, 6-dinitro-4-*sec*-butylphenol.

The invention involving in claim 3 is the process for inhibiting polymerization of an aromatic vinyl compound as claimed in claim 1 wherein sulfonic acid compound represented by the general formula (II) is at least one member selected from the group consisting of sulfuric acid, toluenesulfonic acid, xylenesulfonic acid, cumenesulfonic acid, dodecylbenzenesulfonic acid, pentadecylbenzenesulfonic acid and dinonylnaphthalenesulfonic acid.

The invention involving in claim 4 is the process for inhibiting polymerization of an aromatic vinyl compound as claimed in any one of claims 1 to 3 wherein (A) 2-nitrophenol compound and (B) sulfonic acid compound are added in combination in a proportion of 5:95-95:5 in weight ratio.

The followings illustrate the present invention in detail.

Examples of an aromatic vinyl compound whose polymerization is inhibited in the present invention include styrene, substituted styrene (e.g., methylstyrene, ethylstyrene), divinylbenzene and the like.

2-Nitrophenol compound of the (A) component which is added for inhibiting polymerization of an aromatic vinyl compound during the stage of producing, purifying, storing or transporting the aromatic vinyl compound is one wherein hydroxyl group and nitro group bonded on benzene ring are located in the ortho-position, as represented by the general formula (I) wherein A, B, C and D represent independently hydrogen, a nitro group, a carboxyl group, a hydroxyl group, a straight or branched chain alkyl group having 1-12 carbon atoms. One or more of these 2-nitrophenol compounds may be used. The preferred examples of the 2-nitrophenol compound are 2, 4-dinitrophenol, 2, 6-dinitrophenol, 2, 4-dinitro-6-methylphenol, 2, 6-dinitro-4-methylphenol, 2, 4-dinitro-6-sec-butylphenol and 2, 6-dinitro-4-sec-butylphenol.

Also, sulfonic acid compound of the (B) component which is added in combination with 2-nitrophenol of the (A) component is one represented by the general formula (II) wherein R represents a hydroxyl group, a straight or branched chain alkyl group having 1-32 carbon atoms, an alkylphenyl or an alkyl-naphthyl group each having at least one straight or branched chain alkyl group having 1-32 carbon atoms. One or more of these sulfonic acid compounds may be used. As sulfonic acid compound, any one may be used so long as it is the so-called free sulfonic acid compound which is not in the form of salt with an alkali metal such as sodium or potassium, with an alkaline earth metal such as calcium, with an amine or is not in the form of complex. As is apparent from Examples and

Comparative Examples described later, even when sulfonic acid compound being in the form of salt was used in combination with 2-nitrophenol compound, there can not be obtained the synergic effect as the present invention intended in the polymerization-inhibiting effect toward the aromatic vinyl compound. Compound which is capable of exerting the significant synergic effect in combination with 2-nitrophenol compound is specified to the free sulfonic acid compound. This can be utterly unexpected from the prior art knowledge. Specific examples of a free sulfonic acid compound include sulfuric acid, toluenesulfonic acid, xylenesulfonic acid, cumenesulfonic acid, dodecylbenzenesulfonic acid, pentadecylbenzenesulfonic acid, dinonylnaphthalenesulfonic acid, and the like. Especially, pentadecylbenzenesulfonic acid and dodecylbenzenesulfonic acid are more preferred from the standpoint of view of the dissolubility in the aromatic vinyl compound, cost and so on.

As stated above, the present invention comprises adding 2-nitrophenol compound in combination with sulfonic acid compound to the stage of producing, purifying, storing or transporting the aromatic vinyl compound. Although the mixture ratio of both the compounds may be optionally selected, 2-nitrophenol compound and sulfonic acid compound are mixed in the range of 95:5–5:95, preferably 80:20–20:80, more preferably 70:30–30:70 ratio by weight to achieve the synergic effect.

The amount of 2-nitrophenol compound and of sulfonic acid compound to be added to said step may be varied depending on the condition of the step to be added, the extent required for the polymerization inhibition and so on, and hence it can not be determined as a rule. However, 2-nitrophenol compound is used in

the range of usually 1-3,000 ppm, preferably 10-2,000 ppm, more preferably 100-1,000 ppm based on the aromatic vinyl compound to be added while sulfonic acid compound is similarly used in the range of 1-3,000 ppm, preferably 10-2,000 ppm, more preferably 100-1,000 ppm. These amounts added of the respective components are values found as the proper range to exert the polymerization-inhibiting effect toward the aromatic vinyl compound. When they are smaller than this range, the effect is not sufficient. Also, when they are greater than this range, the effect is sufficient but in some cases it does not become great relative to the added amount and it is not preferable from the economical aspect.

Although the place in said step to that 2-nitrophenol compound and sulfonic acid compound are added is not particularly restricted in the present invention, they are usually added to the upstream process over the place at which aromatic vinyl compound undergoes polymerization to cause the problem as fouling. For example, styrene is generally manufactured by dehydrogenation reaction of ethyl benzene, and the formed styrene is continuously separated from the unreacted ethyl benzene by distillation, and therefore it is recommendable that 2-nitrophenol compound and sulfonic acid compound are supplied to the distillation column after the dehydrogenation reaction of ethyl benzene has been conducted.

Although the means for addition of 2-nitrophenol compound and sulfonic acid compound to said stage is not particularly restricted in the present invention, such a suitable means may be selected as they may be added to the specific place at one stroke or otherwise they may be separately added to some places in portions. In this case, although 2-nitrophenol compound and sulfonic acid compound may be added separately, it is practically convenient that

both the compounds are added in a proper mixture ratio and in a state dissolved in the same liquid as the process fluid, for example in case of being applied to styrene, in a state dissolved in ethyl benzene or crude styrene.

In the present invention, no limitation shall be lodged on that any other known polymerization inhibitor than 2-nitrophenol compound and sulfonic acid compound is used at the same time in the range not impairing the effect of the present invention.

Brief Explanation of the Drawing

Fig. 1 indicates the relationship between the compounding ratio of dodecylbenzenesulfonic acid (DDBSA) and 2, 4-dinitro-6-sec-butylphenol (DNBP) and the polymerization-inhibiting effect toward styrene monomer (the amount of styrene polymer formed after a lapse of 120 minutes).

The Best Mode For Carrying Out The Invention

The present invention is further illustrated by the following Examples but it is not restricted thereto.

[2-Nitrophenol compounds]

DNBP: 2, 4-dinitro-6-sec-butylphenol

DNBP (2): 2, 6-dinitro-4-sec-butylphenol

DNP: 2, 4-dinitrophenol

DNP (2): 2, 6-dinitrophenol

DNOC: 2, 4 dinitro-6-methylphenol

DNOC (2): 2, 6 dinitro-4-methylphenol

[Sulphonic acid compounds]

S: sulfuric acid (98 %)

MS: methanesulfonic acid

PTS: *p*-toluenesulfonic acid

XSA: xylenesulfonic acid

CSA:	cumenesulfonic acid
DDBSA:	dodecylbenzenesulfonic acid
PDBSA:	pentadecylbenzenesulfonic acid
DNNNA:	dinonylnaphthalenesulfonic acid

[Others]

BHT:	2, 6-di- <i>tert</i> -butyl-4-toluene
TBC:	<i>tert</i> -butylcatechol
NDPA:	N-nitrosodiphenylamine
NPH:	<i>p</i> -nitrosophenol
DEHA:	diethylhydroxylamine
DDBSA-Na:	sodium dodecylbenzenesulfonate
DBSA-Ca:	calcium dodecylbenzenesulfonate
DDBSA-N:	tetradecylamine dodecylbenzenesulfonate

[Polymerization-inhibiting test-1]

100 Grams of styrene monomer was placed in a four-necked flask equipped with a reflux condenser, the prescribed amount of each of the polymerization inhibitors shown in table 1 wherein the compounding ratios of each chemical agent were shown in the same table) was added thereto, and highly purified nitrogen gas was injected therein for 30 minutes to remove the dissolved oxygen. And then, the resultant mixture was kept at 110 °C and a part of the content therein was taken out as sampling every a time given to measure the amount of polymer formed in the liquid. 9 Times volume of methanol based on the sampling liquid was added to precipitate the polymer in a state suspended in the liquid, which was filtrated out to weigh its weight amount and its formed amount percent in the monomer was evaluated. Incidentally, before the beginning of this test, styrene monomer was washed with an alkali to

remove the polymerization inhibitor contained in the monomer, washed with water and dried. The obtained results are shown in table 1.

Table 1

Ex.	No.	Sulfonic acid Compounds	2-Nitrophenol Compounds	Passage of time (min.) and Amount of polymer formed (wt. %)			
		Name of compound And amount added (ppm)	Name of compound And amount added (ppm)	After 30 min.	After 60 min.	After 90 min.	After 120 min.
Example	1	DDBSA: 5	DNBP: 95	0.05	0.10	0.19	0.28
	2	DDBSA: 20	DNBP: 80	0.03	0.09	0.14	0.21
	3	DDBSA: 30	DNBP: 70	0.03	0.09	0.14	0.21
	4	DDBSA: 50	DNBP: 50	0.03	0.09	0.14	0.20
	5	DDBSA: 70	DNBP: 30	0.04	0.11	0.17	0.24
	6	DDBSA: 80	DNBP: 20	0.06	0.14	0.23	0.32
	7	DDBSA: 95	DNBP: 5	0.06	0.14	0.26	0.37
	8	DDBSA: 50	DNBP (2): 50	0.03	0.09	0.15	0.21
	9	DDBSA: 50	DNP: 50	0.03	0.08	0.14	0.20
	10	DDBSA: 50	DNP(2):50	0.03	0.09	0.15	0.21
	11	DDBSA: 50	DNOC: 50	0.03	0.09	0.15	0.21
	12	DDBSA: 50	DNOC (2): 50	0.03	0.09	0.15	0.22
	13	S: 50	DNBP: 50	0.04	0.05	0.07	0.10
	14	MS: 50	DNBP: 50	0.03	0.05	0.08	0.11
	15	PTS: 50	DNBP: 50	0.02	0.06	0.09	0.12
	16	XSA: 50	DNBP: 50	0.03	0.06	0.10	0.15
	17	CSA: 50	DNBP: 50	0.03	0.07	0.11	0.15
	18	PDBSA: 50	DNBP: 50	0.02	0.06	0.13	0.21
	19	DNNNSA: 50	DNBP: 50	0.03	0.06	0.13	0.21
Comparative Example	1	Nothing	Nothing	2.73	5.43	>10	>10
	2	DDBSA: 100	Nothing	1.02	2.03	3.02	4.03
	3	PTS: 100	Nothing	1.20	2.40	3.49	4.58
	4	XSA: 100	Nothing	1.22	2.12	3.51	4.80
	5	CSA: 100	Nothing	1.01	2.21	3.61	5.00
	6	PDBSA: 100	Nothing	1.10	2.31	3.70	5.00
	7	DNNNSA: 100	Nothing	1.09	2.39	3.80	5.24
	8	Nothing	DNBP: 100	0.08	0.22	0.39	0.58
	9	Nothing	DNBP (2): 100	0.08	0.23	0.40	0.60
	10	Nothing	DNP: 100	0.06	0.16	0.28	0.42
	11	Nothing	DNP (2): 100	0.06	0.17	0.30	0.45
	12	Nothing	DNOC: 100	0.08	0.21	0.39	0.61
	13	Nothing	DNOC (2): 100	0.08	0.22	0.40	0.63
	14	DDBSA: 50	BHT: 50	2.78	5.48	>10	>10
	15	DDBSA: 50	TBC: 50	2.69	5.45	>10	>10
	16	DDBSA: 50	NDPA: 50	0.30	6.49	>10	>10

17	DDBSA: 50	NPH: 50	0.28	6.98	>10	>10
18	DDBSA: 50	DEHA: 50	0.20	6.66	>10	>10
19	DDBSA-Na: 50	DNBP: 50	0.15	0.41	0.65	1.23
20	DDBSA-Ca: 50	DNBP: 50	0.16	0.41	0.64	1.20
21	DDBSA-N: 50	DNBP: 50	0.15	0.41	0.63	1.22

It can be understood from the results shown in table 1 that by combining sulfonic acid compound and 2-nitrophenol compound, each of them showing almost no appreciable polymerization-inhibiting effect when used singly, synergic effect may be exerted and polymerization-inhibiting effect is kept over a long period of time. Whereas, as shown by Comparative Examples 14-18, when other polymerization inhibitors (BHT, TBC, NDPA, NPH and DEHA) than 2-nitrophenol compound were used, no synergic effect may be exerted. Also, as shown by Comparative Examples 19-21, even when 2-nitrophenol compound was combined with salts of sulfonic acid, no synergic effect may be exerted, too. Thus, only by combination of sulfonic acid compound and 2-nitrophenol compound involved in the present invention, a high polymerization-inhibiting effect may be exerted.

It can be understood that the polymerization-inhibiting effect caused by combination of sulfonic acid compound and 2-nitrophenol compound in the present invention is not dependent on the kind of substituent R in the sulfonic acid compound but dependent on the content of sulfonic acid radical in the sulfonic acid compound (number of sulfonic acid radical/molecular weight of sulfonic acid compound) and that the higher the content of sulfonic acid radical in sulfonic acid compound, the greater the polymerization-inhibiting effect.

The relationship between the compounding ratios of DDBSA and DNBP (total amount added: 100 ppm) and the amount of polymer

formed after a lapse of 120 minutes is indicated in Fig. 1. As is apparent from Fig. 1, it is extremely surprising that merely by combining a small amount of 2-nitrophenol compound with sulfonic acid compound which shows almost no polymerization-inhibiting effect when used singly, excellent polymerization-inhibiting effect is realized than when 2-nitrophenol was used singly.

[Polymerization-inhibiting test-2]

Polymerization-inhibiting test was carried out in a similar manner as in polymerization-inhibiting test-1 except that methylstyrene was used in place of styrene monomer. The obtained results are in table 2.

Table 2

Ex.	No.	Sulfonic acids	2-Nitrophenols	Passage of time (min.) and Amount of polymer formed (wt. %)			
		Name of compound And amount added (ppm)	Name of compound And amount added (ppm)	After 30 min.	After 60 min.	After 90 min.	After 120 min.
Example	20	DDBSA: 95	DNBP: 5	0.08	0.19	0.34	0.52
	21	DDBSA: 50	DNBP: 50	0.07	0.17	0.29	0.42
	22	DDBSA: 5	DNBP: 95	0.09	0.21	0.35	0.50
	23	DDBSA: 95	DNBP (2): 5	0.08	0.20	0.35	0.51
	24	DDBSA: 50	DNBP (2): 5	0.06	0.16	0.29	0.41
	25	DDBSA: 5	DNBP (2): 5	0.09	0.22	0.34	0.52
Comparative Example	22	Nothing	Nothing	3.03	6.15	> 10	> 10
	23	DDBSA: 100	Nothing	2.22	5.10	> 10	> 10
	24	Nothing	DNBP: 100	0.13	0.30	0.52	0.80
	25	Nothing	DNBP (2): 100	0.12	0.31	0.50	0.83

It can be understood from the results shown in table 2 that by addition of 2-nitrophenol compound in combination with sulfonic

acid compound synergic effect is recognized and the polymerization inhibition against methylstyrene is kept over a long period of time.

[Polymerization-inhibiting test-3]

Polymerization-inhibiting test was carried out in a similar manner as in polymerization-inhibiting test-1 except that divinylbenzene was used in place of styrene monomer. The obtained results are in table 3.

Table 3

Ex.	No.	Sulfonic acids	2-Nitrophenols	Passage of time (min.) and Amount of polymer formed (wt. %)			
		Name of compound And amount added (ppm)	Name of compound And amount added (ppm)	After 30 min.	After 60 min.	After 90 min.	After 120 min.
Example	26	DDBSA: 95	DNBP: 5	0.13	0.29	0.54	0.84
	27	DDBSA: 50	DNBP: 50	0.12	0.29	0.48	0.68
	28	DDBSA: 5	DNBP: 95	0.13	0.31	0.53	0.78
	29	DDBSA: 95	DNBP (2): 5	0.11	0.29	0.55	0.88
	30	DDBSA: 50	DNBP (2): 50	0.10	0.27	0.49	0.64
	31	DDBSA: 5	DNBP (2): 95	0.13	0.32	0.53	0.75
Comparative Example	26	Nothing	Nothing	3.45	6.30	> 10	> 10
	27	DDBSA: 100	Nothing	2.01	4.38	> 10	> 10
	28	Nothing	DNBP: 100	0.2	0.44	0.7	1.05
	29	Nothing	DNBP (2): 100	0.19	0.43	0.75	1.03

[Polymerization-inhibiting test-4]

To 30 g the bottom liquid (containing above 90 % by weight of styrene) in the distillation column of styrene production apparatus were added sulfonic acid compound and 2-nitrophenol compound in the present invention or otherwise were added other polymerization inhibitor and a salt of sulfonic acid as comparative examples and in

either case the resultant mixture was allowed to settle in a 100 ml pressure glass autoclave at 100 °C for 2 hours. The formed insoluble matters were filtered out, washed with acetone and dried at 105 °C for 2 hours to measure its weight amount. Also, the state of the insoluble matters adhered to the inner walls of the autoclave was observed. The state of adhesion was visually evaluated according to the following criteria:

A: no adhesion is recognized.

B: slight adhesion is recognized.

C: adhesion is recognized.

D: adhesion of a large amount is recognized.

The obtained results are shown in table 4.

Table 4

		Sulfonic acid Compound	2-Nitrophenols And Polymerization Inhibitors	Effect	
		Compound and Amount added (ppm)	Compound and Amount added (ppm)	Amount of Insoluble Matters formed (mg/kg)	Adhesion State of Insoluble Matters
Example	26	DDBSA: 100	DNBP: 100	5	A
	27	DDBSA: 200	DNBP: 100	2	A
	28	DDBSA: 500	DNBP: 100	1	A
	29	DDBSA: 1000	DNBP: 100	0	A
	30	DDBSA: 100	DNBP (2): 100	6	A
	31	DDBSA: 200	DNBP (2): 100	2	A
	32	DDBSA: 500	DNBP (2): 100	1	A
	33	DDBSA: 1000	DNBP (2): 100	0	A
Comparative Example	30	DDBSA: 100	Nothing	135	D
	31	DDBSA: 1000	Nothing	131	C
	32	Nothing	DNBP: 100	140	C
	33	Nothing	DNBP (2): 100	143	C
	34	DDBSA-Na: 1000	Nothing	123	B
	35	DDBSA-Na: 100	DNBP: 100	41	A
	36	DDBSA-Na: 100	DNBP (2): 100	40	A
	37	DDBSA-Ca: 1000	Nothing	134	D
	38	DDBSA-Ca: 1000	DNBP: 100	42	A

39	DDBSA-Ca: 100	DNBP (2): 100	41	A
40	DDBSA-N: 1000	Nothing	118	B
41	DDBSA-N: 1000	DNBP: 100	41	A
42	DDBSA-N: 100	DNBP (2): 100	41	A
43	DDBSA: 1000	NPH: 100	40	A
44	Nothing	NPH: 100	132	D
45	DDBSA-Na: 100	NPH: 100	44	A
46	DDBSA-Ca: 1000	NPH: 100	90	A
47	DDBSA-N: 1000	NPH: 100	35	A


As is apparent from table 4, with respect to the polymerization-inhibiting effect caused by combination of sulfonic acid compound and 2-nitrophenol compound involved in the present invention, the effect is exerted in the case where sulfonic acid compound is in the free form of sulfonic acid while the effect of the present invention cannot be achieved in the case where sulfonic acid compound is in the form of a metal salt such as sodium, calcium or the like salt and of an amine salt.

Industrial applicability


2-Nitrophenol compound is added in combination with free sulfonic acid compound to the stage of producing, purifying, storing or transporting an aromatic vinyl compound, whereby polymerization of an aromatic vinyl compound or of a process fluid containing it may be efficiently inhibited and the effect may be kept for a long period of time thereby minimizing the amount generated of fouling in the facilities involved and attributing greatly to smooth and long-term operation without causing any trouble in operating the facilities.

CLAIMS

1. A process for inhibiting polymerization of an aromatic vinyl compound which is characterized by adding (A) 2-nitrophenol compound represented by the general formula (I) together with (B) sulfonic acid compound represented by the general formula (II) to the aromatic vinyl compound in the stage of producing, purifying, storing or transporting the aromatic vinyl compound



wherein A, B, C and D represent independently hydrogen, a nitro group, a carboxyl group, a hydroxyl group, a straight or branched chain alkyl group having 1-12 carbon atoms.



wherein R represents a hydroxyl group, a straight or branched chain alkyl group having 1-32 carbon atoms, an alkyl phenyl or an alkyl naphthyl group each having at least one straight or branched chain alkyl group having 1-32 carbon atoms.

2. The process for inhibiting polymerization of an aromatic vinyl compound as claimed in claim 1 wherein 2-nitrophenol

compound represented by the general formula (I) is at least one member selected from the group consisting of 2, 4-dinitrophenol, 2, 6-dinitrophenol, 2, 4-dinitro-6-methylphenol, 2, 6-dinitro-4-methylphenol, 2, 4-dinitro-6-*sec*-butylphenol and 2, 6-dinitro-4-*sec*-butylphenol.

3. The process for inhibiting polymerization of an aromatic vinyl compound as claimed in claim 1 wherein sulfonic acid compound represented by the general formula (II) is at least one member selected from the group consisting of sulfuric acid, toluenesulfonic acid, xylenesulfonic acid, cumenesulfonic acid, dodecylbenzenesulfonic acid, pentadecylbenzenesulfonic acid and dinonylnaphthalenesulfonic acid.

4. The process for inhibiting polymerization of an aromatic vinyl compound as claimed in any one of claims 1 to 3 wherein (A) 2-nitrophenol compound and (B) sulfonic acid compound are added in combination in a proportion of 5: 95-95: 5 in weight ratio.