

NOVEL THIOURACIL DERIVATIVES AND METAL SURFACE-TREATING AGENT COMPRISING THEREOF

This invention relates to thiouracil derivatives each having a radical polymerizable unsaturated bond. These thiouracil derivatives can each be utilized, as a component for an adhesive for noble metals, in many fields such as medical treatment, electronic materials, precision instruments and jewelry wherein resins are bonded to metals, but are particularly useful in the dental field.

The invention further relates to a metal surface-treating agent containing such a thiouracil derivative, useful for exerting excellent adhesiveness to metals.

As adhesives for base metals such as iron, nickel, chromium, cobalt, tin, aluminum, copper and titanium, adhesives each containing an acrylic or methacrylic polymerizable monomer having a functional group such as a phthalic anhydride group, a phthalic acid group, a malonic acid group or a phosphoric acid group are proposed and put to practical use. However, an adhesive having sufficient adhesive strength to noble metals such as gold, platinum, palladium and silver has not been developed. Therefore, as to adhesion to noble metals, it has been common to plate the surface of such a noble metal with tin or oxidize the surface, in advance. Since these methods are complicated in operations and sufficient adhesive strength cannot be obtained thereby, the development of an adhesive for noble metals or a surface-treating agent for noble metals has been desired.

In order to meet the above requirement, adhesive polymerizable monomers each having a functional group such as a thiophosphoric acid group (Japanese Laid-open Patent Publication No. 138,282/1989), a

thiophosphoryl chloride group (Japanese Laid-open Patent Publication No. 117,595/1993) or a triazinedithione derivative (Japanese Laid-open Patent Publication No. 83,254/1989) has been proposed in recent years. In

5 surface-treating agents each containing such an adhesive polymerizable monomer, adhesion to a noble metal is made possible by previously applying such a surface-treating agent onto the surface of the noble metal, and then curing the polymerizable resin.

10 However, in the case of the adhesion of noble metals using the above surface-treating agents, there are problems that adhesive strength or water resistance, or durability is not yet sufficient, and moreover, since the adhesive polymerizable monomers are unstable, the
15 storage stability of the surface-treating agents is poor, the adhesive strength is influenced by the application amount, and so on. Further, the effect of the above surface-treating agents is exerted only in the adhesion of noble metals, and not exerted in the adhe-
20 sion of base metals. Thus, in this invention, it was aimed to provide a metal surface-treating agent which has sufficient initial adhesive strength to both base metals and noble metals, and is good in adhesion durability, water resistance and storage stability.

25 The present inventors had intensely studied for solving the above problems, and as a result, they found that thiouracil derivatives each having a radical polymerizable unsaturated bond and a surface-treating agent containing such a thiouracil derivative as a main
30 component have effect on storage stability, adhesive strength to noble metals, water resistance, durability and so on, they further found that a surface-treating agent containing a thiouracil derivative having a radical polymerizable unsaturated bond and an acidic
35 group-containing (meth)acrylate monomer has sufficient adhesive strength to both base metals and noble metals,

and is excellent in storage stability, water resistance and durability, and they completed the invention.


Thus, the invention is a thiouracil derivative containing at least one radical polymerizable unsaturated bond in the molecule, a metal surface-treating agent containing the thiouracil derivative, a metal surface-treating agent containing a thiouracil derivative containing at least one radical polymerizable unsaturated bond in the molecule and an organic solvent, and a metal surface-treating agent containing the thiouracil derivative, an acidic group-containing (meth)acrylate monomer and an organic solvent.

The thiouracil derivative is not particularly limited so long as it contains a thiouracil group and at least one radical polymerizable unsaturated bond in the molecule, but it is preferably an unsaturated thiouracil derivative which

has at at least one terminus thereof an organic group (I) having a radical polymerizable unsaturated bond, and

has at the other terminus the following thiouracil residue (II)

25



30

wherein

R^1 and R^2 each are a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom, and R^3 is a hydrogen atom, an alkyl group or a phenyl group,

35

and

wherein


the organic group (I) and the thiouracil residue (II) are separated by a bivalent spacer residue containing at least 2 carbon atoms.

5 In the above formula (II), R^1 and R^2 each represent a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom. As preferred alkyl groups, there can be exemplified alkyl groups having 1 to 4 carbon atoms such as a methyl group, an
10 ethyl group, a propyl group and a butyl group.

Further in the above formula (II), R^3 represents a hydrogen atom, an alkyl group or a phenyl group. As the alkyl group, there can be exemplified the same alkyl groups as mentioned in the above R^1 and R^2 .


15 A further preferred unsaturated thiouracil derivative is the above unsaturated thiouracil derivative wherein the organic group (I) having a radical polymerizable unsaturated bond is represented by the following formula (I-1)

20



wherein R^5 is a hydrogen atom or a methyl
25 group, and

Z is a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or a










30 the spacer residue is a bivalent organic group having 2 to 20 carbon atoms which may contain, in the chain skeleton, oxygen, or oxygen and silicon, besides carbon.

The spacer residue is not limited at all so
35 long as it is a bivalent organic group having 2 to 20 carbon atoms which may contain, in the chain skeleton,

oxygen, or oxygen and silicon, besides carbon. Therefore, the spacer residue includes not only a bivalent straight-chain or branched chain hydrocarbon group, but an organic group having an ether linkage, an ester linkage, a siloxane linkage or a phenylene group in the principal chain.

As specific examples of the spacer residue, there can be mentioned







5

etc.


Preferred among the above spacer residues are bivalent saturated hydrocarbon groups each having 2 to 12 carbon atoms, and a group represented by the following formula (III-2), (III-3) or (III-4)



15



20



wherein n is an integer of 1 to 5, o and p each are

25

an integer of 1 to 10, q is an integer of 1 to 5, and r and s each are an integer of 1 to 5.



When the spacer residue is a bivalent saturated hydrocarbon group having 2 to 12 carbon atoms, the saturated hydrocarbon group may have a branch. As specific examples of the bivalent saturated hydrocarbon group, there can be mentioned an ethylene group, a propylene group, an isopropylene group, a hexylene group, a decylene group, a dodecylene group, etc., and among them alkylene groups having 5 to 10 carbon atoms are preferred in view of adhesive strength and the easiness

of synthesis. In the group represented by the above general formula (III-2), n is an integer of 1 to 5. In the group represented by the above general formula (III-3), o and p each are an integer of 1 to 10, and it is preferred that they each are an integer of 3 to 6 in view of adhesive strength and the easiness of synthesis. In the group represented by the above general formula (III-3), q is an integer of 1 to 5, and it is preferred that it is an integer of 1 to 3 in view of adhesive strength and the easiness of synthesis. Further, in the group represented by the above general formula (III-4), r and s each are an integer of 1 to 5, and it is preferred that they each are an integer of 1 to 3 in view of adhesive strength and the easiness of synthesis.




In the above formula (I-1), Z represents a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or a $-\text{C}_6\text{H}_4-\text{CH}_2\text{O}-$ group. Among them, a $-\text{COO}-$ group is preferred in view of polymerizability, the easiness of handling, etc.

Among the above thiouracil derivatives, those wherein in the formula (II), R^1 and R^2 each are a hydrogen atom or an alkyl group having 1 to 4 carbon atoms (provided that at least one of R^1 and R^2 is a hydrogen atom), and R^3 is a hydrogen atom, an alkyl group having 1 to 4 carbon atoms or a phenyl group, the spacer residue is an alkylene group having 5 to 10 carbon atoms or a group represented by the above general formula (III-2), (III-3) or (III-4) (provided that in these formulae, n is an integer of 1 to 5, o and p each are an integer of 3 to 6, q is an integer of 1 to 3, and r and s each are an integer of 1 to 3), R^5 is a hydrogen atom or a methyl group, and Z is a $-\text{COO}-$ group are particularly preferred in view of adhesive strength, the easiness of synthesis and the easiness of handling.

Thus, preferred unsaturated thiouracil derivatives in the invention can also be represented by the following general formula (1) or (2)








{wherein R^1 and R^2 each are a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom, R^3 is a hydrogen atom, an alkyl group or a phenyl group, and R^4 is a bivalent saturated hydrocarbon group having 2 to 12 carbon atoms, or any group selected from the following formulae (3), (4) and (5)}















(wherein n is an integer of 1 to 5, o and p each are an







integer of 1 to 10, q is an integer of 1 to 5, and r and s each are an integer of 1 to 5), Z is a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or a $-\text{C}_6\text{H}_4-\text{CH}_2\text{O}-$ group, and R^5 is a hydrogen atom or a methyl group.}






- 5 Specific examples of the thiouracil derivative of the invention are as follows.






















































A process for producing a thiouracil derivative represented by the above general formula (1) or (2) is not particularly limited, and any process therefor can be adopted. A specific example of an industrially preferred process therefor is as follows.


First, description is made on a process for producing a thiouracil derivative represented by the above general formula (1). Namely, a thiouracil derivative having a polymerizable unsaturated bond of the above general formula (1) can be obtained by condensation reacting a thiourea derivative represented by the following general formula (6)




(wherein, R^1 and R^2 each are a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom) with a malonic acid derivative represented by the following general formula (7)




(wherein, R^3 is a hydrogen atom, an alkyl group or a phenyl group) to give a carbethoxythiouracil derivative represented by the following general formula (8)






5
 (wherein, R^1 , R^2 and R^3 are as defined in the above
 general formulae (6) and (7)), subjecting the derivative
 10 (8) to deesterification reaction to give a
 carboxythiouracil derivative represented by the follow-
 ing general formula (9)



15
 20 (wherein, R^1 , R^2 and R^3 are as defined in the above
 general formulae (6) and (7)), and reacting the deriva-
 tive (9) with an alcohol having a polymerizable unsatu-
 rated bond represented by the following general formula
 25 (10)



30 {wherein, R^4 is a bivalent saturated hydrocarbon group
 having 2 to 12 carbon atoms, or any group selected from
 the following formulae (3), (4) and (5)



(wherein n is an integer of 1 to 5, o and p each are an integer of 1 to 10, q is an integer of 1 to 5, and r and s each are an integer of 1 to 5), Z is a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or a $-\text{C}_6\text{H}_4-\text{CH}_2\text{O}-$ group, and R^5 is a hydrogen atom or a methyl group.}

As the thiourea derivative represented by the above general formula (6), known ones can be used without limitation. For example, thiourea, methylthiourea, ethylthiourea, propylthiourea, butylthiourea, etc. can preferably be used.

The malonic acid derivative represented by the general formula (7) can be synthesized by reacting diethyl malonate with an ortho acid triethyl.

As the ortho acid triethyl, there can be exemplified triethyl orthoformate, triethyl orthoacetate, triethyl orthopropionate, triethyl orthobenzoate, etc.

More specifically, a malonic acid derivative represented by the general formula (7) can be obtained by putting 1 mol of diethyl malonate and 2 to 3 mols of sodium ethoxide in the presence of a solvent, and slowly adding dropwise 1 mol of an ortho acid triethyl to react them.

As to an alcohol having a polymerizable unsaturated bond represented by the above general formula (10), when Z is -COO- group, the alcohol can be obtained by esterification reaction between (meth)acrylic acid and a glycol, by esterification reaction between (meth)acryloyl chloride and a glycol, or the like. When Z is $\text{-CH}_2\text{O-}$ group, such an alcohol can be obtained by reaction between allyl chloride and a glycol, or the like. When Z is a $\text{-C}_6\text{H}_4\text{-CH}_2\text{O-}$ group, such an alcohol can be obtained by reaction between 4-vinylbenzyl chloride and a glycol, or the like.

As the glycol, there can be exemplified ethylene glycol, propylene glycol, pentamethylene glycol, hexamethylene glycol, octamethylene glycol, decamethylene glycol, dodecamethylene glycol, neopentyl glycol, 1,2-propanediol, 1,2-butanediol, 1,5-hexanediol, P-xylene glycol, diethylene glycol, 1,3-bis(3-hydroxypropyl)-1,1,3,3-tetramethyldisiloxane, 1,3-bis(4-hydroxybutyl)-1,1,3,3-tetramethyldisiloxane, etc.

More specifically, when Z in the general formula (10) is a -COO- group, a corresponding alcohol (10) can be obtained by feeding 1 mol of (meth)acrylic acid, 1 to 4 mols of a glycol and 0.01 to 0.1 mol of an acid catalyst, and reacting them. As the acid catalyst, p-toluenesulfonic acid, benzenesulfonic acid, etc. can preferably be used.

The alcohol (10) can also be obtained by feeding 1 to 4 mols of a glycol, and 1 mol of a tertiary amine or molecular sieve 3A as a dehydrohalogenating agent in the presence of a solvent, and slowly adding dropwise 1 mol of (meth)acryloyl chloride to cause esterification reaction. As the tertiary amine, pyridine, triethylamine, etc. can preferably be used.

When Z in the general formula (10) is a $\text{-CH}_2\text{O-}$ group, a corresponding alcohol (10) can be obtained by feeding 1 to 4 mols of a glycol and 1 to 1.2 mols of a

basic catalyst in the presence of a solvent, and slowly adding dropwise 1 mol of allyl chloride to cause reaction. As the basic catalyst, sodium hydride, etc. can preferably be used.

5 When Z in the general formula (10) is a $-\text{C}_6\text{H}_4-\text{CH}_2\text{O}-$ group, a corresponding alcohol (10) can be obtained by feeding 1 to 2 mols of a glycol and 1 to 1.2 mols of a basic catalyst in the presence of a solvent, and slowly adding dropwise 1 mol of 4-vinylbenzyl chloride to cause reaction. As the basic catalyst, sodium
10 hydride, etc. can preferably be used.

In these cases, both of a monosubstitution product (10) and a disubstitution product are obtained as the products. The monosubstitution product (10) can
15 be separated and purified by distillation or column chromatography.

In the condensation reaction between the thiourea derivative of the general formula (6) and the malonic acid derivative of the general formula (7), the
20 reaction molar ratio of the malonic acid derivative of the general formula (7) to the thiourea derivative of the general formula (6) is preferably 0.5 to 1.5.

As a reaction catalyst used at the time, a known one is usable, and sodium ethoxide, etc. can be
25 exemplified, and its addition amount is preferably 0.5 to 1.5 times the molar amount of the thiourea derivative of the general formula (6).

As a solvent used in the reaction, ethanol, etc. can be mentioned. The temperature of the reaction
30 can be selected from the range of 40 to 80°C, preferably from the range of 60 to 80°C. The reaction time is not particularly limited, and can generally be selected from the range of the order of 1 to 10 hours, but can be determined in accordance with the reaction temperature.

35 After the reaction, the salt deposited is dissolved in water, and an acid is added to make the

solution acidic, whereby a carbethoxythiouracil derivative represented by the general formula (8) can be obtained.

In this connection, when, in the thiourea of the general formula (6), one of R^1 and R^2 is an alkyl group, the carbethoxythiouracil derivative of the general formula (8) is obtained as a mixture of isomers based on the substitution position on the N atoms of the alkyl group. These isomers can be separated and purified by column chromatography.

In the deesterification reaction of the carbethoxythiouracil derivative of the general formula (8) obtained by the reaction between the thiourea derivative of the general formula (6) and malonic acid derivative of the general formula (7), as the deesterifying agent to be used, a known one can be used, but a dimethyl sulfoxide solution of potassium tertiary butoxide is preferably used. The addition amount of the deesterifying agent is preferably in the range of 6 to 20 times the molar amount of the carbethoxythiouracil derivative, and more preferably in the range of 12 to 16 times the molar amount thereof.

The temperature of the reaction can be selected from the range of room temperature to 80°C , but preferably from the range of room temperature to 40°C . The reaction time is not particularly limited, and can generally be selected from the range of the order of 1 to 24 hours, but can be determined in accordance with the reaction temperature.

After the reaction, water is added to the reaction mixture, and further an acid is added to make the solution acidic, whereby a carboxythiouracil derivative represented by the general formula (9) can be obtained.

In the reaction between the carboxythiouracil derivative of the general formula (9) and the alcohol

having a polymerizable unsaturated bond of the general formula (10), the reaction molar ratio of the alcohol having a polymerizable unsaturated bond of the general formula (10) to the carboxythiouracil derivative of the general formula (9) can be in the range of 1 to 5, but preferably in the range of 1 to 3.

As an esterifying catalyst for the esterification reaction to be used, there can be mentioned p-toluenesulfonic acid, benzenesulfonic acid, N,N'-dicyclohexylcarbodiimide, etc. The addition amount of the reaction catalyst is preferably in the range of 0.1 to 1 times the molar amount of the carboxythiouracil derivative.

As a solvent to be used in the reaction, there can be mentioned tetrahydrofuran, acetone, toluene, etc. Further, it is preferred to add a small amount of a polymerization inhibitor such as hydroquinone, hydroquinone monomethyl ether or butylhydroxytoluene.


The temperature of the reaction can be selected from the range of room temperature to 80°C, but preferably from the range of room temperature to 70°C. The reaction time is not particularly limited, and can generally be selected from the range of the order of 1 to 50 hours, but can be determined in accordance with the reaction temperature and in such a range that the polymerization does not take place.

After the reaction, the matter deposited is filtered out, the solvent is distilled off from the filtrate under reduced pressure, and the resultant concentrate is passed through a silica gel column using an inert solvent such as ethyl acetate as a developing solvent to carry out separation and purification, whereby a product having high purity can be obtained.

Next, description is made on a process for producing a thiouracil derivative represented by the general formula (2).


Namely, a thiouracil derivative having a polymerizable unsaturated bond of the general formula (2) can be obtained by condensation reacting a thiourea derivative represented by the general formula (6)

5




10 (wherein, R^1 and R^2 are as defined above) with a succinic acid derivative represented by the general formula (11)

15




20 (wherein, R^3 is a hydrogen atom, an alkyl group or a phenyl group) to give a carbethoxythiouracil derivative represented by the general formula (12)

25




30 (wherein, R^1 , R^2 and R^3 are as defined in the above general formulae), subjecting the carbethoxythiouracil derivative (12) to deesterification reaction to give a carboxythiouracil derivative represented by the general formula (13)

5




(wherein, R^1 , R^2 and R^3 are as defined in the above
 10 general formulae), and then reacting the carboxythio-
 uracil derivative (13) with an alcohol represented by
 the following general formula (10)




{wherein, R^4 is a bivalent saturated hydrocarbon group
 having 2 to 12 carbon atoms, or any group selected from
 the following general formula (3), (4) and (5)


20



25



30



(wherein, n is an integer of 1 to 5, o and p each are an
 35 integer of 1 to 10, q is an integer of 1 to 5, and r and
 s each are an integer of 1 to 5), Z is a $-\text{COO}-$ group, a

-CH₂O- group or a -C₆H₄-CH₂O- group, and R⁵ is a hydrogen atom or a methyl group}.

As the thiourea derivative represented by the above general formula (6), known ones can be used without limitation, as in the case of the preparation of the above general formula (1).

As the succinic acid derivative represented by the above general formula (11), known ones can be used without limitation. For example, there can preferably be used diethyl 2-oxosuccinate, diethyl 2-methyl-2'-oxosuccinate, diethyl 2-ethyl-2'-oxosuccinate, diethyl 2-butyl-2'-oxosuccinate, etc.

As the alcohol having a polymerizable unsaturated bond represented by the above general formula (10), there can be used the same ones as in the case of the preparation of the above general formula (1).

In the condensation reaction between the thiourea derivative of the above general formula (6) and the succinic acid derivative of the above general formula (11), the reaction molar ratio of the succinic acid derivative of the general formula (11) to the thiourea derivative of the general formula (6) is preferably 0.5 to 1.5.

As a reaction catalyst to be used at the time, known ones can be used, and sodium ethoxide, etc. are exemplified, and its addition amount is preferably 0.5 to 1.0 times the molar amount of the thiourea derivative of the general formula (6).

As a solvent used in the reaction, ethanol, etc. can be mentioned. The temperature of the reaction can be selected from the range of 40 to 80°C, preferably from the range of 60 to 80°C. The reaction time is not particularly limited, and generally can be selected from the range of the order of 1 to 10 hours, but can be determined in accordance with the reaction temperature.

After the reaction, the salt deposited is

dissolved in water, and an acid is added to make the solution acidic, whereby a carbethoxythiouracil derivative represented by the general formula (12) can be obtained.

5 In this connection, when, in the thiourea of the general formula (6), one of R^1 and R^2 is an alkyl group, the carbethoxythiouracil derivative of the general formula (12) is obtained as a mixture of isomers based on the substitution position on the N atoms of the
10 alkyl group. These isomers can be separated and purified by column chromatography.

 The deesterification reaction of the carbethoxythiouracil derivative of the general formula (12) obtained by the reaction between the thiourea
15 derivative of the general formula (6) and the succinic acid derivative of the general formula (11) can be carried out in the same manner as in the case of the carbethoxythiouracil derivative represented by the general formula (8).

20 The reaction between the carboxythiouracil derivative represented by the general formula (13) and the alcohol having a polymerizable unsaturated bond of the general formula (10) can be carried out in the same manner as in the reaction between the carboxythiouracil
25 derivative of the general formula (9) and the alcohol having a polymerizable unsaturated bond of the general formula (10).

 A thiouracil derivative having a polymerizable unsaturated bond represented by the general formula (1) or (2) can preferably be used as a component of an
30 adhesive which bonds a noble metal, for example a dental noble metal alloy to a resin, and in such an occasion, it is preferred to use the thiouracil derivative as a solution in an organic solvent. As organic solvents
35 used preferably therefor, general organic solvents or polymerizable monomers can be used without any limita-

tion so long as they can dissolve the thiouracil derivative. However, when the organic solvents are nonvolatile, it gets difficult to exert the effects of the invention without heightening the concentration of the thiouracil derivative, and therefore, it is preferred to use organic solvents having volatility.

In the metal surface-treating agent of the invention, the concentration of the thiouracil derivative is not particularly limited, but in view of adhesive strength and the prevention of excess use, it is preferred that the concentration is in the range of 0.001 to 20 % by weight. The further preferred concentration range of the thiouracil derivative is 0.005 to 10 % by weight.


As specific examples of the organic solvents usable preferably, there can be mentioned alcohols such as methanol, ethanol, isopropyl alcohol and butanol; ketones such as acetone and methyl ethyl ketone; ethers such as ethyl ether, 1,4-dioxane and tetrahydrofuran; esters such as ethyl acetate and ethyl formate; aromatic solvents such as toluene, xylene and benzene; hydrocarbon solvents such as pentane, hexane, heptane and octane; chlorine solvents such as methylene chloride, chloroform and 1,2-dichloroethane; fluorine solvents such as trifluoroethanol; etc. Among them, acetone, toluene, ethanol, etc. are particularly preferably used in view of solubility, storage stability, etc.

Polymerizable monomers preferably usable as organic solvents in the invention are, for example, ones showing radical polymerizability. As specific examples of the polymerizable monomers usable preferably, there can be mentioned styrene and acrylic or methacrylic polymerizable monomers having high polymerizability such as methyl (meth)acrylate, ethyl (meth)acrylate, isopropyl (meth)acrylate, butyl (meth)acrylate and hydroxyethyl (meth)acrylate, etc.

The above organic solvents can be used alone or in combination of two or more.

In the metal surface-treating agent of the invention, in order to further heighten adhesiveness to base metals, it is also possible to further compound an acidic group-containing (meth)acrylate monomer. By using a metal surface-treating agent of such an embodiment, it gets possible to bond well a base metal such as a cobalt-chromium alloy or a nickel-chromium alloy to a resin or the like. Particularly, when a metal surface-treating agent of the embodiment is used to an alloy composed of base metal(s) and noble metal(s), the adhesive strength of the resultant composite gets higher than that obtained when a metal surface-treating agent wherein an acidic group-containing (meth)acrylate monomer is not compounded is used. Since alloys each composed of base metal(s) and noble metal(s) are often used for dental uses, metal surface-treating agents of the above embodiment are particularly effective as dental metal surface-treating agents.

The above acidic group-containing (meth)acrylate monomer is not particularly limited so long as it is a (meth)acrylate monomer having in the molecule acidic group(s) such as carboxyl group(s) or anhydride(s) thereof, or phosphoric acid group(s), and can be a known one, but is preferably an acidic group-containing (meth)acrylate monomer represented by the following general formula (14)








35


$$m = 1 \sim 4 \quad n = 1, 2$$

(wherein, R^6 represents a hydrogen atom or a methyl group, R^7 represents a bivalent to hexavalent organic residue having 1 to 20 carbon atoms optionally having ether linkage(s) and/or ester linkage(s), and X represents a group containing carboxyl group(s), anhydrous carboxyl group(s), phosphoric acid group(s) or phosphoric ester group(s)).








In the above general formula, X is a group containing carboxyl group(s), anhydrous carboxyl group(s), phosphoric acid group(s) or phosphoric ester group(s), and its structure is not particularly limited, but preferred specific examples thereof are as follows.









In the above general formula, the structure of R^1 is not particularly limited, and can be known a bivalent to hexavalent organic residue having 1 to 20 carbon atoms optionally having ether linkage(s) and/or ester linkage(s), and specific examples thereof are as follows.





Preferred specific examples of the acidic group-containing (meth)acrylate monomer represented by the above general formula are as follows.









(wherein, R^6 is a hydrogen atom or a methyl group)

In view of adhesiveness to metals, among acidic group-containing (meth)acrylate monomers exemplified above as specific examples, those having carboxyl group(s) or phosphoric acid group(s) are used particularly preferably.

The above acidic group-containing (meth)acrylate monomers can be used alone or in combination of two or more.

10 In the metal surface-treating agent containing the acidic group-containing (meth)acrylate monomer, the compounding rate of the thiouracil derivative (a), the acidic group-containing (meth)acrylate monomer (b) and the organic solvent (c) is not particularly limited, but
15 when the total of (a), (b) and (c) is supposed to be 100 weight parts, if the compounding amount of (a) is 0.001 to 20 weight parts, the compounding amount of (b) is 0.1 to 15 weight parts and (c) is the residual parts, good adhesion is made on both base metals and noble metals.
20 A further preferred compounding rate is that (a) is 0.005 to 10 weight parts, (b) is 1 to 10 weight parts and (c) is the residual parts.

In the metal surface-treating agent of the invention, it is preferred in view of adhesive strength
25 and the easiness of handling to use a thiouracil derivative represented by the general formula (1) or (2) in combination with an organic solvent capable of dissolving the thiouracil derivative and having volatility. Further, when it is desired to heighten adhesiveness to
30 base metals, it is preferred to use the metal surface-treating agent in such a form that an acidic group-containing (meth)acrylate monomer represented by the general formula (14) is compounded therein.

Further, it is also possible, if necessary, to
35 incorporate a polymerization catalyst in the metal surface-treating agent of the invention in such a range

that adhesive strength is not lowered. As polymerization catalysts capable of being added, there can be mentioned peroxide polymerization catalysts, for example, diacyl peroxides such as benzoyl peroxide and decanoyl peroxide, dialkyl peroxides such as dicumyl peroxide and ditertiary butyl peroxide; barbituric acid polymerization catalysts such as 5-butylbarbituric acid and 5-butyl-2-thiobarbituric acid; α -diketones such as camphorquinone and acetylbenzoyl; benzoin alkyl ethers such as benzoin ethyl ether; thioxanthone derivatives such as 2-chlorothioxanthone and methylthioxanthone; photopolymerization catalysts, for example, benzophenone and benzophenone derivatives such as p,p'-methoxybenzophenone; amine co-catalysts such as dimethylaminoethyl methacrylate, N,N-dimethyl-p-toluidine and ethyl p-dimethylaminobenzoate; etc. These polymerization catalysts and co-catalysts can be added alone or, if necessary, in combination of two or more.

Further if necessary, it is also possible to add a polymerization inhibitor such as hydroquinone monomethyl ether, hydroquinone or 4-tertiary butylphenol.

As to a process for mixing the above components to give a metal surface-treating agent, there is no particular limitation, and for example, the metal surface-treating agent can be prepared by weighing the thiouracil derivative, the organic solvent and, if necessary, the acidic group-containing (meth)acrylate monomer, and other optional component(s) and putting them in a vessel at a desired mutual ratio, and stirring and mixing the mixture until it gets uniform.

The use method of the metal surface-treating agent of the invention is not particularly limited, but for giving good adhesion between a metal and a resin or the like, a method which comprises coating the surface of the metal with the metal surface-treating agent of

the invention, piling up a polymerizable composition on the metal surface, and curing the polymerizable composition can suitably be adopted. Further, by bonding another resin, metal, ceramics or the like onto the opposite side of the surface of the polymerizable composition contacting to the metal, it is also possible to indirectly bond the metal to such a material.

In the above method, as the polymerizable composition piled up on the metal surface after the treatment, a known polymerizable composition can be used without any limitation, but a polymerizable composition containing an acrylic or methacrylic polymerizable monomer as a main component and containing a polymerization initiator is preferred in view of polymerizability, easiness of handling, etc. Polymerizable compositions generally used in the dental field such as, for example, denture base resins, quick self-curing resins, hard resins, composite resins, resin cements, etc. can preferably be used since they each contain acrylic or methacrylic polymerizable monomer(s) and a polymerization initiator.

As specific examples of the acrylic or methacrylic polymerizable monomer(s), there can be mentioned monofunctional polymerizable monomers such as methyl (meth)acrylate, ethyl (meth)acrylate, hydroxyethyl (meth)acrylate and methacryloyloxyethyl propionate; polyfunctional polymerizable monomers such as triethylene glycol di(meth)acrylate, 2,2-bis(4-(3-methacryloyloxy-2-hydroxypropoxy)phenyl)propane, 2,2-bis(4-methacryloyloxyethoxyphenyl)propane, 1,6-hexanediol di(meth)acrylate, neopentyl glycol di(meth)acrylate, trimethylhexamethylene diisocyanate and pentaerythritol tri(meth)acrylate; adhesive polymerizable monomers such as 4-methacryloyloxyethoxycarbonylphthalic anhydride, 10-methacryloyloxydecyl dihydrogenphosphate, 10-methacryloyloxy-

decamethylenemalonic acid and 2-methacryloyloxyethyl 3'-methacryloyloxy-2'-(3,4-dicarboxybenzoyloxy)propyl succinate; etc. These can be used alone or in combination of two or more.

5 As specific examples of the polymerization initiation catalyst, there can be mentioned redox initiators such as benzoyl peroxide/ N,N-diethanol-p-toluidine; alkyl metal compounds such as a partial oxide of tributylborane; barbituric acid initiators such as
10 n-butylbarbituric acid/copper chloride; and photo-polymerization initiation catalysts such as camphorquinone/N,N-dimethylaminoethyl methacrylate.

 When the metal surface-treating agent of the invention is used to a pure metal such as gold, palladium,
15 um, platinum, silver or copper, or a gold alloy, gold-silver-palladium alloy, silver alloy or the like for dental uses, its effect is particularly remarkable.

 Thiouracil derivatives represented by the general formula (1) or (2) of the invention are novel
20 compounds, and since the thiouracil derivatives are excellent in adhesiveness to noble metals, they are useful as adhesive components of metal surface-treating agents. Further, since they each have a polymerizable unsaturated bond and sulfur, they are utilizable as
25 intermediates of pharmaceuticals, dyes, etc.

 By using a metal surface-treating agent containing a thiouracil derivative having in the molecule at least one radical polymerizable unsaturated bond of the invention, it is possible to bond a metal, particularly a noble metal to a resin or the like in high
30 adhesive strength, and in high water resistance and in high durability. Further, when a metal surface-treating agent wherein an acidic group-containing (meth)acrylate monomer is further compounded is used, it is possible to
35 exert very excellent adhesiveness to any of a noble metal and a base metal. Particularly, when the metal

surface-treating agent wherein an acidic group-containing (meth)acrylate monomer is compounded is applied to an alloy composed of base metal(s) and noble metal(s), adhesive strength is obtained too high to be anticipated
5 from metal surface-treating agents wherein a thiouracil derivative and an acidic group-containing (meth)acrylate monomer are compounded respectively alone in organic solvents. Further, these metal surface-treating agents of the invention are high in storage stability and very
10 excellent also in handling.

The detail of the reason why the above excellent effects are exerted is not clear at present, but is surmised as follows. Namely, when first the surface of a metal is coated with a metal surface-treating agent
15 composed of a thiouracil derivative and an organic solvent, the sulfur atoms in the thiouracil molecules immediately react with the metal atoms or the metal oxide on the surface whereby chemical bonds excellent in water resistance are formed. Then, when a polymerizable
20 composition is piled up on the surface, the polymerizable unsaturated bond of the thiouracil derivative reacts with the polymerizable monomer in the polymerizable composition to cause copolymerization and curing, whereby strong linkage to the metal is formed. It is
25 surmised that the above first reaction is particularly liable to occur on the surface of a noble metal, and as a result, good adhesion between the noble metal and the resin or the like gets possible.

On the other hand, it is surmised that as to
30 an acidic group-containing (meth)acrylate monomer, its acidic group has a strong tendency to react with a base metal atom or an oxide thereof to form a chemical bond excellent in water resistance, and therefore, when the monomer is compounded, adhesive strength to the base
35 metal is heightened. Further, it is surmised that when an alloy composed of base metal(s) and noble metal(s) is

coated with a metal surface-treating agent wherein an acidic group-containing (meth)acrylate monomer is compounded, the above reaction and the above reactions by the thiouracil derivative simultaneously occur, and
5 adhesive strength is enhanced by the synergistic effects of the time.


The present invention is further detailedly described by examples, but the invention should not be limited thereto.

10 Example 1

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, ethyl
2-thiouracil-5-carboxylate (5.0 g, 25.0 mmol) was slowly
15 added dropwise to the solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered. The resultant precipitate was
20 dissolved in water, and hydrochloric acid was added to this solution to give 5-carboxy-2-thiouracil (2.54 g) as a light yellow solid.

2-hydroxyethylmethacrylate (3.90 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol),
25 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put into 200 ml three-necked flask to make a solution, the solution was continuously stirred at room temperature for 3 days. As the reaction proceeded, a white precipitate was formed. After the
30 reaction was completed, said white precipitate was filtered. Tetrahydrofuran was distilled off from the resultant filtrate under reduced pressure and then the residue was subjected to silica gel chromatography. 2-methacryloyloxyethyl 2-thiouracil-5-carboxylate [A]
35 (0.91 g, 3.2 mmol) represented by following formula was obtained by using mixture of ethyl acetate and hexane as

developing solvent. The result of NMR (d6DMSO), MASS and elementary analysis are shown below.



10 NMR (δ , ppm); 1.88 (3H, $-\text{CH}_3$)
 4.36 (4H, $-\text{COO}-\text{CH}_2\text{CH}_2-\text{OCO}-$)
 5.68, 6.03 (2H, $\text{CH}_2=\text{C}-$)
 7.97 (1H, $-\text{N}-\text{CH}=\text{C}-$)
 12.6 (2H, $-\text{NH}-$)

15 MASS (M+1)⁺=285

Elementary analysis; $\text{C}_{11}\text{H}_{12}\text{N}_2\text{O}_5\text{S}$


		C	H	N
	Calculated	46.47	4.25	9.85
20	Found	46.45	4.26	9.83

Example 2

Under an atmosphere of nitrogen, an aceto-
 nitrile solution (30 ml) of methacryloyl chloride (20.9
 25 g, 0.2 mol) was slowly added dropwise at room tempera-
 ture, using a dropping funnel, to 1,6-hexanediol (47.3
 g, 0.40 mol), molecular sieve 3A powder (40 g) and
 acetonitrile (470 ml) in a 1-L three-necked flask.
 After the completion of the dropwise addition, the
 30 mixture was refluxed with heating for 5 hours. The
 mixture was then left alone to cool to room temperature,
 the molecular sieve 3A powder was filtered out from the
 reaction mixture, and acetonitrile was distilled off
 under reduced pressure from the filtrate. Methylene
 35 chloride (300 ml) was added to the residue, and the
 resultant methylene chloride solution was washed with

water. The methylene chloride layer was dried over anhydrous sodium sulfate, and the solvent was distilled off under reduced pressure. 6-Hydroxyhexyl methacrylate (33.3 g) was separated and purified as a colorless transparent liquid from this residue by silica gel column chromatography.

6-Hydroxyhexyl methacrylate (5.59 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then the same separation and purification operations were carried out as in Example 1 to give 6-methacryloyloxyhexyl 2-thiouracil-5-carboxylate [B] (1.13 g, 3.3 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)

1.87 (3H, $-\text{CH}_3$)

4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)

5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$)

7.94 (1H, $-\text{N}-\text{CH}=\text{C}-$)

12.7 (2H, $-\text{NH}-$)

MASS ($M+1$)⁺=341

Elementary analysis; $\text{C}_{15}\text{H}_{20}\text{N}_2\text{O}_5\text{S}$


	C	H	N
Calculated	52.93	5.92	8.23
Found	52.96	5.92	8.25

5 Example 3

Under an atmosphere of nitrogen, a tetrahydrofuran solution (30 ml) of methacryloyl chloride (10.5 g, 0.1 mol) was slowly added dropwise at room temperature, using a dropping funnel, to 1,10-decanediol (34.9 g, 0.20 mol), molecular sieve 3A powder (20 g) and tetrahydrofuran (350 ml) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating for 5 hours. The mixture was then left alone to cool to room temperature, the molecular sieve 3A powder was filtered out from the reaction mixture, and tetrahydrofuran was distilled off under reduced pressure from the filtrate. Methylene chloride (300 ml) was added to the residue, and the resultant methylene chloride solution was washed with water. The methylene chloride layer was dried over anhydrous sodium sulfate, and the solvent was distilled off under reduced pressure. 10-Hydroxydecyl methacrylate (14.5 g) was separated and purified as a colorless transparent liquid from this residue by silica gel column chromatography.

10-Hydroxydecyl methacrylate (7.27 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 10-methacryloyloxydecyl 2-thiouracil-5-car-

boxylate [C] (1.15 g, 2.9 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.3–1.8 (16H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_8\text{CH}_2-\text{OCO}-$)
 1.87 (3H, $-\text{CH}_3$),
 4.08, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_8\text{CH}_2-\text{OCO}-$)
 5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$),
 7.93 (1H, $-\text{N}-\text{CH}=\text{C}-$),
 12.8 (2H, $-\text{NH}-$)

15

MASS (M+1)⁺ = 397

Elementary analysis; $\text{C}_{19}\text{H}_{28}\text{N}_2\text{O}_5\text{S}$

20

	C	H	N
Calculated	57.56	7.12	7.07
Found	57.51	7.14	7.08

Example 4


25 Under an atmosphere of nitrogen, an acetonitrile solution (30 ml) of acryloyl chloride (18.1 g, 0.2 mol) was slowly added dropwise at room temperature, using a dropping funnel, to an acetonitrile solution (470 ml) of 1,6-hexanediol (47.3 g, 0.40 mol) and molecular sieve 3A powder (40 g) in a 1-L three-necked flask.

30 After the completion of the dropwise addition, the mixture was refluxed with heating for 5 hours. After the reaction, the same treatment as in Example 2 was carried out, and thereafter, 6-hydroxyhexyl acrylate

35 (28.9 g) was separated and purified as a colorless transparent liquid.

6-Hydroxyhexyl acrylate (5.17 g, 30.0 mmol),
 N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol),
 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetra-
 hydrofuran (50 ml) were put in a 200-ml three-necked
 5 flask to make a solution, and the solution was continu-
 ously stirred at room temperature for 3 days. A white
 precipitate was formed as the reaction progressed, and
 after the completion of the reaction, the white precipi-
 10 tate was filtered out. Then, the same separation and
 purification operations as in Example 1 to give
 6-acryloyloxyhexyl 2-thiouracil-5-carboxylate [D] (1.01
 g, 3.1 mmol) represented by the following formula. The
 results of NMR (d6DMSO), MASS and elementary analysis
 are shown below.

15



20

NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 5.82, 6.12, 6.45 (3H, $\text{CH}_2=\text{CH}-$),
 25 7.93 (1H, $-\text{N}-\text{CH}=\text{C}-$),
 12.7 (2H, $-\text{NH}-$)

MASS ($M+1$)⁺ = 327

Elementary analysis; $\text{C}_{14}\text{H}_{18}\text{N}_2\text{O}_5\text{S}$

30

	C	H	N
Calculated	51.52	5.56	8.58
Found	51.56	5.57	8.57


Example 5

35

Under an atmosphere of nitrogen, a
 tetrahydrofuran solution (30 ml) of 1,6-hexanediol (4.72

g, 40 mmol) was slowly added dropwise at room temperature, using a dropping funnel, to a tetrahydrofuran solution (20 ml) of 60% sodium hydride (1.92 g, 48 mmol) in a 300-ml three-necked flask. Successively, a
5 tetrahydrofuran solution (30 ml) of chloromethylstyrene (6.1 g, 40 mmol) was slowly added dropwise. After the completion of the dropwise addition, the mixture was refluxed with heating for 4 hours. The mixture was then left alone to cool to room temperature, and diluted
10 hydrochloric acid was added to the reaction mixture to stop the reaction. The aqueous layer was extracted with ether, and the resultant organic layer combined was washed with aqueous saturated sodium hydrogencarbonate solution and saturated sodium chloride solution. The
15 organic layer was dried over anhydrous magnesium sulfate, the solvent was distilled off under reduced pressure, and then 1-hydroxy-6-(p-vinylbenzyloxy)hexane (7.97 g) was separated and purified by silica gel column chromatography.

20 1-Hydroxy-6-(p-vinylbenzyloxy)hexane (7.03 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was
25 continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried
30 out to give 6-(p-vinylbenzyloxy)hexyl 2-thiouracil-5-carboxylate [E] (1.17 g, 3.0 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



10 NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCH}_2-$)
 3.49, 4.1 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCH}_2-$)
 4.53 (2H, $-\text{OCH}_2-\text{C}_6\text{H}_4$)
 5.27, 5.84, 6.71 (3H, $\text{CH}_2=\text{CH}-$),
 7.3-7.4 (4H, C_6H_4)
 7.93 (1H, $-\text{N}-\text{CH}=\text{C}-$),
 12.7 (2H, $-\text{NH}-$)

15 MASS ($M+1$)⁺ = 389


Elementary analysis; $\text{C}_{20}\text{H}_{24}\text{N}_2\text{O}_4\text{S}$

		C	H	N
20	Calculated	61.84	6.23	7.21
	Found	61.81	6.27	7.24

Example 6

Under an atmosphere of nitrogen, a tetra-
 25 hydrofuran solution (30 ml) of methacryloyl chloride
 (10.5 g, 0.1 mol) was slowly added dropwise at room
 temperature, using a dropping funnel, to 2,2-dimethyl-
 1,3-propanediol (20.8 g, 0.2 mol), molecular sieve 3A
 powder (20 g) and tetrahydrofuran (350 ml) in a 1-L
 30 three-necked flask. After the completion of the
 dropwise addition, the mixture was refluxed with heating
 for 4 hours. After the reaction, the same operations as
 in Example 3 were carried out, and thereby 3-hydroxy-
 2,2-dimethylpropyl methacrylate (13.1 g) was separated
 35 and purified.

3-Hydroxy-2,2-dimethylpropyl methacrylate



NMR (δ , ppm); 0.91 (6H, $-\text{CH}_2\text{C}(\underline{\text{CH}_3})_2\text{CH}_2-$)
 1.87 (3H, $\text{CH}_2=\text{C}-\underline{\text{CH}_3}$),
 4.1, 4.18 (4H, $-\text{COO}-\underline{\text{CH}_2}\text{C}(\text{CH}_3)_2\underline{\text{CH}_2}-\text{OCO}-$)
 5.66, 6.02 (2H, $\underline{\text{CH}_2}=\text{C}-$),
 7.93 (1H, $-\text{N}-\underline{\text{CH}}=\text{C}-$),
 12.8 (2H, $-\text{NH}-$)

$$\text{MASS } (M+1)^+ = 327$$


Elementary analysis; $C_{14}H_{18}N_2O_5S$

	C	H	N
Calculated	51.52	5.56	8.58
Found	51.54	5.55	8.57

Under an atmosphere of nitrogen, an acetoni-

trile solution (30 ml) of methacryloyl chloride (20.9 g, 0.2 mol) was slowly added dropwise at room temperature, using a dropping funnel, to acetonitrile solution (470 ml) of 1-methyl-1,5-pentanediol (47.3 g, 0.40 mol),
 5 molecular sieve 3A powder (40 g) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating for 5 hours. After the reaction, the same operations as in Example 2 were carried out, and thereby 5-hydroxy-5-methyl-
 10 pentylmethacrylate (29.4 g) as a colorless transparent liquid was separated and purified.

5-Hydroxy-5-methylpentyl methacrylate (5.59 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and
 15 tetrahydrofuran (50 ml) were put in a 200 ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white
 20 precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 5-methacryloyloxy-1-methylpentyl 2-thiouracil-5-carboxylate [G] (0.71 g, 2.1 mmol) represented by the following formula. The results of NMR
 25 (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.24 (3H, -OCH(CH₃)CH₂-) .
 35 1.3-1.7 (6H, -COO-CH(CH₂)₃CH₂-OCO-)
 1.87 (3H, CH₂=C-CH₃),

4.69, 4.13 (3H, $-\text{COO}-\underline{\text{CH}}(\text{CH}_2)_3\underline{\text{CH}_2}-\text{OCO}-$)

5.65, 6.01 (2H, $\underline{\text{CH}_2}=\text{C}-$),

7.94 (1H, $-\text{N}-\underline{\text{CH}}=\text{C}-$),

12.7 (2H, $-\underline{\text{NH}}-$)

5 MASS $(M+1)^+ = 341$

Elementary analysis; $\text{C}_{15}\text{H}_{20}\text{N}_2\text{O}_5\text{S}$


		C	H	N
	Calculated	52.93	5.92	8.23
10	Found	52.91	5.95	8.25

Example 8

Under an atmosphere of nitrogen, an acetonitrile solution (30 ml) of methacryloyl chloride (20.9 g, 0.2 mol) was slowly added dropwise at room temperature, using a dropping funnel, to p-xylene glycol (55.2 g, 0.40 mol), molecular sieve 3A powder (40 g) and acetonitrile (470 ml) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating for 5 hours. Then, the reaction mixture was left alone to cool to room temperature, the molecular sieve 3A powder was filtered out from the reaction mixture, and acetonitrile was distilled off from the filtrate under reduced pressure. Methylene chloride (300 ml) was added to the residue, and the methylene chloride solution was washed with water. The resultant methylene chloride layer was dried over anhydrous sodium sulfate, and the solvent was distilled off under reduced pressure. 4-(Hydroxymethyl)benzyl methacrylate (34.8 g) was separated and purified as a white solid from this residue by silica gel column chromatography.

4-(Hydroxymethyl)benzyl methacrylate (6.48 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-

necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 4-(methacryloyloxymethyl)benzyl 2-thio-uracil-5-carboxylate [H] (0.91 g, 2.5 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.90 (3H, $-\text{CH}_3$),
 5.17, 5.23 (4H, $-\text{COO}-\text{CH}_2-\text{C}_6\text{H}_4-\text{CH}_2-\text{OCO}-$)
 5.70, 6.07 (2H, $\text{CH}_2=\text{C}-$),
 7.40 (4H, $-\text{C}_6\text{H}_4-$),
 8.00 (1H, $-\text{N}-\text{CH}=\text{C}-$),
 12.8 (2H, $-\text{NH}-$)

MASS ($M+1$)⁺=361

Elementary analysis; $\text{C}_{17}\text{H}_{16}\text{N}_2\text{O}_5\text{S}$

25

	C	H	N
Calculated	56.66	4.47	7.77
Found	56.42	4.31	7.82


30 Example 9

Under an atmosphere of nitrogen, an acetonitrile solution (30 ml) of methacryloyl chloride (20.9 g, 0.2 mol) was slowly added dropwise at room temperature, using a dropping funnel, to diethylene glycol (42.4 g, 0.40 mol), molecular sieve 3A powder (40 g) and acetonitrile (470 ml) in a 1-L three-necked flask. After the

35

completion of the dropwise addition, the mixture was refluxed with heating for 5 hours. Then, the reaction mixture was left alone to cool to room temperature, the molecular sieve 3A powder was filtered out from the reaction mixture, and acetonitrile was distilled off from the filtrate under reduced pressure. Methylene chloride (300 ml) was added to the residue, and the methylene chloride solution was washed with water. The resultant methylene chloride layer was dried over anhydrous sodium sulfate, and the solvent was distilled off under reduced pressure. Diethylene glycol monomethacrylate (59.2 g) was separated and purified as a colorless transparent liquid from this residue by silica gel column chromatography.

Diethylene glycol monomethacrylate (5.22 g, 30.0 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 2-(2-methacryloyloxyethoxy)-ethyl 2-thiouracil-5-carboxylate [I] (1.05 g, 3.2 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.86 (3H, $-\text{CH}_3$),

3.70 (4H, $-\text{CH}_2\text{CH}_2-\text{O}-\text{CH}_2\text{CH}_2-$)
 4.21, 4.26 (2H, 2H, $-\text{CH}_2\text{CH}_2-\text{O}-\text{CH}_2\text{CH}_2-$)
 5.66, 6.01 (2H, $\text{CH}_2=\text{C}-$),
 7.95 (1H, $-\text{N}-\text{CH}=\text{C}-$),
 12.8 (2H, $-\text{NH}-$)

5

MASS (M+1)⁺=329

Elementary analysis; $\text{C}_{13}\text{H}_{16}\text{N}_2\text{O}_6\text{S}$

		C	H	N
10	Calculated	47.56	4.91	8.53
	Found	47.37	4.84	8.41


Example 10

Under an atmosphere of nitrogen, an acetonitrile solution (30 ml) of methacryloyl chloride (20.9 g, 0.2 mol) was slowly added dropwise at room temperature, using a dropping funnel, to 1,3-bis(3-hydroxypropyl)-1,1,3,3-tetramethyldisiloxane (100 g, 0.40 mol), molecular sieve 3A powder (40 g) and acetonitrile (470 ml) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating for 5 hours. The mixture was then left alone to cool to room temperature, the molecular sieve 3A powder was filtered out from the reaction mixture, and acetonitrile was distilled off under reduced pressure from the filtrate. Methylene chloride (300 ml) was added to the residue, and the resultant methylene chloride solution was washed with water. The methylene chloride layer was dried over anhydrous sodium sulfate, and the solvent was distilled off under reduced pressure. 1-(3-Methacryloyloxypropyl)-3-(3-hydroxypropyl)-1,1,3,3-tetramethyldisiloxane (46.2 g) was separated and purified as a colorless transparent liquid from this residue by silica gel column chromatography.

1-(3-Methacryloyloxypropyl)-3-(3-hydroxypropyl)-1,1,3,3-tetramethyldisiloxane (9.54 g, 30 mmol),

35

N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol),
 5-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetra-
 hydrofuran (50 ml) were put in a 200-ml three-necked
 flask to make a solution, and the solution was continu-
 ously stirred at room temperature for 3 days. A white
 precipitate was formed as the reaction progressed, and
 after the completion of the reaction, the white precipi-
 tate was filtered out. Then, the same separation and
 purification operations as in Example 1 were carried out
 to give Compound [J] represented by the following formu-
 la. The results of NMR (d6DMSO), MASS and elementary
 analysis are shown below.



NMR (δ , ppm); 0.06 (12H, -Si-CH₃),
 0.51 (4H, -Si-CH₂-CH₂-CH₂-OCO-),
 1.69 (4H, -Si-CH₂-CH₂-CH₂-OCO-),
 1.87 (3H, -CH₃),
 4.23 (4H, -Si-CH₂-CH₂-CH₂-OCO-),
 5.67, 6.03 (2H, CH₂=C-),
 7.96 (1H, -N-CH=C-),
 12.8 (2H, -NH-)

MASS (M+1)⁺=473

Elementary analysis; C₁₉H₃₂N₂O₆SSi₂

30

	C	H	N
Calculated	48.28	6.82	5.93
Found	48.35	6.74	5.73

Example 11


35 Under an atmosphere of nitrogen, an ethanol
 solution (100 ml) of diethyl ethoxymethylenemalonate

(43.2 g, 0.2 mol) was slowly added dropwise at room temperature, using a dropping funnel, to an ethanol solution (200 ml) of sodium ethoxide (13.6 g, 0.20mol) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating. Successively, an ethanol solution (100 ml) of methylthiourea (18.0 g, 0.2 mol) was slowly added dropwise using a dropping funnel. After the completion of the dropwise addition, the mixture was refluxed with heating for 3 hours. Then, the reaction mixture was left alone to cool to room temperature, and added to water (500 ml) in a beaker. Concentrated hydrochloric acid was added to the resultant solution, then light yellow solid was formed. Then the solid was filtered out, and, ethyl 3-methyl-2-thiouracil-5-carboxylate(14.1 g) was separated and purified by column chromatography.

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, and ethyl 3-methyl-2-thiouracil-5-carboxylate (5.35 g, 25.0 mmol) was slowly added dropwise to the solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered out. The resultant precipitate was dissolved in water, and hydrochloric acid was added to this aqueous to give 5-carboxy-3-methyl-2-thiouracil (2.88 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30.0 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-3-methyl-2-thiouracil (1.86 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the

white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 6-methacryloyloxyhexyl 3-methyl-2-thiouracil-5-carboxylate [K] (1.16 g, 3.28 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 1.87 (3H, $-\text{CH}_3$)
 3.78 (3H, $\text{N}-\text{CH}_3$)
 4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$)
 7.94 (1H, $-\text{N}-\text{CH}=\text{C}-$)
 12.4 (1H, $-\text{NH}-$)

MASS ($M+1$)⁺=354

Elementary analysis; $\text{C}_{16}\text{H}_{22}\text{N}_2\text{O}_5\text{S}$

25

	C	H	N
Calculated	54.22	6.25	7.90
Found	54.20	6.23	7.93

30 Example 12


Ethyl 1-methyl-2-thiouracil-5-carboxylate (15.3 g), an isomer of ethyl 3-methyl-2-thiouracil-5-carboxylate prepared in Example 8, was obtained as they were purified.

35

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L

egg-plant type flask to make a solution, and ethyl
1-methyl-2-thiouracil-5-carboxylate (5.3 g, 25.0 mmol)
was slowly added dropwise to the solution, and the
mixture was subjected to reaction at room temperature
5 for 1 hour. After the completion of the reaction,
methanol (500 ml) was added to the reaction mixture, and
the precipitate deposited was filtered out. The resul-
tant precipitate was dissolved in water, and hydrochlo-
ric acid was added to this solution to give 5-carboxy-
10 1-methyl-2-thiouracil (2.65 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30.0
mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol),
5-carboxy-1-methyl-2-thiouracil (1.86 g, 10 mmol) and
tetrahydrofuran (50 ml) were put in a 200-ml three-
15 necked flask to make a solution, and the solution was
continuously stirred at room temperature for 3 days. A
white precipitate was formed as the reaction pro-
gressed, and after the completion of the reaction, the
white precipitate was filtered out. Then, the same
20 separation and purification operations as in Example 1
were carried out to give 6-methacryloyloxyhexyl 1-
methyl-2-thiouracil-5-carboxylate [L] (1.23 g, 3.56
mmol) represented by the following formula. The results
of NMR (d6DMSO), MASS and elementary analysis are shown
25 below.



35 NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
1.87 (3H, $-\text{CH}_3$)
3.61 (3H, N- CH_3)

4.09, 4.13 (4H, $-\text{COO}-\underline{\text{CH}_2}(\text{CH}_2)_4\underline{\text{CH}_2}-\text{OCO}-$)

5.65, 6.01 (2H, $\underline{\text{CH}_2}=\text{C}-$)

7.94 (1H, $-\text{N}-\underline{\text{CH}}=\text{C}-$)

12.4 (1H, $-\underline{\text{NH}}-$)

5 MASS (M+1)⁺=354

Elementary analysis; $\text{C}_{16}\text{H}_{22}\text{N}_2\text{O}_5\text{S}$

		C	H	N
	Calculated	54.22	6.26	7.90
10	Found	54.21	6.24	7.90

Example 13

Under an atmosphere of nitrogen, an ethanol solution (50 ml) of diethyl malonate (16.0 g, 0.1 mol) was slowly added dropwise at room temperature, using a dropping funnel, to an ethanol solution (200 ml) of sodium ethoxide (13.6 g, 0.2 mol) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating. Successively, an ethanol solution (100 ml) of triethyl orthobenzoate (22.4 g, 0.1 mol) was slowly added dropwise, using a dropping funnel. After the completion of the dropwise addition, the mixture was refluxed with heating for 6 hours. Then the reaction mixture was left alone to cool to room temperature, and ethanol was distilled off under reduced pressure. Water (200 ml) was added to the residue, and the mixture was extracted with ether (3 three times). The ether layer was washed with saturated sodium saline water, dried over anhydrous magnesium sulfate and concentrated. Then the residue was distilled off under reduced pressure. Diethyl 1'-ethoxy-1'-phenylmethylenemalonate (18.2 g) was obtained.

Under an atmosphere of nitrogen, an ethanol solution (50 ml) of diethyl 1'-ethoxy-1'-phenylmethylenemalonate (14.6 g, 0.05 mol) was slowly added dropwise at room temperature, using a dropping funnel,


to an ethanol solution (50 ml) of sodium ethoxide (3.4 g, 0.05 mol) in a 500 ml three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating. Then, an ethanol solution (50 ml) of thiourea (3.8 g, 0.05 mol) was slowly added dropwise at room temperature using a dropping funnel. After the completion of the dropwise addition, the mixture was refluxed with heating for 3 hours. Then the reaction mixture was left alone to cool to room temperature, and reaction mixture was added to water (200 ml) in a beaker. Concentrated hydrochloric acid was added to the resultant solution, then light yellow solid was formed. By filtration of the deposited solid, ethyl 6-phenyl-2-thiouracil-5-carboxylate (7.6 g) was obtained.

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, and ethyl 6-phenyl-2-thiouracil-5-carboxylate (6.90 g, 25.0 mmol) was slowly added dropwise to the solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered out. The resultant precipitate was dissolved in water, and hydrochloric acid was added to this aqueous solution to give 5-carboxy-6-phenyl-2-thiouracil (3.10 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30.0 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 5-carboxy-6-phenyl-2-thiouracil (2.00 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white

precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 6-methacryloyloxyhexyl

6-phenyl-2-thiouracil-5-carboxylate [M] (1.29 g, 3.10 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



15

NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 1.87 (3H, $\text{C}=\text{C}-\text{CH}_3$)
 4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$)
 7.62 (5H, C_6H_5)
 12.5 (2H, $-\text{NH}-$)

20

MASS ($M+1$)⁺=416

Elementary analysis; $\text{C}_{21}\text{H}_{24}\text{N}_2\text{O}_5\text{S}$

25

	C	H	N
Calculated	60.56	5.81	6.73
Found	60.55	5.79	6.73

Example 14

30

Under an atmosphere of nitrogen, an ethanol solution (100 ml) of diethyl 2-oxosuccinate (37.6 g, 0.20 mol) was slowly added dropwise at room temperature, using a dropping funnel, to ethanol solution (200 ml) of sodium ethoxide (13.6 g, 0.20 g) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating. Successively, an


35

ethanol solution (100 ml) of thiourea (15.2 g, 0.20 mol) was slowly added dropwise at room temperature, using a dropping funnel. After the completion of the dropwise addition, the mixture was refluxed with heating for 5 three hours. Then, the reaction mixture was left alone to cool to room temperature, and then the reaction mixture was added to water (500 ml) in a beaker. Concentrated hydrochloric acid was added to the resultant solution, then light yellow solid was formed. By filtration of the deposited solid, ethyl 2-thiouracil-6-carboxylate (28.4 g) was obtained.

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, ethyl 2-thiouracil-6-carboxylate (5.00 g, 25.0 mmol) was slowly added dropwise to the solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered out. The resultant precipitate was dissolved in water, and hydrochloric acid was added to this solution to give 6-carboxy-2-thiouracil (2.80 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30.0 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 6-carboxy-2-thiouracil (1.72 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 6-methacryloyloxyhexyl 2-thiouracil-6-carboxylate [N] (1.07 g, 3.15 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elemen-

tary analysis are shown below.



- 10 NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 1.87 (3H, $-\text{CH}_3$)
 4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$)
 6.87 (1H, $-\text{N}-\text{CH}=\text{C}-$)
 15 12.9 (2H, $-\text{NH}-$)

MASS ($M+1$)⁺=340

Elementary analysis; $\text{C}_{15}\text{H}_{20}\text{N}_2\text{O}_5\text{S}$

		C	H	N
20	Calculated	52.93	5.92	8.23
	Found	52.96	5.95	8.25


Example 15

Under an atmosphere of nitrogen, an ethanol
 25 solution (100 ml) of diethyl 2-methyl-2'-oxosuccinate
 (40.4 g, 0.20 mol) was slowly added dropwise at room
 temperature, using a dropping funnel, to an ethanol
 solution (200 ml) of sodium ethoxide (13.6 g, 0.20 mol)
 in a 1-L three-necked flask. After the completion of
 30 the dropwise addition, the mixture was refluxed with
 heating. Successively, an ethanol solution (100 ml) of
 thiourea (15.2 g, 0.20 mol) was slowly added dropwise at
 room temperature, using a dropping funnel, After the
 completion of the dropwise addition, the mixture was
 35 refluxed with heating for three hours. Then, the reac-
 tion mixture was left alone to cool to room temperature,

and then the reaction mixture was added to water (500 ml) in a beaker. Concentrated hydrochloric acid was added to the resultant solution, then light yellow solid was formed. By filtration of the deposited solid, ethyl 5-methyl-2-thiouracil-6-carboxylate (26.5 g) was obtained.

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, ethyl 5-methyl-2-thiouracil-6-carboxylate (5.35 g, 25.0 mmol) was slowly added dropwise to the solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered out. The resultant precipitate was dissolved in water, and hydrochloric acid was added to this solution to give 6-carboxy-5-methyl-2-thiouracil (2.93 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30.0 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 6-carboxy-5-methyl-2-thiouracil (1.86 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 6-methacryloyloxyhexyl 5-methyl-2-thiouracil-6-carboxylate [O] (1.13 g, 3.19 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



10 NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 1.87 (3H, $\text{CH}_2=\text{C}-\underline{\text{CH}_3}$)
 2.34 (3H, $\text{C}=\text{C}-\underline{\text{CH}_3}$)
 4.09, 4.13 (4H, $-\text{COO}-\underline{\text{CH}_2}(\text{CH}_2)_4\underline{\text{CH}_2}-\text{OCO}-$)
 5.65, 6.01 (2H, $\underline{\text{CH}_2}=\text{C}-$)
 12.6 (2H, $-\underline{\text{NH}}-$)

15 MASS ($M+1$)⁺=354

Elementary analysis; $\text{C}_{16}\text{H}_{22}\text{N}_2\text{O}_5\text{S}$

	C	H	N
Calculated	54.22	6.25	7.90
20 Found	54.19	6.23	7.90


Example 16

Under an atmosphere of nitrogen, an ethanol solution (100 ml) of diethyl 2-methyl-2'-oxosuccinate
 25 (40.4 g, 0.20 mol) was slowly added dropwise at room temperature, using a dropping funnel, to an ethanol solution (200 ml) of sodium ethoxide (13.6 g, 0.20 g) in a 1-L three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heat-
 30 ing. Successively, an ethanol solution (100 ml) of methylthiourea (18.0 g, 0.20 mol) was slowly added dropwise at room temperature, using a dropping funnel, After the completion of the dropwise addition, the mixture was refluxed with heating for three hours, Then,
 35 the reaction mixture was left alone to cool to room temperature, and then the reaction mixture was added to

water (500 ml) in a beaker. Concentrated hydrochloric acid was added to the resultant solution, then light yellow solid was formed. The solid deposited was filtered out then ethyl 3,5-dimethyl-2-thiouracil-6-carboxylate (16.2 g) was separated and purified by column chromatography.

Potassium tertiary butoxide (43.7 g, 389 mmol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, ethyl 3,5-dimethyl-2-thiouracil-6-carboxylate (5.70 g, 25.0 mmol) was slowly added dropwise to the solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered. The resultant precipitate was dissolved in water, and hydrochloric acid was added to this solution to give 6-carboxy 3,5-dimethyl-2-thiouracil (2.88 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30 mmol), N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol), 6-carboxy-3,5-dimethyl-2-thiouracil (2.00 g, 10 mmol) and tetrahydrofuran (50 ml) were put in a 200-ml three-necked flask to make a solution, and the solution was continuously stirred at room temperature for 3 days. A white precipitate was formed as the reaction progressed, and after the completion of the reaction, the white precipitate was filtered out. Then, the same separation and purification operations as in Example 1 were carried out to give 6-methacryloyloxyhexyl 3,5-dimethyl-2-thiouracil-6-carboxylate [P] (1.13 g, 3.07 mmol) represented by the following formula. The results of NMR (d6DMSO), MASS and elementary analysis are shown below.



NMR (δ , ppm); 1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 10 1.87 (3H, $\text{CH}_2=\text{C}-\text{CH}_3$)
 2.36 (3H, $\text{C}=\text{C}-\text{CH}_3$)
 3.68 (3H, $\text{N}-\text{CH}_3$)
 4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
 5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$)
 15 12.3 (1H, $-\text{NH}-$)

MASS ($M+1$)⁺ = 368

Elementary analysis; $\text{C}_{17}\text{H}_{24}\text{N}_2\text{O}_5\text{S}$

		C	H	N
20	Calculated	55.42	6.57	7.60
	Found	55.48	6.54	7.61

Example 17

Under an atmosphere of nitrogen, an ethanol
 25 solution (50 ml) of diethyl malonate (16.0 g, 0.1 mol)
 was slowly added dropwise at room temperature, using a
 dropping funnel, to an ethanol solution (200 ml) of
 sodium ethoxide (13.6 g, 0.2 mol) in a 1-L three-necked
 flask. After the completion of the dropwise addition,
 30 the mixture was refluxed with heating. Successively, an
 ethanol solution (100 ml) of triethyl orthopropionate
 (17.6 g, 0.1 mol) was slowly added dropwise, using a
 dropping funnel. After the completion of the dropwise
 addition, the mixture was refluxed with heating for 6
 35 hours. The mixture was then left alone to cool to room
 temperature, ethanol was distilled off under reduced


pressure, 200 ml of water was added to the residue, and the mixture was extracted with ether (three times). The ether layer was washed with saturated aqueous sodium chloride solution, dried over anhydrous magnesium sulfate, and concentrated. The residue was distilled under reduced pressure to give diethyl 1-ethoxy-1-ethylmethylenemalonate (17.2 g).

Under an atmosphere of nitrogen, an ethanol solution (50 ml) of diethyl 1-ethoxy-1-ethylmethylenemalonate (12.2 g, 0.05 mol) was slowly added dropwise at room temperature, using a dropping funnel, to an ethanol solution (50 ml) of sodium ethoxide (3.4 g, 0.05 mol) in a 500-ml three-necked flask. After the completion of the dropwise addition, the mixture was refluxed with heating. Successively, an ethanol solution (50 ml) of thiourea (3.8 g, 0.05 mol) was slowly added dropwise at room temperature, using a dropping funnel. After the completion of the dropwise addition, the mixture was refluxed with heating for 3 hours. The mixture was then left alone to cool to room temperature, and the reaction mixture was added to water (200 ml) in a beaker. Concentrated hydrochloric acid was added to the resultant solution, and thereby a light yellow solid was deposited. The deposited solid was filtered to give ethyl 6-ethyl-2-thiouracil-5-carboxylate (7.3 g).

Potassium tertiary butoxide (43.7 g, 389 mol) and dimethyl sulfoxide (400 ml) were put in a 2-L egg-plant type flask to make a solution, ethyl 6-ethyl-2-thiouracil-5-carboxylate (5.70 g, 25.0 mol) was slowly added dropwise to this solution, and the mixture was subjected to reaction at room temperature for 1 hour. After the completion of the reaction, methanol (500 ml) was added to the reaction mixture, and the precipitate deposited was filtered. The obtained precipitate was dissolved in water, and hydrochloric acid was added to this aqueous solution to give

5-carboxy-6-ethyl-2-thiouracil (3.10 g) as a light yellow solid.

6-Hydroxyhexyl methacrylate (5.59 g, 30 mmol),
N,N'-dicyclohexylcarbodiimide (2.27 g, 11 mmol),
5 5-carboxy-6-ethyl-2-thiouracil (2.00 g, 10 mmol) and
tetrahydrofuran (50 ml) were put in a 200-ml three-
necked flask to make a solution, and the solution was
continuously stirred at room temperature for 3 days. A
white precipitate was formed as the reaction pro-
10 gressed, and after the completion of the reaction, the
white precipitate was filtered out. Then, the same
separation and purification operations as in Example 1
were carried out to give 6-methacryloyloxyhexyl
6-ethyl-2-thiouracil-5-carboxylate [Q] (1.14 g, 3.1
15 mmol) represented by the following formula. The results
of NMR (d6DMSO), MASS and elementary analysis are shown
below.



25 NMR (δ , ppm); 1.02 (3H, $-\text{CH}_2\text{CH}_3$)
1.3-1.7 (8H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
1.87 (3H, $\text{C}=\text{C}-\text{CH}_3$)
2.05 (2H, $-\text{CH}_2\text{CH}_3$)
4.09, 4.13 (4H, $-\text{COO}-\text{CH}_2(\text{CH}_2)_4\text{CH}_2-\text{OCO}-$)
5.65, 6.01 (2H, $\text{CH}_2=\text{C}-$)
30 12.5 (2H, $-\text{NH}-$)

MASS (M+1)⁺ = 369

Elementary analysis; $C_{17}H_{24}N_2O_5S$

		C	H	N
35	Calculated	55.42	6.57	7.60
	Found	55.42	6.59	7.63

10



"KINPARA 12", a dental gold-silver-palladium alloy (made by Towa Giken Co., 10 x 10 x 3 mm) and a pure gold plate (10 x 10 x 3 mm), which were adherends, were abraded with #1500 waterproof abrasive paper, and then sand-
35 blasted. An adhesive tape wherein a hole of 4 mm in diameter was made was stuck on the treated surface of

each adherend to fix an area to be adhesive-treated. Each of the surfaces was coated with each of the previously prepared metal surface-treating agents, using a brush, respectively, and the acetone was volatilized by
5 air drying. One minute later, kneaded paste of "Bistite resin cement" (made by Tokuyama), a dental adhesive, was piled on each of the surfaces treated with each of the metal surface-treating agents, respectively. Then, a 8 mm x 18 mm SUS304-made round bar, which was previously
10 sandblasted, was pressed on each of the adhesive surfaces to carry out adhesion, respectively. The excess resin cement was removed, and one hour later, each adhesion test piece was immersed in water of 37°C. 24 Hours later, tensile adhesive strength was measured,
15 using an autograph (crosshead speed: 10 mm/min) made by SHIMADZU CORPORATION. In each case, the measured values on 6 test pieces were averaged, and the measurement results were shown in Table 1.

Table 1

	Adhesive component in the surface-treating agent	Adhesive strength to KINPARA 12 MPa	Adhesive strength to the pure gold plate MPa
Example 18	A	21	25
19	B	24	29
20	C	24	28
21	D	22	27
22	E	18	23
23	F	20	25
24	G	22	27
25	H	22	25
26	I	22	25
27	J	22	24
28	K	21	25
29	L	22	24
30	M	23	28
31	N	23	27
32	O	24	27
33	P	20	24
34	Q	23	28
Comparative example 1	R	11	10
2	S	10	9
3	T	10	9
4	-	10	9

Examples 35-43

Using Compound (B) shown in Example 19 in Table 1, the effect of the concentration of the adhesive component contained in the metal surface-treating agent was examined. Namely, Compound (B) was dissolved in acetone to prepare acetone solutions having concentrations of 20, 10, 5, 1, 0.5, 0.1, 0.01, 0.005 and 0.001 % by weight, respectively. The same operations as in Examples 18 to 34 were carried out except that each of these solutions was used as a metal surface-treating agent, and thereby adhesive effects on "KINPARA 12", a dental gold-silver-palladium alloy, and a pure gold plate were examined. The results are shown in Table 2.

Table 2

	Concentration of the adhesive component wt%	Adhesive strength to KINPARA 12 MPa	Adhesive strength to the pure gold plate MPa
Example 35	20.0	15	16
36	10.0	16	18
37	5.0	19	21
38	1.0	22	25
39	0.5	25	28
40	0.1	23	28
41	0.01	20	24
42	0.005	17	17
43	0.001	14	16

Example 44 and Comparative example 5

A 0.5% methyl methacrylate solution of Compound (B) used in Example 9 was prepared. In the same manner as in Examples 18 to 34, "KINPARA 12", a dental noble metal alloy, was coated with the solution, and one minute later, the coated surface was washed with pure acetone, and the same stainless steel bar as in the examples was bonded onto the coated surface with "Bistite resin cement" (made by Tokuyama) to prepare an
10 adhesion test piece (Example 44). On the other hand, a test piece coated with methyl methacrylate alone (Comparative example 5) was also prepared as a comparative example. In the same manner as in Examples 18 to 34, these test pieces were immersed in water of 37°C for one
15 day, and tensile adhesive strength was measured. As a result, the average adhesive strength was 23 MPa in Example 44, whereas 10 MPa in Comparative example 5.

Examples 45 to 61 and Comparative example 6

20 A 0.5% acetone solution of Compound A used in Example 18 was prepared. In the same manner as in Examples 18 to 34, "KINPARA 12", a dental noble metal alloy, and a "pure gold plate" were coated with the solution, and after the adherends were air dried, the same stainless steel bar as in Examples 18 to 34 was bonded onto
25 the adherends with "Bistite resin cement" (made by Tokuyama) to prepare adhesion test pieces (Example 45). Likewise, adhesion test pieces (Examples 46 to 61) were prepared using Compounds B to Q. On the other hand, the
30 same stainless steel bar as in Examples 18 to 34 was bonded, using Bistite resin cement, onto "KINPARA 12" and a "pure gold plate" each coated with pure acetone liquid alone, to prepare test pieces (Comparative example 6). For the assessment of adhesion durability, one
35 hour after the adhesion, these test pieces were immersed in water of 37°C, and 24 hours later, a heat cycle test

wherein the test pieces were alternately immersed in temperature-adjustable water baths, each kept at 4°C and 60°C , each for one minute was carried out 5,000 times, and then tensile adhesive strength was measured. The
5 results are shown in Table 3.

Table 3

	Adhesive component in the surface-treating agent	Adhesive strength to KINPARA 12 MPa	Adhesive strength to the pure gold plate MPa
Example 45	A	17 (21)	19 (25)
46	B	22 (24)	26 (29)
47	C	21 (24)	26 (28)
48	D	20 (22)	24 (27)
49	E	16 (18)	20 (23)
50	F	17 (20)	20 (25)
51	G	20 (22)	23 (27)
52	H	21 (22)	23 (25)
53	I	22 (22)	24 (25)
54	J	22 (22)	23 (24)
55	K	21 (21)	23 (25)
56	L	20 (22)	23 (24)
57	M	21 (23)	25 (28)
58	N	20 (23)	24 (27)
59	O	23 (24)	25 (27)
60	P	20 (20)	24 (24)
61	Q	21 (23)	25 (28)
Comparative example 6	-	2 (10)	2 (9)

() Initial adhesive strength

Whenever any of the metal surface-treating agents was used (Examples 45 to 61), there was no case where the adhesive strength of each metal after the heat cycle test was largely lowered compared with the initial adhesive strength (the values in the parentheses in Table 3). On the other hand, in Comparative example 6, the adhesive strength was largely lowered.

Examples 62 to 78

10 A 0.5% acetone solution of Compound A used in Example 18 was prepared, and then in order to assess the storage stability of the primer, the solution was stored in a constant temperature chamber of 37°C for 2 months. In the same manner as in Examples 18 to 34, "KINPARA
15 12", a dental noble metal alloy, and a "pure gold plate" were coated with the primer after the storage, and after the adherends were air dried, the same stainless steel bar as in Examples 18 to 34 was bonded onto the adherends with "Bistite resin cement" (made by Tokuyama)
20 to prepare adhesion test pieces (Example 62). Likewise, 0.5% acetone solutions of Compounds B to Q were prepared, and stored at 37°C for 2 months, adhesion was carried out using them to give adhesion test pieces (Examples 63 to 78). One hour after the adhesion, these
25 test pieces were immersed in water of 37°C, and 24 hours later, tensile adhesive strength was measured. The results are shown in Table 4.

Table 4

	Adhesive component in the surface-treating agent	Adhesive strength to KINPARA 12 MPa	Adhesive strength to the pure gold plate MPa
Example 62	A	20 (21)	23 (25)
63	B	25 (24)	29 (29)
64	C	24 (24)	28 (28)
65	D	22 (22)	26 (27)
66	E	19 (18)	22 (23)
67	F	18 (20)	26 (25)
68	G	23 (22)	27 (27)
69	H	22 (22)	24 (25)
70	I	23 (22)	25 (25)
71	J	21 (22)	22 (24)
72	K	20 (21)	23 (25)
73	L	23 (22)	24 (24)
74	M	22 (23)	25 (28)
75	N	25 (23)	26 (27)
76	O	23 (24)	25 (27)
77	P	20 (20)	25 (24)
78	Q	22 (23)	25 (28)

() Initial adhesive strength

Also when the metal surface-treating agents after the storage at 37°C for 2 months were used (Examples 62 to 78), there was no case where the adhesive strength to each metal was largely lowered compared with the initial adhesive strength (the values in the parentheses in Table 4).


Example 79

10-Methacryloyloxydecyl 2-thiouracil-5-carboxylate [C] (0.001 g), 11-methacryloyloxy-1,1-undecanedicarboxylic acid [R] (1.4 g) and acetone (18.599 g) were mixed to give a uniform solution, which was assumed to be a metal surface-treating agent. "KINPARA 12", a dental gold-silver-palladium alloy (made by Towa Giken Co., 10 x 10 x 3 mm), "WACROME", a dental cobalt-chromium alloy (made by Towa Giken Co., 10 x 10 x 3 mm), a pure gold plate (10 x 10 x 3 mm) and a pure copper plate (10 x 10 x 3 mm) which were adherends, were abraded with #1500 waterproof abrasive paper, and then sandblasted. An adhesive tape wherein a hole of 4 mm in diameter was made was stuck on the treated surface of each adherend to fix an area to be adhesive-treated. Each of the surfaces was coated with the previously prepared metal surface-treating agent, using a brush, and the acetone was volatilized by air drying. One minute later, kneaded paste of "Bistite resin cement" (made by Tokuyama), a dental adhesive, was piled on each of the surfaces treated with the metal surface-treating agent. Then, a 8 mm x 18 mm SUS304-made round bar, which was previously sandblasted, was pressed on each of the adhesive surfaces to carry out adhesion, respectively. The excess resin cement was removed, and one hour later, each adhesion test piece was immersed in water of 37°C. 24 Hours later, tensile adhesive strength was measured, using an autograph (crosshead speed: 10 mm/min) made by SHIMADZU CORPORATION. In each case, the measured values


on 6 test pieces were averaged, and the measurement results were shown in Table 6.

Examples 80 to 93


- 5 Metal surface-treating agents of the compositions shown in Table 5 were prepared according to the process of Example 79, and adhesive strength to various metals were measured in the same manner as therein. The measurement results are shown in Table 6. In this
- 10 connection, the structures and abbreviations of the acidic group-containing (meth)acrylate monomers used are shown below.




[R]




[S]



[T]



[U]



[V]

Table 5

	Thiouracil derivative (wt%)		Acidic group-containing (meth)acrylate monomer (wt%)		Organic solvent
Example 79	C	0.005	R	7	acetone
Example 80	P	0.05	R	0.1	acetone
Example 81	B	0.05	U	5	acetone
Example 82	D	0.1	S	3	acetone
Example 83	H	0.1	R	5	acetone
Example 84	B	0.1	R	10	ethanol
Example 85	Q	0.2	U+R = 3+4		acetone
Example 86	C	0.2	R	5	ethanol
Example 87	C	0.5	T	10	acetone
Example 88	F	0.5	U	15	acetone/toluene=1/1
Example 89	B	0.5	R	5	acetone
Example 90	B	1.0	V	5	MMA
Example 91	J	1.0	R	5	acetone
Example 92	E	5.0	R	3	acetone
Example 93	C	10.0	U	7	toluene

Table 6

	KINPARA 12 MPa	Pure gold plate MPa	WACROME MPa	Pure copper plate MPa
Example 79	20	17	33	26
Example 80	21	23	26	21
Example 81	25	26	33	25
Example 82	24	26	33	24
Example 83	24	24	33	24
Example 84	27	28	34	26
Example 85	27	27	35	27
Example 86	28	27	35	26
Example 87	28	28	34	25
Example 88	23	24	28	22
Example 89	29	28	35	27
Example 90	27	26	33	25
Example 91	23	24	33	23
Example 92	20	19	32	24
Example 93	18	19	33	25

Examples 81, 82, 84, 87 and 90 represent the results in the cases where different acidic group-containing (meth)acrylate monomers were used, Examples 80, 82, 83, 85, 86, 88, 89, 91 and 92 represent the results in the cases where different thiouracil derivatives were used, and Examples 84, 87, 90 and 93 represent the results in the cases where different solvents were used. Examples 79 and 93 show the range of the content of the thiouracil derivative on which the test was carried out, and Examples 80 and 88 show the range of the content of the acidic group-containing (meth)acrylate monomer on which the test was carried out. Example 88 is an example wherein plural organic solvents were used, and Example 85 is an example wherein plural acidic group-containing (meth)acrylate monomers were used. In all the examples, adhesive strength to "KINPARA 12", "WACROME", the pure gold plate and the pure copper plate were good.

Further, as apparent from comparison between Example 87 and Example 20 and between Example 89 and Example 19, the adhesive strength to "KINPARA 12", an alloy composed of base metals and noble metals is higher, compared with the cases where an acidic group-containing (meth)acrylate monomer was not compounded.

25

Examples 94 to 95 and Comparative examples 7 to 8

In the same manner as in Example 79, metal surface-treating agents of the compositions shown in Table 7 were prepared and assessment was made. The results are shown in Table 8.

30

Table 7

	Thiouracil derivative (wt%)	Acidic group- containing (meth)acrylate monomer (wt%)	Organic solvent
Example 94	B 0.5	-	acetone
Example 95	B 0.5	R 20	acetone
Comparative example 7	-	R 5	acetone
Comparative example 8	B 0.5	R 5	-

Table 8

	KINPARA 12 MPa	Pure gold plate MPa	WACROME MPa	Pure copper plate MPa
Example 94	23	29	24	19
Example 95	22	23	25	18
Comparative example 7	10	9	33	25
Comparative example 8	-	-	-	-

Comparative example 7 is an example wherein a thiouracil derivative is not contained, and there arised problems in adhesive strength to "KINPARA 12" and the pure gold plate. In each of Examples 94 and 95, the
5 content of the acidic group-containing (meth)acrylate monomer is out of the range, and therefore, the adhesive strength to "WACROME" and the pure copper plate is lowered. In Comparative example 8, an organic solvent is not contained, and therefore, the thiouracil deriv-
10 ative did not dissolve in the acidic group-containing (meth)acrylate monomer and a uniform solution was not obtained.

Examples 96 to 102 and Comparative example 9

15 "KINPARA 12" and "WACROME" as dental alloys, and a pure gold plate and a pure copper plate were coated with the metal surface-treating agent used in Example 89, according to the process of Example 79, and after the adherends were dried, the stainless steel bar
20 was bonded to each of the surfaces of the adherends using "Bistite resin cement" (made by Tokuyama), whereby adhesion test pieces (Example 96) were obtained. Likewise, adhesion test pieces (Examples 97 to 102) were prepared using the metal surface-treating agents used in
25 Examples 82, 83, 84, 85, 86 and 87. On the other hand, adhesion test pieces in the case where pure acetone liquid alone was applied (Comparative example 9) was also prepared. For the assessment of adhesion durabili-
ties of these test pieces, one hour after the adhesion,
30 these test pieces were immersed in water of 37°C , and 24 hours later, a heat cycle test wherein the test pieces were alternately immersed in temperature-adjustable water baths, each kept at 4°C and 60°C , each for one minute was carried out 5,000 times, and then tensile
35 adhesive strength was measured. The results are shown in Table 9.

Table 9

	KINPARA 12	Pure gold plate	WACROME	Pure copper plate	
	MPa	MPa	MPa	MPa	
5	Example 96	28 (29)	26 (28)	33 (35)	24 (27)
	Example 97	21 (24)	23 (26)	31 (33)	23 (24)
	Example 98	23 (24)	24 (24)	31 (33)	23 (24)
	Example 99	25 (27)	27 (28)	31 (34)	24 (26)
10	Example 100	24 (27)	25 (27)	32 (35)	23 (27)
	Example 101	28 (28)	26 (27)	31 (35)	23 (26)
	Example 102	25 (28)	27 (28)	34 (34)	23 (25)
	Comparative example 9	4 (10)	3 (9)	10 (23)	9 (18)

15 () Initial adhesive strength

Whenever any of the metal surface-treating agents was used (Examples 96 to 102), there was no case
 20 where the adhesive strength of each metal after the heat cycle test was largely lowered compared with the initial adhesive strength (the values in () in Table 9). On the other hand, in Comparative example 9, the adhesive strength was largely lowered.

25

Examples 103 to 109

The metal surface-treating agent used in Example 89 was stored in a constant temperature chamber of 37°C for 2 months. According to the process of
 30 Example 79, "KINPARA 12", "WACROME", a pure gold plate and a pure copper plate were coated with the resultant metal surface-treating agent, and then air dried. The stainless steel bar was bonded to each of the adherends using "Bistite resin cement" (made by Tokuyama) to give
 35 adhesion test pieces (Example 103). Likewise, adhesion was carried out using the metal surface-treating agents

which were used in Examples 82, 83, 84, 85, 86 and 87 and stored at 37°C for 2 months, whereby adhesion test pieces (Examples 104 to 109) were obtained. One hour after the adhesion, each test piece was immersed in water of 37°C for one hour, and 24 hours later, tensile adhesive strength was measured. The results are shown in Table 10.

10

Table 10

		KINPARA 12	Pure gold plate	WACROME	Pure copper plate
		MPa	MPa	MPa	MPa
15	Example 103	28 (29)	28 (28)	36 (35)	25 (27)
	Example 104	25 (24)	24 (26)	33 (33)	23 (24)
	Example 105	23 (24)	24 (24)	33 (33)	23 (24)
	Example 106	27 (27)	28 (28)	34 (34)	25 (26)
	Example 107	25 (27)	26 (27)	32 (35)	27 (27)
20	Example 108	27 (28)	27 (27)	33 (35)	24 (26)
	Example 109	28 (28)	27 (28)	33 (34)	24 (25)

() Initial adhesive strength

25

Also when the metal surface-treating agents after storage at 37°C for 2 months were used (Examples 103 to 109), the adhesive strength to each metal was not greatly lowered, compared with the initial adhesive strength (the values in the parentheses in Table 10).

30




What is claimed is:

1. An unsaturated thiouracil derivative which

has at least at one terminal thereof an organic group (I) having a radical polymerizable unsaturated bond, and

has at the other terminal the following thiouracil residue (II)



wherein


R^1 and R^2 each is a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom, and R^3 is a hydrogen atom, an alkyl group or a phenyl group,

and

wherein


the organic group (I) and the thiouracil residue (II) are separated by a bivalent spacer residue containing at least 2 carbon atoms.

2. An unsaturated thiouracil derivative according to claim 1 wherein the organic group (I) having a radical polymerizable unsaturated bond is represented by the following formula (I-1)






wherein R^5 is a hydrogen atom or a methyl group, and

Z is a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or




the spacer residue is a bivalent organic group having 2 to 20 carbon atoms which may contain, in the chain skeleton, oxygen, or oxygen and silicon, besides carbon.


3. An unsaturated thiouracil derivative according to claim 1 or 2 wherein the spacer residue is a bivalent saturated hydrocarbon group having 2 to 12 carbon atoms, or any group selected from the following formulae (III-2), (III-3) and (III-4)



wherein n is an integer of 1 to 5, o and p each is an integer of 1 to 10, q is an integer of 1 to 5, and r and s each is an integer of 1 to 5.

4. An unsaturated thiouracil derivative represented by the following formula (1) or (2)








wherein

R^1 and R^2 each are a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom, and


R^3 is a hydrogen atom, an alkyl group or a phenyl group,

R^4 is a bivalent saturated hydrocarbon group having 2 to 12 carbon atoms, or any group selected from the following formulae (III-2), (III-3) and (III-4)



wherein n is an integer of 1 to 5, o and p each are an integer of 1 to 10, q is an integer of 1 to 5, and r and s each are an integer of 1 to 5,

Z is a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or a






R^5 is a hydrogen atom or a methyl group.

5. A metal surface-treating agent comprising an unsaturated thiouracil derivative which

has at least at one terminal thereof an organic group (I) having a radical polymerizable unsaturated bond, and

has at the other terminal the following thiouracil residue (II)



wherein

R^1 and R^2 each is a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom, and

R^3 is a hydrogen atom, an alkyl group or a phenyl group,

and

wherein

the organic group (I) and the thiouracil residue (II) are separated by a bivalent spacer residue containing at least 2 carbon atoms.

6. A metal surface-treating agent according to claim 5 comprising an unsaturated thiouracil derivative in which the organic group (I) having a radical polymerizable unsaturated bond is represented by the following formula (I-1)




wherein R^5 is a hydrogen atom or a methyl






group, and

Z is a -COO- group, a $\text{-CH}_2\text{O-}$ group or a





the spacer residue is a bivalent organic group having 2 to 20 carbon atoms which may contain, in the chain skeleton, oxygen, or oxygen and silicon, besides carbon.

7. A metal surface-treating agent according to claim 5 or 6 comprising an unsaturated thiouracil derivative in which the spacer residue is a bivalent saturated hydrocarbon group having 2 to 12 carbon atoms, or any group selected from the following formulae (III-2), (III-3) and (III-4)






wherein n is an integer of 1 to 5, o and p each is an integer of 1 to 10, q is an integer of 1 to 5, and r and s each is an integer of 1 to 5.

8. A metal surface-treating agent comprising an unsaturated thiouracil derivative represented by the following formula (1) or (2)



wherein


R^1 and R^2 each is a hydrogen atom or an alkyl group, and at least one of R^1 and R^2 is a hydrogen atom, and R^3 is a hydrogen atom, an alkyl group or a phenyl group, R^4 is a bivalent saturated hydrocarbonic group having 2 to 12 carbon atoms, or any group selected from the following formulae (III-2), (III-3) and (III-4)





wherein n is an integer of 1 to 5, o and p each are an integer of 1 to 10, q is an integer of 1 to 5, and r and s each are an integer of 1 to 5,

Z is a $-\text{COO}-$ group, a $-\text{CH}_2\text{O}-$ group or a



R^5 is a hydrogen atom or a methyl group.

9. A metal surface-treating agent according to any of claims 5 to 8 further containing an organic solvent.

10. A metal surface-treating agent according to claims 9 wherein the concentration of the unsaturated thiouracil derivative is 0.001 to 20 % by weight based on the total amount of the unsaturated thiouracil derivative and the organic solvent.

11. A metal surface-treating agent according to claim 9 or 10 wherein the organic solvent is acetone, toluene, methyl methacrylate or ethanol.

12. A metal surface-treating agent according to any of claims 5 to 8 further containing an organic solvent and an acidic group-containing (meth)acrylate monomer.

13. A metal surface-treating agent according to claim 12 wherein, the compounding amount of the unsaturated thiouracil derivative is 0.001 to 20 weight parts, the compounding amount of the acidic group-containing (meth)acrylate monomer is 0.1 to 15 weight parts, and the rest is the organic solvent per 100 wt parts of total amount of the unsaturated thiouracil derivative, the acidic group-containing (meth)acrylate monomer and the organic solvent.

14. A metal surface-treating agent according to claim 12 or 13 wherein the acidic group-containing (meth)acrylate monomer is a (meth)acrylate monomer



having a carboxyl group or a phosphoric acid group as the acidic group, and the organic solvent is acetone, toluene, methyl methacrylate or ethanol.