

THIXOTROPIC COMPOSITIONS

Field of the Invention

[0001] The present invention relates generally to ethylcellulose-containing compositions, and in particular, to thixotropic compositions comprising ethylcellulose.

Background of the Invention

[0002] Petroleum jelly or petrolatum is a well-known product that has many utilities, including cosmetic-related utilities. Petroleum jelly is an anhydrous semi-solid mixture of hydrocarbons, generally having carbon numbers greater than 25 and a melting-point usually within a few degrees of 75°C (167°F). It is colorless, or of a pale yellow color (when not highly distilled), translucent, and devoid of taste and smell when pure. It does not oxidize on exposure to air and is relatively inert. It is insoluble in water and soluble in several organic solvents. Although this product has been found to have many utilities, if prepared improperly, it has been found to contain toxic compounds, including polycyclic aromatic hydrocarbons (PAHs) linked to cancer. As a result, the European Union has classified petrolatum as a carcinogen and restricts its use in cosmetics. Moreover, petrolatum is not extensively used in cosmetic products due to its “greasy feel” on the skin.

[0003] Very few non-hydrocarbon-based gels have also been developed for use in cosmetics. US-B-6187323, for example, describes pharmaceutical and cosmetic compositions comprising a mixture of a gelled oil and an aqueous gel. The oil may be gelled with ethylcellulose by heating to 140°C to dissolve the ethylcellulose. WO2008/081175 also describes an aqueous composition containing an active agent for cosmetic and pharmaceutical applications. This composition is a homogeneous mixture (not emulsion) of an oil component with an aqueous component. The oil component is gelled with ethylcellulose at 120°C or 150°C prior to mixing with the aqueous component. The aqueous component is gelled with a conventional cosmetic gelling agent. Aqueous gels such as these, however, do not provide the properties of the anhydrous semi-solid hydrophobic petroleum jelly.

[0004] M.A. Ruiz-Martinez *et al.* in Il Farmaco, 58 (2003) 1289-1294 describe compositions formed by dispersing ethylcellulose with certain polyethylene glycol (PEG) – olivate ester surfactants in olive oil at 100°C. Compositions with varying amounts of ethylcellulose, prepared at different temperatures with different surfactants, were made to find a composition suitable for use in drug delivery. The compositions were determined to be unable to recover structurally following shear stress, i.e., were not thixotropic. More importantly, PEG is a petroleum-based compound, and depending on manufacturing processes, PEGs may be contaminated with measurable amounts of 1,4-dioxane, a possible human carcinogen that doesn't easily degrade. Although 1,4-dioxane can be removed from cosmetics during the manufacturing process by vacuum stripping, there is no easy way for consumers to know whether products containing PEGs have undergone this process. PEGs themselves have also shown some evidence of genotoxicity and, if used on broken skin, can cause irritation and systemic toxicity.

[0005] U.S. Patent No. 5,908,631 describes alcohol-free compositions for topical use in which ethylcellulose is solubilized in a solvent such as a natural oil, a triglyceride, a propylene glycol ester, a neopentyl glycol ester, or a fatty alcohol. Propylene glycol esters are made from propylene and fatty acids. Propylene glycol is produced by hydrochlorination of propylene. Propylene (or Propene) is produced from non-renewable fossil fuels - petroleum, natural gas and, to a much lesser extent, coal. Propene is a byproduct of oil refining and natural gas processing. Ethylene, propene, and other compounds are produced by cracking larger hydrocarbon molecules. Propene is separated by fractional distillation from hydrocarbon mixtures obtained from cracking and other refining processes. Neopentyl glycol (IUPAC name 2,2-dimethyl-1,3-propanediol) is an organic chemical compound. It is used in the synthesis of polyesters, paints, lubricants and plasticizers. Neopentyl glycol is synthesized industrially by the aldol reaction of formaldehyde and isobutyraldehyde. This creates the intermediate hydroxypivaldehyde, which can be converted to neopentyl glycol with either excess formaldehyde or catalytic hydrogenation of the aldehyde group to an alcohol group. Thus, this composition is definitely not hydrocarbon-free.

[0006] In view of the foregoing, it would be desirable to develop a novel non-hydrocarbon-based composition having more desirable rheological properties.

Summary of the Invention

[0007] Novel thixotropic compositions have now been developed comprising ethylcellulose.

5 [0008] In a first aspect, the present invention provides a thixotropic composition comprising ethylcellulose in combination with at least one oil and a surfactant.

[0009] In another aspect, the present invention provides a method of preparing a thixotropic composition comprising:

- 10 a) combining ethylcellulose in an amount ranging from 1-15% by weight with an oil and a surfactant, wherein the weight ratio of surfactant to oil is in the range of about 35:65 to 65:35 oil:surfactant to form a mixture;
- b) heating the mixture until the ethylcellulose is solubilized; and
- c) allowing the mixture to cool to form a thixotropic composition.

15 [0010] In a further aspect, a thixotropic composition is provided comprising ethylcellulose and an oil component, wherein the oil component comprises triacylglycerol oil and a polar acylglycerol oil.

[0011] In another aspect, the present invention provides a method of preparing a thixotropic composition comprising:

- 20 a) combining ethylcellulose in an amount ranging from 1-15% by weight with an oil component comprising a triacylglycerol oil and a polar acylglycerol oil in a weight ratio of triacylglycerol oil:polar acylglycerol oil of about 40:60 to 60:40 (w/w) to form a mixture;
- b) heating the mixture until the ethylcellulose is solubilized; and
- c) allowing the mixture to cool to form a thixotropic composition.

25 [0012] These and other aspects of the invention will become more apparent from the following description in which reference is made to the appended drawings.

Description of the Drawings

[0013] Figure 1 graphically illustrates the effect of varying the glycerol monooleate (GMO):high oleic sunflower oil (HOSO) weight ratio in compositions

comprising 8% ethylcellulose (A) and 5% ethylcellulose (B) on viscosity recovery following shear stress;

[0014] Figure 2 graphically illustrates the viscosity of ethylcellulose compositions comprising 45:55 (w:w) GMO to various oils (A), and viscosity recovery of such compositions following shearing (B);

[0015] Figure 3 graphically illustrates the viscosity of compositions comprising 8% ethylcellulose of different molecular weights in 45:55 (w/w) GMO:HOSO (A), and viscosity recovery of such compositions following shearing (B) as well as compositions including mixtures of ethylcellulose of different molecular weights (C);

[0016] Figure 4 graphically illustrates the viscosity of compositions comprising varying concentrations of ethylcellulose 10cP in 45: 55 (w/w) GMO:HOSO;

[0017] Figure 5 graphically illustrates the viscosity of 8% ethylcellulose 10cP compositions comprising HOSO and various surfactants in a 55:45 (w/w) ratio (A), and viscosity recovery of such compositions following shearing (B);

[0018] Figure 6 graphically illustrates the water vapour barrier properties of an 8% ethylcellulose 10cP composition comprising 45:55 (w/w) GMO:HOSO (A), as well as a comparison of 8% ethylcellulose 10cP compositions comprising 40:60 (w/w) GMO and different oils (B);

[0019] Figure 7 graphically illustrates oil and water absorption of an 8% ethylcellulose 10cP composition comprising 45:55 (w:w) GMO:HOSO;

[0020] Figure 8 graphically illustrates the turbidity in terms of absorbance of surfactant- (A) and castor oil- (B) containing thixotropic compositions;

[0021] Figure 9 graphically illustrates viscosity recovery of ethylcellulose compositions containing castor oil following shearing.

Detailed Description of the Invention

[0022] In a first aspect, a thixotropic composition comprising ethylcellulose in combination with at least one oil and a surfactant is provided.

[0023] The term “thixotropic” as used herein with respect to the present ethylcellulose composition refers to a composition that exhibits a decrease in viscosity from the original equilibrium viscosity when exposed to shear stress, and exhibits viscosity recovery from the decreased post-shear viscosity to the original (e.g. pre-shear) equilibrium viscosity within a finite period of time following cessation of shear stress. In this regard, viscosity recovery refers to at least about 50% recovery to pre-shear equilibrium viscosity, e.g. to at least about 60-80% recovery, preferably to at least about 90%-95% recovery to the original equilibrium viscosity and, more preferably, to recovery of viscosity to essentially the original equilibrium viscosity.

[0024] The physical characteristics of the thixotropic composition of the present invention will generally vary with the amounts and nature of each of the components thereof. Thus, the viscosity of the composition decreases with a decrease in the amount of ethylcellulose and a decrease in the molecular weight of ethylcellulose in the composition. The equilibrium viscosity of the composition is preferably less than about 100 Pa s, for example, a viscosity of about 50 Pa s or less, preferably in the range of about 2-30 Pa s, and more preferably in the range of about 10-30 Pa s, such as a viscosity of 20-25 Pa s. As one of skill in the art will appreciate, the target viscosity will vary with the intended utility of the composition. For example, for use in a lip balm, the viscosity may be about 30-40 Pa s, while for use as a moisturizer, the viscosity may be lower than 30 Pa s, such as 15-25 Pa s. Within the foregoing viscosity ranges, the present thixotropic composition will generally be a paste-like composition.

[0025] The present composition generally comprises from about 1-15% by weight of ethylcellulose, and preferably from about 5-10% by weight ethylcellulose. As one of skill in the art will appreciate, the molecular weight of the ethylcellulose may vary. The greater the molecular weight, the greater the viscosity of the composition. Generally, ethylcellulose 4cp, 10cp, 22cp, 45cp, 100cp, 300cp and mixtures thereof (cp = centipoise, a measure of the viscosity of a 5% solution of ethylcellulose in a toluene-ethanol solution) may be used in the present compositions to achieve a composition having a target equilibrium viscosity of less than about 100 Pa s. Ethylcellulose is a GRAS material (generally regarded as safe) for use in food and cosmetic products, particularly EC 10cp, EC 22cp and EC 45cp. The degree of ethoxylation of ethylcellulose is suitably from about 25% to about 75%, for example from about 40% to

about 60%, by weight, which corresponds to a degree of substitution in the range of about 2.3-2.7, and more preferably a degree of substitution of about 2.5.

[0026] The oil component of the composition may include one or more of a variety of triacylglycerol oils, including, but not limited to, animal, vegetable, fish, yeast and algal triacylglycerol oils, for example, high oleic acid/ low polyunsaturated fatty acid containing oils, for example, vegetable oils, e.g. high-oleic sunflower, high-oleic & high-stearic sunflower oil, high-oleic soybean, high-oleic canola, high-oleic safflower oil, avocado oil and olive oil, and medium and short-chain saturated triglycerides oils such as caprylic-capric triglyceride oils, Neobee oil and coconut oil, soybean oil, canola oil, sunflower oil, safflower oil, corn oil, flaxseed oil, almond oil, peanut oil, pecan oil, cottonseed oil, algal oil, palm oil, palm stearin, palm olein, palm kernel oil, hydrogenated palm kernel oil, hydrogenated palm stearin, fully hydrogenated soybean, canola or cottonseed oils, high stearic sunflower oil, enzymatically and chemically inter-esterified oils, butteroil, cocoa butter, cosmetic oils such as isotridecyl isononate, and mixtures thereof. Preferably, oils utilized in the present composition do not crystallize extensively (e.g. do not form a strong fat crystal network), are liquid at or above 4 °C and are stable against oxidation, e.g. are not susceptible to oxidation when stored at room temperature for a period of at least about 1 month, and preferably for a period of at least about 3 months or more, e.g. for a period of at least about 6 months. Preferred triglyceride oils include mono, di- or tri-unsaturated oils, preferably mono-unsaturated oils such as oleic acid containing oils, and more preferably, high oleic acid-containing oils, e.g. oils that comprise at least about 50% oleic acid, preferably greater than 60% oleic acid, e.g. at least about 70-80% oleic acid, such as vegetable oils, e.g. high-oleic sunflower, high-oleic & high-stearic sunflower oil, high-oleic soy, high-oleic canola, olive, high-oleic safflower oil, sunflower oil, safflower oil, canola oil, avocado oil, as well a medium and short-chain saturated triglycerides oils such as Neobee oil and coconut oil.

[0027] The surfactant component of the composition is a non-ionic surfactant, preferably a mono-unsaturated surfactant, and may include mono-unsaturated surfactant selected from the group consisting of a myristoleate, palmitoleate, oleate and gadoleate. Preferred surfactants for use in the present composition are liquid at room temperature, do not crystallize and are transparent. Examples of suitable surfactants include, but are

not limited to, polyoxyethylene sorbitan monooleate (Tween 80), sorbitan monooleate (SMO or Span 80), glyceryl monooleate (GMO), glyceryl dioleate (GDO), polyglyceryl ester of oleic acid (PGO), polyglyceryl polyoleate (PGPO), polyglyceryl polyricinoleate (PGPR), triglyceryl monooleate (TGMO) and decaglyceryl decaoleate (DGDO).

5 [0028] The surfactant to oil weight ratio in thixotropic compositions according to the invention may be in the range of about 40:60 to 60:40 (w/w) surfactant:oil, and preferably in the range of about 45:55 to 55:45 (w/w) surfactant:oil. The surfactant:oil component comprises the balance of the composition, e.g. about 85-99% by weight of the composition, depending on the amount of ethylcellulose in the composition.

10 [0029] The present composition is prepared by combining ethylcellulose with an oil and a surfactant to form a mixture, and heating the mixture with constant mixing until the ethylcellulose solubilizes, e.g. to a temperature above the glass transition temperature of the ethylcellulose, e.g. above 130 °C, for example, between about 130-160 °C, and typically between about 140° to about 150°C. Once the ethylcellulose has fully
15 dissolved and the mixture appears translucent, it is allowed to cool to form a thickened thixotropic composition. Rapid cooling of the mixture, e.g. no more than about 10 minutes after the clear point has been reached, may result in a more homogeneous and stable gel.

[0030] In another aspect, a thixotropic composition is provided comprising
20 ethylcellulose and an oil component. The oil component comprises at least one triacylglycerol oil and a polar acylglycerol oil. The ethylcellulose component is as described above. The oil component comprises a triacylglycerol oil to polar acylglycerol oil weight ratio in the range of about 40:60 to 60:40 (w/w) triacylglycerol:polar acylglycerol oil, and preferably in the range of about 45:55 to 55:45 (w/w)
25 triacylglycerol:polar acylglycerol oil. Examples of suitable non polar triacylglycerol oils are set out above. The polar acylglycerol oil is an acylglycerol oil in which the fatty acid component thereof includes polar sidegroups, e.g. hydroxyl groups. Examples of suitable polar acylglycerol oils include castor oil.

[0031] The polar acylglycerol oil-containing composition is prepared by
30 combining 1-15% by weight ethylcellulose with the oil component (85-99% by weight) to form a mixture, and heating the mixture with constant mixing until the ethylcellulose

solubilizes, e.g. to a temperature above the glass transition temperature of the ethylcellulose, e.g. above 130 °C, for example, between about 130-160 °C, and typically between about 140° to about 150°C. Once the ethylcellulose has fully dissolved and the mixture appears translucent, it is allowed to cool to form a thickened thixotropic composition.

[0032] The present compositions exhibit unique properties including thixotropic properties and vapour barrier properties that render them appropriate for use in cosmetic applications. The compositions, thus, may be used as creams, lotions, balms and the like to function as a skin protectant against drying, chapping, chafing, aging and the like. In this regard, as one of skill in the art will appreciate, the present compositions may be combined with other compositions, such as creams or lotions, including petrolatum or petrolatum-like products. The present compositions may also be combined with components that alter consistency, e.g. with a wax to harden the composition, such as carnauba wax, beeswax, rice bran wax, sunflower wax, candelilla wax, sugarcane wax and the like.

[0033] The present thixotropic compositions have been found to function as a vapour barrier. In this regard, the compositions prevent less than about 5% weight loss, e.g. less than about 3%, due to moisture loss in a moisture-containing sample when covered with the composition for a given period of time, e.g. several days such as up to about 5 days.

[0034] In addition, the present compositions may be combined with bioactive components, and in particular, lipid-soluble bioactive components to provide the compositions with additional desirable cosmetic or therapeutic properties. Suitable such bioactive components include, but are not to be limited to, antioxidants such as alpha-tocopherol, coenzyme-Q, tocotrienols, phytosterols, lycopene, omega-3 fats, essential oils, fragrances and the like.

[0035] The present compositions may also be utilized in the food industry for inclusion in foods to maintain a desired level of viscosity in a food such as in spreads, margarines, butters (e.g. peanut and other butters), toppings, fillings, desserts, yoghurts, and the like.

[0036] Embodiments of the invention are described by reference to the following specific examples which are not to be construed as limiting.

Example 1 – Ethylcellulose Pastes including Various Oils and Surfactants

[0037] Ethylcellulose pastes were made by combining ethylcellulose (EC) 10 cP with an oil, e.g. high oleic sunflower oil (HOSO), high-oleic canola oil (HOCO), Neobee oil, soy oil, canola oil, flax oil and avocado oil, and a surfactant, e.g. glycerol monooleate (GMO), sorbitan monooleate (SMO), polyglyceryl oleate (PGO), sorbitan monostearate (SMS), decaglyceryl decaoleate (DGDO) and triglyceryl monooleate (TGMO) and Tween 80. The mixture was heated with stirring on a hot plate until the ethylcellulose was solubilized. Solubilization was achieved when the solution appeared translucent. The amount of ethylcellulose added was 5-8% by weight. The balance of the composition was oil and surfactant including varying ratios of oil to surfactant from 0:100 to 100:0 (w/w). These samples were tested for viscosity and viscosity recovery (immediate and 1 week after initial testing) and observed for crystallization, separation, flow, stickiness, oiliness, thickness and turbidity, as well as water barrier and binding properties, as detailed below.

Viscosity Measurement

[0038] An AR 2000 rheometer (TA Instruments) was used for measuring the viscosity of the gels. The gels were prepared as explained above and left to rest at room temperature (RT $\approx 25^{\circ}\text{C}$) for two days prior to testing. Samples were then pre-sheared by hand using a long, flat, rectangular shaped spatula. Pre-shear was 30 rotations in 30 sec with direction of shear reversed after 15 rotations. The sample was then placed on the Pelletier plate of the rheometer. The geometry used for this analysis was a 60 mm diameter, 2° acrylic cone. The cone was lowered into the sample until a gap size of 900 μm was reached. Any excess sample was removed from the outside of the cone. A stress sweep test was then performed at 25°C from shear rate of $20\text{-}200\text{ s}^{-1}$. A second stress sweep step was performed immediately with shear rate from $200\text{-}20\text{ s}^{-1}$. The sample was then removed from the Pelletier plate, placed in a sealed container and stored at room temperature for 1 week. After this period the sample was tested again in the same manner. This procedure was used for all samples unless otherwise indicated.

[0039] The viscosity of the samples was interpreted from the results of the above analyses using Rheology Advantage Data Analysis software from TA Instruments. A power law model (Equation 1 below) was fitted to the data from each individual step (from 20-200 s⁻¹). The consistency coefficient was chosen to represent the viscosity of the sample.

$$\sigma = k \times \dot{\gamma}^n$$

Where σ is the shear stress, k is the consistency coefficient and $\dot{\gamma}$ is the shear rate.

Physical Characteristics

[0040] After testing for viscosity, samples were stored at room temperature and occasionally observed for the following characteristics:

i) Clarity – refers to both the number and size of white crystals as well as any other factor contributing to cloudiness of the sample observed after storage > 1 month

ii) Separation – any signs of liquid separated from the whole (i.e. liquid observed flowing from the top of the gel-like mass when inverted at an angle

iii) Flow – signs of immediate flow of the mass after storage > 1 month when observed inverted at an angle. For separated samples, the flow refers to that of the non-separated layer.

Sensory Analysis

[0041] The following parameters were used by an individual trained in sensory evaluation of cosmetics to analyse the paste samples:

i) Stickiness – the feeling of stickiness as determined by pressing and releasing middle finger to thumb with sample between

ii) Oiliness – feeling of infinite spreadability of sample on skin

iii) Thickness – feeling of thickness as determined by shearing the sample on thumb using middle finger in a circular motion

Water Vapour Barrier Analysis

[0042] The method used for analysing the water vapour barrier properties of the samples was similar to that used by Martini et al. 2006, the contents of which are incorporated herein by reference. Paste samples were prepared as above and left at room temperature for 2 days undisturbed. A mixture of 37.5% silica gel, 3% hydroxypropyl

methyll cellulose, 13.2% saturated solution of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, and 46.3% deionized water was prepared. This original mixture was too liquid-like to use for the analysis therefore silica gel was added until a mixture with very little flow was obtained. About 12 g of this mixture was added to plastic AQUALAB cups (Decagon Devices, Inc., WA) and then placed in the freezer (-20°C) for about 2 hr where it was left to freeze. The paste samples were pre-sheared as in the preparation for viscosity measurements, smeared onto the frozen silica gel cups and evenly smoothed on the top of the cup using a flat spatula. The amount of sample added to the cup was approximately 1.6 g. This process was repeated for petroleum jelly, and oil controls. Cups were also made to represent an uncovered control and completely covered control (with AQUALAB lid in place and parafilm around the seal). Three replicates of each sample were placed on the platform in a sealed dessiccator with a saturated solution of $\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$ in the bottom of the dessiccator to control the humidity in the dessiccator to 32.9%. The dessiccator was placed in an incubator at 20°C and the weight change of the samples was measured occasionally. The following equation (2) was used to determine sample weight loss:

$$\% \text{ weight loss} = \frac{w_i - w_t}{w_s} \times 100\%$$

Where w_i is the total initial weight of the sample (including cup, silica, and paste, if present), w_t is the total weight of the sample at time t and w_s is the weight of the silica mixture in the cup.

Water Binding Analysis

[0043] Approximately 1 g of product made with 60:40 HOSO:GMO and 8% EC 10 cP was pipetted into the bottom of a tall glass vial. The composition was pre-sheared with a flat spatula by hand with 30 rotations in 30 s. The vial was capped and the samples were left in an incubator at 40°C for 2 days to encourage any air bubbles to dissipate. After the two days, approximately 1 mL of water or oil was pipetted on top of the composition. Controls were made to account for water or oil that was not absorbed but could not be easily removed from the vial. The controls were made in the same manner as described above, however, the water or oil was poured off and weighed immediately after being added to the composition, i.e. the composition was not allowed to absorb any water or oil. After addition of water or oil, the samples were placed in an incubator at 25°C for 3 days. The vials were then inverted at an angle for 15 s with shaking to remove the unabsorbed water or oil. The weight of recovered water or oil was

weighed and recorded. The amount of absorbed water or oil was calculated by subtracting the wt% recovered at 3 days from the wt% recovered immediately.

Turbidity Analysis

[0044] Prepared pastes (60:40 HOSO:GMO and 8% EC 10 cP) were heated up to 60-70°C to liquefy, poured into 3mL acrylic cuvettes and allowed to set overnight at room temperature, taking care not to introduce air bubbles in the sample. The turbidity of the gels was then determined by measuring the absorbance of the gel samples in the cuvettes by using a spectrophotometer at a wavelength of 400nm. A high absorbance (low transmittance, high turbidity), e.g. absorbance of greater than ~0.7, depending on the baseline absorbance of the oil used, is due to the incomplete solubilisation of ethylcellulose in the oil mixture and is indicative of phase separation.

Results

Viscosity Measurement

[0045] Figure 1 illustrates viscosity of ethylcellulose pastes having a range of surfactant, e.g. GMO, concentrations. As shown, shearing has the effect of substantially reducing viscosity. This means that the shearing “disrupted” the structure of the pastes, e.g. broke down structure, and the paste appeared more thin or fluid. However, compositions having a GMO concentration of or greater than 40% GMO (of total oil composition) showed recovery of viscosity within 1 week. This means these pastes are time dependent fluids of the thixotropic type – viscosity is lost initially, but then recovers upon standing. Below 40:60 GMO:HOSO, the structure never fully recovers. The mixtures are thus in a gel-state below 40:60 GMO:HOSO and in a reversible, time-dependent state at and above 40:60 GMO:HOSO. The correct terminology would be thixotropic (time-dependent, reversible viscosity loss) at and above 40:60 (GMO:HOSO) and rheodestructive (irreversible viscosity loss) below 40:60 GMO:HOSO. From the data in Fig. 1, a ratio of oil to surfactant in the range of 55:45-45:55 (HOSO:GMO) was preferable. Further experiments were completed using the 55:45 HOSO:GMO ratio only.

[0046] The viscosities of the pastes made with various oils are shown in Fig. 2A. Following shearing as described above, viscosity recovery (e.g. consistency index) was

determined after 1 week and is illustrated in Fig. 2B. The results show viscosity recovery in each case, and viscosity recovery of almost 100% in most cases.

[0047] Pastes were also made with 45:55 GMO:HOSO and 8% ethylcellulose (EC) of various viscosities or molecular weights, e.g. 10cP, 20cP and 45cP. The viscosity of the resulting paste was measured. The results are shown in Fig. 3A. The viscosity recovery of these pastes following shearing was also determined as shown in Figure 3B. Pastes comprising ethylcellulose of varying molecular weight exhibit viscosity recovery. Figure 3C displays viscosity values for pastes made with mixtures of different EC molecular weights, or viscosities, and the viscosity recovery characteristics of these pastes following shearing. For the gray symbols, 8% EC high-oleic sunflower oils gels (55:45 HOSO:GMO) were prepared using 1/3 of each of 10 cP, 20 cP and 45 cP ethylcellulose. The white symbols correspond to an 8% EC high-oleic sunflower oil gel (55:45 HOSO:GMO) prepared using 1/4 of each of 4 cP, 10 cP, 20 cP and 45 cP ethylcellulose. Each of these ethylcellulose combinations also exhibit viscosity recovery. These data demonstrate that a thixotropic paste can be prepared using a single EC molecular weight or a combination of molecular weights. An effective molecular weight can readily be achieved by a simple linear combination of EC of different molecular weights.

[0048] Paste samples were then made with 45:55 GMO:HOSO and various concentrations of EC 10cP. The results are shown in Fig. 4.

[0049] The effect of surfactant type was also studied. Samples were made with a ratio of 45:55 surfactant:HOSO with 8% EC 10cP. The viscosities of the resulting pastes made with GMO, sorbitan monooleate (SMO), or polyglyceryl oleate (PGO) are shown in Fig. 5A. Following shearing as described above, viscosity recovery (e.g. consistency index) was determined after 1 week and is illustrated in Fig. 5B. The results show significant viscosity recovery in each case.

[0050] Samples were also made with sorbitan monostearate (SMS), and Tween 80; however, the viscosity of both of these samples could not be tested using the rheological method described above. The formula which included SMS as the surfactant produced a sample that was solid at room temperature. The sample with Tween 80 was somewhat gel-like but when sheared produced small clumps. These clumps were hard

and the oil was squeezed out of them when the rheological test was attempted. The SMO product was orange in colour.

Physical Characteristics

[0051] The characteristics of sample products were observed as set out in Table 1 below.

5

Table 1.

Sample Description		Characteristics		
	Surfactant:Oil	Clarity	Separation	Flow
5% EC 10cP GMO:HOSO	100:0	Many crystals and cloudy bands	None	Some
	90:10	Many crystals and cloudy	None	Much
	80:20	Some very small crystals on bottom	None	Much
	70:30	Few crystals on bottom	None	Much
	60:40	Few crystals on bottom	None	Much
	50:50	Clear	None	Much
	45:55	Clear	None	Some
	40:60	Clear	None	Little
	30:70	Cloudy	Much	Some
	20:80	Cloudy	Much	Some
	10:90	Cloudy	Much	Some
	0:100	Bottom cloudy, top clear	Much	Much
8% EC 10cP GMO:HOSO	100:0	Many crystals and cloudy bands	None	None
	90:10	Many crystals and cloudy	None	Little
	80:20	Many crystals and cloudy	None	Little
	70:30	Many crystals	None	Little
	60:40	Many small crystals	None	Little
	50:50	Clear; very few crystals	None	Very little
	45:55	Clear	None	Very little
	40:60	Clear	None	None
	30:70	Somewhat cloudy	Much	None
	20:80	Cloudy with bubbles	Much	Some
	10:90	Cloudy	Much	Much
	0:100	Cloudy	Much	Much

8% EC; 45:55 GMO:HOSO	EC 10cP	Clear	None	Very little
	EC 20cP	Clear	None	Very little
	EC 45cP	Clear	None	Very little
EC 10cP 40:60 GMO:HOSO	5% EC	Clear	None	Little
	6% EC	Clear	None	Little
	7% EC	Clear	None	Very little
	8% EC	Clear	None	None
8% EC 10cP 45:55 GMO:Oil	HOSO	Clear	None	Very little
	Soybean	Clear; slight orange tinge	None	Some
	Canola	Clear; slight yellow tinge	None	Very little
	Flax Seed	Some crystals; cloudy; orange	None	Some
	Neobee	Clear; colourless	None	Much
	HOCO	Clear	None	None
	Avocado	Clear; green	None	None
8% EC 10cP 45:55 Surfactant: HOSO	GMO	Clear	None	Very little
	SMO	Very cloudy; dark orange	Some	None
	PGO	Clear	None	Much
	SMS	Opaque; off-white; solid	None	None
	Tween 80	Cloudy; chunky	Much	Some
Vaseline		Cloudy/opaque; slightly yellow	None	None

Sensory Analysis

[0052] Many of the pastes were analysed for thickness, stickiness, and oiliness as described above. Thickness and stickiness were rated on a scale of 0-5 and oiliness was described as either oily or not oily. The results are set out in Table 2 below.

Table 2.

Sample Description			
	Surfactant:Oil	Stickiness	Thickness
8% EC 10cP; GMO:HOSO	100:0	5	5
	90:10	5	4.5
	80:20	4.5	4.5
	70:30	4.5	4.5

	60:40	3.5	2.5-3
	50:50	4	3.5
	45:55	3	3-3.5
	40:60	2.5-3	2.5
	30:70	2.5	2.5
	20:80*	2.0	1.5
	10:90*	0	0.5
	0:100*	0	0
8% EC; 45:55 GMO:HOSO	EC 10cP	3.5	3
	EC 20cP	3.25	2.5
	EC 45cP	3.5	2.5
EC 10cP; 40:60 GMO:HOSO	5% EC*	2	2
	6% EC*	1.5	1
	7% EC	2	1.5
	8% EC	2.5-3	2.5
8% EC 10cP 45:55 GMO:Oil	HOSO	3.5	3
	Soybean	3.5	2.5
	Canola	2.5	2
	Flax Seed	2.5	2.5
	Neobee	2	1.5
	HOCO	3	2.5
	Avocado	4	3.5
Vaseline		2.5	3-3.5
HOSO		0.5	1
GMO		1	1
GMO:HOSO	40:60	0.5	0.5

* Samples felt oily

Water Vapour Barrier Analysis

[0053] A water vapour barrier test was performed as described above. The samples used included a paste made with 8% EC 10cP and HOSO (45:55 GMO:HOSO) (Fig. 6A), as well as a paste made with 8% EC 10cP and either HOSO or avocado oil in a ratio of 40:60 GMO:oil (Fig. 6B). Commercially available Vaseline petroleum jelly

was used as a comparison for the above samples. As can be seen in Fig. 6, each of the samples exhibited less than 3% weight loss at up to 5 days of incubation.

Water Binding Analysis

[0054] Pastes had the ability to bind water and oil to an extent of 3.3% and 4.3% of the water and oil phase added on top of the paste, respectively, as illustrated in Fig. 7.

Turbidity Analysis

[0055] Gels exhibiting an absorbance of greater than about 0.7 were considered to be unstable, with poor clarity and limited stability. Figure 8A demonstrates that the pastes/gels are quite turbid below 40% (w/w) GMO:oil, and that above 45% GMO:oil (w/w), the sample has a minimal turbidity, and hence is clear and homogeneous. This low turbidity or high transparency correlates with surfactant:oil ratios of compositions which exhibit thixotropic properties indicating that maximal EC solubilisation is achieved in thixotropic compositions.

Example 2 – Ethylcellulose Paste with Castor oil

[0056] An ethylcellulose paste (8% EC 10 cP) in HOSO:castor oil was prepared as described in Example 1 with varying amounts of castor oil in HOSO.

[0057] The viscosity of each paste made with various amounts of castor oil is shown in Fig. 9. Following shearing as described above, viscosity recovery (e.g. consistency index) was determined after 1 week and is illustrated in Fig. 9. The results show viscosity recovery in compositions comprising a wide range of castor oil concentrations, with viscosity recovery of at least about 50% evident in samples comprising at least about 40% by wt castor oil, preferably at least about 45% by wt castor oil (55% by wt HOSO) up to about 65% by wt castor oil (35% by wt HOSO).

[0058] Turbidity analysis of this composition was also determined. Figure 8B illustrates that minimum turbidity and maximal transparency and stability are observed at castor oil:HOSO ratios at and above 45:55 (w/w).

[0059] The above embodiments have been described by way of example only. Many other embodiments falling within the scope of the accompanying claims will be apparent to the skilled reader.

CLAIMS

1. A thixotropic composition comprising ethylcellulose in combination with a triacylglycerol oil and a non-ionic surfactant, wherein the ethylcellulose concentration is in the range of about 1-15 wt%.
5
2. The composition of claim 1, wherein the surfactant to oil ratio is in the range of about 40:60 to 60:40 (w/w) surfactant to oil.
10
3. The composition of claim 1, wherein the surfactant to oil ratio is in the range of about 45:55 to 55:45 (w/w) surfactant to oil.
4. The composition as defined in claim 1, wherein the oil is a mono-unsaturated triacylglycerol oil.
15
5. The composition of claim 4, wherein the oil is an oleic acid-containing oil.
6. The composition of claim 1, wherein the oil is selected from the group consisting of high-oleic sunflower, high-oleic & high-stearic sunflower oil, high-oleic soybean, high-oleic canola, high-oleic safflower oil, sunflower oil, safflower oil, soybean oil, algal oil, microbial oil, canola oil, avocado oil, olive oil, medium and short-chain saturated triglyceride oils and mixtures thereof.
20
7. The composition as defined in claim 1, wherein the ethylcellulose has a molecular weight selected from the group consisting of 4cp, 10cp, 22cp, 45cp, 100cp, 300cp and mixtures thereof.
25
8. The composition as defined in claim 1, wherein the surfactant comprises at least one of myristoleate, palmitoleate, oleate and gadoleate.
30
9. The composition as defined in claim 1 wherein the surfactant is selected from the group consisting of polyoxyethylene sorbitan monooleate (Tween 80), sorbitan

monooleate (SMO or Span 80), glyceryl monooleate (GMO), glyceryl dioleate, polyglyceryl ester of oleic acid (PGO), polyglyceryl polyoleate (PGPO) and polyglyceryl polyricinoleate (PGPR).

- 5 10. The composition as defined in claim 9, wherein the surfactant is GMO.
11. The composition of claim 1, wherein the ethylcellulose concentration is about 5-10%.
- 10 12. A method of preparing a thixotropic composition comprising:
- a) combining ethylcellulose in an amount ranging from 1-15% with a triacylglycerol oil and a non-ionic surfactant, wherein the ratio of surfactant to oil is in the range of about 40:60 to 60:40 (w/w) to form a mixture;
- b) heating the mixture until the ethylcellulose is solubilized; and
- 15 c) allowing the mixture to cool to form a thixotropic composition.
13. The method of claim 12, wherein the surfactant to oil ratio is in the range of about 45:55 to 55:45 (w/w) surfactant to oil.
- 20 14. The method as defined in claim 12, wherein the oil is a mono-unsaturated triacylglycerol oil.
15. The method of claim 14, wherein the oil is an oleic acid-containing oil.
- 25 16. The method of claim 14, wherein the oil is selected from the group consisting of high-oleic sunflower, high-oleic & high-stearic sunflower oil, high-oleic soybean, high-oleic canola, high-oleic safflower oil, canola oil, avocado oil, olive oil, sunflower oil, safflower oil, soybean oil, algal oil, microbial oil, medium and short-chain saturated triglyceride oils and mixtures thereof.
- 30 17. The method as defined in claim 12, wherein the surfactant is selected from the group consisting of polyoxyethylene sorbitan monooleate (Tween 80), sorbitan monooleate (SMO or Span 80), glyceryl monooleate (GMO), glyceryl dioleate (DGO),

polyglyceryl ester of oleic acid (PGO), polyglyceryl polyoleate (PGPO) and polyglyceryl polyricinoleate (PGPR).

5 18. A thixotropic composition comprising ethylcellulose and an oil component, wherein the oil component comprises a triacylglycerol oil and a polar acylglycerol oil and the amount of ethylcellulose in the composition is in the range of about 1-15 wt%.

10 19. The composition as defined in claim 18, wherein the amount of ethylcellulose in the composition is in the range of about 5-10 wt%, the oil component is present in a weight ratio of triacylglycerol oil:polar acylglycerol oil of about 40:60 to 60:40 (w/w), the triacylglycerol oil is an oleic acid-containing oil and the polar acylglycerol oil is castor oil.

15 20. A method of preparing a thixotropic composition as defined in claim 18 comprising:

- a) combining ethylcellulose in an amount ranging from 1-15% by weight with an oil component comprising triacylglycerol oil and a polar acylglycerol oil in a weight ratio of triacylglycerol oil:polar acylglycerol oil of about 40:60 to 60:40 (w/w) to form a mixture;
- 20 b) heating the mixture until the ethylcellulose is solubilized; and
- c) allowing the mixture to cool to form a thixotropic composition.