



- (51) International Patent Classification:
C08J 5/18 (2006.01) *C08L 23/08* (2006.01)
- (21) International Application Number:
PCT/US2013/068785
- (22) International Filing Date:
6 November 2013 (06.11.2013)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/723,335 7 November 2012 (07.11.2012) US
- (72) Inventors; and
- (71) Applicants : **MCDANIEL, Max, P.** [US/US]; 1601 Melmart Drive, Bartlesville, OK 74006 (US). **SUKHADIA, Ashish, M.** [US/US]; 2550 SE Regency Road, Bartlesville, OK 74006 (US). **DING, Errun** [US/US]; 5906 Woodland Road, Bartlesville, OK 74006 (US). **TSO, Chung, Ching** [US/US]; 5641 Chestnut Hill, Bartlesville, OK 74006 (US). **MASINO, Albert, P.** [US/US]; 8628 S. Oswego Avenue, Tulsa, OK 74137 (US). **YANG, Qing** [CN/US]; 2917 Montrose Drive, Bartlesville, OK 74006 (US). **GUATNEY, Lloyd, W.** [US/US]; 2475 E. Mountain Road, Bartlesville, OK 74003 (US). **ST. JEAN, Guylaine** [US/US]; 2557 Georgetown Drive, Bartlesville, OK 74006 (US). **HERT, Daniel, G.** [US/US]; 8185 N. 72nd E. Avenue, Owasso, OK 74055 (US).
- (74) Agent: **KOWALCHYK, Katherine, M.**; Merchant & Gould P.C., P.O. Box 2903, Minneapolis, MN 55402-0903 (US).
- (81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report (Art. 21(3))

(54) Title: LOW DENSITY POLYOLEFIN RESINS AD FILMS MADE THEREFROM

(57) Abstract: Disclosed herein are broad molecular weight distribution olefin polymers having densities in the 0.895 to 0.930 g/cm³ range, and with improved impact and tear resistance. These polymers can have a ratio of Mw/Mn in the 8 to 35 range, a high load melt index in the 4 to 50 range, less than about 0.008 LCB per 1000 total carbon atoms, and a reverse comonomer distribution.

