

EMM-25 MOLECULAR SIEVE MATERIAL, ITS SYNTHESIS AND USE

FIELD OF THE INVENTION

[0001] This invention relates to a novel molecular sieve material, designated EMM-25, its synthesis, and its use as an adsorbent and/or a hydrocarbon conversion catalyst.

BACKGROUND OF THE INVENTION

[0002] Molecular sieve materials, both natural and synthetic, have been demonstrated in the past to be useful as adsorbents and to have catalytic properties for various types of hydrocarbon conversion reactions. Certain molecular sieves, such as zeolites, AlPOs, and mesoporous materials, are ordered, porous crystalline materials having a definite crystalline structure as determined by X-ray diffraction (XRD). Within the crystalline molecular sieve material there are a large number of cavities which may be interconnected by a number of channels or pores. These cavities and pores are uniform in size within a specific molecular sieve material. Because the dimensions of these pores are such as to accept for adsorption molecules of certain dimensions while rejecting those of larger dimensions, these materials have come to be known as "molecular sieves" and are utilized in a variety of industrial processes.

[0003] Such molecular sieves, both natural and synthetic, include a wide variety of positive ion-containing crystalline silicates. These silicates can be described as rigid three-dimensional framework of SiO_4 and Periodic Table Group 13 element oxide (*e.g.*, AlO_4). The tetrahedra are cross-linked by the sharing of oxygen atoms with the electrovalence of the tetrahedra containing the Group 13 element (*e.g.*, aluminum or boron) being balanced by the inclusion in the crystal of a cation, for example a proton, an alkali metal or an alkaline earth metal cation. This can be expressed wherein the ratio of the Group 13 element (*e.g.*, aluminum or boron) to the number of various cations, such as H^+ , $\text{Ca}^{2+}/2$, $\text{Sr}^{2+}/2$, Na^+ , K^+ , or Li^+ , is equal to unity.

[0004] Molecular sieves that find application in catalysis include any of the naturally occurring or synthetic crystalline molecular sieves. Examples of these molecular sieves include large pore zeolites, intermediate pore size zeolites, and small pore zeolites. These zeolites and their isotypes are described in "Atlas of Zeolite Framework Types", eds. Ch. Baerlocher, L.B. McCusker, D.H. Olson, Elsevier, Sixth Revised Edition, 2007, which is hereby incorporated by reference. A large pore zeolite generally has a pore size of at least about 6.5 to 7 Angstroms and includes LTL, MAZ, FAU, OFF, *BEA, and MOR framework type zeolites (IUPAC

Commission of Zeolite Nomenclature). Examples of large pore zeolites include mazzite, offretite, zeolite L, zeolite Y, zeolite X, omega, and beta. An intermediate pore size zeolite generally has a pore size from about 4.5 Angstroms to less than about 7 Angstroms and includes, for example, MFI, MEL, EUO, MTT, MFS, AEL, AFO, HEU, FER, MWW, and TON framework type zeolites (IUPAC Commission of Zeolite Nomenclature). Examples of intermediate pore size zeolites include ZSM-5, ZSM-11, ZSM-22, MCM-22, silicalite 1, and silicalite 2. A small pore size zeolite has a pore size from about 3 Angstroms to less than about 5.0 Angstroms and includes, for example, CHA, ERI, KFI, LEV, SOD, and LTA framework type zeolites (IUPAC Commission of Zeolite Nomenclature). Examples of small pore zeolites include ZK-4, SAPO-34, SAPO-35, ZK-14, SAPO-42, ZK-21, ZK-22, ZK-5, ZK-20, zeolite A, chabazite, zeolite T, and ALPO-17.

[0005] According to the present invention, a new zeolite structure, designated EMM-25, has now been synthesized using at least one of the following four organic templates: N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium, N, N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium, N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium, and mixtures thereof.

SUMMARY OF THE INVENTION

[0006] In one aspect, the invention relates to a molecular sieve material having, in its as-calcined form, an X-ray diffraction pattern including the following peaks in Table 1:

Table 1

d-spacing (Å)	Relative Intensity [100 x I/I(o)]%
11.74-11.34	60-100
9.50-9.10	30-80
8.68-8.28	10-40
5.64-5.44	20-60
4.52-4.42	10-50
4.28-4.18	10-40
3.96-3.86	40-80
3.69-3.59	30-70

[0007] In another aspect, the invention relates to a molecular sieve having a framework defined by the following connectivities for the tetrahedral (T) atoms in the unit cell in Table 2, the tetrahedral atoms (T) being connected by bridging atoms:

Table 2

T atom	Connected to:
T1	T3, T4, T33, T71
T2	T5, T48, T72, T82
T3	T1, T31, T47, T97
T4	T1, T5, T81, T106
T5	T2, T4, T55, T75
T6	T8, T9, T38, T76
T7	T10, T43, T77, T84
T8	T6, T36, T42, T98
T9	T6, T10, T83, T105
T10	T7, T9, T60, T80
T11	T13, T14, T23, T61
T12	T15, T58, T62, T86
T13	T11, T21, T57, T99
T14	T11, T15, T85, T108
T15	T12, T14, T45, T65
T16	T18, T19, T28, T66
T17	T20, T53, T67, T88
T18	T16, T26, T52, T100
T19	T16, T20, T87, T107
T20	T17, T19, T50, T70
T21	T13, T23, T24, T51
T22	T25, T52, T68, T90
T23	T11, T21, T67, T101
T24	T21, T25, T89, T110
T25	T22, T24, T55, T75
T26	T18, T28, T29, T56
T27	T30, T57, T63, T92
T28	T16, T26, T62, T102
T29	T26, T30, T91, T109
T30	T27, T29, T60, T80
T31	T3, T33, T34, T41
T32	T35, T42, T78, T94
T33	T1, T31, T77, T103
T34	T31, T35, T93, T112
T35	T32, T34, T45, T65
T36	T8, T38, T39, T46
T37	T40, T47, T73, T96
T38	T6, T36, T72, T104
T39	T36, T40, T95, T111
T40	T37, T39, T50, T70
T41	T31, T43, T44, T73
T42	T8, T32, T45, T86
T43	T7, T41, T71, T103
T44	T41, T45, T85, T112

T45	T15, T35, T42, T44
T46	T36, T48, T49, T78
T47	T3, T37, T50, T88
T48	T2, T46, T76, T104
T49	T46, T50, T87, T111
T50	T20, T40, T47, T49
T51	T21, T53, T54, T63
T52	T18, T22, T55, T82
T53	T17, T51, T61, T101
T54	T51, T55, T81, T110
T55	T5, T25, T52, T54
T56	T26, T58, T59, T68
T57	T13, T27, T60, T84
T58	T12, T56, T66, T102
T59	T56, T60, T83, T109
T60	T10, T30, T57, T59
T61	T11, T53, T63, T64
T62	T12, T28, T65, T94
T63	T27, T51, T61, T99
T64	T61, T65, T93, T108
T65	T15, T35, T62, T64
T66	T16, T58, T68, T69
T67	T17, T23, T70, T96
T68	T22, T56, T66, T100
T69	T66, T70, T95, T107
T70	T20, T40, T67, T69
T71	T1, T43, T73, T74
T72	T2, T38, T75, T90
T73	T37, T41, T71, T97
T74	T71, T75, T89, T106
T75	T5, T25, T72, T74
T76	T6, T48, T78, T79
T77	T7, T33, T80, T92
T78	T32, T46, T76, T98
T79	T76, T80, T91, T105
T80	T10, T30, T77, T79
T81	T4, T54, T89, T92
T82	T2, T52, T91, T113
T83	T9, T59, T90, T91
T84	T7, T57, T89, T114
T85	T14, T44, T93, T96
T86	T12, T42, T95, T115
T87	T19, T49, T94, T95
T88	T17, T47, T93, T116
T89	T24, T74, T81, T84
T90	T22, T72, T83, T113
T91	T29, T79, T82, T83

T92	T27, T77, T81, T114
T93	T34, T64, T85, T88
T94	T32, T62, T87, T115
T95	T39, T69, T86, T87
T96	T37, T67, T85, T116
T97	T3, T73, T103, T112
T98	T8, T78, T104, T111
T99	T13, T63, T101, T110
T100	T18, T68, T102, T109
T101	T23, T53, T99, T108
T102	T28, T58, T100, T107
T103	T33, T43, T97, T106
T104	T38, T48, T98, T105
T105	T9, T79, T104, T113
T106	T4, T74, T103, T114
T107	T19, T69, T102, T115
T108	T14, T64, T101, T116
T109	T29, T59, T100, T113
T110	T24, T54, T99, T114
T111	T39, T49, T98, T115
T112	T34, T44, T97, T116
T113	T82, T90, T105, T109
T114	T84, T92, T106, T110
T115	T86, T94, T107, T111
T116	T88, T96, T108, T112

[0008] Conveniently, the molecular sieve material can have a composition comprising the molar relationship: $X_2O_3:(n)YO_2$; wherein n can be at least 10, X can be a trivalent element, such as one or more of B, Al, Fe, and Ga (especially containing or being B), and Y can be a tetravalent element, such as one or more of Si, Ge, Sn, Ti, and Zr (especially containing or being Si).

[0009] In another aspect, the invention relates to a molecular sieve material having, in its as-synthesized form, an X-ray diffraction pattern including the following peaks in Table 3:

Table 3

d-spacing (Å)	Relative Intensity [100 x I/I(o)]%
11.77-11.37	30-80
9.51-9.11	20-70
8.67-8.27	5-30
5.64-5.44	10-40
4.50-4.40	30-80
4.28-4.18	30-80
3.95-3.85	60-100
3.70-3.60	50-90

[0010] Conveniently, the molecular sieve material can have a composition comprising the molar relationship: $mQ:(n)YO_2:X_2O_3$; wherein $0.004 < m/n \leq 0.04$, n can be at least 10, Q can be an organic structure directing agent, X can be a trivalent element, and Y can be a tetravalent element.

[0011] In embodiments, X may be one or more of B, Al, Fe, Ga, and Al; and Y may be one or more of Si, Ge, Sn, Ti, and Zr.

[0012] Conveniently, Q can comprise a cation of the formula:



wherein R_1 and R_2 can be chosen independently from butyl, pentyl, and hexyl.

[0013] Optionally, Q can comprise or be a cation selected from the group consisting of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium (C_4 diquat of dihexylmethylamine), N,N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium (C_4 diquat of hexylpentylmethylamine), N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium (C_4 diquat of dipentylmethylamine), N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium (C_4 diquat of pentylbutylmethylamine), and mixtures thereof.

[0014] In a further aspect, the invention relates to a process for producing the molecular sieve material as described herein, the process comprising: (i) preparing a synthesis mixture capable of forming said material, said mixture comprising water, a source of hydroxide ions, a source of an oxide of a tetravalent element Y, a source of a trivalent element X, optionally a source of halide ions Z^- , optionally a source of alkali metal ions M^+ , and a structure directing agent Q selected from the group consisting of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N'-dipentyl-

N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium cations, and mixtures thereof, and said synthesis mixture having a composition, in terms of mole ratios, in the following amounts and/or ranges:


$\text{YO}_2/\text{X}_2\text{O}_3$	at least 2;
$\text{H}_2\text{O}/\text{YO}_2$	5 to 60;
OH^-/YO_2	0.01 to 1;
Z^-/YO_2	0 to 0.30;
M^+/YO_2	0 to 0.40; and
Q/YO_2	0.03 to 1.0;

(ii) heating said synthesis mixture under crystallization conditions including a temperature of from about 100°C to about 200°C and a time from about 1 to about 100 days until crystals of said material are formed; and (iii) recovering said crystalline material from said synthesis mixture.

[0015] Preferably, M^+ can include or be a sodium and/or potassium ion. When Z^- is present, Z^- can advantageously include or be chloride ions.

[0016] Optionally, Q can be selected from N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium cations, and mixtures thereof. The structures of those cations are shown below.

N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium



N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium

[0017] In another aspect, the invention relates to a process of converting a feedstock comprising an organic compound to a conversion product which comprises contacting said feedstock at organic compound conversion conditions with a catalyst comprising an active form of the molecular sieve material as described herein.

BRIEF DESCRIPTION OF THE DRAWINGS

[0018] Figure 1 shows the X-ray diffraction pattern of the synthesized zeolite of Example 1.

[0019] Figure 2 shows the X-ray diffraction pattern of samples of the zeolite of Example 2 taken from the synthesis mixture: line a) ~17 days, line b) ~31 days, line c) ~38 days, line d) ~45 days, and line e) ~52 days.

[0020] Figure 3 shows Scanning Electron Microscopy (SEM) images of the zeolite of Example 2 taken from the synthesis mixture at ~38 days.

[0021] Figure 4 shows the X-ray diffraction pattern of samples of the zeolite of Example 6 taken from the synthesis mixture at different times: line a) ~25 days, line b) ~35 days, and line c) ~49 days.

[0022] Figure 5 shows the X-ray diffraction pattern of samples of the zeolite of Example 7 taken from the synthesis mixture at different times: line a) ~16 days, line b) ~23 days, and line c) ~27 days.

[0023] Figure 6 shows the X-ray diffraction pattern of samples of the zeolite of Example 8 taken from the synthesis mixture at different times: line a) ~7 days, line b) ~14 days, and line c) ~21 days.

[0024] Figure 7 shows the X-ray diffraction pattern of samples of the zeolite of Example 9 taken from the synthesis mixture at different times: line a) ~7 days, line b) ~21 days, line c) ~24 days, and line d) ~28 days.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0025] Described herein is a novel molecular sieve material, designated EMM-25, its synthesis in the presence of a structure directing agent, and its use, *e.g.*, as an adsorbent and a catalyst for organic conversion reactions.

[0026] The novel molecular sieve material EMM-25 can be characterized by an X-ray diffraction pattern which, in its as-calcined form of the molecular sieve, can include at least the peaks shown below in Table 1 above and, in its as-synthesized form, can include at least the peaks shown in Table 3 above.

[0027] Optionally, the calcined form of the molecular sieve can have an XRD pattern including the additional peaks shown in Table 4 below.

Table 4

d-spacing (Å)	Relative Intensity [100 x I/I(o)] %
12.70-12.30	10-50
6.20-6.10	1-30
3.85-3.77	1-30

[0028] Optionally, the as-made form of the molecular sieve can have an XRD pattern including the additional peaks shown in Table 5 below.

Table 5

d-spacing (Å)	Relative Intensity [100 x I/I(o)] %
12.65-12.25	1-30
6.42-6.22	1-20
4.04-3.96	10-50
3.84-3.78	10-50

[0029] The EMM-25 may additionally or alternately be characterized, in its calcined form, by the framework defined by the connectivities of the tetrahedral (T) atoms shown in Table 2 above. Optionally, the tetrahedral atoms can include one or more elements selected from the group consisting of Li, Be, Al, P, Si, Ga, Ge, Zn, Cr, Mg, Fe, Co, Ni, Mn, As, In, Sn, Sb, Ti, and Zr (*e.g.*, selected from the group consisting of Si, Ge, Sn, Ti, and Zr). Optionally, the bridging atoms include one or more elements selected from the group consisting of O, N, F, S, Se, and C. In such embodiments, the bridging atoms can preferably predominantly be oxygen atoms (*e.g.*, at least 90% of the bridging atoms may be oxygen).

[0030] Optionally, the molecular sieve of the invention can be a borosilicate.

[0031] The X-ray diffraction data reported herein were collected with a PANalytical X-Pert Pro diffraction system, equipped with an X'Celerator detector, using copper K-alpha radiation and a fixed ~0.25 degrees divergence slit. The diffraction data were recorded by step-scanning at ~0.017 degrees of two-theta, where theta is the Bragg angle, and a counting time of about 2 seconds for each step. The interplanar (d-) spacings were calculated in Angstrom units, and the relative peak area intensities, $I/I_{(0)}$, of the peaks were determined using the MDI Jade peak profile fitting algorithm to approximately one-hundredth of the intensity of the strongest peak (above background). The peak intensities were uncorrected for Lorentz and polarization effects.

It should be understood that diffraction data listed for each sample as a single peak may contain multiple overlapping peaks that, under certain conditions (such as differences in crystallographic changes), may appear as resolved (single local maximum) or partially resolved peaks. Typically, such conditions (*e.g.*, crystallographic changes) can include minor changes in unit cell parameters and/or a change in crystal symmetry, without a corresponding change in the structure. These minor effects, including changes in relative intensities, can additionally or alternately occur as a result of differences in cation content, framework composition, nature and degree of pore filling, crystal size and shape, preferred orientation, thermal and/or hydrothermal history, or the like, or combinations thereof.

[0032] The molecular sieve material (EMM-25), in its calcined form, can have a chemical composition having the following molar relationship: $X_2O_3:(n)YO_2$; wherein n can be at least about 10 (such as from about 10 to about 200), X can be a trivalent element (such as one or more of B, Al, Fe, and Ga), and Y can be a tetravalent element (such as one or more of Si, Ge, Sn, Ti, and Zr). In one preferred embodiment, X can comprise or be B, and Y can comprise or be Si.

[0033] In its as-synthesized form, molecular sieve (EMM-25) can have a chemical composition having the following molar relationship: $mQ:(n)YO_2: X_2O_3$; wherein $0.004 < m/n \leq 0.04$, n can be at least 10, Q can be an organic structure directing agent, X can be a trivalent element (such as one or more of B, Al, Fe, and Ga), and Y can be a tetravalent element (such as one or more of Si, Ge, Sn, Ti, and Zr). Optionally, as in the calcined form, X can comprise or be B, and Y can comprise or be Si.

[0034] Suitable examples of the organic structure directing agent Q can include, but are not necessarily limited to, cations such as N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium, N,N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium, N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium, and mixtures thereof.

[0035] The Q component, which is typically associated with the as-synthesized form of molecular sieve EMM-25 as a result of its presence during crystallization, may be easily decomposed/removed by conventional post-crystallization methods, such as calcination.

[0036] The molecular sieve material EMM-25 can advantageously represent a thermally stable zeolite with a unique XRD pattern.

[0037] EMM-25 can be prepared from a synthesis mixture comprising water, a source of hydroxide ions, a source of an oxide of a tetravalent element Y, a source of a trivalent element X, optionally a source of halide ions Z^- , optionally a source of alkali metal ions M^+ , such as sodium or potassium ions, and a directing agent Q described above. The synthesis mixture may have a composition, in terms of mole ratios of oxides, within the following amounts and/or ranges:

<u>Reactants</u>	<u>Useful</u>	<u>Preferred</u>
YO_2/X_2O_3	at least 1	2 to 14
H_2O/YO_2	5 to 60	15 to 40
OH/YO_2	0.01 to 1.0	0.10 to 0.60
Q/YO_2	0.03 to 1.0	0.10 to 0.25
Z/YO_2	0 to 0.30	0 to 0.20
M^+/YO_2	0 to 0.4	0 to 0.10


[0038] In a preferred embodiment where Z^- is present, Z^- can comprise or be Cl^- .

Additionally or alternately, in a preferred embodiment where M^+ is present, M^+ can comprise or be Na^+ and/or K^+ .

[0039] Suitable sources of tetravalent element Y can depend on the element Y that is selected (*e.g.*, silicon, germanium, strontium, titanium and zirconium). In embodiments where Y is silicon, suitable sources of silicon include colloidal suspensions of silica, precipitated silica alkali metal silicates, tetraalkyl orthosilicates, and fumed silicas. In embodiments where Y is germanium, germanium oxide may be used as an oxide source.

[0040] If present, suitable sources of trivalent element X depend on the element X that is selected (*e.g.*, boron, aluminum, iron and gallium). In embodiments where X is boron, sources of boron include boric acid, sodium tetraborate and potassium tetraborate.

[0041] Q can preferably comprise or be a cation of the formula:



wherein R_1 and R_2 can be chosen independently from butyl, pentyl and hexyl.

[0042] Nevertheless, suitable sources of the directing agent Q can include, but are not necessarily limited to, the hydroxides and/or salts of the relevant quaternary ammonium compounds. N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium compounds can be readily synthesized, *e.g.*, by the reaction of dihexylmethylamine with a 1,4-dihalobutane (such as 1,4-diiodobutane or 1,4-dibromobutane). N,N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-

diammonium compounds can be readily synthesized, *e.g.*, by the reaction of hexylpentylmethylamine with a 1,4-dihalobutane (such as 1,4-diiodobutane or 1,4-dibromobutane). N,N,N',N'-tetrapentyl- N',N'-dimethylbutane-1,4-diammonium compounds can be readily synthesised, *e.g.*, by the reaction of dipentylmethylamine with a 1,4-dihalobutane (such as 1,4-diiodobutane or 1,4-dibromobutane). N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium compounds can be readily synthesized, *e.g.*, by the reaction of pentylbutylmethylamine with a 1,4-dihalobutane (such as 1,4-diiodobutane or 1,4-dibromobutane).

[0043] Crystallization of EMM-25 can be carried out at either static or stirred conditions in a suitable reactor vessel, *e.g.*, a polypropylene jar or a TeflonTM-lined or stainless steel autoclave, at a temperature from about 100°C to about 200°C (such as from about 150°C to about 170°C) for a time sufficient for crystallization to occur at the temperature used (*e.g.*, from about 1 day to about 100 days, from about 1 day to about 50 days, or from about 2 days to about 20 days). Thereafter, the synthesized crystals can be separated from the liquid and advantageously recovered.

[0044] The synthesis may be aided by seeds from a previous synthesis of EMM-25, with the seeds, when present, suitably comprising an amount from about 0.01 ppm by weight to about 10000 ppm by weight, *e.g.*, from about 100 ppm by weight to about 5000 ppm by weight, of the synthesis mixture.

[0045] To the extent desired and depending on the X_2O_3/YO_2 molar ratio of the material, any cations in the as-synthesized EMM-25 can be replaced in accordance with techniques well known in the art by ion exchange with other cations. When utilized, preferred replacing cations can include metal ions, hydrogen ions, hydrogen precursor (*e.g.*, ammonium) ions, and mixtures thereof. When utilized, particularly preferred cations can include those that can tailor the catalytic activity for certain hydrocarbon conversion reactions, such as hydrogen, rare earth metals, and metals of Groups 2 to 15 of the Periodic Table of the Elements. As used herein, the numbering scheme for the Periodic Table Groups is as disclosed in Chemical and Engineering News, 63(5), 27 (1985).

[0046] The molecular sieve described herein may be subjected to treatment to remove a portion of or the entire amount of organic directing agent Q used in its synthesis. This can be conveniently done by thermal treatment (calcination), *e.g.*, by heating the as-synthesized material

to a temperature of at least about 370°C for at least 1 minute (and generally not longer than 20 hours). While subatmospheric pressure can be employed for the thermal treatment, atmospheric pressure can typically be desired for reasons of convenience. The thermal treatment can be performed at a temperature up to about 1000°C, *e.g.*, up to about 925°C. The thermally treated product, especially in its metal, hydrogen, and/or ammonium forms, can be particularly useful in the catalysis of certain organic, *e.g.*, hydrocarbon, conversion reactions.

[0047] The molecular sieve described herein may be intimately combined with a hydrogenating component, such as molybdenum, rhenium, nickel, cobalt, chromium, manganese, or with a noble metal (such as platinum and/or palladium) where a hydrogenation-dehydrogenation function may be desired. Such component can be present in the composition by way of co-crystallization, by being exchanged into the composition (to the extent a Group 13 element, *e.g.*, aluminum, is in the structure), by impregnation therein, by being intimately physically admixed therewith, or the like, or some combination thereof. Such component can be impregnated into/onto the molecular sieve, for example, in the case of platinum, by treating the silicate with a solution containing a platinum metal-containing ion. Thus, suitable platinum compounds for this purpose can include, but are not necessarily limited to, chloroplatinic acid, platinous chloride, various compounds containing the platinum amine complex, or mixtures/combinations thereof.

[0048] The molecular sieve of the present disclosure, when employed either as an adsorbent or as a catalyst, can advantageously be at least partially (or substantially) dehydrated, *e.g.*, by heating to a temperature from about 100°C to about 500°C (such as from about 200°C to about 370°C) in an atmosphere (such as containing air, nitrogen, etc.) at atmospheric, subatmospheric, or superatmospheric pressures for an appropriate time, *e.g.*, between about 30 minutes and about 48 hours. Dehydration can additionally or alternately be performed at room temperature (~20-25°C), *e.g.*, merely by placing the EMM-25 under vacuum (*e.g.*, 0.01 torr or less), but a longer time may be required to sufficiently dehydrate.

[0049] The molecular sieve of the present disclosure may be used as an adsorbent or, particularly in its borosilicate form, as a catalyst for a wide variety of organic compound conversion processes, including many of present commercial/industrial importance. Examples of chemical conversion processes which can be effectively catalyzed by the crystalline material of this invention, by itself or in combination with one or more other catalytically active substances

(including other crystalline catalysts), can include those requiring a catalyst with acid activity. Examples of organic conversion processes that may be catalyzed by EMM-25 can include, but are not necessarily limited to, (hydro)cracking, disproportionation, alkylation, isomerization/dewaxing, and the like, and combinations thereof.

[0050] As in the case of many catalysts, it may be desirable to incorporate EMM-25 with another component resistant to the temperatures and other conditions employed in organic conversion processes. Such components can include active and inactive materials and synthetic or naturally occurring zeolites, as well as inorganic materials such as clays, silica, and/or metal oxides such as alumina. The latter may be either naturally occurring or in the form of gelatinous precipitates or gels including mixtures of silica and other metal oxides. Use of a material in conjunction with EMM-25 (*i.e.*, combined therewith or present during synthesis of the crystalline material, which can be in its active state) can tend to change the level of conversion and/or selectivity of the catalyst in certain organic conversion processes. Inactive materials can suitably serve as diluents, *e.g.*, to control the amount of conversion in a given process, so that products can be obtained in an economic and orderly manner, such as without employing other means for controlling the rate of reaction. These materials may be incorporated into naturally occurring clays, *e.g.*, bentonite and/or kaolin, to improve the crush strength of the catalyst under commercial operating conditions. Said materials, *i.e.*, clays, oxides, etc., can function as binders for the catalyst. It can be desirable to provide a catalyst having good crush strength, because, in commercial use, it can be desirable to prevent/limit the catalyst from breaking down into powder-like materials (fines). These clay and/or oxide binders can be employed, *e.g.*, solely to improve the crush strength of the catalyst.

[0051] Naturally occurring clays that can be composited with EMM-25 can include the montmorillonite and kaolin families, which families include the subbentonites, and the kaolins commonly known as Dixie, McNamee, Georgia and Florida clays, as well as others in which the main mineral constituent is halloysite, kaolinite, dickite, nacrite, or anauxite. Such clays can be used in the raw state (as originally mined) and/or initially subjected to calcination, acid treatment, and/or chemical modification. Binders useful for compositing with EMM-25 can additionally or alternately include inorganic oxides, such as silica, zirconia, titania, magnesia, beryllia, alumina, and mixtures thereof.

[0052] Additionally or alternatively to the foregoing materials, as desired, EMM-25 can be composited with a porous matrix material, such as silica-alumina, silica-magnesia, silica-zirconia, silica-thoria, silica-beryllia, silica-titania, as well as ternary compositions such as silica-alumina-thoria, silica-alumina-zirconia, silica-alumina-magnesia, silica-magnesia-zirconia, and mixtures or combinations thereof.

[0053] The relative proportions of EMM-25 and inorganic oxide matrix may vary widely, with the EMM-25 content typically ranging from about 1 wt% to about 90 wt%, or, particularly when the composite is prepared in the form of beads, from about 2 wt% to about 80 wt%, based on the total composite weight.

[0054] The invention can additionally or alternately include one or more of the following embodiments.

[0055] Embodiment 1. A molecular sieve material having, in its calcined form, an X-ray diffraction pattern including the peaks listed in Table 1.

[0056] Embodiment 2. A molecular sieve material having a framework defined by the connectivities for the tetrahedral (T) atoms in the unit cell listed in Table 2, the tetrahedral (T) atoms being connected by bridging atoms.

[0057] Embodiment 3. The molecular sieve material of embodiment 1 or embodiment 2, having a composition comprising the molar relationship: $(n)YO_2:X_2O_3$, wherein n is at least 10, X is a trivalent element (*e.g.*, comprising one or more of B, Al, Fe, and Ga, such as comprising or being B), and Y is a tetravalent element (*e.g.*, comprising one or more of Si, Ge, Sn, Ti, and Zr, such as comprising or being Si).

[0058] Embodiment 4. The molecular sieve material of embodiment 3, further comprising a noble metal and/or a salt of a noble metal.

[0059] Embodiment 5. A molecular sieve material having, in its as-synthesized form, an X-ray diffraction pattern including the peaks listed in Table 3.

[0060] Embodiment 6. The molecular sieve material of embodiment 5, having a composition comprising the molar relationship: $mQ:(n)YO_2:X_2O_3$, wherein $0.004 < m/n \leq 0.04$, n is at least 10, Q is an organic structure directing agent, X is a trivalent element (*e.g.*, comprising one or more of B, Al, Fe, and Ga, such as comprising or being B), and Y is a tetravalent element (*e.g.*, comprising one or more of Si, Ge, Sn, Ti, and Zr, such as comprising or being Si).

[0061] Embodiment 7. The molecular sieve material of embodiment 6, wherein Q is a cation of the formula: $R_1R_2(CH_3)N^+CH_2CH_2CH_2CH_2N^+(CH_3)R_1R_2$, wherein R_1 and R_2 are chosen independently from butyl, pentyl, and hexyl (*e.g.*, wherein Q is a cation selected from the group consisting of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium, N, N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium, N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium, and mixtures thereof).

[0062] Embodiment 8. A process for producing the molecular sieve material of any one of the previous embodiments, the process comprising: (i) preparing a synthesis mixture capable of forming said material, said mixture comprising water, a source of hydroxyl ions, a source of an oxide of a tetravalent element Y, a source of a trivalent element X, optionally a source of halide ions Z^- , optionally a source of alkali metal ions M^+ , and a structure directing agent Q selected from the group consisting of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium cations, N, N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium cations, and mixtures thereof, and said synthesis mixture having a composition, in terms of mole ratios, in the following amounts and/or ranges: YO_2/X_2O_3 of at least 1; H_2O/YO_2 of 5 to 60; OH^-/YO_2 of 0.01 to 1; Z^-/YO_2 of 0 to 0.30; Q/YO_2 of 0.03 to 1.0; and M^+/YO_2 of 0 to 0.40; (ii) heating said synthesis mixture under crystallization conditions including a temperature from about 100°C to about 200°C and a time from about 1 day to about 100 days until crystals of said material are formed; and (iii) recovering said crystalline material from said synthesis mixture.

[0063] Embodiment 9. The process of embodiment 8, wherein the source of trivalent element X is one or more of boric acid, sodium tetraborate, and potassium tetraborate.

[0064] Embodiment 10. The process of embodiment 8 or embodiment 9, wherein the synthesis mixture has a pH from 8.0 to 10.5.

[0065] Embodiment 11. A process for converting a feedstock comprising an organic compound to a conversion product which comprises contacting said feedstock at organic compound conversion conditions with a catalyst comprising an active form of the molecular sieve material of any one of embodiments 1-7 and/or made according to the process of any one of embodiments 8-10.

[0066] The invention can now be more particularly described with reference to the following non-limiting Examples and the accompanying drawings.

EXAMPLES

Example 1

[0067] First, ~5.08 g of a hydroxide solution of the C₄ diquat of dihexylmethylamine (N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium hydroxide; [OH] $\approx$ 0.59 mmol/g) was mixed with ~2.22 g deionized water inside a Teflon™ liner for a ~23-mL steel Parr autoclave. Next about 0.19 g boric acid was added to the solution and mixed until nearly complete dissolution. Then about 2.25 g Ludox™ AS-40 (a colloidal suspension of ~40 mass% silica in water) was added to the solution, and ~1.50 g of ~1N HCl was added and mixed to create a relatively uniform suspension. The synthesis mixture had the following molar ratios: Si:B $\approx$ 5; HCl:Si $\approx$ 0.10; H₂O:Si $\approx$ 35; and Q:Si $\approx$ 0.1. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). The reactor was removed after ~38 days, quenched, and the solid was isolated by filtration, washed, dried, and analyzed with powder XRD. Figure 1 shows that the powder XRD of the product appeared to be a mixture of amorphous material and EMM-25.

Example 2

[0068] Example 1 was repeated using seeds (~0.04 g seeds/g SiO₂) of the EMM-25 product from Example 1. The reactor was removed after different heating periods and quenched. Aliquots of the gel mixture were removed, and the solids were isolated by filtration, washed, dried, and then analyzed with powder XRD. Figure 2 shows that the synthesis appeared to be mostly complete after ~38 days of heating and appeared to be completely finished after ~52 days of heating. The powder XRD pattern of the final product could be indexed on a C-centered orthorhombic cell ($a \approx 22.95 \text{ \AA}$, $b \approx 11.07 \text{ \AA}$, and $c \approx 24.85 \text{ \AA}$). Figure 3 shows SEM images of the product taken after ~38 days. The product appeared to show mostly a crystalline phase with a minor amorphous phase. The images appeared to show crystalline plates with edges of about 0.25 microns to about 1 micron in length and thicknesses of about 0.025 microns to about 0.1 microns.


[0069] The final product from Example 2 was heated inside a muffle furnace from ambient temperature (~20-25°C) to about 400°C at ~4°C/min under a nitrogen atmosphere, then heated to ~600°C at ~4°C/min in air, and maintained at ~600°C in air for about 2 hours. The calcined

product was then measured with nitrogen physisorption, and the data were analyzed by the t-plot method, according to the method of Lippens, B.C. and deBoer, J.H., “Studies on pore systems in catalysts: V. The t method”, *J. Catal.*, 4, 319 (1965). The determined micropore volume was $\sim 0.15 \text{ cm}^3/\text{g}$, and the total BET surface area was $\sim 419 \text{ m}^2/\text{g}$.

Example 3 – Synthesis of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium hydroxide


[0070] A diquaternary ammonium salt of N,N-dihexyl-N-methylamine was prepared by its reaction with 1,4-dibromobutane. To $\sim 100 \text{ mL}$ of acetone in a $\sim 500\text{-mL}$ round bottom flask were added $\sim 25.0 \text{ g}$ of N,N-dihexyl-N-methylamine (Aldrich, $\sim 0.125 \text{ mol}$) and $\sim 12.3 \text{ g}$ 1,4-dibromobutane ($\sim 0.057 \text{ mol}$). The resultant mixture was then refluxed for ~ 2 days. The solvent was then removed by rotary evaporation, and the product oil was extracted with ether to remove unreacted amine. The oil was then dried by rotary evaporation at $\sim 80^\circ\text{C}$ under gradually reduced pressure (down to $\sim 50 \text{ torr}$). The dibromide product was then ion-exchanged into the hydroxide form by dissolving it in a mixture of water and ethanol. To this solution was added approximately a two-fold excess of Dowex™ LC NG hydroxide exchange resin. The solution was recovered by filtration and extensive washing of the resin. The hydroxide solution was then extracted with ether to remove any amine impurities, and it was subsequently concentrated by rotary evaporation under gradually reduced pressure (down to $\sim 50 \text{ torr}$) at $\sim 65^\circ\text{C}$. The concentration of the aqueous solution was determined by titration with a standard solution of $\sim 0.1\text{N HCl}$.

Example 4 – Synthesis of N, N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide



[0071] The N-pentyl-N-hexyl-N-methylamine was prepared by reductive amination of valeraldehyde (N-pentanal) with N-hexyl-N-methylamine. About 500 mL of tetrahydrofuran (THF) was placed in a ~1L suction flask. About 28.4 g valeraldehyde (~0.34 mol) and then ~37.8 g N-hexyl-N-methylamine (~0.33 mol) were mixed into the THF. About 100 g of sodium triacetoxyborohydride powder was then added in ~5-10 g increments to the solution. During the addition, vigorous stirring was used to ensure that the powder clumped as little as possible at the bottom of the flask, thereby preventing efficient mixing of the suspension. After each addition of the sodium triacetoxyborohydride powder, adequate time was provided to form a relatively uniform slurry before the next addition of the powder. Once all of the powder had been added, the nitrogen flow was then turned on. After overnight mixing (~8-16 hours), the product was worked up by quenching the suspension with the slow addition of ~275 g of a ~24 mass% KOH (aqueous) solution. The product was then extracted from the resultant solution with pentane. The organic fraction was then collected with a separatory funnel and dried with anhydrous magnesium sulfate. The amine product was then isolated by rotary evaporation of the THF and pentane solvents under gradually reduced pressure (down to ~50 torr) to yield ~60.6 g of amine product (~95% pure by ^1H NMR).

[0072] A diquatary ammonium salt of N-pentyl-N-hexyl-N-methylamine was prepared by its reaction with 1,4-dibromobutane. To ~150 mL acetone in a ~500-mL round bottom flask were added ~60.6 g of N-pentyl-N-hexyl-N-methylamine (~0.32 mol) and ~31.9 g 1,4-dibromobutane (~0.15 mol). The resultant mixture was then refluxed for ~2 days. The solvent was then removed by rotary evaporation, and the product oil was extracted with ether to remove unreacted amine. The oil was then dried by rotary evaporation at ~80°C under gradually reduced pressure (down to ~50 torr) to give ~84.1 g product. The dibromide product was then ion-exchanged into the hydroxide form by dissolving it in water and adding approximately a two-fold excess of Dowex™ LC NG hydroxide exchange resin. The solution was then recovered by filtration and extensive washing of the resin. The aqueous solution was then concentrated by rotary evaporation of the water under gradually reduced pressure (down to ~50 torr) at ~65°C. The aqueous solution concentration was determined by titration with a standard solution of ~0.1N HCl.

Example 5 – Synthesis of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide

[0073] The di-N-pentyl-N-methylamine was prepared by reductive amination of formaldehyde with di-N-pentylamine using a procedure similar to that in Example 4. A diquatery ammonium salt of di-N-pentyl-N-methylamine was prepared by its reaction with 1,4-dibromobutane using a procedure similar to that described in Example 4.

Example 6

[0074] About 3.84 g of a hydroxide solution of N,N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of N-hexyl-N-pentyl-N-methylamine; [OH] $\approx$ 0.78 mmol/g) was mixed with $\sim$ 3.42 g deionized water inside a Teflon™ liner for a $\sim$ 23-mL steel Parr autoclave. Next $\sim$ 0.19 g boric acid was added to the solution and mixed until nearly complete dissolution. Then $\sim$ 2.25 g Ludox™ AS-40 was added to the solution, and $\sim$ 1.50 g of $\sim$ 1N HCl was added and mixed to create a relatively uniform suspension. Seeds ($\sim$ 0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the $\sim$ 23-mL autoclave, and heated at $\sim$ 160°C under tumbling conditions ($\sim$ 40 rpm). The reactor was removed and quenched, and small quantities of product were sampled after $\sim$ 25, $\sim$ 35, and $\sim$ 49 days of heating. Figure 4 shows that EMM-25 appeared to be slowly crystallizing, although it appeared not to be complete after $\sim$ 49 days.

Example 7

[0075] About 4.41 g of a hydroxide solution of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of di-N-pentyl-N-methylamine; [OH] $\approx$ 0.68 mmol/g) was mixed with $\sim$ 2.81 g deionized water inside a Teflon™ liner for a $\sim$ 23-mL steel Parr

autoclave. Next ~0.19 g boric acid was added to the solution and mixed until nearly complete dissolution. Then ~2.25 g Ludox AS-40 was added to the mixture, and ~1.50 g of ~1N HCl was added and mixed to create a relatively uniform suspension. Seeds (~0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). The reactor was removed and quenched, and small quantities of product were sampled after ~16, ~23, and ~27 days of heating. Figure 5 shows that EMM-25 appeared to be nearly completely crystallized after ~27 days.

Example 8

[0076] Example 7 was repeated, except using a ratio of NaOH/Si $\approx$ 0.04. In Example 8, about 4.40 g of a hydroxide solution of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of di-N-pentyl-N-methylamine; [OH] $\approx$ 0.68 mmol/g) was mixed with ~2.24 g deionized water inside a Teflon™ liner for a ~23-mL steel Parr autoclave. To this solution was added ~0.60 g of ~1N NaOH. Next ~0.19 g boric acid was added to the solution and mixed until nearly complete dissolution. Then ~2.25 g Ludox™ AS-40 was added to the mixture, and ~1.50 g of ~1N HCl was added and mixed to create a relatively uniform suspension. Seeds (~0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). The reactor was removed and quenched, and small quantities of product were sampled after ~7, ~14, and ~21 days of heating. Figure 6 shows that the EMM-25 appeared to be completely crystallized after ~21 days.

Example 9

[0077] Example 7 was repeated, except that the liner was heated at ~170°C rather than at ~160°C. The reactor was removed and quenched, and small quantities of product were sampled after ~7, ~21, ~24, and ~28 days of heating. Figure 7 shows that EMM-25 appeared to be completely or nearly completely crystallized after ~28 days.

Example 10

[0078] Example 7 was repeated, except that no HCl was added to the reaction. About 4.41 g of a hydroxide solution of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of di-N-pentyl-N-methylamine; [OH] $\approx$ 0.68 mmol/g) was mixed with ~4.27 g deionized water inside a Teflon™ liner for a ~23-mL steel Parr autoclave. Next ~0.19 g boric acid was added to the solution and mixed until nearly complete dissolution. Then ~2.25 g

Ludox™ AS-40 was added to the mixture and mixed to create a relatively uniform suspension. Seeds (~0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). After ~27 days of heating, the product appeared to be completely crystallized EMM-25, with a trace impurity of ZSM-5.

Example 11

[0079] About 2.63 g of a hydroxide solution of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of di-N-pentyl-N-methylamine; [OH] ≈ 0.68 mmol/g) and ~0.72 g of ~1N NaOH were mixed with ~5.20 g deionized water inside a Teflon™ liner for a ~23-mL steel Parr autoclave. Next ~0.093 g boric acid was dissolved in the solution. Then ~0.54 g Cabosil™ M-5 fumed silica was added to the mixture and mixed to create a relatively uniform suspension. Seeds (~0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). After ~7 days of heating, the product appeared to be completely crystallized EMM-25, with a minor impurity of ZSM-5.

Example 12

[0080] Example 11 was repeated, except that ~1N KOH was used instead of ~1N NaOH. After ~7 days of heating, the product appeared to be completely crystallized EMM-25, with a minor impurity of ZSM-5.

Example 13

[0081] A reaction similar to Example 11 was repeated, except that no alkali hydroxide was used in the reaction. About 3.69 g of a hydroxide solution of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of di-N-pentyl-N-methylamine; [OH] ≈ 0.68 mmol/g) was mixed with ~7.93 g deionized water inside a Teflon™ liner for a ~23-mL steel Parr autoclave. Next ~0.13 g boric acid was dissolved in the solution. Then ~0.76 g Cabosil™ M-5 fumed silica was added to the mixture and mixed to create a relatively uniform suspension. Seeds (~0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). After ~13 days of heating, the product was determined to be substantially pure EMM-25.

Example 14

[0082] Example 12 was repeated with half the amount of ~1N KOH. About 2.63 g of a hydroxide solution of N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium hydroxide (the C₄ diquat of di-N-pentyl-N-methylamine; [OH] $\approx$ 0.68 mmol/g) was mixed with ~5.55 g deionized water and ~0.36 g ~1N KOH inside a Teflon™ liner for a ~23-mL steel Parr autoclave. Next ~0.093 g boric acid was dissolved in the solution. Then ~0.54 g Cabosil™ M-5 fumed silica was added to the mixture and mixed to create a uniform suspension. Seeds (~0.04 g) of EMM-25 were added to the suspension. The liner was then capped, sealed inside the ~23-mL autoclave, and heated at ~160°C under tumbling conditions (~40 rpm). After ~10 days of heating, the product was determined to be EMM-25, with a trace ZSM-5 impurity.

Example 15

[0083] Example 14 was repeated, except that the liner was heated at ~175°C rather than at ~160°C. After ~11 days of heating, the product of Example 14 was determined to be EMM-25, with a trace layered phase impurity.

Characterization

[0084] A sample of as-synthesized EMM-25 yielded an XRD pattern having the following peaks (whose values are approximate):

2-Theta	d	[100 x I/I(o)]%
7.10	12.45	13
7.64	11.57	47
8.46	10.45	2
9.50	9.31	38
10.44	8.47	17
14.00	6.32	8
14.47	6.11	4
15.87	5.58	9
15.98	5.54	27
16.19	5.47	4
17.64	5.02	1
19.14	4.63	3
19.43	4.57	5
19.92	4.45	50
20.96	4.23	43
22.26	3.99	27
22.76	3.9	100
23.20	3.83	28

2-Theta	d	[100 x I/I(o)]%
23.53	3.78	8
24.37	3.65	72
24.65	3.61	21
25.25	3.52	15
25.71	3.46	2
26.58	3.35	8
27.01	3.3	13
27.34	3.26	5
27.60	3.23	8
27.96	3.19	5
28.29	3.15	4
28.56	3.12	8
29.26	3.05	2
30.36	2.94	8
31.13	2.87	3
31.83	2.81	8
32.30	2.77	2
32.72	2.74	3
34.35	2.61	3
36.09	2.49	11

[0085] The as-synthesized EMM-25 was calcined in a muffle furnace by heating in a nitrogen stream from ambient temperature (~ 20 - 25°C) to $\sim 400^{\circ}\text{C}$ over a ~ 2 -hour period, maintaining this temperature for ~ 15 minutes, switching the gas stream to air, increasing the temperature from $\sim 400^{\circ}\text{C}$ to $\sim 600^{\circ}\text{C}$ over a ~ 2 -hour period, maintaining the temperature at $\sim 600^{\circ}\text{C}$ for ~ 2 hours, and then allowing the furnace to cool to ambient temperature (~ 20 - 25°C). A sample of as-calcined EMM-25 yielded an XRD pattern having the following peaks (whose values are approximate):

2-Theta	d	[100 x I/I(o)]%
7.07	12.5	35
7.66	11.54	100
8.48	10.42	2
9.51	9.3	56
10.43	8.48	27
14.06	6.3	12
14.5	6.1	9
15.44	5.73	2
15.99	5.54	40

2-Theta	d	[100 x I/I(o)]%
16.19	5.47	6
19.29	4.6	3
19.87	4.47	34
20.99	4.23	23
22.33	3.98	14
22.71	3.91	59
23.25	3.82	18
23.59	3.77	7
24.4	3.64	48
24.69	3.6	8
25.22	3.53	8
25.64	3.47	2
26.5	3.36	7
26.79	3.32	1
27	3.3	3
27.37	3.26	2
27.6	3.23	7
27.92	3.19	4
28.36	3.14	5
28.6	3.12	8
29.3	3.05	2
30.36	2.94	5
31.88	2.8	5
32.37	2.76	2
32.64	2.74	2
33.26	2.69	2
34.42	2.6	4
35.99	2.49	5

[0086] A sample of as-calcined EMM-25 was further tested for its capacity to adsorb n-hexane, 2,2-dimethylbutane, and mesitylene. All the materials were thermally treated at ~500°C for a time sufficient to substantially dehydrate the materials and/or to remove any adsorbed species prior to doing the sorption test; the hydrocarbon was then introduced through a sparger to saturate the nitrogen stream. Each sorbate was adsorbed at a different temperature: hexane at ~90°C, 2,2-dimethylbutane at ~120°C, and mesitylene at ~100°C. The results are summarized below:

- 26 -

n-hexane	-	~80.6 mg/g
2,2-dimethylbutane	-	~51.3 mg/g
mesitylene	-	~22.2 mg/g

[0087] A sample of as-synthesized EMM-25 was also analyzed for boron content by ^{12}B NMR by comparison of signal intensity with a standard of known boron concentration. The boron concentration in the EMM-25 was found to be ~0.63% by mass.

[0088] While the present invention has been described and illustrated by reference to particular embodiments, those of ordinary skill in the art will appreciate that the invention lends itself to variations not necessarily illustrated herein. For this reason, then, reference should be made solely to the appended claims for purposes of determining the true scope of the present invention.

CLAIMS

What is claimed is:

1. A molecular sieve material having, in its calcined form, an X-ray diffraction pattern including the peaks listed in Table 1.
2. A molecular sieve material having a framework defined by the connectivities for the tetrahedral (T) atoms in the unit cell listed in Table 2, the tetrahedral (T) atoms being connected by bridging atoms.
3. The molecular sieve material of claim 1 or claim 2, having a composition comprising the molar relationship: $(n)YO_2:X_2O_3$, wherein n is at least 10, X is a trivalent element (*e.g.*, comprising one or more of B, Al, Fe, and Ga, such as comprising or being B), and Y is a tetravalent element (*e.g.*, comprising one or more of Si, Ge, Sn, Ti, and Zr, such as comprising or being Si).
4. The molecular sieve material of claim 3, further comprising a noble metal and/or a salt of a noble metal.
5. A molecular sieve material having, in its as-synthesized form, an X-ray diffraction pattern including the peaks listed in Table 3.
6. The molecular sieve material of claim 5, having a composition comprising the molar relationship: $mQ:(n)YO_2:X_2O_3$, wherein $0.004 < m/n \leq 0.04$, n is at least 10, Q is an organic structure directing agent, X is a trivalent element (*e.g.*, comprising one or more of B, Al, Fe, and Ga, such as comprising or being B), and Y is a tetravalent element (*e.g.*, comprising one or more of Si, Ge, Sn, Ti, and Zr, such as comprising or being Si).
7. The molecular sieve material of claim 6, wherein Q is a cation of the formula: $R_1R_2(CH_3)N^+CH_2CH_2CH_2CH_2N^+(CH_3)R_1R_2$, wherein R_1 and R_2 are chosen independently from butyl, pentyl, and hexyl (*e.g.*, wherein Q is a cation selected from the group consisting of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium, N,N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium, N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium, and mixtures thereof).
8. A process for producing the molecular sieve material of any one of the previous claims, the process comprising:
 - (i) preparing a synthesis mixture capable of forming said material, said mixture comprising water, a source of hydroxyl ions, a source of an oxide of a tetravalent element Y , a

source of a trivalent element X, optionally a source of halide ions Z^- , optionally a source of alkali metal ions M^+ , and a structure directing agent Q selected from the group consisting of N,N,N',N'-tetrahexyl-N,N'-dimethylbutane-1,4-diammonium cations, N, N'-dihexyl-N,N'-dipentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N,N',N'-tetrapentyl-N,N'-dimethylbutane-1,4-diammonium cations, N,N'-dipentyl-N,N'-dibutyl-N,N'-dimethylbutane-1,4-diammonium cations, and mixtures thereof, and said synthesis mixture having a composition, in terms of mole ratios, in the following amounts and/or ranges: YO_2/X_2O_3 of at least 1; H_2O/YO_2 of 5 to 60; OH^-/YO_2 of 0.01 to 1; Z^-/YO_2 of 0 to 0.30; Q/YO_2 of 0.03 to 1.0; and M^+/YO_2 of 0 to 0.40;

(ii) heating said synthesis mixture under crystallization conditions including a temperature from about 100°C to about 200°C and a time from about 1 day to about 100 days until crystals of said material are formed; and

(iii) recovering said crystalline material from said synthesis mixture.

9. The process of claim 8, wherein the source of trivalent element X is one or more of boric acid, sodium tetraborate, and potassium tetraborate.

10. The process of claim 8 or claim 9, wherein the synthesis mixture has a pH from 8.0 to 10.5.

11. A process for converting a feedstock comprising an organic compound to a conversion product which comprises contacting said feedstock at organic compound conversion conditions with a catalyst comprising an active form of the molecular sieve material of any one of claims 1-7 and/or made according to the process of any one of claims 8-10.