

Description

This invention relates to lightwave devices and more particularly to a subassembly used in packaging optoelectronic devices such as photodiodes and light emitting diodes (LEDs).

Conventional packages for discrete optoelectronic devices typically are made out of a variety of dissimilar materials, such as metal, glass and ceramic, and involve relatively complicated manipulation of components during assembly. U. S. Patents No. 4,357,072 (LED), 4,119,363 (laser) and 4,233,619 (photodetector) are illustrative. Assembly involves manipulating components in three dimensions in order to place the components in the desired locations; for example, alignment of a device to a substrate, alignment of a fiber to a ferrule, alignment of a ferrule to a package, and finally alignment of the package to the device. These alignment steps depend upon fairly specialized, expensive equipment. In general, therefore, z-axis assembly is not possible in those designs; that is, one cannot simply move the components along a z-axis perpendicular to the substrate and place them on the substrate without further orientation being required in the x-y plane. In addition, because the packages include dissimilar materials, great care is required to insure that the thermal-expansion coefficients are adjusted in such a way that the alignments are stable even though the ambient temperature changes. Instability, of course, leads to mechanical movement of the components and consequently to a decrease in optical coupling between, for example, the device and the fiber. Often this situation leads package designers to compromise between thermal sinking and stability criteria. At the very least, it increases cost.

For many expensive applications, notably long haul transmission systems, the relatively high cost of manufacturing such packages can be tolerated. However, for some cost sensitive, high volume applications, such as lightwave systems between central switching offices or remote-terminals and subscribers' homes (known as the subscriber loop), the high cost of such packages renders them unsuitable.

Thus, it would be desirable to have a packaging scheme which (1) uses, as much as possible, commercially available equipment for the production of the pieceparts, for the alignment of the parts, and for closing of the package; and (2) which accommodates different size packages for different applications without requiring extensive retooling or new assembly techniques. For example, it would be desirable, on the one hand, to have a subassembly which fits inside of a dual-in-line package (DIP) header and is adapted to a 125 μm diameter fiber and, on the other hand, to have a different

subassembly which is adapted to a larger diameter fiber and is surface mounted on a printed circuit (PC) board. Normally, the fabrication of these two designs would require retooling which is undesirable for reasons of cost and commonality.

Reference DE 3,543,558 teaches an optoelectronic coupling arrangement including an optical waveguide (i.e. optical fiber) disposed in groove formed in a substrate. The substrate further includes a deflection component for redirecting the light propagating along the optical waveguide out of the plane of the substrate and into a light sensitive device positioned above the substrate.

According to the present invention there is provided a subassembly as defined in claim 1.

One aspect of the invention is the use of a single crystal semiconductor such as silicon as the basic material from which the subassembly for packaging optoelectronic devices is constructed and to exploit many of the well-known techniques for shaping silicon pieceparts and for depositing metals thereon. The use of silicon in this way will be referred to as "silicon optical bench" technology.

The maturity of silicon technology means several things: first, there is available a large body of silicon processing techniques which, therefore, do not have to be specifically developed; second, there are available numerous pieces of commercial equipment which have been already cost-reduced by years of high volume manufacturing; and, third, using these techniques and equipments, various shapes in silicon pieceparts can be realized by relatively simple and inexpensive photolithographic processes, which do not require large volume to render them cost effective.

In accordance with the invention, the subassembly includes an optoelectric device mounted on a silicon base and the two following features: (1) A groove is located in the base for guiding an optical fiber and a reflector is formed on the end face of the groove. The device is placed over the reflector which directs light between the device and the fiber. Positioning the device over the reflector is the only active alignment step required in the x-y plane. All other alignments are automatically achieved by the geometry of the pieceparts; (2) Electrical contacts are disposed on the base with one of the contacts overlapping the end face of the groove to form the reflector. The subassembly of the present invention may also have one or more of the following additional features: (3) A silicon lid is disposed on the base with at least one dimension of the lid being less than the corresponding one of the base so that the contacts protrude from under the lid to the exterior of the subassembly; (4) The lid has a cavity for receiving the device and a groove, aligned with the groove in the base, to form

a channel in which the coated part of the fiber is positioned; (5) Detents are provided in the base and lid for aligning them to one another; (6) Portions of the exteriors of the base and lid are metalized to provide a ground shield and a place to make electrical contact to the rest of the package.

In another embodiment for devices, such as photodiodes, which are passivated by a conformal coating, an aperture in the lid communicates with the cavity and the coating is injected therethrough.

The invention, together with its various features and advantages, can be readily understood from the following more detailed description taken in conjunction with accompanying drawings, in which the various figures are schematic and hence are not drawn to scale in the interests of clarity.

FIG. 1 is an isometric, cut-away view of a package for an optoelectronic device; the package includes a subassembly 10 in accordance with an illustrative embodiment of the invention.

FIG. 2 is an exploded view of FIG. 1 showing the illustrative subassembly 10, a lead frame 12, a DIP header 14, and a cover 16.

FIG. 3 is an expanded view of a cross-section of the optical subassembly 10 of FIG. 1 depicting a photodiode 11 therein.

FIGS. 4-7 show isometric views of the illustrative subassembly 10 in various stages of fabrication.

With reference now to FIGS. 1-3, subassembly 10 in accordance with one embodiment of the invention is shown enclosed within a dual-in-line package (DIP). Other package designs, such as molded ones, are also suitable, however. In the DIP configuration the subassembly 10 is mounted on a lead frame 12 which is inserted in a DIP header 14. A cover 16 has a slot 18 to permit an optical fiber 20 to extend from the subassembly 10 to the exterior of the package. Fiber 20 permits lightwave signals to be transmitted to and/or from an optoelectronic device (e.g., photodiode 11) within the subassembly.

The subassembly 10 is constructed in accordance with the invention from a single crystal semiconductor, preferably silicon in order to exploit the mature silicon technology from the standpoint of processing and equipment availability, as discussed earlier. In addition, the design reduces to one the number of alignment steps which have to be performed in the x-y plane. Thus, the invention is advantageously very close to the desiderata of z-axis alignment. More specifically, FIGS. 4-7 show subassembly 10 for a photodiode 11 including a single crystal silicon base 22 on which the photodiode is mounted, a single crystal silicon lid 24, and an optical fiber 20 disposed in a channel formed along the interface between the base and lid so that it is optically coupled to the photodiode.

The subassembly 10 is characterized by one or more of the following features.

(1) Anisotropically-etched tandem grooves (30 and 32 in the base and 34 in the lid) provide strain relief for and alignment of fiber 20. Groove 30 in the base is aligned with groove 34 in the lid so as to receive the coated portion 21 of fiber 20, and the width of groove 34 is slightly smaller than that of groove 30 so that portion 21 fits snugly and provides strain relief. Groove 32, on the other hand, is formed in the base in tandem with groove 30 but has a considerably smaller width so as to receive and align the bare end portion 23 of fiber 20. The use of tandem grooves is preferred where the shape and structural strength of the fiber coating (e.g., urethane) are not sufficiently well controlled in different environmental conditions (e.g., humidity) that the coating can be relied on for alignment purposes. On the other hand, some fiber coatings (e.g., polyimide) are suitable for alignment purposes; and, in those cases, neither the tandem groove arrangement in the base nor the groove in the lid need be utilized; rather the base may simply have a groove for holding the coated portion 21 of the fiber against the bottom of the lid.

(2) After the grooves are etched, the base is oxidized (e.g., 1-10 μm of SiO_2 is formed) and metalized, and standard photolithography is utilized to pattern electrical contacts 40 and 42. The oxide layer (not shown) prevents the contacts from being short circuited through the silicon and reduces their mutual capacitance. As shown in FIG. 4, contact 40 overlaps the end face of groove 32 and forms a turning mirror of reflector 44. When the major surface of the base is a (100) crystallographic plane, the end face is a (111) crystallographic plane and hence reflector 44 is oriented at a 54.7° angle. The latter serves both as a mechanical stop for the fiber and as a director of light emanating from the end of fiber 20. The reflected light is thus made incident on the photosensitive area of photodiode 11. Even though mirror 44 is not at a 45° angle, it is adequate to couple light into the photodiode and to enable the axis of the fiber and that of the photodiode to be aligned to about $\pm 1 \mu\text{m}$ (where $\pm 5 \mu\text{m}$ accuracy is sufficient).

(3) The photodiode is illustratively an InP/InGaAs back-illuminated design of the type described by O. K. Kim in U. S. Patent No. 4,608,586; that is, the device is illuminated through an opening in the metalization on its transparent substrate, thereby to permit ingress of light into the photosensitive area of the photodiode. The substrate metalization of the photodiode is bonded to contact 40, and the photodiode is oriented in

the x-y plane so that its photosensitive area is over the mirror 44. Advantageously, this step is the only active alignment step required in the assembly procedure. After alignment is accomplished, the top contact of the photodiode is connected to contact 42 via a wire bond 46, as shown in FIG. 5.

(4) The dimensions of the base, lid and contacts are mutually adapted so that the pads at the ends of the contacts 40 and 42 extend out from under the lid, as shown in FIGs. 6 and 7, thereby enabling wire-bonds to be made to the lead frame. One such bond 48 is shown in FIG. 1.

(5) The lid and base are aligned relative to one another by means of detents 50. Illustratively, these detents are small pyramidal-shaped holes etched into the lid and base with a ball bearing in each hole in the base to facilitate alignment by merely snapping the base and lid together. The balls may be fabricated from a number of materials such as metal, sapphire or tungsten carbide. This technique has a relatively large capture range because the balls are curved and, therefore, tend to readily guide a slightly misaligned lid into alignment. In addition, instead of aligning lids and bases one at a time, one can take advantage of the fact that the bases are cut from a wafer and that prior to separating the bases, the photodiodes can be mounted thereon, tested and burned in before the lids are put in place. Or, the bases may be cut into 1 x N strips before the photodiodes, N in number, are mounted. A similar 1 x N strip of lids can then be aligned to the strip of bases using, for example, only a pair of alignment detents, one at each end of the strips rather than a pair for each individual lid and base.

(6) The lid has a cavity 26 and a pair of apertures 52 and 54, as shown in FIG. 7. When the lid is in place, the photodiode 11 is located in the cavity and funnel-shaped aperture 52 permits a conformal coating (e.g., silicone for passivation) to be inserted therethrough (and then cured) to cover the photodiode. Likewise, aperture 54 permits epoxy or other adhesive to be inserted to secure the position of the fiber 20 in the subassembly. Where, however, passivation is not required (or a hermetic design is), aperture 52 may be omitted. Likewise, where the fiber needs to slide in and out of the subassembly (in a plug-in design, for example), the epoxy/adhesive and aperture 54 may be omitted.

(7) The top of the lid and the bottom of the base are metalized (not shown) to provide a ground shield. For adhesion purposes, the silicon may be oxidized before the metal is deposited. As shown in FIG. 1, the metalized bottom of the base contacts lead frame 12, and the top of the

lid is connected thereto by wire bond 49.

Subassemblies according to FIGs. 1-7 have been fabricated using silicon optical bench technology with the silicon piecparts (base, lid) measuring about 3 mm wide by 4 mm long by 750 μ m thick. The anisotropically etched V-grooves 30, 32 and 34 were adapted to receive single mode glass fibers 20 having a coated portion 21 with about a 250 μ m diameter and a bare portion 23 with about a 125 μ m outside diameter. The oxide on the silicon base was about 10 μ m thick. The contacts 40 and 42 and mirror 44 were Ti-Pt-Au multilayers (Cr-Au is also suitable) with Au the outermost layer. The photodiode 11, which had an active area of about 75 μ m, was bonded to contact 40 with a eutectic solder (Au/Ge or Au/Sn) which was evaporated onto the substrate side of the photodiode. Because the silicon base is extremely flat, very thin (e.g., 3 μ m) layers of solder could be used thereby reducing expense associated with the cost of a separate preform of eutectic solder. From a convenience standpoint, the fiber should not be secured into the subassembly too soon during the fabrication sequence, otherwise manipulation of the subassembly may be cumbersome. Thus, it is preferred that, after the base, photodiode and lid are in place, but before the conformal coating is applied, the subassembly is bonded to the lead frame with epoxy or with a lower melting point solder than used for the photodiode. After wire bonds are made to the photodiode and to the ground shields, the fiber is inserted into the V-grooves of the subassembly and epoxied in place.

It is apparent that the lid serves multiple purposes including: protecting the device during molding operations associated with encapsulating the subassembly in a package; electrically isolating the device; containing epoxy and the conformal coating, if necessary; and guiding the optical fiber.

In operation, photodiodes packaged in this fashion are relatively inexpensive, have reasonably high yields and responsivities of about 0.8-0.9 A/W. No failures were observed when the packages were cycled between -40°C and +85°C in ambient humidity. The frequency response of the package depends on a number of factors, principally the oxide thickness, the area of the contacts and the length of the leads. When properly designed, a frequency response of about 200 MHz was measured.

It is to be understood that the above-described arrangements are merely illustrative of the many possible specific embodiments which can be devised to represent application of the principles of the invention. Numerous and varied other arrangements can be devised in accordance with these principles by those skilled in the art without departing from the spirit and scope of the invention. In

particular, although the subassemblies of FIGs. 1-7 were described in terms of light in a fiber being detected by a photodiode, they are also useful for coupling light from an LED into the fiber. However, when doing so, the divergence of the light emission from the LED affects the coupling efficiency into the fiber, and the relatively high current carried by the LED requires adequate heat sinking.

Finally, it will be appreciated that although today's technology suggests that silicon is the preferred material from which the principal piecparts of the invention are made, it is possible that different circumstances (e.g., system specifications and cost considerations) might render it desirable to utilize a different semiconductor (e.g., Ge, GaAs).

Claims

1. An optoelectronic device subassembly (10) comprising
 - a semiconductor base (22) having a major surface,
 - a first groove (32) in said major surface adapted to receive a portion of an optical fiber (20), said first groove having side walls and an end face formed by crystallographic planes which are oblique to said major surface, said groove end face forming a reflector and an optoelectronic device (11) being disposed over said reflector, CHARACTERIZED BY
 - an insulative layer formed on at least a portion of said major surface, and
 - metal contacts (40,42) disposed on said layer, at least one of said contacts (40) overlapping said end face and forming said reflector (44), said device being connected to said contacts, so that said reflector directs light between said device and said fiber.
2. The subassembly of claim 1 wherein said base has a second groove (30) arranged in tandem with said first groove and extending to the exterior of said subassembly, said fiber having a larger diameter portion (21) which fits into said second groove and a narrower diameter portion (23) which fits into said first groove.
3. The subassembly of claim 2 wherein the length of said grooves permits the end of said fiber to abut said reflector.
4. The subassembly of claim 1 further including a semiconductor lid (24) disposed on said base, said lid having a major surface and a cavity (26) therein for receiving said device, and further having a third groove (34) therein aligned with said first groove, thereby forming an elongated channel for receiving said fiber.
5. The subassembly of claim 4 wherein said lid has an opening (52) in communication with said cavity and a conformal coating, inserted through said opening, covers said device.
6. The subassembly of claim 4 including said fiber attached thereto and wherein said lid has an opening (54) in communication with said elongated channel and an adhesive, inserted through said opening, secures said fiber to said subassembly.
7. The subassembly of claim 4 wherein exterior major surfaces of said base and lid are metalized.
8. The subassembly of claims 1-6 or 7 wherein said semiconductor constitutive of said base comprises single crystal silicon, said major surface is a (100) crystallographic plane and said end face is a (111) crystallographic plane.
9. The subassembly of claims 1-6 or 7 wherein the optoelectronic device is a photodiode.
10. The subassembly of claim 1 further including (FIG.7) a semiconductor lid having a cavity, said lid being disposed over said base so that said device is positioned in said cavity, at least one dimension of said lid parallel to said surface being less than the corresponding dimension of said base, so that segments of said contacts (40,42) extend from under said lid to the exterior of said subassembly, and
 - said subassembly having channel means for receiving an optical fiber for carrying light between said device and the exterior of said subassembly.
11. The subassembly of claim 10 wherein said lid has an opening (52) in communication with said cavity, and a conformal coating, inserted through said opening, covers said device.
12. The subassembly of claim 10 including said fiber attached thereto and wherein said lid has an opening (54) in communication with said channel means and an adhesive, inserted through said opening, secures said fiber to said subassembly.
13. The subassembly of claim 12 wherein said channel means comprises a groove (30) in said base and a groove (34) in said lid, said grooves facing, and being aligned with, one another and having side walls which are

particular, although the subassemblies of FIGs. 1-7 were described in terms of light in a fiber being detected by a photodiode, they are also useful for coupling light from an LED into the fiber. However, when doing so, the divergence of the light emission from the LED affects the coupling efficiency into the fiber, and the relatively high current carried by the LED requires adequate heat sinking.

Finally, it will be appreciated that although today's technology suggests that silicon is the preferred material from which the principal pieceparts of the invention are made, it is possible that different circumstances (e.g., system specifications and cost considerations) might render it desirable to utilize a different semiconductor (e.g., Ge, GaAs).

Claims

1. An optoelectronic device subassembly (10) comprising
 - a semiconductor base (22) having a major surface,
 - a first groove (32) in said major surface adapted to receive a portion of an optical fiber (20), said first groove having side walls and an end face formed by crystallographic planes which are oblique to said major surface, said groove end face forming a reflector and an optoelectronic device (11) being disposed over said reflector, CHARACTERIZED BY
 - an insulative layer formed on at least a portion of said major surface, and
 - metal contacts (40,42) disposed on said layer, at least one of said contacts (40) overlapping said end face and forming said reflector (44), said device being connected to said contacts, so that said reflector directs light between said device and said fiber.
2. The subassembly of claim 1 wherein said base has a second groove (30) arranged in tandem with said first groove and extending to the exterior of said subassembly, said fiber having a larger diameter portion (21) which fits into said second groove and a narrower diameter portion (23) which fits into said first groove.
3. The subassembly of claim 2 wherein the length of said grooves permits the end of said fiber to abut said reflector.
4. The subassembly of claim 1 further including a semiconductor lid (24) disposed on said base, said lid having a major surface and a cavity (26) therein for receiving said device, and further having a third groove (34) therein aligned with said first groove, thereby forming an elongated channel for receiving said fiber.
5. The subassembly of claim 4 wherein said lid has an opening (52) in communication with said cavity and a conformal coating, inserted through said opening, covers said device.
6. The subassembly of claim 4 including said fiber attached thereto and wherein said lid has an opening (54) in communication with said elongated channel and an adhesive, inserted through said opening, secures said fiber to said subassembly.
7. The subassembly of claim 4 wherein exterior major surfaces of said base and lid are metalized.
8. The subassembly of claims 1-6 or 7 wherein said semiconductor constitutive of said base comprises single crystal silicon, said major surface is a (100) crystallographic plane and said end face is a (111) crystallographic plane.
9. The subassembly of claims 1-6 or 7 wherein the optoelectronic device is a photodiode.
10. The subassembly of claim 1 further including (FIG.7) a semiconductor lid having a cavity, said lid being disposed over said base so that said device is positioned in said cavity, at least one dimension of said lid parallel to said surface being less than the corresponding dimension of said base, so that segments of said contacts (40,42) extend from under said lid to the exterior of said subassembly, and
 - said subassembly having channel means for receiving an optical fiber for carrying light between said device and the exterior of said subassembly.
11. The subassembly of claim 10 wherein said lid has an opening (52) in communication with said cavity, and a conformal coating, inserted through said opening, covers said device.
12. The subassembly of claim 10 including said fiber attached thereto and wherein said lid has an opening (54) in communication with said channel means and an adhesive, inserted through said opening, secures said fiber to said subassembly.
13. The subassembly of claim 12 wherein said channel means comprises a groove (30) in said base and a groove (34) in said lid, said grooves facing, and being aligned with, one another and having side walls which are



crystallographic planes.

14. The subassembly of claim 13 wherein said channel means comprises a reflector (44) and a third groove (32) in tandem with the groove in said base, said third groove having a crystallographic end face on which said reflector is disposed, said device being positioned over said reflector which directs light between said device and said fiber.
15. The subassembly of claims 10-13 or 14 wherein said base and lid comprise single crystal silicon.

Patentansprüche

1. Optoelektronische Baugruppe (10) mit einer Halbleiterbasis (22) mit einer Hauptoberfläche, einer ersten Furche (32) in der Hauptoberfläche, die einen Abschnitt einer optischen Faser (20) aufnehmen kann, wobei die erste Furche Seitenwände und eine Endfläche hat, die durch kristallographische Ebenen ausgebildet sind, die zur Hauptoberfläche geneigt sind, wobei die Furchenendfläche einen Reflektor ausbildet und eine optoelektronische Einrichtung (11) über dem Reflektor angeordnet ist, gekennzeichnet durch eine isolierende Schicht, die wenigstens an einem Teil der Hauptoberfläche ausgebildet ist und Metallkontakte (40, 42), die auf der Schicht angeordnet sind, wobei wenigstens ein Kontakt (40) die Endfläche überlagert und den Reflektor (44) ausbildet, wobei die Einrichtung so an die Kontakte angeschlossen ist, daß der Reflektor das Licht zwischen der Einrichtung und der Faser umlenkt.
2. Baugruppe nach Anspruch 1, in welcher die Basis eine zweite Furche (30) hat, die in Tandemanordnung zur ersten Furche angeordnet ist und sich zum Äußeren der Baugruppe erstreckt, wobei die Faser einen Abschnitt mit größerem Durchmesser (21) hat, der in die zweite Furche paßt, und einen Abschnitt mit engerem Durchmesser (23) hat, der in die erste Furche paßt.
3. Baugruppe nach Anspruch 2, in welcher die Länge der Furchen es gestattet, daß die Faser an den Reflektor anstößt.
4. Baugruppe nach Anspruch 1, ferner umfassend einen Halbleiterdeckel (24), der an der Basis angeordnet ist, wobei der Deckel eine Hauptoberfläche und eine Aushöhlung (26) darin hat, um die Einrichtung aufzu-

nehmen, und ferner eine dritte Furche (34) hat, die in diesem zur ersten Furche ausgerichtet ist, wobei ein langgestreckter Kanal zur Aufnahme der Faser ausgebildet ist.

5. Baugruppe nach Anspruch 4, in welcher der Deckel eine Öffnung (52) hat, die mit der Aushöhlung kommuniziert und eine anschiessame Beschichtung, die durch die Öffnung eingebracht ist, die die Einrichtung bedeckt.
6. Baugruppe nach Anspruch 4, in welcher die Faser an dieser befestigt ist, und in welcher der Deckel eine Öffnung (54) hat, die mit dem langgestreckten Kanal kommuniziert, und ein Klebstoff, der durch die Öffnung eingebracht ist, die Faser an der Baugruppe sichert.
7. Baugruppe nach Anspruch 4, in welcher die äußeren Hauptoberflächen der Basis und des Deckels metallisiert sind.
8. Baugruppe nach den Ansprüchen 1 bis 6 oder 7, in welcher der Halbleiter, aus welchem die Basis besteht, einen Siliciumeinkristall enthält, die Hauptoberfläche eine kristallographische (100) Ebene ist und die Endfläche eine kristallographische (111) Ebene ist.
9. Baugruppe nach den Ansprüchen 1 bis 6 oder 7, in welcher die optoelektronische Einrichtung eine Fotodiode ist.
10. Baugruppe nach Anspruch 1, ferner umfassend (Fig. 7) einen Halbleiterdeckel mit einer Aushöhlung, wobei der Deckel über der Basis so angeordnet ist, daß die Einrichtung in der Aushöhlung angeordnet ist, wobei wenigstens eine Abmessung des Deckels parallel zur Oberfläche kleiner als die entsprechende Abmessung der Basis ist, so daß Abschnitte der Kontakte (40, 42) sich unter dem Deckel zum Äußeren der Baugruppe erstrecken, und die Baugruppe eine Kanaleinrichtung zur Aufnahme einer optischen Faser zum Führen von Licht zwischen der Einrichtung und dem Äußeren der Baugruppe hat.
11. Baugruppe nach Anspruch 10, in welcher der Deckel eine Öffnung (52) hat, die mit der Aushöhlung kommuniziert, und eine anschiessame Beschichtung, die durch die Öffnung eingebracht ist, die die Einrichtung bedeckt.



12. Baugruppe nach Anspruch 10,
umfassend eine daran befestigte Faser und in
welcher der Deckel eine Öffnung (54) hat, die
mit der Kanaleinrichtung kommuniziert und einen
Klebstoff umfaßt, der durch die Öffnung
eingebracht ist, der die Faser an der Baugruppe
sichert.
13. Baugruppe nach Anspruch 12,
in welcher die Kanaleinrichtung eine Furche
(30) in der Basis und eine Furche (34) im
Deckel umfaßt, wobei die Furchen einander
zugewandt und zueinander ausgerichtet sind
und Seitenwände haben, die kristallographische
Ebenen sind.
14. Baugruppe nach Anspruch 13,
in welcher die Kanaleinrichtung einen Reflektor
(44) und eine dritte Furche (32) in Tandeman-
ordnung zur Furche in der Basis umfaßt, wobei
die dritte Furche eine kristallographische End-
fläche hat, an welcher der Reflektor angeordnet
ist, wobei die Einrichtung über dem Reflektor
angeordnet ist, der Licht zwischen der Ein-
richtung und der Faser umlenkt.
15. Baugruppe nach den Ansprüchen 10 bis 13
oder 14,
in welcher die Basis und der Deckel einkristal-
lines Silicium enthalten.

Revendications

1. Sous-élément pour composants opto-électroniques (10) comprenant
 - une base de semiconducteur (22) ayant une surface principale,
 - une première rainure (32) dans ladite surface principale adaptée pour recevoir une partie d'une fibre optique (20), ladite première rainure ayant des parois latérales et une face d'extrémité formées par des plans cristallographiques qui sont obliques à ladite surface principale, ladite face d'extrémité de rainure formant un réflecteur et un composant opto-électronique (11) étant disposé par dessus ledit réflecteur, CARACTERISE PAR
 - une couche isolante formée sur au moins une partie de ladite surface principale, et
 - des contacts métalliques (40,42) disposés sur ladite couche, au moins l'un desdits contacts (40) chevauchant ladite face d'extrémité et formant ledit réflecteur (44), ledit composant étant connecté auxdits contacts, de sorte que ledit réflecteur dirige la lumière entre ledit composant et ladite fibre.
2. Sous-élément selon la revendication 1, dans lequel ladite base a une seconde rainure (30) disposée en tandem avec ladite première rainure et s'étendant vers l'extérieur dudit sous-élément, ladite fibre ayant une partie de diamètre plus large (21) qui entre dans ladite seconde rainure et une partie de diamètre plus étroit (23) qui entre dans ladite première rainure.
3. Sous-élément selon la revendication 2, dans lequel la longueur desdites rainures permet à l'extrémité de ladite fibre d'être contiguë audit réflecteur.
4. Sous-élément selon la revendication 1, comportant en outre un couvercle semiconducteur (24) disposé sur ladite base, ledit couvercle ayant une surface principale et une cavité (26) dans celle-ci pour recevoir ledit composant, et ayant en outre une troisième rainure (34) alignée avec ladite première rainure, formant ainsi un conduit allongé pour recevoir ladite fibre.
5. Sous-élément selon la revendication 4, dans lequel ledit couvercle a une ouverture (52) en communication avec ladite cavité et un enrobage de faible épaisseur, inséré à travers ladite ouverture, couvre ledit composant.
6. Sous-élément selon la revendication 4, comportant ladite fibre qui y est attachée et dans lequel ledit couvercle a une ouverture (54) en communication avec ledit conduit allongé et un adhésif, inséré à travers ladite ouverture, fixe ladite fibre audit sous-élément.
7. Sous-élément selon la revendication 4, dans lequel des surfaces principales extérieures de ladite base et dudit couvercle sont métallisées.
8. Sous-élément selon les revendications 1-6 ou 7, dans lequel ledit semiconducteur constituant ladite base se compose de silicium monocristallin, ladite surface principale est un plan cristallographique (100) et ladite face d'extrémité est un plan cristallographique (111).
9. Sous-élément selon les revendications 1-6 ou 7, dans lequel le composant opto-électronique est une photodiode.
10. Sous-élément selon la revendication 1, comportant en outre (figure 7) un couvercle semiconducteur ayant une cavité, ledit couvercle étant disposé sur ladite base de sorte que ledit composant est positionné dans ladite cavité, au moins une dimension dudit couvercle paral-



lèle à ladite surface étant inférieure à la dimension correspondante de ladite base, de sorte que des segments desdits contacts (40,42) s'étendent depuis le dessous dudit couvercle vers l'extérieur dudit sous-élément, et

5

ledit sous-élément ayant un moyen de conduit pour recevoir une fibre optique pour acheminer la lumière entre ledit composant et l'extérieur dudit sous-élément.

10

11. Sous-élément selon la revendication 10, dans lequel ledit couvercle a une ouverture (52) en communication avec ladite cavité, et un enrobage de faible épaisseur, inséré à travers ladite ouverture, couvre ledit composant.

15

12. Sous-élément selon la revendication 10, comportant ladite libre qui y est attachée et dans lequel ledit couvercle a une ouverture (54) en communication avec ledit moyen de conduit et un adhésif, inséré à travers ladite ouverture, fixe ladite libre audit sous-élément.

20

13. Sous-élément selon la revendication 12, dans lequel ledit moyen de conduit comprend une rainure (30) dans ladite base et une rainure (34) dans ledit couvercle, lesdites rainures se faisant face, et étant alignées l'une avec l'autre, et ayant des parois latérales qui sont des plans cristallographiques.

25

30

14. Sous-élément selon la revendication 13, dans lequel ledit moyen de conduit comprend un réflecteur (44) et une troisième rainure (32) en tandem avec la rainure dans ladite base, ladite troisième rainure ayant une face d'extrémité cristallographique sur laquelle ledit réflecteur est disposé, ledit composant étant positionné par dessus ledit réflecteur qui dirige la lumière entre ledit composant et ladite fibre.

35

40

15. Sous-élément selon les revendications 10-13 ou 14, dans lequel ladite base et ledit couvercle se composent de silicium monocristallin.

45

50

55

8

