

Method for preparing polyols

Technical field

The present invention relates to a method for preparing a polycarbonate ether polyol, by
5 reacting an epoxide and carbon dioxide in the presence of a catalyst of formula (I), a double
metal cyanide (DMC) catalyst and a starter compound.

Background

Polyurethanes are polymers which are prepared by reacting a di- or polyisocyanate with a
10 polyol. Polyurethanes are used in many different products and applications, including as
insulation panels, high performance adhesives, high-resilience foam seating, seals and gaskets,
wheels and tyres, synthetic fibres, and the like.

The polyols used to make polyurethanes are polymers which have multiple reactive sites (e.g.
15 multiple hydroxyl functional groups). The polyols which are most commonly used are based on
polyethers or polyesters.

One method for making polyether polyols in industry is by reacting an epoxide with a double
metal cyanide (DMC) catalyst in the presence of a starter compound.

20 The nature and properties of the polyols have a great impact on the nature and the properties of
the resultant polyurethanes. It is desirable to include polycarbonate linkages in the backbone of
polyether polyols, as carbonate linkages in the polyol may improve the properties of the
resultant polyurethane, for example, the presence of carbonate linkages may improve the UV
25 stability, hydrolytic stability, chemical resistance and/or mechanical strength of the resulting
polyurethane. The presence of carbonate linkages also increases the viscosity of the resulting
polyol, which can limit use in some applications. It is therefore important to be able to control the
ratio of ether linkages to carbonate linkages in polyols to tailor properties for widespread
application. It is also important to be able to control the molecular weight and polydispersity of
30 the polyol, as these properties impact usefulness and ease of processing of the resultant
polyols.

DMC catalysts for use in the preparation of polyethers were first disclosed in US 3427256 by
The General Tyre and Rubber Company. It was subsequently found that carrying out this
35 reaction in the presence of a starter compound yielded a polyether polyol.

DMC catalysts are also capable of preparing polyether polyols which contain carbonate linkages
in the polymer backbone (hereinafter referred to as polycarbonate ether polyols). To prepare

these types of polymers, the reaction is typically carried out at high pressures of carbon dioxide. It has generally been found that, for DMC catalysts, in order to obtain appreciable incorporation of carbon dioxide, the reaction must be carried out at pressures of 40 bar or above. This is undesirable as industrial equipment for preparing polyols are typically limited to pressures of up to 10 bar. For example, in US 2013/0072602, the examples set out the polymerisation of propylene oxide in the presence of a starter compound, and an additive at 50 bar CO₂. The resulting polycarbonate ether polyols incorporate between 17.8 and 24.1 wt% CO₂. Similar results can be seen in US 2013/0190462.

- 10 In WO 2015/022290, the examples show that when the polymerisation of propylene oxide is carried out in the presence of a DMC catalyst and a starter compound in the range of 15-25 bar CO₂, the resulting polyols incorporated between 10.0 and 15.4 wt% CO₂.


- 15 It is therefore desirable to be able to prepare polycarbonate ether polyols under pressures used in industrial polyether polyol equipment. It is also desirable to obtain appreciable incorporation of carbon dioxide (e.g. ≥ 20 wt% carbon dioxide, which requires a proportion of carbonate linkages of ~ 0.5 in the polymer backbone, depending on the nature of the starter used) under low pressures.

- 20 WO 2010/028362 discloses a method for making polycarbonate polyols by copolymerising carbon dioxide and an epoxide in the presence of a chain transfer agent and a catalyst having a permanent ligand set which complexes a single metal atom. The polyols prepared in the examples have a proportion of carbonate linkages ≥ 0.95 in the polymer backbone. These systems are designed to prepare polycarbonates having little or no ether linkages in the polymer backbones. Furthermore, each of the examples is carried out at high pressures of 300 psig (about 20 bar) carbon dioxide.

WO 2013/034750 discloses a method for preparing polycarbonate polyols using a catalyst of formula (I):


30

35



The polyols prepared in the examples have $\geq 95\%$ carbonate linkages, and generally $\geq 99\%$ carbonate linkages in the polymer backbone.

WO 2012/121508 relates to a process for preparing polycarbonate ethers, which are ultimately intended for use as resins and soft plastics. This document is not concerned with preparing polyols. The process disclosed in WO 2012/121508 requires the copolymerisation of an epoxide and carbon dioxide in the presence of a DMC catalyst and a metal salen catalyst having the following formula:



The examples are each carried out at 16 bar CO_2 or above. The resulting polycarbonate ethers contain varying amounts of ether and carbonate linkages. However, said polymers have a high molecular weight, have high polydispersity indices (that is, PDIs of 3.8 and above) and are not terminated by hydroxyl groups. These polymers cannot therefore be used to make polyurethanes.


Gao *et al*, Journal of Polymer Science Part A: Polymer Chemistry, 2012, 50, 5177-5184, describes a method for preparing low molecular weight polycarbonate ether polyol using a DMC catalyst and a di-carboxylic acid starter. The proportion of carbonate linkages can be increased up to 0.75 in the resultant polyols by decreasing the temperature (50°C) and increasing the pressure (40 bar), when using a dicarboxylic acid starter which is apparently crucial to the ability to prepare polyols with high proportions of carbonate linkages. These conditions are unfavourable for economic industrial application. Gao *et al* suggests that dual catalysts systems for preparing polycarbonate ether polyols are unfavourable.

With previously reported catalyst systems, even at the widest range of temperature and pressures that have been deployed, it has reportedly not been possible to prepare polyols with proportions of carbonate linkages between 0.75 and 0.9.

Summary of the Invention

The invention relates to a method for preparing a polycarbonate ether polyol by reacting an epoxide and carbon dioxide in the presence of a catalyst of formula (I), a double metal cyanide (DMC) catalyst and a starter compound.

The catalyst of formula (I) is as follows:



wherein:

M_1 and M_2 are independently selected from Zn(II), Cr(II), Co(II), Cu(II), Mn(II), Mg(II), Ni(II), Fe(II), Ti(II), V(II), Cr(III)-X, Co(III)-X, Mn(III)-X, Ni(III)-X, Fe(III)-X, Ca(II), Ge(II), Al(III)-X, Ti(III)-X, V(III)-X, Ge(IV)-(X)₂ or Ti(IV)-(X)₂;

R_1 and R_2 are independently selected from hydrogen, halide, a nitro group, a nitrile group, an imine, an amine, an ether group, a silyl group, a silyl ether group, a sulfoxide group, a sulfonyl group, a sulfinate group or an acetylide group or an optionally substituted alkyl, alkenyl, alkynyl, haloalkyl, aryl, heteroaryl, alkoxy, aryloxy, alkylthio, arylthio, alicyclic or heteroalicyclic group;

R_3 is independently selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, arylene, heteroarylene or cycloalkylene, wherein alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene and heteroalkynylene, may optionally be interrupted by aryl, heteroaryl, alicyclic or heteroalicyclic;

R_5 is independently selected from H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl;

E_1 is C and E_2 is O;

E_3 , E_4 , E_5 and E_6 are selected from N, NR_4 , O and S, wherein when E_3 , E_4 , E_5 or E_6 are N, ----- is $\equiv$, and wherein when E_3 , E_4 , E_5 or E_6 are NR_4 , O or S, ----- is

—; R_4 is independently selected from H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl, -alkylC(O)OR₁₉ or -alkylC≡N or alkylaryl;


X is independently selected from OC(O)R^x, OSO₂R^x, OSOR^x, OSO(R^x)₂, S(O)R^x, OR^x,
5 phosphinate, halide, nitrate, hydroxyl, carbonate, amino, amido or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl;

R_x is independently hydrogen, or optionally substituted aliphatic, haloaliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, alkylaryl or heteroaryl; and

G is absent or independently selected from a neutral or anionic donor ligand which is a
10 Lewis base.

The DMC catalyst comprises at least two metal centres and cyanide ligands. The DMC catalyst may additionally comprise an organic complexing agent, water and/or a metal salt (e.g. in non-stoichiometric amounts).

For example, the DMC catalyst may comprise:



Wherein M' is selected from Zn(II), Fe(II), Ni(II), Mn(II), Co(II), Sn(II), Pb(II), Fe(III), Mo(IV),
20 Mo(VI), Al(III), V(V), V(VI), Sr(II), W(IV), W(VI), Cu(II), and Cr(III),

M'' is selected from Fe(II), Fe(III), Co(II), Co(III), Cr(II), Cr(III), Mn(II), Mn(III), Ir(III), Ni(II), Rh(III), Ru(II), V(IV), and V(V); and

d, e, f and g are integers, and are chosen to such that the DMC catalyst has electroneutrality.

25 The starter compound may be of the formula (III):



Z can be any group which can have 2 or more -R^Z groups attached to it. Thus, Z may be selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene,
30 heteroalkenylene, heteroalkynylene, cycloalkylene, cycloalkenylene, heterocycloalkylene, heterocycloalkenylene, arylene, heteroarylene, or Z may be a combination of any of these groups, for example Z may be an alkylarylene, heteroalkylarylene, heteroalkylheteroarylene or alkylheteroarylene group.

35 a is an integer which is at least 2, each R^Z may be -OH, -NHR', -SH, -C(O)OH, -P(O)(OR')(OH), -PR'(O)(OH)₂ or -PR'(O)OH, and R' may be H, or optionally substituted alkyl, heteroalkyl, aryl, heteroaryl, cycloalkyl or heterocycloalkyl.

The method can be carried out at pressure of between about 1 bar and about 60 bar, between about 1 bar and about 30 bar, between about 1 bar and about 20 bar, between about 1 bar and about 15 bar, or between about 1 bar and about 10 bar carbon dioxide. It will also be appreciated that the reaction is capable of being carried out at a pressure of about 5 bar or below.

The method can be carried out at temperatures of from about 0°C to about 250°C, for example from about 40°C to about 140°C, e.g. from about 50°C to about 110°C, such as from about 60°C to about 100°C, for example, from about 70°C to about 100°C.

The invention also provides a polymerisation system for the copolymerisation of carbon dioxide and an epoxide, comprising:

- a. A catalyst of formula (I) as defined herein,
- b. A DMC catalyst as defined herein, and
- c. A starter compound as herein.

The invention is capable of preparing polycarbonate ether polyols which have n ether linkages and m carbonate linkages, wherein n and m are integers, and wherein $m/(n+m)$ is from greater than zero to less than 1.

The polyols prepared by the method of the invention may be used for further reactions, for example to prepare a polyurethane, for example by reacting a polyol composition comprising a polyol prepared by the method of the invention with a composition comprising a di- or polyisocyanate.

Brief Description of Figures

Figure 1 is a GPC trace for Run 3 in Table 1, showing the narrow polydispersity polyol produced by the combination of a catalyst of formula (I) and a DMC catalyst.

Figure 2 is a GPC trace for Run 2 in Table 1, demonstrating the high polydispersity polyol produced by using a DMC catalyst alone.

Figure 3 is a GPC trace for Run 3 in Table 2, using 1,6-hexanediol as a starter.

Figure 4 is a GPC trace for Run 2 in Table 2, using PPG-725 as a starter.

Figure 5 is a GPC trace for Run 1 in Table 2, using PPG-1000 as a starter.

Figure 6 shows the viscosity at 75 °C of (approximately) Mw 2000 polyols prepared in Example 2, having varying CO₂ content.

Figure 7 shows the viscosity at 25 °C of (approximately) Mw 2000 polyols prepared in Example 2, having varying CO₂ content.

Figure 8 is a ¹H NMR spectrum of the polyol prepared in Example 2a, containing 33 wt% CO₂.

Figure 9 is a ¹H NMR spectrum of the polyol prepared in Example 2b, containing 26.6 wt% CO₂ and an R_{PEC} of 0.67.

Figure 10 show the overlaid Thermogravimetrics Analysis (TGA) traces for examples 2a-e and Benchmark B2.

Definitions

For the purpose of the present invention, an aliphatic group is a hydrocarbon moiety that may be straight chain or branched and may be completely saturated, or contain one or more units of unsaturation, but which is not aromatic. The term “unsaturated” means a moiety that has one or more double and/or triple bonds. The term “aliphatic” is therefore intended to encompass alkyl, alkenyl or alkynyl groups, and combinations thereof. An aliphatic group is preferably a C₁₋₂₀ aliphatic group, that is, an aliphatic group with 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an aliphatic group is a C₁₋₁₅aliphatic, more preferably a C₁₋₁₂aliphatic, more preferably a C₁₋₁₀aliphatic, even more preferably a C₁₋₈aliphatic, such as a C₁₋₆aliphatic group.

An alkyl group is preferably a “C₁₋₂₀ alkyl group”, that is an alkyl group that is a straight or branched chain with 1 to 20 carbons. The alkyl group therefore has 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an alkyl group is a C₁₋₁₅ alkyl, preferably a C₁₋₁₂ alkyl, more preferably a C₁₋₁₀ alkyl, even more preferably a C₁₋₈ alkyl, even more preferably a C₁₋₆ alkyl group. Specifically, examples of “C₁₋₂₀ alkyl group” include methyl group, ethyl group, n-propyl group, iso-propyl group, n-butyl group, iso-

butyl group, sec-butyl group, tert-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, n-nonyl group, n-decyl group, n-undecyl group, n-dodecyl group, n-tridecyl group, n-tetradecyl group, n-pentadecyl group, n-hexadecyl group, n-heptadecyl group, n-octadecyl group, n-nonadecyl group, n-eicosyl group, 1,1-dimethylpropyl group, 1,2-dimethylpropyl group, 2,2-dimethylpropyl group, 1-ethylpropyl group, n-hexyl group, 1-ethyl-2-methylpropyl group, 1,1,2-trimethylpropyl group, 1-ethylbutyl group, 1-methylbutyl group, 2-methylbutyl group, 1,1-

dimethylbutyl group, 1,2-dimethylbutyl group, 2,2-dimethylbutyl group, 1,3-dimethylbutyl group, 2,3-dimethylbutyl group, 2-ethylbutyl group, 2-methylpentyl group, 3-methylpentyl group and the like.

- 5 Alkenyl and alkynyl groups are preferably “C₂₋₂₀alkenyl” and “C₂₋₂₀alkynyl”, more preferably “C₂₋₁₅ alkenyl” and “C₂₋₁₅ alkynyl”, even more preferably “C₂₋₁₂ alkenyl” and “C₂₋₁₂ alkynyl”, even more preferably “C₂₋₁₀ alkenyl” and “C₂₋₁₀ alkynyl”, even more preferably “C₂₋₈ alkenyl” and “C₂₋₈ alkynyl”, most preferably “C₂₋₆ alkenyl” and “C₂₋₆ alkynyl” groups, respectively.
- 10 A heteroaliphatic group (including heteroalkyl, heteroalkenyl and heteroalkynyl) is an aliphatic group as described above, which additionally contains one or more heteroatoms. Heteroaliphatic groups therefore preferably contain from 2 to 21 atoms, preferably from 2 to 16 atoms, more preferably from 2 to 13 atoms, more preferably from 2 to 11 atoms, more preferably from 2 to 9 atoms, even more preferably from 2 to 7 atoms, wherein at least one
- 15 atom is a carbon atom. Particularly preferred heteroatoms are selected from O, S, N, P and Si. When heteroaliphatic groups have two or more heteroatoms, the heteroatoms may be the same or different.

- An alicyclic group is a saturated or partially unsaturated cyclic aliphatic monocyclic or polycyclic
- 20 (including fused, bridging and spiro-fused) ring system which has from 3 to 20 carbon atoms, that is an alicyclic group with 3, 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 17, 18, 19 or 20 carbon atoms. Preferably, an alicyclic group has from 3 to 15, more preferably from 3 to 12, even more preferably from 3 to 10, even more preferably from 3 to 8 carbon atoms, even more preferably from 3 to 6 carbons atoms. The term “alicyclic” encompasses cycloalkyl, cycloalkenyl
- 25 and cycloalkynyl groups. It will be appreciated that the alicyclic group may comprise an alicyclic ring bearing one or more linking or non-linking alkyl substituents, such as –CH₂-cyclohexyl. Specifically, examples of the C₃₋₂₀ cycloalkyl group include cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl, adamantyl and cyclooctyl.

- 30 A heteroalicyclic group is an alicyclic group as defined above which has, in addition to carbon atoms, one or more ring heteroatoms, which are preferably selected from O, S, N, P and Si. Heteroalicyclic groups preferably contain from one to four heteroatoms, which may be the same or different. Heteroalicyclic groups preferably contain from 5 to 20 atoms, more preferably from 5 to 14 atoms, even more preferably from 5 to 12 atoms.

- 35 An aryl group is a monocyclic or polycyclic ring system having from 5 to 20 carbon atoms. An aryl group is preferably a “C₆₋₁₂ aryl group” and is an aryl group constituted by 6, 7, 8, 9, 10, 11 or 12 carbon atoms and includes condensed ring groups such as monocyclic ring group, or

bicyclic ring group and the like. Specifically, examples of "C₆₋₁₀ aryl group" include phenyl group, biphenyl group, indenyl group, naphthyl group or azulenyl group and the like. It should be noted that condensed rings such as indan and tetrahydro naphthalene are also included in the aryl group.

5

A heteroaryl group is an aryl group having, in addition to carbon atoms, from one to four ring heteroatoms which are preferably selected from O, S, N, P and Si. A heteroaryl group preferably has from 5 to 20, more preferably from 5 to 14 ring atoms. Specifically, examples of a heteroaryl group include pyridine, imidazole, methylimidazole and dimethylaminopyridine.

10

Examples of alicyclic, heteroalicyclic, aryl and heteroaryl groups include but are not limited to cyclohexyl, phenyl, acridine, benzimidazole, benzofuran, benzothiophene, benzoxazole, benzothiazole, carbazole, cinnoline, dioxin, dioxane, dioxolane, dithiane, dithiazine, dithiazole, dithiolane, furan, imidazole, imidazoline, imidazolidine, indole, indoline, indolizine, indazole, isoindole, isoquinoline, isoxazole, isothiazole, morpholine, naphthyridine, oxazole, oxadiazole, oxathiazole, oxathiazolidine, oxazine, oxadiazine, phenazine, phenothiazine, phenoxazine, phthalazine, piperazine, piperidine, pteridine, purine, pyran, pyrazine, pyrazole, pyrazoline, pyrazolidine, pyridazine, pyridine, pyrimidine, pyrrole, pyrrolidine, pyrroline, quinoline, quinoxaline, quinazoline, quinolizine, tetrahydrofuran, tetrazine, tetrazole, thiophene, thiadiazine, thiadiazole, thiatriazole, thiazine, thiazole, thiomorpholine, thianaphthalene, thiopyran, triazine, triazole, and trithiane.

20

The term "halide" or "halogen" are used interchangeably and, as used herein mean a fluorine atom, a chlorine atom, a bromine atom, an iodine atom and the like, preferably a fluorine atom, a bromine atom or a chlorine atom, and more preferably a fluorine atom.

25

A haloalkyl group is preferably a "C₁₋₂₀ haloalkyl group", more preferably a "C₁₋₁₅ haloalkyl group", more preferably a "C₁₋₁₂ haloalkyl group", more preferably a "C₁₋₁₀ haloalkyl group", even more preferably a "C₁₋₈ haloalkyl group", even more preferably a "C₁₋₆ haloalkyl group" and is a C₁₋₂₀ alkyl, a C₁₋₁₅ alkyl, a C₁₋₁₂ alkyl, a C₁₋₁₀ alkyl, a C₁₋₈ alkyl, or a C₁₋₆ alkyl group, respectively, as described above substituted with at least one halogen atom, preferably 1, 2 or 3 halogen atom(s). Specifically, examples of "C₁₋₂₀ haloalkyl group" include fluoromethyl group, difluoromethyl group, trifluoromethyl group, fluoroethyl group, difluoroethyl group, trifluoroethyl group, chloromethyl group, bromomethyl group, iodomethyl group and the like.

35

An alkoxy group is preferably a "C₁₋₂₀ alkoxy group", more preferably a "C₁₋₁₅ alkoxy group", more preferably a "C₁₋₁₂ alkoxy group", more preferably a "C₁₋₁₀ alkoxy group", even more preferably a "C₁₋₈ alkoxy group", even more preferably a "C₁₋₆ alkoxy group" and is an oxy group

that is bonded to the previously defined C₁₋₂₀ alkyl, C₁₋₁₅ alkyl, C₁₋₁₂ alkyl, C₁₋₁₀ alkyl, C₁₋₈ alkyl, or C₁₋₆ alkyl group respectively. Specifically, examples of "C₁₋₂₀ alkoxy group" include methoxy group, ethoxy group, n-propoxy group, iso-propoxy group, n-butoxy group, iso-butoxy group, sec-butoxy group, tert-butoxy group, n-pentyloxy group, iso-pentyloxy group, sec-pentyloxy group, n-hexyloxy group, iso-hexyloxy group, , n-hexyloxy group, n-heptyloxy group, n-octyloxy group, n-nonyloxy group, n-decyloxy group, n-undecyloxy group, n-dodecyloxy group, n-tridecyloxy group, n-tetradecyloxy group, n-pentadecyloxy group, n-hexadecyloxy group, n-heptadecyloxy group, n-octadecyloxy group, n-nonadecyloxy group, n-eicosyloxy group, 1,1-dimethylpropoxy group, 1,2-dimethylpropoxy group, 2,2-dimethylpropoxy group, 2-methylbutoxy group, 1-ethyl-2-methylpropoxy group, 1,1,2-trimethylpropoxy group, 1,1-dimethylbutoxy group, 1,2-dimethylbutoxy group, 2,2-dimethylbutoxy group, 2,3-dimethylbutoxy group, 1,3-dimethylbutoxy group, 2-ethylbutoxy group, 2-methylpentyloxy group, 3-methylpentyloxy group and the like.

15 An aryloxy group is preferably a "C₅₋₂₀ aryloxy group", more preferably a "C₆₋₁₂ aryloxy group", even more preferably a "C₆₋₁₀ aryloxy group" and is an oxy group that is bonded to the previously defined C₅₋₂₀ aryl, C₆₋₁₂ aryl, or C₆₋₁₀ aryl group respectively.

20 An alkylthio group is preferably a "C₁₋₂₀ alkylthio group", more preferably a "C₁₋₁₅ alkylthio group", more preferably a "C₁₋₁₂ alkylthio group", more preferably a "C₁₋₁₀ alkylthio group", even more preferably a "C₁₋₈ alkylthio group", even more preferably a "C₁₋₆ alkylthio group" and is a thio (-S-) group that is bonded to the previously defined C₁₋₂₀ alkyl, C₁₋₁₅ alkyl, C₁₋₁₂ alkyl, C₁₋₁₀ alkyl, C₁₋₈ alkyl, or C₁₋₆ alkyl group respectively.

25 An arylthio group is preferably a "C₅₋₂₀ arylthio group", more preferably a "C₆₋₁₂ arylthio group", even more preferably a "C₆₋₁₀ arylthio group" and is a thio (-S-) group that is bonded to the previously defined C₅₋₂₀ aryl, C₆₋₁₂ aryl, or C₆₋₁₀ aryl group respectively.

30 An alkylaryl group is preferably a "C₆₋₁₂ aryl C₁₋₂₀ alkyl group", more preferably a preferably a "C₆₋₁₂ aryl C₁₋₁₆ alkyl group", even more preferably a "C₆₋₁₂ aryl C₁₋₆ alkyl group" and is an aryl group as defined above bonded at any position to an alkyl group as defined above. The point of attachment of the alkylaryl group to a molecule may be via the alkyl portion and thus, preferably, the alkylaryl group is -CH₂-Ph or -CH₂CH₂-Ph. An alkylaryl group can also be referred to as "aralkyl".

35 A silyl group is preferably a group -Si(R_s)₃, wherein each R_s can be independently an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain

embodiments, each R_s is independently an unsubstituted aliphatic, alicyclic or aryl. Preferably, each R_s is an alkyl group selected from methyl, ethyl or propyl.

A silyl ether group is preferably a group $OSi(R_6)_3$ wherein each R_6 can be independently an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, each R_6 can be independently an unsubstituted aliphatic, alicyclic or aryl. Preferably, each R_6 is an optionally substituted phenyl or optionally substituted alkyl group selected from methyl, ethyl, propyl or butyl (such as n-butyl or tert-butyl (tBu)). Exemplary silyl ether groups include $OSi(Me)_3$, $OSi(Et)_3$, $OSi(Ph)_3$, $OSi(Me)_2(tBu)$, $OSi(tBu)_3$ and $OSi(Ph)_2(tBu)$.

A nitrile group (also referred to as a cyano group) is a group CN.

An imine group is a group $-CRNR$, preferably a group $-CHNR_7$ wherein R_7 is an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_7 is unsubstituted aliphatic, alicyclic or aryl. Preferably R_7 is an alkyl group selected from methyl, ethyl or propyl.

An acetylide group contains a triple bond $-C\equiv C-R_9$, preferably wherein R_9 can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above.

For the purposes of the invention when R_9 is alkyl, the triple bond can be present at any position along the alkyl chain. In certain embodiments, R_9 is unsubstituted aliphatic, alicyclic or aryl. Preferably R_9 is methyl, ethyl, propyl or phenyl.

An amino group is preferably $-NH_2$, $-NHR_{10}$ or $-N(R_{10})_2$ wherein R_{10} can be an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, a silyl group, aryl or heteroaryl group as defined above. It will be appreciated that when the amino group is $N(R_{10})_2$, each R_{10} group can be the same or different. In certain embodiments, each R_{10} is independently an unsubstituted aliphatic, alicyclic, silyl or aryl. Preferably R_{10} is methyl, ethyl, propyl, $SiMe_3$ or phenyl.

An amido group is preferably $-NR_{11}C(O)-$ or $-C(O)-NR_{11}-$ wherein R_{11} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{11} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{11} is hydrogen, methyl, ethyl, propyl or phenyl. The amido group may be terminated by hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group.

An ester group is preferably $-OC(O)R_{12}-$ or $-C(O)OR_{12}-$ wherein R_{12} can be an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{12} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{12} is methyl, ethyl,

propyl or phenyl. The ester group may be terminated by an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group. It will be appreciated that if R_{12} is hydrogen, then the group defined by $-OC(O)R_{12}-$ or $-C(O)OR_{12}-$ will be a carboxylic acid group.

- 5 A sulfoxide is preferably $-S(O)R_{13}$ and a sulfonyl group is preferably $-S(O)_2R_{13}$ wherein R_{13} can be an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{13} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{13} is methyl, ethyl, propyl or phenyl.
- 10 A carboxylate group is preferably $-OC(O)R_{14}$, wherein R_{14} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{14} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{14} is hydrogen, methyl, ethyl, propyl, butyl (for example n-butyl, isobutyl or tert-butyl), phenyl, pentafluorophenyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, trifluoromethyl or adamantyl.
- 15

An acetamide is preferably $MeC(O)N(R_{15})_2$ wherein R_{15} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{15} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{15} is hydrogen, methyl, ethyl, propyl or phenyl.

20

A phosphinate group is preferably a group $-OP(O)(R_{16})_2$ or $-P(O)(OR_{16})(R_{16})$ wherein each R_{16} is independently selected from hydrogen, or an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{16} is

25 aliphatic, alicyclic or aryl, which are optionally substituted by aliphatic, alicyclic, aryl or C_{1-6} alkoxy. Preferably R_{16} is optionally substituted aryl or C_{1-20} alkyl, more preferably phenyl optionally substituted by C_{1-6} alkoxy (preferably methoxy) or unsubstituted C_{1-20} alkyl (such as hexyl, octyl, decyl, dodecyl, tetradecyl, hexadecyl, stearyl). A phosphonate group is preferably a group $-P(O)(OR_{16})_2$ wherein R_{16} is as defined above. It will be appreciated that when either or

30 both of R_{16} is hydrogen for the group $-P(O)(OR_{16})_2$, then the group defined by $-P(O)(OR_{16})_2$ will be a phosphonic acid group.

A sulfinate group is preferably $-S(O)OR_{17}$ or $-OS(O)R_{17}$ wherein R_{17} can be hydrogen, an aliphatic, heteroaliphatic, haloaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as

35 defined above. In certain embodiments, R_{17} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{17} is hydrogen, methyl, ethyl, propyl or phenyl. It will be appreciated that if R_{17} is hydrogen, then the group defined by $-S(O)OR_{17}$ will be a sulfonic acid group.

A carbonate group is preferably -OC(O)OR_{18} , wherein R_{18} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{18} is optionally substituted aliphatic, alicyclic or aryl. Preferably R_{18} is hydrogen, methyl, ethyl, propyl, butyl (for example n-butyl, isobutyl or tert-butyl), phenyl,

- 5 pentafluorophenyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl, trifluoromethyl, cyclohexyl, benzyl or adamantyl. It will be appreciated that if R_{17} is hydrogen, then the group defined by -OC(O)OR_{18} will be a carbonic acid group.
- 10 In an -alkylC(O)OR_{19} or -alkylC(O)R_{19} group, R_{19} can be hydrogen, an aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. In certain embodiments, R_{19} is unsubstituted aliphatic, alicyclic or aryl. Preferably R_{19} is hydrogen, methyl, ethyl, propyl, butyl (for example n-butyl, isobutyl or tert-butyl), phenyl, pentafluorophenyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl,
- 15 octadecyl, nonadecyl, eicosyl, trifluoromethyl or adamantyl.


It will be appreciated that where any of the above groups are present in a Lewis base G, one or more additional R groups may be present, as appropriate, to complete the valency. For example, in the context of an amino group, an additional R group may be present to give

- 20 RNHR_{10} , wherein R is hydrogen, an optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl group as defined above. Preferably, R is hydrogen or aliphatic, alicyclic or aryl.


Any of the aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, haloalkyl, alkoxy, aryloxy, alkylthio, arylthio, alkylaryl, silyl, silyl ether, ester, sulfoxide, sulfonyl, carboxylate, carbonate, imine, acetylde, amino, phosphinate, sulfonate or amido groups wherever mentioned in the definitions above, may optionally be substituted by halogen, hydroxy, nitro, carboxylate, carbonate, alkoxy, aryloxy, alkylthio, arylthio, heteroaryloxy, alkylaryl, amino, amido, imine, nitrile, silyl, silyl ether, ester, sulfoxide, sulfonyl, acetylde, phosphinate, sulfonate or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl groups (for example, optionally substituted by halogen, hydroxy, nitro, carbonate, alkoxy, aryloxy, alkylthio, arylthio, amino, imine, nitrile, silyl, sulfoxide, sulfonyl, phosphinate, sulfonate or acetylde).


- 35 It will be appreciated that although in formula (I), the groups X and G are illustrated as being associated with a single M_1 or M_2 metal centre, one or more X and G groups may form a bridge between the M_1 and M_2 metal centres.

For the purposes of the present invention, the epoxide substrate is not limited. The term epoxide therefore relates to any compound comprising an epoxide moiety. Examples of epoxides which may be used in the present invention include, but are not limited to, cyclohexene oxide, styrene oxide, ethylene oxide, propylene oxide, butylene oxide, substituted cyclohexene oxides (such as limonene oxide, $C_{10}H_{16}O$ or 2-(3,4-epoxycyclohexyl)ethyltrimethoxysilane, $C_{11}H_{22}O$), alkylene oxides (such as ethylene oxide and substituted ethylene oxides), unsubstituted or substituted oxiranes (such as oxirane, epichlorohydrin, 2-(2-methoxyethoxy)methyl oxirane (MEMO), 2-(2-(2-methoxyethoxy)ethoxy)methyl oxirane (ME2MO), 2-(2-(2-(2-methoxyethoxy)ethoxy)ethoxy)methyl oxirane (ME3MO), 1,2-epoxybutane, glycidyl ethers, vinyl-cyclohexene oxide, 3-phenyl-1,2-epoxypropane, 1,2- and 2,3-epoxybutane, isobutylene oxide, cyclopentene oxide, 2,3-epoxy-1,2,3,4-tetrahydronaphthalene, indene oxide, and functionalized 3,5-dioxaeponoxides. Examples of functionalized 3,5-dioxaeponoxides include:



The epoxide moiety may be a glycidyl ether, glycidyl ester or glycidyl carbonate. Examples of glycidyl ethers, glycidyl esters glycidyl carbonates include:





The epoxide substrate may contain more than one epoxide moiety, i.e. it may be a bis-epoxide, a tris-epoxide, or a multi-epoxide containing moiety. Examples of compounds including more than one epoxide moiety include bisphenol A diglycidyl ether and 3,4-epoxycyclohexylmethyl 3,4-epoxycyclohexanecarboxylate. It will be understood that reactions carried out in the presence of one or more compounds having more than one epoxide moiety may lead to cross-linking in the resulting polymer.

The skilled person will appreciate that the epoxide can be obtained from “green” or renewable resources. The epoxide may be obtained from a (poly)unsaturated compound, such as those deriving from a fatty acid and/or terpene, obtained using standard oxidation chemistries.

The epoxide moiety may contain –OH moieties, or protected –OH moieties. The –OH moieties may be protected by any suitable protecting group. Suitable protecting groups include methyl or other alkyl groups, benzyl, allyl, tert-butyl, tetrahydropyranyl (THP), methoxymethyl (MOM), acetyl (C(O)alkyl), benzoyl (C(O)Ph), dimethoxytrityl (DMT), methoxyethoxymethyl (MEM), p-methoxybenzyl (PMB), trityl, silyl (such as trimethylsilyl (TMS), *t*-Butyldimethylsilyl (TBDMS), *t*-Butyldiphenylsilyl (TBDPS), tri-*iso*-propylsilyloxymethyl (TOM), and triisopropylsilyl (TIPS)), (4-methoxyphenyl)diphenylmethyl (MMT), tetrahydrofuranyl (THF), and tetrahydropyranyl (THP).

The epoxide preferably has a purity of at least 98%, more preferably >99%.


It will be understood that the term “an epoxide” is intended to encompass one or more epoxides. In other words, the term “an epoxide” refers to a single epoxide, or a mixture of two or more different epoxides. For example, the epoxide substrate may be a mixture of ethylene oxide and propylene oxide, a mixture of cyclohexene oxide and propylene oxide, a mixture of ethylene oxide and cyclohexene oxide, or a mixture of ethylene oxide, propylene oxide and cyclohexene oxide.

Detailed Description

The present invention provides a method for reacting an epoxide with carbon dioxide in the presence of a catalyst of formula (I), a double metal cyanide (DMC) catalyst, and a starter compound.

Catalysts of formula (I)

The catalyst of formula (I) has the following structure:



wherein:

M_1 and M_2 are independently selected from Zn(II), Cr(II), Co(II), Cu(II), Mn(II), Mg(II), Ni(II), Fe(II), Ti(II), V(II), Cr(III)-X, Co(III)-X, Mn(III)-X, Ni(III)-X, Fe(III)-X, Ca(II), Ge(II), Al(III)-X, Ti(III)-X, V(III)-X, Ge(IV)-(X)₂ or Ti(IV)-(X)₂;

R_1 and R_2 are independently selected from hydrogen, halide, a nitro group, a nitrile group, an imine, an amine, an ether group, a silyl group, a silyl ether group, a sulfoxide group, a sulfonyl group, a sulfinate group or an acetylide group or an optionally substituted alkyl, alkenyl, alkynyl, haloalkyl, aryl, heteroaryl, alkoxy, aryloxy, alkylthio, arylthio, alicyclic or heteroalicyclic group;

R_3 is independently selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, arylene, heteroarylene or cycloalkylene, wherein alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene and heteroalkynylene, may optionally be interrupted by aryl, heteroaryl, alicyclic or heteroalicyclic;

R_5 is independently selected from H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl;

E_1 is C and E_2 is O;

E_3 , E_4 , E_5 and E_6 are selected from N, NR_4 , O and S, wherein when E_3 , E_4 , E_5 or E_6 are N, ----- is =====, and wherein when E_3 , E_4 , E_5 or E_6 are NR_4 , O or S, ----- is -----; R_4 is independently selected from H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl, -alkylC(O)OR₁₉ or -alkylC≡N or alkylaryl;

X is independently selected from OC(O)R^x, OSO₂R^x, OSOR^x, OSO(R^x)₂, S(O)R^x, OR^x, phosphinate, halide, nitrate, hydroxyl, carbonate, amino, amido or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl;

R_x is independently hydrogen, or optionally substituted aliphatic, haloaliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, alkylaryl or heteroaryl; and

G is absent or independently selected from a neutral or anionic donor ligand which is a Lewis base.

5

Each of the occurrences of the groups R₁ and R₂ may be the same or different, and R₁ and R₂ can be the same or different.

Preferably R₁ and R₂ are independently selected from hydrogen, halide, amino, nitro, sulfoxide, sulfonyl, sulfinate, and an optionally substituted alkyl, alkenyl, aryl, heteroaryl, silyl, silyl ether, alkoxy, aryloxy or alkylthio. Preferably each occurrence of R₂ is the same. Preferably, each occurrence of R₂ is the same, and is hydrogen.

Both occurrences of R₁ may be the same, and may be selected from hydrogen, halide, amino, nitro, sulfoxide, sulfonyl, sulfinate, silyl, silyl ether and an optionally substituted alkyl, alkenyl, aryl, heteroaryl, alkoxy, aryloxy or alkylthio. For example, both occurrences of R₁ may be the same, and may be selected from hydrogen, halide, sulfoxide, and an optionally substituted alkyl, heteroaryl, silyl, alkylthio or alkoxy. Exemplary options for R₁ (which may both be the same) include hydrogen, methyl, t-butyl, methoxy, ethoxy, alkylthio, trialkylsilyl such as trimethylsilyl or triethylsilyl, bromide, methanesulfonyl, or piperidinyl, e.g. both occurrences of R₁ may be the same, and may be selected from methyl, t-butyl or trialkylsilyl.

Preferably, each occurrence of R₂ is hydrogen and each R₁ is independently selected from hydrogen, halide, amino, nitro, sulfoxide, sulfonyl, sulfinate, and optionally substituted alkyl, alkenyl, aryl, heteroaryl, silyl, silyl ether, alkoxy, aryloxy, alkylthio, arylthio, such as hydrogen, C₁₋₆ alkyl (e.g. haloalkyl), alkoxy, aryl, halide, nitro, sulfonyl, silyl and alkylthio, for example, ^tBu, iPr, Me, OMe, H, nitro, SO₂Me, SiEt₃, SiMe₃, SMe, halogen or phenyl.

It will be understood that each occurrence of R₁ may be the same, and each occurrence of R₂ may be the same, and R₁ may be different to R₂.

It will be appreciated that the group R₃ can be a disubstituted divalent alkyl, alkenyl, alkynyl, heteroalkyl, heteroalkenyl or heteroalkynyl group which may optionally be interrupted by an aryl, heteroaryl, alicyclic or heteroalicyclic group, or may be a disubstituted aryl or cycloalkyl group which acts as a bridging group between two nitrogen centres in the catalyst of formula (I). Thus, where R₃ is an alkylene group, such as dimethylpropylenyl, the R₃ group has the structure –CH₂-C(CH₃)₂-CH₂–. The definitions of the alkyl, aryl, cycloalkyl etc groups set out above therefore also relate respectively to the divalent alkylene, arylene, cycloalkylene etc groups set

out for R₃, and may be optionally substituted. Exemplary options for R₃ include ethylenyl, 2,2-fluoropropylenyl, 2,2-dimethylpropylenyl, propylenyl, butylenyl, phenylenyl, cyclohexylenyl or biphenylenyl. When R₃ is cyclohexylenyl, it can be the racemic, RR- or SS- forms.

- 5 R₃ can be independently selected from substituted or unsubstituted alkylene and substituted or unsubstituted arylene, preferably substituted or unsubstituted propylenyl, such as propylenyl and 2,2-dimethylpropylenyl, and substituted or unsubstituted phenylenyl or biphenylenyl. Preferably both occurrences of R₃ are the same. Even more preferably R₃ is a substituted propylenyl, such as 2,2-di(alkyl)propylenyl, especially 2,2-di(methyl)propylenyl.

10

R₃ can be independently selected from substituted or unsubstituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene or heteroalkynylene, arylene or cycloalkylene.

Preferably, R₃ is selected from substituted or unsubstituted alkylene, cycloalkylene, alkenylene, heteroalkylene and arylene. More preferably, R₃ is selected from 2,2-dimethylpropylenyl, -CH₂

- 15 CH₂ CH₂-, -CH₂CH(CH₃)CH₂-, -CH₂C(CH₂C₆H₅)₂CH₂-, phenylene, -CH₂ CH₂-, -CH₂ CH₂ CH₂ CH₂-, -CH₂ CH₂N (CH₃) CH₂ CH₂-, 1,4-cyclohexandiyl or -CH₂CH₂CH (C₂H₅)-. Still more preferably R₃ is selected from 2,2-dimethylpropylenyl, -CH₂ CH₂ CH₂-, -CH₂CH(CH₃)CH₂-, -CH₂C(CH₂C₆H₅)₂CH₂-, -CH₂CH₂CH (C₂H₅)-, -CH₂ CH₂ CH₂ CH₂-. More preferably still, R₃ is selected from 2,2-dimethylpropylenyl, -CH₂C(CH₂C₆H₅)₂CH₂-, CH₂CH(CH₃)CH₂ and -CH₂

- 20 C(C₂H₅)₂ CH₂-.

Most preferably R₃ is a substituted propylenyl, such as 2,2-di(alkyl)propylenyl, more preferably 2,2-dimethylpropylenyl.

- 25 As set out above, E₃, E₄, E₅ and E₆ are each independently selected from N, NR₄, O and S. The skilled person will understand that if any of E₃, E₄, E₅ or E₆ are N, ----- is =====, and if any of E₃, E₄, E₅ or E₆ are NR₄, O or S, ----- is ----- . Preferably, E₃, E₄, E₅ and E₆ are each independently selected from NR₄, O and S.

- 30 Preferably each R₄ is independently selected from hydrogen, and an optionally substituted alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroalkenyl, heteroalkynyl, heteroaryl, -alkylC(O)OR₁₉ or -alkylC≡N. Each R₄ may be the same or different. Preferably, R₄ is selected from hydrogen, and an optionally substituted alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroalkenyl, heteroalkynyl or heteroaryl. Exemplary options for R₄ include H, Me, Et, Bn, iPr, tBu or Ph, and -CH₂-(pyridine).
- 35 Preferably each R₄ is hydrogen or alkyl.


Preferably each R₅ is independently selected from hydrogen, and optionally substituted aliphatic or aryl. More preferably, each R₅ is independently selected from hydrogen, and optionally

substituted alkyl or aryl. Even more preferably, each R_5 is the same, and is selected from hydrogen, and optionally substituted alkyl or aryl. Exemplary R_5 groups include hydrogen, methyl, ethyl, phenyl and trifluoromethyl, preferably hydrogen, methyl or trifluoromethyl. Even more preferably, each R_5 is hydrogen.

5

The skilled person will appreciate that the macrocyclic ligand of the catalyst of formula (I) may be symmetric, or may be asymmetric.

When the macrocyclic ligand is symmetric, it will be appreciated that each occurrence of E_3 , E_4 , E_5 and E_6 will be the same. For example, each occurrence of E_3 , E_4 , E_5 and E_6 may be NR_4 (and each R_4 may be the same). It will be understood that E_3 , E_4 , E_5 and E_6 may be the same and may be NH. In other words, the catalyst of formula (I) may have the following structure:



15 When the macrocyclic ligand is symmetric, it will be appreciated that each occurrence of R_1 may be the same, each occurrence of R_2 may be the same, each occurrence of R_3 may be the same, each occurrence of R_5 may be the same (although R_1 , R_2 , R_3 and R_5 are not necessarily the same as each other), and E_3 , E_4 , E_5 and E_6 are the same.

20 For example, each occurrence of R_2 , and R_5 may be hydrogen, each occurrence of E_3 , E_4 , E_5 and E_6 are NR_4 , and each R_4 is hydrogen or alkyl, each occurrence of R_3 may be substituted or unsubstituted alkylene, cycloalkylene, alkenylene, heteroalkylene and arylene, each occurrence of R_1 may be selected from hydrogen, halogen, sulfoxide or substituted or unsubstituted alkyl, heteroaryl, silyl, alkylthio or alkoxy.

25

When the ligand of the catalyst of formula (I) is asymmetric, it will be appreciated that at least one of the occurrences of the groups R_1 , R_2 , R_3 , R_4 , R_5 may be different from the remaining occurrences of the same group, or at least one occurrence of E_3 , E_4 , E_5 and E_6 is different to a

remaining occurrence of E₃, E₄, E₅ and E₆. For example each occurrence of R₃ may be different, or each occurrence of R₁ may be different.

It will also be appreciated that E₃ and E₅ may be the same, and E₄ and E₆ may be the same, but E₃ and E₅ are different to E₄ and E₆. It will also be appreciated that E₃ and E₄ may be the same, and E₅ and E₆ may be the same, but E₃ and E₄ are different to E₅ and E₆. Alternatively one occurrence of E₃, E₄, E₅ and E₆ is different to the remaining occurrences of E₃, E₄, E₅ and E₆ (and the remaining three occurrences are the same).

For example, E₃, E₄ and E₅ may be -NR₄ where R₄ is H, and E₆ may be NR₄ where R₄ is alkyl. Furthermore, E₃ and E₅ may be NR₄ where R₄ is H, and E₄ and E₆ may be NR₄ where R₄ is alkyl, or E₃ and E₄ may be NR₄ where R₄ is H, and E₅ and E₆ may be NR₄ where R₄ is alkyl. Thus, it will be appreciated that each E₃, E₄, E₅ and E₆ is preferably NR₄, where at least one occurrence of R₄ is different to the remaining occurrences of R₄.

For the catalysts of formula (I), (symmetric and asymmetric), each X is independently selected from OC(O)R^x, OSO₂R^x, OS(O)R^x, OSO(R^x)₂, S(O)R^x, OR^x, phosphinate, halide, nitro, hydroxyl, carbonate, amino, nitrate, amido and optionally substituted, aliphatic, heteroaliphatic (for example silyl), alicyclic, heteroalicyclic, aryl or heteroaryl. Preferably each X is independently OC(O)R^x, OSO₂R^x, OS(O)R^x, OSO(R^x)₂, S(O)R^x, OR^x, halide, nitrate, hydroxyl, carbonate, amino, nitro, amido, alkyl (e.g. branched alkyl), heteroalkyl, (for example silyl), aryl or heteroaryl. Even more preferably, each X is independently OC(O)R^x, OR^x, halide, carbonate, amino, nitro, alkyl, aryl, heteroaryl, phosphinate or OSO₂R^x. Preferred optional substituents for when X is aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl include halogen, hydroxyl, nitro, cyano, amino, or substituted or unsubstituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl. Each X may be the same or different and preferably each X is the same. It will also be appreciated that X may form a bridge between the two metal centres.

R^x is independently hydrogen, or optionally substituted aliphatic, haloaliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, alkylaryl, or heteroaryl. Preferably, R^x is alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl, cycloalkyl, or alkylaryl. Preferred optional substituents for R^x include halogen, hydroxyl, cyano, nitro, amino, alkoxy, alkylthio, or substituted or unsubstituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl (e.g. optionally substituted alkyl, aryl, or heteroaryl).

Exemplary options for X include OAc, OC(O)CF₃, halogen, OSO(CH₃)₂, Et, Me, OMe, OiPr, OtBu, Cl, Br, I, F, N(iPr)₂ or N(SiMe₃)₂, OPh, OBn, salicylate, dioctyl phosphinate, etc.

Preferably each X is the same, and is selected from OC(O)R^x, OR^x, halide, carbonate, amino, nitro, alkyl, aryl, heteroaryl, phosphinate or OSO₂R^x, R^x is alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl or alkylaryl. More preferably each X is the same and is OC(O)R^x, OR^x, halide, alkyl, aryl, heteroaryl, phosphinate or OSO₂R^x. Still more preferably each X is the same and is OC(O)R^x. More preferably still each X is the same and is selected from OAc, O₂CCF₃, or O₂C(CH₂)₃Cy. Most preferably each X is the same and is OAc.

Preferably each R^x is the same and is selected from an optionally substituted alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl, cycloalkyl or alkylaryl. More preferably each R^x is the same and is an optionally substituted alkyl, alkenyl, heteroalkyl, aryl, heteroaryl, cycloalkyl or alkylaryl. Still more preferably each R^x is the same and is an optionally substituted alkyl, alkenyl, heteroalkyl; or cycloalkyl. More preferably still R^x is an optionally substituted alkyl, heteroalkyl or cycloalkyl. Most preferably R^x is an optionally substituted alkyl.

It will be appreciated that preferred definitions for X and preferred definitions for R^x may be combined. For example, each X may be independently OC(O)R^x, OSO₂R^x, OS(O)R^x, OSO(R^x)₂, S(O)R^x, OR^x, halide, nitrate, hydroxyl, carbonate, amino, nitro, amido, alkyl (e.g. branched alkyl), heteroalkyl, (for example silyl), aryl or heteroaryl, e.g. each may be independently OC(O)R^x, OR^x, halide, carbonate, amino, nitro, alkyl, aryl, heteroaryl, phosphinate or OSO₂R^x, and R^x may be optionally substituted alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl, cycloalkyl, or alkylaryl.

As detailed above, M₁ and M₂ are independently selected from any of: Zn(II), Cr(III)-X, Cr(II), Co(III)-X, Co(II), Cu(II), Mn(III)-X, Mn(II), Mg(II), Ni(II), Ni(III)-X, Fe(II), Fe(III)-X, Ca(II), Ge(II), Ti(II), Al(III)-X, Ti(III)-X, V(II), V(III)-X, Ge(IV)-(X)₂ or Ti(IV)-(X)₂.

Preferably, at least one of M₁ and M₂ is selected from Zn(II), Cr(III)-X, Co(II), Mn(II), Mg(II), Ni(II), Fe(II), and Fe(III)-X, more preferably at least one of M₁ and M₂ is selected from Mg(II), Zn(II), and Ni(II), for example, at least one of M₁ and M₂ is Ni(II).

It will be appreciated that M₁ and M₂ may be the same or different. For example, M₁ and/or M₂ may be selected from Zn(II), Cr(III)-X, Co(II), Mn(II), Mg(II), Ni(II), Fe(II), and Fe(III)-X, more preferably M₁ and/or M₂ is selected from Mg(II), Zn(II) and Ni(II), for example, M₁ and/or M₂ is Ni(II).

Exemplary combinations of M₁ and M₂ include Mg(II) and Mg(II), Zn(II) and Zn(II), Ni(II) and Ni(II), Mg(II) and Zn(II), Mg(II) and Ni(II), Zn(II) and Co(II), Co(II) and Co(III), Fe(III) and Fe(III), Zn(II) and Fe(II), or Zn(II) and Ni(II).


It will be appreciated that when one of M_1 or M_2 is Cr(III), Co(III), Mn(III), Ni(III), Fe(III), Al(III), Ti(III) or V(III) the catalyst of formula (I) will contain an additional X group co-ordinated to the metal centre, wherein X is as defined above. It will also be appreciated that when one of M_1 or M_2 is Ge(IV) or Ti(IV), the catalyst of formula (III) will contain two additional X group co-ordinated to the metal centre, wherein X is as defined above. In certain embodiments, when one of M_1 or M_2 is Ge(IV)-(X)₂ or Ti(IV)-(X)₂, both G may be absent.

When G is not absent, it is a group which is capable of donating a lone pair of electrons (i.e. a Lewis base). In certain embodiments, G is a nitrogen-containing Lewis base. Each G may be neutral or negatively charged. If G is negatively charged, then one or more positive counterions will be required to balance out the charge of the complex. Suitable positive counterions include group 1 metal ions (Na⁺, K⁺, etc), group 2 metal ions (Mg²⁺, Ca²⁺, etc), imidazolium ions, a positively charged optionally substituted heteroaryl, heteroaliphatic or heteroalicyclic group, ammonium ions (i.e. N(R¹²)₄⁺), iminium ions (i.e. (R¹²)₂C=N(R¹²)₂⁺, such as bis(triphenylphosphine)iminium ions) or phosphonium ions (P(R¹²)₄⁺), wherein each R¹² is independently selected from hydrogen or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl. Exemplary counterions include [H-B]⁺ wherein B is selected from triethylamine, 1,8-diazabicyclo[5.4.0]undec-7-ene and 7-methyl-1,5,7-triazabicyclo[4.4.0]dec-5-ene.

G is preferably independently selected from an optionally substituted heteroaliphatic group, an optionally substituted heteroalicyclic group, an optionally substituted heteroaryl group, a halide, hydroxide, hydride, a carboxylate and water. More preferably, G is independently selected from water, an alcohol (e.g. methanol), a substituted or unsubstituted heteroaryl (imidazole, methyl imidazole (for example, N-methyl imidazole), pyridine, 4-dimethylaminopyridine, pyrrole, pyrazole, etc), an ether (dimethyl ether, diethylether, cyclic ethers, etc), a thioether, carbene, a phosphine, a phosphine oxide, a substituted or unsubstituted heteroalicyclic (morpholine, piperidine, tetrahydrofuran, tetrahydrothiophene, etc), an amine, an alkyl amine trimethylamine, triethylamine, etc), acetonitrile, an ester (ethyl acetate, etc), an acetamide (dimethylacetamide, etc), a sulfoxide (dimethylsulfoxide, etc), a carboxylate, a hydroxide, hydride, a halide, a nitrate, a sulfonate, etc. In some embodiments, one or both instances of G is independently selected from optionally substituted heteroaryl, optionally substituted heteroaliphatic, optionally substituted heteroalicyclic, halide, hydroxide, hydride, an ether, a thioether, carbene, a phosphine, a phosphine oxide, an amine, an alkyl amine, acetonitrile, an ester, an acetamide, a sulfoxide, a carboxylate, a nitrate or a sulfonate. In certain embodiments, G may be a halide; hydroxide; hydride; water; a heteroaryl, heteroalicyclic or carboxylate group which are optionally substituted by alkyl, alkenyl, alkynyl, alkoxy, halogen, hydroxyl, nitro or nitrile. In preferred

embodiments, G is independently selected from halide; water; a heteroaryl optionally substituted by alkyl (e.g. methyl, ethyl etc), alkenyl, alkynyl, alkoxy (preferably methoxy), halogen, hydroxyl, nitro or nitrile. In some embodiments, one or both instances of G is negatively charged (for example, halide). In further embodiments, one or both instances of G is an optionally substituted heteroaryl. Exemplary G groups include chloride, bromide, pyridine, methylimidazole (for example N-methyl imidazole) and dimethylaminopyridine (for example, 4-methylaminopyridine).

It will be appreciated that when a G group is present, the G group may be associated with a single M metal centre as shown in formula (I), or the G group may be associated with both metal centres and form a bridge between the two metal centres, as shown below in formula (IIa):




Wherein R₁, R₂, R₃, R₄, R₅, M₁, M₂, G, X, E₁ and E₂, are as defined for formula (I) and formula (II).


The skilled person will understand that, in the solid state, the catalysts of the first aspect may be associated with solvent molecules such as water, or alcohol (e.g. methanol or ethanol). It will be appreciated that the solvent molecules may be present in a ratio of less than 1:1 relative to the molecules of catalyst of the first aspect (i.e. 0.2:1, 0.25:1, 0.5:1), in a ratio of 1:1, relative to the molecules of catalyst of the first aspect, or in a ratio of greater than 1:1, relative to the molecules of catalyst of the first aspect.

The skilled person will understand that, in the solid state, the catalysts of the first aspect may form aggregates. For example, the catalyst of the first aspect may be a dimer, a trimer, a tetramer, a pentamer, or higher aggregate.


Exemplary catalysts of formula (I) are as follows:




$[L^1M_1M_2(X)_2(G)_2]$




$[L^2M_1M_2(X)_2(G)_2]$




$[L^3M_1M_2(X)_2(G)_2]$




$[L^4M_1M_2(X)_2(G)_2]$




$[L^5M_1M_2(X)_2(G)_2]$




$[L^6M_1M_2(X)_2(G)_2]$




$[L^7M_1M_2(X)_2(G)_2]$




$[L^8M_1M_2(X)_2(G)_2]$




$[L^9M_1M_2(X)_2(G)_2]$




$[L^{10}M_1M_2(X)_2(G)_2]$




$[L^{11}M_1M_2(X)_2(G)_2]$




$[L^{12}M_1M_2(X)_2(G)_2]$




$[L^{13}M_1M_2(X)_2(G)_2]$




$[L^{14}M_1M_2(X)_2(G)_2]$




$[L^{15}M_1M_2(X)_2(G)_2]$




$[L^{16}M_1M_2(X)_2(G)_2]$



$[L^{17}M_1M_2(X)_2(G)_2]$



$[L^{18}M_1M_2(X)_2(G)_2]$



Where M_1 , M_2 , G and X are as defined above for formula (I), and it will be appreciated that one or both G groups may be absent.

For example, at least one of M_1 and M_2 may be selected from $Zn(II)$, $Cr(III)-X$, $Co(II)$, $Mn(II)$, $Mg(II)$, $Ni(II)$, $Fe(II)$, and $Fe(III)-X$, e.g. at least one of M_1 and M_2 may be selected from $Mg(II)$, $Zn(II)$ and $Ni(II)$, for example, at least one of M_1 and M_2 may be $Ni(II)$.

As set out above, M_1 and M_2 may be the same or different. For example, M_1 and/or M_2 may be selected from $Zn(II)$, $Cr(III)-X$, $Co(II)$, $Mn(II)$, $Mg(II)$, $Ni(II)$, $Fe(II)$, and $Fe(III)-X$, preferably M_1 and/or M_2 is selected from $Mg(II)$, $Zn(II)$ and $Ni(II)$, for example, M_1 and/or M_2 is $Ni(II)$.

Exemplary combinations of M_1 and M_2 include $Mg(II) / Mg(II)$, $Zn(II) / Zn(II)$, $Ni(II) / Ni(II)$, $Mg(II) / Zn(II)$, $Mg(II) / Ni(II)$, $Zn(II) / Ni(II)$.

For example, each X may be independently OC(O)R^x, OSO₂R^x, OS(O)R^x, OSO(R^x)₂, S(O)R^x, OR^x, halide, nitrate, hydroxyl, carbonate, amino, nitro, amido, alkyl (e.g. branched alkyl), heteroalkyl (for example silyl), aryl or heteroaryl, e.g. each may be independently OC(O)R^x, OR^x, halide, carbonate, amino, nitro, alkyl, aryl, heteroaryl, phosphinate or OSO₂R^x. For example, R^x may be alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl, cycloalkyl, or alkylaryl.

For example, if either G are present, G may be independently selected from halide; water; a heteroaryl optionally substituted by alkyl (e.g. methyl, ethyl etc), alkenyl, alkynyl, alkoxy (preferably methoxy), halogen, hydroxyl, nitro or nitrile, e.g. one or both instances of G (if present) can be chloride, bromide, pyridine, methylimidazole (for example N-methyl imidazole) and dimethylaminopyridine (for example, 4-methylaminopyridine).

The skilled person will appreciate that the above definitions may be combined. For example, for the catalysts above, M₁ and M₂ may be the same or different, and may be selected from Zn(II), Cr(III)-X, Co(II), Mn(II), Mg(II), Ni(II), Fe(II), and Fe(III)-X; each X may be independently OC(O)R^x, OSO₂R^x, OS(O)R^x, OSO(R^x)₂, S(O)R^x, OR^x, halide, nitrate, hydroxyl, carbonate, amino, nitro, amido, alkyl (e.g. branched alkyl), heteroalkyl (for example silyl), aryl or heteroaryl, e.g. each may be independently OC(O)R^x, OR^x, halide, carbonate, amino, nitro, alkyl, aryl, heteroaryl, phosphinate or OSO₂R^x; R^x may be alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl, cycloalkyl, or alkylaryl; G may be absent or if present, may be independently selected from halide; water; a heteroaryl optionally substituted by alkyl (e.g. methyl, ethyl etc), alkenyl, alkynyl, alkoxy (preferably methoxy), halogen, hydroxyl, nitro or nitrile.

Thus, the skilled person will understand that the above exemplary catalysts of formula (I) encompass, but are not restricted to, the following catalysts:

[L¹Ni₂(OAc)₂], [L¹Mg₂(OAc)₂], [L¹Zn₂(OAc)₂], [L¹MgZn(OAc)₂], [L¹MgNi(OAc)₂],
 [L¹Ni₂(CO₂CF₃)₂], [L¹Mg₂(CO₂CF₃)₂], [L¹Zn₂(CO₂CF₃)₂], [L¹MgZn(CO₂CF₃)₂], [L¹MgNi(CO₂CF₃)₂],
 [L¹Ni₂(CO₂^tBu)₂], [L¹Mg₂(CO₂^tBu)₂], [L¹Zn₂(CO₂^tBu)₂], [L¹MgZn(CO₂^tBu)₂], [L¹MgNi(CO₂^tBu)₂],
 [L¹Ni₂(OPh)₂], [L¹Mg₂(OPh)₂], [L¹Zn₂(OPh)₂], [L¹MgZn(OPh)₂], [L¹MgNi(OPh)₂],
 [L¹Ni₂(Ph)₂], [L¹Mg₂(Ph)₂], [L¹Zn₂(Ph)₂], [L¹MgZn(Ph)₂], [L¹MgNi(Ph)₂],
 [L¹Ni₂(OⁱPr)₂], [L¹Mg₂(OⁱPr)₂], [L¹Zn₂(OⁱPr)₂], [L¹MgZn(OⁱPr)₂], [L¹MgNi(OⁱPr)₂],
 [L¹Ni₂(C₆F₅)₂], [L¹Mg₂(C₆F₅)₂], [L¹Zn₂(C₆F₅)₂], [L¹MgZn(C₆F₅)₂], [L¹MgNi(C₆F₅)₂],
 [L¹Ni₂Cl₂], [L¹Mg₂Cl₂], [L¹Zn₂Cl₂], [L¹MgZnCl₂], [L¹MgNiCl₂],
 [L¹Ni₂Br₂], [L¹Mg₂Br₂], [L¹Zn₂Br₂], [L¹MgZnBr₂], [L¹MgNiBr₂],
 [L¹Ni₂I₂], [L¹Mg₂I₂], [L¹Zn₂I₂], [L¹MgZnI₂], [L¹MgNiI₂],
 [L¹Ni₂(OC(O)(CH₂)₄CH₃)₂], [L¹Mg₂(OC(O)(CH₂)₄CH₃)₂], [L¹Zn₂(OC(O)(CH₂)₄CH₃)₂],
 [L¹MgZn(OC(O)(CH₂)₄CH₃)₂], [L¹MgNi(OC(O)(CH₂)₄CH₃)₂],

- [L¹Ni₂(OC(O)(CH₂)₆CH₃)₂], [L¹Mg₂(OC(O)(CH₂)₆CH₃)₂], [L¹Zn₂(OC(O)(CH₂)₆CH₃)₂],
 [L¹MgZn(OC(O)(CH₂)₆CH₃)₂], [L¹MgNi(OC(O)(CH₂)₆CH₃)₂],
 [L¹Ni₂(OC(O)(CH₂)₁₀CH₃)₂], [L¹Mg₂(OC(O)(CH₂)₁₀CH₃)₂], [L¹Zn₂(OC(O)(CH₂)₁₀CH₃)₂],
 [L¹MgZn(OC(O)(CH₂)₁₀CH₃)₂], [L¹MgNi(OC(O)(CH₂)₁₀CH₃)₂],
 5 [L¹Ni₂(OC(O)C₆F₅)₂], [L¹Mg₂(OC(O)C₆F₅)₂], [L¹Zn₂(OC(O)C₆F₅)₂], [L¹MgZn(OC(O)C₆F₅)₂],
 [L¹MgNi(OC(O)C₆F₅)₂],
 [L¹Ni₂Cl₂(methylimidazole)], [L¹Mg₂Cl₂(methylimidazole)], [L¹Zn₂Cl₂(methylimidazole)],
 [L¹MgZnCl₂(methylimidazole)], [L¹MgNiCl₂(methylimidazole)],
 [L¹Ni₂Cl₂(pyridine)], [L¹Mg₂Cl₂(pyridine)], [L¹Zn₂Cl₂(pyridine)], [L¹MgZnCl₂(pyridine)],
 10 [L¹MgNiCl₂(pyridine)],
 [L¹Ni₂Cl₂(dimethylaminopyridine)], [L¹Mg₂Cl₂(dimethylaminopyridine)],
 [L¹Zn₂Cl₂(dimethylaminopyridine)], [L¹MgZnCl₂(dimethylaminopyridine)],
 [L¹MgNiCl₂(dimethylaminopyridine)],
 [L¹Ni₂Br₂(dimethylaminopyridine)], [L¹Mg₂Br₂(dimethylaminopyridine)],
 15 [L¹Zn₂Br₂(dimethylaminopyridine)], [L¹MgZnBr₂(dimethylaminopyridine)],
 [L¹MgNiBr₂(dimethylaminopyridine)],
 [L¹Ni₂(bis(4-methoxy)phenyl phosphinate)₂], [L¹Mg₂(bis(4-methoxy)phenyl phosphinate)₂],
 [L¹Zn₂(bis(4-methoxy)phenyl phosphinate)₂], [L¹MgZn(bis(4-methoxy)phenyl phosphinate)₂],
 [L¹MgNi(bis(4-methoxy)phenyl phosphinate)₂],
 20 [L¹Ni₂(adamantyl carbonate)₂], [L¹Mg₂(adamantyl carbonate)₂], [L¹Zn₂(adamantyl carbonate)₂],
 [L¹MgZn(adamantyl carbonate)₂], [L¹MgNi(adamantyl carbonate)₂],
 [L¹Ni₂(diphenylphosphinate)₂], [L¹Mg₂(diphenylphosphinate)₂], [L¹Zn₂(diphenylphosphinate)₂],
 [L¹MgZn(diphenylphosphinate)₂], [L¹MgNi(diphenylphosphinate)₂],
 [L²Ni₂(OAc)₂], [L²Mg₂(OAc)₂], [L²Zn₂(OAc)₂], [L²MgZn(OAc)₂], [L²MgNi(OAc)₂],
 25 [L³Ni₂(OAc)₂], [L³Mg₂(OAc)₂], [L³Zn₂(OAc)₂], [L³MgZn(OAc)₂], [L³MgNi(OAc)₂],
 [L⁴Ni₂(OAc)₂], [L⁴Mg₂(OAc)₂], [L⁴Zn₂(OAc)₂], [L⁴MgZn(OAc)₂], [L⁴MgNi(OAc)₂],
 [L⁵Ni₂(OAc)₂], [L⁵Mg₂(OAc)₂], [L⁵Zn₂(OAc)₂], [L⁵MgZn(OAc)₂], [L⁵MgNi(OAc)₂],
 [L⁶Ni₂(OAc)₂], [L⁶Mg₂(OAc)₂], [L⁶Zn₂(OAc)₂], [L⁶MgZn(OAc)₂], [L⁶MgNi(OAc)₂],
 [L⁷Ni₂(OAc)₂], [L⁷Mg₂(OAc)₂], [L⁷Zn₂(OAc)₂], [L⁷MgZn(OAc)₂], [L⁷MgNi(OAc)₂],
 30 [L⁸Ni₂(OAc)₂], [L⁸Mg₂(OAc)₂], [L⁸Zn₂(OAc)₂], [L⁸MgZn(OAc)₂], [L⁸MgNi(OAc)₂],
 [L⁹Ni₂(OAc)₂], [L⁹Mg₂(OAc)₂], [L⁹Zn₂(OAc)₂], [L⁹MgZn(OAc)₂], [L⁹MgNi(OAc)₂],
 [L¹⁰Ni₂(OAc)₂], [L¹⁰Mg₂(OAc)₂], [L¹⁰Zn₂(OAc)₂], [L¹⁰MgZn(OAc)₂], [L¹⁰MgNi(OAc)₂],
 [L¹¹Ni₂(OAc)₂], [L¹¹Mg₂(OAc)₂], [L¹¹Zn₂(OAc)₂], [L¹¹MgZn(OAc)₂], [L¹¹MgNi(OAc)₂],
 [L¹²Ni₂(OAc)₂], [L¹²Mg₂(OAc)₂], [L¹²Zn₂(OAc)₂], [L¹²MgZn(OAc)₂], [L¹²MgNi(OAc)₂],
 35 [L¹³Ni₂(OAc)₂], [L¹³Mg₂(OAc)₂], [L¹³Zn₂(OAc)₂], [L¹³MgZn(OAc)₂], [L¹³MgNi(OAc)₂],
 [L¹⁴Ni₂(OAc)₂], [L¹⁴Mg₂(OAc)₂], [L¹⁴Zn₂(OAc)₂], [L¹⁴MgZn(OAc)₂], [L¹⁴MgNi(OAc)₂],
 [L¹⁵Ni₂(OAc)₂], [L¹⁵Mg₂(OAc)₂], [L¹⁵Zn₂(OAc)₂], [L¹⁵MgZn(OAc)₂], [L¹⁵MgNi(OAc)₂],
 [L¹⁶Ni₂(OAc)₂], [L¹⁶Mg₂(OAc)₂], [L¹⁶Zn₂(OAc)₂], [L¹⁶MgZn(OAc)₂], [L¹⁶MgNi(OAc)₂],

$[L^{17}Ni_2(OAc)_2]$, $[L^{17}Mg_2(OAc)_2]$, $[L^{17}Zn_2(OAc)_2]$, $[L^{17}MgZn(OAc)_2]$, $[L^{17}MgNi(OAc)_2]$,
 $[L^{18}Ni_2(OAc)_2]$, $[L^{18}Mg_2(OAc)_2]$, $[L^{18}Zn_2(OAc)_2]$, $[L^{18}MgZn(OAc)_2]$, $[L^{18}MgNi(OAc)_2]$,
 $[L^{19}Ni_2(OAc)_2]$, $[L^{19}Mg_2(OAc)_2]$, $[L^{19}Zn_2(OAc)_2]$, $[L^{19}MgZn(OAc)_2]$, $[L^{19}MgNi(OAc)_2]$,
 $[L^{20}Ni_2(OAc)_2]$, $[L^{20}Mg_2(OAc)_2]$, $[L^{20}Zn_2(OAc)_2]$, $[L^{20}MgZn(OAc)_2]$, $[L^{20}MgNi(OAc)_2]$,
5 $[L^{21}Ni_2(OAc)_2]$, $[L^{21}Mg_2(OAc)_2]$, $[L^{21}Zn_2(OAc)_2]$, $[L^{21}MgZn(OAc)_2]$, $[L^{21}MgNi(OAc)_2]$,
 $[L^{22}Ni_2(OAc)_2]$, $[L^{22}Mg_2(OAc)_2]$, $[L^{22}Zn_2(OAc)_2]$, $[L^{22}MgZn(OAc)_2]$, $[L^{22}MgNi(OAc)_2]$,
 $[L^{23}Ni_2(OAc)_2]$, $[L^{23}Mg_2(OAc)_2]$, $[L^{23}Zn_2(OAc)_2]$, $[L^{23}MgZn(OAc)_2]$, $[L^{23}MgNi(OAc)_2]$,
 $[L^1Co_2(OAc)_3]$, $[L^1ZnCoI_2]$, $[L^1ZnFe(OAc)_2]$, $[L^1ZnFeBr_2]$, $[L^1ZnFeCl_2]$, $[L^1ZnFeI_2]$,
 $[L^1ZnCo(OAc)_2]$, $[L^1ZnCoCl_2]$, $[L^1ZnCoBr_2]$, $[L^1Fe_2Cl_4]$, $[L^1Co_2Cl_2(\text{methylimidazole})]$,
10 $[L^1Co_2Cl_2(\text{pyridine})]$, $[L^1Co_2Cl_3]^- [H\text{-DBU}]^+$, and $[L^1Co_2Cl_3]^- [H\text{-MTBD}]^+$.

The skilled person will appreciate that in any of the above complexes, any one ligand defined by
 "L" may be replaced by another ligand defined by a different "L". For example, in complexes
 which refer to L^1 , this ligand may be replaced by any of the ligands defined by L^2 to L^{22} .

Double metal cyanide (DMC) catalyst

DMC catalysts are complicated compounds which comprise at least two metal centres and
 cyanide ligands. The DMC catalyst may additionally comprise an organic complexing agent,
 water and/or a metal salt (e.g. in non-stoichiometric amounts).

Examples of DMC catalysts which can be used in the method of the invention include those
 described in US 3427256, US 5536883, US 6291388, US 6486361, US 6608231, US7008900,
 US 5482908, US 5780584, US 5158922, US 5693584, US 7811958, US 6835687, US
 6699961, US 6716788, US 6977236, US 7968754, US 7034103, US 4826953, US4500704, US
 7977501, EP-A-1568414, EP-A-1529566, and WO 2015/022290, the entire contents of which
 are incorporated by reference.

DMC catalysts which are useful in the invention may be produced by treating a solution (such as
 an aqueous solution) of a metal salt with a solution (such as an aqueous

solution) of a metal cyanide salt in the presence of an organic complexing agent. Suitable metal
 salts include compounds of the formula $M'(X')_p$, wherein M' is selected from Zn(II), Fe(II), Ni(II),
 Mn(II), Co(II), Sn(II), Pb(II), Fe(III), Mo(IV), Mo(VI), Al(III), V(V), V(VI), Sr(II), W(IV), W(VI),
 Cu(II), and Cr(III), and M' is preferably selected from Zn(II), Fe(II), Co(II) and Ni(II), even more
 preferably M' is Zn(II). X' is an anion selected from halide, hydroxide, sulphate, carbonate,
 cyanide, oxalate, thiocyanate, isocyanate, isothiocyanate, carboxylate and nitrate, preferably X'
 is halide. p is an integer of 1 or more, and the charge on the anion multiplied by p satisfies the
 valency of M' . Examples of suitable metal salts include zinc chloride, zinc bromide, zinc acetate,


zinc acetylacetonate, zinc benzoate, zinc nitrate, iron(II) sulphate, iron (II) bromide, cobalt(II) chloride, cobalt(II) thiocyanate, nickel(II) formate, nickel(II) nitrate, and mixtures thereof.

Suitable metal cyanide salts include compounds of the formula $(Y)_q[M''(CN)_b(A)_c]$, wherein M'' is selected from Fe(II), Fe(III), Co(II), Co(III), Cr(II), Cr(III), Mn(II), Mn(III), Ir(III), Ni(II), Rh(III), Ru(II), V(IV), and V(V), preferably M'' is selected from Co(II), Co(III), Fe(II), Fe(III), Cr(III), Ir(III) and Ni(II), more preferably M'' is selected from Co(II) and Co(III). Y is an alkali metal ion or an alkaline earth metal ion (such as K^+), A is an anion selected from halide, hydroxide, sulphate, cyanide oxalate, thiocyanate, isocyanate, isothiocyanate, carboxylate and nitrate. q and b are integers of 1 or more, preferably b is 4 or 6. c may be 0 or an integer of 1 or more. The sum of the charges on the ions Y, CN and A multiplied by q, b and c respectively (e.g. $Y \times q + CN \times b + A \times c$) satisfies the valency of M'' . Examples of suitable metal cyanide salts include potassium hexacyanocobaltate(III), potassium hexacyanoferrate(II), potassium hexacyanoferrate(III), calcium hexacyanocobaltate(III), lithium hexacyanocobaltate(III), and mixtures thereof.

Suitable complexing agents include ethers, ketones, esters, amides, alcohols, ureas and the like, such as dimethoxyethane, tert-butyl alcohol, ethylene glycol monomethyl ether, diglyme, triglyme, ethanol, isopropyl alcohol, n-butyl alcohol, isobutyl alcohol, sec-butyl alcohol, etc.

In one common preparation, an aqueous solution of zinc chloride (excess) is mixed with an aqueous solution of potassium hexacyanocobaltate, and an organic complexing agent (such as dimethoxyethane) is added to the resulting slurry. After filtration and washing of the catalyst with an aqueous solution of the complexing agent (e.g. aqueous dimethoxyethane), and active catalyst is obtained.

For example, the DMC catalyst may comprise:



Wherein M' and M'' are as defined above, d, e, f and g are integers, and are chosen to such that the DMC catalyst has electroneutrality. Preferably, d is 3. Preferably, e is 1. Preferably f is 6. Preferably g is 2. Preferably, M' is selected from Zn(II), Fe(II), Co(II) and Ni(II), more preferably M' is Zn(II). Preferably M'' is selected from Co(III), Fe(III), Cr(III) and Ir(III), more preferably M'' is Co(III).

It will be appreciated that any of these preferred features may be combined, for example, d is 3, e is 1, f is 6 and g is 2, M' is Zn(II) and M'' is Co(III).

Suitable DMC catalysts of the above formula may include zinc hexacyanocobaltate(III), zinc hexacyanoferrate(III), nickel hexacyanoferrate(II), and cobalt hexacyanocobaltate(III).

There has been a lot of development in the field of DMC catalysts, and the skilled person will appreciate that the DMC catalyst may comprise, in addition to the formula above, further additives to enhance the activity of the catalyst. Thus, while the above formula may form the “core” of the DMC catalyst, the DMC catalyst may additionally comprise stoichiometric or non-stoichiometric amounts of one or more additional components, such as an organic complexing agent, a metal salt, and/or water.

For example, the DMC catalyst may have the following formula:



Wherein M', M'', d, e, f and g are as defined above.

M''' can be M' and/or M''. X'' is an anion selected from halide, hydroxide, sulphate, carbonate, cyanide, oxalate, thiocyanate, isocyanate, isothiocyanate, carboxylate and nitrate, preferably X' is halide. i is an integer of 1 or more, and the charge on the anion X'' multiplied by i satisfies the valency of M'''.

R^c is a complexing agent, and may be as defined above. For example, R^c may be an ether, a ketone, an ester, an amide, an alcohol (e.g. a C₁₋₆ alcohol), a urea and the like, such as dimethoxyethane, tert-butyl alcohol, ethylene glycol monomethyl ether, diglyme, triglyme, ethanol, isopropyl alcohol, n-butyl alcohol, isobutyl alcohol, sec-butyl alcohol, for example, R^c may be tert-butyl alcohol.

It will be appreciated that if the water, complexing agent and/or metal salt are not present in the DMC catalyst, h, j and/or k will be zero respectively. If the water, complexing agent and/or metal salt are present, then h, j and/or k are a positive number and may, for example, be between 0 and 20. For example, h may be between 0.1 and 4. j may be between 0.1 and 6. k may be between 0 and 20, e.g. between 0.1 and 10, such as between 0.1 and 5.

As set out above, DMC catalysts are complicated structures, and thus, the above formula including the additional components is not intended to be limiting. Instead, the skilled person will appreciate that this definition is not exhaustive of the DMC catalysts which are capable of being used in the invention.

An exemplary DMC catalyst is of the formula $Zn_3[Co(CN)_6]_2 \cdot hZnCl_2 \cdot 0.5H_2O \cdot 2[(CH_3)_3COH]$.

Starter compound

The starter compound which may be used in the method of the invention comprises at least two groups selected from a hydroxyl group (-OH), a thiol (-SH), an amine having at least one N-H bond (-NHR'), a group having at least one P-OH bond (e.g. -PR'(O)OH, PR'(O)(OH)₂ or -P(O)(OR')(OH)), or a carboxylic acid group (-C(O)OH).

Thus, the starter compound which is useful in the method of the invention may be of the formula (III):



Z can be any group which can have 2 or more -R^Z groups attached to it. Thus, Z may be selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, cycloalkylene, cycloalkenylene, heterocycloalkylene, heterocycloalkenylene, arylene, heteroarylene, or Z may be a combination of any of these groups, for example Z may be an alkylarylene, heteroalkylarylene, heteroalkylheteroarylene or alkylheteroarylene group. Preferably Z is alkylene, heteroalkylene, arylene, or heteroarylene.

It will be appreciated that a is an integer which is at least 2, preferably a is in the range of between 2 and 8, preferably a is in the range of between 2 and 6.

Each R^Z may be -OH, -NHR', -SH, -C(O)OH, -P(O)(OR')(OH), -PR'(O)(OH)₂ or -PR'(O)OH, preferably R^Z is selected from -OH, -NHR' or -C(O)OH, more preferably each R^Z is -OH, -C(O)OH or a combination thereof (e.g. each R^Z is -OH).

R' may be H, or optionally substituted alkyl, heteroalkyl, aryl, heteroaryl, cycloalkyl or heterocycloalkyl, preferably R' is H or optionally substituted alkyl.

It will be appreciated that any of the above features may be combined. For example, a may be between 2 and 8, each R^Z may be -OH, -C(O)OH or a combination thereof, and Z may be selected from alkylene, heteroalkylene, arylene, or heteroarylene.

Exemplary starter compounds include diols such as 1,2-ethanediol (ethylene glycol), 1,2-propanediol, 1,3-propanediol (propylene glycol), 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,8-octanediol, 1,10-decanediol, 1,4-cyclohexanediol, 1,2-diphenol, 1,3-diphenol, 1,4-diphenol, neopentyl glycol, catechol, cyclohexenediol, 1,4-cyclohexanedimethanol, dipropylene glycol, diethylene glycol, tripropylene glycol, triethylene glycol, tetraethylene glycol, polypropylene glycols (PPGs) or polyethylene glycols (PEGs)

having an Mn of up to about 1500g/mol, such as PPG 425, PPG 725, PPG 1000 and the like, triols such as glycerol, benzenetriol, 1,2,4-butanetriol, 1,2,6-hexanetriol, tris(methylalcohol)propane, tris(methylalcohol)ethane, tris(methylalcohol)nitropropane, trimethylol propane, polypropylene oxide triols and polyester triols, tetraols such as

5 calix[4]arene, 2,2-bis(methylalcohol)-1,3-propanediol, erythritol, pentaerythritol or polyalkylene glycols (PEGs or PPGs) having 4–OH groups, polyols, such as sorbitol or polyalkylene glycols (PEGs or PPGs) having 5 or more –OH groups, or compounds having mixed functional groups including ethanolamine, diethanolamine, methyldiethanolamine, and phenyldiethanolamine.

10 For example, the starter compound may be a diol such as 1,2-ethanediol (ethylene glycol), 1,2-propanediol, 1,3-propanediol (propylene glycol), 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,8-octanediol, 1,10-decanediol, 1,12-dodecanediol, 1,4-cyclohexanediol, 1,2-diphenol, 1,3-diphenol, 1,4-diphenol, neopentyl glycol, catechol, cyclohexenediol, 1,4-cyclohexanedimethanol, poly(caprolactone) diol, dipropylene glycol,

15 diethylene glycol, tripropylene glycol, triethylene glycol, tetraethylene glycol, polypropylene glycols (PPGs) or polyethylene glycols (PEGs) having an Mn of up to about 1500g/mol, such as PPG 425, PPG 725, PPG 1000 and the like. It will be appreciated that the starter compound may be 1,6-hexanediol, 1,4-cyclohexanedimethanol, 1,12-dodecanediol, poly(caprolactone) diol, PPG 425, PPG 725, or PPG 1000.

20 Further exemplary starter compounds may include diacids such as oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, undecanedioic acid, dodecanedioic acid or other compounds having mixed functional groups such as lactic acid, glycolic acid, 3-hydroxypropanoic acid, 4-hydroxybutanoic acid, 5-

25 hydroxypentanoic acid.

Reaction conditions

The method of the invention may be carried out at pressures of between about 1 bar and about 60 bar carbon dioxide, e.g. between about 1 bar and about 30 bar carbon dioxide, for example

30 between about 1 to about 20 bar, such as between about 1 and about 15 bar carbon dioxide.

The method of the invention is capable of preparing polycarbonate ether polyols at pressures that are within the limits of existing polyether polyol equipment used in industry (e.g. 10 bar or less). Therefore, the method of the invention is capable being carried out at pressures of

35 between about 1 bar and about 10 bar, for example, the reaction is capable of being carried out at a pressure of about 5 bar or less carbon dioxide. Under these conditions, the method of the invention is still capable of producing polycarbonate ether polyols having a varying amount of carbonate linkages, and may produce a polyol having a high content of carbonate linkages.

The method of the invention may be carried out in the presence of a solvent, however it will also be appreciated that the reaction may be carried out in the absence of a solvent. When a solvent is present, it may be toluene, diethyl carbonate, dimethyl carbonate, dioxane, dichlorobenzene, methylene chloride, propylene carbonate, ethylene carbonate, acetone, ethyl acetate, propyl acetate, n-butyl acetate, tetrahydrofuran (THF), etc.

The epoxide which is used in the method may be any containing an epoxide moiety. Exemplary epoxides include ethylene oxide, propylene oxide, butylene oxide and cyclohexene oxide.

The epoxide may be purified (for example by distillation, such as over calcium hydride) prior to reaction with carbon dioxide. For example, the epoxide may be distilled prior to being added to the reaction mixture comprising the catalysts.

The process may be carried out at a temperature of about 0°C to about 250°C, for example from about 40°C to about 140°C, e.g. from about 50°C to about 110°C, such as from about 60°C to about 100°C, for example from about 70°C to about 100°C. The duration of the process may be up to about 168 hours, such as from about 1 minute to about 24 hours, for example from about 5 minutes to about 12 hours, e.g. from about 1 to about 6 hours.

The method of the invention may be carried out at low catalytic loading. For example, the catalytic loading of the catalyst of formula (I) may be in the range of about 1:1,000-300,000 [catalyst of formula (I)]:[epoxide], such as about 1:1,000-100,000 [catalyst of formula (I)]:[epoxide], e.g. in the region of about 1:10000-50,000 [catalyst of formula (I)]:[epoxide], for example in the region of about 1:10,000 [catalyst of formula (I)]:[epoxide]. The ratios above are molar ratios.

The ratio of the catalyst of formula (I) to the DMC catalyst may be in the range of from about 300:1 to about 0.1:1, for example, from about 120:1 to about 0.25:1, such as from about 40:1 to about 0.5:1, e.g. from about 30:1 to about 0.75:1 such as from about 20:1 to about 1:1, for example from about 10:1 to about 2:1, e.g. from about 5:1 to about 3:1. These ratios are mass ratios.

The starter compound may be present in amounts of from about 200:1 to about 1:1, for example, from about 175:1 to about 5:1, such as from about 150:1 to about 10:1, e.g. from about 125:1 to about 20:1, for example, from about 50:1 to about 20:1, relative to the catalyst of formula (I). These ratios are molar ratios.

The starter may be pre-dried (for example with molecular sieves) to remove moisture. It will be understood that any of the above reaction conditions described may be combined. For example, the reaction may be carried out at 20 bar or less (e.g. 10 bar or less) and at a temperature in the range of from about 50 °C to about 130°C, for example, from about 50°C to about 110°C, such as from about 60°C to about 100°C, e.g. from about 70°C to about 100°C.

The method may be a batch reaction, a semi-continuous reaction, or a continuous reaction.

Polyols


The method of the invention is capable of preparing polycarbonate ether polyols, which are capable of being used, for example, to prepare polyurethanes.

The method of the invention is capable of producing polycarbonate ether polyols in which the amount of ether and carbonate linkages can be controlled. Thus, the invention provides a polycarbonate ether polyol which has n ether linkages and m carbonate linkages, wherein n and m are integers, and wherein $m/(n+m)$ is from greater than zero to less than 1.

For example, the method of the invention is capable of preparing polycarbonate ether polyols having a wide range of $m/(n+m)$ values. It will be understood that $m/(n+m)$ may be about 0.05, about 0.10, about 0.15, about 0.20, about 0.25, about 0.30, about 0.35, about 0.40, about 0.45, about 0.50, about 0.55, about 0.60, about 0.65, about 0.70, about 0.75, about 0.80, about 0.85, about 0.90, about 0.95, or within any range prepared from these specific values. For example, $m/(n+m)$ may be from about 0.05 to about 0.95, from about 0.10 to about 0.90, from about 0.15 to about 0.85, from about 0.20 to about 0.80, or from about 0.25 to about 0.75, etc.

Thus, the method of the invention makes it possible to prepare polycarbonate ether polyols having a high proportion of carbonate linkages, e.g. $m/(n+m)$ may be greater than about 0.50, such as from greater than about 0.55 to less than about 0.95, e.g. about 0.65 to about 0.90, e.g. about 0.75 to about 0.90. The method of the invention is able to prepare polyols having a high ratio of $m/(n+m)$ under mild conditions, for example, under pressures of about 20 bar or below, such as 10 bar or below.

For example, the polycarbonate ether polyols produced by the method of the invention may have the following formula (IV):



It will be appreciated that the identity of Z and Z' will depend on the nature of the starter compound, and that the identity of R^{e1} and R^{e2} will depend on the nature of the epoxide used to prepare the polycarbonate ether polyol. m and n define the amount of the carbonate and ether linkages in the polycarbonate ether polyol.

The skilled person will understand that in the polymers of formula (IV), the adjacent epoxide monomer units in the backbone may be head-to-tail linkages, head-to-head linkages or tail-to-tail linkages.

It will also be appreciated that formula (IV) does not require the carbonate links and the ether links to be present in two distinct "blocks" in each of the sections defined by "a", but instead the carbonate and ether repeating units may be statistically distributed along the polymer backbone, or may be arranged so that the carbonate and ether linkages are not in two distinct blocks.

Thus, the polycarbonate ether polyol prepared by the method of the invention (e.g. a polymer of formula (IV)) may be referred to as a random copolymer, a statistical copolymer, an alternating copolymer, or a periodic copolymer.

The skilled person will appreciate that the wt% of carbon dioxide incorporated into a polymer cannot be definitively used to determine the amount of carbonate linkages in the polymer backbone. For example, two polymers which incorporate the same wt% of carbon dioxide may have very different ratios of carbonate to ether linkages. This is because the "wt% incorporation" of carbon dioxide does not take into account the length and nature of the starter compound. For instance, if one polymer (M_n 2000 g/mol) is prepared using a starter with a molar mass of 100 g/mol, and another polymer (M_n also 2000 g/mol) is prepared using a starter having a molar mass of 500 g/mol, and both the resultant polymers have the same ratio of m/n then the wt% of carbon dioxide in the polymers will be different due to the differing proportion of the mass of the starter in the overall polymer molecular weight (M_n). For example, if m/(m+n) was 0.5, the two polyols described would have carbon dioxide contents of 26.1 wt% and 20.6 wt% respectively.

As highlighted above, the method of the invention is capable of preparing polyols which have a wide range of carbonate to ether linkages (e.g. $m/(n+m)$ can be from greater than zero to less than 1), which, when using propylene oxide, corresponds to incorporation of up to about 43 wt% carbon dioxide. This is surprising, as DMC catalysts which have previously reported can

5 generally only prepare polyols having a ratio of carbonate to ether

linkages of up to 0.75, and these amounts can usually only be achieved at high pressures of carbon dioxide, such as 30 bar, more commonly 40 bar or above.

10 Furthermore, catalysts which are used to prepare polycarbonate polyols can typically achieve a ratio of carbonate to ether linkages of about 0.95 or above (usually about 0.98 or above), and thus also incorporate a high wt% of carbon dioxide. However, these catalysts are not capable of preparing polyols having a ratio of carbonate to ether linkages below 0.95. The carbon dioxide wt% can be moderated by changing the mass of the starter: the resultant polyols contain blocks
15 of polycarbonate. For many applications this is not desirable, as polycarbonates produced from epoxides and carbon dioxide are less thermally stable than polyethers and block copolymers can have very different properties from random or statistical copolymers.

All other things being equal, polyethers have higher temperatures of degradation than
20 polycarbonates produced from epoxides and carbon dioxide. Therefore, a polyol having a statistical or random distribution of ether and carbonate linkages will have a higher temperature of degradation than a polycarbonate polyol, or a polyol having blocks of carbonate linkages. Temperature of thermal degradation can be measured using thermal gravimetric analysis (TGA).

25

As set out above, the method of the invention prepares a random copolymer, a statistical copolymer, an alternating copolymer, or a periodic copolymer. Thus, the carbonate linkages are not in a single block, thereby providing a polymer which has improved properties, such as improved thermal degradation, as compared to a polycarbonate polyol. Preferably, the polymer
30 prepared by the method of the invention is a random copolymer or a statistical copolymer.

The polycarbonate ether polyol prepared by the method of the invention may be of formula (IV), in which n and m are integers of 1 or more, the sum of all m and n groups is from 4 to 200, and wherein $m/(m+n)$ is in the range of from greater than zero to less than 1.00. As set out above,
35 $m/(n+m)$ may be from about 0.05, about 0.10, about 0.15, about 0.20, about 0.25, about 0.25, about 0.30, about 0.35, about 0.40, about 0.45, about 0.50, about 0.55, about 0.60, about 0.65, about 0.70, about 0.75, about 0.80, about 0.85, about 0.90, about 0.95, or within any range prepared from these specific values. For example, $m/(n+m)$ may be from about 0.05 to about

0.95, from about 0.10 to about 0.90, from about 0.15 to about 0.85, from about 0.20 to about 0.80, or from about 0.25 to about 0.75, etc.

The skilled person will also appreciate that the polyol must contain at least one carbonate and at least one ether linkage. Therefore it will be understood that the number of ether and carbonate linkages ($n+m$) in the polyol will be $\geq a$. The sum of $n+m$ must be greater than or equal to a .

Each R^{e1} may be independently selected from H, halogen, hydroxyl, or optionally substituted alkyl, alkenyl, alkynyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, heteroalkyl or heteroalkenyl. Preferably R^{e1} may be selected from H or optionally substituted alkyl.

Each R^{e2} may be independently selected from H, halogen, hydroxyl, or optionally substituted alkyl, alkenyl, alkynyl, cycloalkyl, heterocycloalkyl, aryl, heteroaryl, heteroalkyl or heteroalkenyl. Preferably R^{e2} may be selected from H or optionally substituted alkyl.

It will also be appreciated that R^{e1} and R^{e2} may together form a saturated, partially unsaturated or unsaturated ring containing carbon and hydrogen atoms, and optionally one or more heteroatoms (e.g. O, N or S). For example, R^{e1} and R^{e2} may together form a 5 or six membered ring.

As set out above, the nature of R^{e1} and R^{e2} will depend on the epoxide used in the reaction. If the epoxide is cyclohexene oxide (CHO), then R^{e1} and R^{e2} will together form a six membered alkyl ring (e.g. a cyclohexyl ring). If the epoxide is ethylene oxide, then R^{e1} and R^{e2} will both be H. If the epoxide is propylene oxide, then R^{e1} will be H and R^{e2} will be methyl (or R^{e1} will be methyl and R^{e2} will be H, depending on how the epoxide is added into the polymer backbone). If the epoxide is butylene oxide, then R^{e1} will be H and R^{e2} will be ethyl (or *vice versa*). If the epoxide is styrene oxide, then R^{e1} may be hydrogen, and R^{e2} may be phenyl (or *vice versa*).

It will also be appreciated that if a mixture of epoxides are used, then each occurrence of R^{e1} and/or R^{e2} may not be the same, for example if a mixture of ethylene oxide and propylene oxide are used, R^{e1} may be independently hydrogen or methyl, and R^{e2} may be independently hydrogen or methyl.


Thus, R^{e1} and R^{e2} may be independently selected from hydrogen, alkyl or aryl, or R^{e1} and R^{e2} may together form a cyclohexyl ring, preferably R^{e1} and R^{e2} may be independently selected from hydrogen, methyl, ethyl or phenyl, or R^{e1} and R^{e2} may together form a cyclohexyl ring.

Z' corresponds to R^Z, except that a bond replaces the labile hydrogen atom. Therefore, the identity of each Z' depends on the definition of R^Z in the starter compound. Thus, it will be appreciated that each Z' may be -O-, -NR'-, -S-, -C(O)O-, -P(O)(OR')O-, -PR'(O)(O-)₂ or -PR'(O)O- (wherein R' may be H, or optionally substituted alkyl, heteroalkyl, aryl, heteroaryl, cycloalkyl or heterocycloalkyl, preferably R' is H or optionally substituted alkyl), preferably Z' may be -C(O)O-, -NR'- or -O-, more preferably each Z' may be -O-, -C(O)O- or a combination thereof, more preferably each Z' may be -O-.

Z also depends on the nature of the starter compound. Thus, Z may be selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, cycloalkylene, cycloalkenylene, heterocycloalkylene, heterocycloalkenylene, arylene, heteroarylene, or Z may be a combination of any of these groups, for example Z may be an alkylarylene, heteroalkylarylene, heteroalkylheteroarylene or alkylheteroarylene group. Preferably Z is alkylene, heteroalkylene, arylene, or heteroarylene, e.g. alkylene or heteroalkylene. It will be appreciated that each of the above groups may be optionally substituted, e.g. by alkyl.

The variable a will also depend on the nature of the starter compound. The skilled person will appreciate that the value of a in formula (IV) will be the same as a in formula (III). Therefore, for formula (IV), a is an integer of at least 2, preferably a is in the range of between 2 and 8, preferably a is in the range of between 2 and 6.


The skilled person will also appreciate that the value of a will influence the shape of the polyol prepared by the method of the invention. For example, when a is 2, the polyol of formula (IV) may have the following structure:



(IV-A)

Where Z, Z', m, n, R^{e1} and R^{e2} are as described above for formula (IV).

For example, when a is 3, the polyol of formula (IV) may have the following formula:



Where Z, Z', m, n, R^{e1} and R^{e2} are as described above for formula (IV).

5

The skilled person will understand that each of the above features may be combined. For example, R^{e1} and R^{e2} may be independently selected from hydrogen, alkyl or aryl, or R^{e1} and R^{e2} may together form a cyclohexyl ring, each Z' may be -O-, -C(O)O- or a combination thereof (preferably each Z' may be -O-), and Z may be optionally substituted alkylene, heteroalkylene, arylene, or heteroarylene, e.g. alkylene or heteroalkylene, and a may be between 2 and 8.

10

The polyols produced by the method of the invention are preferably low molecular weight polyols. It will be appreciated that the nature of the epoxide used to prepare the polycarbonate ether polyol will have an impact on the resulting molecular weight of the product. Thus, the upper limit of n+m is used herein to define "low molecular weight" polymers of the invention.

15

The method of the invention can advantageously prepare a polycarbonate ether polyol having a narrow molecular weight distribution. In other words, the polycarbonate ether polyol may have a low polydispersity index (PDI). The PDI of a polymer is determined by dividing the weight average molecular weight (M_w) by the number average molecular weight (M_n) of a polymer, thereby indicating the distribution of the chain lengths in the polymer product. It will be appreciated that PDI becomes more important as the molecular weight of the polymer decreases, as the percent variation in the polymer chain lengths will be greater for a short chain polymer as compared to a long chain polymer, even if both polymers have the same PDI.

20

Preferably the polymers produced by the method of the invention have a PDI of from about 1 to less than about 2, preferably from about 1 to less than about 1.75, more

preferably from about 1 to less than about 1.5, even more preferably from about 1 to less than about 1.3.

5 The M_n and M_w , and hence the PDI of the polymers produced by the method of the invention may be measured using Gel Permeation Chromatography (GPC). For example, the GPC may be measured using an Agilent 1260 Infinity GPC machine with two Agilent PLgel μ -m mixed-E columns in series. The samples may be measured at room temperature (293K) in THF with a flow rate of 1mL/min against narrow polystyrene standards (e.g. polystyrene low easivials supplied by Agilent Technologies with a range of M_n from 405 to 49,450 g/mol). Optionally, the
10 samples may be measured against poly(ethylene glycol) standards, such as polyethylene glycol easivials supplied by Agilent Technologies.

Preferably, the polymers produced by the method of the invention may have a molecular weight in the range of from about 500 to about 10,000 Da, preferably from about 700 to about 5,000
15 Da, preferably from about 800 to about 2,000 Da.


The invention also provides a polymerisation system for the copolymerisation of carbon dioxide and an epoxide, comprising:

- d. A catalyst of formula (I) as defined herein,
- 20 e. A DMC catalyst as defined herein, and
- f. A starter compound as herein.

It will also be appreciated that the polyols prepared by the method of the invention may be used for further reactions, for example to prepare a polyurethane, for example by reacting a polyol
25 composition comprising a polyol prepared by the method of the invention with a composition comprising a di- or polyisocyanate.

The skilled person will also appreciate that it may be possible to use other catalysts which are known to prepare polycarbonates *via* the reaction of an epoxide and carbon dioxide either as
30 well as, or instead of, the catalysts of formula (I). For example, catalysts as defined in WO 2010/028362 are considered for this purpose.

There is herein disclosed a catalyst of formula (IIb):



Wherein R_1 , R_2 , R_3 , R_5 , G , X , E_1 and E_2 , are as defined for formula (I) or formula (II).



Each R_4 is independently selected from an optionally substituted alkyl, alkenyl, alkynyl, aryl, heteroalkyl, heteroalkenyl, heteroalkynyl, heteroaryl, $-\text{alkylC}(\text{O})\text{OR}_{19}$ or $-\text{alkylC}\equiv\text{N}$, preferably

- 5 each R_4 is independently selected from an optionally substituted alkyl, aryl, heteroalkyl, or heteroaryl group. Each R_4 may be the same or different. Preferably each R_4 is the same. For example, each R_4 is the same and is selected from optionally substituted alkyl, aryl, heteroalkyl, or heteroaryl group. Exemplary R_4 groups include optionally substituted methyl, ethyl, propyl, butyl, cyclohexyl and phenyl.

10

It will be appreciated that each of the preferred definitions as set out for formula (I) and formula (II) may equally be applied to formula (IIb).

It will be understood that the compound of formula (IIb) may have the following structure:



15

Wherein X and G are as defined for formula (I) or formula (II).

It will be appreciated that the catalyst of formula (IIb) may be used in the method of the present invention.

The catalyst of formula (IIb) may also be used in a method of reacting (i) carbon dioxide and an epoxide, (ii) an epoxide and an anhydride, and/or (iii) a lactide and/or a lactone, optionally in the presence of a chain transfer agent. The epoxide may be as defined herein, for example, it may be ethylene oxide, propylene oxide or cyclohexene oxide.

Examples

Methods

¹H NMR analysis

The assessment of polyether and polycarbonate content of the polyethercarbonate polyols has been reported in a number of different ways. In order to calculate the molar carbonate content and the CO₂ wt% in the polyethercarbonate polyols, the method described in US2014/0323670 was used herein. The method is as follows:

The samples were dissolved in deuterated chloroform and measured on a *Bruker* spectrometer. The relevant resonances in the ¹H-NMR spectra used for integration (in the case that 1,6-hexanediol is used as a starter) were:

Table A:

¹ H NMR resonance (ppm)	Protons from repeating units	No of protons
A(1.08-1.18)	CH ₃ of Polyether	3
B(1.18-1.25)	CH ₃ of Polycarbonate end groups	3
C (1.25-1.38)	CH ₃ of Polycarbonates	3
D (1.45-1.49)	CH ₃ of cyclic carbonate	3
E (1.64-1.75) or (1.40-1.48)	CH ₂ of hexanediol	4
F(2.95-2.99)	CH of propylene oxide	1

The resonances A, C-F have been previously defined for polyethercarbonates containing a low proportion of carbonate linkages in the methods described in US2014/0323670. An extra resonance (B, 1.18-1.25 ppm) has been identified that is only present in significant quantities in polyethercarbonates with a high carbonate content. It has been assigned (by 2D NMR) as a terminal propylene CH₃ group between a carbonate unit and a hydroxyl end group. It is therefore added to the total carbonate units (C) as described in US2014/0323670.

Carbonate/ether ratio (m/n+m): molar ratio of carbonate and ether linkages:

$$\frac{m}{n+m} = R_C = \frac{B+C}{A+B+C} \quad (\text{Equation 1})$$

5 CO₂ wt % in polyol: amount of CO₂ incorporated into the total polyol:

$$CO_2 \text{ wt}\% = \frac{(C+B) \times 44}{(A \times 58) + ((B+C) \times 102) + (0.75 \times (E \times 118))} \times 100 \quad (\text{Equation 2})$$

Wherein 44 is the mass of CO₂ within a carbonate unit, 58 is the mass of a polyether unit, 102 is
10 the mass of a polycarbonate unit and 118 is the mass of the hexanediol starter (the factor 0.75
is added as the hexanediol resonance corresponds to 4 protons whilst all the other resonances
correspond to 3). This is the total proportion of CO₂ that is present in the entire polyol. If other
starters are used it is appreciated the relevant NMR signals, relative integrations and molecular
weights will be used in the calculation.

15

Furthermore, resonance C can be broken down into two different resonances. From 1.26-1.32
ppm (C¹) corresponds to the propylene CH₃ in a polymer unit between a carbonate and an ether
linkage (a polyethercarbonate, PEC linkage) whilst the resonance from 1.32-1.38 ppm (C²)
comes from a propylene CH₃ in a polymer unit in between two carbonate linkages (a
20 polycarbonate, PC linkage). The ratio of PEC, PC and PE linkages gives an indication of the
structure of the polymer. A completely blocked structure will contain very few PEC linkages
(only those at the block interfaces), whilst a more random structure will include a significant
proportion of PEC linkages where both polyether and polycarbonate units are adjacent to each
other in the polymer backbone. The ratio of these two units gives an indication of the structure.

25

Polyethercarbonate/polycarbonate linkage ratio:

$$R_{PEC} = \frac{C^1}{C^1 + C^2} \quad (\text{Equation 3})$$

Gel Permeation Chromatography

30 GPC measurements were carried out against narrow polydispersity poly(ethylene glycol) or
polystyrene standards in THF using an Agilent 1260 Infinity machine equipped with Agilent
PLgel Mixed-E columns.

Viscosity

The viscosity of the polyol samples was measured according to ASTM Standard D4878-15 using a Lamy RM200 Rheometer at sheer rates between 10-400s⁻¹.


OH value

- 5 The OH value was determined by titration against NaOH according to ASTM D4274-11 using a Mettler Toledo T50M manual titrator.

Example 1

Synthesis of DMC catalyst

- 10 The DMC catalyst used in this example was prepared according to the method reported in Journal of Polymer Science; Part A: Polymer Chemistry, 2002, 40, 1142. In brief, 1.0g of K₃Co(CN)₆ was dissolved in a mixture solvent of 13g distilled water and 2g tert-butyl alcohol. 6g of ZnCl₂ was dissolved in a mixture solvent of 13g water and 4g tert-butyl alcohol, and then this mixture was added slowly to the K₃Co(CN)₆ solution over a period of 20 minutes, whilst stirring.
- 15 The mixture was then stirred for a further 40 minutes and then centrifugal separation was performed to yield a white precipitate. The precipitate was dispersed in a mixture solvent of 16g water and 16g tert-butyl alcohol, and stirred for 20 minutes, and then the precipitate was separated by centrifuge. This washing procedure was repeated 3 times. The white precipitate was then dispersed in 50g tert-butyl alcohol, and then stirred for 20 minutes, followed by
- 20 centrifugal separation to obtain a white precipitate. The washing with tert-butyl alcohol was then repeated once more. The solvent was then removed under reduced pressure at 60°C for 8 hours. The resultant compound is understood to have the formula Zn₃[Co(CN)₆]₂ · hZnCl₂ · 0.5H₂O · 2[(CH₃)₃COH].
- 25 **Synthesis of [L¹Ni₂(OAc)₂], Catalyst 1**
Ligand H₂L¹ was synthesised by the method previously described by Kember et al, Angew. Chem. Int. Ed., 2009, 48, 931-933.



H₂L¹ (2 mmol) was dissolved in MeOH (50 mL), then Ni(OAc)₂·4H₂O (0.498 g, 4 mmol) was added portionwise over 15 minutes and the solution stirred overnight. The solvent was removed under vacuum and excess water/AcOH was removed by azeotrope with toluene (3 x 40 mL).

- 5 [L¹Ni₂(OAc)₂]: IR (ν_{C=O}, cm⁻¹, neat): 1581 and 1413. MALDI-TOF MS: *m/z*: 727.6 ([M -OAc])⁺, 100%).

Polymerisation reaction

X mg of DMC catalyst, optionally 165 mg of [L¹Ni₂(OAc)₂], and 3 g of PPG-425 (polypropylene glycol) starter were taken into a 100 ml oven dried reactor. The reactor vessel was closed and set to the reactor controller. The catalyst and starter were dried at 110° C – 120° C under vacuum of -1.0 bar for 1-2 hours. After that, the reactor was cooled down to the room temperature and propylene oxide (PO) (15 ml) was injected into the vessel via a syringe under 1 bar CO₂ gas and the reaction mixture heated up to 80 °C. Once at temperature, the desired CO₂ pressure was added and the reaction was continued for the desired time. After completion, the reactor was cooled down to below 10° C and the pressure was released very slowly. NMR and GPC was measured instantly. The crude reaction mixture was diluted in CH₂Cl₂ and poured into HCl/MeOH..

20 Results

Table 1: Combination of DMC and [L¹Ni₂(OAc)₂]: influence on polymer properties

No.	DMC (mg)	[L ¹ Ni ₂ (OAc) ₂] (mg)	Time	Pressure (bar)	Mn (g/mol)	PDI	CO ₂ Wt%
1	1.9	-	6	10	1100	2.3	7.5
2	1.9	-	6	5	1400	2.5	7.5
3	1.6	165	6	5	700	1.18	17.6
4	1.3	165	6	10	850	1.1	21.6

The results set out in Table 1 show that the combination of a DMC catalyst and a catalyst of formula (I) can prepare short chain polyols under low CO₂ pressures but still containing a high CO₂ content. It can clearly be seen that by combining both the DMC catalyst and [L¹Ni₂(OAc)₂] under 5 or 10 bar pressure, significantly more CO₂ can be incorporated than can be by just using the DMC catalyst alone. It also advantageously gives low polydispersities (<1.2) which will give better performance in polyurethane formulations.

Reactions were carried out using the same procedure as above but a range of starters (20 molar eq. vs [L¹Ni₂(OAc)₂])

Table 2: Variation of starter compound

No.	DMC (mg)	[L ¹ Ni ₂ (OAc) ₂] (mg)	Starter	Pressure (bar)	CO ₂ wt%	Mn (g/mol)	PDI
1	1.7	165	PPG 1000	10	12.27	1700	1.05
2	1.7	165	PPG 725	10	13.4	1400	1.06
3	1.7	165	1,6 hexanediol	10	12.9	700	1.08

The results in Table 2 demonstrate that a variety of starters can be successfully used to produce low polydispersity polyols with a variety of molecular weights under low CO₂ pressures.


5

Example 2

Synthesis of [L²³Ni₂(OAc)₂] - Catalyst 2

Catalyst [L²³Ni₂(OAc)₂] - **2** was prepared as per catalyst **1** except using a methylated macrocyclic ligand.

10



Catalyst 2

Example 2a:

15 All polymerizations were performed in 100 mL Parr reaction vessels which were dried at 140 °C in an oven for 1 h prior to use. The DMC catalyst as prepared in Example 1 (15 mg) and 1,6-hexanediol (2.28 g, 19.32 mmol) were taken inside the reactor vessel while the vessel temperature was below 80 °C. The reactor was assembled and placed under vacuum for 30 minutes at 120 °C. The vessel was cooled to room temperature. Catalyst **2** (270 mg, 0.321 mmol) was dried in a Schlenk tube under vacuum for about 30–40 minutes before propylene oxide (45 ml, 643.08 mmol) was added. The catalyst solution was transferred into the Parr reaction vessel via syringe under CO₂ at atmospheric pressure. The reactants were stirred under atmospheric pressure CO₂ whilst the vessel was heated to 60 °C. When the temperature reached to the reaction temperature, the reactor vessel was charged with 5 bar CO₂. After 16 hours, the reactor was cooled down to 5–6 °C, vented, and the product removed from the

20

25

reactor. The crude product was analysed by ^1H NMR and GPC. The crude product was stabilized using p-toluenesulfonic acid, 12% acetic acid (5 mol/mol c.f. catalyst **2**).

The polyol was formed with 89% selectivity over the cyclic carbonate with a propylene oxide conversion of 78%. For viscosity/OH number measurements the cyclic propylene carbonate by-product was removed on a Kugelrohr by vacuum distillation at 100 °C for 3 hours.

Example 2b:

Example 2b was carried out in the same way as Example **2a** except using 128 mg Catalyst **2**, at a reaction temperature of 55 °C for 64 hours (over a weekend).

The resulting polyol was formed in 89% selectivity over the cyclic carbonate with a propylene oxide conversion of 91%.

Example 2c:

Example 2c was carried out in the same way as Example **2a** except using a reaction temperature of 60 °C for 64 hours (over a weekend).

The polyol was formed with 84% selectivity over the cyclic carbonate with a propylene oxide conversion of 99.5%.

Example 2d:

Example 2d was carried out in the same way as Example **2a** except using a reaction temperature of 80 °C for 16 hours.

The resulting polyol was formed in 92.1% selectivity over the cyclic carbonate with a propylene oxide conversion of >99.5%

Example 2e:

Example 2e was carried out in the same way as Example **2a** except using a reaction temperature of 85 °C for 16 hours.

The resulting polyol was formed in 92% selectivity over the cyclic carbonate, with a propylene oxide conversion of 95%.

Table 3: Copolymerisation data for Examples 2a-2e

E.g.	P (bar)	R _C	R _{PEC}	CO ₂ (wt%)	Mn (GPC)*	PDI	OH No.	Mw from OH. No.	Viscosity (mPa.s, 21 °C)	Viscosity (mPa.s, 75 °C)
2a	5	0.72	0.35	33%	1400	1.7	-	1700 [‡]	- [‡]	2050
2b	5	0.54	0.67	26.6%	1700	1.6	54.9	2050	21300	520
2c	5	0.46	0.69	25.6%	1750	1.5	55.9	2010	14400	430
2d	5	0.31	0.82	18.4%	1950	1.5	-	2200 [‡]	3800	230
2e	5	0.15	0.53	10%	1450	1.6	-	1750 [‡]	860	60

* Gel Permeation Chromatography run against narrow poly(ethylene glycol) standards in THF. [‡]

Mw estimated based upon calibration between OH no. titration experiments and GPC

measurements across a wide range of polycarbonate polyol samples with varying molecular

5 weights. [‡] Not measured as the viscosity was too high for the torque rating of the machine at this temperature.

The results in Table 3 demonstrate that the catalyst system of the present invention can be used to produce a range of polyols with moderate (10 wt%) to high (33 wt%) CO₂ incorporation at just 5 bar CO₂ pressure. The polyols can be made in high yields with good polyol selectivities and performance can be tailored for preferred process and product parameters by selection of either catalyst.

15 Furthermore, Table 3 and Figures 6 and 7 demonstrate the significant effect CO₂ content has on polyol viscosity. Taking into account the slight variation in molecular weights, a clear correlation can be seen between the polyol viscosity and CO₂ content. The CO₂ content can be tuned using the inventive process to meet the requirements of the desired application without the need for high pressure operation. The inventive process can also be tuned to make relatively short chain polyols (<2000 g/mol) which have high CO₂ content as a pre-polymerisation (or activation) phase in the absence of CO₂ that only produces polyether is not necessary using the claimed invention.

Figures 6 and 7 set out the viscosity of the polymers produced in Examples 2a-2e at 75°C and 25°C respectively, the benchmarks used were **B1** PPG-2000 (viscosity at 75°C from

25 US3054755, viscosity at 25 °C from Sigma Aldrich) and **B2** - a polyol produced just with catalyst

2 using a poly(propylene glycol)-425 starter under conditions which favour high CO₂ incorporation (the polyol is essentially a polycarbonate – polyether – polycarbonate triblock with an R_c of 0.80 and an R_{PEC} of 0.16). All polymers have a M_w of approximately 2000.

5 It can be seen from R_{PEC}, which is the ratio of PEC/PC, that in all cases a very significant proportion of the carbonate linkages present are adjacent to an ether linkage, indicating the polymers are formed with a significantly random structure and not a well-defined block structure. In comparison, 2a and B2, have similar R_c values (0.71 vs. 0.80) but very different R_{PEC} values (0.35 and 0.16) indicating a significant increase in the random structure in 2a. Figures 8 and 9
10 show the ¹H NMR spectra from examples 2a and 2b, demonstrating the change in the amount of PEC and PC linkages.

Figure 10 demonstrates the different the structure of the polyol has on the thermal stability. B2 demonstrates significant decomposition at around 200 °C, with a clear second degradation at
15 250 °C which is understood to correspond to the polyether block section. In comparison, the polyol of example 2a demonstrates a similar onset but a much slower degradation and a much less defined two-stage degradation – indicating the random mixing of the ether and carbonate units within the polyols structure. Polyols produced in examples 2b-e show a significantly increased degradation temperature as well as a one-stage degradation indicating the polyols
20 are random in structure and do not contain significant blocks of polycarbonate (as indicated by the high R_{PEC} values).

Example 3:

Several experiments were carried out as per Example 2, except with variation of the starter.

25

Example 3a:

Example 3a was carried out as per Example 2a except 1,4-cyclohexanedimethanol (2.77g, 19.3 mmol) was used as the starter, and the reaction carried out at 75 °C and 10 bar CO₂ pressure.

30 The resulting polyol was formed in 74% selectivity over the cyclic carbonate with a propylene oxide conversion of 94.5%.

Example 3b:

Example 3b was carried out as per Example 3a except 1,12-dodecanediol (3.88g, 19.3 mmol)
35 was used as the starter.

The resulting polyol was formed in 78.8% selectivity over the cyclic carbonate with a propylene oxide conversion of 98.2%.

Example 3c:

- 5 Example 3c was carried out as per Example 3a except Poly(caprolactone) diol (Mn 530, 10.1g, 19.3 mmol) was used as the starter.

The resulting polyol was formed in 81.4% selectivity over the cyclic carbonate with a propylene oxide conversion of 98.6%.

10

Example 3d:

Example 3d was carried out as per Example 3a except poly(propylene glycol) (Mn 425, 8.17g, 19.3 mmol) was used as the starter.

- 15 The resulting polyol was formed in 78.8% selectivity over the cyclic carbonate with a propylene oxide conversion of 95.0%.

Table 4: Copolymerisation data for Examples 3a-d

E.g.	P (bar)	Starter	R _c	CO ₂ (wt%)	Mn (GPC)*	PDI
3a	10	1,4-cyclohexanedimethanol	0.51	23.8%	1900	1.9
3b	10	1,12-dodecanediol	0.60	28.0%	2600	1.8
3c	10	Poly(caprolactone) diol Mn - 530	0.48	19.8%	2700	1.7
3d	10	Poly(propylene glycol)- 425	0.47	26.7%	2500	1.9

The results in Table 4 demonstrate the invention can be carried out in the presence of a range of starters, producing polyols with varying molecular weights and still incorporate significant quantities of CO₂ under low pressures.

Example 4:

Example 4a

Example 4a was run according to Example 2a except with 1.08g 1,6-hexanediol, for 6 hours at 75 °C and 10 bar.

Example 4b

Example 4b was run according to Example 4a except in the absence of catalyst 2.

Example 4c

Example 4c was run according to Example 4a except in the absence of the DMC catalyst.

Table 5: Copolymerisation data for Examples 4a-c

E.g.	P (bar)	Cat 2	DMC	Conv.	R _c	CO ₂ (wt%)	Mn (GPC)*	PDI
4a	10	Yes	Yes	88%	0.57	28.4%	2000	1.9
4b	10	No	Yes	8%	0.60	25%	350	1.1
4c	10	Yes	No	34%	0.97	37%	700	1.16

Table 5 demonstrates that the invention provides a product and a performance that isn't achieved by either catalyst on its own under the same conditions, giving an increased conversion, molecular weight and balanced R_c . Whilst the DMC alone gives a reasonable carbonate content under these conditions it provides almost no conversion of monomer to polymer or molecular weight development.

10

15

20


25

30

35

Claims

1. A method for preparing a polycarbonate ether polyol, the method comprising reacting carbon dioxide and an epoxide in the presence of a double metal cyanide (DMC) catalyst, a catalyst of formula (I), and a starter compound, wherein the catalyst of formula (I) has the following structure:



Wherein M_1 and M_2 are independently selected from Zn(II), Cr(II), Co(II), Cu(II), Mn(II), Mg(II), Ni(II), Fe(II), Ti(II), V(II), Cr(III)-X, Co(III)-X, Mn(III)-X, Ni(III)-X, Fe(III)-X, Ca(II), Ge(II), Al(III)-X, Ti(III)-X, V(III)-X, Ge(IV)-(X)₂ or Ti(IV)-(X)₂;

R_1 and R_2 are independently selected from hydrogen, halide, a nitro group, a nitrile group, an imine, an amine, an ether group, a silyl group, a silyl ether group, a sulfoxide group, a sulfonyl group, a sulfinate group or an acetylide group or an optionally substituted alkyl, alkenyl, alkynyl, haloalkyl, aryl, heteroaryl, alkoxy, aryloxy, alkylthio, arylthio, alicyclic or heteroalicyclic group;

R_3 is independently selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, arylene, heteroarylene or cycloalkylene, wherein alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene and heteroalkynylene, may optionally be interrupted by aryl, heteroaryl, alicyclic or heteroalicyclic;

R_5 is independently selected from H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl or alkylaryl;

E_1 is C and E_2 is O;

E_3 , E_4 , E_5 and E_6 are selected from N, NR_4 , O and S, wherein when E_3 , E_4 , E_5 or E_6 are N, ----- is =====, and wherein when E_3 , E_4 , E_5 or E_6 are NR_4 , O or S, ----- is -----;

R₄ is independently selected from H, or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, heteroaryl, alkylheteroaryl, -alkylC(O)OR₁₉ or -alkylC≡N or alkylaryl;

X is independently selected from OC(O)R_x, OSO₂R_x, OSOR_x, OSO(R_x)₂, S(O)R_x, OR_x, phosphinate, halide, nitrate, hydroxyl, carbonate, amino, amido or optionally substituted aliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl or heteroaryl;

R_x is independently hydrogen, or optionally substituted aliphatic, haloaliphatic, heteroaliphatic, alicyclic, heteroalicyclic, aryl, alkylaryl or heteroaryl; and

G is absent or independently selected from a neutral or anionic donor ligand which is a Lewis base; and

and wherein the starter is a compound having the following structure:



Z is selected from optionally substituted alkylene, alkenylene, alkynylene, heteroalkylene, heteroalkenylene, heteroalkynylene, cycloalkylene, cycloalkenylene, heterocycloalkylene, heterocycloalkenylene, arylene, heteroarylene, or Z may be a combination of any of these groups, such as an alkylarylene, heteroalkylarylene, heteroalkylheteroarylene or alkylheteroarylene group;

a is an integer which is at least 2; and

each R^Z may be -OH, -NHR', -SH, -C(O)OH, PR'(O)(OH)₂, -P(O)(OR')(OH) or -PR'(O)OH, preferably R^Z may be -OH, -C(O)OH or -NHR', more preferably each R^Z may be -OH, -C(O)OH or a combination thereof.

2. The method of claim 1 wherein the reaction is carried out at a pressure of between about 1 bar and about 60 bar carbon dioxide, preferably between about 1 bar and about 30 bar carbon dioxide, more preferably between about 1 bar and about 20 bar carbon dioxide, more preferably between about 1 bar and about 15 bar carbon dioxide, more preferably between about 1 bar and about 10 bar carbon dioxide.
3. The method of claim 1 or 2, wherein M₁ and/or M₂ is selected from Mg(II), Zn(II), or Ni(II), preferably wherein M₁ and M₂ are selected from Mg(II), Zn(II), or Ni(II),.
4. The method of any preceding claim, wherein X is independently selected from OC(O)R^x, OSO₂R^x, OS(O)R^x, OSO(R^x)₂, S(O)R^x, OR^x, halide, nitrate, hydroxyl, carbonate, amino, nitro, amido, alkyl, heteroalkyl, aryl or heteroaryl, and/or R^x may be optionally substituted alkyl, alkenyl, alkynyl, heteroalkyl, aryl, heteroaryl,

cycloalkyl, or alkylaryl.

5. The method of any preceding claim, wherein the catalyst of formula (I) has a symmetric macrocyclic ligand.

5


6. The method of any of claims 1 to 4, wherein the catalyst of formula (I) has an asymmetric macrocyclic ligand.

7. The method of claim 6, wherein E_3 , E_4 , E_5 and E_6 are NR_4 , wherein at least one occurrence of E_3 , E_4 , E_5 and E_6 is different to the remaining occurrence(s) of E_3 , E_4 , E_5 and E_6 are, preferably wherein R_4 is H or alkyl.


10

8. The method according to any preceding claim, wherein the catalyst is of the formula:


15



$[L^1M_1M_2(X)_2(G)_2]$




$[L^2M_1M_2(X)_2(G)_2]$




$[L^3M_1M_2(X)_2(G)_2]$


20




$[L^4M_1M_2(X)_2(G)_2]$




$[L^5M_1M_2(X)_2(G)_2]$




$[L^6M_1M_2(X)_2(G)_2]$




$[L^7M_1M_2(X)_2(G)_2]$




$[L^8M_1M_2(X)_2(G)_2]$




$[L^9M_1M_2(X)_2(G)_2]$




$[L^{10}M_1M_2(X)_2(G)_2]$




$[L^{11}M_1M_2(X)_2(G)_2]$




$[L^{12}M_1M_2(X)_2(G)_2]$




$[L^{13}M_1M_2(X)_2(G)_2]$



$[L^{14}M_1M_2(X)_2(G)_2]$




$[L^{15}M_1M_2(X)_2(G)_2]$




[L¹⁶M₁M₂(X)₂(G)₂]

[L¹⁷M₁M₂(X)₂(G)₂]


[L¹⁸M₁M₂(X)₂(G)₂]



[L¹⁹M₁M₂(X)₂(G)₂]




[L²⁰M₁M₂(X)₂(G)₂]





[L²¹M₁M₂(X)₂(G)₂]

or



[L²²M₁M₂(X)₂(G)₂]

5 9. The method according to any of claims 1 to 7, wherein the catalyst is of the formula:



10. The method of any preceding claim, wherein the reaction is carried out at a temperature in the range of from about 50°C to about 110°C, preferably from about 60°C to about 100°C.

11. The method of any preceding claim, wherein each occurrence of R^Z may be $-OH$.

12. The method of any preceding claim, wherein a is an integer in the range of between about 2 and about 8, preferably in the range of about 2 and about 6.

13. The method of any of claims 1 to 10, wherein the starter compound is from diols such as 1,2-ethanediol (ethylene glycol), 1,2-propanediol, 1,3-propanediol (propylene glycol), 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,8-octanediol, 1,10-decanediol, 1,4-cyclohexanediol, 1,2-diphenol, 1,3-diphenol, 1,4-diphenol, neopentyl glycol, catechol, cyclohexenediol, 1,4-cyclohexanedimethanol, dipropylene glycol, diethylene glycol, tripropylene glycol, triethylene glycol, tetraethylene glycol, polypropylene glycols (PPGs) or polyethylene glycols (PEGs) having an M_n of up to about 1500g/mol, such as PPG 425, PPG 725, PPG 1000 and the like, triols such as glycerol, benzenetriol, 1,2,4-butanetriol, 1,2,6-hexanetriol, tris(methylalcohol)propane, tris(methylalcohol)ethane, tris(methylalcohol)nitropropane, trimethylol propane, polypropylene oxide triols and polyester triols, tetraols such as calix[4]arene, 2,2-bis(methylalcohol)-1,3-propanediol, erythritol, pentaerythritol or polyalkylene glycols (PEGs or PPGs) having 4- $-OH$ groups, polyols, such as sorbitol or polyalkylene glycols (PEGs or PPGs) having 5 or more $-OH$ groups, diacids such as oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid,

suberic acid, azelaic acid, sebacic acid, undecanedioic acid, dodecanedioic acid or other compounds having mixed functional groups such as lactic acid, glycolic acid, 3-hydroxypropanoic acid, 4-hydroxybutanoic acid, 5-hydroxypentanoic acid.

14. The method of any of claims 1 to 10, wherein the starter compound is a diol such as 1,2-ethanediol (ethylene glycol), 1,2-propanediol, 1,3-propanediol (propylene glycol), 1,2-butanediol, 1,3-butanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,8-octanediol, 1,10-decanediol, 1,12-dodecanediol, 1,4-cyclohexanediol, 1,2-diphenol, 1,3-diphenol, 1,4-diphenol, neopentyl glycol, catechol, cyclohexenediol, 1,4-cyclohexanedimethanol, poly(caprolactone) diol, dipropylene glycol, diethylene glycol, tripropylene glycol, triethylene glycol, tetraethylene glycol, polypropylene glycols (PPGs) or polyethylene glycols (PEGs) having an Mn of up to about 1500g/mol, such as PPG 425, PPG 725, PPG 1000 and the like, preferably wherein the starter compound is 1,6-hexanediol, 1,4-cyclohexanedimethanol, 1,12-dodecanediol, poly(caprolactone) diol, PPG 425, PPG 725, or PPG 1000.

15. The method of any preceding claim, wherein the DMC catalyst is prepared by treating an aqueous solution of a metal salt with an aqueous solution of a metal cyanide salt in the presence of an organic complexing agent, preferably wherein the metal salt is of the formula $M'(X')_p$, wherein M' is selected from Zn(II), Fe(II), Ni(II), Mn(II), Co(II), Sn(II), Pb(II), Fe(III), Mo(IV), Mo(VI), Al(III), V(V), V(VI), Sr(II), W(IV), W(VI), Cu(II), and Cr(III), X' is an anion selected from halide, hydroxide, sulphate, carbonate, cyanide, oxalate, thiocyanate, isocyanate, isothiocyanate, carboxylate and nitrate, p is an integer of 1 or more, and the charge on the anion multiplied by p satisfies the valency of M' ;

the metal cyanide salt is of the formula $(Y)_qM''(CN)_b(A)_c$, wherein M'' is selected from Fe(II), Fe(III), Co(II), Co(III), Cr(II), Cr(III), Mn(II), Mn(III), Ir(III), Ni(II), Rh(III), Ru(II), V(IV), and V(V),

Y is an alkali metal ion or an alkaline earth metal ion (such as K^+),

A is an anion selected from halide, hydroxide, sulphate, cyanide oxalate, thiocyanate, isocyanate, isothiocyanate, carboxylate and nitrate;

q and b are integers of 1 or more;


c may be 0 or an integer of 1 or more;

the sum of the charges on the anions Y , CN and A multiplied by q , b and c respectively (e.g. $Y \times q + CN \times b + A \times c$) satisfies the valency of M'' ; and

the complexing agent is an ether, a ketone, an ester, an amide, an alcohol, an urea or a combination thereof, preferably wherein the complexing agent is dimethoxyethane, tert-butyl alcohol, ethylene glycol monomethyl ether, diglyme, triglyme, ethanol, isopropyl alcohol, n-butyl alcohol, isobutyl alcohol, or sec-butyl alcohol.

5

16. The method of any preceding claim, wherein the DMC catalyst comprises the formula:



Wherein M' and M'' are as defined in claim 15, and d, e, f and g are integers, and are chosen to such that the DMC catalyst has electroneutrality,

10

preferably, d is 3, e is 1, f is 6 and g is 2.

17. The method of claims 15 or 16 wherein M' is selected from Zn(II), Fe(II), Co(II) and Ni(II) and/or M'' is selected from Co(II), Co(III), Fe(II), Fe(III), Cr(III), Ir(III) and Ni(II), preferably M' is Zn(II) and M'' is Co(III).

15

18. The method of claims 15 to 18, wherein the DMC catalyst additionally comprises water, an organic complexing agent and/or a metal salt.

19. A polymerisation system for the copolymerisation of carbon dioxide and an epoxide, comprising:

20

- a. A catalyst of formula (I) as defined in any preceding claim,
- b. A DMC catalyst as defined in any preceding claim, and
- c. A starter compound as defined in any preceding claim.

25

20. A polycarbonate ether polyol prepared by the method of any of claims 1 to 18, wherein the polycarbonate ether polyol has n ether linkages and m carbonate linkages, wherein n and m are integers, and wherein $m/(n+m)$ is from 0.05 to 0.95.

30

21. A polyurethane or other polymer prepared from a polycarbonate ether polyol as defined in claim 20.