

TITLE OF THE INVENTION:

Selectively Removing Titanium Nitride Hard Mask and Etch Residue Removal

[0001] This Application claims the benefit of U.S. Provisional Application No. 62/140,846, filed on March 31, 2015. The disclosure of this Application is hereby
5 incorporated by reference.

BACKGROUND OF THE INVENTION

[0002] As scaling continues to ever smaller feature sizes, integrated circuit (IC) reliability is an increasing concern in IC fabrication technology. The impact of trace
10 interconnect failure mechanisms on device performance and reliability demand much more from integration schemes, interconnect materials, and processes. An optimal low-k dielectric material and its related deposition, pattern lithography, etching and cleaning are required to form dual-damascene interconnect patterns. A hard-mask scheme approach of interconnects-patterning wafer fabrication is the ability to transfer patterns
15 into under layers with tightest optimal dimension control.

[0003] As technology nodes advance to nanotechnology, metal hard-mask materials such as TiN are used to gain better etching / removal selectivity, better pattern retention and profile control to the low-k materials during the pattern etching process.

[0004] Formulations have been developed to pullback or remove these types of metal
20 hard-masks from substrates.

[0005] The following patents are representatives.

[0006] US2013/0157472 describes the formulations comprising Cl⁻, or Br⁻ an oxidizer and potentially a Cu corrosion inhibitor to clean substrates containing low-k dielectric and Cu and to etch a TiN or TiN_xO_y hardmask and tungsten. The formulation typically
25 contains 6% hydrogen peroxide as the oxidizer and diglycolamine to adjust the pH to > 7.

[0007] US 2009/0131295 A1 describes the removal of hard mask residues (typically TiF containing) after plasma etch from TiN at a pH of 1-8 using acidic or basic fluoride or bifluoride.

[0008] US7479474 B2 describes cleaning formulations comprising H_2SiF_6 or HBF_4 to
5 reduce oxide etch in a substrate comprising low-K dielectric.

[0009] WO 2013/101907 A1 describes formulations comprising etchants including hexafluorosilicic acid and hexafluorotitanate, at least one oxidant including high valent metals, peroxide or high oxidation state species and at least one solvent.

10

BRIEF SUMMARY OF THE INVENTION

[0010] The present invention relates to composition, system and process for selectively etching hard mask layers and/or etch residues relative to metal conductor layers and low-k dielectric layers that are present. More specifically, the present invention relates to a composition, system and process for selectively etching a Titanium nitride hard mask
15 and/or etch residues relative to tungsten, copper and low-k dielectric layers.

[0011] In one aspect, a composition for selectively removing titanium nitride (TiN or TiN_xO_y ; where $x = 0$ to 1.3 and $y = 0$ to 2) from a semiconductor device comprising TiN or TiN_xO_y and a second material; the composition comprising:

an amine salt buffer;

20 a non-ambient oxidizer; and

liquid carrier;

wherein

the composition comprises no hydrogen peroxide;

the composition has a $\text{pH} < 4$, preferably < 3 , more preferably < 2.5 ;

25 the second material is selected from the group consisting of Cu, W, aluminum nitride (AlN_x with $x=0.5$ to 1), aluminum oxide (AlO_x with $x=1$ to 1.5), low-k dielectric material, and combinations thereof

and

30 the composition offers a removal selectivity of TiN or TiN_xO_y vs. the second material $> 1:1$, preferably $> 5:1$, and more preferably $> 10:1$.

[0012] In another aspect, a system for selectively removing titanium nitride (TiN or TiN_xO_y, where x = 0 to 1.3 and y = 0 to 2) from a surface of a microelectronic device, comprising:

the semiconductor device comprising TiN or TiN_xO_y and a second material,

5 a composition for selectively removing the TiN or TiN_xO_y from the semiconductor device comprising:

an amine salt buffer;

a non-ambient oxidizer; and

liquid carrier;

10 wherein

the composition comprises no hydrogen peroxide;

the composition has a pH < 4, preferably < 3, more preferably < 2.5;

the second material is selected from the group consisting of Cu, W, aluminum nitride (AlN_x with x=0.5 to 1), aluminum oxide (AlO_x with x=1 to 1.5), low-k dielectric material, and combinations thereof; and

15

the composition offers a removal selectivity of TiN or TiN_xO_y vs. the second material > 1:1, preferably > 5:1, and more preferably >10:1.

[0013] In yet another aspect, a process of selectively removing titanium nitride (TiN or TiN_xO_y, where x = 0 to 1.3 and y = 0 to 2) comprising:

20 providing a semiconductor device comprising TiN or TiN_xO_y and a second material;

contacting the semiconductor device with a composition comprising:

an amine salt buffer;

a non-ambient oxidizer; and

25 liquid carrier;

wherein

the composition comprises no hydrogen peroxide;

the composition has a pH < 4, preferably < 3, more preferably < 2.5;

the second material is selected from the group consisting of Cu, W, aluminum nitride (AlN_x with $x=0.5$ to 1), aluminum oxide (AlO_x with $x=1$ to 1.5), low-k dielectric material, and combinations thereof; and

5 selectively removing TiN or TiN_xO_y ; and removal selectivity of TiN or TiN_xO_y vs. the second material is $> 1:1$, preferably $> 5:1$, and more preferably $>10:1$.

[0014] The amine salt buffer includes but is not limited to ammonium chloride; ammonium bisulfate; ammonium phosphates; ammonium oxalate; ammonium perfluorosulfonates; ammonium tetrafluoroborate; ammonium hexafluorotitanate; ammonium hexafluorosilicate; ammonium salts of organic acid selected from ammonium
10 citrate, ammonium acetate, ammonium lactate; and combinations thereof;

wherein the ammonium having a form of $\text{N}(\text{R}^1\text{R}^2\text{R}^3\text{R}^4)^+$;

wherein $\text{R}^1, \text{R}^2, \text{R}^3, \text{R}^4$ is independently selected from the group consisting of H, CH_3 , C_2H_5 , and C_3H_7 .

[0015] A non-ambient oxidizer includes but is not limited to salts of persulfates
15 including but not limited to sodium persulfate, ammonium persulfate; salts of iodate; salts of periodate; Cl(I, III or V) compounds; Br(I, III or V) compounds; and combinations thereof.

[0016] The liquid carrier includes but is not limited to water and non-water liquid carrier selected from the group consisting of dimethyl sulfone, lactic acid, glycol, and a polar
20 aprotic solvent including but not limited to sulfolanes, sulfoxides, nitriles, formamides and pyrrolidones. Specific examples of polar aprotic solvent include but are not limited to sulfolane, acetonitrile, dimethylformamide and N-methylpyrrolidone.

[0017] The composition can be aqueous when the liquid carrier is water. The aqueous composition further comprises acidic fluoride.

25 **[0018]** The composition can be semi-aqueous when it contains water and at least one non-water liquid carrier. The semi-aqueous composition can further comprises acidic fluoride when the non-water liquid carrier is not a polar aprotic solvent.

[0019] The acidic fluoride includes but is not limited to ammonium bifluoride, alkylammonium bifluoride or aqueous hydrogen fluoride itself, fluorosilicic acid,
30 fluoroboric acid, acids of hydrated fluoroaluminates, and combinations thereof. The compositions may further comprise a weakly coordinating anion having negative charge highly dispersed throughout its structure, corrosion inhibitor, and surfactant

[0020] The weakly coordinating anion includes but is not limited to p-toluenesulfonate ($C_7H_8SO_3^-$), sulfate (SO_4^{2-}), nitrate (NO_3^-), triflate ($CF_3SO_3^-$), fluorosulfate, perfluorosulfonates ($R_fSO_3^-$; R_f is a perfluoroalkyl group from C1 to C4), perfluorosulfonimides; ($(R_f)_2NSO_2^-$; where R_f is a perfluoroalkyl group from C1 to C4),
5 hexafluorosilicate (SiF_6^{2-}), hexafluorotitanate (TiF_6^{2-}), tetrafluoroborate (BF_4^-), hexafluorophosphate (PF_6^-), hexafluoroantimonate (SbF_6^-), perfluoroalkylaluminates ($(R_fO)_4Al^-$, R_f is a perfluoroalkyl group), and combinations thereof.

[0021] Other aspects, features and embodiments of the invention will be more fully
10 apparent from the ensuing disclosure and appended claims.

DETAILED DESCRIPTION OF THE INVENTION

[0022] In general, the present invention relates to compositions, systems and processes for selectively etching hard mask layers and/or photoresist etch residues
15 relative to metal conductor layers and low-k dielectric layers that are present. Specifically, this invention describes compositions, systems and processes with good removal rate for titanium nitride hard mask material (TiN or TiN_xO_y , where $x = 0$ to 1.3 and $y = 0$ to 2), called TiN hard mask material for simplicity hereafter; without damage to the metal 1 layer (M1) (such as tungsten) and other M1 level components including low
20 k dielectric materials, and in some cases aluminum nitride (AlN_x with $x=0.5$ to 1), aluminum oxide (AlO_x with $x=1$ to 1.5) dielectric layers.

[0023] Compositions, or formulations (compositions, formulations are used exchangeable in present invention) designed for the removal of titanium nitride hard mask materials (TiN or TiN_xO_y , where $x = 0$ to 1.3 and $y = 0$ to 2) after wafer patterning
25 typically use hydrogen peroxide as an oxidant. The terms "formulation" and "composition" as used herein, are used interchangeably.

[0024] Chemistries involving hydrogen peroxide as an oxidizing agent for Titanium nitride hard mask removal have proven effective, but appear to be incompatible with tungsten metal in the M1 layer of the wafer. The formulations often etch tungsten even
30 more readily than the desired TiN hard mask. When hydrogen peroxide is used as an oxidant under slightly basic conditions to solubilize the titanium nitride as titanium

peroxide species, unfortunately the M1 level metal, such as tungsten, also readily forms soluble peroxides and is attacked by these chemistries.

5 **[0025]** The chemistry of this invention avoids the use of hydrogen peroxide. That is, this invention, more specifically, describes a new, hydrogen peroxide-free, platform of strippers (formulations) for Titanium nitride hard mask removal on 28nm wafers and smaller nodes. This aspect of the invention makes the chemistry much more compatible with tungsten.

[0026] Air at atmospheric conditions is an example of a mild ambient oxidizer. The term non-ambient oxidizer includes any oxidizer that is not air or oxygen in air.

10 **[0027]** Unless specified, air at atmospheric conditions is normally present during tool operation, a mild ambient oxidizer is considered be present for the formulations.

[0028] The invention operates at a low pH < 4, preferably < 3, and more preferably <2.5. The formulation can be both aqueous (those containing water only) and semi-aqueous (those containing water and at least one non-water liquid carrier) formulations.

15 The formulations comprise an amine salt buffer, a non-ambient oxidizer, an acidic fluoride source, and liquid carrier to remove the titanium nitride hard mask without etching tungsten. Nor does this chemistry etch the TiN liner between the tungsten and low-k dielectric layers. The amine salt buffer is used to maintain the pH of the formulation below 4, preferably < 3, and more preferably <2.5. The non-ambient oxidizer and acidic
20 fluoride are used to efficiently remove TiN.

[0029] The formulations contain an amine salt buffer. The amine salt buffer may include, but is not limited to, ammonium chloride, ammonium bisulfate, ammonium phosphates, ammonium oxalate, ammonium perfluorosulfonates, ammonium tetrafluoroborate, ammonium hexafluorotitanate or ammonium hexafluorosilicate (which
25 may be formed from ammonium hydroxide and hexafluorosilicic acid), or ammonium salts of organic acids, including but not limited to ammonium citrate, ammonium acetate, ammonium lactate, and combinations thereof.

[0030] By ammonium is meant a salt of any amine of the form $N(R^1R^2R^3R^4)^+$ where R^1, R^2, R^3, R^4 may all be the same or different or and may constitute H, CH₃, C₂H₅, C₃H₇.

30 **[0031]** The amount of the amine salt buffer is in the range of 0.5 – 10 wt%, preferably 1-10 wt% and more preferably 2-8 wt%.

[0032] The formulations contain a non-ambient oxidizer including but not limited to salts of persulfates including but not limited to sodium persulfate, ammonium persulfate, salts of iodate, salts of periodate, Cl(I,III or V) compounds, Br(I, III or V) compounds, and combinations thereof.

5 **[0033]** The non-ambient non-metal oxidizers are used in amounts ranging from 0.2 to 3 wt %, preferably from 0.5 to 2 wt% and more preferably from 0.5 to 1%.

[0034] The formulations contain an acidic fluoride which can be a solvolysing acidic fluoride at quantities < 4000 ppm, or < 2000 ppm, or < 500 ppm, depending on the stability of the oxide, e.g., O₃-tetraethylorthosilicate (TEOS) layer, or other low-k
10 dielectric layers.

[0035] The solvolysing acidic fluoride may include, but is not limited to ammonium bifluoride, alkylammonium bifluoride or aqueous hydrogen fluoride itself, fluorosilicic acid, fluoroboric acid, and acids of hydrated fluoroaluminates.

[0036] The formulations also include a liquid carrier. The liquid carrier may include, but
15 is not limited to water, and a non-water liquid carrier selected from the group consisting of dimethyl sulfone, lactic acid, glycol, and a polar aprotic solvent including but not limited to sulfolanes, sulfoxides, nitriles, formamides and pyrrolidones. Specific examples of polar aprotic solvent include but are not limited to sulfolane, acetonitrile, dimethylformamide and N-methylpyrrolidone. selected from the group consisting of
20 sulfolane, dimethyl sulfone, lactic acid, glycols, such as propylene glycol and mixtures thereof.

[0037] The formulations may further contain a weakly coordinating anion in either the acidic form or an amine substituted form. The weakly coordinating anion is also used to maintain the pH of the formulation below 4 and preferably below 3; and more preferably
25 below 2.5.

[0038] A weakly coordinating anion has negative charge highly dispersed throughout its structure and so is designed to stabilize and keep very reactive cations, such as those of dissolved titanium nitride, in aqueous formulation.

[0039] The weakly coordinating anion may include, but is not limited to, p-toluenesulfonate (C₇H₈SO₃⁻), sulfate (SO₄²⁻), nitrate(NO₃⁻), triflate(CF₃SO₃⁻), fluorosulfate, perfluorosulfonates (R_fSO₃⁻; where R_f is a perfluoroalkylgroup from C1 to C4),
30 perfluorosulfonimides; ((R_f)₂NSO₂⁻; where R_f is a perfluoroalkylgroup from C1 to C4),

hexafluorosilicate(SiF_6^{2-}), hexafluorotitanate (TiF_6^{2-}), tetrafluoroborate(BF_4^-), hexafluorophosphate (PF_6^-), hexafluoroantimonate (SbF_6^-) and perfluoroalkylaluminates($(\text{R}_f\text{O})_4\text{Al}^-$, where R_f is a perfluoroalkyl group), and combinations thereof.

- 5 **[0040]** The amount of the weakly coordinating anion is in the range of 1-10 wt%, preferably 2-8 wt%, and more preferably 4-8 wt%

[0041] The formulations may contain corrosion inhibitors to improve compatibility to other metals.

- 10 **[0042]** The corrosion inhibitor may include, but is not limited to benzotriazole or substituted benzotriazole, polyethyleneimine, catechol, cysteine and cystine derivatives, glycine, thiourea and thiobiuret, siloxane, aluminum chloride, aluminum fluoride, imidazole, triazole and boric acid.

[0043] The corrosion inhibitor is used in amounts of < 10000 ppm, preferably < 5000 ppm and more preferably < 1000 ppm.

- 15 **[0044]** The formulations may also contain surfactants to improve wettability of wafer surfaces. Examples of surfactants include but are not limited to ammonium lauryl sulfate and a wide range of organic sulfates, including salts of p-toluene sulfate. The surfactant is typically used in quantities < 1000 ppm, preferably < 500 ppm and more preferably < 100 ppm.

- 20 **[0045]** The formulations of this invention offer the following advantages.

1. High rates of Titanium nitride etch are observed at 70 °C and lower.
2. Aqueous and semi-aqueous solutions of the formulations are stable.
3. Low active fluoride containing formulations show low TEOS etch and patterned PDEMs® 2.2 ILD film.
- 25 4. Low or essentially no etch of tungsten, W, is observed, so formulations of this platform are compatible with and may be used in cleaning the M1 layer.
5. The formulations do not damage the TiN liner between the tungsten and the low-k dielectric layers.
- 30 6. Semi-aqueous formulations show low aluminum nitride etch compared with other formulations.

Working examples have exhibited key features and benefits of present invention.

[0046] Working examples have exhibited key features and benefits of present invention.

5

Working Examples

[0047] Aqueous formulations were prepared by blending the components as described in Tables 1A. Semi-aqueous formulations were prepared as described in Table 1 B.

[0048] Wafers of varying types of TiN, W, TEOS and typical inter- layer dielectric (ILD) materials, for example, patterned PDEMs 2.2, were immersed in the formulations with
10 500 rpm stirring and heating to between 40 and 70°C. Immersion times were varied depending on the etch rates.

[0049] Etch rates for metals were determined by determining film thicknesses before and after the etch process by sheet resistivity on a CDE RESMAP Model 273, table-top four point probe, manufactured by Creative Design Engineering, 20565 Alves Drive,
15 Cupertino, CA 95014. Etch rates for the ILD and TEOS were measured by before and after thicknesses on a SCI FilmTeK Ellipsometer.

[0050] Aqueous formulations were shown in Table 1 A.

Table 1A

		92B	92D	92E	92F	92I	92J	92K
	Assay	100	100	100	100	100	100	100
De-ionized water	100%	94.5	89.5	91	91	94	91.5	91.25
sodium persulfate	100%	2.5	2.5	1	1	1	0.5	0.75
ammonium chloride	100%	3	3	0	3	0	3	3
ammonium bisulfate	100%	0	0	3	0	0	0	0
ammonium acetate	100%	0	0	0	0	3	0	0
ammonium bifluoride	10%	0	0	0	0	2	0	0
hydrofluoric acid	5%	0	5	5	5	0	5	5

20

[0051] Semi-aqueous formulations using non-water liquid carriers were shown in Table 1 B.

[0052] All formulations had a pH < 4, except formulation 92I where the pH of the formulation was > 4.

Table 1 B

		94A	94B	94C	94D	94E	94F
	Assay						
De-ionized water	100%	67	47	68	57	67	37
sodium persulfate	100%	1	1				
ammonium persulfate	12%			10	10	10	10
ammonium chloride	100%	3	3	3	3	3	3
hydrofluoric acid	5%	4	4	4			
sulfolane	100%	25	45		30		25
dimethylsulfone	100%			15		20	25

5

[0053] TiN Stripping studies at 40-70°C using the formulations were carried out in the following examples and comparative examples. Blend data in with other examples

Example 1

10

Use of Persulfate salts as non-ambient oxidizers

[0054] The etch data at 45 and 50 °C for formulations shown in Table 1A and 1B were shown in Table 2.

15

[0055] Formulation 92A served as a comparative example in which hydrogen peroxide was used as the oxidant. The formulation contained 0.5% hydrogen peroxide as a non-ambient oxidant. This formulation was buffered to pH ~ 4 with 3 wt % ammonium chloride. Minimal TiN etching was observed from formulation 92A, while significant etching of tungsten was observed.

20

[0056] Formulation 92B served as another comparative example in which the formulation contained non-ambient oxidizer (i.e. persulfate), but no acidic fluoride (i.e. trace bifluoride). The result from 92B has shown low TiN etch rates.

[0057] Formulation 92I also served as a comparative example where the pH of the formulation was > 4. Formulation 92I offered a minimal TiN etch rate, rather a relative high W etch rate.

Table 2 Etch Data for Persulfate formulations

	PVD TiN	W	TiN/W ratio	low k	AlN	PVD TiN	W	TiN/W ratio	low k	AlN
	Etch Rates (A/min) at 45 C					Etch Rates (A/min) at 50 C				
92A						3	100	0.03	< 1	ND
92B						2	6	0.33	< 1	ND
92D						130	20	6.50	3	ND
92E						174	10	17.40	4	ND
92F	101	17	5.94	<1	>30	185	18	10.28	1	ND
92I						1	63	0.02	< 1	ND
92J	98	8	12.25	< 1	>60					
92K	98	13	7.54	<1	>60					
94A	73	18	4.06	< 1	11	80	13	6.15	<1	34
94B	72	23	3.13	<1	15	80	18	4.44	<1	40
94C	84	15	5.60	< 1	7	102	12	8.50	<1	33
94D	60	6	10.00	<1	1	79	12	6.58	<1	20
94E	60	10	6.00	<1	>30	101	13	7.77	<1	>33
94F						80	18	4.44	<1	>43

*ND – Not determined

*Low k- patterned PEDMs 2.2

5

[0058] The data from aqueous formulations 92D, E and F has shown that formulations of this invention containing non-ambient oxidizer (i.e. persulfate), and acidic fluoride (i.e. trace bifluoride) at a pH < 4 were able to offer high TiN etch rates, while provided excellent compatibility towards W and low k dielectric materials. The formulations offered good selectivity of TiN vs W (up to 17) and TiN vs low k dielectric materials (up to >100).

10

[0059] For semi- aqueous formulations with the addition of non-water liquid carriers such as sulfolane (a polar aprotic solvent) or dimethyl sulfone, the data in Table 2 showed that the semi- aqueous formulations containing non-ambient oxidizer (i.e. persulfate) with or without an acidic fluoride (i.e. trace bifluoride) at a pH < 4 were also able to offer high TiN etch rates while provided excellent compatibility towards W and low k dielectric materials. The formulations offered good selectivity of TiN vs W (up to 10) and TiN vs low k dielectric materials (up to >100).

15

[0060] Furthermore, the data in Table 2 also showed that semi-aqueous formulations containing acidic fluoride greatly reduced the aluminum nitride (AlN) etch rate, while maintaining good TiN vs W, and/or TiN vs low k dielectric etch selectivity at temperature < 50°C. The formulations showed protection for the AlN layer.

20

[0061] Semi-aqueous formulation containing a polar aprotic solvent sulfolane as the only non-water liquid carrier in the absence of acidic fluoride (94D) greatly reduced the aluminum nitride (AlN) etch rate, while maintaining good TiN vs W, and/or TiN vs low k dielectric etch selectivity. The formulations showed protection for the AlN layer.

25

[0062] The formulations of present invention have demonstrated their effectiveness for the removal of the TiN hard mask, and their good compatibility towards W, aluminum nitride (AlN), and low k dielectric materials.

5 **[0063]** The semi-aqueous formulations of present invention are extremely useful for systems where compatibility toward aluminum nitride or aluminum oxide is desired.

10 **[0064]** The foregoing examples and description of the preferred embodiments should be taken as illustrating, rather than as limiting the present invention as defined by the claims. As will be readily appreciated, numerous variations and combinations of the features set forth above can be utilized without departing from the present invention as set forth in the claims. Such variations were not regarded as a departure from the spirit and scope of the invention, and all such variations were intended to be included within the scope of the following claims.

15

CLAIMS

1. A composition for selectively removing titanium nitride (TiN or TiN_xO_y; where x = 0 to 1.3 and y = 0 to 2) from a semiconductor device comprising titanium nitride and a second material; the composition comprising:

an amine salt buffer selected from the group consisting of ammonium chloride and ammonium bisulfate;

sodium persulfate;

hydrofluoric acid;

and

liquid carrier;
wherein

the composition comprises no hydrogen peroxide;

the composition has a pH < 4;

the second material is selected from the group consisting of Cu, W, aluminum nitride (AlN_x with x=0.5 to 1), aluminum oxide (AlO_x with x=1 to 1.5), low-k dielectric material, and combinations thereof; and

the composition offers a removal selectivity of TiN or TiN_xO_y vs. the second material > 1:1.
2. The composition of Claim 1, wherein the amine salt buffer is present in the range of 0.5 to 10 wt%.
3. The composition of Claim 1, wherein the sodium persulfate is present in the range of 0.2 to 3 wt%.
4. The composition of Claim 1, wherein the liquid carrier is water; and the amount of hydrofluoric acid is < 4000ppm.
5. The composition of Claim 1, wherein the composition is a semi-aqueous composition having liquid carrier comprising water and dimethyl sulfone.

6. The composition of Claim 1 further comprising at least one selected from the group consisting of
a weakly coordinating anion is present in the range of 1 to 10 wt% and is selected from the group consisting of:
p-toluenesulfonate ($C_7H_8SO_3^-$), sulfate (SO_4^{2-}), nitrate (NO_3^-), triflate ($CF_3SO_3^-$),
perfluorosulfonates ($R_fSO_3^-$; where R_f is a perfluoroalkyl group from C1 to C4),
perfluorosulfonimides; $((R_f)_2NSO_2^-$; where R_f is a perfluoroalkyl group from C1 to C4),
hexafluorosilicate (SiF_6^{2-}), hexafluorotitanate (TiF_6^{2-}), tetrafluoroborate (BF_4^-),
hexafluorophosphate (PF_6^-), hexafluoroantimonate (SbF_6^-),
perfluoroalkylaluminates ($(R_fO)_4Al^-$, R_f is a perfluoroalkyl group), and combinations thereof; and
a corrosion inhibitor in the range of < 2000 ppm selected from the group consisting of benzotriazole or substituted benzotriazole, polyethylenimine, catechol, cysteine and cystine derivative, glycine, thiourea and thiobiuret, siloxane, aluminum chloride, aluminum fluoride, imidazole, triazole, boric acid, and combinations thereof.
7. The composition of Claim 1, wherein the pH of the composition is < 3; the composition offers a removal selectivity of TiN or $TiNxOy$ vs. the second material > 5:1.
8. A system for selectively removing titanium nitride (TiN or $TiNxOy$, where $x = 0$ to 1.3 and $y = 0$ to 2) from a surface of a microelectronic device, comprising:
the semiconductor device comprising TiN or $TiNxOy$ and a second material,
a composition for selectively removing the TiN or $TiNxOy$ from the semiconductor device according to claim 1, 5, or 6.
9. The system of Claim 8, wherein the composition is a semi-aqueous composition having liquid carrier comprising water and dimethyl sulfone.
10. A process of selectively removing titanium nitride (TiN or $TiNxOy$, where $x = 0$ to 1.3 and $y = 0$ to 2) comprising:
providing a semiconductor device comprising TiN or $TiNxOy$ and a second material;
contacting the semiconductor device with a composition according to either claim 1, 5, or 6

wherein

the second material is selected from the group consisting of Cu, W, aluminum nitride (AlN_x with $x=0.5$ to 1), aluminum oxide (AlO_x with $x=1$ to 1.5), low-k dielectric material, and combinations thereof; and

TiN or TiN_xO_y is in direct contact with the composition; and removal selectivity of TiN or TiN_xO_y vs. the second material is $> 1:1$.

11. The process of Claim 10, wherein the liquid carrier in the composition is water; and the hydrofluoric acid is present in an amount $< 4000\text{ppm}$.
12. The process of Claim 10, wherein the composition is a semi-aqueous composition having liquid carrier comprising water and dimethyl sulfone.