

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 27/32, B65B 53/00		A1	(11) International Publication Number: WO 98/38041
			(43) International Publication Date: 3 September 1998 (03.09.98)
(21) International Application Number: PCT/US98/03576		(81) Designated States: AU, BR, CA, CN, ID, JP, KR, <u>SG</u> , VN, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 24 February 1998 (24.02.98)			
(30) Priority Data: 08/806,428 26 February 1997 (26.02.97) US		Published With international search report.	
(71) Applicant: MOBIL OIL CORPORATION [US/US]; 3225 Gallows Road, Fairfax, VA 22037 (US).			
(72) Inventor: WILLIAMS, David, Randall; 82 Grand View Drive, Fairport, NY 14450 (US).			
(74) Agents: CUOMO, Lori, F. et al.; Mobil Oil Corporation, 3225 Gallows Road, Fairfax, VA 22037 (US).			
(54) Title: UNIAXIALLY SHRINKABLE BIAXIALLY ORIENTED POLYPROPYLENE FILM WITH HDPE SKIN			
(57) Abstract			
A uniaxially heat-shrinkable, biaxially oriented, multilayer film having a polypropylene-containing core layer comprising at least 70 wt.% of said multilayer film and at least one polyolefin-containing skin layer adjacent said core layer is prepared by biaxially orienting a coextrudate and thereafter orienting said coextrudate by stretching 10 to 40 % in the machine direction. The core layer contains isotactic polypropylene and a modifier which reduces the crystallinity of the polypropylene by increasing chain imperfections or reducing isotacticity of the polypropylene-containing core. Such modifiers can be selected from the group consisting of atactic polypropylene, syndiotactic polypropylene, ethylene-propylene copolymer, propylene-butene-1 copolymer, ethylene-propylene-butene-1 terpolymer, and linear low density polyethylene. The skin layer can be high density polyethylene on both sides or high density polyethylene on one side and isotactic polypropylene on the other side.			
9903827-5 11 AUG 1999			