

ABSTRACT OF THE DISCLOSURE

A resin composition comprising an inorganic filler in the form of fiber or plate compounded in a liquid crystal polyester resin composition obtained by compounding 10 to 150 parts by weight of a liquid crystal polyester (B) into 100 parts by weight of a liquid crystal polyester (A), wherein the liquid crystal polyester (A) has a flow temperature of from 310 to 400°C, the liquid crystal polyester (B) has a flow temperature of from 270 to 370°C, the difference between the flow temperature of the liquid crystal polyester (A) and the flow temperature of the liquid crystal polyester (B) is from 10 to 60°C, and the content of the inorganic filler is from 15 to 180 parts by weight based on 100 parts by weight of the total amount of the liquid crystal polyester (A) and the liquid crystal polyester (B).

The resin composition is excellent in thin-wall flowability and can provide a molded article having excellent heat resistance and low warpage, and can provide a super thin-wall molded article.

(No suitable figure)

