CLAIMS

1. A resin composition comprising

(i) 100 parts by weight of a resin (component A),

(ii) plate-like magnesium hydroxide having a crystal thickness (y) of 0.2 μm or less, a crystal width (x) of 0.5 to 10 μm, and an aspect ratio (x/y) of 20 to 100 (component B), and

(iii) needle-like basic magnesium sulfate (component C), having a width (w) of 0.5 to 1 μm, a length (L) of 20 to 100 μm and an aspect ratio of 20 or more, wherein

the total content of the components B and C is 1 to 100 parts by weight based on 100 parts by weight of the resin, and the weight ratio of the component B to the component C is 0.1 to 0.9:0.9 to 0.1.

2. The resin composition according to claim 1, wherein the weight ratio of the component B to the component C is 0.2 to 0.6:0.8 to 0.4.

3. The resin composition according to claim 1, wherein the component B has a crystal thickness (y) of 0.2 μm or less and an aspect ratio of 30 or more.

4. The resin composition according to claim 1, wherein the component B has a crystal thickness (y) of 0.1 μm or less and an aspect ratio of 40 or more.

~~5. The resin composition according to claim 1, wherein the component C has a width (w) of 0.5 to 1 μm, a length (L) of 20 to 50 μm and an aspect ratio of 20 or more.~~

~~6~~5. The resin composition according to claim 1, wherein the component B and the component C are surface treated with an anionic surfactant.