

Description

The invention relates to a magnetic transducing head comprising a magnetic core having two core limbs formed from a ferrite, which core limbs have two core faces facing each other and at least one of which is provided with a cladding consisting of a layer of an Fe-Si-Al-based alloy, a non-magnetizable transducing gap extending between the core faces and a winding aperture with an electric coil passing therethrough and being provided around a core limb.

A magnetic transducing head of this type is known and described, inter alia in the publication IEEE 1984, September, Volume May 20, No. 5, pages 872-874, Analysis Of Metal In Gap Heads, by J.J.M. Ruigrok.

The transducing heads which are used in present-day video recorders generally have an Mn-Zn ferrite core. Mn-Zn ferrite has a saturation magnetization of approximately 0.5 Tesla at room temperature, which is sufficient to comply with the requirements imposed by the registration on conventional video tapes, such as CrO₂-tapes with a coercive force H_c of approximately 56 kA/m. If, however, magnetic tapes having a higher coercive force such as Fe-tapes which have a H_c of roughly 80-160 kA/m are used for improving the quality of the video registration, such magnetic tapes can no longer be written satisfactorily. The magnetic fields generated by the transducing head at the area of the transducing gap for writing information on the magnetic tape are in fact limited by the relatively low saturation magnetization of the ferrite in the transducing head core. The strength of the writing field of the transducing head is therefore insufficiently high to ensure optimum writing of magnetic tapes with a high coercive force.

In the known transducing head defined in the opening paragraph the above-described problem is tackled by sputtering a layer of Fe-Si-Al on at least one of the core faces present on either side of the transducing gap. In fact, the Fe-Si-Al alloy sputtered on the core faces enhance the recording and reproducing characteristics of the transducing head. In addition Fe-Si-Al is a wear-resistant material so that hollow-out of the transducing head owing to moving a magnetic tape along the tape contact face of the transducing head can be mitigated.

A drawback of the known transducing head is that pseudo-gaps or side gaps are formed between the ferrite core limbs and the Fe-Si-Al layers so that constructive and destructive interferences causing troublesome oscillations in the frequency characteristic of the known transducing head may occur at the area of the interfaces between the core limbs and the Fe-Si-Al layers.

To reduce the detrimental effect of the occurrence of pseudo-gaps in magnetic heads with a ferrite core it has been proposed in the publication Digests of Intermag 85, April 29-May 2, USA, p. DA-1, A tilted sendust-sputtered ferrite video head, by T. Kobayashi, c.s. to position the faces in which the pseudo-gaps occur in such a way that the pseudo-gaps do not run parallel to the transducing gap, but constitute an angle with this gap.

A magnetic head in which this measure is used is indeed less subject to pseudo-gap effects, but a magnetic head of this type is rather complicated in its construction and difficult to manufacture from a technological point of view.

It is an object of the invention to improve the transducing head defined in the opening paragraph in such a way that the problem of the occurring pseudo-gaps is solved in a technologically simple manner.

To this end the transducing head according to the invention is characterized in that the cladding provided on the core face also comprises a layer of an Ni-Fe-based alloy, the layer of an Ni-Fe-based alloy being provided on the core face and the layer of an Fe-Si-Al-based alloy being provided on the layer of an Ni-Fe-based alloy.

In the transducing head according to the invention no pseudo-gaps are produced at the transition of the ferrite core limb to the layer of an Ni-Fe-based alloy, nor at the transition of the layer of an Ni-Fe-based alloy to the layer of an Fe-Si-Al-based alloy, which is also clearly evident from the favourable frequency characteristics of the transducing head in which perturbations caused by possible side gaps are not present.

The transducing head according to the invention can be manufactured in a simple manner in accordance with known techniques in which the different layers are provided one after the other, for example by means of sputtering.

A main embodiment of the transducing head according to the invention, which has very good properties for writing information on high coercive registration media and which can be manufactured in an economically attractive way is characterized in that the said cladding is provided on both core faces, whilst parallel gap boundary faces of equal width for defining the gapwidth of the transducing gap are formed, central core face parts parallel to the gap boundary faces extending between the core limbs and the claddings thereof, and oblique core face parts constituting an angle with the central core face parts

extending on either side thereof, the said central core face parts having a width which is larger than half the width of the gap boundary faces.

In the transducing head according to the invention the cladding may be considerably thinner than in the known magnetic heads as described, for example in European Patent Application 0,125,891. This has the advantage that the cladding can be provided without any complications on the core faces in accordance with known methods such as sputtering.

An embodiment which is favourable from a manufacturing-technical point of view is characterized in that the width of the central core face parts is at least substantially equal to the width of the gap boundary faces.

A further favourable embodiment is characterized in that on either side of the transducing gap between the core limbs and the claddings thereof there extend further core face parts contiguous to the oblique core faces and running parallel to the central core faces. This embodiment, which can be manufactured in a simple manner, is particularly interesting because after sputtering the transducing head does not need to be provided with recesses on either side of the transducing gap for the purpose of locally constricting the tape contact face.

Particularly favourable results can be achieved when the above-mentioned embodiments are also characterized in that the thickness of the cladding is defined by the relation:

$$D_1 \geq 1/3 \cdot W_1 (1 - M_f/M_b) ,$$

in which

D_1 is the sum of the thicknesses of the layer of an Fe-Si-Al-based alloy and the layer of an Ni-Fe-based alloy, W_1 is the gapwidth, M_b is the weighted saturation magnetization of the materials of the said layers and M_f is the saturation magnetization of the ferrite. The weighted saturation magnetization is herein understood to mean:

$$M_b = (t_s \cdot M_s + t_p \cdot M_p) / D_1 ,$$

in which

t_s is the thickness of the layer of an Fe-Si-Al-based alloy, M_s is the saturation magnetization of this layer, t_p is the thickness of the layer of an Ni-Fe-based alloy and M_p is the saturation magnetization of this layer.

An alternative main embodiment of the transducing head according to the invention is characterized in that the cladding is provided on both core faces, whilst parallel gap boundary faces of equal width for defining the gapwidth of the transducing gap are formed, the core faces parallel to the gap boundary faces extending between the core limbs and the claddings thereof, and the said core faces having a width which is larger than the width of the gap boundary faces, whilst the claddings on either side of the transducing gap have side faces which extend from the gap boundary faces to the said core faces and which constitute an acute angle with the core faces.

A high efficiency and a frequency characteristic in which a side gap effect is hardly noticeable can be achieved with this transducing head according to the invention. The particularly satisfactory measuring results are all the more surprising because the constructive measures used in the transducing head are completely in contrast with the prior art trend as described in the said EP 0,125,891.

In EP 0,125,891 a magnetic head is described whose core is coated on at least one side of the transducing gap with a thick cladding of a magnetic material having a higher saturation magnetization than the ferrite of the core. The cladding is at least substantially provided on two core faces obliquely positioned with respect to the gap boundary face formed by the cladding, which core faces are mutually positioned in such a way that a core face parallel to the gap boundary face is formed between the oblique core faces, which core face has a width which is at most equal to half the width of the transducing gap but which is preferably minimal. In fact, it is asserted in the said European Patent Application that with an increasing width of the central core face there is such a side gap effect (contour effect) at the area of the transition between the core and the cladding that the frequency characteristic of the magnetic head is increasingly disturbed, whereas the side gap effect is hardly disturbing in the case of the smallest possible width of the core face or in the case of a total absence of the core face. However, the side gaps in the known magnetic head still yield magnetic potential losses and consequently signal losses.

The magnetic head described in EP 0,125,891 has thick claddings of the order corresponding to half the gapwidth of the magnetic head or half the trackwidth of the magnetic tape. Thick claddings have the drawback that they are difficult to provide and therefore require a complicated manufacturing technique. Moreover, a very narrow central core face located between the oblique core faces is difficult to realise with the conventional sawing techniques.

An additional advantage of the alternative main embodiment of the transducing head according to the invention is the absence of oblique core faces. In fact, the faces on which the claddings are provided need not be profiled, which simplifies the manufacture of the magnetic heads quite considerably. The side faces of the claddings can be formed by means of a laser technique known per se during which treatment the gap is also provided at the desired width.

The angle constituted by the said side faces with the core faces will preferably be approximately 45° , but good results have also been achieved with angles of between 20° and 70° .

The transducing head defined hereinbefore as an alternative main embodiment is preferably also characterized in that the thickness of the cladding is defined by the relation:

$$D_2 \geq \frac{1}{2} \cdot \left(\frac{M_b}{M_f \cdot \sin \alpha} \right) - 1 \cdot W_2 \cdot \tan \alpha, \text{ in}$$

which

D_2 is the sum of the thicknesses of the layer of an Fe-Si-Al-based alloy and the layer of an Ni-Fe-based alloy, W_2 is the gapwidth, M_b is the weighted saturation magnetization of the materials of the said layers, M_f is the saturation magnetization of the ferrite and α is the angle between a side face and a core face.

It is to be noted that the thickness of the layer of an Ni-Fe-based alloy is preferably small with respect to the layer of an Fe-Si-Al-based alloy and does not essentially contribute to the thickness of the total cladding. Furthermore it is to be noted that for achieving the envisaged object it is unimportant that the material of one of the two layers of the cladding has a higher permeability than the material of the other layer.

The invention will now be described in greater detail, by way of example, with reference to the accompanying drawings in which

Figure 1 is a diagrammatic perspective elevational view of a first embodiment of the magnetic transducing head according to the invention,

Figure 2 is a similar elevational view of a second embodiment,

Figure 2A shows the frequency characteristic of the second embodiment,

Figure 3 is a plan view on a larger scale of part of the second embodiment,

Figure 4 is a plan view on a larger scale of part of a transducing head in accordance with the second embodiment,

Figure 5 is an elevational view of a third embodiment of the transducing head according to the invention, and

Figure 6 is a plan view on a larger scale of part of the third embodiment.

The magnetic transducing heads shown in the Figures are suitable for writing and reading magnetic tapes having high coercive forces.

The transducing head of Figure 1 has a magnetic core consisting of two core limbs 1 and 3 and accommodating a winding aperture 5. The winding aperture 5 accommodates a portion of a coil 7 wound around one of the core limbs. The core limbs 1 and 3, which are formed from a ferrite, for example monocrystalline Mn-Zn ferrite are fixed together by means of an adhesive layer 9 of a non-magnetic material such as glass or quartz. The core limbs 1 and 3 are provided with contact faces 1A and 3A, respectively, on which a magnetic tape (not shown) is moved in the direction of the arrow A during operation of the transducing head. Near the contact faces 1A and 3A the layer 9 constitutes a non-magnetic transducing gap 11 extending between the core limbs 1 and 3, which gap has a length of, for example approximately $0.3 \mu\text{m}$.

In the embodiments shown the core limbs 1 and 3 each have a completely flat core face 1B and 3B, respectively, facing the gap 11 on which faces a cladding consisting of two layers 13 and 15 is provided. The core faces 1B and 3B on either side of the transducing head are bounded by two recesses 17 which partly extend in the tape contact face constituted by the contact faces 1A and 3A and partly extend as far as the side faces of the transducing head. The layer 13 consists of an Ni-Fe-based alloy, such as $\text{Ni}_{80}\text{Fe}_{20}$, and is provided on the core faces 1B and 3B by means of, for example sputtering or vapour-deposition, whilst the layer 15 consists of an Fe-Si-Al-based alloy such as $\text{Fe}_{85.8}\text{Si}_{9.2}\text{Al}_{5.0}$ and is provided on the said layer 13 by means of sputtering, vapour-deposition or another process.

If the Ni-Fe-based alloy is provided by means of sputtering, a mixture of Ar- N_2 gas may be used during sputtering to increase the hardness of the sputtered alloy. The use of such a gas during sputtering is known per se and has been described, inter alia, in DE 3342533.

It has been found by experiment that favourable results can be achieved with layer thicknesses whose values are between 0.05 and 2.0 μm for layer 13 and between 1 and 10 μm for layer 15. These values are only examples because satisfactory results can also be achieved beyond the limits indicated.

In the embodiment shown the transducing gap, viewed widthwise, is at right angles to the direction of movement of the magnetic tape. Embodiments in which the transducing gap in the direction viewed is not oriented at right angles to the said direction of movement are of course also possible.

The transducing head 201 shown in Figure 2 is suitable for writing and reading magnetic tapes having a high coercive force. The transducing head 201 has a magnetic core consisting of two core limbs 203 and 205, which core is provided with a winding aperture 207 through which a coil 209 is wound. The core limbs 203 and 205, which consist of a mono-crystalline Mn-Zn ferrite, are sealed together by means of a sealing material, such as glass in the regions 211 and 213. In region 211 a transducing gap 215 is thus formed. The core limbs 203 and 205 have a tape contact face 217 along which a magnetic tape (not shown) is moved in the direction of the arrow A1 during operation of the transducing head 201.

The visible parts of the transducing heads shown in Figures 3 and 4 have the same reference numerals as the parts of the transducing head according to Figure 2 corresponding to the said parts.

As is shown in Figures 2, 3 and 4, claddings are provided on the core limbs 203 and 205. The cladding consists of a layer 223 of an Ni-Fe-based alloy and a layer 225 of an Fe-Si-Al-based alloy. The claddings constitute two parallel gap boundary faces 225A and 225B, respectively (see particularly Figures 3 and 4) of equal width. These gap boundary faces 225A and 225B define the gapwidth W1 of the transducing gap 215 which is filled with a non-magnetic material such as glass or quartz. The direction in which the gapwidth is defined is oriented, at least in these embodiments, at right angles to the direction of movement of the magnetic tape. Embodiments in which the said two directions are not at right angles to each other or of course also possible.

According to the invention central core face parts 203A and 205A are present between the core limbs 203 and 205 on the one hand and the claddings on the other hand, and on either side of these core faces and contiguous thereto there are provided oblique core face parts 203B and 205B constituting an angle with the central core face parts. The central core face parts 203A and 205A are almost equal to the width of the gap boundary faces. In the embodiments shown in Figures 2, 3 and 4 further core face parts 203C and 205C contiguous to the oblique core face parts are provided, which extend parallel to the central core-face parts 203A and 205A. For the supply of flux to the gap 215 at the tape contact face 217 it is favourable to cover not only the core face parts 203A, B, C and 205A, B, C at the area of the transducing gap with a layer of a magnetic material of the type described, but also the other face parts of the magnetic core adjacent the said core face parts and facing the transducing gap 215, so that the core limbs 203 and 205 are provided with a cladding on their sides facing the gap 215 over the entire height h. The claddings 223 and 225 may be provided during the manufacture of the transducing heads on the core limbs 203 and 205 by means of, for example sputtering, electro-deposition or vapour-deposition after the said core faces have been formed by means of, for example sawing. After the claddings 223 and 225 are provided, the core limbs 203 and 205 can be sealed together.

The magnetic head shown in Figure 4 has undergone an extra processing treatment in which for the purpose of constriction of the tape contact face 217 in the neighbourhood of the transducing gap 215 two recesses 219 have been provided by means of, for example a laser.

For determining the thickness D1 of the cladding use can be made of the relation already given in the introduction to the description. In the embodiment according to Figure 1 the thickness D1 is 3 μm . The gapwidth W1 is preferably smaller than 18 μm .

Figure 2A shows the frequency characteristic with the output signal V as a function of the measuring frequency f of a transducing head of the type according to Figure 2 whose cladding consists of a layer of an Ni-Fe-based alloy having a thickness of 0.5 μm and a layer of an Fe-Si-Al-based alloy having a thickness of 2.5 μm . It can clearly be seen that oscillations hardly occur in the frequency characteristic.

The transducing head 101 according to the invention shown in Figures 5 and 6 has principally the same properties as the transducing heads already described. The transducing head 101 has two core limbs 103 and 105 of ferrite which together form a magnetic core with a tape contact face 117 along which an information carrier can be moved in the direction shown by arrow A2 for magnetic co-operation with the transducing head 101. An electric coil 109 passing through a winding aperture 107 is provided around the core limb 105. The core limbs 103 and 105 which are connected together by means of a sealing layer 113 of, for example, glass each have a core face 103A and 105A, respectively. The core faces 103A and 105A face each other and run parallel to each other. A cladding composed of a layer 123 and a layer 125 is provided on each of the two core faces 103A and 105A. The layers 123 and 125 consist of an Ni-Fe-based alloy and an Fe-Si-Al-based alloy, respectively. The claddings 125 constitute a gap boundary face 125A and

125B, respectively of a predetermined width, with the direction in which the width is defined being at right angles to the direction denoted by the arrow A2 in this embodiment. The overall gap boundary faces bound a transducing gap 115 having a gapwidth W2. The transducing gap is formed by means of a layer of a non-magnetizable material such as quartz, which may also serve to seal the claddings 125 together.

5 In front of and behind the transducing gap 115 the two core limbs 103 and 105, respectively, are wedge-shaped, as viewed in the direction of the arrow A2, it being essential according to the invention that this wedge is also present in the claddings. This means that the claddings 123 and 125 have side faces 123B1 and 125B1, respectively, which constitute acute angles α with the core faces 103A and 105A, respectively. The side faces 123B1 and 125B1 of the claddings 123 and 125 as well as the further wedge
10 shape of the core limbs may be realized, for example by means of known laser techniques. In this example angle α is equal to 45° . The sum, D2, of the thicknesses of the claddings 123 and 125 can be determined by means of the relation already mentioned in the introduction to the description.

In the latter embodiment in which the gapwidth W2 is 20 μm and the said angle α is 45° , 5 μm is a favourable value for the thickness D2.

15

Claims

- 20 1. A magnetic transducing head comprising
 - a magnetic core having two core limbs (1, 3; 203, 205; 103, 105) formed from a ferrite, which core limbs have two core faces (1B, 3B; 203 A,B,C, 205 A,B,C; 103 A, 105A) facing each other and at least one of which is provided with a cladding consisting of a layer of an Fe-Si-Al-based alloy (15; 225; 125),
 - 25 - a non-magnetizable transducing gap (11; 215; 115) extending between the core faces and
 - a winding aperture (5; 207; 107) with an electric coil (7; 209; 109) passing therethrough and being provided around a core limb, characterized in that the cladding provided on the core face also comprises of a layer of an Ni-Fe-based alloy (13; 223; 123), the layer of an Ni-Fe-based alloy being provided on the core face and the layer of an Fe-Si-Al-based alloy being provided on the layer of an Ni-Fe-based alloy.
 - 30
2. A magnetic transducing head as claimed in Claim 1, characterized in that the said cladding is provided on both core faces, whilst parallel gap boundary faces (225A, 225B) of equal width for defining the gapwidth of the transducing head are formed, central core face parts (203A, 205A) parallel to the gap
35 boundary faces extending between the core limbs (203, 205) and the claddings thereof, and oblique core face parts (203B, 205B) constituting an angle with the central core face parts extending on either side thereof, the said central core face parts having a width which is larger than half the width of the gap boundary faces.
- 40 3. A magnetic head as claimed in Claim 2, characterized in that the width of the central core face parts (203A, 205A) is at least substantially equal to the width of the gap boundary faces (225A, 225B).
4. A magnetic head as claimed in Claim 2 or 3, characterized in that further core face parts (203C, 205C) extend on either side of the transducing gap (215) between the core limbs (203, 205) and the claddings
45 thereof, which core face parts are contiguous to the oblique core face parts (203B, 205B) and are parallel to the central core faces (203A, 205A).
5. A magnetic head as claimed in Claim 2, 3 or 4, characterized in that the thickness of the cladding is defined by the relation:

50 $D_1 \geq 1/3 \cdot W_1 (1 - M_r/M_b)$,

in which

D₁ is the sum of the thicknesses of the layer of an Fe-Si-Al-based alloy and the layer of an Ni-Fe-based
55 alloy, W₁ is the gapwidth, M_b is the weighted saturation magnetization of the ferrite.
6. A magnetic transducing head as claimed in Claim 1, characterized in that the cladding is provided on both core faces (103A, 105A), whilst parallel gap boundary faces (125A, 125B) of equal width for



125B, respectively of a predetermined width, with the direction in which the width is defined being at right angles to the direction denoted by the arrow A2 in this embodiment. The overall gap boundary faces bound a transducing gap 115 having a gapwidth W2. The transducing gap is formed by means of a layer of a non-magnetizable material such as quartz, which may also serve to seal the claddings 125 together.

In front of and behind the transducing gap 115 the two core limbs 103 and 105, respectively, are wedge-shaped, as viewed in the direction of the arrow A2, it being essential according to the invention that this wedge is also present in the claddings. This means that the claddings 123 and 125 have side faces 123B1 and 125B1, respectively, which constitute acute angles α with the core faces 103A and 105A, respectively. The side faces 123B1 and 125B1 of the claddings 123 and 125 as well as the further wedge shape of the core limbs may be realized, for example by means of known laser techniques. In this example angle α is equal to 45° . The sum, D2, of the thicknesses of the claddings 123 and 125 can be determined by means of the relation already mentioned in the introduction to the description.

In the latter embodiment in which the gapwidth W2 is $20\text{ }\mu\text{m}$ and the said angle α is 45° , $5\text{ }\mu\text{m}$ is a favourable value for the thickness D2.

Claims

1. A magnetic transducing head comprising

- a magnetic core having two core limbs (1, 3; 203, 205; 103, 105) formed from a ferrite, which core limbs have two core faces (1B, 3B; 203 A,B,C, 205 A,B,C; 103 A, 105A) facing each other and at least one of which is provided with a cladding consisting of a layer of an Fe-Si-Al-based alloy (15; 225; 125),
- a non-magnetizable transducing gap (11; 215; 115) extending between the core faces and
- a winding aperture (5; 207; 107) with an electric coil (7; 209; 109) passing therethrough and being provided around a core limb, characterized in that the cladding provided on the core face also comprises of a layer of an Ni-Fe-based alloy (13; 223; 123), the layer of an Ni-Fe-based alloy being provided on the core face and the layer of an Fe-Si-Al-based alloy being provided on the layer of an Ni-Fe-based alloy.

2. A magnetic transducing head as claimed in Claim 1, characterized in that the said cladding is provided on both core faces, whilst parallel gap boundary faces (225A, 225B) of equal width for defining the gapwidth of the transducing head are formed, central core face parts (203A, 205A) parallel to the gap boundary faces extending between the core limbs (203, 205) and the claddings thereof, and oblique core face parts (203B, 205B) constituting an angle with the central core face parts extending on either side thereof, the said central core face parts having a width which is larger than half the width of the gap boundary faces.

3. A magnetic head as claimed in Claim 2, characterized in that the width of the central core face parts (203A, 205A) is at least substantially equal to the width of the gap boundary faces (225A, 225B).

4. A magnetic head as claimed in Claim 2 or 3, characterized in that further core face parts (203C, 205C) extend on either side of the transducing gap (215) between the core limbs (203, 205) and the claddings thereof, which core face parts are contiguous to the oblique core face parts (203B, 205B) and are parallel to the central core faces (203A, 205A).

5. A magnetic head as claimed in Claim 2, 3 or 4, characterized in that the thickness of the cladding is defined by the relation:

$$D_1 \geq 1.3 \cdot W_1 (1 - M_r M_b),$$

in which

D₁ is the sum of the thicknesses of the layer of an Fe-Si-Al-based alloy and the layer of an Ni-Fe-based alloy, W₁ is the gapwidth, M_b is the weighted saturation magnetization of the ferrite.

6. A magnetic transducing head as claimed in Claim 1, characterized in that the cladding is provided on both core faces (103A, 105A), whilst parallel gap boundary faces (125A, 125B) of equal width for



defining the gapwidth of the transducing gap (115) are formed, the core faces parallel to the gap boundary faces extending between the core limbs (103, 105) and the claddings thereof, and the said core faces having a width which is larger than the width of the gap boundary faces, whilst the claddings on either side of the transducing gap have side faces (123B₁, 125B₁) which extend from the gap boundary faces to the said core faces and which constitute an acute angle with the core faces.

7. A magnetic head as claimed in Claim 6, characterized in that the said angle has a value of between 20° and 70°.

8. A magnetic head as claimed in Claim 6 or 7, characterized in that the thickness of the cladding is defined by the relation:

$$D_2 \geq 1/2 \cdot ((M_b / (M_i \sin \alpha))^{1/2} - 1) W_2 \tan \alpha,$$

in which

D₂ is the sum of the thicknesses of the layer of an Fe-Si-Al-based alloy and the layer of an Ni-Fe-based alloy, W₂ is the gapwidth, M_b is the weighted saturation magnetization of the materials of the said layers, M_i is the saturation magnetization of the ferrite and α is the angle between a side face and a core face.

Revendications

1. Tête magnétique comportant

- un noyau magnétique ayant deux branches de noyau (1, 3; 203, 205; 103, 105) formées d'une ferrite, branches de noyau qui ont deux faces de noyau (1B, 3B; 203 A,B,C, 205 A,B,C; 103A, 105A) opposées dont au moins une est prévue d'un revêtement se composant d'une couche d'un alliage à base de Fe-Si-Al (15; 225; 125),
- un entrefer de transmission non magnétisable (11; 215; 115) s'étendant entre les faces de noyau et
- un espace d'enroulement (5; 207; 107) traversé par une bobine électrique (7; 209; 109) prévue autour d'une branche de noyau, caractérisée en ce que le revêtement prévu sur la face de noyau comporte en outre une couche d'un alliage à base de Ni-Fe (13; 223; 123), la couche d'un alliage à base de Ni-Fe étant prévue sur la face de noyau et la couche d'un alliage à base de Fe-Si-Al étant prévue sur la couche d'un alliage à base de Ni-Fe.

2. Tête magnétique conforme à la revendication 1, caractérisée en ce que ledit revêtement est prévu sur les deux faces de noyau, et en ce que sont formées des faces de limitation d'entrefer parallèles (225A, 225B) de largeur égale pour définir la largeur de l'entrefer de la tête magnétique, des parties de face de noyau centrales (203A, 205A) parallèles aux faces de limitation d'entrefer s'étendant entre les branches de noyau (203, 205) et leurs revêtements, et des parties de face de noyau obliques (203B, 205B) formant un angle avec les parties de face de noyau centrales s'étendant des deux côtés de celles-ci, lesdites parties de face de noyau centrales ayant une largeur supérieure à la moitié de la largeur des faces de limitation d'entrefer.

3. Tête magnétique conforme à la revendication 2, caractérisée en ce que la largeur des parties de face de noyau centrales (203A, 203B) est au moins sensiblement égale à la largeur des faces de limitation d'entrefer (225A, 225B).

4. Tête magnétique conforme à la revendication 2 ou 3, caractérisée en ce que, des deux côtés de l'entrefer de transmission (215), entre les branches de noyau (203, 205) et leurs revêtements, s'étendent d'autres parties de face de noyau (203C, 205C) contiguës aux parties de face de noyau obliques (203B, 205B) et parallèles aux faces de noyau centrales (203A, 205A).

5. Tête magnétique conforme à la revendication 2, 3 ou 4, caractérisée en ce que l'épaisseur du revêtement est définie par la relation:



$$D_1 \geq 1/3 \cdot W_1 (1 - M_f / M_b)$$

où

D_1 est la somme de l'épaisseur de la couche d'un alliage à base de Fe-Si-Al et de l'épaisseur de la couche d'un alliage à base de Ni-Fe, W_1 est la largeur de l'entrefer, M_b est la magnétisation de saturation pondérée de la ferrite.

6. Tête magnétique conforme à la revendication 1, caractérisée en ce que le revêtement est prévu sur les deux faces de noyau (103A, 105A), et en ce que sont formées des faces de limitation d'entrefer parallèles (125A, 125B), de largeur égale déterminant la largeur de l'entrefer de transmission 115, les faces de noyau parallèles aux faces de limitation d'entrefer s'étendant entre les branches de noyau (103, 105) et leurs revêtements, lesdites faces de noyau ayant une largeur supérieure à la largeur des faces de limitation d'entrefer, tandis que les revêtements prévus des deux côtés de l'entrefer de transmission présentent des faces latérales (123B₁, 125B₁) s'étendant à partir des faces de limitation d'entrefer jusqu'auxdites faces de noyau et formant un angle aigu avec les faces de noyau.
7. Tête magnétique conforme à la revendication 6, caractérisée en ce que ledit angle a une valeur se situant entre 20° et 70°.
8. Tête magnétique conforme à la revendication 6 ou 7, caractérisée en ce que l'épaisseur du revêtement est définie par la relation:

$$D_2 \geq 1/2 \cdot ((M_b / (M_f \cdot \sin \alpha))^2 - 1) W_2 \cdot \tan \alpha,$$

où

D_2 est la somme de l'épaisseur de la couche d'un alliage à base de Fe-Si-Al et l'épaisseur de la couche d'un alliage à base de Ni-Fe, W_2 est la largeur de l'entrefer, M_b est la magnétisation de saturation pondérée des matériaux desdites couches, M_f est la magnétisation de saturation de la ferrite et α est l'angle faite par une face latérale et une face de noyau.

Ansprüche

1. Magnetkopf mit:

- einem Magnetkern mit zwei aus einem Ferrit gebildeten Kernteilen (1, 3; 203, 205; 103, 105) mit zwei einander zugewandten Kernflächen (1B, 3B; 203 A,B,C, 205 A,B,C; 103 A, 105 A), von denen mindestens eine mit einer Verkleidung aus einer Schicht einer Fe-Si-Al-Legierung (15; 225; 125) versehen ist,
- einem nicht-magnetisierbaren Übertragungsspalt (11; 215; 115), der sich zwischen den Kernflächen erstreckt und
- einer Spulenkommer (5; 207; 107) mit einer hindurchgehenden und um einen Kernteil vorgesehenen elektrischen Spule (7; 209; 109), **dadurch gekennzeichnet**, daß die auf der Kernfläche vorgesehene Verkleidung ebenfalls eine Schicht aus einer Ni-Fe-Legierung (13; 223; 123) aufweist, wobei die Ni-Fe-Legierungsschicht auf der Kernfläche und die Fe-Si-Al-Legierungsschicht auf der Ni-Fe-Legierungsschicht angebracht ist.

2. Magnetkopf nach Anspruch 1, **dadurch gekennzeichnet**, daß die genannte Verkleidung auf beiden Kernflächen vorgesehen ist, während parallele Spaltbegrenzungsflächen (225A, 225B) gleicher Breite zum Definieren der Spaltbreite des Magnetkopfes gebildet sind, wobei zentrale Kernflächenteile (203A, 205A) sich parallel zu den Spaltbegrenzungsflächen erstrecken, und zwar zwischen den Kernteilen (203, 205) und der Verkleidung derselben, und wobei schräge Kernflächenteile (203B, 205B) mit den sich auf beiden Seiten erstreckenden zentralen Kernflächenteilen einen Winkel einschließen, wobei die zentralen Kernflächenteile eine Breite aufweisen, die größer ist als die Hälfte der Breite der Spaltbegrenzungsflächen.

3. Magnetkopf nach Anspruch 2, **dadurch gekennzeichnet**, daß die Breite der zentralen Kernflächenteile (203A, 205A) der Breite der Spaltbegrenzungsflächen (225A, 225B) mindestens im wesentlichen entspricht.



4. Magnetkopf nach Anspruch 2 oder 3, dadurch gekennzeichnet, daß weitere Kernflächenteile (203C, 205C) sich auf beiden Seiten des Übertragungsspalt (215) zwischen den Kernteilen (203, 205) und der Verkleidung derselben erstrecken, wobei diese Kernflächenteile an den schrägen Kernflächenteilen (203B, 205B) anliegen und sich parallel zu den zentralen Kernflächen (203A, 205A) erstrecken.

5. Magnetkopf nach Anspruch 2, 3 oder 4, dadurch gekennzeichnet, daß die Dicke der Verkleidung durch die nachfolgende Beziehung definiert ist:

$$D_1 \geq 1/3 \cdot W_1 (1 - M_f/M_b)$$

in der D_1 die Summe der Dicken der Fe-Si-Al-Legierungsschicht und der Ni-Fe-Legierungsschicht ist, W_1 die Spaltbreite ist und M_b die gewichtete Sättigungsmagnetisierung des Ferrits ist.

6. Magnetkopf nach Anspruch 1, dadurch gekennzeichnet, daß die Verkleidung an beiden Kernflächen (103A, 105A) vorgesehen ist, während parallele Spaltbegrenzungsflächen (125A, 125B) gleicher Breite zum Definieren der Spaltbreite des Übertragungsspalt (115) gebildet werden, wobei die Kernflächen sich parallel zu den Spaltbegrenzungsflächen zwischen den Kernteilen (103, 105) und der Verkleidung derselben erstrecken, und eine Breite haben, die größer ist als die der Spaltbegrenzungsflächen, während die Verkleidung auf den beiden Seiten des Übertragungsspalt Seitenflächen (123B₁, 125B₁) aufweist, die sich von den Spaltbegrenzungsflächen bis an die Kernflächen erstrecken und mit den Kernflächen einen scharfen Winkel einschließen.

7. Magnetkopf nach Anspruch 6, dadurch gekennzeichnet, daß der genannte Winkel einen Wert zwischen 20° und 70° aufweist.

8. Magnetkopf nach Anspruch 6 oder 7, dadurch gekennzeichnet, daß die Dicke der Verkleidung durch die nachfolgende Beziehung definiert ist:

$$D_2 \geq 1/2 \cdot ((M_b/(M_f \cdot \sin \alpha))^2 - 1) W_2 \cdot \tan \alpha,$$

in der D_2 die Summe der Dicken der Fe-Si-Al-Legierungsschicht und der Ni-Fe-Legierungsschicht ist, W_2 die Spaltbreite ist, M_b die gewichtete Sättigungsmagnetisierung der Materialien der genannten Schichten ist, M_f die Sättigungsmagnetisierung des Ferrits und α der Winkel zwischen einer Seitenfläche und einer Kernfläche ist.