Claims:

1. A method of processing a substrate, comprising:

exposing the substrate positioned in a processing volume of a processing chamber to a hydrocarbon-containing gas mixture;

exposing the substrate to a boron-containing gas mixture, wherein the hydrocarbon-containing gas mixture and the boron-containing gas mixture are flowed into the processing volume at a precursor ratio of (boron-containing gas mixture/((boron-containing gas mixture)+hydrocarbon-containing gas mixture) of about 0.38 to about 0.85; and

generating a radio frequency (RF) plasma in the processing volume to deposit a boron-carbon film on the substrate, wherein the boron-carbon film has about 55 atomic percentage to about 95 atomic percentage of boron.

2. The method of claim 1, wherein the hydrocarbon-containing gas mixture comprises an alkane.

3. The method of claim 2, wherein the hydrocarbon-containing gas mixture comprises propylene (C_3H_6).

4. The method of claim 1, wherein the boron-containing gas mixture comprises about 9 weight percentage (wt. %) diborane (B_2H_6) diluted in hydrogen gas (H_2).

5. The method of claim 1, wherein a ratio of the hydrocarbon-containing gas mixture to the boron-containing gas mixture is in a range between about 0.7:1 and about 0.12:1.

6. The method of claim 1, wherein the generating the RF plasma comprises applying a high frequency of about 12 MHz to about 14 MHz and a low frequency of about 0.1 kHz to about 1 kHz.

7. The method of claim 6, wherein the applying a high and low frequency is applied at a power level between about 50 W and about 2,500 W.

8. A method of processing a substrate, comprising:

exposing the substrate positioned in a processing volume of a processing chamber to a hydrocarbon-containing gas mixture;

exposing the substrate to a boron-containing gas mixture, wherein the hydrocarbon-containing gas mixture and the boron-containing gas mixture are flowed into the processing volume at a precursor ratio of (boron-containing gas mixture/((boron-containing gas mixture)+hydrocarbon-containing gas mixture) of about 0.38 to about 0.85; and

generating a radio frequency (RF) plasma in the processing volume to deposit a boron-carbon film on the substrate, wherein the boron-carbon film has about 35 atomic percentage to about 55 atomic percentage of boron.

9. The method of claim 8, wherein the generating the RF plasma comprises applying a high frequency of about 12 MHz to about 14 MHz and a low frequency of about 0.1 kHz to about 1 kHz.

10. The method of claim 9, wherein the applying a high and low frequency is applied at a power level between about 50 W and about 2,500 W.

11. The method of claim 8, wherein the substrate is secured to an electrostatic chuck (ESC).

12. A non-transient computer readable medium, the medium containing program instructions for causing a computer to perform a method of:

exposing a substrate positioned in a processing volume of a processing chamber to a hydrocarbon-containing gas mixture;

exposing the substrate to a boron-containing gas mixture, wherein the hydrocarbon-containing gas mixture and the boron-containing gas mixture are flowed into the processing volume at a precursor ratio of (boron-containing gas mixture/((boron-containing gas mixture)+hydrocarbon-containing gas mixture) of about 0.38 to about 0.85; and

generating a radio frequency (RF) plasma in the processing volume to deposit a boron-carbon film on the substrate, wherein the boron-carbon film has about 55 atomic percentage to about 95 atomic percentage of boron.

13. The non-transient computer readable medium of claim 12, wherein the hydrocarbon-containing gas mixture comprises an alkane.

14. The non-transient computer readable medium of claim 12, wherein the boron-containing gas mixture comprises about 9 weight percentage (wt. %) diborane (B_2H_6) diluted in hydrogen gas (H_2).

15. The non-transient computer readable medium of claim 12, wherein a ratio of the hydrocarbon-containing gas mixture to the boron-containing gas mixture is in a range between about 0.7:1 and about 0.12:1.

16. The method of claim 1, wherein a pressure in the processing volume is between 2 Torr and 10 Torr.

17. The method of claim 1, wherein the substrate is maintained at a temperature from about 450 °C to about 650 °C.

18. The method of claim 8, wherein the boron-containing gas mixture comprises about 9 weight percentage (wt. %) diborane (B_2H_6) diluted in hydrogen gas (H_2).

19. The method of claim 8, wherein a ratio of the hydrocarbon-containing gas mixture to the boron-containing gas mixture is in a range between about 0.07:1 and about 0.12:1.

20. The non-transient computer readable medium of claim 12, wherein the hydrocarbon-containing gas mixture comprises propylene (C_3H_6).