Claims:

1. A clear coat composition comprising a first acrylic resin, a second acrylic resin, a polyester resin, a urethane resin, and a melamine resin,

wherein the first acrylic resin has a glass transition temperature of 0.5°C to 10°C and a hydroxyl value of 120 mgKOH/g to 200 mgKOH/g; and

the second acrylic resin has a glass transition temperature of -10°C to -1°C and a hydroxyl value of 50 mgKOH/g to 110 mgKOH/g,

the polyester resin has a hydroxyl value of 240 mgKOH/g to 320 mgKOH/g,

the urethane resin has a weight average molecular weight of 1,400 g/mol to 2,000 g/mol and a glass transition temperature of 10°C to 20°C.

2. The clear coat composition of claim 1, wherein the first acrylic resin has a weight average molecular weight of 7,700 g/mol to 8,200 g/mol; and the second acrylic resin has a weight average molecular weight of 8,500 g/mol to 9,000 g/mol.

3. The clear coat composition of claim 1, wherein the polyester resin has a glass transition temperature of 8°C to 15°C, and a weight average molecular weight of 2,500 g/mol to 3,500 g/mol.

4. The clear coat composition of claim 1, wherein the clear coat composition, based on the total weight of the composition, comprises 30 wt% to 50 wt% of the first acrylic resin, 6 wt% to 13wt% of the second acrylic resin, 2 wt% to 9 wt% of the polyester resin, 6 wt% to 12 wt% of the urethane resin, 15 wt% to 30 wt% of the melamine resin, and a remainder of a solvent.