



ABSTRACT OF THE DISCLOSURE

A non-reducible dielectric ceramic composition comprises of a basic composition expressed by the general formula:



wherein $0.05 \leq x \leq 0.30$, $0.005 \leq y \leq 0.12$, $0 < o \leq 0.20$, $0.0005 \leq p \leq 0.012$, and $1.002 \leq m \leq 1.03$, or



wherein $0.05 \leq x \leq 0.35$, $0.005 \leq y \leq 0.12$, $0.0005 \leq z \leq 0.05$, $0 < o \leq 0.20$, $0.0005 \leq p \leq 0.02$, $1.000 \leq m \leq 1.04$.

The composition contains an additive (A) composed of one or more oxides selected from the group of MnO_2 , Fe_2O_3 , Cr_2O_3 , CoO and NiO in an amount of 0.02 to 2.0 moles per 100 moles of the basic composition. The composition further contains an additive (B) consisting of SiO_2 and/or ZnO in an amount of 0.1 to 2.0 moles per 100 moles of the basic composition, or an additive (B) composed of a glass composition of a $\text{BaO-SrO-Li}_2\text{O-SiO}_2$ system in an amount of 0.05 to 5.0 parts by weight per 100 parts by weight of the basic composition.

This Sheet Has Been Replaced

