
CLAIMS

1. An adhesive composition comprising the following components (A) to (C):

(A) a radically polymerizable compound;

(B) a polymer having a weight-average molecular weight of 35,000 to 110,000 and having a repeat unit derived from a polymerizable compound of formula (I):



(I)

wherein X^1 and X^2 each independently represent a C7 to C20 alkyl group or a C7 to C20 alkoxy group, n represents 0 or 1, Z^1 and Z^2 each independently represent a single bond or a C1 to C3 alkylene group, each R independently represents an organic group or a halogeno group, m1 and m2 each independently represent any integer of 0 to 4, and Y represents a polymerizable functional group, and a repeat unit derived from (meth)acrylic acid ester; and

(C) a radical polymerization initiator.

2. The adhesive composition according to claim 1, wherein in formula (I), Y is an acryloyl group or a methacryloyl group.

3. The adhesive composition according to claim 1 or 2, wherein the adhesive composition is an adhesive composition for a plastic base material.

4. The adhesive composition according to any one of claims 1 to 3, wherein the radical polymerization initiator (C) is a photopolymerization initiator.

5. The adhesive composition according to any one of claims 1 to 3, wherein the radical polymerization initiator (C) is an organic peroxide.

6. The adhesive composition according to claim 4, wherein the adhesive composition is a coating agent.

7. The adhesive composition according to claim 6, wherein the coating agent is a primer.

8. The adhesive composition according to claim 4 or 5, wherein the adhesive composition is an adhesive agent.

9. A compact obtained by applying an adhesive composition according to any one of claims 1 to 8 onto a plastic base material, and curing the adhesive composition so that the resulting layer is disposed on the base material or between base materials.