

Description

This invention relates to a DC electric power cable.

Polyethylene and cross-linked polyethylene have heretofore been extensively used as an insulation for a DC power cable since they are superior in dielectric strength and other dielectric characteristics. However, in the case where such a cable having an insulation of either polyethylene or cross-linked polyethylene is used as a high-voltage power transmission line, some difficulties are encountered. The most serious of these is that when the cable is supplied with a high DC voltage, long-lasting space charge tends to be produced in the insulation. It is generally considered that this space charge has the nature of electron, hole or ion and that such space charge results from the charge entrapped in those portions of the polyethylene insulation contributing to the formation of a crystal structure thereof. Polyethylene has good insulating properties and is non-polar, so that the entrapped charge can not easily escape from said portions to form the long-lasting space charge. When such space charge is accumulated in the insulation of polyethylene upon application of DC voltage to the cable, the electric field intensity is increased adjacent to the conductor of the cable, so that the breakdown voltage of the cable is disadvantageously lowered.

DE-A-1694559 discloses an A-C cable having a conductor surrounded by an insulation layer comprising a thermoplastics resin containing 100 parts by weight of polyethylene. The electric and thermal properties of the polyethylene are improved by adding 2 parts by weight of 1,3-Ditert-butylperoxy-diisopropylbenzol 0.5 parts by weight of polymerised trimethyldihydroxyquinoline and 2.5 parts by weight of FEF carbon black.

With the above deficiencies in view, it is an object of this invention to provide a DC power cable of the type in which the accumulation of space charge in the insulation is reduced to enhance the dielectric strength of the insulation to thereby eliminate adverse effects on the insulation.

According to the present invention there is provided a DC power cable comprising a conductor and an insulation of a thermoplastic resin formed around said conductor, said insulation containing carbon black forming about 0.2 to about 5% of the total weight of the resin and carbon black together, the ratio of mineral oil absorption (cc/100 g) to specific surface (m²/g) in said carbon black being not less than 0.7, and said carbon black having a hydrogen content of not more than 0.6% by weight. With this construction, the accumulation of the space charge in the insulation can be reduced to a satisfactory level to eliminate undue irregularities in electric field exerted on the insulation, so that DC breakdown voltage of the cable can be increased, thereby improving dielectric resistance of the cable.

In a preferred form of the invention, the DC power cable comprises a conductor, an insulation layer formed on the inner semi-conductive layer, an outer semiconductive layer formed on the insulation layer, and a sheath formed on the outer semi-conductive layer, the insulation layer comprising a thermoplastic resin and carbon black as defined above.

The specific surface is measured by BET equation. The specific surface of the carbon black represents an amount of absorption of a specified substance (for example, N₂ or Ar) per gram of carbon black, and is expressed in terms of m²/g. This procedure is used since it is difficult to measure the surface area of each particle of the carbon black.

The oil absorption merely implies the amount of absorption of oil in the carbon black, and the particle structure of the carbon black, and the particle structure of the carbon black can be realized from the oil absorption.

The thermoplastic resin of which the insulation layer is made includes polyethylene such as low-density polyethylene and high-density polyethylene, polypropylene, ethylene vinyl acetate copolymer (EVA), ethylene ethyl acrylate copolymer (EEA), ethylene propylene rubber (EPR) and a mixture of at least two of these substances. Also, these substances can be used in the cross-linked form.

Examples of the carbon black contained in the thermoplastic resin include SAF carbon, acetylene carbon, ISAF carbon, I-ISAF carbon, CF carbon, SCF carbon and HAF carbon.

With the above-mentioned construction, leakage of space charge in the insulation layer is enhanced. The reason for this will now be described.

Resistivity (specific resistance) ρ (Ω -m) of the insulation layer is represented by the following formula (1):

$$\rho = \rho_0 e^{-\alpha T} e^{-\beta E} \quad (1)$$

wherein α is a temperature coefficient ($^{\circ}\text{C}^{-1}$) of the insulation layer, β is a coefficient of electric field (a stress coefficient of the insulation layer) (mm/kV), and E is the electric field (kV/mm) exerted on the insulation layer.

The addition of carbon black to the insulation increases the electric field coefficient β while the temperature coefficient α is decreased, thereby promoting the leakage of the space charge from the insulation layer. The reason is that when the electric field coefficient β is increased, the resistivity ρ is decreased, so that the electric field at the high stress portion of the insulation layer on which a high electric field is exerted is reduced in intensity, and also when the temperature coefficient α is decreased, the maximum electric field E_{max} , appearing on the side of the cable sheath when the temperature of the

conductor is high, is decreased. Thus, the electric field profile in the insulation layer is inclined toward a uniformity, so that the accumulation of the space charge in the insulation is reduced.

(1) The carbon black content should be in the range of about 0.2 to about 5% by weight. If the carbon black content is below 0.2%, the above-mentioned advantages can not fully be achieved. On the other hand, if the carbon black content is above 5%, the reduction of the resistivity ρ and the increase of the electric field coefficient β are excessive, so that a thermal breakdown of the insulation may occur.

(2) The ratio of oil absorption to specific surface should be not less than 0.7. When the amount of addition of carbon black is increased, the distance between adjacent particles thereof becomes shorter so that electric current flows between the particles under a high electric field due to a tunnel effect. As a result, the electric field coefficient β becomes unduly high, thereby inviting a thermal breakdown of the insulation. Therefore, it is of absolute necessity that the resistivity ρ represented by the formula (1) should be kept to a low level with a reasonably low content of the carbon black. Also, in the case where the carbon black is a furnace black, the ratio of oil absorption to specific surface should be not more than 3.5. If the ratio exceeds this level, the apparent particle size of the carbon black is increased, so that the carbon black can not be efficiently mixed with the polyethylene. Particularly, in the case of acetylene carbon, this tendency is marked, since the particles are linked in a chain-like manner.

When one of SAF carbon, ISAF carbon, I-ISAF carbon, CF carbon, SCF carbon and HAF carbon is used as the carbon black, the above ratio is in the range of between 0.7 and 1.5.

The carbon black having a higher ratio of oil absorption to specific surface can decrease the resistivity ρ in smaller amount. When this ratio is not less than 0.7, satisfactory results can be achieved.

(3) The carbon black should have the hydrogen content of not more than 0.6% by weight. If the hydrogen content is too great, too many π electrons are present in the insulation, so that the electrons can not be smoothly moved. As a result, much carbon black must be added to the thermoplastic insulation material so as to achieve the desired resistivity ρ . This is not desirable for the reasons mentioned in the above Item (2). Therefore, the lower the hydrogen content is the better. And, the hydrogen content of not more than 0.6% achieved satisfactory results.

(4) The carbon black should preferably have a particle size of 10 to 100 nm. Within this range, the crystalline structure of the polyethylene is not disturbed, and when the crystalline structure is disturbed, electrical characteristics of the cable are adversely affected. If the particle size exceeds this range, the carbon is not dispersed in the thermoplastic resin efficiently. The use of the carbon black having a particle size below this range is not practical.

(5) Preferably the carbon black should contain not less than 97% by weight of carbon. The higher the carbon content is, the better. The carbon black may contain as impurities ash, O_2 and H_2 , and if the content of such impurities is increased, electrical characteristics are adversely affected.

The invention will now be illustrated by way of Example.

Sample DC power cables 1 to 12 of this invention and comparative DC power cables 13 and 14 were prepared by the steps of simultaneously forming an inner semi-conductive layer, an insulation layer and an outer semi-conductive layer on a conductor by extrusion. The insulation layer interposed between the inner and outer semi-conductive layers had a thickness of 3 mm, and the conductor had a circular cross-sectional area of 200 mm².

Each of the insulation layers was made of polyethylene having the carbon black content shown in Table below. The carbon black added to the polyethylene had a particle size of 10 to 100 nm. Particularly, the carbon black contained in the insulation of each of the sample cables 9 and 10 was SAF carbon, and the carbon black contained in the insulation of each of the sample cables 11 and 12 was acetylene carbon.

Each of the sample cables were subjected to a DC breakdown test. The results obtained are also shown in Table.

As can be seen from Table, the sample cables 1 to 12 of this invention exhibited much improved DC breakdown voltage.

TABLE

Sample No.	CB	Oil absorption specific surface	Hydrogen content of CB (%)	DC breakdown voltage (KV/mm)
	PE+CB (%)			
1	0.8	0.99	0.33	112
2	1.5	"	"	"
3	3.0	"	"	96
4	5.0	"	"	72
5	0.2	4.16	0.08	"
6	0.4	"	"	112
7	0.8	"	"	104
8	1.5	"	"	96
9	0.8	0.99	0.33	"
10	1.5	"	"	"
11	0.4	4.16	0.08	92
12	0.8	"	"	84
13	0			72
14	8.0	0.99	0.33	48

* CB mans carbon black

Claims

1. A DC power cable comprising a conductor and an insulation of a thermoplastic resin formed around said conductor, said insulation containing carbon black forming about 0.2 to about 5% of the total weight of the resin and carbon black together, the ratio of mineral oil absorption (cc/100 g) to specific surface (m²/g) in said carbon black being not less than 0.7, and said carbon black having a hydrogen content of not more than 0.6% by weight.

2. A DC power cable according to Claim 1, in which said carbon black has a particle size of 10 to 100 nm.

3. A DC power cable according to Claim 1 or 2, in which said thermoplastic resin of which said insulation layer is made is at least polyethylene such as low-density polyethylene and high-density polyethylene, polypropylene, ethylene vinyl acetate copolymer (EVA), ethylene ethyl acrylate copolymer (EEA), ethylene propylene rubber (EPR).

4. A DC power cable according to Claim 1, 2 or 3 in which said thermoplastic resin is in the crosslinked form.

5. A DC power cable according to Claim 1, 2, 3 or 4 in which an inner semi-conductive layer is formed on the conductor, said insulation layer being formed on the inner semi-conductive layer, an outer semi-conductive layer being formed on the insulating layer, and a sheath formed on the outer semi-conductive layer.

6. A DC power cable according to any preceding claim in which said carbon black contains not less than 97% by weight of carbon.

7. A DC power cable according to any preceding claim in which said carbon black is a furnace black and said ratio of oil absorption to specific surface is not more than 3.5.

8. A DC power cable according to any of Claims 1 to 6, in which said carbon black is one of SAF carbon, ISAF carbon, I-ISAF carbon, CF carbon, SCF carbon and HAF carbon and said ratio of oil absorption to specific surface is not more than 1.5.

TABLE

Sample No.	CB	Oil absorption specific surface	Hydrogen content of CB (%)	DC breakdown voltage (KV/mm)
	PE+CB (%)			
1	0.8	0.99	0.33	112
2	1.5	"	"	"
3	3.0	"	"	96
4	5.0	"	"	72
5	0.2	4.16	0.08	"
6	0.4	"	"	112
7	0.8	"	"	104
8	1.5	"	"	96
9	0.8	0.99	0.33	"
10	1.5	"	"	"
11	0.4	4.16	0.08	92
12	0.8	"	"	84
13	0			72
14	8.0	0.99	0.33	48

* CB mans carbon black

Claims

1. A DC power cable comprising a conductor and an insulation of a thermoplastic resin formed around said conductor, said insulation containing carbon black forming about 0.2 to about 5% of the total weight of the resin and carbon black together, the ratio of mineral oil absorption (cc/100 g) to specific surface (m²/g) in said carbon black being not less than 0.7, and said carbon black having a hydrogen content of not more than 0.6% by weight.

2. A DC power cable according to Claim 1, in which said carbon black has a particle size of 10 to 100 nm.

3. A DC power cable according to Claim 1 or 2, in which said thermoplastic resin of which said insulation layer is made is at least polyethylene such as low-density polyethylene and high-density polyethylene, polypropylene, ethylene vinyl acetate copolymer (EVA), ethylene ethyl acrylate copolymer (EEA), ethylene propylene rubber (EPR).

4. A DC power cable according to Claim 1, 2 or 3 in which said thermoplastic resin is in the crosslinked form.

5. A DC power cable according to Claim 1, 2, 3 or 4 in which an inner semi-conductive layer is formed on the conductor, said insulation layer being formed on the inner semi-conductive layer, an outer semi-conductive layer being formed on the insulating layer, and a sheath formed on the outer semi-conductive layer.

6. A DC power cable according to any preceding claim in which said carbon black contains not less than 97% by weight of carbon.

7. A DC power cable according to any preceding claim in which said carbon black is a furnace black and said ratio of oil absorption to specific surface is not more than 3.5.

8. A DC power cable according to any of Claims 1 to 6, in which said carbon black is one of SAF carbon, ISAF carbon, I-ISAF carbon, CF carbon, SCF carbon and HAF carbon and said ratio of oil absorption to specific surface is not more than 1.5.



Patentansprüche

1. Gleichstromkabel aus einem Leiter und einer den Leiter umhüllenden Isolierung aus einem thermoplastischen Harz mit etwa 0,2 bis etwa 5% Ruß, bezogen auf das Gesamtgewicht Harz und Ruß, wobei das Verhältnis Mineralölabsorption (ml/100 g)/spezifische Oberfläche (m²/g) in dem Ruß nicht weniger als 0,7 beträgt und der Ruß einem Wasserstoffgehalt von nicht mehr als 0,6 Gew.-% aufweist.
2. Gleichstromkabel nach Anspruch 1, dadurch gekennzeichnet, daß der Ruß eine Teilchengröße von 10—100 nm aufweist.
3. Gleichstromkabel nach Ansprüchen 1 oder 2, dadurch gekennzeichnet, daß das thermoplastische Harz, aus dem die Isolierschicht gefertigt ist, aus mindestens einem der folgenden Harze: Polyethylen, z.B. niedrigdichtes Polyethylen und hochdichtes Polyethylen, Polypropylen, Ethylen/Vinylacetat-Mischpolymerisat (EVA), Ethylen-/Ethylacrylate-Mischpolymerisaten (EEA) und Ethylen-/Propylen-Kautschuk (EPR) besteht.
4. Gleichstromkabel nach Ansprüchen 1, 2 oder 3, dadurch gekennzeichnet, daß das thermoplastische Harz in vernetzter Form vorliegt.
5. Gleichstromkabel nach Ansprüchen 1, 2, 3 oder 4, dadurch gekennzeichnet, daß auf dem Leiter eine innere halbleitende Schicht, auf dieser die Isolierschicht, auf der Isolierschicht eine äußere halbleitende Schicht und auf dieser ein Mantel ausgebildet sind.
6. Gleichstromkabel nach einem der vorhergehenden Ansprüche, dadurch gekennzeichnet, daß der Ruß nicht weniger als 97 Gew.-% Kohlenstoff enthält.
7. Gleichstromkabel nach einem der vorhergehenden Ansprüche, dadurch gekennzeichnet, daß es sich bei dem Ruß um Ofenruß handelt und daß das Verhältnis Ölabsorption/spezifische Oberfläche nicht mehr als 3,5 beträgt.
8. Gleichstromkabel nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß es sich bei dem Ruß um SAF-Kohlenstoff, ISAF-Kohlenstoff, I-ISAF-Kohlenstoff, CF-Kohlenstoff, SCF-Kohlenstoff oder HAF-Kohlenstoff handelt und daß das Verhältnis Ölabsorption/spezifische Oberfläche nicht mehr als 1,5 beträgt.

Revendications

1. Câble de transport d'énergie en courant continu, comprenant un conducteur et une isolation en résine thermoplastique formée autour dudit conducteur, ladite isolation contenant du noir de carbone formant environ 0,2 à environ 5% du poids total de la résine et du noir de carbone ensemble, le rapport entre l'absorption d'huile minérale (cm³/100 g) et la surface spécifique (m²/g) dans ledit noir de carbone étant non inférieur à 0,7, et ledit noir de carbone ayant une teneur en hydrogène ne dépassant pas 0,6% en poids.
2. Câble de transport d'énergie en courant continu selon la revendication 1, dans lequel ledit noir de carbone a une taille de particules de 10 à 100 nm.
3. Câble de transport d'énergie en courant continu selon la revendication 1 ou 2, dans lequel ladite résine thermoplastique dont est fait ladite couche d'isolation est au moins du polyéthylène tel que le polyéthylène à basse densité et le polyéthylène à haute densité, le polypropylène, le copolymère d'éthylène et d'acétate de vinyle (EVA), le copolymère d'éthylène et d'acrylate d'éthyle (EEA), le caoutchouc d'éthylène-propylène (EPR).
4. Câble de transport d'énergie en courant continu selon la revendication 1, 2 ou 3 dans lequel ladite résine thermoplastique est sous la forme réticulée.
5. Câble de transport d'énergie en courant continu selon la revendication 1, 2, 3 ou 4, dans lequel une couche interne semi-conductrice est formée sur le conducteur, ladite couche d'isolation étant formée sur la couche interne semi-conductrice, une couche externe semi-conductrice étant formée sur la couche d'isolation, et une gaine formée sur la couche semi-conductrice externe.
6. Câble de transport d'énergie en courant continu selon l'une quelconque des revendications précédentes, dans lequel ledit noir de carbone contient pas moins de 97% de carbone, en poids.
7. Câble de transport d'énergie en courant continu selon l'une quelconque des revendications précédentes, dans lequel ledit noir de carbone est un noir du type d'un noir produit dans un four et ledit rapport entre l'absorption d'huile et la surface spécifique ne dépasse pas 3,5.
8. Câble de transport d'énergie en courant continu selon l'une quelconque des revendications 1 à 6, dans lequel ledit noir de carbone est un des carbones SAF, ISAF, I-ISAF, CF, SCF et HAF, et ledit rapport entre l'absorption d'huile et la surface spécifique ne dépasse pas 1,5.

