

ABSTRACT

Disclosed is a temporary protective film for semiconductor sealing molding comprising: a support film; and an adhesive layer provided on one surface or both surfaces of the support film and containing a resin and a silane coupling agent, and the content of the silane coupling agent in the temporary protective film may be more than 5% by mass and less than or equal to 35% by mass with respect to the total mass of the resin.