THIS SHEET HAS BEEN
REPLACED

## ABSTRACT

A highly reliable connecting lead for devices that mount semiconductors. The lead is made of copper or copper alloy. The thickness of the oxide film at the interface between the copper or copper alloy lead and an aluminum bump electrode is 10 nm or less. The contents of oxygen and carbon in the aluminum bump electrode are 1 atm % or less each.

This Sheet Has Been Replaced