

ABSTRACT

The pressure sensitive adhesive sheet (5) is a photocurable pressure sensitive adhesive in which a pressure sensitive adhesive composition containing a base polymer and a photocurable compound is formed in a layer shape. The pressure sensitive adhesive sheet has a haze of 1% or less, an adhesive strength of 1.5 N/10 mm or more to glass, and a shear storage elastic modulus of 0.15 MPa or less at a temperature of 25°C. When the pressure sensitive adhesive is post-cured to have a polymerization ratio of 99%, the post-cured pressure sensitive adhesive has a glass transition temperature of -3°C or lower, and a shear storage elastic modulus of 0.16 MPa or more at 25°C.

FIG. 1