

SPECIFICATION

Separation of non-ferromagnetic metals from fragmented material

5 This invention relates to the separation of non-ferromagnetic metals from fragmented material and has particular application to the recovery of non-ferromagnetic metals from fragmented scrap.

10 At present, when objects fabricated from metal, such as cars and domestic appliances, reach the end of their useful life, they are initially crushed and then fed into a so-called fragmentiser in which all parts, including solid metal parts are broken into pieces, 15 the maximum dimension of which is unlikely to exceed about fifteen or twenty centimetres. Wire tends to form itself into tangled ball-like masses but it is unusual for pieces of other material to be trapped in such entanglement. Ferrous metal is 20 extracted from the output of the fragmentiser using a magnetic separator. The remaining material is then commonly hand sorted from a conveyor belt. The ball-like tangles of wire are readily removed but the non-ferrous metal pieces are separated by experi- 25 enced operatives recognising the objects of which the pieces are broken fragments and knowing, from experience, the metal of which such pieces are commonly made. This is a relatively inefficient procedure and a substantial proportion of the non-ferrous material is not recovered. In addition, it is 30 very labour-intensive.

In the present invention it is proposed to use a linear induction motor to remove non-ferromagnetic metals from mixtures of materials. In the system the 35 mixture of fragmented material is brought into proximity with a linear induction motor primary so that the non-ferromagnetic pieces of material, which act as secondaries to the linear induction motor primary, are displaced out of the rest of the frag- 40 mented material.

It is an object of the present invention to provide a metal sorting system in which a linear motor system is used which can economically sort the non-ferromagnetic material from a mixture of material. It 45 is also an object of the present invention to provide a metal sorting system which can sort the individual metals such as aluminium, brass, copper etc. into their various categories. It is also an object of the present invention to be able to sort automatically the 50 smaller sizes of non-ferromagnetic material and it is an object to be able to sort the non-ferromagnetic material at a greater rate than the present hand sorting methods.

According to the present invention I provide a 55 metal sorting apparatus including a conveyor belt means for feeding a mixture of non-ferromagnetic material on to said conveyor belt, at a first position, drive means for said conveyor belt to move said conveyor belt at a predetermined speed in a first 60 direction; linear induction motor means situated as a second position along said conveyor belt said second position being intermediate said first position and the end of the conveyor belt; said linear induction motor 65 means being positioned with the faces of the motor

poles adjacent to and substantially underneath said conveyor belt and orientated with respect to said conveyor to produce when actuated a field of magnetomotive force in which the lines of force are 70 at right angles to the said first direction;

electrical drive means for said linear induction motor for providing an alternating current supply to said motor at a power level and with a frequency to force, by means of the travelling wave of magnetomotive 75 force produced by said linear motor a percentage of said non-ferromagnetic material from said conveyor, reception means situated adjacent said linear motor means on a side of said conveyor belt for receiving non-ferromagnetic material forced from said con- 80 veyor belt by the magnetomotive force of said linear motor in the direction of travel of the magnetic field when actuated; terminal reception means situated adjacent said conveyor belt at a position downstream from said 85 linear motor induction for reception of the material remaining on said conveyor belt characterised in that the windings of the linear motor comprise hollow tubes for the passage of cooling water from a suitable supply and that in operation primary cur- 90 rents of the order of thousands of amperes are fed through the primary windings, the heat generated by these high primary currents being substantially dissipated by the cooling water, and in that the pole pitch of the motor is of the order of 5 cms to enable 95 efficient sorting of the non-ferromagnetic metal from the mixture of non-ferromagnetic material on the conveyor belt.

According to a further aspect of the present invention the means for feeding the mixture of 100 non-ferromagnetic material on to the conveyor belt comprises screening means to allow only material within predetermined size limits on to the conveyor belt. This means may comprise one or more screens which may be of the vibratory or rotary type.

105 The power of the linear motor can thus be chosen to induce sufficient flux in pieces of a specified metal to remove these pieces from the belt. Pieces of a denser metal for example though having a large amount of flux induced will not be removed because 110 of their weight and thus the consequent friction forces involved in their movement.

In a further aspect the invention provides a further linear induction motor associated with the conveyor belt at a position downstream from the first linear 115 induction motor means. By operating this further linear induction motor at a frequency and power higher than the first linear induction motor pieces of a denser metal are removed by the second motor. It is thus possible to provide respective receptacles or 120 bins associated with each motor which will collect different types of metal.

One of the problems with a conveyor belt system is that small pieces of a particular metal can often be trapped under for example larger pieces of non-metallic substance for example plastics material. 125 This problem may be alleviated by the above described screening process but a further solution may be found by performing a secondary sorting action using a linear induction motor mounted to operate on material falling off the end of the 130

conveyor belt. This solution also obviates the problem of friction between the pieces of metal and the conveyor belt.

Accordingly in a further embodiment the present invention provides a further linear induction motor means mounted adjacent the end of the conveyor in a position vertically below the end of the conveyor belt such that non-ferromagnetic material remaining on the conveyor belt after removal of a portion of the material by the first linear induction motor means and reception means situated substantially vertically below the end of the conveyor belt to catch material not deflected by the further linear induction motor and reception means situated to one side in a position to receive material deflected by the further linear induction motor means.

In a practical sorting system it may be more convenient to incline the conveyor with respect to the horizontal to give a more practical layout. This may require adjustment of the angle of orientation of the linear induction motor with respect to the conveyor belt. Inclination of the conveyor belt can also provide for greater efficiency of operation of the motor.

Metal sorting systems in accordance with the present invention will be more readily understood from the following description with reference to the accompanying drawings, in which:

Figure 1 is a schematic diagram illustrating the flux pattern produced by a single-sided linear induction motor.

Figure 2 is a transverse cross-sectional view in accordance with the invention, showing in cross sectional elevation a conveyor belt and a single sided linear induction motor.

Figure 3 is a plan view of part of separating apparatus similar to that shown in Figure 2 showing a possible orientation of the linear induction motor of Figure 2.

Figure 4 is a graph illustrating the power required to move pieces of non-ferrous material plotted against the size of the pieces of material.

Figure 5 is a side elevational view of a feed apparatus including flattening rollers.

Figure 6 shows a comparison between the stator slot geometry of a normal induction motor and that of a suitable linear induction motor.

Figure 7 shows a first practical embodiment of a complete metal sorting system according to the present invention.

Figure 8 shows a second practical embodiment according to the present invention, and

Figure 9 shows a third complete metal sorting system according to the present invention.

Figure 10 shows in greater detail a part of the system of Figure 9.

Figure 11 shows a cooling system for a linear induction motor used in the metal sorting system, and

Figure 12 shows the use of a linear motor on a wide conveyor belt.

Figure 1 shows the travelling magnetic field pattern produced by a single-sided linear motor, 10 being the plane of the pole faces. It is assumed that the field is travelling from right to left, as viewed in

the drawing. Consequently, a circular object 12, held stationary relative to the primary will move, relative to the field pattern along the path indicated by the dotted lines 14 and 16. It will be seen that, as the object 12 moves along this path, it is subject to a magnetic field which rotates in the clockwise direction as viewed in the drawing. Consequently, if the object 12 was a cylinder placed on a flat surface at the level indicated by the line 16, it would roll along that surface in the opposite direction to that of the travelling field of magnetomotive force produced by the linear induction motor primary.

In Figure 2, a longitudinal flux single-sided linear induction motor primary 20 is disposed with its working face upwards below a conveyor belt 22 on to which a mixture of pieces of material, including non-ferrous metals, is to be deposited. In use, the conveyor belt 22 moves in a direction perpendicular to the plane of the paper and the primary 20 produces a field of magnetomotive force which travels from left to right, as illustrated by the arrow 24. As will be understood from the foregoing discussion of Figure 1, pieces of non-ferromagnetic electrically conductive material disposed on the conveyor belt, such as the pieces 26 and 28, are subject to a field of magnetomotive force which travels from left to right and are also subject to a force which attempts to rotate in an anti-clockwise direction. In pieces such as piece 26, of dimensions in the direction of the travelling field substantially less than half the pole pitch of the motor, the rotating field predominates and such pieces are rolled towards the left, as viewed in Figure 2, off the side of the conveyor belt 22 and into a receptacle 30. On the other hand, pieces 28 of dimensions in the direction of the travelling field of the order of half the pole pitch of the motor or greater are subject to a force which displaces them from left to right, off the conveyor belt 22 and into another receptacle 32 on the other side thereof. The pieces 28 are, however, also subject to the rotating field components which tend to lift their leading edges, thereby assisting them in sliding over any particles not being moved by the motor which may lie in their path.

Pieces of non-ferromagnetic metal of a size approximately equal to half the pole pitch of the motor tend to remain on the conveyor belt 22, due to a part forward sliding and part backward rolling motion. Referring to Figure 3, in order to remove such pieces, a second linear induction motor primary 34 is arranged downstream of the motor 20 and parallel thereto, the conveyor belt 22 moving from left to right as viewed in Figure 3. The linear motor 34 has a shorter pole pitch than that of the motor 20. For example, if both motors are wound on cores assembled from the same size of stamping, the motor 34 may be wound with one slot per pole per phase, the motor 20 is wound with two slots per pole per phase. Thus the pole pitch of the motor 20 is twice that of the motor 34 and pieces of a size which would be left on the conveyor belt 22 by the motor 20 are displaced off the conveyor belt by the motor 34 in the direction of the travelling field.

It will be seen from Figure 3 that the axes of the motors 20 and 34 are not perpendicular to the

direction of the movement of the conveyor belt 22 but are disposed at an angle such that the travelling magnetic field has a component opposing the direction of movement of the belt 22. The effect of this is to slow down the movement of electrically conductive pieces on the belt so that they are exposed to the influence of each motor for a longer period of time thereby increasing the probability that they will be displaced off the belt before the belt moves them out of range of the motor. This enables either the speed of the belt to be increased or the width of the motors to be reduced as compared with what would be required if the axes of the motors were perpendicular to the direction of movement of the belt.

Figure 4 illustrates the variation of the power P required to cause movement on the conveyor belt 22 of pieces of a particular non-ferromagnetic metal with the smallest dimension d of such pieces. It will be seen that the power P required increases as the dimension d decreases.

It should be realised that the dimension d is the dimension of the material in closed proximity to the conveyor belt 22. This is because the flux density falls off exponentially with distance above the surface. Consequently, in order to optimise the use of the available power, the pieces of material are preferably flattened and laid on the belt with their major dimensions perpendicular to the direction of movement of the belt.

Referring to Figure 5, the material is preferably fed on to the belt from a hopper 40 with a pair of rolls 42 and 44 disposed between the outlet of the hopper 40 and the belt with their axes parallel to the axis of the driving roller 46 of the belt. Material from the hopper 40 is therefore flattened by the rolls 42 and 44 and deposited on the belt with the major dimension of the various pieces tending to be oriented parallel to the axes of the rolls.

The use of a motor with a relatively short pole pitch enables a large range of sizes of the various pieces of non-ferrous material to be moved in the direction of the travelling field of magnetomotive force. Consequently, it is in general preferable to use a relatively small pole pitch.

Other factors affecting the movement of pieces of non-ferromagnetic material are the density of material, which determines the frictional force which has to be overcome, and the electrical conductivity which determines the magnitude of the induced secondary current for a given flux. When comparing copper and aluminium, the effect of the smaller density of aluminium predominates over that of the higher conductivity of copper with the result that aluminium can be moved at lower field strength than copper. Consequently, if the waste material is segregated into a number of size ranges and the material in each size range fed separately to separating apparatus in accordance with the invention, the field strength of the linear motors 20 and 34 can be arranged to be such that the aluminium pieces are displaced off the belt while copper pieces are allowed to remain on it. If the belt then passes over a further pair of linear motors which are capable of displacing the copper, the latter can then be sepa-

ately removed from the remaining material. Thus, by using a series of separate pairs of linear motors, different non-ferromagnetic metals can be separated from one another.

One way of increasing the effectiveness of the linear motors is to increase the frequency of the alternating current used to power the motors. For example the motors used to remove the aluminium may be powered at 50 Hz while the motors used to remove the copper may be powered at a higher frequency, up to about 500 Hz. However, the skin effect at the higher frequency has the result of reducing the apparent conductivity of the electrically conductive materials as frequency increases. Since for any particular frequency, skin depth increases as conductivity decreases, this has the effect of compressing the spread of apparent conductivity between different metals. Consequently, it is preferable to use the lowest acceptable frequency and, in particular, to remove medium and large pieces of aluminium using linear motors powered at a relatively low frequency before the conveyor belt passes over motors suitable for the removal of metals whose conductivity or size require a higher frequency.

As previously stated, the cores of the primaries of all linear induction motors for use in accordance with the invention should have a tooth width which is less than 30% of the tooth pitch.

Referring now to Figure 6 of the drawings Figure 6A shows the configuration of the stator of a normal type of induction motor. Figure 6B shows by way of contrast the stator of a linear induction motor suitable for use in the metal sorting system of the present invention.

In the stator of Figure 6A the tooth width a is approximately half the tooth pitch B but in the stator of Figure 6B the tooth width a may be seen to be less than 30% of the tooth pitch b . It may also be seen that it is possible to considerably increase the depth c of the slot thus allowing a greater cross section of copper and correspondingly allowing an increase in power of the motor by increased stator current.

Referring now to Figure 7 there is shown a first embodiment of a practical metal sorting system. A fragmentiser 50 has an outlet 52 which feeds material both ferromagnetic and non-ferromagnetic onto a first conveyor belt 54 driven at a constant predetermined speed by drive roller 56 connected to an electric motor 58.

The material conveyed by the conveyor 54 is deposited on to a first sieve 60 which removes the dust and very small particles from the mixture. The dust is collected by a first hopper 62. As an alternative an air extractor system can be used at this stage. The larger remaining particles are transported by a second conveyor 70 past an overband electromagnet 72 which removes the ferromagnetic material from the mixture. The ferromagnetic material is attracted by the electromagnet 72 and on to a continuous belt 74 equipped with slats which is wiped across the face of the electromagnet and deposited into a hopper 76.

The material left on the conveyor belt 70 is deposited on to a transfer sieve 78 which removes

material below a predetermined dimension from the flow of material. The material falling through the sieve 78 is collected by a hopper 80 and the remaining material is deposited on to a further conveyor 82 driven at a predetermined speed by a drive roller 84. The conveyor 82 deposits the remaining material on to a further transfer sieve 86 which is of large dimension and therefore allows material of larger dimensions to fall into a hopper 88.

It may be seen therefore that if the transfer sieve 78 is a one inch mesh the hopper 80 will contain only material under one inch in any one dimension. If the sieve 86 is a three inch mesh then the hopper 88 will contain material between one and three inches in dimension.

Thus only material over three inches in dimension will be fed onto the last conveyor 90 which is driven by a drive roller 92 at a constant speed over the top of a linear induction motor 94. Material deflected from the conveyor 90 by the motor 94 is collected in a hopper 96 and material left on the conveyor is collected in a last hopper or bin 98.

The linear induction motor 94 is arranged with respect to the conveyor in a manner as described with reference to the preceding Figures 1 to 6. The frequency of operation of the motor 94 and the power input to the motor may be chosen to remove the larger pieces of non-ferromagnetic material which are the only sizes left on the conveyor after the two sieving operations.

The contents of each of the hoppers 80 and 88 may subsequently be fed to respective conveyor belt and linear motor systems. The frequency and power of the linear motors being chosen to suit the removal of the appropriate sizes of non-ferromagnetic material in these respective hoppers.

Referring now to Figure 8 there is shown a second metal sorting system according to the present invention. Material to be sorted is fed as for the system of Figure 7 into a fragmentiser 100 where it is smashed into relatively small pieces. These are transported by a conveyor 102 onto a dust sieve 104, the dust being collected in a hopper 106. As above alternatively an air extraction system to remove the dust and light material may be used. The rest of the material is conveyed on a conveyor belt 108 past an overband electromagnet 110 which removes the ferromagnetic material.

Material left on conveyor belt 108 is carried on to transfer a sieve 112 which is of relatively small mesh. Material of all types metal rubber and plastics falls on to a secondary conveyor belt 114, which moves at a constant predetermined speed in the direction shown. A linear induction motor 116 is mounted beneath the belt and when actuated causes the non-ferromagnetic metal on the conveyor to be deflected sideways off the conveyor to be collected in a hopper 118. Material such as plastics and rubber remaining on the conveyor is collected in a further hopper 120.

Material too large for the sieve 112 is fed to a conveyor belt 122 underneath which are mounted two linear induction motors, 124 and 126, motor 126 being downstream from motor 124. Non-ferromagnetic material on the belt is deflected by the

first motor 124 into a hopper 128 and by the second motor 126 into a hopper 130. Material left on the conveyor is collected by a hopper 132.

The system of Figure 8 operates by separating at the sieve 112 the smaller pieces of non-ferromagnetic material and small pieces of plastics and rubber. The non-ferromagnetic material is separated from the rest by the linear motor 116.

The larger pieces of material fed on to the conveyor 122 are fed to the linear motor 124 which is operated at a lower power than the motor 116. This motor therefore for example separates all the aluminium from the mixture. The remainder of the material is fed to the second linear induction motor 126 which is operated at a higher power and which thereby deflects the heavier metals such as brass, copper from the conveyor.

Thus by sieving and feeding the material to a series of linear induction motors the non-ferromagnetic metals can be sorted into their various types.

A further system utilising the principles of the present invention is shown in Figure 9. Again the material such as a motor car or part thereof is fed into a fragmentiser 150 the output material from which is fed via a conveyor 152 to a dust sieve 154 of fine mesh. Material not passing through the sieve is passed to a conveyor belt 158 and ferromagnetic material is removed by an overband electromagnet 160.

The remaining material comprising non-ferromagnetic metal rubber, plastics etc is fed via a small mesh sieve 162 to a conveyor 164. Material falling through the sieve 162 is collected in a hopper 166. The sieve 162 can merely be a further dust sieve to remove dust created by the removal of the ferromagnetic material or very small particles. Alternatively as in the arrangement of Figure 8 it can be of a mesh size to remove the relatively smaller pieces of material.

Material on the conveyor belt 164 is fed past at least one linear motor 168 and the non-ferromagnetic metal deflected by this motor is collected in a hopper 170. As in the arrangement shown in Figure 8 a second linear induction motor could be situated downstream from the motor 168 to sort out other sizes or types of non-ferromagnetic metal.

The conveyor belt 164 is inclined so that material passing the motor 168 and deflected by it may be assisted by rolling or sliding down the conveyor belt when lifted by the motor thus spending a greater period of time in the field of the motor. This can allow a lower power motor to be used relative to the size of non-ferromagnetic metal to be deflected.

Material left on the conveyor after the motor 168 is moved to the top end of the conveyor 172 and dropped in a free fall between a double sided primary linear induction motor 174. It may be seen that the larger pieces of conductive material are deflected into a first hopper 176 and the rest of the material is collected by a hopper 178 situated vertically below the end of the belt 172.

The movement of the conductive material can be to the right as illustrated in Figure 10. The conductive material 180 falling between the poles of the double

sided motor 174 is deflected to the right past a baffle 182 and is directed by the baffle to a hopper (not shown).

- The use of a double sided primary as shown in
 5 Figures 9 and 10 increases the detection sensitivity because the field between the primaries is substantially greater than with an open single primary. The friction of the belt is also eliminated by this system and also the pieces of material are more freely
 10 dispersed than on the conveyor where pieces may impede each others movement.

- The design of each linear induction motor is important and the deflecting power of any motor depends on a number of factors including principally
 15 the design of the stator, the frequency of operation and the motor current. The motors in general however require large operating currents and hence the need to remove considerably more heat than is normally generated with conventional linear motors.
 20 For this reason the motor is water cooled for example by using hollow copper tubes for the windings and forcing water through the tubes to provide the necessary cooling.

- A suitable cooling system is shown in Figure 11 in
 25 which water 200 is stored in a tank 202. A motor driven pump 204 circulates the water round the system in the direction shown back to the tank 200. The flow is split at 206 into three paths to supply each phase of the three phase linear induction
 30 motor. Each path has a respective air purge gate and has electrical isolation means 208, 210 on each side of the motor 212. The flow is recombined at 214 and is fed via radiators 216, 218 cooled by electric fans 220, 222 back to the tank 202. Numerous isolation
 35 valves are provided as shown.

- The linear induction motor may not always be of the same width as the conveyor especially if the sorting system is added to an existing installation. Figure 12 shows a solution to this problem. A
 40 conveyor 230 is moved in a direction indicated by arrow 232 by known conveyor drive means (not shown). Material is introduced onto the centre portion of the conveyor by baffles 234, 236. The linear induction motor 238 has a full travelling field zone 240 as shown shaded. The travelling field is in
 45 the direction shown by arrow 242. Deflectors 244 and 247, pivoted on pivots 245, 249 are adjusted and then fixed to push any material towards the centre of the conveyor belt 230. The non-ferromagnetic material deflected by the motor 238 is either ejected
 50 directly into a hopper 246 or in the case of heavier or less conductive pieces onto a collector deflector 248 which guides the material into the hopper 246.

- Material fed onto any of the above described
 55 conveyor belt and linear motor systems is preferably fed by a vibratory arrangement which effectively spreads the material on the conveyor and stabilises the load on the conveyor. As an alternative the conveyor can be run at a relatively high speed with
 60 respect to any immediately upstream conveyors to spread out the material.

- In linear motors used in the above described systems the pole pitch was of the order of 2" and an operating frequency of 50/60 Hz was used to
 65 remove aluminium. The current in the primary was

2000 amps at 18 volts line. For removal of denser metals higher frequencies of 50-500 Hz is required.

CLAIMS

- 70 1. A metal sorting apparatus including a conveyor belt means for feeding a mixture of non-ferromagnetic material on to said conveyor belt, at a first position, drive means for said conveyor belt to
 75 move said conveyor belt at a predetermined speed in a first direction; linear induction motor means situated at a second position along said conveyor belt said second position being intermediate said first position and the
 80 end of the conveyor belt; said linear induction motor means being positioned with the faces of the motor poles adjacent to and substantially underneath said conveyor belt and orientated with respect to said conveyor to produce when actuated a field of
 85 magnetomotive force in which the lines of force are at right angles to the said first direction; electrical drive means for said linear induction motor for providing an alternating current supply to said motor at a power level and with a frequency to force,
 90 by means of the travelling wave of magnetomotive force produced by said linear motor a percentage of said non-ferromagnetic material from said conveyor, reception means situated adjacent said linear motor means on a side of said conveyor belt for receiving
 95 non-ferromagnetic material forced from said conveyor belt by the magnetomotive force of said linear motor in the direction of travel of the magnetic field when actuated; terminal reception means situated adjacent said
 100 conveyor belt at a position downstream from said linear motor induction for reception of the material remaining on said conveyor belt the windings of the linear motor comprising hollow tubes for the passage of cooling water from a suitable supply in
 105 which in operation primary currents of the order of thousands of amperes are fed through the primary windings, the heat generated by these high primary currents being substantially dissipated by the cooling water, and in which the pole pitch of the motor is
 110 of the order of 5cms to enable efficient sorting of the non-ferromagnetic metal from the mixture of non-ferromagnetic material on the conveyor belt.
2. A metal sorting apparatus as claimed in claim 1 in which the windings of the linear motor are
 115 terminated in electrical isolation means 208, 210 on each side of the motor to isolate the electrical current from the water supply.
3. A metal sorting apparatus as claimed in claim 1 in which the linear induction motor means primary
 120 member has a toothed core in which the width of each tooth (a) is less than 30% of the tooth pitch (b).
4. A metal sorting system as claimed in Claim 1 or Claim 2 in which said means for feeding a mixture of non-ferromagnetic material on to said conveyor
 125 belt comprises means to allow only material within predetermined limit sizes on to said conveyor belt.
5. A metal sorting system as claimed in Claim 4 in which said means for feeding a mixture of non-ferromagnetic material on to said conveyor belt
 130 further comprises an electromagnet for extracting



sided motor 174 is deflected to the right past a baffle 182 and is directed by the baffle to a hopper (not shown).

- The use of a double sided primary as shown in
- 5 Figures 9 and 10 increases the detection sensitivity because the field between the primaries is substantially greater than with an open single primary. The friction of the belt is also eliminated by this system and also the pieces of material are more freely
- 10 dispersed than on the conveyor where pieces may impede each others movement.

- The design of each linear induction motor is important and the deflecting power of any motor depends on a number of factors including principally
- 15 the design of the stator, the frequency of operation and the motor current. The motors in general however require large operating currents and hence the need to remove considerably more heat than is normally generated with conventional linear motors.
- 20 For this reason the motor is water cooled for example by using hollow copper tubes for the windings and forcing water through the tubes to provide the necessary cooling.

- A suitable cooling system is shown in Figure 11 in
- 25 which water 200 is stored in a tank 202. A motor driven pump 204 circulates the water round the system in the direction shown back to the tank 200. The flow is split at 206 into three paths to supply each phase of the three phase linear induction
- 30 motor. Each path has a respective air purge gate and has electrical isolation means 208, 210 on each side of the motor 212. The flow is recombined at 214 and is fed via radiators 216, 218 cooled by electric fans 220, 222 back to the tank 202. Numerous isolation
- 35 valves are provided as shown.

- The linear induction motor may not always be of the same width as the conveyor especially if the sorting system is added to an existing installation. Figure 12 shows a solution to this problem. A
- 40 conveyor 230 is moved in a direction indicated by arrow 232 by known conveyor drive means (not shown). Material is introduced onto the centre portion of the conveyor by baffles 234, 236. The linear induction motor 238 has a full travelling field zone 240 as shown shaded. The travelling field is in the direction shown by arrow 242. Deflectors 244
- 45 and 247, pivoted on pivots 245, 249 are adjusted and then fixed to push any material towards the centre of the conveyor belt 230. The non-ferromagnetic material deflected by the motor 238 is either ejected
- 50 directly into a hopper 246 or in the case of heavier or less conductive pieces onto a collector deflector 248 which guides the material into the hopper 246.

- Material fed onto any of the above described
- 55 conveyor belt and linear motor systems is preferably fed by a vibratory arrangement which effectively spreads the material on the conveyor and stabilises the load on the conveyor. As an alternative the conveyor can be run at a relatively high speed with
- 60 respect to any immediately upstream conveyors to spread out the material.

- In linear motors used in the above described systems the pole pitch was of the order of 2" and an operating frequency of 50/60 Hz was used to
- 65 remove aluminium. The current in the primary was

2000 amps at 18 volts line. For removal of denser metals higher frequencies of 50-500 Hz is required.

CLAIMS

- 70 1. A metal sorting apparatus including a conveyor belt means for feeding a mixture of non-ferromagnetic material on to said conveyor belt, at a first position, drive means for said conveyor belt to
- 75 move said conveyor belt at a predetermined speed in a first direction; linear induction motor means situated at a second position along said conveyor belt said second position being intermediate said first position and the
- 80 end of the conveyor belt; said linear induction motor means being positioned with the faces of the motor poles adjacent to and substantially underneath said conveyor belt and orientated with respect to said conveyor to produce when actuated a field of
- 85 magnetomotive force in which the lines of force are at right angles to the said first direction; electrical drive means for said linear induction motor for providing an alternating current supply to said motor at a power level and with a frequency to force,
- 90 by means of the travelling wave of magnetomotive force produced by said linear motor a percentage of said non-ferromagnetic material from said conveyor, reception means situated adjacent said linear motor
- 95 means on a side of said conveyor belt for receiving non-ferromagnetic material forced from said conveyor belt by the magnetomotive force of said linear motor in the direction of travel of the magnetic field when actuated;
- terminal reception means situated adjacent said
- 100 conveyor belt at a position downstream from said linear motor induction for reception of the material remaining on said conveyor belt the windings of the linear motor comprising hollow tubes for the passage of cooling water from a suitable supply in
- 105 which in operation primary currents of the order of thousands of amperes are fed through the primary windings, the heat generated by these high primary currents being substantially dissipated by the cooling water, and in which the pole pitch of the motor is of the order of 5cms to enable efficient sorting of the
- 110 non-ferromagnetic metal from the mixture of non-ferromagnetic material on the conveyor belt.
2. A metal sorting apparatus as claimed in claim 1 in which the windings of the linear motor are
- 115 terminated in electrical isolation means 208, 210 on each side of the motor to isolate the electrical current from the water supply.
3. A metal sorting apparatus as claimed in claim 1 in which the linear induction motor means primary
- 120 member has a toothed core in which the width of each tooth (a) is less than 30% of the tooth pitch (b).
4. A metal sorting system as claimed in Claim 1 or Claim 2 in which said means for feeding a mixture of non-ferromagnetic material on to said conveyor
- 125 belt comprises means to allow only material within predetermined limit sizes on to said conveyor belt.
5. A metal sorting system as claimed in Claim 4 in which said means for feeding a mixture of non-ferromagnetic material on to said conveyor belt
- 130 further comprises an electromagnet for extracting

any pieces of ferromagnetic material from an initial mixture of material and further means for removal of small pieces below a predetermined size.

6. A metal sorting system as claimed in Claim 1 or Claim 2 in which a further linear induction motor means is associated with said conveyor belt at a position downstream from said first linear induction motor means and in which in operation said first linear induction motor means is operated at a frequency and power to remove a selected portion of said non-ferromagnetic material from said conveyor belt and said second linear induction motor means is operated at a frequency and power to remove a further selected portion from the remaining non-ferromagnetic material.

7. A metal sorting system as claimed in Claim 6 in which the further linear motor induction means is located underneath the conveyor belt and in which third reception means is provided adjacent said conveyor belt for reception of material forced from said conveyor belt by said second linear induction motor means.

8. A metal sorting system as claimed in Claim 6 in which the further linear induction motor means is mounted adjacent the end of the conveyor in a position vertically below the end of the conveyor belt such that non-magnetic material remaining on said conveyor belt after removal of a portion of said material by said first linear induction motor means falls freely past said further linear induction motor means, fourth reception means situated substantially vertically below the end of said conveyor belt and fifth reception means situated to one side of the fourth reception means in a position to receive material deflected by said further linear induction motor means when energised.

9. A metal sorting system as claimed in Claim 8, in which the further linear induction motor means is a double sided linear induction motor and in which the material falls between the two halves.

10. A metal sorting system as claimed in Claim 9 in which a deflector plate is situated adjacent said further linear induction motor means to direct the material deflected by the motor into an associated hopper.

11. A metal sorting system as claimed in Claim 1 or Claim 2 in which the width of the linear induction motor is substantially less than the width of the conveyor and including deflector means situated upstream from the linear induction motor to confine the passage of material to the width of conveyor covered by the linear induction motor.

12. A metal sorting system as claimed in Claim 1 or Claim 2 in which the conveyor belt is installed so as to be along its length at an angle with respect to the horizontal.

13. A metal sorting system as claimed in Claim 1 in which said means for feeding the mixture of non-ferromagnetic material onto the conveyor belt includes means for flattening the pieces of material.

14. A metal sorting system as claimed in Claim 1 in which the linear induction motor means is positioned such that the axis of the motor is at an angle with respect to the conveyor.

Printed for Her Majesty's Stationery Office, by Croydon Printing Company Limited, Croydon, Surrey, 1983.
Published by The Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from which copies may be obtained.



* C L M S *