

SEALING SHEET

ABSTRACT

The present invention provides a sealing sheet mainly composed of an adhesive sheet, wherein
5 the adhesive sheet comprises a core film and an adhesive layer formed on both surfaces of the core film, and the core film shows a relaxation rate of not less than 10% as measured by the following bending-stress relaxation rate measurement test, and a tensile strength of not less than

10 35N/10 mm:

[bending-stress relaxation rate measurement test]

(1) a core film is cut into a tape (width 20 mm, length 100 mm), the tape is rolled to form a loop with one surface thereof being inside, one end (10 mm) of the rolled tape is
15 laid on top of the other and fixed with an adhesive tape to give a loop sample,

(2) the loop sample is put on a balance, and pressed with a flat plate surface of the jig such that the distance between the flat plate surface and the balance is 20 mm to deflect the
20 loop sample, and

(3) from the start of pressing, the weight of the loop sample is measured by the balance, a ratio of the weight of the loop sample at 60 seconds from the start of pressing to the weight of the loop sample at 0 second therefrom is calculated based
25 on the following calculation formula, and the obtained rate is taken as the relaxation rate.

$$\text{relaxation rate (\%)} = (1 - (F_{60} - W) / (F_0 - W)) \times 100$$

F_0 : weight at 0 second from the start of pressing

F_{60} : weight at 60 seconds from the start of pressing

30 W: sample weight

Fig.1