

Abstract of invention

The present invention provides cement composition including 100 parts by weight of binder (B) including, 5-30 parts
5 by weight of cement, 0-20 parts by weight of silica fume, 0-50 parts by weight of fly ash, and 42-75 parts by weight of blast furnace slag; water (W) equivalent to 80-185 kg/m³ of water content per unit volume of concrete; aggregate (A); and chemical admixture for concrete (AD).

10

Figure 1