

AIRCRAFT PLASTICS REPAIR

Area of the Invention

This invention relates to the area of plastic and other synthetic materials and to the repair of these materials. In particular the invention relates to a means for repairing the interior components of aircraft.

Background to the Invention

It is common for the various interior fittings of aircraft to become damaged over time with use.

Most of these fittings, whether actual components such as seats, trays and the like or alternatively veneers for surfaces, are manufactured from some synthetic material or plastic approved for use in aircraft. These fittings while not including structural airplane components have an unpleasant visual effect if damaged even if the damage is of a minor nature such as scratching.

Unfortunately the synthetic materials can be difficult to repair in a visually aesthetic fashion however the alternative of replacing each damaged item is very costly.

For example, while it may appear desirable to repair a damaged component with fibreglass type materials because of the advantage of laying a mat layer over a crack, in this situation it is not appropriate as these surfaces act to release epoxy resins and the like.

Outline of the Invention

It is the object of this invention to provide a means whereby damaged non structural components in the interior of an aircraft may be repaired to a standard that does not derogate from the appearance the components.

The invention in one aspect is a process for the repair of materials used in the manufacture of non structural aircraft interior components which includes the laying of fibreglass material over a damaged surface and adhering it to the damaged surface with a glue of the "instant glue" variety.

The invention in a second aspect is a means of removing pen and pencil marks from materials used in the manufacture of non structural aircraft interior components.

It is preferred that the instant glue variety used be a cyanoacrylate type material.

It is further preferred that the cyanoacrylate material include Loctite® both in the form of Loctite® liquid super glue and Loctite® gel.

It is also preferred that the fibreglass material used be of a mat form. It is further preferred that the mat used have an adhesive backing to provide a bond with an underlying surface.

It is further preferred that such a backing could include synthetic rubber-acrylic compound elastomeric -adhesive resin which can flexibly adhere fibreglass mat to a substrate. The precise type of fibreglass used whether with a backing or not or the type of adhesive backing used is however not restricted in the invention.

In order that the invention may be more readily understood we shall describe by way of non limiting example specific embodiments of the invention.

Brief Description of an Embodiment of the Invention

As previously stated the invention provides a process for the repair of non structural interior components of an aircraft.

Such components, whether being veneered surfaces which are scratched or trays and the like which have breaks or cracks in them, are generally constructed or surfaced with synthetic materials which can be difficult to repair.

Many glues available do not adhere well to plastics and synthetics. From the point of providing a well distributed join and smooth repair it may seem advantageous to cover a break or the like with fibreglass mat of some variety however these materials are commonly bonded using epoxy resins which do not adhere well to synthetics.

Given that glues of the "instant glue" or "super glue" type can be used to bond to a wide variety of substrates it would be desirable to use these products however they are not alone suitable for the repair of deep cracks, breaks or extensively damaged surfaces.

The invention involves the use of a combination of these materials. For example fibreglass mat which is penetrable by a glue can be used to cover a damaged surface. Glue such as Loctite® which can be delivered as a liquid from a tube can be squeezed onto the fibreglass mat where it will pass through and bond to an underlying surface.

In the invention the preferred type of fibreglass material to be used is a fibreglass mesh having an adhesive backing, which can adhere well to a plastic or other such

surface, which is of the type often used to cover discontinuities in materials such as plasterboard.

For additional strength it is often also preferred the a plurality of layers of this material be used over each other. No particular alignment of the mesh is required as the glue used can pass through it to the surface.

The final lay up or repair may also be finished, prior to colouring the surface, using a Loctite® Tac Pac® product sprayed on with an atomiser or the like.

Where a particularly deep scratch is encountered it may preferred that a Loctite® gel, or other such product, be used to fill the scratch prior to being repaired as described above.

The invention also includes a means of removing pen and pencil marks from materials used in the manufacture of non structural aircraft interior components and in particular synthetic leather type materials.

This can be effected using a compound such as Loctite 7452™ which is a cyanoacrylate activator consisting of acetone and amine which is customarily used to ensure rapid fixturing however we have found it to be useful in removing the above mentioned marks.

A fine brush is stroked lightly over the marked area repeatedly until the pen mark becomes faded. The synthetic leather is then dabbed lightly with a clean cloth and allowed to dry before the process is repeated until the pen mark is unnoticeable

It is important at this stage not to rub the synthetic leather with the cloth as this will cause the surface of the synthetic leather to release from its cloth backing instantly thereby causing a hole to appear.

When the synthetic leather has dried it is preferably sprayed with an approved aviation cleaner and wiped lightly over the previously marked areas to remove any halo effect which may have appeared whilst washing out the pen mark.

In some cases it may be necessary to repeat this process several times to achieve a good result, depending on the composition of the ink in the pen which caused the mark. The synthetic leather will however shrink back to its original look once the effects of the chemical have evaporated from the material. This method has been found to be most effective on removing ball point pen marks.

Clearly many repairs to the interior fittings of aircraft can be carried out using a combination of fibreglass and "instant glue" type products and surface finished to blend with the untouched parts of these fittings.

This process is not as such restricted to any particular range of commercially available products however any of these, if of the appropriate type, may be used in the repair process.

The invention described here provides a unique means for repairing synthetic surfaces and fittings in an aircraft interior and while we have described here specific embodiments of the invention it is to be understood that variations and modifications in these can be made without departing from the spirit and scope of the invention.

The claims defining the invention are as follows:

1. A process for the repair of materials used in the manufacture of non structural aircraft interior components which utilises the application of cyanoacrylate type material and/or cyanoacrylate activator to a damaged underlying surface.
2. A process as claimed in claim 1 which includes the steps of:
 - laying fibreglass material over an underlying damaged surface;
 - and adhering it to the damaged surface with a glue of the "instant glue" variety being a cyanoacrylate type material.
3. A process as claimed in claim 2 wherein the cyanoacrylate material includes Loctite® both in the form of Loctite® liquid super glue and Loctite® gel.
4. A process as claimed in any one of claims 1 to 3 wherein the fibreglass material used is of a fibreglass mat form.
5. A process as claimed in claim 5 wherein the mat used has an adhesive backing to provide an initial bond with an underlying surface.
6. A process as claimed in claim 5 wherein the adhesive backing is a synthetic rubber-acrylic compound elastomeric -adhesive resin which can flexibly adhere fibreglass mat to a substrate.
7. A process as claimed in claim 1 wherein pen and pencil marks are removed from synthetic leather type materials using a compound such as a cyanoacrylate activator.

8. A process as claimed in claim 7 which includes the steps of:
 - Using a fine brush to lightly stroke the cyanoacrylate activator over the marked area repeatedly until the pen mark becomes faded;
 - and dabbing the synthetic leather lightly with a clean cloth and allowing to dry;
 - repeating the process until the pen mark is unnoticeable;
9. A process as claimed in claim 8 wherein once the synthetic leather has dried it is sprayed with an approved aviation cleaner and wiped lightly over the previously marked areas to remove any halo effect which may have appeared whilst washing out the pen mark.
10. A process as claimed in claim 9 wherein the cyanoacrylate activator is a compound comprised of acetone and amine.