

ABSTRACTLAMINATED MULTILAYER THICK-FILM ACTUATORFIELD OF THE INVENTION

5

A process for producing a multilayer actuator comprising the steps of:

- (a) forming alternate piezoelectric or electrostrictive ceramic layers and electrode layers on a substrate to form a laminate body comprising a plurality of piezoelectric or electrostrictive ceramic layers and a plurality of electrode layers, each electrode layer being interposed between two ceramic layers;
- 10 (b) applying isostatic pressure to the laminate body; and
- (c) firing the laminate body.

Figure 1



G00002



162162