

SG 9600767-9
ETMP'S COPY

REPLACED SHEETS		SG
☒ Description	: paged 4... to paged 7...	
☒ Claim(s)	: paged 21... to paged 24...	
☐ Drawing(s)	: paged to paged	
☒ Abstract	: paged 25... to paged	

SA9-93-014

1

TRANSDUCER-SUSPENSION ASSEMBLY
FOR A MAGNETIC STORAGE DEVICE

The present invention relates to a transducer-suspension assembly for a magnetic storage device.

5 Moving magnetic storage devices, especially magnetic disk drives, are the memory device of choice. This is due to their expanded non-volatile memory storage capability together with a relatively low cost. Accurate retrieval of the stored information from these devices becomes critical, requiring the magnetic transducer to be positioned as close to
10 the storage media as possible. Optimally, the transducer may actually contact the media.

Magnetic disk drives are information storage devices which utilize at least one rotatable magnetic media disk having concentric data tracks defined for storing data, a read/write transducer for reading the data
15 from or writing the data to the various data tracks, a support means, generally referred to as a slider, for supporting the transducer adjacent the data tracks typically in a flying mode above the storage media, a suspension assembly for resiliently supporting the slider and the transducer over the data tracks, and a positioning actuator coupled to
20 the transducer/slider/suspension combination for moving the transducer across the media to the desired data track and maintaining the transducer over the data track center line during a read or a write operation. The transducer is attached to or is formed integrally with the slider which supports the transducer above the data surface of the storage disk by a
25 cushion of air, referred to as an air bearing, generated by the rotating disk. Alternatively, the transducer may operate in contact with the surface of the disk. The suspension provides desired slider loading and dimensional stability between the slider and an actuator arm which couples the transducer/slider/suspension assembly to the actuator. The
30 suspension is required to maintain the transducer and the slider adjacent the data surface of the disk with as low a loading force as possible. The actuator positions the transducer over the correct track according to the data desired on a read operation or to the correct track for placement of the data during a write operation. The actuator is
35 controlled to position the transducer over the desired data track by shifting the combination assembly across the surface of the disk in a direction generally transverse to the data tracks.

In conventional disk drives, the transducer and the slider are formed separately and then attached to the suspension in a manual, operator controlled precision operation. Typically, these components are extremely small and the positioning of each relative to the other is critical and must be exact. During operation of the disk drive, the transducer must be exactly positioned relative to the data track, which in turn means that the suspension must be exactly positioned onto the slider. The suspension must also provide flexibility to pitch and roll motion for the slider relative to the direction of motion of the rotating disk and yet at the same time provide resistance to yaw motion. Electrical conductor leads connected to the transducer signal input/output terminals are directed along the suspension and connected to an amplifier placed on the suspension or on the actuator. The conductor leads must not add to the spring stiffness of the slider while providing good electrical interconnection: The conductor leads are generally bonded by soldering or ultrasonic bonding, for example, to both the transducer output terminals and the amplifier manually by an operator.

While magnetic recording of information is enormously successful, there is an ever increasing need to improve recording density. In the present state of the art the popular method of magnetic recording has been longitudinal recording. More recently, magnetic recording techniques have turned to considering vertical recording as compared to longitudinal recording as a means for improving the linear density of recorded information. In vertical recording, the magnetic polarity of the recorded bits is oriented vertically or perpendicularly with respect to the recording media surface. The magnetic flux from a recording head write pole tip passes vertically through the magnetic storage medium, then downstream (or upstream) within the storage disk and back through the magnetic medium to a return pole which forms the flux return path for the magnetic head. The flux return pole has a pole face many times larger than the write pole tip so that the flux passing into the flux return pole is disbursed therealong and hence the flux density is low. Because the density of the flux passing through the recording medium at the return pole is low, there is very little effect by way of reversing or weakening any magnetic patterns in the recording medium downstream of the write pole tip.

As discussed above, the transducer, mounted on a slider, is supported above the relatively moving recording media surface by an air

bearing. The performance of magnetic recording systems improve dramatically as the separation between the read/write transducer and the recording medium decreases. Additionally, decreasing the separation between the read/write transducer and the recording medium provides

5 improved track density, the number of data tracks that can be defined on the media surface, as well as the recorded data linear density in an individual data track. However, as the flying height is reduced, the risk of head wear, and in particular, the potential for the transducer to inadvertently contact the disk surface incurring catastrophic wear

10 increases greatly. In recording systems designed to operate with the read/write transducer/slider in contact with the media, the wear may be minimized by the proper selection of both slider and medium surface materials relating to hardness, coefficient of friction, thermal conductivity, etc. The wear between two surfaces in rubbing or sliding

15 contact is also a significant function of the area of contact between the two surfaces and the applied load and inertial forces. While the actual area of contact is significantly less than the area of the surfaces involved, actual contact taking place only at microscopic asperities in the surfaces, reduction of the size and mass of the slider enables a

20 significant reduction in the local pressure greatly reducing wear between the surface of the slider and the medium.

To this end there have been disclosed a variety of mechanisms which utilize an integrated "REED" approach to fabricating the transducer/slider/suspension assembly. Structured to work in a

25 perpendicular or vertical magnetic recording environment, these devices permit the head and suspension to be easily manufactured having: (i) precise control of component elements utilizing thin film vacuum deposition techniques, (ii) precise formation of air bearings to achieve specified flying heights, (iii) bonding of sliders to suspensions, and,

30 (iv) easy routing of conductor leads.

U.S. Patent Nos. 5,041,932; 5,073,242; and 5,111,351 entitled "Integrated Magnetic Read/Write Head/Flexure/Conductor Structure" granted to Harold J. Hamilton disclose an integral magnetic

transducer/suspension/conductive structure having the form of an elongate

35 dielectric flexure or suspension body with a magnetic read/write transducer embedded within at one end thereof. In a preferred embodiment, Hamilton discloses an elongate, dielectric flexure body of aluminum oxide having a magnetic pole structure and helical coil



SA9-93-014

4

integrally formed at one end of the flexure body with embedded copper conductor leads running the length of the flexure body to provide electrical connection for the transducer. The integral structure is fabricated utilizing conventional vapor deposition and photolithography techniques. The integral transducer/suspension structure disclosed by Hamilton may be used in a contact recording system or in a system where the transducer flies above the storage medium on a cushion of air.

Contact recording provides greater recording density and achieves higher read signals and greater resolution unregulated by variations in flying height. However, the wear associated with prior art contact recording is generally not acceptable. While Hamilton, cited above, discloses an integrated transducer/suspension assembly with greatly reduced mass and size, the disclosed perpendicular head requires fabrication processing in two orthogonal planes which creates processing problems and greatly complicates the manufacturing process.

In accordance with the present invention, there is now provided a transducer-suspension assembly for a magnetic storage device, the assembly comprising: an elongated resilient member formed of a dielectric material and having a first end and a second end, said elongated member shaped to have a suspension portion and a transducer portion, said transducer portion disposed at the first end of said elongated member; magnetic transducer means embedded in said elongated member at said transducer portion and having at least a vertically oriented first magnetic pole tip, said magnetic pole tip extending to and exposed at an air bearing surface defined on an exterior surface of said transducer portion of said elongated member; and an electrical conductor having access on an exterior surface of said elongated member and magnetically communicating with said magnetic transducer means.

Viewing the present invention from a second aspect, there is now provided an integral, unitary magnetic transducer and suspension assembly comprising: a horizontal first magnetic pole piece; a slanted, vertically oriented magnetic pole tip, said pole tip extending to and exposed at an air bearing surface; a second magnetic pole piece magnetically coupling said first pole piece to said vertically oriented pole tip, said second pole piece joined magnetically to said vertically oriented pole tip at an upper portion thereof, said first and second pole pieces magnetically connected at a backgap region; a coil inductively coupled to but

electrically isolated from said first and second pole pieces, said coil
operatively associated with said pole pieces and said pole tip; and
suspension means including at least one layer of a resilient material
covering said first and second pole pieces and said coil, said suspension
5 means electrically and magnetically isolated from said magnetic pole
pieces and pole tip, said resilient material extending beyond said
backgap region.

Viewing the present invention from a third aspect, there is now
provided a method for fabricating a magnetic transducer-suspension
10 assembly comprising the steps of: forming a cavity in the surface of a
substrate, said cavity having slanted sidewalls forming a predetermined
angle with the plane of the substrate surface; forming a first wear layer
of a wear resistance material over said substrate; forming a slanted
vertically oriented magnetic pole tip of a magnetic material on at least
15 one of the slanted sidewalls of said cavity, said slanted pole tip
defining an angle with the plane of the substrate surface substantially
equal to said sidewall angle; forming a second wear layer over said
magnetic pole tip and said first wear layer; forming a horizontal first
magnetic pole piece of a magnetic material over said second wear layer;
20 forming an insulation layer over said first pole piece; forming a coil of
an electrically conductive material in said insulation layer, said
insulation layer electrically insulating said coil from said first pole
piece and said pole tip; forming a second pole piece of a magnetic
material, said second pole piece magnetically coupling said vertically
25 oriented pole tip to said horizontal first pole piece, said second pole
piece magnetically joined to an upper end of said vertically oriented
pole tip, said first and second pole pieces being magnetically connected
at ends remote from said pole tip at a magnetic backgap, said magnetic
backgap extending through said coil, said insulation layer electrically
30 said second pole piece from said coil; and forming a suspension member of
a dielectric material, said suspension member including at least one
layer of dielectric material covering said second pole piece, said
insulation layer and said coil and extending beyond said magnetic
backgap.

35 The present invention thus provides an enhanced magnetic moving
storage device having a integrated transducer/suspension structure that
includes an enhanced read/write transducer configuration.





SA9-93-014

6

The head-suspension structure of the present invention is especially suitable for vertical magnetic recording.

Also, the structure of the present invention is suitable for use in a contact recording environment.

- 5 Still furthermore the present invention provides an integrated transducer/suspension assembly which is suitable for batch processing in planes parallel to the surface of the initial wafer or substrate.

In a preferred embodiment of the present invention, there is provided an integrated, unitary suspension and magnetic transducer
10 assembly for use with perpendicular or vertical recording media which can be adapted for contact recording as well as for flying above the recording media. Preferably a substrate is first patterned and etched to provide a cavity therein for formation of the REED assembly wear pad and the magnetic head vertical pole tip. A release layer is then deposited
15 over the substrate and the individual thin film layers comprising the transducer and suspension sections are deposited. Horizontal coil conductors are inductively coupled to the transducer magnetic yoke structure and are connected to lead terminals formed at the end of the suspension section opposite the end at which the transducer is formed.
20 The coil lead conductors and lead terminals are plated at the same time as the coil conductors and are encapsulated in the suspension section forming an integral element of the REED assembly. The transducer and suspension section layers are deposited on a process support substrate wafer in rows. The substrate is removed by dissolving the release layer
25 to leave an integrated transducer/suspension assembly produced by batch fabrication.

In a partially preferred embodiment of the integrated REED assembly according to the present invention, the transducer section of the assembly comprises separate read and write heads, each head optimized for
30 its particular function. For example, the read head is constructed to have a narrow read magnetic pole tip while the write head has a relatively wide write magnetic pole tip. In the track width direction, the write wide, read narrow aspect of the invention minimizes the effect of spindle runout and intertrack interference. In one embodiment, the
35 read head comprises a magnetoresistive sensor located remote to the AES and disposed in a gap formed in a magnetic yoke structure having the read

pole tip adapted to conduct magnetic flux to the MR sensor. The remote MR read sensor location makes track width independent of sensor length for narrow track sensor optimization. The remote location of the MR sensor away from the ABS eliminates design and operational problems
5 associated with corrosion and wear, for example, present at the ABS.

Since the probe or pole tip of the vertical recording transducer is fabricated first, relatively high temperature annealing processes may be utilized prior to formation of the remaining transducer elements in subsequent process steps. This permits the use of temperature-critical
10 materials and processes in subsequent fabrication steps without danger of adverse effects resulting from required annealing processes.

Additionally, the planar deposition arrangement in accordance with the present invention permits all processing of the transducer and suspension sections to be performed on a wafer surface. This allows
15 batch production of the transducer and suspension sections as a unitary assembly.

Still another advantage of the present invention is the use of wear resistant material in the transducer structure and at the ABS. This protects the pole tip regions of the transducer and may be localized
20 through patterning of the ABS to create a favorable air bearing loading condition for use in a flying environment.

Preferred embodiments of the present invention will now be described with reference to the accompanying drawings, wherein:

Fig. 1 is a top view illustrating a magnetic recording mechanism
25 having a rotary actuator and incorporating the integrated REED transducer/suspension of the present invention;

Fig. 2 is a cross-sectional view of an integrated REED transducer/suspension assembly in accordance with the present invention;

Fig. 3 is a cross-sectional view illustrating a preferred
30 embodiment of an integrated REED transducer/suspension assembly in accordance with the present invention;

Fig. 4 is a top plan view of the REED assembly shown in Fig. 3;

Fig. 5 is a cross-sectional view illustrating the probe tip and contact pad after wear-in for the REED assembly shown in Figs. 3 and 4;



Fig. 6 is a view in perspective of the air bearing surface of the REED assembly shown in Figs. 3 and 4 adapted for flying above the recording media;

Fig. 7 is a top plan view of a wafer illustrating batch processing of the REED assembly shown in Figs. 3 and 4 in accordance with the present invention;

Figs. 8a-8i are cross-sectional views illustrating the processing steps involved in the manufacture of the preferred embodiment of the present invention shown in Figs. 3, 4, 5 and 6;

Fig. 9 is a cross-sectional view illustrating a second preferred embodiment of an integrated REED transducer/suspension assembly in accordance with the present invention;

Fig. 10 is a top plan view of the REED assembly shown in Fig. 9;

Figs. 11a and 11b are cross-sectional views illustrating the probe tip and contact pad after separation and after wear-in, respectively, for the REED assembly shown in Figs. 9 and 10;

Fig. 12 is a cross-sectional view illustrating a third preferred embodiment of an integrated REED transducer/suspension assembly in accordance with the present invention;

Fig. 13 is a top plan view of the REED assembly shown in Fig. 12; and

Figs. 14a and 14b are cross-sectional views illustrating the probe tip and contact pad after separation and after wear-in, respectively, for another embodiment of the REED assembly shown in Figs. 12 and 13.

DESCRIPTION OF THE PREFERRED EMBODIMENT

The preferred embodiments of the present invention are preferable for use in high density direct access storage devices such as found in large information storage systems as well as in the single disk files typically used in personal computers. The devices, e.g., disk drives or files, may use magnetic memory disks as the media.

Referring now to Figs. 1 and 2, a magnetic storage system including a housing 11 in which is mounted a rotary actuator 13, one or more associated magnetic storage disks 15 mounted on a spindle 17 and a drive means (not shown) coupled to spindle 17 for rotating the disk 15 is shown. The rotary actuator 13 moves an integrated REED transducer/suspension assembly 19 in accordance with the present invention in an arcuate path across the surface of the storage disk 15.

The rotary actuator 13 includes a voice coil motor comprising a coil 21 movable within the magnetic field of a fixed permanent magnet assembly 23. An actuator arm 25 having the moving coil 21 formed on one thereof is pivotably mounted on pivot post 27. A support arm 29 is attached to the other end of the actuator arm 25 and projects across the surface of the disk 15. The support arm 29 supports the integrated REED transducer/slider/suspension assembly 19 produced according to the procedure set forth herein in cantilever fashion over the surface of the disk 15. The REED assembly 19 includes a suspension section 31 and a transducer/slider 33 (as shown in Fig. 2) formed at one end integral with the suspension section 31. The suspension section 31 supports the transducer/slider 33 above the surface of the disk 15 on a bearing or cushion of air generated by the rotation of the disk 15. While for a particular application the specific dimensions are chosen for optimum performance, in general the REED assembly 19 will have an overall length in the range of about 5 to 20 millimeters (mm), a maximum width in the range of about 0.3 to 2.0 mm, a maximum thickness of about 20 to 50 micrometers (μm) in the suspension section 31 and about 30 to 65 μm in the transducer section 33 and a total mass in the range of about 200 micrograms to 1.5 milligrams. Alternatively, the suspension section 31 may support the transducer/slider 33 in contact with the disk media 15. The surface of the slider parallel to and adjacent the disk surface is referred to as the air bearing surface (ABS). It includes both configurations where the slider is designed to fly above the disk, sometimes referred to as a winchester-type drive, and where the slider is designed to contact the recording media, the disk 15, during operation. As described in more detail below, in a contact recording application, the slider may also be referred to as a wear or contact pad.

While only one disk 15 and one actuator arm 25 are shown, it is understood that the magnetic storage system 10 may comprise a number of magnetic storage disks 15 wherein the actuator arm 25 includes a plurality of support arms 29 with each arm 29 supporting at least one integral REED transducer/suspension assembly 19, each REED assembly 19 associated with a surface of one of the disks 15. Thus, disk 15 also has a REED assembly 19 mounted to an arm 29 of the actuator arm 25 on the underside of the disk 15. Further, other combination assemblies are associated with the top and bottom sides of other disks, the transducer access of which is controlled by the actuator 13.

The suspension section 31 of the REED transducer/suspension assembly 19 provides a load on the transducer/slider 33 which is substantially normal or perpendicular to the surface of the disk 15. This perpendicular load maintains the transducer/slider 33 in contact
5 with the data surface of the disk 15 when the disk 15 is not being rotated. During operation of the disk drive 10 a aerodynamic lifting force is generated between the transducer/slider 33 ABS and the rotating disk 15 opposing the perpendicular load applied to the transducer/slider 33 causing the transducer/slider 33 to fly above the disk surface.
10 Alternatively, in contact recording, during rotation of the disk 15, the transducer/slider 33 remains in contact with the media for reading or recording data.

During operation, the transducer/slider 33 is moved to the desired track of a plurality concentric data tracks defined on the data surface
15 of the disk 15 by means of the actuator 13. The moveable coil 21 is controlled by positioning signals to move within the magnetic field of the magnet assembly 23 and thus pivot the actuator arm 25 about the pivot post 27. Because it is desired to provide rapid access of the transducer/slider 33 from one track to another track for read or write
20 operations, it is necessary that the transducer be properly positioned over the desired track and reach that track in a minimum amount of time. It should be noted that while the actuator 13 illustrated in Fig. 1 is a rotatory actuator, other disk drive systems may utilize a linear actuator such as is known in the art. The REED assembly 19 must provide radial
25 stiffness, and have substantial flexibility about the pitch and roll axes as it rides above the data surface of the disk 15. If desired, an integrated circuit amplifier assembly 35 may also be produced on the suspension section 31 of the integrated REED assembly 19.

Referring now also to Figs. 3, 4 and 5, a preferred embodiment of
30 the integrated REED transducer/suspension assembly 40 according to the principles of the present invention is illustrated. The integrated REED transducer/transducer structure 40 comprises an elongated generally rectangular body 39 of a dielectric material such as aluminum oxide (Al_2O_3) or silicon dioxide (SiO_2), for example, having a relatively
35 uniform thickness along most of its length forming a suspension section 31 and a somewhat greater thickness at one end, the left hand end as shown, wherein a magnetic read/write transducer or head 33 is formed and a slider air bearing surface (ABS) is patterned on a lower side thereof.

As mentioned above, the term ABS refers to the side of the slider which is generally parallel to and adjacent the media surface in both winchester-type disk files and contact recording applications. As shown in Fig. 2, the ABS comprises a shaped protrusion 37 formed on the lower side of the REED assembly body 39, preferably forming a wear or contact pad for contact recording applications. Alternatively, the shaped protrusion 37 can form a slider having an ABS patterned to generate a lifting force (as shown in Fig. 6) when relative motion exists between the REED assembly 19 and the media disk 15 to allow the slider to fly closely above the media surface. The shaped protrusion 37 and its surface are formed of a suitable material, such as diamond-like carbon, for example, to minimize wear and damage when the REED assembly contacts the media surface.

The read/write transducer 33 is formed integrally with the suspension section 31 to provide an integrated and unitary REED assembly 40. In the preferred embodiment, the transducer is a dual-purpose read/write head 33 and comprises a vertical probe-type magnetic inductive head for perpendicular recording applications, but can alternatively comprise a ring-type magnetic inductive head utilized in horizontal recording applications as described in co-pending U.S. Patent Application Serial No. 08/002,290 filed on January 8, 1993 and hereby incorporated by reference as if fully set forth herein. The read/write head 33 includes a magnetic circuit comprising an upper magnetic yoke or pole piece 43 magnetically coupled to a vertical probe or pole tip 49 at a front stud 51 and to a lower magnetic yoke or pole piece 45 at a back-gap 47. The vertical pole tip 49 is formed parallel to the protrusion 37 wall and intersects the ABS at an acute angle with respect to a vertical axis through the ABS. The pole tip 49 is generally rectangularly shaped having a relatively small cross-sectional area to concentrate the magnetic flux and provide a high flux density write signal at the recording media 15. The width of the pole tip 49 at the ABS is traverse to the data tracks and is selected to define the desired data track width. The lower magnetic pole 45 forms the return path for the head magnetic circuit. The lower magnetic pole 45 is shaped to have a relatively large surface and cross-sectional area and to provide a low flux density return path. Inductively coupled to the magnetic yoke structure is a horizontal spiral coil 41, with the ends of the coil connecting through lead conductors 53 extending the length of the suspension section 31 to terminal bonding pads 55. Bonding pads 55

provide terminals for coupling the transducer 33 to external circuitry, such as amplifier 35 (as shown in Fig. 1).

In a preferred embodiment, the integral REED assembly 40 comprises a body 39 of Al_2O_3 having a length of 12 mm, a width of 0.5 mm and a thickness of 35 μm for that portion of the body 39 forming suspension section 31 and maximum thickness of 50 μm for the read/write head section 33. The integral REED assembly 40 is fabricated utilizing well-known deposition and photolithography techniques on a base substrate or wafer, as described in greater detail below, utilizing a release layer to separate the finished REED assembly from the substrate. The upper and lower magnetic yokes 43 and 45 are of nickel-iron alloy (NiFe), generally referred to as permalloy, or other suitable magnetic material, such as iron (Fe), nickel (Ni) and cobalt (Co) or their alloys, and are preferably plated as is well-known in the art. Similarly, the coil windings 41, lead conductors 53 and terminal bonding pads 55 are also formed of copper (Cu) or gold (Au), for example, by plating techniques. Manufacturability of this embodiment is greatly simplified in that the vertical pole tip 49 is first fabricated and various annealing processes completed prior to the remaining portions of the REED assembly 40 being fabricated in layers parallel to the supporting substrate by conventional, well-known techniques. Once the REED assembly 40 has been formed and separated from the process supporting substrate, a portion of the wear-resistance material covering the lower portion of the protrusion 37 is removed by a wear-in or post-fabrication lapping process to expose the vertical pole tip 49 at the ABS as shown in Fig. 5.

Referring now also to Fig. 6, a plan view of the ABS of the REED assembly shown in Fig. 3 adapted to fly above the recording media 15 is shown. The ABS formed on the bottom surface of the protrusion 37 comprises a pair of rails formed along opposing sides of the protrusion 37 substantially parallel to the direction of the air flow as indicated by arrow 58 generated by the relative motion between the REED assembly and the disk 15. wear pad 59 formed between the rails 57 provides support and protection from abrasive wear for the vertical pole tip 49 exposed at the surface thereof. Rails 57 and wear pad 59 are fabricated from a suitable wear resistant material such as diamond-like carbon, for example. As described with reference to Fig. 5, at the completion of the REED assembly fabrication process, the surface of the protrusion 37 is subjected to a lapping process which removes a portion of the wear

resistant material planarizing the tops of the rails 57 and the wear pad 59 and exposing the pole tip 49

Referring now to Figs. 7 and 8a-8i, Fig. 7 is a plan view of the deposition surface of the process supporting substrate wafer 70.

- 5 Individual REED assemblies 73 are batch fabricated in rows 71 on the surface of the wafer 70, the width of the row 70 being equal to the desired length of the completed REED assembly body 39. The entire fabrication process, with the exception of the post-fabrication lapping or wear-in process, comprises a series of process steps accomplished at
- 10 the wafer level. Figs. 8a-8i are cross-sectional views illustrating the processing steps involved in the fabrication of a preferred embodiment of the present invention incorporating the vertical read/write head 33 shown in Fig. 3.

- First, as seen in Fig. 8a, a layer of photoresist (not shown) is
- 15 deposited over the entire surface of the substrate wafer 70 and patterned. Then, for each REED assembly 73 cavity 75 having slanted sidewalls 77 is formed or etched in the substrate 70, by laser, ion, chemical or mechanical etching, for example. The cavity 75 forms a template for the subsequent formation of the wear pad 37. A separation
- 20 or release layer 79 is then deposited by sputter deposition, for example, over the substrate 70. The release layer 79 can be a single layer of a suitable material, such as Cu, for example, or may also include additional thin film layers (not shown) of titanium (Ti) or chromium (Cr) serving as adhesion layers. The release layer 79 allows the completed
- 25 REED assembly 73 to be separated from the substrate 70 at the conclusion of the batch processing. A first wear layer 81 of wear resistant material is deposited on the substrate 70 over the release layer 79 and patterned coating the bottom and slanted sidewalls 77 of cavity 75. Alternatively, as shown in Fig. 8b, cavity 75 may be formed by etching a layer of
- 30 suitable material, such as alumina (Al_2O_3), for example, deposited over the surface of the substrate 70. First, a patterned etch stop 76 is formed on the substrate 70. The etch stop material is preferably a thin layer of Cr or tantalum (Ta) formed by sputter deposition or evaporation. Next, an alumina layer 78 is deposited onto substrate 70 to a thickness
- 35 equal to the desired depth of the cavity 75. Following the deposition of the alumina layer 78, a via is etched into the alumina down to the etch stop layer 76 creating the cavity 75 and a template for the subsequent formation of the wear pad 37.

Next, as seen in Figs. 8c and 8d, the vertical pole tip 83 is patterned and formed over a portion of the first wear layer 81 on the cavity sidewall 77. The vertical pole tip 83 is preferably of NiFe, or other suitable magnetic material, and may be sputter-deposited or
5 electro-plated as is known in the art. A second wear layer 85 is now patterned and formed over the first wear layer 81 and the vertical pole tip 83. Sufficient material is deposited to fill the cavity 75 which serves as the wear pad in the finished REED assembly. At this point in the fabrication process, or immediately after its formation, required
10 annealing steps and other high temperature processes for optimizing the electrical and magnetic characteristics of the vertical pole tip 49 may be completed.

Next, as illustrated in Fig. 8e, a first layer 87 of dielectric material, such as Al_2O_3 , is deposited over the entire structure forming
15 the first of several layers of material comprising the REED assembly body and suspension section. The first dielectric layer 87 forms a surface for the deposition of the lower magnetic pole piece 91 and is patterned and etched to open via 88 exposing the upper surface of the vertical pole tip 83. As seen in Fig. 8f, a layer of photoresist is formed over the
20 first dielectric layer 87 and patterned. The lower magnetic pole piece 91 and the vertical pole tip connection pad or stud 89 are formed by plating, for example, as is known in the art.

Next, as shown in Figs. 8g and 8h, photoresist is deposited over the first dielectric layer 87 and patterned and hard baked to provide a
25 first insulation layer 95 for formation of the head coil. The first insulation layer 95 provides a surface for the formation of the electrical coil 97 and electrically insulates the coil from the magnetic pole piece 91 and pole tip 83 structure. The coil conductors 97 are then plated or otherwise deposited on the surface provided by the first
30 insulation layer 95. A layer of photoresist is then deposited over the coils 97 and the insulation layer 95, patterned and hard baked to provide a second insulation layer 99. The end coil conductor 98 is not covered by the second insulation layer 99b, but is left exposed for forming a connection to a leadout conductor and terminal. A layer of NiFe, or
35 other suitable magnetic material, is then plated or otherwise deposited as is known in the art over the front portion of the second insulation layer 99a to form the upper magnetic pole piece 101. The upper magnetic

pole piece 010 is connected to the vertical pole tip 83 stud 89 and lower magnetic pole piece 91 through vias 96.

The final series of process steps, as seen in Fig. 8i, comprise a second layer 103 of dielectric material deposited over the upper magnetic pole piece 101 and the rear portion of the second dielectric layer 99b covering and encapsulating the completed read/write head, and leaving a via 104 open to the end coil conductor 98. This second dielectric layer is about one-half the remaining desired thickness of the suspension section 31. A leadout conductor 105 is then deposited and patterned electrically connecting the coil 97 at conductor 98 to a conductor terminal 55 (as shown in Fig. 3) formed at a remote end of the conductor 105 through via 104. A final dielectric layer 107 is then deposited over the second dielectric layer 103 encapsulating the leadout conductor 105 and building up the assembly body to the desired thickness.

To separate the completed REED assemblies 73, the final dielectric layer 111 is coated with a photoresist layer which is patterned to define the external dimensions of the assembly body 39 (as shown in Fig. 2). The dielectric layer 111 is then wet etched in a basic solution to form and separate the individual REED transducer/suspension assemblies from each other on the wafer 70 surface. To separate the completed transducer/suspension assemblies from the substrate 70, the release layer 79 between the substrate 70 and the first dielectric layer 87 is dissolved as is known in the art.

With continuing reference to Figs. 7 and 8a-8i, the wafer substrate 70 can be of any suitable material known to those in the art, such as alumina-titanium-carbide (AlTiC) or silicon, for example. The use of single-crystal Si is preferred in that it provides precise control of the cavity sidewall 77 angle. For example, a <100> oriented Si wafer anisotropically etched in a basic solution, KOH, for example, provides a sidewall 77 angle along the <110> plane of 54.7 degrees with respect to the horizontal plane.

The release layer 79 formed on the substrate 70 serves several purposes. The release layer 79 is a sacrificial layer which is eventually dissolved to free the finished transducer/suspension assemblies 73 from the substrate 70. The release layer 79 can, for instance, be an electrically conductive material and thereby serve as a

seed or plating base layer for the subsequent layers deposited utilizing plating techniques, such as the pole pieces of the transducer. Likely candidates for the release layer 79 are NiFe or Cu which could be deposited through a sputtering or plating process. The release layer 79
5 may also serve as a barrier layer, or alternatively, a separate barrier layer may be formed over the release layer 79.

The barrier layer (not shown) similarly serves several functions in the production process. The barrier layer is used to isolate the subsequently deposited layers from the release layer 79. The barrier
10 layer serves as an etch stop to terminate the wet etch process utilized to separated the individual REED assemblies 73 from each other in the wafer rows 71, as described above. The barrier layer also serves as an etch stop to protect the vertical pole tip from any etchant which may be later used to dissolve the release layer 79. The barrier layer may also
15 be used as a wear layer to protect the vertical pole tip during operation in close proximity to a rotating magnetic media. If the barrier layer is not to be used as a wear layer, it is desirable to remove it after the release layer 79 is dissolved.

A thin film deposition process, such as sputter deposition, is
20 utilized for fabrication of the vertical pole tip 81. While Fig. 6c illustrates the vertical pole tip 81 slanted at the angle formed by the cavity 75 slanted sidewalls 77, the slanted vertical pole tip 81 is not restricted to the angle shown. The slope of the slanted vertical pole tip can be any acute angle of 45 to 90 degrees with respect to the ABS
25 as shown in Fig. 5. Since the vertical pole tip 81 is the first transducer element to be formed in the fabrication process, relatively high temperature annealing processes may be employed to optimize the magnetic characteristics of the pole tip 81 without danger of adverse effects on other transducer elements to be fabricated in process steps
30 subsequent to the heat treatment processes. For example, forming the first and second insulation layers 95 and 113 after the pole tip 83 heat treatment processes allows a polyimide material to be used, such as hard-baked photoresist which has a maximum exposure temperature of approximately 250 degrees C, rather than an amorphous dielectric
35 material, such as alumina, for example. It should be noted that, with the exception of the wear-in process to expose the vertical pole tip, the entire REED assembly fabrication process is completed at the wafer level with no mechanical processing steps. For example, there are no lapping

steps required. The final surface 109 or the final dielectric layer 107 (as shown in Fig. 8i) of the REED assembly is not lapped, but rather follows the contours of the transducer components and the leadout conductors which the layer 107 covers. Since the portion of the surface area which deviates from being flat comprises only a small percentage of the total area of surface 109, the performance of the REED assembly suspension is not adversely affected. In addition to reduction of the number of process steps and process complexity, the elimination of any lapping or other mechanical processing steps minimizes stress induced in the REED assembly during fabrication.

Referring now to Figs. 9, 10, 11a and 11b, a second preferred embodiment of an integrated REED transducer/suspension assembly 120 formed in accordance with the present invention is shown. The REED assembly 120 formed on a substrate 121 over separation layer 122 comprises an elongated rectangular-shaped, resilient body 123 forming a suspension section 125 and a transducer section 127. In this embodiment, the transducer comprises separate read and write heads. A first vertical probe-type write head 129 and a second vertical probe-type read head 131 are formed adjacent one another having their vertical pole tips 143 and 141, respectively, extending parallel to the slanted sidewalls of the wear pad 140 in opposed, facing relationship. The two heads are fabricated in a series of process steps similar to that described above with respect to Figs. 8a-8i. Inductively coupled to the magnetic yoke for each head 129, 131 is a separate horizontal coil 133, 135, respectively, optimized for the purpose of the respective heads. The coils 133, 135 are connected to pairs of connection terminals 137 via lead conductors 139. The lead conductors 139 are plated during the REED assembly fabrication process and run the length of the suspension section 125. Similarly, the materials used and the dimensions of the read magnetic circuit and the write magnetic circuit are chosen to optimize the magnetic characteristics for the read or write function. For example, the width and cross-sectional area of the read head vertical pole tip 141 are substantially smaller than that of the write head vertical pole tip 143.

Figs. 11a and 11b illustrate the structure of the wear pad 140 for this preferred embodiment. During fabrication, the vertical pole tips 141, 143 for both the read head 131 and the write head 129 are initially formed as a single magnetic layer 149 sandwiched between the first and

second wear layers 145 and 147. Dimensional and material differences between the two pole tips 141, 143 are adjusted at the time of the layer deposition using well-known photoresist patterning and etch techniques prior to the deposition of the second wear layer 147. As described
5 above, the second wear layer 147 is etched to open vias 151 to allow subsequent forming of studs to couple the read head magnetic yoke and the write head magnetic yoke to their respective vertical pole tip 141 and 143. Once the fabrication process is complete and the REED assembly 120 is released from the substrate 121 by dissolution of the release layer
10 122, the wear pad 140 is lightly lapped to remove the bottom horizontal portions of the first wear layer 145 and the magnetic layer 149 to form the AES and separate and expose the read and write pole tips 141 and 143, respectively.

Referring now to Figs. 12, 13, 14a and 14b, a third preferred
15 embodiment of an integrated REED transducer/suspension assembly 160 formed in accordance with the present invention is shown. The Reed assembly 160 formed on a substrate 161 over separation layer 162 comprises an elongated rectangular-shaped, resilient body 163 forming a suspension section 165 and a transducer section 167. In this embodiment,
20 the transducer comprises separate read and write heads. A vertical probe-type write head 169 and a magnetoresistive (MR) read head 171 incorporating magnetic circuit 172 which serves as a magnetic flux guide for the MR element 175 are formed adjacent one another having vertical pole tips 183 and 181, respectively, extending parallel to the slanted
25 sidewalls of the wear pad 180 in opposed, facing relationship. The two heads are fabricated in a series of process steps similar to that described above with respect to Figs. 8a-8i. Inductively coupled to the magnetic yoke for the write head 169 is a horizontal coil 173 optimized for a write only function. The coil 173 is connected to a pair of
30 connection terminals 177 via lead conductors 179. The read head 171 includes a magnetic yoke structure 172 magnetically coupled to the read vertical pole tip 181 by stud 174 through via 191. The read yoke structure 172 conducts magnetic flux to an MR sensor element located remotely from the AES. The MR sensor element 175 is preferably position
35 immediately adjacent a gap 182 formed in the read yoke structure 172 and magnetically connects the end ports of the yoke forming the gap 182. The MR element 172 is typically a thin film of NiFe or other suitable magnetic magnetoresistive material. While shown spaced apart slightly from the read yoke 172, the MR element 172 can alternatively be in

contact with the end portions of the read yoke forming the gap 182. The MR element 175 is preferably formed on a planarized alumina layer. While the MR sensor element 175 is shown as a single layer, it should be noted that the MR sensor 175 will typically comprise a multilayered structure including various layers for biasing and stabilizing the MR sensor. The MR sensor element 175 is connected to a pair of lead terminals 176 by lead conductors 178. The lead conductors 178, 179 are plated during the REED assembly fabrication process and run the length of the suspension section 125. The materials used and the dimensions of the read magnetic circuit and the write magnetic circuit are chosen to optimize the magnetic characteristics for the read or write function. For example, the width and cross-sectional area of the read head vertical pole tip 181 are substantially smaller than that of the write head vertical pole tip 183. The remote location of the MR sensor 175 provides important design freedom so that performance can be optimized. For example, with a remotely located MR sensor, track width is a function of the read pole tip dimensions and is independent of the MR sensor length.

Figs. 14a and 14b illustrate the structure of the wear pad 180 for this preferred embodiment. During fabrication, the vertical pole tips 181, 183 for both the read head 171 and the write head 169 are initially formed as a single magnetic layer 189 sandwiched between the first and second wear layers 185 and 187. As shown in Figs. 14a and 14b, the MR sensor element 175 can alternatively be located adjacent a gap 182 formed in the read pole tip 181 structure. Similarly, as in the configuration shown in Figs. 12 and 13, the MR sensor element is located remotely from the ABS and utilizes the read pole tip 181 and read yoke structure 172 to conduct the magnetic flux. Dimensional and material differences between the two pole tips 181, 183 are adjusted at the time of the layer deposition using well-known photoresist patterning and etch techniques prior to the deposition of the second wear layer 187. As described above, the second wear layer 187 is etched to open vias 191 to allow subsequent forming of studs to couple the read head magnetic yoke and the write head magnetic yoke to their respective vertical pole tip 181 and 183. Once the fabrication process is complete and the REED assembly 160 is released from the substrate 161 by dissolution of the release layer 162, the wear pad 180 is lightly lapped to remove the bottom horizontal portions of the first wear layer 185 and the magnetic layer 189 to form the ABS and separate and expose the read and write pole tips 181 and 183, respectively.

While the invention has been particularly shown and described with reference to preferred embodiments thereof, it will be understood by those skilled in the art that various changes in form and detail may be made therein without departing from the spirit and scope of the invention. Although the suspension portions of the present invention are preferably composed of sputter-deposited alumina, it is recognized that other methods of deposition may be employed and that other materials may be utilized, including other suitable oxides, nitrides, carbonides, glasses, amorphous carbon, diamond-like carbon or laminated combinations of suitable conducting and insulating materials. The suspension section according to the preferred embodiments could be a dual layer of a polyimide material and a metal layer deposited thereon to provide sufficient resiliency and stiffness as required by a suspension assembly. It is also well understood that many electrically conductive materials are available to form the conductive circuitry and the transducer leads. Copper or gold is the preferred conductive material but many others are available as is well known in the art.



SA9-93-014

21

CLAIMS

1. A transducer-suspension assembly for a magnetic storage device, the assembly comprising:
- an elongated resilient member formed of a dielectric material and
- 5 having a first end and a second end, said elongated member shaped to have a suspension portion and a transducer portion, said transducer portion disposed at the first end of said elongated member;
- magnetic transducer means embedded in said elongated member at said transducer portion and having at least a vertically oriented first
- 10 magnetic pole tip, said magnetic pole tip extending to and exposed at an air bearing surface defined on an exterior surface of said transducer portion of said elongated member; and
- an electrical conductor having access on an exterior surface of said elongated member and magnetically communicating with said magnetic
- 15 transducer means.
2. An assembly as claimed in Claim 1, including at least one electrical contact pad formed in a surface of said elongated member and electrically communicating with said electrical conductor, said electrical contact pad disposed at the second end of said elongated
- 20 member.
3. An assembly as claimed in Claim 1, comprising a second magnetic pole tip extending to and exposed at said air bearing surface, said second pole tip associated with a read sensor for reading information stored in a magnetic storage medium, said first magnetic pole tip
- 25 associated with a write sensor for recording information in said magnetic storage medium.
4. An assembly as in Claim 3 wherein said write sensor is adapted for effecting vertical magnetic recording of information in said magnetic media, and said read sensor is adapted for reading vertically recorded
- 30 information from said magnetic media.
5. A assembly as claimed in Claim 3 wherein said read sensor comprises an inductive read sensor.
6. An assembly as claimed in Claim 3 wherein said read sensor comprises a magnetoresistive read sensor.





SA9-93-014

22

7. An integral, unitary magnetic transducer and suspension assembly comprising:

a horizontal first magnetic pole piece;

a slanted, vertically oriented magnetic pole tip, said pole tip

5 extending to and exposed at an air bearing surface;

a second magnetic pole piece magnetically coupling said first pole piece to said vertically oriented pole tip, said second pole piece joined magnetically to said vertically oriented pole tip at an upper portion thereof, said first and second pole pieces magnetically connected at a

10 backgap region;

a coil inductively coupled to but electrically isolated from said first and second pole pieces, said coil operatively associated with said pole pieces and said pole tip; and

15 suspension means including at least one layer of a resilient material covering said first and second pole pieces and said coil, said suspension means electrically and magnetically isolated from said magnetic pole pieces and pole tip, said resilient material extending beyond said backgap region.

8. An assembly as claimed in Claim 1 or Claim 7 further comprising a
20 wear pad protruding from an exterior portion of said transducer portion, a lower portion of said wear pad forming said air bearing surface.

9. An assembly as claimed in Claim 7 wherein said slanted vertically oriented pole tip defines an angle with respect to said horizontal first pole piece in the range of 45 degrees to 90 degrees.

25 10. An assembly as claimed in Claim 9 wherein said air bearing surface is formed substantially parallel to said horizontal first pole piece.

11. An assembly as claimed in Claim 7 wherein air bearing surface is adapted for operation in contact with a recording media surface.

12. An assembly as claimed in Claim 7 wherein air bearing surface is
30 adapted for operation in a flying mode suspended above and closely adjacent a recording media surface.

13. An assembly as claimed in Claim 7 wherein transducer and suspension assembly has an overall length in the range of about 5 to 20 millimeters,





SA9-93-014

23

an overall width in the range of about 0.3 to 2.0 millimeters and a thickness in the range of about 20 to sixty-five micrometers.

14. A disk drive assembly comprising:
a housing;
5 at least one magnetic storage media disk mounted in said housing having means for storing data in data tracks provided thereon;
an actuator arm positioned in said housing in proximity to said media disk; and
a transducer-suspension assembly as claimed in any preceding claim
10 coupled to said actuator arm.
15. A method for fabricating a magnetic transducer-suspension assembly, comprising the steps of:
forming a cavity in the surface of a substrate, said cavity having slanted sidewalls forming a predetermined angle with the plane of the
15 substrate surface;
forming a first wear layer of a wear resistance material over said substrate;
forming a slanted vertically oriented magnetic pole tip of a magnetic material on at least one of the slanted sidewalls of said
20 cavity, said slanted pole tip defining an angle with the plane of the substrate surface substantially equal to said sidewall angle;
forming a second wear layer over said magnetic pole tip and said first wear layer;
forming a horizontal first magnetic pole piece of a magnetic
25 material over said second wear layer;
forming an insulation layer over said first pole piece;
forming a coil of an electrically conductive material in said insulation layer, said insulation layer electrically insulating said coil from said first pole piece and said pole tip;
30 forming a second pole piece of a magnetic material, said second pole piece magnetically coupling said vertically oriented pole tip to said horizontal first pole piece, said second pole piece magnetically joined to an upper end of said vertically oriented pole tip, said first and second pole pieces being magnetically connected at ends remote from
35 said pole tip at a magnetic backgap, said magnetic backgap extending through said coil, said insulation layer electrically insulating said second pole piece from said coil; and



forming a suspension member of a dielectric material, said suspension member including at least one layer of dielectric material covering said second pole piece, said insulation layer and said coil and extending beyond said magnetic backgap.



This Sheet Has Been Replaced



ABSTRACT

A magnetic transducer and suspension assembly suitable for use in both contact recording and in winchester-type applications is described. A generally rectangular elongated flat suspension member includes a
5 vertical-type inductive read/write transducer formed integrally with the suspension member and is embedded in one end of the suspension member. The vertical inductive transducer is suitable for vertical recording applications. The transducer vertical magnetic pole tip and magnetic
10 yoke structure are formed at one end of the suspension member with the vertical pole tip extending to and exposed at an air bearing surface formed on the lower surface of a slider-shaped protrusion extending from the lower surface of the end of the suspension member. The integral
transducer/suspension assembly can be adapted for either flying above the
15 recording media or for use in continuous contact with the recording media. The air bearing surface is formed on the lower surface of a wear pad. The fabrication of the transducer/suspension assembly is adapted to be performed at the wafer level.

This Sheet Has Been Replaced






FIG. 1




FIG 2




FIG 3




FIG 4

3/9




FIG 5




FIG 6




FIG 7




FIG 8A




FIG 8B




FIG 8C




FIG 8D




FIG 8F




FIG 8F




FIG 8G




FIG 8H




FIG 8I




FIG 9




FIG. 10




FIG. 11A




FIG. 11B




FIG 12




FIG. 13




FIG. 14A




FIG. 14B

REPLACED SHEETS SG

- ☐ Description : paged to paged
- ☐ Claim(s) : paged to paged
- ☐ Drawing(s) : paged to paged
- ☒ Abstract : paged 25 to paged

25

REPLACEMENT SHEETS SG

- ☐ Description : paged to paged
- ☐ Claim(s) : paged to paged
- ☐ Drawing(s) : paged to paged
- ☒ Abstract : paged 25 to paged

DATE OF RECEIPT 03 JUL '996

TRANSDUCER-SUSPENSION ASSEMBLY FOR A MAGNETIC STORAGE DEVICE

ABSTRACT

A magnetic transducer and suspension assembly suitable for use in both contact recording and in winchester-type applications is described. A generally rectangular elongated flat suspension member includes a vertical-type inductive read/write transducer (33) formed integrally with the suspension member (31) and is embedded in one end of the suspension member. The vertical inductive transducer is suitable for vertical recording applications. The transducer vertical magnetic pole tip (49) and magnetic yoke structure are formed at one end of the suspension member with the vertical pole tip (49) extending to and exposed at an air bearing surface formed on the lower surface of a slider-shaped protrusion extending from the lower surface of the end of the suspension member. The integral transducer/suspension assembly (40) can be adapted for either flying above the recording media (15) or for use in continuous contact with the recording media (15). The air bearing surface is formed on the lower surface of a wear pad. The fabrication of the transducer/suspension assembly (40) is adapted to be performed at the wafer level.

FIG. 3

This is the replacement sheet

Date: 3 JUL 1996

This Sheet Has Been Replaced



DATE OF RECEIPT 1-12-1997

integrally formed at one end of the flexure body with embedded copper conductor leads running the length of the flexure body to provide electrical connection for the transducer. The integral structure is fabricated utilizing conventional vapor deposition and photolithography techniques. The integral transducer/suspension structure disclosed by Hamilton may be used in a contact recording system or in a system where the transducer flies above the storage medium on a cushion of air.

Contact recording provides greater recording density and achieves higher read signals and greater resolution unregulated by variations in flying height. However, the wear associated with prior art contact recording is generally not acceptable. While Hamilton, cited above, discloses an integrated transducer/suspension assembly with greatly reduced mass and size, the disclosed perpendicular head requires fabrication processing in two orthogonal planes which creates processing problems and greatly complicates the manufacturing process.

SUMMARY OF THE INVENTION

It is an object of the present invention to ameliorate one or more disadvantages of the prior art.

According to one aspect of the present invention there is provided an integral, unitary magnetic transducer and suspension assembly comprising: an elongated resilient member formed of a dielectric material and having a first end and a second end, said elongated member shaped to have a suspension portion and a transducer portion, said transducer portion disposed at the first end of said elongated member and including a wear pad protruding from an exterior portion thereof, a lower surface of said wear pad defining an air bearing surface; magnetic transducer means embedded in said elongated member at said transducer portion, said magnetic transducer means comprising: a first vertically-oriented magnetic pole tip, said first magnetic pole tip extending to and exposed at said air bearing surface, said first magnetic pole tip forming a portion of a magnetic write sensor only for magnetically recording information in a magnetic storage media; and a second vertically-oriented magnetic pole tip, said second magnetic pole tip

extending to and exposed at said air bearing surface adjacent said first magnetic pole tip, said second magnetic pole tip forming a portion of a magnetic read sensor only for reading information magnetically stored in said magnetic storage media; and at least one electrical conductor associated with each of said magnetic write and magnetic read sensors, said electrical conductor embedded in said elongated member and having access on an exterior surface of said elongated member for providing electrical connection to said magnetic write and magnetic read sensors.

According to another aspect of the present invention there is provided a method for fabricating an integral, unitary magnetic transducer and suspension assembly comprising the steps of: forming a cavity in the surface of a substrate, said cavity having slanted sidewalls forming a predetermined angle with the plane of the substrate surface; forming a first wear layer of a wear resistance material over said substrate, said first wear layer covering the slanted sidewalls of said cavity; forming a slanted vertically oriented magnetic pole tip of a magnetic material on at least one of the slanted sidewalls of said cavity, said slanted pole tip defining an angle with the plane of the substrate surface substantially equal to said sidewall angle; forming a second wear layer over said magnetic pole tip and said first wear layer; forming a horizontal first magnetic pole piece of a magnetic material over said second wear layer; forming an insulation layer over said first pole piece; forming a coil of an electrically conductive material in said insulation layer, said insulation layer electrically insulating said coil from said first pole piece and said pole tip; forming a second pole piece of a magnetic material, said second pole piece magnetically coupling said vertically oriented pole tip to said horizontal first pole piece, said second pole piece magnetically joined to an upper end of said vertically oriented pole tip, said first and second pole pieces being magnetically connected at ends remote from said pole tip at a magnetic backgap, said magnetic backgap extending through said coil, said insulation layer electrically insulating said second pole piece from said coil, said pole tip first and second pole pieces and coil forming a magnetic transducer; and forming a suspension member of a dielectric material, said suspension member including

at least one layer of dielectric material covering and encapsulating said magnetic transducer, said layer of dielectric material extending beyond said magnetic backgap.

According to still another aspect of the present invention there is provided a method for fabricating an integral, unitary magnetic transducer and suspension assembly wherein an elongated resilient member includes a suspension section and a transducer section, said transducer section encapsulating a magnetic read sensor and a magnetic write sensor, said transducer section having a wear pad protruding from an exterior portion thereof, said wear pad defining an air bearing surface, said method comprising the steps of: forming a cavity in the surface of a substrate, said cavity having a bottom and slanted sidewalls, said sidewalls forming a predetermined angle with the plane of the substrate surface; forming a first wear layer of a wear resistant material over said substrate, said first wear layer covering the cavity bottom and sidewalls; forming a magnetic write sensor including forming a first vertically-oriented pole tip of a magnetic material on one of said slanted sidewalls of said cavity, said first pole tip defining an angle with the plane of the substrate surface substantially equal to the sidewall angles, said first pole tip associated with said magnetic write sensor; forming a magnetic read sensor including forming a second vertically-oriented pole tip of a magnetic material on a different one of said slanted sidewalls of said cavity, said second pole tip defining an angle with the plane of the substrate surface substantially equal to the sidewall angle, said second pole tip associated with said magnetic read sensor; forming a second wear layer over said first and second pole tips, said second wear layer filling said cavity; and forming a suspension member of a dielectric material, said suspension member including at least one layer of dielectric material covering and encapsulating said magnetic read and write sensors, said layer of dielectric material extending beyond said magnetic read and write sensors forming an elongated suspension member.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

Preferred embodiments of the present invention will now be described with reference to the accompanying drawings, wherein:

Fig. 1 is a top view illustrating a magnetic recording mechanism having a rotary actuator and incorporating the integrated REED transducer/suspension of the present invention;

Fig. 2 is a cross-sectional view of an integrated REED transducer/suspension assembly in accordance with the present invention;

Fig. 3 is a cross-sectional view of illustrating a preferred embodiment of an integrated REED transducer/suspension assembly in accordance with the present invention;

Fig 4 is a top plan view of the REED assembly shown in Fig. 3;

Fig 5 is a cross-sectional view illustrating the probe tip and contact pad after wear-in for the REED assembly shown in Figs. 3 and 4;

CLAIMS

1. An integral, unitary magnetic transducer and suspension assembly comprising:

an elongated resilient member formed of a dielectric material and having a first end and a second end, said elongated member shaped to have a suspension portion and a transducer portion, said transducer portion disposed at the first end of said elongated member and including a wear pad protruding from an exterior portion thereof, a lower surface of said wear pad defining an air bearing surface;

magnetic transducer means embedded in said elongated member at said transducer portion, said magnetic transducer means comprising:

a first vertically-oriented magnetic pole tip, said first magnetic pole tip extending to and exposed at said air bearing surface, said first magnetic pole tip forming a portion of a magnetic write sensor only for magnetically recording information in a magnetic storage media; and

a second vertically-oriented magnetic pole tip, said second magnetic pole tip extending to and exposed at said air bearing surface adjacent said first magnetic pole tip, said second magnetic pole tip forming a portion of a magnetic read sensor only for reading information magnetically stored in said magnetic storage media; and

at least one electrical conductor associated with each of said magnetic write and magnetic read sensors, said electrical conductor embedded in said elongated member and having access on an exterior surface of said elongated member for providing electrical connection to said magnetic write and magnetic read sensors.

2. An integral, unitary magnetic transducer and suspension assembly as in claim 1 wherein said wear pad is formed of diamond-like carbon.

3. An integral, unitary transducer and suspension assembly as in claim 1 wherein:

said magnetic write sensor includes a first lower magnetic pole piece formed substantially parallel to said air bearing surface, and a first upper magnetic pole piece magnetically coupling said first lower magnetic pole piece to an upper portion of said



first magnetic pole tip, said first lower and upper magnetic pole pieces magnetically connected at a first backgap region; and

said magnetic read sensor includes a second lower magnetic pole piece formed substantially parallel to said air bearing surface, and a second upper magnetic pole piece magnetically coupling said second lower magnetic pole piece to an upper portion of said second magnetic pole tip, said second lower and upper magnetic pole pieces magnetically connected at a second backgap region.

4. A magnetic disk drive system including the unitary transducer and suspension assembly as claimed in claim 1 further including:

a housing;

at least one magnetic storage media disk mounted in said housing and having means for storing information in data tracks defined thereon;

means for moving said magnetic media disk; and

means mounted in said housing for supporting said unitary magnetic transducer and suspension assembly in a transducing relationship with respect to the magnetic media in response to movement of said magnetic media disk.

5. An integral, unitary transducer and suspension assembly as in claim 1 further including at least one electrical contact pad associated with each of said electrical conductors formed in a surface of said elongated member and electrically communicating with said electrical conductor, said electrical contact pad disposed at the second end of said elongated member.

6. An integral, unitary transducer and suspension assembly as in claim 1 wherein said write sensor is adapted for effecting vertical magnetic recording of information in said magnetic media, and said read sensor is adapted for reading vertically recorded information from said magnetic media.

7. An integral, unitary transducer and suspension assembly as in claim 1 wherein said read sensor comprises an inductive read sensor.



8. An integral, unitary transducer and suspension assembly as in claim 1 wherein said read sensor comprises a magnetoresistive read sensor.

9. A method for fabricating an integral, unitary magnetic transducer and suspension assembly comprising the steps of:

forming a cavity in the surface of a substrate, said cavity having slanted sidewalls forming a predetermined angle with the plane of the substrate surface;

forming a first wear layer of a wear resistance material over said substrate, said first wear layer covering the slanted sidewalls of said cavity;

forming a slanted vertically oriented magnetic pole tip of a magnetic material on at least one of the slanted sidewalls of said cavity, said slanted pole tip defining an angle with the plane of the substrate surface substantially equal to said sidewall angle;

forming a second wear layer over said magnetic pole tip and said first wear layer;

forming a horizontal first magnetic pole piece of a magnetic material over said second wear layer;

forming an insulation layer over said first pole piece;

forming a coil of an electrically conductive material in said insulation layer, said insulation layer electrically insulating said coil from said first pole piece and said pole tip;

forming a second pole piece of a magnetic material, said second pole piece magnetically coupling said vertically oriented pole tip to said horizontal first pole piece, said second pole piece magnetically joined to an upper end of said vertically oriented pole tip, said first and second pole pieces being magnetically connected at ends remote from said pole tip at a magnetic backgap, said magnetic backgap extending through said coil, said insulation layer electrically insulating said second pole piece from said coil, said pole tip first and second pole pieces and coil forming a magnetic transducer; and

forming a suspension member of a dielectric material, said suspension member including at least one layer of dielectric material covering and encapsulating said



magnetic transducer, said layer of dielectric material extending beyond said magnetic backgap.

10. The method as in claim 9 wherein the step of forming a suspension member includes the step of forming an electrical conductor having access on an exterior surface of said suspension member remote from said coil, said electrical conductor for coupling said coil to external circuitry, said electrical conductor insulated from said first and second pole pieces and said pole tip.

11. The method as in claim 10 including the step of forming at least one electrical contact on said exterior surface of said suspension member, said electrical conductor coupled to said at least one electrical contact.

12. The method as in claim 9 including the step of providing a release layer covering the surface of said substrate and said sidewalls and bottom of said cavity, said release layer deposited prior to said step of forming said first wear layer.

13. The method as in claim 12 including the step of releasing said unitary magnetic transducer and suspension assembly from said substrate.

14. The method as in claim 12 wherein said release layer is of copper or nickel-iron.

15. A method for fabricating an integral, unitary magnetic transducer and suspension assembly wherein an elongated resilient member includes a suspension section and a transducer section, said transducer section encapsulating a magnetic read sensor and a magnetic write sensor, said transducer section having a wear pad protruding from an exterior portion thereof, said wear pad defining an air bearing surface, said method comprising the steps of:

forming a cavity in the surface of a substrate, said cavity having a bottom and slanted sidewalls, said sidewalls forming a predetermined angle with the plane of the substrate surface;

forming a first wear layer of a wear resistant material over said substrate, said first wear layer covering the cavity bottom and sidewalls;



forming a magnetic write sensor including forming a first vertically-oriented pole tip of a magnetic material on one of said slanted sidewalls of said cavity, said first pole tip defining an angle with the plane of the substrate surface substantially equal to the sidewall angles, said first pole tip associated with said magnetic write sensor;

forming a magnetic read sensor including forming a second vertically-oriented pole tip of a magnetic material on a different one of said slanted sidewalls of said cavity, said second pole tip defining an angle with the plane of the substrate surface substantially equal to the sidewall angle, said second pole tip associated with said magnetic read sensor;

forming a second wear layer over said first and second pole tips, said second wear layer filling said cavity; and

forming a suspension member of a dielectric material, said suspension member including at least one layer of dielectric material covering and encapsulating said magnetic read and write sensors, said layer of dielectric material extending beyond said magnetic read and write sensors forming an elongated suspension member.

16. The method as in claim 15 wherein the step of forming a suspension member includes the step of forming an electrical conductor having access on an exterior surface of said suspension member remote from said magnetic write and read sensors, said electrical conductor for coupling said magnetic write and read sensors to external circuitry, said electrical conductor insulated from said first and second pole tips.

17. The method as in claim 16 including the step of forming at least one electrical contact on said exterior surface of said suspension member, said electrical conductor coupled to said at least one electrical contact.

18. The method as in claim 15 wherein said magnetic read sensor comprises a magnetoresistive sensor.



* C L M S *

TRANSDUCER-SUSPENSION ASSEMBLY FOR A MAGNETIC STORAGE DEVICE

ABSTRACT

A magnetic transducer and suspension assembly suitable for use in both contact recording and in winchester-type applications is described. A generally rectangular elongated flat suspension member includes a vertical-type inductive read/write transducer (33) formed integrally with the suspension member (31) and is embedded in one end of the suspension member. The vertical inductive transducer is suitable for vertical recording applications. The transducer vertical magnetic pole tip (49) and magnetic yoke structure are formed at one end of the suspension member with the vertical pole tip (49) extending to and exposed at an air bearing surface formed on the lower surface of a slider-shaped protrusion extending from the lower surface of the end of the suspension member. The integral transducer/suspension assembly (40) can be adapted for either flying above the recording media (15) or for use in continuous contact with the recording media (15). The air bearing surface is formed on the lower surface of a wear pad. The fabrication of the transducer/suspension assembly (40) is adapted to be performed at the wafer level.

FIG. 3

