

METHOD AND DEVICE FOR ROLLING METAL STRIPS

The invention pertains to a method for manufacturing metal strips by rolling.

- 5 It is generally known to produce different thickness profiles of the strip by using mills. However, in a case of strip width like more than 650 mm it is difficult to manufacture by ordinary mills.

In the description of the process patent EP 1 074 317 B1, a duo- and quarto-mill
10 is mentioned. The patent describes the process of flexible rolling with a quarto or a duo mill. In dependence of the content is focused on the control engineering, measurement systems and the bending of the work roll in dependence to the roll gap setting. The control engineering is divided into the phases of steering and controlling. The steering phase is characterized by the
15 immediate adjustment of the roll gap, so that the transition between two thicknesses (edge) will be achieved. In contrast, during the phase of controlling the flatness and thickness are controlled in minimum one loop (plateau). The flatness is influenced by the bending of the work rolls in a defined relation. The flatness is measured by an optical laser system or a stressometer roll. The
20 patent of EP 1074317 describes the bending of the working rolls. Furthermore it is important to get an utilizable flatness for the following plants after the cold rolling mill.

The patent JP 61-172603 discloses to obtain a different-thickness rolling stock
25 in flatness and yield. That is done by lowering the number of revolutions of rolls and controlling roll crowns in accordance with a load variation at the time of changing a roll gap.

In the patent application JP 61-172603 the operation mode is not able to define
30 the rolling gap with a direct measurement. The method of flexible rolling is based on the working with the position of the hydraulic cylinder, which transmits the force with the ratio of the angular relationship of all axles and rolls. That

control process is not connected to the bending during flexible rolling and thus plays significant role during the rolling procedure.

The flatness controlling of the process is mentioned in Patent US 8050792 B2
5 with a known flatness profile, the rolling mill can be provided with a flatness control system that is based on the measured flatness profile and a given target or reference flatness profile computes set points to the available control devices, achieving closed-loop flatness control and connected to the development of their stressometer rolls. It is well known that measurement can
10 be done for example by laser, optical or non-contact techniques.

The invention is based on the flexible rolling of a metallic strip profile, in which the operating concept mode is based on two steps. The first step is called learning phase, which is based on the controlling and storing the parameter
15 values during rolling. The stored parameter values consisting of the thickness and flatness data (positions of the hydraulic adjustment and the flatness actuators) of the strip and those are collected during the learning phase.

The second step to achieve the defined tolerances is called a program-loop, where the values are achieved from the first stage as starting values.

20

The first step is only for the determination of the parameter set by the learning phase and the second step is the loop for flexible rolling, which is primarily based on the parameters from the first step i.e. by the program-loop to have the start values from the first phase. As a final result the rolling process has the
25 program-loop for collecting, optimizing and using the data through the flexible rolling process. It is possible to use for example a Sendzimir mill for achieving the process steps.

In the second step the special core element is the "learning phase", which
30 allows to react to the strip specific properties and defined profile with different thicknesses over the length of the strip during the manufacturing. Furthermore this process ensures to have a fast control process and it is able to achieve the

tolerances by the first profile. The invention is based on the bending of the work rolls, which is depending on the forces like it is mentioned in Patent JP 61-172603 and likewise not on the setting of the rolling gap. The bending stage is divided into two separate sections. The first section is the presetting which is
 5 based on already rolled strips which are stored in a database or a manual setting by the operators. After that the controlled part is to get switched on when the flatness measurement is able to deliver data from the rolling process.

In the invention the described bending process is not based on other
 10 parameters than the integrated flatness steering process which is influenced by the rolling forces, which is connected to the setting of the rolling. The invention furthermore influences on the bending of the work rolls but slightly in a different way. The reason for that is the Sendzimir mills and the concept of flexible rolling use different stored settings of the actuators for bending at the different
 15 thicknesses.

The differences compared to the generally known mills for the flexible rolling of a metallic strip are wider in the invention, which has a greater width, where the area is possible to cover width range of 400 to 1600 mm.

20

By the method of manufacturing metal strips by flexible rolling of profile the invention is to increase the production depth in automotive, transportation industry where is need for weight reduction. Furthermore structure components, container, tank or exhaust systems are possible to manufacture by this
 25 invention. Regarding the implementation of weight reduction, which consists of component integration, thickness reduction in areas with less load and stress oriented component design thickness or strength. These are very important tasks, when needed to reduce emissions.

30 In individual cases rolling procedure of a metallic strip profile is used by Quarto-Mills and due to that is needed to have a bigger diameter of the working rolls compared to Sendzimir design, where it is possible to use significantly smaller

diameters of the working rolls. The benefit of that is to cold roll grades with a higher strength and quality demands like flatness.

A mill structure can consists for example of 20 rolls like in a Sendzimir mill. In that case the eccentric adjustment of four rolls A/B/C/D or only two rolls A/D or
 5 B/C can be used to influence the flatness of the strip. The eccentric adjustment consists of 5-7 bearings, which could be adjusted individually. The adjustment range of each bearing is about +/- 40 mm in the case of ZR22-55. Other mills have a larger adjustment range especially mills up to 1600 mm width. In addition the flatness could be influenced by the first intermediates. They could
 10 be shifted transversal to the rolling direction. The displacement path is between 50-300 mm.

The invention reduces, due the width of strip significantly, the amount of scrap and enables better possibilities of nesting which shortens process times in
 15 further processing. The Sendzimir-mill requires totally different control engineering in contrast to the construction of a duo or quarto-mill.

Manufacturing metal strips by the flexible rolling profile enables the phase of controlling the thickness and adjusts the work roll bending. Furthermore for a
 20 use a part of the edge can be used for the evaluation of the plateau based on the area integral.

The bending of the working rolls depends on the needed working force to roll a specific grade. The steering is based on the reference variables of the flatness measurement system which is allocated to different conditions (thickness/force).
 25

The objective of the invention is also to attain with a device for manufacturing metal strips features by a rolling stand which contains several rolls, wherein at least one upper and at least one lower roll adjoin the upper and the lower surface of the metal strip under the influence of pressure, and wherein the wider
 30 width is more than 650 mm to be produced on the metal strip. During the manufacturing process a strip profile with different thicknesses over the length

of the strip is achieved. The defined profile can consist of two, three or more different thicknesses over the length of the strip. Essential features of the inventive device are disclosed in the attached claims.

5 On the contrary to the prior art, the bending process of the invention is connected to the forces of the rolling process and steered in dependence of the transition time and not based on other parameters, in particular. Stainless steel and other metals therefore can be processed by means of rolling, particularly cold-rolling, in a continuous operation, wherein width range of 400 and 1600
10 mm can be realized.

This is achieved with a different cold rolling mill type, where the differences are the number of rolls and actuators (hydraulic adjustment, crowns, first intermediates) to influence the thickness and flatness.

15 The existing standard process is focused on a consistent thickness above the strip length in close tolerance limits. In contrast to that, the flexible rolling is characterized by different thicknesses in short distances but none the less in close tolerance limits. One profile which is normally between 500 and 2000 mm long repeats continuously above the length of the strip. This process requires
20 continuous highly dynamic changes of the cold rolling mill. Hereinafter the key issues to implement the process are mentioned. In addition the control engineering takes the characteristic of the mill type into account and permits faster regulation of the process. Furthermore the specific properties of every strip profile are considered because the bending of the work roll is not
25 depending on the rolling gap.

As in the prior art, it is also possible to utilize multi-roll rolling stands such as, for example, Sendzimir rolling stands in order to technically realize the corresponding metal strips.

30

The following principle applies in this respect: the softer the metallic material of the metal strip, the smaller the number of rolls used may be chosen. The typical

metallic materials are consisting for example of copper, aluminum, stainless steel or steel.

The object of the invention makes it possible to form metal strips consisting, in particular, of stainless steel and other metals with the aid of a continuous rolling process, particularly a single-pass or multi-pass cold-rolling process, preferably in a multi-roll stand, so that is possible to roll a profile in rolling direction.

There are also possibilities to manufacture a metal strip by rolling to the industry areas like for automotive or transportation industry, and further in building industry.

An exemplary embodiment of the object of the invention is illustrated in the drawings and described in greater detail below. In these drawings:

15

Fig. 1 shows a schematic diagram of rolling stands for profiling a metal strip and the geometry definition of the flexible rolled strip.

Fig. 2 shows a schematic diagram of a metal strip that is wound up on a coil with subsequent cold deformation and another coiling operation and measuring of the plateau to control the process.

Fig. 1 shows a schematic diagram of the rolling stands. A metal strip is produced by a Sendzimir mill in a width range of 400 and 1600 mm which is recurring above the length of the strip. The concept of the invention is especially focused on flexible rolling. The existing standard process is focused on a consistent thickness above the strip length in close tolerance limits. In contrast to that, the flexible rolling is characterized by different thicknesses in short distances but none the less in close tolerance limits. One profile, which is normally between 500 and 2000 mm long repeats continuously above the length of the strip. This process requires continuously highly dynamic changes of the cold rolling mill. The V adjustment increases for example by factor 3,5 because of the spring rate of the mill and this is multiplied by 14-30, preferable

18-26 is the velocity of the hydraulic cylinder. Typical numbers for velocity of the hydraulic cylinder are a range between 0,17 mm/s and 5,83 mm/s, where 0,17 mm/s (rolling gap) → 13,09 mm/s (hydraulic cylinder) and 5,83 mm/s (rolling gap) → 448,91 mm/s (hydraulic cylinder). In a figure 1 is a sketch of a geometry definition after rolling a metallic strip. The steering phase is characterized by the immediate adjustment of the roll gap (edge), so that the transition between two thicknesses will be achieved. In figure 1 during the phase of controlling the thickness is controlled in minimum one loop (plateau). During the controlled phase it is possible to influence the flatness actuators manually. The flatness gets influenced by the bending of the work rolls in a defined relation. The flatness can be measured for example by an optical laser system, a stressometer roll or a SI-Flat System. The process of the roll gap adjustment is steered by switching to a controlled phase during the rolling of the plateau. The use of a following plateau which is already rolled to control the plateau between the working rolls. Furthermore two existing systems are to measure the flatness of the strip. A contactless SI-Flat System can be used, which is based on the evaluation of the local amplitude of oscillation.

Fig. 2 shows the number of rolls and the actuators (hydraulic adjustment, crowns, first intermediates) to influence the thickness and flatness. In addition the control engineering takes the characteristic of the mill type into account and permits faster regulation of the process. Furthermore the specific properties of every metal strip are considered because the bending of the work roll is not depending on the rolling gap. Furthermore the figure shows a defined profile with different thicknesses over the length of the strip. The bending is necessary for the process. By using a 20 roller instead of duo- and quarto-mill the final result will be a flat and higher strength strip. The bending of the working rolls depends on the needed working force to roll a specific grade. The steering of the work roll bending is based on the reference variables of the flatness measurement system, which are determined during the “learning phase”.

CLAIMS

1. A method for manufacturing flexible rolling of metal strips, in which a metal strip with a predefinable material thickness is guided through a mill stand, containing several rolls, wherein the method is based on two operating steps, the first step being a learning phase based on controlling and storing parameter values during rolling in which thickness and flatness data of the metal strip are collected and the second step being a program loop for flexible rolling having the starting values from the first step for providing a metal strip having a defined profile with different thicknesses over the length of the metal strip, wherein the metal strip is set to lead through a roll gap during the rolling operation where bending of the work rolls is steered to achieve the defined profile.
2. The method according to claim 1, wherein the width of the rolled strip is within the range of 400 to 1600 mm.
3. The method according to any one of the preceding claims, wherein the work roll bending is influenced in dependence to the rolling force to influence the flatness.
4. A device for manufacturing metal strips having a width range of 400 – 1600 mm by flexible rolling, comprising a mill stand comprising several rolls, said mill stand being arranged so that at least one upper roll and at least one lower roll provide a roll gap through which a metal strip for flexible rolling is guided whereby the at least one upper roll adjoins the upper surface of the metal strip for flexible rolling and the at least one lower roll adjoins the lower surface of the metal strip, wherein the device is configured to carry out two operating steps, the first step being a learning phase based on controlling and storing parameter values during rolling in which thickness and flatness data of the metal strip are collected and the second step being a program loop for flexible rolling having the starting values from the first step for providing a metal

strip having a defined profile with different thickness over the length of the metal strip, whereby bending of the work rolls is steered to achieve the defined profile.

5. The device according to claim 4, wherein the device has three systems
5 to measure the flatness of the strip.