

WO 01/36527

PCT/US00/27143

FLAME-RETARDED POLYPHENYLENE ETHER COMPOSITION AND

METHOD OF MAKING SAME

BACKGROUND OF THE INVENTION

This application relates to a flame-retarded polyphenylene ether (PPE) compositions and to a method of making same.

PPE is a thermoplastic material with high glass transition temperature, high dimensional stability, low specific gravity, hydrolytic stability and good mechanical performance. This combination of properties allows PPE based formulations to be injected molded into products which are used for high heat applications, for example in the automotive, electrical, and construction industries. For some applications, where increased modulus and strength are required, PPE may be reinforced with glass fibers. However, these reinforced PPE formulations have undesirable flammability characteristics. At high temperature or when exposed to flame, glass-filled PPE tends to burn continuously without extinguishing. Because of this, fire-retarded grades of glass-filled PPE (especially those rated UL94 V0) tend to be formulated using a large amount (for example >15% by weight for a rating of UL94 V0 at 1/16th inch thickness) of fire-retardant additives such as phosphorus-containing organic compounds. This increases the cost of the product, and also makes it more difficult to formulate glass fiber-reinforced PPE to meet UL94 V0 fire-retardant standards, because the addition of large amounts of phosphorus-containing organic compounds like resorcinol diphosphate plasticizes the composition and significantly reduces the heat deflection temperature of the formulation.

SUMMARY OF THE INVENTION

The present invention provides PPE compositions with good fire and flame-retardant characteristics, which utilize lower levels of organophosphate fire-retardant and which therefore do not suffer from the drawbacks of previously known fire-and flame-retardant PPE compositions.

In an aspect of the present invention, there is provided a composition comprising:

- (a) a polymer component comprising at least 50% of a polyphenylene ether;
- (b) glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the polymer component,
- (c) a fire retardant component, wherein the fire retardant is an organophosphate;
- (d) an organoclay component in an amount effective to enhance the flameretardant characteristics of the composition; and
- (e) a mineral component, wherein the mineral component is mica. Other conventional additives utilized in formulation of PPE may be included. This composition can be used in the manufacture of injection molded articles such as electronic components, including television internals such as deflection yokes; printer chassis and plastic pallets.

In another aspect of the present invention, there is provided an injection-molded article formed from a glass fiber-reinforced polyphenylene ether composition, wherein the glass fiber-reinforced polyphenylene ether composition comprises:

- (a) a polymer component comprising at least 50% of a polyphenylene ether;
- (b) glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the polyphenylene ether composition;
- (c) a fire retardant component, wherein the fire retardant component is an organophosphate;
- (d) an organoclay component in an amount effective to enhance the flame-retardant characteristics of the composition; and
- (e) a mineral component, wherein the mineral component is mica.

In yet another aspect of the present invention, there is provided a method for preparation of a glass-reinforced PPE composition. In accordance with this method, the composition is prepared by compounding a mixture of

- (a) a polymer component comprising at least 50% of a polyphenylene ether;
- (b) glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the polyphenylene ether matrix;
- (c) a fire retardant component, wherein the fire retardant component

comprises an organophosphate fire retardant;

(d) an organoclay component in an amount effective to enhance the flameretardant characteristics of the composition; and

(e) a mineral component, wherein the mineral component is mica, as well as optional other components at elevated temperature to provide a homogenous blend of the materials. This compounding is suitably carried out in a screw type extruder at a temperature of 520 to 620 °F, preferably from 540 to 560 °F.

DETAILED DESCRIPTION OF THE INVENTION

The PPE compositions of the present invention comprise a polymer component comprising at least 50% of a polyphenylene ether; glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the polyphenylene ether matrix; an organophosphate fire retardant component ; an organoclay component in an amount effective to enhance the flame-retardant characteristics of the composition; and a mineral component. These components actsynergistically to provide glass-fiber reinforced PPE with good fire and flame-retardant characteristics, which utilize lower levels of organophosphate fire-retardant and which therefore do not suffer from the drawbacks of previously known fire-and flame-retardant PPE compositions.

This synergism is demonstrated in the results of the tests described below in the Examples which are summarized in Tables 1, 3 and 4. In these tests, samples of glassfiber reinforced PPE without organoclay and with various loadings of organoclay were prepared by compounding in a twin screw extruder. Some of the compositions were prepared with a mineral component (mica) and others without a mineral component. The samples were then injection molded and tested for flame-out time in accordance with the UL protocol for VO rating.

The experiments indicated that addition of small amounts of organoclay along with a mineral component to fire-retardant glass-fiber reinforced PPE allowed


WO 01/36527

PCT/US00/27143

achievement of enhanced fire-retardant performance and compliance with the UL94 V0 standard. Addition of larger amounts of organoclay, or the addition of small amounts of organoclay in the absence of the mineral component resulted in a deterioration of the fire-retardant performance. Thus, it is clear that there is a critical
 5 and synergistic combination of ingredients which leads to the improved characteristics of the compositions of the present invention.

The composition of the invention is made from a polymer component in which various fillers and additives are incorporated. As used herein, the term "polymer component" refers to the combined mass of all organic polymers present in the
 10 composition. While the polymer component may be 100% of a polyphenylene ether, it may also include other polymers selected to achieve desired properties in the final composition. Thus, the polymer component of the composition comprises at least 50% and preferably at least of one or more species of polyphenylene ether. As used herein, the term "polyphenylene ether" refers to individual polymeric PPE species or to
 15 mixtures of polymeric PPE species unless the context indicates otherwise.

PPE useful in the present invention is a polymer having repeat units of the general formula



wherein in the formula, R₁, R₂, R₃, and R₄ which may be the same or different each represent a member selected from the group consisting of hydrogen atoms, halogen
 20 atoms, substituted and unsubstituted alkyl groups and substituted and unsubstituted alkoxy groups. The PPE may be a homopolymer, i.e. the repeat units have the same structural formula, or a copolymer consisting of a combination of two or more types of

WO 01/36527

PCT/US00/27143

repeat units where at least one of the R_1 , R_2 , R_3 , and R_4 are different for each different repeat unit comprising the copolymer. The polymer is terminated at each end by a monovalent chemical group or atom such as hydrogen, a halogen, a monovalent hydrocarbon radical (saturated, unsaturated or aromatic) or the like. There are no particular restrictions on the method of manufacturing PPE. For example, this may be produced by reacting phenols according to the procedures presented in the specifications of U.S. Pat. Nos. 3,306,874, 3,257,357, or 3,257,358. Examples of these phenols include 2,6-dimethylphenol, 2,6-diethylphenol, 2,6-dibutylphenol, 2,6-dilaurylphenol, 2,6-dipropylphenol, 2,6-diphenylphenol, 2-methyl-6-ethylphenol, 2-methyl-6-cyclohexylphenol, 2-methyl-6-tolylphenol, 2-methyl-6-methoxyphenol, 2-methyl-6-butylphenol, 2,6-dimethoxyphenol, 2,3,6-trimethylphenol, 2,3,5,6-tetramethylphenol, 2,6-diethoxyphenol, etc., but the invention is not limited to these. One may either use a corresponding homopolymer obtained by reacting one of the above substances or a corresponding copolymer obtained by reacting two or more of the above substances and having the different units contained in the above formula. Specific examples of PPE polymers useful in the invention include but are not limited to poly(2,6-dimethyl-1,4-phenylene) ether, poly(2,6-diethyl-1,4-phenylene) ether, poly(2-methyl-6-ethyl-1,4-phenylene) ether, poly(2-methyl-6-propyl-1,4-phenylene) ether, poly(2,6-dipropyl-1,4-phenylene) ether, and poly(2-ethyl-6-propyl-1,4-phenylene) ether. Moreover, an example of the PPE copolymer is a copolymer partially containing an alkyl trisubstituted phenol such as 2,3,6-trimethylphenol in the aforementioned polyphenylene ether repeated unit. The PPE resins may also be copolymers having a styrene compound grafted on. An example of such a styrene-compound-grafted polyphenylene ether is a copolymer obtained by graft polymerization of a styrene compound such as styrene, .alpha.-methylstyrene, vinylstyrene, or chlorostyrene onto the aforementioned PPE.

Additional polymeric materials which may be included, individually or in combination, in the polymer component of the invention include crystalline polystyrene which can be added in amounts of 0 to 50 % by weight of the polymer component to improve processability, high impact polystyrene (HIPS), which can be

WO 01/36527

PCT/US00/27143

added in amounts of 0 to 50 % by weight of the polymer component to improve processability and increase impact strength; EPDM and styrene-butadiene block copolymers which can be added in amounts of 0 to 20 % by weight of the polymer component to improve the impact properties of the polymer component; and
5 polyamides such as nylon-6,6 and nylon-6 which can be added in amounts of 0 to 50% by weight of the polymer component to improve melt flow and impart increased resistance to organic solvents. The polymeric component may also include a terpene phenol resin (i.e, a copolymer of monoterpenes and phenol such as NIREZ 2150/7042™) in amounts of 0 to 25 % by weight of the polymeric component to
10 provide better flow to the composition. Other polymers that can be blended in the compositions of the invention include polyphenylene sulfides in amounts from 0 to 50 % by weight to improve heat deflection temperature and the flow.

Glass fibers suitable for use in the compositions of the invention may be of various lengths appropriate and thicknesses appropriate to the application. Coatings of
15 coupling agents, such as aminosilanes may be employed if desired. The glass fibers are added in an amount sufficient to increase the modulus and the strength of the product by a desired amount, and persons skilled in the art will be able to judge the appropriate levels and type of glass fiber needed to achieve a given result. In general, glass fibers are added in amounts of 5 to 50% by weight.

20 The fire retardant component of the compositions may be a halogenated fire retardant such as brominated polystyrene. Ecologically-preferred compositions, however, are halogen-free and utilize an organophosphate fire retardant. The organophosphate fire retardant component of the compositions may be any of numerous organophosphorus fire retardants which are known in the art. Specific
25 examples include resorcinol diphosphate, bisphenol A diphosphate, tetraaryl piperazine diphosphamide and the like, e.g. such as disclosed in US patents 4,933,386; 4,343,732; 5,455,292 and RE 36,188 herein and herewith specifically incorporated by reference. The amount of organophosphate fire retardant is selected to achieve the desired final level of fire-retardance. Because of the synergistic effects of utilizing the
30 organoclay additives in the compositions of the invention, the amount of

WO 01/36527

PCT/US00/27143

organophosphate fire-retardant can be reduced, and will generally be in the range of 5 to 30% by weight.

The organoclay component comprises one or more organoclay materials. As used herein, organoclay is a layered silicate clay, derived from layered minerals, in which organic structures have been chemically incorporated. Illustrative examples of organic structures are trimethyldodecylammonium ion and N,N'-didodecylimidazolium ion. Since the surfaces of clay layers, which have a lattice-like arrangement, are electrically charged, they are capable of binding organic ions. There is no limitation with respect to the layered minerals employed in this invention other than that they are capable of undergoing an ion exchange with the organic ions. The preferred organoclays are layered minerals that have undergone cation exchange with organocations and/or onium compounds. Illustrative of such layered minerals are the kaolinite group and the montmorillonite group. It is also within the scope of this invention to employ minerals of the illite group which can include hydromicas, phengite, brammallite, glaucomite, celadonite and the like. Often, however, the preferred layered minerals include those often referred to as 2:1 layered silicate minerals like muscovite, vermiculite, saponite, hectorite and montmorillonite, wherein montmorillonite is often preferred. The layered minerals described above may be synthetically produced. However, most often they are naturally occurring and commercially available.

Organoclays of the type suitable for use in this invention are described in US Patents Nos. 5,773,502 and 5,530,052 which are incorporated herein by reference.

The mineral component may be a silicate, such as mica, or regular clay or talc.

Other additives can be included in the compositions of the invention in accordance with conventional practice in the art. For example, stabilizers such as sterically hindered phenols, organic phosphites, diazide oxalates, sterically hindered amines or amine N-oxides may be incorporated. Other exemplary additives include ZnS which functions to deactivate residual copper-based catalyst present in PPE, MgO or ZnO which function as an acid quencher to quench acid generated by the

WO 01/36527

PCT/US00/27143

deactivation of residual catalyst, and carbon black or other colorant which functions as a pigment to color the composition.

The invention will now be further described with reference to the following, non-limiting examples.

5 Example 1

Samples of glass fiber-reinforced PPE were prepared without organoclay and with various loadings of organoclay. The materials used in each sample are summarized in Table 1, where 0.33 IV PPE refers to a PPE homopolymer prepared by an oxidative coupling process and having an intrinsic viscosity of 0.33; Nirez
10 2150/7240 is a terpene phenol resin available from Arizona Chemical Co.; OCF R22Y K-filament glass fibers are 4 mm long, 14 micron diameter glass fibers sized with an amino silane coupling agent and a urethane film former obtained from Owens-Corning Fiberglas; Mica Suzorite 200HK is a preparation of special delaminated pure phlogopite mica having a median particle size of 45 microns obtained from Zemex
15 Industrial Minerals, Inc.; organoclay CLOISITE 15A is a sodium montmorillonite that has been exchanged with dimethyl hydrogenated ditallow ammonium chloride obtained from Southern Clay Products, Gonzalez, TX; and phosphite 168 stabilizer is tris-(2,4-di-*t*-butylphenyl) phosphite which acts as a thermal stabilizer and antioxidant and which is available from various sources including Argus Chemical, Witco, Great Lakes
20 Chemical and Ciba Geigy Corp. All amounts in the Table are set forth in units of weight.

The samples were compounded in a Werner & Pfleiderer co-rotating intermeshing twin-screw extruder. The extruder has a primary (upstream) melting and mixing section for melting resins and mixing with each other, and mixing mica with the
25 polymer melt, and a secondary (downstream) mixing section for distributive mixing of glass fibers. Thus, glass fibers are added downstream. For the experiments described in this example, the extruder was operated at a temperature of 550 °F, and a speed of 350 rpm, to result in polymer production at a rate of 40 lb/hr. After compounding the

WO 01/36527

PCT/US00/27143

samples were injection molded using a Van Dorn Demag 120 ton injection molding machine (melt temperature: 560 °F, mold temperature: 190 °F) to produce specimens for testing.

Table 1

Raw Material	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5
0.33 IV PPE	53.25	53.25	53.25	53.25	53.25
Nirez 2150/7042	9	9	9	9	9
RDP FR	12	12	12	12	12
OCF R22 K-filament glass fibers	20	19.75	19.5	19.25	15
Mica Suzorite 200 HK	5	5	5	5	5
Organoclay Cloistite™ 15A	-	0.25	.5	.75	5
Phosphite 168 Stabilizer	0.3	0.3	0.3	0.3	0.3
MgO	0.3	0.3	0.3	0.3	0.3
ZnS	0.15	0.15	0.15	0.15	0.15
C Black	0.5	0.5	0.5	0.5	0.5
Total	100.5	100.5	100.5	100.5	100.5

- 5 The compositions made in Example 1 were tested for flammability using a flame retardance testing tool which provides a prediction of the likelihood that a particular UL standard, such as UL-94 will be passed. The UL-94 protocol calls for bar-shaped specimens of dimensions 5" (12.7 cm) x ½" (1.3 cm) width x the desired normal thickness, UL-94 ratings being specified for a particular thickness. A flame

WO 01/36527

PCT/US00/27143

- having an inner cone of height $\frac{3}{4}$ " (1.9 cm) is applied to each specimen so that a distance of $\frac{3}{8}$ " (1.0 cm) separates the lower end of the specimen from base of the flame. The flame is held in that position for 10 seconds and then removed. A burn time is defined as the time required for the flame issuing from the specimen to
- 5 disappear. If burning of the specimen ceases within 30 seconds, the flame is reapplied for an additional 10 seconds. The criteria for V-0, V-1, and V-2 ratings are listed in Table 2.

Table 2

Vertical Flame Class Requirements

	94V-0	94V-1	94V-2
Individual burn time, seconds	#10	#30	#30
Total burn time, seconds	#50	#250	#250
(5 specimens x 2) Glowing time, seconds	#30	#60	#60
(Individual specimen) Drip particles that ignite cotton	NO	NO	YES

- For a V-0 rating, no individual burn times, from the first or second application may exceed 10 seconds. The total of the burn times for any five specimens may not
- 10 exceed 50 seconds. Drip particles that ignite a piece of cotton gauze situated below the specimen are not allowed.

For a V-1 rating, no individual burn times, from the first or second application may exceed 30 seconds. The total of the burn times for any five specimens may not

WO 01/36527

PCT/US00/27143

exceed 250 seconds. Drip particles that ignite a piece of cotton gauze situated below the specimen are not allowed.

For a V-2 rating, no individual burn times, from the first or second application may exceed 30 seconds. The total of the burn times for any five specimens may not
5 exceed 250 seconds. Drip particles that ignite a piece of cotton gauze situated below the specimen are allowed.

A statistical analysis of the data obtained from a flame test can be applied to determine the probability of at least one possible outcome of the test. Possible outcomes include a first submittal pass, including first time pass and retest, and a
10 second submittal pass, including first time pass and retest, and failure. The probability of at least one outcome, preferably a first time pass on a first submission, provides a measure of the flame retardance of the polymer composition, while minimizing the variability inherent in flame testing, particularly the UL-94 test.

The raw data may be transformed prior to use in the statistical calculations by
15 conversion to equivalent logarithmic values. ("Logarithm" and "logarithmic" refer to base 10 logarithms.) Times less than one second may be rounded up to one second in order to avoid negative logarithmic values. The logarithm of the burn time may then be calculated and used in subsequent steps. Use of transformed data is preferred as a more normal distribution of values associated with burn time is thereby provided. Raw
20 data do not show a normal (bell-shaped) distribution curve because there can be no values less than zero, and data points are typically clustered in the space below the maximum individual burn time. The transformed data, however, more closely fit a normal distribution curve.

The probability of a first time pass may be determined according to the
25 formula:

$$P_{\text{first time pass}} = (P_{t1 > \text{mbt}, n=0} \times P_{t2 > \text{mbt}, n=0} \times P_{\text{total} > \text{mbt}} \times P_{\text{drip}, n=0})$$

WO 01/36527

PCT/US00/27143

where $P_{t1>mbt, n=0}$ is the probability that no first burn time exceeds a maximum burn time value, $P_{t2>mbt, n=0}$ is the probability that no second burn time exceeds a maximum burn time value, $P_{total \leq mibt}$ is the probability that the sum of the burn times is less than or equal to a maximum total burn time value, and $P_{drip, n=0}$ is the probability that no specimen exhibits dripping during the flame test. First and second burn time refer to burn times after a first and second application of the flame, respectively.

The probability that no first burn time exceeds a maximum burn time value, $P_{t1>mbt, n=0}$, may be determined from the formula:

$$P_{t1>mbt, n=0} = (1 - P_{t1>mbt})^5$$

where $P_{t1>mbt}$ is the area under the log normal distribution curve for $t1>mbt$.

and where the exponent "5" relates to the number of bars tested.

The probability that a single second burn time exceeds a maximum burn time value may be determined from the formula:

$$P_{t2>mbt, n=0} = (1 - P_{t2>mbt})^5$$

where $P_{t2>mbt}$ is the area under the normal distribution curve for $t2>mbt$. As above, the mean and standard deviation of the burn time data set are used to calculate the normal distribution curve. For the UL-94 V-0 rating, the maximum burn time is 10 seconds. For a V-1 or V-2 rating, the maximum burn time is 30 seconds.

The probability $P_{drip, n=0}$ that no specimen exhibits dripping during the flame test is an attribute function, estimated by:

$$(1 - P_{drip})^5$$

where P_{drip} = the number of bars that drip / the number of bars tested.

The probability $P_{total \leq mibt}$ that the sum of the burn times is less than or equal to a maximum total burn time value may be determined from a normal distribution curve

WO 01/36527

PCT/US00/27143

of simulated 5-bar total burn times. The distribution may be generated from a Monte Carlo simulation of 1000 sets of five bars using the distribution for the burn time data determined above. Techniques for Monte Carlo simulation are well known in the art. A normal distribution curve for 5-bar total burn times may be generated using the mean and standard deviation of the simulated 1000 sets. Therefore, $P_{total \leq mibt}$ may be determined from the area under a log normal distribution curve of a set of 1000 Monte Carlo simulated 5-bar total burn time for total $\leq$ maximum total burn time. For the UL-94 V-0 rating, the maximum total burn time is 50 seconds. For a V-1 or V-2 rating, the maximum total burn time is 250 seconds.

10 The probability of a retest is determined according to the following formula:

$$\begin{aligned}
 P_{retest} = & (P_{t1 > mibt, n=1} \times P_{t2 > mibt, n=0} \times P_{total = mibt} \times P_{drip, n=0}) + \\
 & (P_{t1 > mibt, n=0} \times P_{t2 > mibt, n=1} \times P_{total \leq mibt} \times P_{drip, n=0}) + \\
 & (P_{t1 > mibt, n=0} \times P_{t2 > mibt, n=0} \times P_{mibt < total \leq mrtbt} \times P_{drip, n=0}) + \\
 & (P_{t1 > mibt, n=0} \times P_{t2 > mibt, n=0} \times P_{total \leq mibt} \times P_{drip, n=1})
 \end{aligned}$$

15 where $P_{t1 > mibt, n=1}$ is the probability that a single first burn time exceeds a maximum burn time value, $P_{t2 > mibt, n=1}$ is the probability that a single second burn time exceeds a maximum burn time value, $P_{mibt < total \leq mrtbt}$ is the probability that the sum of individual burn times is greater than the maximum total burn time value and is less than or equal to the maximum retest total burn time value, $P_{drip, n=1}$ is the probability that a single specimen exhibits dripping during the flame test and $P_{t1 > mibt, n=0}$, $P_{t2 > mibt, n=0}$, $P_{total \leq mibt}$, and $P_{drip, n=0}$, are as defined above.

The probability that a single first burn time exceeds a maximum burn time value may be determined from the formula:

$$P_{t1 > mibt, n=1} = 5 \times P_{t1 > mibt} \times (1 - P_{t1 > mibt})^4$$

25 where $P_{t1 > mibt}$ is defined as above.

WO 01/36527

PCT/US00/27143

The probability that a single second burn time exceeds a maximum burn time value may be determined from the formula:

$$P_{t2>mbt, n=1} = 5 \times P_{t2>mbt} \times (1 - P_{t2>mbt})^4$$

where $P_{t2>mbt}$ is defined above.

- 5 The probability that the sum of individual burn times is greater than the maximum total burn time value and is less than or equal to the maximum retest total burn time value may be determined from the normal distribution curve of simulated 5-bar total times, as described above for $P_{total \leq mltbt}$. $P_{mltbt \cdot total \leq mltbt}$ is equal to the area under a log normal distribution curve of a set of 1000 Monte Carlo simulated 5-bar
- 10 total burn time for maximum total burn time $\leq$ total $\leq$ the maximum retest total burn time value. For the UL-94 V-0 rating, the maximum total burn time is 50 seconds, and the maximum retest total burn time value is 55 seconds. For a V-1 or V-2 rating, the maximum total burn time is 250 seconds, and the maximum retest total burn time value is 255.

- 15 The probability that a single specimen exhibits dripping during the flame test may be estimated from the following attribute function:

$$P_{drip, n=1} = 5 \times P_{drip} \times (1 - P_{drip})^4$$

where P_{drip} is defined as for a first time pass, above.

- 20 By definition, the sum of the probabilities of possible outcomes of a first submittal is one:

$$\Sigma(\text{Probabilities}) = P_{\text{first time pass}} + P_{\text{retest}} + P_{\text{failure, no retest}} = 1.$$

Therefore, the probability of a failure is given by:

$$P_{\text{failure, no retest}} = 1 - P_{\text{first time pass}} - P_{\text{retest}}$$

The probability of a first submittal pass is given by:

WO 01/36527

PCT/US00/27143

$$P_{1st\ submittal\ pass} = P_{first\ time\ pass} + P_{retest} \times P_{first\ time\ pass}$$

where $P_{first\ time\ pass}$ and P_{retest} are as defined above.

The probability of a second submittal pass is determined according to:

$$P_{2nd\ submittal\ pass} = P_{failure,\ no\ retest} \times (P_{first\ time\ pass} + P_{retest} \times P_{first\ time\ pass})$$

5 where $P_{first\ time\ pass}$, P_{retest} and $P_{failure,\ no\ retest}$ as defined above.

Finally, the probability of a pass after a first and second submittal, or the overall probability of a pass is:

$$P_{overall\ pass} = P_{1st\ submittal\ pass} + P_{2nd\ submittal\ pass}$$

Using this procedure, each of the compositions of Table 1 were evaluated, and
 10 the results are summarized in Table 3. As shown, compositions containing mineral
 filler and organoclay in an amount of from 0.5 to 0.75 % by weight had very good
 flame retardance properties and high likelihood of passing the UL-94 tests.
 Compositions with lower levels of organoclay worked less well, while compositions
 with 5 % by weight exhibited a deterioration in performance.

15 Example 2

The experiments of Examples 1 were repeated using samples with and without
 mineral filler in accordance with the compositions set forth in Table 4 and tested for
 flame retardance characteristics. In these compositions, the importance of mineral
 filler with various levels of the organoclay component was tested. As shown, the
 20 presence of both the organoclay and the mineral filler result in the best flame-
 retardance properties.

WO 01/36527

PCT/US00/27143

Table 3

Test	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5 ¹
t1 – Total Flame-Out Time, 1 st Flame Application (sec)	34	36	28	36	880
t2 – Total Flame-Out Time, 2 nd Flame Application (sec)	84	81	51	59	---
t1 + t2 (sec)	118	117	79	95	---
Average Flame-Out time (sec)	3	2.9	2	2.4	---
Standard Deviation (Flame-Out time, sec)	3	2.2	1.4	1.5	---
Probability of Passing UL94 V0 rating on 1 st submittal of 5 flame bars	0.80	0.85	0.98	0.93	0

Notes:

1. Sample 5 burned completely when the flame was applied the first time. Thus a second flame application was not possible. A consequence of this was that t1-total flame out time, first application (sec.) was 880 second, and t2 could not be calculated.

WO 01/36527

PCT/US00/27143

Table 4

Raw Material	Samp. 6	Samp. 7	Samp. 8	Samp. 9	Samp. 10	Samp. 11	Samp. 12	Samp. 13
0.33 IV PPE	60.25	60	59.75	59.5	60.25	60	59.75	59.5
Nirez 2150/7042	9	9	9	9	9	9	9	9
RDP FR	10	10	10	10	10	10	10	10
OCP R22 K-filament glass fibers	15	15	15	15	20	20	20	20
Mica Suzorite 200 HK	5	5	5	5				
Organoclay Cloisite™ 15A	-	0.25	.5	.75	-	0.25	.5	.75
Phosphite 168 Stabilizer	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
MgO	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
ZnS	0.15	0.15	0.15	0.15	0.15	0.15	0.15	0.15
C Black	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
Total	100.5	100.5	100.5	100.5	100.5	100.5	100.5	100.5
Test								
11 - Total Flame-Out Time, 1 st Flame Application (sec)	43	36	35	52	96	64	63	84
12 - Total Flame-out Time, 2 nd Flame Application (sec)	76	43	48	82	72	102	122	173
11 + 12 (sec)	119	79	83	134	168	166	185	257
Average Flame-out Time (sec)	3	2	2.1	3.4	4.2	4.2	4.6	6.4
Standard Deviation (Flame-Out Time, sec)	1.9	1.2	1.1	3	3.9	4.3	3.5	7.4
Probability of Passing UL94 VO rating on 1 st submittal of 5 flame tests	0.90	0.99	0.98	0.75	0.58	0.40	0.27	0.04

WO 01/36527

PCT/US00/27143

Note to Table 4: The total loading of glass fiber and mica was kept constant at 20 weight percent which enabled studying the effect of replacing glass fibers by mica.

CLAIMS

1. A composition comprising :
 - (a) a polymer component comprising at least 50% of polyphenylene ether;
 - (b) glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the composition;
 - (c) a fire retardant component, wherein the fire retardant component is an organophosphate;
 - (d) an organoclay component in an amount effective to enhance the flame-retardant characteristics of the composition; and
 - (e) a mineral component, wherein the mineral component is mica.
2. The composition of claim 1, wherein the organoclay component is a silicate.
3. The composition according to claim 2, wherein the organoclay component is present in an amount from 0.25 to 0.75 % by weight of the composition.
4. The composition according to claim 1, wherein the organoclay component is present in an amount from 0.25 to 0.75 % by weight of the composition.
5. The composition of claim 1, wherein the composition comprises 5 to 50% by weight of glass fibers and 5 to 30% by weight of the organophosphorus fire retardant.
6. The composition of claim 1, wherein the organophosphorus fire retardant is resorcinol diphosphate.
7. An injection-molded article formed from a glass fiber-reinforced polyphenylene ether composition, wherein the glass fiber-reinforced polyphenylene ether composition comprises:
 - (a) a polymer component comprising at least 50% of a polyphenylene ether;

(b) glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the polyphenylene ether composition;

(c) a fire retardant component, wherein the fire retardant component is an organophosphate;

(d) an organoclay component in an amount effective to enhance the flame-retardant characteristics of the composition; and

(e) a mineral component, wherein the mineral component is mica.

8. The article of claim 7, wherein the organoclay component is a silicate.

9. The article of claim 7, wherein the organoclay component is present in an amount from 0.25 to 0.75 % by weight of the composition.

10. The article of claim 7, wherein the organoclay component is present in an amount from 0.25 to 0.75 % by weight of the composition.

11. The article of claim 7, wherein the composition comprises 5 to 50% by weight of glass fibers and 5 to 30% by weight of the organophosphorus fire retardant.

12. A method for making a glass fiber-reinforced polyphenylene ether composition, comprising the steps of:

preparing a mixture by combining the following ingredients:

(a) a polymer component comprising at least 50% of a polyphenylene ether;

(b) glass reinforcing fibers in an amount sufficient to increase the modulus and strength of the polyphenylene ether composition;

(c) a fire retardant component, wherein the fire retardant component comprises an organophosphate fire retardant;

(d) an organoclay component in an amount effective to enhance the flame-retardant characteristics of the composition; and

(e) a mineral component, wherein the mineral component is mica; and

compounding the mixture to blend the ingredients into a uniform composition.

13. The method of claim 12, wherein the organoclay component is present in an amount from 0.25 to 0.75 % by weight of the composition.

14. The composition of claim 1, wherein the polymer component further comprises a terpene phenol resin.

15. The composition of claim 5, wherein the organoclay component is present in an amount from 0.25 to 0.75% by weight of the composition, mica is present in an amount 5% by weight of the composition and the polymer component further comprises a terpene phenol resin.

16. The article of claim 7, wherein the polymer component further comprises a terpene phenol resin.

17. The article of claim 11, wherein the organoclay component is present in an amount from 0.25 to 0.75% by weight of the composition, mica is present in an amount of 5% by weight of the composition and the polymer component further comprises a terpene phenol resin.

18. The method of claim 12, wherein the polymer component further comprises a terpene phenol resin.

19. The method of claim 13, wherein the composition comprises 5 to 50% by weight of the composition of glass fibers, 5 to 30% by weight of the composition of the organophosphorous fire retardant, 5% by weight of the composition of mica and the polymer component further comprises a terpene phenol resin.